# Interplay between 3d and 4f m agnetism in C eC oP O

C.K rellner<sup>a;</sup>, U.Burkhardt<sup>a</sup>, and C.Geibel<sup>a</sup>

<sup>a</sup>M ax P lanck Institute for C hem ical P hysics of Solids, D -01187 D resden, G erm any

#### A bstract

The ground state properties of C eC oPO, a hom obgue of the new high tem perature superconductors LnFeP nO<sub>1 x</sub> F<sub>x</sub>, were studied by m eans of susceptibility, speci c heat, and resistivity m easurem ents on polycrystals. The observation of a wellde ned C urie-W eiss behavior above 230 K with  $_{e} = 2.9 _{B}$  and a ferror agnetic ordering below T<sub>C</sub> = 75K is sim ilar to what was observed in LaC oPO and points to m agnetism of the C o-3d electrons. However, the C e-ions are on the border to m agnetism with a K ondo scale of T<sub>K</sub> 40 K and show an enhanced Som m erfeld-coe cient of 200 m J/m olK<sup>2</sup>.

Key words: Ferrom agnetic system, ZrCuSiA s-type structure, Kondo lattice system, Heavy-Ferm ion PACS: 7520Hr, 7120Eh, 7550Cc

#### 1 Introduction

The compound series LnTPnO (Ln: lanthanides, T: transition m etal, Pn: P or As) have started to attract considerable attention because of the recent discovery of superconductivity with a transition temperature  $T_c$  exceeding 50K in the LnFeA sO<sub>1 x</sub>  $F_x$  series of compounds [1],[2],[3], being the highest  $T_c$  except for cuprate system s. W hile the recent reports focus on the importance of electronic correlation e ects due to 3d-electrons close to a magnetic state, the hom ologous compounds with Ln = Ce are attractive candidates for strong correlation e ects induced by the 4f-electrons. Thus, last year we presented a detailed study of the properties of CeRuPO and CeO sPO [4], [5], [6] and demonstrated that the form er one is a rare example for a ferrom agnetic (FM)

Corresponding author. Tel/Fax: + 49 351 46462249

Em ailaddress: krellner@cpfs.mpg.de (C.Krellner).

K ondo lattice system with a FM ordering tem perature  $T_c = 15$  K and a K ondo tem perature  $T_K = 10$  K, while the latter one shows antiferrom agnetic order of stable trivalent C e-ions below  $T_N = 4.5$  K. M ore recently, we have show n that C eFePO is a heavy Ferm ion m etal close to a FM instability, dom inated by the m agnetism of the 4f-electrons [7]. Therefore, it was natural to look also for the physical properties of the related com pound with T = C o.

In this report, we present a rst study of the basic physical properties of CeCoPO using susceptibility (T), speci c heat C(T), and resistivity (T) m easurements as well as x-ray absorption near-edge spectroscopy structure (XANES) at the CeL<sub>III</sub> edge. The results reveal a FM ordering of the Co-ions at  $T_c = 75$ K in analogy to the FM order at 43K in LaCoPO [8]. An enhanced Sommerfeld-coe cient of 200 mJ/m olK<sup>2</sup> and the temperature dependence of the resistivity reveal a nite K ondo scale of the 4f-m om ents of order  $T_K$  40 K. In addition, we con in the reported data of the magnetic properties of polycrystalline LaCoPO.

# 2 Experiment

Polycrystalline samples of CeCoPO and LaCoPO were synthesized using a Snux m ethod in evacuated quartz tubes as described elsewhere [4], [9]. Several powder x-ray di raction patterns recorded on a Stoe di ractom eter in transm ission mode using monochromated  $Cu-K_1$  radiation ( = 1:5406A) conm ed the form ation of LnCoPO with ZrCuSiAs structure type (space group: P = 4 = nmm; Z = 2). The lattice parameters rended by simple least square tting for C eC oPO a = 3:924 (3) A, c = 8:223 (5) A and LaC oPO a = 3:968 (3) A, c = 8:379(5) A were found to be in good agreement with the reported structure data [8], [10]. In addition, energy dispersive x-ray spectra of CeC oPO and LaCoPO performed on a scanning electron microscope (Philips XL30) with Si(Li)-x-ray detector show similar strong intensities of the oxygen line which con m a substantial oxygen content of both phases. How ever, they revealed diam agnetic  $CoP_2$  [11] as in purity phase and some oxide phases which are present only with small concentration, so that they could not be observed in the x-ray di raction patterns. (I) measurements were performed in the tem perature range 2 350K in a commercial Quantum Design (QD) magnetic property m easurem ent system (MPMS), the T-dependent m easurem ents were performed after zero-eld cooling the sample. The resistivity was determined down to 0.4K using a standard AC four-probe geometry in a QD physical property measurement system (PPM S). The PPM S was also used to measure C (I) with a standard heat-pulse relaxation technique. XANES-spectra near the C e  $L_{TTT}$  edge were taken at 300 K in transm ission geom etry at the EXAFS beam line A 1 of HASYLAB at DESY, Germ any. The wavelength selection was realized by means of Si(111) double crystal monochromator, which allowed



Fig.1. Inverse susceptibility as function of temperature for CeCoPO (squares) and LaCoPO (circles) measured in a magnetic eld of  $_0H = 5T$ . Both compounds show similar Curie-W elss behavior above 230 K with  $_e = 2.9 _B$  and  $_W = 3K$  (straight line). Inset: The magnetization of CeCoPO presents a small hysteresis at small magnetic elds and a nearly saturated moment at higher elds.

an experimental resolution of approximately 2 eV (FW HM) at the Ce  $\rm L_{III}$  threshold of 5723 eV .

In Fig. 1 the inverse susceptibility is shown for both CeCoPO and LaCoPO. Above 230K both curves present sim ilar Curie-W eiss behavior with an e ective moment of  $_{\rm e}$  = 2:9  $_{\rm B}$  and a W eiss temperature of  $_{\rm W}$  = 3K.Our results for LaCoPO are very similar to those of Ref. [8] but important to analyze the magnetism in CeCoPO. The identical behavior of CeCoPO and LaCoPO in <sup>1</sup> (T) evidences that in both compounds the main contribution to the magnetism results from the 3d-electrons of Co. However, in CeCoPO the Ce-ions are not completely unm agnetic as will be discussed later. In the inset of Fig. 1, the magnetization M (H) of CeCoPO is shown. M (H) presents a small hysteresis at low eld and a saturated moment of sat  $0:4_{\rm B}$  at 3T, similar to what was observed in LaCoPO [8]. At higher elds,  $H_0$ M (H) increases further slightly which m ight be due to the param agnetism of the Ce-ions.

In Fig. 2, we present (T) of CeC oPO as a function of temperature at three di erent magnetic elds. The transition into a FM ordered state is visible by a sharp increase at  $T_c = 75$ K and a strong eld dependence of at low T. However, the peak at  $T_c$  observed in low elds ( $_0$ H 0.1T) does not correspond to the expectation for a simple ferrom agnet. Presently, it is not settled whether this is the result of measuring powder samples of a system with a complex anisotropic behavior or if it points to a more intricate magnetic structure with polarization e ects on the Ce-ions by the internal magnetic



Fig. 2. (T) of C eC oPO at various magnetic elds. The magnetic transition into a FM ordered state is visible at  $T_C = 75 K$ . For comparison, (T) for LaC oPO at  $_0H = 0:1 T$  is presented as well (straight line).

elds of the Co-magnetism. The later scenario is more likely, because the T-dependence of for LaCoPO (line in Fig. 2), where no 4f-electrons are present, behaves as expected for a simple ferrom agnet.

The tem perature dependence of the speci cheat of CeCoPO is shown in Fig. 3 without any subtraction of the phonons. Therefore, at high T, C (T) converges to the classical lim it of 4 3R 100 J/m olK . An anom aly is visible on top of the phonon excitations just below  $T_{\rm C}$ . This anom all is rather broad, possibly due to inhom ogeneities in our polycrystalline sam ple. In the inset of Fig. 3 we have plotted the specic heat as C = T on a logarithm ic tem perature scale. In this representation the peak due to the onset of FM order is more pronounced. Below T = 10K, C = T increases logarithm ically and tends to saturate below  $200 \text{ m J/m o } \mathbb{K}^2$ . This value is strongly enhanced compared T = 1K at to the expectation for a norm alFM Co-system . This enhancem ent can be attributed to 4f-correlation e ects resulting in the form ation of heavy Fermions. The entropy at low T was calculated by integrating C = T over temperature. The entropy gain at 10K corresponds to about 25% of R ln 2, giving a rough estimation of the K ondo energy scale of order  $T_{K}$ 40K.For the calculation, we have not subtracted any nonmagnetic contribution which for T < 10 K is negligible compared to the large value of C = T. As an example, the contribution of the nonmagnetic LaRuPO to the specic heat at T = 1K would only correspond to 2% of the here m easured speci c heat [4].

In Fig. 4 we present the resistivity data on a pressed powder-pellet of Ce-CoPO which was subsequently annealed for 150 hours at 700 C, in proving the conductivity of the sample by a factor of 20. How ever, the absolute value of  $_{300\,\text{K}} = 5\,\text{m}$  cm is still rather high; we believe that this is not intrinsic of



Fig.3. Tem perature dependence of the speci cheat of CeC oPO. The phonon contribution is not subtracted in this representation. A broad anomaly is visible below  $T_C$  due to the FM order of CeC oPO. The inset shows the speci cheat plotted as C=T on a logarithm ic tem perature scale. Below T = 10 K, C=T of CeC oPO increases logarithm ically down to lower T, presenting an enhanced 200 m J/m olK<sup>2</sup> at 0.35 K.

CeC oPO but due to the remaining granularity of the polycrystalline sample. To compare our results with (T) of LaC oPO from Yanagi et al., we have norm alized our data to  $_{300\,\text{K}}$ . From Fig. 4 it is obvious that (T) of CeC oPO di ers signi cantly from the data of LaC oPO which decreases linearly with temperature with a small change in slope at the FM ordering temperature. In contrast, CeC oPO shows linear m etallic behavior only above 100K, followed by a pronounced decrease which is a distinct feature of a K ondo lattice system. However, we can not exclude that this decrease is due to reduced spin-spin scattering because of the FM order at  $T_{\rm C}$ , as both energy scales ( $T_{\rm K}$  40K and  $T_{\rm C}$  = 75K) are comparable. Therm opower measurements on CeC oPO would be desirable to distinguish between both e ects.

We have perform ed XANES measurements at the  $Ce^{3^+}$  edge to determ ine the valency of the Ce-ions to gain a deeper insight of the relevance of cerium to the magnetic behavior in CeCoPO. In the inset of Fig. 5 we have plotted the evolution of the tetragonal unit cell volume V for the three LnTPO series (T = Co, Fe, Ru). The contraction of V is typical for the Ln series, and a sm ooth evolution is expected if Ce is in a trivalent state. Therefore, one would expect a stable, magnetic  $Ce^{3^+}$  in CeRuPO but a stronger tendency to intermediate-valent Ce-ions in CeFePO and CeCoPO [12]. This trend is conmediate of a constraint of the valency of Ce is not changing dram atically when going from Ru-to the Co-com pound. Above 5.73 keV, the Co-com pound show a slightly higher intensity com pared to CeRuPO, but far away from the



Fig. 4. Tem perature dependence of the resistivity of C eC oPO (squares) normalized to the room tem perature value  $_{300K} = 5 \text{ m}$  cm. For comparison, (T) of LaC oPO taken from Yanagi et al. [8] is shown (straight line).

double-peak behavior in the form al pure  $Ce^{4+}$ -system  $CeO_2$  [13]. From this we conclude a predom inantly  $Ce^{3+}$  for all three systems. Prelim inary x-ray magnetic circular dichroism (XMCD) measurements on CeCoPO con m this result showing that more than 90% of the Ce-ions are in the J = 5=2 con g-uration [14].

### 3 D iscussion

Our results on CeCoPO evidence three interesting features which shall now be discussed: The interplay of the 3d and 4f m agnetism, the comparison with the results obtained on CeRuPO and CeFePO, and the relation to the new high temperature superconductors  $LnFePnO_{1 \times}F_{\times}$ .

The presented results point to a FM ordering of the Co-ions in CeC oPO similar to the FM order in LaCoPO [8]; however, the unusual temperature dependence of (T) at  $T_c$  together with an increasing magnetization for elds B 3T are not expected for a simple FM and not observed in LaCoPO.On the other hand, the XANES spectra suggest the Ce-ions to be close to trivalent which is in agreement with the enhanced , and the temperature dependence of (T) which are typical for pronounced K ondo-interactions. Therefore, we suggest the following scenario for CeCoPO. The spins of the Co-ions (3d-electrons) order ferrom agnetically at  $T_c = 75$ K, the resulting internal elds partially polarize the Ce-ions (4f-electrons), which however remain also partially uctuating down to lowest measured temperatures. One could even in agine that a K ondo screening increasing with decreasing temperature lead to a decreas-



Fig. 5.XANES spectra at the Ce  $L_{III}$  edge of CeTPO (T = Co, Fe, Ru) taken on pow dered sam ples at T = 300 K. The data are norm alized to 1 at 5.755 keV. Inset: Cell volum es of the tetragonal phosphide oxides LnTPO [10], [12].

ing Ce-polarization with temperature. In order to get a deeper insight into the many-body phenom ena in this compound, a more microscopic local probe should be used to study the magnetism . We therefore, started an investigation of CeCoPO with XMCD [14] as well as  $^{31}$ P NMR and  $^{59}$ CoNMR [15] to distinguish between 3d and 4f magnetism .

The Doniach picture can be used to classify the CeTPO series with respect to the magnetism of the 4f-electrons [16]. From the inset of Fig. 5 it is evident that the volum e of the unit cell decreases from T = R u to Fe and further to Co. W ith decreasing V the magnetism of the Ce-ions becomes more and more screened by the conduction electrons because of an increasing K ondo energy scale. A coordingly, we observe stable ferror agnetism of the Ce-ions in CeRuPO [4] which has the largest  $V_{Ru} = 0.1339 \text{ nm}^3$ . CeFePO has a smaller  $V_{Fe} = 0.1279 \text{ nm}^3$  and is close but already on the nonmangetic side of a FM instability [7]. The volum e related suppression of the magnetic order can also be observed in pressure experiments on single crystals of CeRuPO [17]. Our conclusion of a larger screening of the 4f electrons as identieed by a higher K ondo temperature  $T_K = 40 \text{ K}$  in CeCoPO is in nice continuation of this system atic trend since this compound has a further reduced volume  $V_{Co} = 0.1266 \text{ nm}^3$  compared to CeFePO.

The superconductivity at  $T_c = 26$ K in F-doped LaFeA sO came as a big surprise [1] and subsequently research on these systems reveals systems with  $T_c$ 's exceeding 50 K in the elements with heavier Ln [2], [3]. The connection between a vanishing magnetic transition and the simultaneous formation of a superconducting state is reminiscent of the behavior in the cuprates and in the heavy Ferm ion systems, and therefore suggests the superconducting

state in these doped RFeAsO systems to be of unconventional nature, too. In CeCoPO, we could not observe superconductivity down to 350mK, which is not so much surprising taking into account the FM Co-state. The magnetism might be easy to suppress either by doping or pressure, because an ordering temperature of  $T_c = 75$ K is rather low for Co-ordering. Further research has to answer the question whether superconductivity appears in this compound after suppression of the FM order.

## 4 Conclusion

In summary, we have shown that CeCoPO presents ferrom agnetic order of the Co-ions at  $T_c = 75 \text{ K}$ . The 4f-electrons are screened due to pronounced K ondo-interactions with a K ondo energy scale of order  $T_K = 40 \text{ K}$  revealed by the temperature dependence of the resistivity and an enhanced Sommerfeld-coe cient  $200 \text{ m J/m olK}^2$ . In addition, we con rm the FM order in La-CoPO at  $T_c = 43 \text{ K}$ .

# A cknow ledgem ents

The authors thank P. Scheppan for energy dispersive x-ray analysis of the sam ples and N.Caroca-Canales and R.W eise for technical assistance in sam ple preparation.H.Rosner, E.M.Bruning, and M.Baenitz are acknow ledged for valuable discussions.

#### References

- Y.Kamihara, T.Watanabe, M.Hirano, H.Hosono, J.Am. Chem. Soc. 130 (11) (2008) 3296.
- G.F.Chen, Z.Li, D.Wu, G.Li, W.Z.Hu, J.Dong, P.Zheng, J.L.Luo, N.L.
  Wang, Phys. Rev. Lett. 100 (24) (2008) 247002.
- [3] X.H.Chen, T.Wu, G.Wu, R.H.Liu, H.Chen, D.F.Fang, Nature 453 (2008) 1224 { 1227.
- [4] C. Krellner, N. S. Kini, E. M. Bruning, K. Koch, H. Rosner, M. Nicklas, M. Baenitz, C. Geibel, Phys. Rev. B 76 (10) (2007) 104418.
- [5] C.Krellner, C.Geibel, J.Cryst.Growth 310 (7-9) (2007) 1875{1880.
- [6] C.Krellner, T.Forster, H.Jeevan, C.Geibel, J.Sichelschmidt, Phys. Rev. Lett. 100 (6) (2008) 117206.

- [7] E.M.Bruning, C.Krellner, M.Baenitz, A.Jesche, F.Steglich, C.Geibel, Phys. Rev.Lett. 101 (11) (2008) 066401.
- [8] H.Yanagi, R.Kawamura, T.Kamiya, Y.Kamihara, M.Hirano, T.Nakamura,
  H.Osawa, H.Hosono, Phys. Rev. B 77 (22) (2008) 224431.
- [9] M.G.Kanatzidis, R.Pottgen, W. Jeitschko, Angew. Chem ie 117 (43) (2005) 7156{7184.
- [10] B. Zimmer, W. Jeitschko, J. H. Albering, R. Glaum, M. Reehuis, Journal of Alloys and Compounds 229 (2) (1995) 238(242.
- [11] W . Jeitschko, U. Florke, U. Scholz, J. Solid State Chem 52 (1984) 320.
- [12] We have redrawn the volumes of the unit cell from Ref. [10]; however, the volume plot there is dierent as Z immer et al. have used wrong absolute values for CeCoPO.
- [13]G.Kaindl, G.Schmiester, E.V.Sam pathkum eran, P.W achter, Phys. Rev.B 38 (14) (1988) 10174 (10177.
- [14] E.Goering, Max-Planck-Institute for Metals research, private communication.
- [15] E.M. Bruning, Ph.D. thesis, TU Dresden (2008).
- [16] S.Doniach, Physica B & C 91 (Jul.) (1977) 231 { 234.
- [17] M. Macovei et al, this proceedings (2008).