

Long wavelength behavior of two dimensional photonic crystals

S. T. Chui¹ and Zhifang Lin²

¹Bartol Research Institute, University of Delaware, Newark, DE

19716, ²Physics Dept., Fudan University, Shanghai, China.

Abstract

We solve analytically the multiple scattering (KKR) equations for the two dimensional photonic crystals in the long wavelength limit. Different approximations of the electric and magnetic susceptibilities are presented from a unified pseudopotential point of view. The nature of the so called plasmon-polariton bands are clarified. Its frequency as a function of the wire radius is discussed.

There is much interest recently in two dimensional (2D) photonic crystals (PC) consisting of arrays of metallic or dielectric cylinders (wires) in an insulating matrix or arrays of insulating cylinders in a metallic matrix. These include recent interest in left-handed materials [1] and in plasmonics. [5] A key issue is the effective susceptibilities ϵ_{eff} and μ_{eff} of the system. To design systems at different frequencies such as in the infrared range it is useful to know their values for different system parameters. The photonic bands in an array of cylinders can be understood entirely in terms of the scattering phase shift of the cylinders. In the pseudopotential idea in electronic structure calculation a real potential is replaced by an effective one so that the same scattering of the electrons is produced. Similarly effective susceptibilities can be introduced so that the correct scattering effect for electromagnetic waves is produced. We examine this idea to derive effective susceptibilities for the cylinder. For example, from the scattering phase shift for a mode with the electric field along the cylinder axis, an effective dielectric constant for the cylinder is found to be

$$\epsilon_{eff}^0 = \frac{2J_0^0}{J_1^0} = \frac{(J_1^i R) [1 + 0.5(k_o R)^2 \ln(k_o R)]}{J_1^o R J_0^0 \ln(k_o R)} = \frac{J_1^i}{J_1^o}; \quad (1)$$

where $J_1^i = J_1(k_i R)$; $J_1^o = J_1(k_o R)$. The subscripts i, o refers to quantities inside and outside the cylinder, respectively. For metallic cylinders, when the skin depth is much less than the radius of the cylinder, the second term in the denominator is larger than the first term, we obtain an effective dielectric constant of a metallic form given by

$$\epsilon_{eff}^0 = 1 - \frac{\omega_p^0{}^2}{\omega^2}$$

where the effective "plasma frequency" is given by

$$\omega_p^0{}^2 = \frac{2c^2}{R^2} \ln(R/c); \quad (2)$$

R is the radius of the cylinder. While the original analysis [2] for the effective dielectric constant is carried out for a wire radius less than the skin depth, the experiments [3] for the left-handed materials are carried out for wires the width of which is larger than the skin depth. The above formula provides for an extension of the original analysis. There is a log correction term that has not been noticed before.

This clarifies the issue of damping. For frequencies from 1 to 10 GHz, the imaginary part of the dielectric constant of most metals is about a thousand times larger than the real part. When the skin depth is much less than the wire radius, the loss in the metal is only

restricted near the surfaces of the wires and the effective damping is reduced. Indeed, the above effective dielectric constant depends only on the wavelength and the wire radius, with no damping!

Eq (1) encompasses other recent results. For dielectric rods. If the second term of the denominator is smaller than the first term, we recover recent results by Wu et al. and Hu et al.[11, 12] that

$$\epsilon_{\text{eff}}^0 = 2J^0 = (J_k^0 R)$$

This pseudopotential idea is also implicit in recent results using cylinders with a high dielectric constant ferroelectric.[13] Eq. (1) extends these results to more general regions of the parameter space.

In this paper we further calculate the photonic band structure of an array of cylinders of radius R in the long wavelength limit when the separation between the wires a is less than the free space wavelength $\lambda = 2\pi/k_0$. We solve analytically the multiple scattering (KKR) equations in the long wavelength limit. We find that both the s and the p wave scattering phase shifts are of the same order of magnitude, $(k_0 R)^2$, and need to be considered. These produced two photonic branches, an "acoustic" mode with a frequency proportional to the wave vector with an effective dielectric constant $\epsilon_{\text{eff}} < \epsilon_0$ (eq. (1) and (8)) and a magnetic susceptibility $\chi_{\text{eff}} < \chi_0$ (eq. (5) and (8)) and an "optic" mode with a gap. For negative susceptibilities and narrow cylinders, the "optic" mode corresponds to a flat band at frequencies close to the surface plasmon resonances, as has been previously discovered numerically. For the acoustic mode, we found that ϵ_{eff} can be expressed as the arithmetic mean of that of the medium and an effective dielectric constant of the cylinder ϵ_c^0 . We now describe our result in detail.

Pseudopotential: We first describe our "pseudopotential" idea for the effective dielectric constant of the cylinder. As far as the EM field outside the cylinder is concerned, all that matters is the scattering phase shift for angular momentum component n given, for the E (TM) mode, by

$$\tan \delta_n^E = \frac{J_n^0(k_o R) k_i J_n(k_i R) - J_n^0(k_i R) J_n(k_o R) k_o}{k_i J_n(k_i R) N_n^0(k_o R) - k_o N_n(k_o R) J_n^0(k_i R)} \quad (3)$$

$k_j = k_0 (a_j/j)^{1/2}$ for $j = o, i$, $a_i = a_o$. Similarly, for the H (TE) mode $k_i = (a_i/a_o)^{1/2} k_o$.

$$\tan \delta_n^H = \frac{J_n^0(k_o R) k_o J_n(k_i R) - J_n^0(k_i R) J_n(k_o R) k_i}{k_o J_n(k_i R) N_n^0(k_o R) - k_i N_n(k_o R) J_n^0(k_i R)} \quad (4)$$

We first focus on the s wave with $n=0$. For $k_0R \ll 1$; $J_0 = 1$; $J_0^0 = k_0R=2$; $N_0 = 2 \ln(k_0R) = 0$; $N_0^0 = 2 = (k_0R)$:

$$\tan \delta_0^E = 0.25 (k_0R)^2 [1 + 2J_0^0 = (J_0^0 k_0R)] = [1 - k_0R J_0^0 \ln(k_0R) = (J_0^0)];$$

$$\tan \delta_0^H = 0.25 (k_0R)^2 [1 + 2J_0^0 k_0R = (J_0^0 k_0R^2)] = [1 - k_0R \ln(k_0R) J_0^0 = (J_0^0)]:$$

For k_0R also small

$$\tan \delta_0^E = (k_0R)^2 [1 - 4]; \tan \delta_0^H = (k_0R)^2 [1 - 4]$$

As is expected, when $k_0R = 1$; there is no scattering and $\tan \delta_0^E = 0$:

When k_0R is not small, one can define effective susceptibilities so that the same phase shift is produced:

$$\tan \delta_0^E = (k_0R)^2 [1 - \epsilon_0^0] = 4; \tan \delta_0^H = (k_0R)^2 [1 - \mu_0^0 = \epsilon_0^0] = 4 \quad (5)$$

This is the "pseudopotential" idea that we mentioned. From eq. (5) we obtain eq. (1) for the effective dielectric constant and also an effective magnetic susceptibility for the H mode:

$$\epsilon_0^0 = [k_0R \ln(k_0R) J_0^0 = (J_0^0) + 2J_0^0 k_0R = (J_0^0 k_0R^2)] = [1 - k_0R \ln(k_0R) J_0^0 = (J_0^0)]: \quad (6)$$

The second term in the denominator is of the order of $(k_0R)^{0.5} k_0R$ and is usually smaller than the first term. We obtain

$$\epsilon_0^0 = 2J_0^0 k_0R = (J_0^0 k_0R^2):$$

We next investigate the phase shifts for the higher order partial waves. In the limit $k_0R \ll 1$,

$$\tan \delta_n^E = (k_0R=2)^{2n} = (n-1) \ln 2 [1 - J_n^0 J_n = (J_n^0 k_0R)] = [1 + J_n^0 J_n = (J_n^0 k_0R)];$$

$$\tan \delta_n^H = (k_0R=2)^{2n} = (n-1) \ln 2 [1 - J_n^0 J_n = (J_n^0 k_0R)] = [1 + n J_n^0 = (J_n^0 k_0R)]:$$

Here $J_n = J_n(k_0R)$: When k_0R is also small

$$\tan \delta_n^E = [(k_0R=2)^{2n} - n] (n-1) = (n+1); \tan \delta_n^H = [(k_0R=2)^{2n} - n] (n-1) = (n+1):$$

There is recently much interest in "plasmonics" when the frequency is close to the interface plasmon frequency so that $k_0R = 1$: At this frequency $\epsilon_n^0 = -2$. A Mie scattering resonance

is exhibited for the TE modes for all $n \neq 0$. For $n = 1$ the requirement that the same scattering phase shift is obtained even when $k_1 R$ is not small provides for the equations determining the effective susceptibilities:

$$\tan \frac{E}{1} = (k_0 R = 2)^2 (\epsilon_0 \frac{0}{E}) = (\frac{0}{E} + \epsilon_0): \quad (7)$$

$$\tan \frac{H}{1} = (k_0 R = 2)^2 (\epsilon_0 \frac{0}{H}) = (\epsilon_0 + \frac{0}{H}): \quad (8)$$

From these we obtain the effective susceptibilities

$$\frac{0}{E} = -iJ_1 = (J_1^0 k_1 R); \quad \frac{0}{H} = -iJ_1 = (J_1^0 k_1 R): \quad (9)$$

Similar equations have also been obtained by Hu et al. and Wu et al. [11, 12] from a coherent potential approximation. The results here provides a different interpretation of their results. With the current view, "plasmonics" phenomena can also be manifested for non-metallic rods if $\frac{0}{H} + \epsilon_0 = 1$ and the same scattering phase shift is produced. We next turn our attention to the photonic bands.

Photonic band structure: First we briefly recapitulate the multiple scattering (KKR) technique. The basic idea is that the scattered wave from the photonic crystal is self-consistently sustained. More precisely, consider a cylinder at the origin. The scattered wave from all the other cylinders sum to produce a net incoming wave at the origin which is scattered by the cylinder at the origin and in turn produce a scattered wave from the origin. This scattered wave from the origin is related to the scattered wave from the other sites by a phase factor determined by the wave vector.

More precisely, we denote the amplitude of the partial scattered wave with angular momentum n by a_n : The sum of the scattered waves from all the other sites becomes an incoming wave at the origin with the amplitude $p_n = \sum_{n \neq 0} a_n S(n \rightarrow n^0)$ where

$$S(n \rightarrow n^0) = \sum_{R \neq 0} \exp(ik \cdot R) H_n^{(1)}(k_0 R) \exp(im \cdot R): \quad (10)$$

Note that S does not include the wave from the origin; thus the sum in eq. (10) does not include the term at $R=0$. The outgoing scattered wave at the origin is related to the incoming wave by the t matrix: $a_n = t_n p_n$: Substitute in the definition of p_n , we arrive at the equation $\det[S(n \rightarrow n^0) - (n \rightarrow n^0) t_n] = 0$: Since the t matrix is related to the phase shift by $t_n = \tan \delta_n = (\tan \delta_n + i)$; we obtain the KKR equation

$$\det[A(n \rightarrow n^0) - (n \rightarrow n^0) \cot \delta_n] = 0: \quad (11)$$

$$\langle \epsilon \rangle = \epsilon_o [\epsilon_i^o (1 + f) + \epsilon_o (1 - f)] = [\epsilon_i^o (1 - f) + \epsilon_o (1 + f)] : \quad (16)$$

In the static (zero wavevector and frequency) limit [4] for the case with the E field along the axis the tangential component of the electric field in the cylinder (i) and the medium outside (o) is the same: $E_o = E_i = E$. The average displacement field is given by $\langle D \rangle = \epsilon_o D_o + (1 - \epsilon_o) D_i$. Since $D_o = \epsilon_o E_o$; $D_i = \epsilon_i E_i$; we obtain $\langle D \rangle = (\epsilon_o \epsilon_o + (1 - \epsilon_o) \epsilon_i) E = \langle \epsilon \rangle E$. Hence the average dielectric constant is just the arithmetic mean of the dielectric constants of the components: $\langle \epsilon \rangle = (\epsilon_o \epsilon_o + (1 - \epsilon_o) \epsilon_i)$. This is the same as eq. (15).

In multilayer systems, a similar result is obtained. [8] In that case the effective ϵ is the harmonic mean of the components while the effective dielectric constant is still the arithmetic mean of that of its components.

We next discuss the "optic" mode. Substituting in the expressions for the phase shifts and the A's, the equation for the second optic mode becomes

$$2 \ln k_o a = 2 \sqrt{(k_o a)^2 - \epsilon_o} - 4 f \sqrt{\epsilon_o + \epsilon_i^o} = \left(\frac{\epsilon_o}{\epsilon_i^o} \epsilon_o \right) + O(k^2)$$

for the E mode and

$$2 \ln k_o a = 2 \sqrt{(k_o a)^2 - \epsilon_o} - 4 f \sqrt{\epsilon_o + \epsilon_H^o} = \left(\frac{\epsilon_o}{\epsilon_H^o} \epsilon_o \right) + O(k^2)$$

for the H mode. When k approaches zero, k_o is not zero! Let us illustrate the physics by looking at the H mode. The limit of small f is particularly interesting. In that limit, the frequency is determined by the condition that $\epsilon_o + \epsilon_H^o = 0$ where ϵ_H^o is given in eq. (8).

For metallic cylinders with their radii less than the skin depths, $k_i R \ll 1$, $\epsilon_H^o = \epsilon_i = 1 - \omega_p^2 / \omega^2$ where ω_p is the plasma frequency. $\epsilon_o + \epsilon_i = 0$ when ω is equal to the interface plasmon resonance, $\omega_{sp} = \omega_p (1 + \epsilon_o)^{1/2}$; For small k , from the above equation, we see that $\omega(k) = \omega(k=0) + O(fk)$: If f is small, the dispersion is weak and the bands are flat. This flat band has been observed numerically previously. [9] The present calculation provides for a more direct analytic demonstration of this result. If $k_i R$ is not small, eq. (8) suggests that even with insulating cylinders, flat "plasmonic" photonic bands can still be obtained if the condition

$$\epsilon_i J_1^0(J_1^0 k_i R) = \epsilon_o :$$

is satisfied.

Let us next look at the E mode, the condition becomes $\epsilon_E^o = \epsilon_o = 1$: We call this the "magnetic surface plasmon" mode. Even though there is a lot of interest in plasmonics that

focus on the condition $\epsilon_H^0 = \epsilon_0 = 1$, the corresponding condition on ϵ_m have not been much discussed.

There is another way to think of this type of solutions. As can be seen from eq. (5) and (6), when the susceptibilities of the metal are negative, $\epsilon_0 + \epsilon_m$ can become zero and $\tan \delta = 1$: The scattering can go through resonances due to the interface plasmon. This can lead to flat photonic bands, as has been observed in previous numerical calculations. In general, the more rapidly varying the phase shift, the flatter the band.

Pokrovsky and Efros [10] have recently investigated the propagation of electromagnetic (EM) waves in a periodic array of metallic cylinders (wires) in the limit $R \gg 1$: Our conclusion differs from theirs. In their paper, an expression similar to our $S(0)$ also appears. However, in their expression, the sum is over all R whereas the $R=0$ term is absent in ours.

This research is partly supported by the DOE.

-
- [1] J. B. Pendry, Phys. Rev. Lett. 85, 3966 (2000); R. A. Shelby, D. R. Smith, and S. Schultz, Science 292, 79 (2001).
- [2] J. B. Pendry, A. J. Holden, D. J. Robbins and W. J. Stewart, Jour. Phys. Cond. Mat., 10, 4785 (1998).
- [3] R. A. Shelby, D. R. Smith, S. C. Nemat-Nasser and S. Schultz, Appl. Phys. Lett., 78, 489 (2001). The dimensions of the wires are 0.25 mm x 0.03 mm x 1 cm.
- [4] M. Born and E. Wolf, Principles of Optics, 7th Ed., Cambridge University Press, (1999), p. 837.
- [5] A. V. Zayats, I. I. Smolyaninov, A. A. Maradudin, "Nano-optics of surface plasmon polaritons," Phys. Rep., vol. 408, pp. 131-314 (2005).
- [6] Xinhua Hu, C. T. Chan, Jian Zi, Ming Li and Kai-Ming Ho, Phys. Rev. Lett. 96, 223901, (2006); Ying Wu, Jensen Li, Zhao-Qing Zhang and C. T. Chan, Phys. Rev. B 74, 085111 (2006).
- [7] We expect $k_i R \gg 2$ where the skin depth $\delta = c(2\epsilon_0 \mu_0)^{-1/2}$: In terms of the wavelength, we get $\delta = [c/(2\epsilon_0 \mu_0)]^{1/2} = (2\epsilon_0 \mu_0)^{-1/2}$: Take the conductivity of Cu, $\sigma = 5.88 \times 10^5 \text{ s}^{-1}$; $\delta = 0.38 \times 10^{-4} \text{ (cm)} = 3.8 \times 10^{-6} \text{ m}$: The smallest R possible with lithography is 0.1 μm : For $R = 1 \text{ m} = 10^4 \text{ cm}$; $k_i R \gg 100$.

- [8] S. T. Chui, Z. F. Lin and C. T. Chan, *Jour. Phys. Conds. Mat.* 18, L89 (2006).
- [9] A. V. Zayats, I. I. Smolyaninov, A. A. Maradudin, "Nano-optics of surface plasmon polaritons," *Phys. Rep.*, vol. 408, pp. 131-314 (2005).
- [10] A. L. Prokrovsky and A. L. Efros, *Phys. Rev. Lett.*, 89, 093901 (2002).
- [11] Y. Wu, J. S. Li, Z. Q. Zhang, and C. T. Chan, *Phys. Rev. B* 74, 085111 (2006). ⁰ here corresponds to \sim_s in this paper.
- [12] X. H. Hu, C. T. Chan, J. Zi, M. Li, and K. M. Ho, *Phys. Rev. Lett.* 96, 223901 (2006). See eq. (4) and (5) in this paper.
- [13] L. Peng, L. X. Ran, H. S. Chen, H. F. Zhang, J. A. Kong, and T. M. Grzegorzczuk, *Phys. Rev. Lett.* 98 157403 (2007).
- [14] We change the variable R to $x=kR$ and get

$$S(0) = \sum_{x \neq 0} (x)^2 \exp(ik \cdot x) H_0(x) = (k_0 a)^2$$

In the long wavelength limit, x becomes small. We approximate this sum by an integral and get

$$S(0) \approx \int_{x_1}^{\infty} dx x \exp(ik \cdot x) H_0(x) = (k_0 a)^2 :$$

We pick the lower limit so that the empty area remains the same. ($x_1^2 = (k_0 a)^2$) Since $\exp[ia \cos(\theta)] = \sum_m i^m J_m(a) \exp(im\theta)$; only the $m=0$ term remains in the integral. The radial integral can be easily done. [We assume that k_0 has a small imaginary part so that the upper limit contribution can be set to zero.] We get,

$$S(0) \approx 2 \int_{x_1}^{\infty} dx (J_0(xk=k_0)) H_0(x) = \int_{x_1}^{\infty} dx (H_0(x)) = [(k_0 a)^2 (k^2=k_0^2 - 1)]_{x_1}$$

Using the small argument expansions for the Bessel functions, we obtain In the limit $x \ll 1$, $J_0(x) \approx [1 - (x/2)^2]$, $J^0(x) \approx x/2 + O(x^3)$, $N_0(x) = 2 \ln(x/2) [1 - x^2/4] = : N_0^0(x) = 2[1 - x^2/4] - x \ln(x/2) = 2$:

$$S(0) \approx 1 + 4i [1 - x_1^2 (1 - (k=k_0)^2=2) \ln x_1] = [(k_0 a)^2 (k^2=k_0^2 - 1)];$$

$$A(0) \approx 4 [1 - (k_0 a)^2 (1 - (k=k_0)^2=2) \ln(k_0 a)] = (2) = [(k_0 a)^2 = (k^2=k_0^2 - 1)]:$$

Similarly for $n \neq 0$; in the limit $k_0 R \ll 1$, $J_n(x) \approx (x/2)^n / n! [1 - (x/2)^2 = (n+1)]$, $J^0(x) \approx (n-x) (x/2)^n / n! [1 - (n+2) (x/2)^2 = (n(n+1))]$, $N_n(x) = (2-x)^n (n-1)! [1 + n (x/2)^2] = :$

$$S(n) \approx 2 [i \exp(i k \cdot x)]^n \int_{x_1}^{\infty} dx (J_n(xk=k_0)) H_n(x) = \int_{x_1}^{\infty} dx (H_n(x)) = [(k_0 a)^2 (k^2=k_0^2 - 1)]_{x_1}$$

The dominant contribution in the long wavelength limit is obtained by replacing H by iN .

$$A(n) = 4 [i \exp(i k) k = k_0]^n [1 + O(k_0^2 a^2)] = [(k_0 a)^2 (k^2 = k_0^2 - 1)]$$