Polarization Properties of Single Quantum Dots in N anow ires

M.H.M. van Weert, N.Akopian, F.Kelkensberg, U.Perinetti,

M.P. van Kouwen, L.P. Kouwenhoven, and V.Zwiller^y

Kavli Institute of Nanoscience Delft, Delft University of Technology, Delft 2628CJ, The Netherlands

J.Gomez Rivas

FOM Institute for Atom ic and Molecular Physics AMOLF, c/o Philips Research Laboratories, 5656AE, The Netherlands

M. T. Borgstrom,^z R. E. Algra,^x M. A. Verheijen, and E. P. A. M. Bakkers Philips Research Laboratories, Eindhoven 5656AE, The Netherlands

We study the absorption and emission polarization of single semiconductor quantum dots in semiconductor nanow ires. We show that the polarization of light absorbed or emitted by a nanow ire quantum dot strongly depends on the orientation of the nanow ire with respect to the directions along which light is incident or emitted. Light is preferentially linearly polarized when directed perpendicular to the nanow ire elongation. In contrast, the degree of linear polarization is low for light directed along the nanow ire. This result is vital for photonic applications based on intrinsic properties of quantum dots, such as generation of entangled photons. As an example, we demonstrate optical access to the spin states of a single nanow ire quantum dot.

PACS num bers: 78.55.Cr, 78.67.Hc, 81.07.-b

Sem iconductor quantum dots (QDs) are sources of single [1, 2] and entangled photons [3, 4, 5], single electrons [6], and are naturally integrated with modern sem iconductor electronics. Incorporating them in sem iconducting nanowires (NW s) [7, 8, 9, 10, 11] brings additional unique features such as natural alignment of vertically stacked QDs [12] and an inherent one-dimensional channel for charge carriers. Furtherm ore, the unprecedented material and design freedom makes them very attractive for novel opto-electronic devices [13, 14, 15, 16, 17, 18] and quantum information science in general [19, 20, 21, 22]. How ever, access to intrinsic spin and polarization properties of a QD in a NW has never been dem onstrated, most likely due to an insu cient quality of the NW QDs. Moreover, the NW geometry strongly a ects the polarization of photons em itted or absorbed by a NW QD, and thus becomes the main obstacle for applications based on intrinsic spin or polarization properties of QDs such as an electron spin memory [23] or generation of entangled photons [3]. Indeed, it has been shown that lum inescence of pure NW s is highly linearly polarized and the polarization direction is parallel to the NW elongation [13, 17, 24].

In this Letter we dem onstrate that by directing light along the NW elongation we can access intrinsic spin and polarization properties of a QD in a NW .W e introduce a theoreticalm odel which intuitively explains our experimental ndings and shows how polarization is a ected by various parameters such as NW diameter, dielectric constant of the surroundings and photon wavelength. As an example, we dem onstrate access to the spin properties of a Zeem an split exciton in a QD by measuring the right- and left-hand circular photon polarization.

For our experim ents we used single InA $s_{0:25}P_{0:75}$ QDs em bedded in InP NW s, grown by means of metal-organic vapor-phase epitaxy [25, 26, 27, 28]. Colloidal gold particles of 20 nm diam eter were deposited on a (111)B InP substrate as catalysts for vertical NW growth. The diameter of the NW and the QD was controlled by the gold particle size, while the NW density was set by the gold particle density on the substrate. The QD height and NW length were determ ined by growth time [8]. By controlling diam eter, height, and As concentration one can tune the QD emission in the wide range of 900 nm to 1.5 m [9]. Under appropriate grow th conditions we were able to grow a sam ple with low density of NW swith a single QD that em its around 950 nm . In Fig. 1a) we show a scanning electron m icroscope (SEM) in age of an as-grown sample with a low density of NW s, enabling optical study of a single NW QD. The NW length is about 2 m.A transmission electron microscope (TEM) in age of a NW QD is shown in Fig. 1b). The QD is typically 9 nm high with a diam eter of 31 nm, determ ined by energy dispersive X -ray analysis in a TEM . To sim plify TEM studies, the InP section following QD growth was reduced, while for the sam ples used in our experim ents, the QD was centered in the NW .

A s-grown samples with vertically oriented NW s, referred as standing NW s, were used for experiments where the excitation (em ission) was directed (m easured) along the NW .W e also transferred NW s to a Sisubstrate with a 290 nm SiO₂ top layer, referred as lying NW s, for the experiments where light was directed perpendicular to the NW .B oth samples were studied under the same experimental conditions. M icro photolum inescence (PL) studies were performed at 4.2 K. The NW QD s were excited



FIG.1: (color online) a) SEM image of an as-grown sample with low density of standing NW QDs. b) TEM image of a NW QD.TheQD is indicated by the red rectangle. The low contrast of theQD is due to the low As concentration.c) PL spectra of a single standing NW QD for various excitation powers. The two emission lines denoted with X and XX correspond to the exciton and biexciton emission, respectively. d) PL intensity of X and XX transitions as a function of the excitation power. The solid (dashed) line is a guide to the eye for linear (quadratic) power dependence.

with a linearly polarized 532 nm cw laser focused to a spot size of 1 m using a microscope objective with a numerical aperture NA = 0.85. The PL signal was collected by the same objective and was sent to a spectrom eter, which dispersed the PL onto a nitrogen-cooled silicon array detector, enabling 50 eV resolution. Linear and circular polarizations were determ ined with a xed polarizer together with a half-and quarter-waveplate, respectively.

In Fig. 1c) we show PL spectra of a single standing NW QD for various excitation powers. At low excitation power only one em ission line is visible at 1.284 eV, denoted as X.W ith increasing excitation power a second em ission line, denoted as XX, em erges 2.2 m eV above X. The PL intensities of X and XX as a function of excitation power, represented in Fig. 1d), show that X (XX) increases linearly (quadratically) with excitation power and saturates at high excitation powers. This behavior is typical for the exciton and biexciton under cw excitation. The spectral linew idths for various NW QDs in our sam ples are in the range of 50-200 eV, dem onstrating good quality of the NW QDs. Sim ilar spectral characteristics are also found for lying NW QDs.



FIG.2: (color online) Integrated PL intensity of the exciton in a lying NW QD a) as a function of the orientation of the linear excitation polarization and b) by probing the orientation of the linear em ission polarization. Zero angle of orientation was chosen to m atch the NW elongation, determ ined by in aging. The solid curves are \sin^2 to used to extract the degree of linear polarization from m inim a and m axim a of the t.

In Fig.2 we show the integrated PL intensity of the excitation in a lying NW QD as a function of linear excitation and em ission polarization orientation. In Fig.2b) the excitation polarization is set parallel to the NW elongation. However, the em ission polarization is independent of the excitation polarization. We et this data to a $\sin^2 -$ function with amplitude, o set, and phase as the parameters. The degree of linear polarization, $=\frac{I_{m \mbox{ ax }} I_{m \mbox{ in }} I_{m \mbox{ ax }}$

Polarization-sensitive PL measurements were performed on a number of NW QDs, both lying and standing, which are shown in Fig. 3a). The upper two graphs show the statistics of absorption and emission for lying NW QDs, for which absorbed (emitted) light is directed (measured) perpendicular to the NW elongation. The average degree of linear polarization is $_{\rm abs} = 0.78 \quad 0.06$ ($_{\rm em \ i} = 0.72 \quad 0.08$) for absorbed (emitted) light.

The same m easurem ents were performed on standing NW QDs, for which light absorbed (em itted) by the QD is directed (m easured) parallel to the NW elongation. The results are shown in the lower two graphs of Fig. 3a) and give a degree of linear polarization for absorbed (em itted) light of $_{\rm abs} = 0.1$ ($_{\rm em \ i} = 0.2$). This low value is expected for the symmetric structure of the NW s for light incident or em itted in the direction along the NW elongation. In addition, the m easured degree of circular polarization of the QD em ission is also low, 0.1.

To explain our experim ental results for absorption by a lying NW QD, we use M is theory for light scattering on dielectrics of cylindrical shape [29, 30]. The NW is modeled as an in nite cylinder. This approximation is



FIG.3: (color online) a) Statistics of the degree of linear polarization for lying and standing NW QDs. The lying NW QDs (shown in blue) show high degree of linear polarization, about 0.8 and 0.7, for absorbed and em itted light, respectively. In contrast, the degree of linear polarization is low for standing NW QDs (shown in red), about 0.1 and 0.2 for absorbed and em itted light, respectively. Insets illustrate the NW orientations with respect to the light direction. b) Calculated degree of linear polarization in absorption as a function of NW diam eter. In this case incident light is directed perpendicular to the NW elongation, as for the lying NW QDs. For the solid (dashed) curve an elective refractive index of n = 1 (n = 1:85) is used.

valid as long as the nanow ire diam eter is much sm aller than its length, as in our case. We calculate the scattering and absorption of light using the scalar wave equation in cylindrical coordinates. We consider two cases: incident electric eld parallel or perpendicular to the NW elongation. We extract the scattered eld for both polarizations from the wave equation, using the boundary conditions at the interface of two di erent dielectrics [31], i.e., at the NW surface. From this eld, we calculate for both cases the cross-sections Q_{sca} and Q_{ext} for scattering and extinction. The absorption cross section is obtained by $Q_{abs} = Q_{ext}$ Q_{sca} for both polarizations. To take into account the illum ination of the NW through a microscope objective, we integrate the average absorption cross section over angles of incidence with respect to the NW elongation comprised between $\arccos(NA)$ and =2.

M is theory assumes the surrounding of the NW as a hom ogeneous medium, which diers from our situation where the NW is lying on a substrate. Therefore, to approxim ate the e ect of the substrate we consider the nanowire as being embedded in a medium with an e ective refractive index, i.e., an average of the refractive indices of the di erent media surrounding the NW : vacuum, SiO_2 , and Si. The outcome of the calculations, assuming an elective refractive index of $n_{eff} = 1.85 = 0.5n_{vacuum} + 0.25n_{SiO_2} + 0.25n_{Si}$ is represented by the dashed curve in Fig. 3b). As an upper lim it we consider the NW in vacuum, thus ignoring the substrate, which is represented by the solid curve in Fig. 3b). For the calculations we use our actual excitation wavelength of 532 nm. Our experimental value lies in between the two curves, having a surrounding refractive index consisting of a mixture of vacuum, Si, and SiO₂. As can be seen in Fig. 3b) one can increase the degree of linear polarization by measuring NW QD in vacuum, or decrease it by increasing the NW diam eter. However, in the latter case the advantage of the one-dimensional channel of the device is reduced as well.

The NW geometry is not the only source of polarization anisotropy. Calculations by N iquet and M o jica [32] show that the polarization properties are strongly affected by the aspect ratio of the QD dimensions, due to strain originating from the lattice m ism atch between the NW and the QD. However, in our case the strain is negligible due to the low phosphorus content and the m ain contribution to polarization anisotropy com es from the NW geometry.

The low degree of linear polarization for vertical NW QDs implies that the NW does not a ect the polarization of photons radiated from the QD, thus allowing access to intrinsic spin and polarization properties of NW QDs. To experim entally dem onstrate this we measure the polarization of photons emitted from a Zeeman split exciton in a NW QD. In Fig. 4b) we show PL of the NW QD exciton under external magnetic eld B in the Faraday con guration (B k N W). C learly, the exciton undergoes a Zeem an splitting and diam agnetic shift. From these measurements we extract the exciton g-factor, g = 1:3 0:1, which is typical for our sample. Polarization properties of the split exciton lines at 9 Tesla are shown in Fig. 4a). The high energy em ission line is right-hand circularly polarized, while the lower energy em ission line is left-hand circularly polarized. These two polarization states, +

and , correspond to the two di erent spin states of the exciton #* and "+, respectively, where " (*) represents a spin-up electron (hole) and # (+) represents a spin-down electron (hole). These results show that the em ission polarization of a Q D is not obscured by the NW geom etry, and that electron-hole spin states in a Q D are properly converted to the polarization states of the em itted photons. In contrast, m easurem ents on a lying NW



FIG.4: (color online) a) Polarization sensitive PL of a standing NW QD at 9T.The solid (dashed) curve represent right-(left-) hand circularly polarized exciton em ission, denoted by $^+$ ().b) PL of a standing NW QD under external m agnetic eld.M agnetic eld is varied between 0 and 9T in steps of 0.5 T.

QD show that the two emission lines of a Zeem an split exciton are strongly linearly polarized, with respect to the NW elongation, as expected (not shown).

To conclude, we have correlated the polarization of light absorbed and em itted by a QD em bedded in a NW with its propagation direction with respect to the NW elongation. We found that the polarization of the absorbed (em itted) light, when directed (m easured) perpendicular to the NW elongation, is a ected by the NW geom etry and is strongly linearly polarized along the NW . In contrast, this is not the case for the con guration where the absorbed (em itted) light is directed (m easured) parallel to the NW elongation. In this con guration the intrinsic spin and polarization of the NW QD can be accessed. We have demonstrated this by m easuring polarization states of photons radiated from a Zeem an split exciton in a NW QD.

W e acknowledge W.G.G.Imm ink for technical assistance and F.Holthuysen for providing the SEM im – age. This work was supported by the European FP6

NODE (015783) project. The work of JGR was supported by the Netherlands Foundation Fundam enteel Onderzoek der M aterie (FOM) and the Nederlandse Organisatie voor W etenschappelijk Onderzoek (NWO) and is part of an industrial partnership program between Philips and FOM. The work of REA was carried out under project number MC3.0524 in the fram ework of the strategic research program of the M aterials Innovation Institute (M 2I) (www m 2inl).

Current address: FOM -Institute AMOLF, Am sterdam, The N etherlands

- ^y E lectronic address: v.zw iller@ tudelft.nl
- ^z Current address: Lund University, Lund, Sweden
- * A lso at: M aterials Innovation Insitute, D elft, T he N etherlands, and Solid State C hem istry, R adboud U niversity N ijn egen, N ijn egen, T he N etherlands
- [1] P.M ichler et al., Science 290, 2282 (2000).
- [2] C.Santoriet al, Phys.Rev.Lett.86, 1502 (2001).
- [3] N.Akopian et al, Phys. Rev. Lett. 96, 130501 (2006).
- [4] R.J.Young et al, New J.Phys. 8, 29 (2006).
- [5] R.Hafenbrak et al, New J.Phys. 9, 315 (2007).
- [6] A. Zrenner et al, Nature 418, 612 (2002).
- [7] M.T.Borgstrom et al, Nano Lett. 5, 1439 (2005).
- [8] E.D.M inot et al., Nano Lett. 7, 367 (2007).
- [9] M. Tchemycheva et al, N ano Lett. 7, 1500 (2007).
- [10] Y.Ding et al, N ano Lett. 7, 3598 (2007).
- [11] J.Renard et al., Nano Lett. (2008).
- [12] T.Lundstrom et al, Science 286, 2312 (1999).
- [13] J.W ang et al., Science 293, 1455 (2001).
- [14] M.H.Huang et al, Science 292, 1897 (2001).
- [15] X.Duan et al, Nature 409, 66 (2001).
- [16] X.Duan et al, Nature 421, 241 (2003).
- [17] H.Pettersson et al., N ano Lett 6, 229 (2006).
- [18] J.Bao et al., N ano Lett. 6, 1719 (2006).
- [19] D. Loss and D. P. Divincenzo, Phys. Rev. A 57, 120 (1998).
- [20] M.T.Bjork et al., Nano Lett. 4, 1621 (2004).
- [21] Z. Zhong et al., N ano letters 5, 1143 (2005).
- [22] A.Pfund et al, Appl. Phys. Lett. 89, 252106 (2006).
- [23] M.K routvar et al, Nature 432, 81 (2004).
- [24] O.L.Muskens et al, Opt.Lett. 32, 2097 (2007).
- [25] K.Hirum a et al, Appl. Phys. Lett. 59, 431 (1991).
- [26] L.J.Lauhon et al, Nature 420, 57 (2002).
- [27] M. A. Verheigen et al., J. Am. Chem. Soc. 128, 1353 (2006).
- [28] M.T.Borgstrom et al, Nat. Nanotechn. 2, 541 (2007).
- [29] C.F.Bohren and D.R.Hu man, Absorption and scattering of light by sm all particles (W ikey-VCH, 1998).
- [30] H. E. Ruda and A. Shik, J. Appl. Phys. 100, 024314 (2006).
- [31] J. D. Jackson, Classical Electrodynamics (Wiley, 1999), 3rd ed.
- [32] Y.M. Niquet and D.C. Mojica, Phys. Rev. B 77 (2008).