E lectronic structure and x-ray magnetic circular dichroism of Y B a_2 C u_3 O $_7$ /L a_1 $_x$ C a_x M nO $_3$ superlattices from st-principles calculations

X isoping $Yang_{1}^{1} A.N.Yaresko_{1}^{1} V.N.Antonov_{1}^{1,2}$ and O.K.Andersen¹

¹M ax-P lanck-Institut fur Festkorperforschung, Heisenbergstra e 1, D -70569 Stuttgart, G erm any

²Institute of M etal Physics, 36 Vernadsky Street, 03142 K iev, U kraine

(D ated: February 22, 2024)

The origin of x-ray magnetic circular dichroism (XMCD) at the Cu $L_{2,3}$ edge in YBa₂Cu₃O₇/La₁ _xCa_xMnO₃ superlattices is revealed by performing rst-principle electronic structure calculation using fully-relativistic spin-polarized linear mu n-tin orbital and projected augmented plane wavem ethods. We show that the XMCD spectra at the Cu $L_{2,3}$ edges are proportional to the di erence of the densities of Cu d_{32^2} 1 and d_{432^2} 1 states. A linough the Cu d_{32^2} 1 states lie wellbelow the Fermi level, a sm all num ber of d_{32^2} 1 holes is created by the Cu d_{32^2} 1 (O Ba pz (M n d_{32^2} 1 hybridization across the interface. Even this tiny num ber of holes is su cient to produce appreciable Cu $L_{2,3}$ XMCD. The robustness of this conclusion is veried by studying the in uence of doping, atom ic relaxation, correlation e ects, and antiferrom agnetic order in a CuO₂ plane on the XMCD spectra.

PACS num bers: 75.50.C c, 71.20 Lp, 71.15 R f

I. IN TRODUCTION

A rti cially grown heterostructures and superlattices of alternating superconducting (SC) and ferrom agnetic (FM) materials have become an important tool for exploring the interplay between superconductivity and ferrom agnetism. Various interaction phenom ena that may occur, like proximity e ects, coupling phenom ena, charge transfer etc., are directly in uenced by the structure and especially by the physical and/or chemical disorder of the interfaces that separate them. The combination of ferrom agnetic and superconducting materials could end up in devices like a spin-controlled transistor with a high gain current and short switching times.

In the last years much attention has been payed to oxide based FM/SC superlattices (SL), combining a high- T_c superconductor YBa₂Cu₃O₇ (YBCO) with a $La_{2=3}Ca_{1=3}M nO_3$ (LCMO) manganite which exhibits colossalm agnetoresistance.^{1,2,3,4,5,6,7,8,9,10,11} Both YBCO and LCMO have oxide perovskite structure with very similar in-plane lattice parameters, which allows the growth of superlattices with sharp interfaces, thus strongly reducing extrinsic "structural" e ects which otherwise could obscure the FM /SC interplay. Using scanning transmission electron microscopy and high spatial resolution electron energy loss spectroscopy, Varela et al. showed in Ref. 2 that individual layers of the $YBa_2Cu_3O_7/La_1 xCa_xMnO_3$ superlattices are at over long lateral distances. The interfaces are coherent, free of defects, exhibiting no roughness, and are located at the BaO plane of the superconductor. Concerning chem ical disorder, EELS m easurem ents show the absence of m easurable chem ical interdi usion within experim entalerror bars.

The work on the perovskite oxide FM /SC superlattices is motivated by the appealing properties of the cuprate high- T_c superconductors (HTSC) whose high SC critical

tem peraturesm ake them potentially useful for technological applications. Further, since H T SC are believed to be susceptible to a variety of competing instabilities, there is a high potential for SC /FM quantum states in multilayer structures. It has been suggested by Si in Ref. 12 that electron injection from hole-doped rare earth m anganites into high-tem perature superconductors can yield inform ation on spin-charge separation in high-T_c superconductors. The spin-polarization, in addition to the ferrom agnetic ordering nature, is one particular property of hole-doped rare earth R₁ $_xA_xM$ nO₃ m anganite, where R is a trivalent rare-earth ion and A is a divalent alkaline-earth ion. In the case of La₂₌₃C a₁₌₃M nO₃ a nearly full spin polarization of the transport electrons can be found.¹³

Magnetization measurements of epitaxially grown bilayers of LCM 0 and YBCO show a coexistence of ferromagnetism and superconductivity in these bilayer sam ples at low tem peratures.¹⁴ B oth m agnetization m easurements which are used to determ ine T_{c} and magnetooptical measurements for the j_c evaluation of the superconducting Im show up a critical thickness for the YBCO Im of about d= 30 nm, below which the superconductivity is strongly a ected by the magnetic Im. Sefrioui et al. in Ref. 3 studied the interplay between magnetism and superconductivity in high-quality YBCO/LCMO superlattices. They found evidences for the YBCO superconductivity depression in the presence of the LCMO layers. Due to its short coherence length, superconductivity survives in the YBCO down to a much smaller thickness in the presence of the magnetic layer than in low T_{c} superconductors. For a xed thickness of the superconducting layer, superconductivity is depressed over a thickness interval of the magnetic layer in the 100 nm range.

Holden et al. in Ref. 4 reported ellipsom etry m easurem ents of the far-infrared dielectric properties of SL com posed of thin layers of YBCO and LCMO. The optical data provide clear evidence that the free-carrier response is strongly suppressed in these SL as compared to the one in the pure YBCO and LCMO lms. The suppression occurs in the norm alas well as in the SC state and involves a quite large length scale.

This research is in its early stage, and relatively little is known about the nature of magnetism at the interface, the spatial distribution of the magnetization throughout the layers, and the interplay of FM and SC order param – eters in general.

X-ray magnetic circular dichroism (XMCD) spectra at Mn and Cu L_{2:3} edges in YBCO/LCMO SL were measured by Chakhalian et al. in Ref. 10. It was shown that magnetic dichroism is clearly present at both Mn and Cu edges, although the Cu XM CD signal is sm all com pared to that of M n (27%) and does not exceed 1.4% . The m easurem ents suggest the presence of an uncom pensated induced magnetic moment in a YBCO layer close to the YBCO/LCMO interface. A sm anganite layers undergo a ferrom agnetic transition at around 180 K, the large dichroism at the M n $L_{2,3}$ edge is expected. However, the presence of the net ferrom agnetic m agnetization on Cu is quite surprising. A uthors investigated also the tem perature dependence of the dichroic signals at both the M n and C u L_{2:3} edges. At tem peratures above 170 K, the dichroism on M n disappears, consistent with the ferrom agnet-param agnet transition. Sim ilar behavior was also found for Cu, except that already above 150 K its XMCD signal decreases below the detection lim it. From the sim ilar tem perature dependences of the XMCD spectra authors concluded that the magnetic moment on Cu is induced by strong interactions between Cu spins and the ferrom agnetic m om ent of M n across the interface.

Later, x-ray absorption spectra (X A S) and x-ray linear dichroism (X LD) at M n and C u L_{2;3} edges were recorded in the total electron yield (T EY) and uorescence-yield (FY) modes from the same sample of Y BCO/LCM O SL.¹¹ In contrast to strong C u L_{2;3} X LD detected in the bulk sensitive FY mode, only a very weak X LD signalwas m easured in the TEY mode, which is supposed to probe interfacial C u ions. This led authors to the conclusion that the electronic states of C u ions at the Y BCO/LCM O interface are strongly reconstructed, with the num ber of holes in the C u d_{3z²} 1 states being close to the num - ber of C u d_{x²} y² holes. A mechanism for such orbital reconstruction was proposed.

In the present study, we focus our attention on the electronic band structure of YBa₂Cu₃O₇/La₁ $_x$ Ca_xMnO₃ superlattices and their XMCD and XAS spectra. We show that the magnetic circular dichroism at the Cu L_{2;3} edges appears due to the hybridization between com – pletely lled Cu d_{3z²} 1 states and unoccupied Mn d_{3z²} 1 states split by the on-site exchange interaction. The num – ber of Cu d_{3z²} 1 holes created by the hybridization is much sm aller than the num ber of holes in the Cu d_{x²} y² states. Nevertheless, even this tiny number of d_{3z²} 1 holes is su cient to produce appreciable Cu L_{2;3} XMCD.

YBCO/LCMO SL. The paper is organized as follows. The details of the calculations are described in Sec. II. A structural model of YBCO/LCMO superlattices considered in this study is presented in Sec. III. Section IV is devoted to the electronic structure and XMCD spectra of the YBCO/LCMO SL calculated using the local spin-density approximation (LSDA) and the LSDA+U method. Finally, the results are summarized in Sec.V.

fects on the electronic structure and XMCD spectra of

II. COMPUTATIONALDETAILS

The electronic structure and XMCD spectra of YBCO/LCMO SL were investigated by means of ab initio calculations based on the spin-polarized density functional theory. The energy band structure, densities of states (DOS), and magnetic moments were calculated within the local spin-density approximation (LSDA) using the projected augmented plane wave (PAW) method^{15,16,17} and the linear mu n-tin orbital (LMTO) method.¹⁸ The cuto energy of the plane-wave expansion was 500 eV and the spacing between k points was 0.03 A¹.

XMCD calculations were performed using the spinpolarized fully relativistic LMTO method (see Refs. 19,20 for details). To investigate the e ect of electronic correlations on the XMCD spectra the rotationally invariant LSDA+U method^{21,22} with the double-counting term approximated by the atom ic lim it^{23} was used. The screened on-site C oulom b repulsion U was considered as an adjustable parameter. We used U = 3 to 5 eV for the M n d states and U = 7.5 eV for the Cu d states. For the exchange integral J the value of 1.0 eV estimated from constrained LSDA calculations was used.

The nite lifetime of a core hole was accounted for by folding the XMCD spectra with a Lorentzian. The widths of the $\rm L_2$, and $\rm L_3$ core level spectra, with $\rm L_2=0.97\,eV$, $\rm L_3=0.36\,eV$ for the Mn and $\rm L_2=1.04\,eV$, $\rm L_3=0.61\,eV$ for the Cu were taken from Ref. 24. Finite instrum ental resolution was accounted for by a G aussian of 0.5 eV .

III. STRUCTURALMODEL

The crystal structure of YBCO/LCM O SL was approximated by a tetragonal (P 4=m m m) unit cell consisting of one YBCO and up to 3 LMO unit cells stacked along the c direction. The interface is form ed by a BaO plane from the YBCO side and a M nO₂ plane of LMO, which replaces a CuO plane of YBCO. The unit cell consisting of one YBCO and one LMO layer is shown in Fig. 1. For the in-plane lattice constants a= b= 3.94 A the experimental value for pseudo-cubic LMO is used. Thus,



FIG.1: (Color online) Schem atic representation of the crystal structure of the 1 YBaCuO/1 LMO superlattice. The tetragonal unit cell used in the calculations is marked by the double-arrowed line. The number of electrons provided by each plane to Cu and Mnd shells is given in parenthesis.

the orthorhom bic distortion of bulk YBCO is neglected and the YBCO layer is slightly expanded in the ab plane. The c constant of 15.61 A is taken to be equal to the sum of the lattice constants of bulk YBCO ($_{\rm YBCO}$ = 11.67 A) and pseudo-cubic LMO ($_{\rm CLM O}$ = 3.94 A).

Interfacial ions are subject to forces di erent from those in the bulk and, thus, can change their positions. The mere transfer of charge at an interface can lead to "electronic reconstruction".²⁵ Since the exact atom ic structure at the YBCO/LCMO interface is not known, atom ic positions were optim ized using the PAW method. During the optimization the a and c lattice constants were xed to the above mentioned values. As can be expected, the most sensitive to the optim ization are the positions of the atom swhich are close to the YBCO /LCM O interface. An oxygen ion denoted as O_{Ba}, which sits in the BaO plane between the nearest Cu and Mn ions, m oves in the course of the optim ization towards Mn.As a result, the $Cu\{O_{Ba} \text{ distance increases from } 2.29 \text{ A in}$ bulk YBCO to 2.37 A in the superlattice and, thus, becom es even larger as com pared to the separation of 1.98 A between Cu and O_{Cu} ionswithin the CuO₂ plane. The

M n{ O_{Ba} distance decreases from 1.97 A to 1.82 A. The optim ized separation between Cu and M n ions is slightly (4.18 A vs. 4.15 A) larger than between Cu ions residing in CuO₂ and CuO planes in bulk YBCO. The structure optim ization leads also to weak buckling of M nO₂ planes. Nevertheless, the M n{ O_{Mn} distance (1.98 A) remains practically the same as the M n{ O_{La} one (1.97 A). As the LaO plane is a m irror plane, the positions of O_{La} ions do not change during the optim ization. Thus, the interfacial M n ion is surrounded by a slightly distorted O₆ octahedron formed by O_{Ba}, O_{La}, and 4 O_{Mn} ions.

Atom ic positions were also optimized for 1 YBCO/2 LMO SL with c= 19.55 A ($c_{YBCO} + 2c_{LMO}$) containing 2 LMO unit cells. In this case, the Cu{O_{Ba} and Mn{O_{Ba} distances of 2.48 A and 1.80 A were obtained, which gives the separation of 4.28 A between Cu and Mn ions at the interface. As the clattice constant was xed, the expansion at the interface occurs at the expense of som e decrease of the distances between CuO₂ planes and between the \bulk" and \interfacial" MnO₂ planes.

Under the assumption that 0 p states are completely lled and s and d states of Ba, Y, and La are empty, M n and Cu d states in the SL shown in Fig. 1 are lled with 24 electrons. Taking into account that the unit cell contains 2 Cu and 2 M n ions and assum ing that som e charge m ay be transferred across the interface, the occupations

of the d shells are Cu d⁹ and M n d³. Hence, the occupation of M n d states in this model SL corresponds to La_{1 x}Ca_xM nO₃ with x 1. W ith each LM O layer, consisting of one M nO₂ and one LaO plane, added to a model unit cell, the number of electrons which 11 the d states of transition m etal ions increases by 4, while the number of M n d states increases by 4, while the number of M n d states increases with the increase of the LM O layer thickness. This should be taken into account when comparing the results calculated for di erent m odel YBCO /LM O SL.

IV. RESULTS AND DISCUSSION

A. XMCD spectra

The x-ray magnetic circular dichroism in the YBCO/LCMO SL has been measured at the Mn and Cu $L_{2;3}$ edges by Chakhalian et al. (Ref. 10). The measurements were carried out at 30 K in an applied eld of 500 O e on a superlattice of alternating 100 A -thick, c-axis-oriented YBa₂Cu₃O₇ and $La_{2=3}Ca_{1=3}MnO_3$ layers. A circularly polarized x-ray beam was shined at a sm all angle to the lm surface, so that the x-ray propagation direction was alm ost parallel to the LCMO magnetization oriented in the ab plane.

Figure 2 show sXMCD spectra at the M n and Cu $L_{2,3}$ edges calculated within LSDA for the 1 YBCO/1 LMO SL together with the experimental spectra from Ref. 10. The corresponding normalized theoretical x-ray absorp-



FIG. 2: (Color online) The theoretical and experimental (Ref. 10) XMCD spectra of the YBCO/LCMO superlattice at the Mn and Cu $L_{2;3}$ edges. The experimental Cu $L_{2;3}$ XMCD spectrum is multiplied by a factor of 2. The insets show theoretical XAS spectra averaged over two circular polarizations (solid line). The Cu $L_{2;3}$ XAS calculated with the x-ray polarization along the c axis is plotted by dashed line. All the spectra are plotted relative to the corresponding L_3 absorption edge marked by vertical dashed lines.

tion spectra averaged over two circular polarizations are plotted by solid lines in the insets in Fig. 2. The LSDA calculations reproduce very well the experimental Cu L_{2:3} XMCD spectra, although the calculated magnetic dichroism has a small oscillatory structure at the high energy part of the C u L_{2:3} spectra which is not detected by the experim ent probably due to a weak signal. XMCD peaks at the M n and C u L_3 edges are of opposite signs, as it is expected when the magnetization induced on Cu is antiparallel to M $_{\rm M\,n}$. The theory overestim ates the dichroism at the Cu L2;3 edges approximately by a factor of two in comparison with the experim ental observation. This can be explained by the fact that our calculations were perform ed for the unit cell containing a single YBCO cell, with the Cu ions in both CuO₂ planes polarized due to their proxim ity to magnetic LCM 0 layers. In the experim ental sam ples, on the other hand, YBCO layers, consisting of about 3 unit cells of bulk YBa₂Cu₃O₇, are signi cantly thicker. It is natural to expect that only Cu ions in the interfacial CuO₂ planes have a nonzero com ponent of the magnetic moment along the light propagation direction and, consequently, contribute to

the measured XMCD signal, whereas inner CuO₂ planes are XMCD-inert. W ith the increase of the YBCO layer thickness in the model unit cell, the XAS intensity would increase proportionally to the num ber of CuO planes, but not the dichroism. Since the calculated XMCD spectra were normalized by the intensity of the corresponding x-ray absorption spectra, the normalized XMCD signal would tend to decrease with the increase of the YBCO layer thickness, which would in prove the agreem ent between the calculations and the experiment.

O ur calculations for the 1 YBCO/1 LMO SL result in strong linear dichroism at the C u $L_{2,3}$ edges. The XAS spectrum calculated for the x-ray polarization " parallel to the c axis is compared to the spectrum averaged over two circular polarizations, which in this geometry corresponds to the averaging over "jb and "jc polarizations, in the inset to the lower panel of Fig. 2. A prominent peak at 1 eV in the averaged spectrum is strongly suppressed when e becomes parallel to c. The strong XLD at the C u $L_{2,3}$ edges is at variance with the interface-sensitive TEY measurements,¹¹ which showed a very weak polarization dependence of C u $L_{2,3}$ XAS.

In the case of M n, the experim ental L_{2;3} XM CD spectrum shows two additional positive peaks at the energies around 4 eV and 10 eV which are absent in the theoretical spectrum. The cause of such a disagreem ent is yet unclear. One of possible reasons m ay be m any-body e ects, e.g., the interaction of the partially led M n d states with a 2p core hole, which is not taken into account in the theoretical calculations. The M n L_{2;3} XM CD spectrum m ay change if the m agnetization in interfacial M nO₂ planes is reversed relative to the rest of the LCM O layer or it m ay be strongly in uenced by possible orbital ordering in LCM O . These questions need further theoretical consideration.

In the following we focus on the origin of the magnetic circular dichroism at the Cu $L_{2,3}$ edges, but rst we turn our attention to the electronic band structure of YBCO/LMO superlattices.

B. Energy band structure

Symmetry-resolved densities of Cu d, Mn d, and O p states calculated within LSDA for the model 1 YBCO/1 LMO SL (Fig. 1) assuming ferrom agnetic ordering of Mn magneticm on ents are presented in Fig.3. Mn d states are split by the octahedral component of the ligand eld into rather narrow d_{xy} and $d_{xz,yz}$ (t_{2g} ") states and much wider $d_{x^2 y^2}$ and $d_{3z^2 1}$ (t_{2g} ") ones. The latter are strongly hybridized with, respectively, $O_{Mn} p_{x,y}$ and O_{Ba} and $O_{La} p_z$ states. The $d_{3z^2 1}$ states, orm ore precisely their antibonding combinations with O p states, are shifted to higher energies due to the shortening of the Mn { O_{Ba} bond at the interface. Because of the small thickness of a LMO layer, they are narrower than the $d_{x^2 y^2}$ states.

The on-site H und's coupling splits the M n t_{2g} states



FIG.3: (Color online) Spin- and symmetry-resolved LSDA densities of states, N (E), for 1 YBCO/1 LMO SL. The Fermi energy is at zero.

into alm ost completely occupied majority-and unoccupied minority-spin states. The t_{2g} states provide the dominant contribution (2.21 $_{\rm B}$) to the magnetization M $_{\rm M n}$ = 2.75 $_{\rm B}$ inside a M n sphere. The rest comes from the M n $d_{\rm x^2}$ $_{\rm y^2}$ (0.32 $_{\rm B}$) and $d_{\rm 3z^2}$ $_1$ (0.21 $_{\rm B}$) states which are also split by the on-site exchange interaction. W hile the minority-spin $d_{\rm 3z^2}$ $_1$ and, especially, $d_{\rm x^2}$ $_{\rm y^2}$ states is partially lled.

Figure 3 shows that, as it is usual for cuprates, all Cu d states, except for $d_{x^2 \ v^2}$ ones, lie well below the Ferm i level ("_F). The $d_{x^2 \ \ \, y^2}$ states, interacting strongly in the ab plane due to dp -type bonds with O_{Cu} p_{x;y} states, form 3 eV {wide bands in the range from 1 to 2 eV, as can be seen in Fig. 4 which shows the contributions of the d_{3z^2} 1 and d_{x^2} v^2 states of C u and M n to the bands calculated for the 1 YBCO/1 LMO SL. The bands originating from Cu and Mn d_{x^2} v^2 states have sim ilardispersions. The Cu d_{x^2} v_{y^2} bands for both spin directions are nearly degenerate and cross $"_{\rm F}$. The majority-spin M n bands also cross ${\tt "}_{\rm F}$, whereas the m inority-spin ones lie 2 eV higher and are completely empty. Mn d_{3z^2} 1-derived bands are split into bonding and antibonding ones by strong interaction between the d_{3z^2} 1 orbitals of M n ions from two M nO $_2$ planes via O $_{La}$ p $_z$ states. The bonding m a jority-spin M n d_{3z^2} 1 bands are found just above "_F.

Finally, Cu d_{3z^2} 1 bands for both spin directions lie about 2 eV below "_F and hybridize strongly with 0 p bands. Owing to the hybridization of the Cu d_{3z^2} 1 states with the spin-split M n d_{3z^2} 1 states, which is mediated by O_{Ba} p_z orbitals, the densities of the majorityand minority-spin Cu d_{3z^2} 1, as well as O_{Ba} p_z, states are rem arkably di erent (see Fig. 3), with the di erences being mostly restricted to the occupied bands. How ever, due to the Cu d_{3z^2} $_1$ {O Ba pz {M n d_{3z^2} $_1$ hybridization, the Cu d_{3z^2} $_1$ states contribute also to the unoccupied M n d_{3z^2} $_1$ -derived bands. Because of the large (2.37 A) Cu {O Ba separation and a large energy di erence between the Cu and M n d_{3z^2} $_1$ states, this contribution is quite sm alland can hardly be seen in Fig. 3. It is, how ever, important for understanding the origin of Cu L_{2;3} XM CD spectra presented in Fig. 2.

It is well docum ented that LSDA fails to produce a local Cu magnetic moment in HTSC cuprates.^{23,26} In the model 1 YBCO/1 LMO SL, a tiny Cu moment $M_{Cu} = 0.002_{B}$, i.e., directed oppositely to the M n m oment, is induced by the proximity of a ferrom agnetic M nO $_2$ plane. The dom inant contribution of 0.014 $_{\rm B}$ to M_{Cu} is provided by the d_{3z^2} 1 states. It is, however, partially compensated by the magnetization of opposite sign (0.012 $_{\rm B}$) induced in the $d_{xz,yz}$ chanel. The contributions of the d_{xy} (0.003 $_{\rm B}$) and d_{x^2} $_{y^2}$ (0.003 $_{\rm B}$) states are even smaller and cancel each other. Such a sm all di erence in the occupations of the majority-and m inority-spin Cu d states produces negligibly sm all exchange splitting of the d shell. The d_{3z^2-1} states become spin-polarized as a result of their hybridization with the spin-split unoccupied M n d_{3z^2} 1 states. The majorityspin M n d_{3z^2} 1 bands disperse just above "_F, about 3 eV higher than the center of C u $d_{3\,z^2 \ 1}$ states, while the m inority-spin bands are shifted by the on-site exchange splitting _{ex} 2 eV to higher energies (Fig. 4). Because of this energy di erence, the Cu d_{3z^2} 1{0_{Ba} p_z { M n d_{3z² 1} hybridization creates a larger num ber of holes in them a jority-than in them inority-spin O $_{B\,a}\,p_z$ and C u d_{3z^2} 1 states, as illustrated schem atically in Fig. 5. C onsequently, the sign of the corresponding contributions to Cu and O_{Ba} magnetizations is opposite to the magnetization of M n. The negative $O_{Ba} p_z$ spin-polarization is, however, over-compensated by the positive one, induced by the hybridization of $p_{x,y}$ orbitals with M n $d_{xz,yz}$ states: as the majority-spin $d_{xz,yz}$ states are completely lled, only m inority-spin $p_{\boldsymbol{x},\boldsymbol{y}}$ holes are created and the calculated total O_{Ba} spin m om ent of 0.13 $_{B}$ is parallel to M_{Mn}.

The spacial distribution of the spin-density (SD) calculated for the 1 YBCO/1 LMO SL is presented in Fig.6. Large positive iso-surfaces surrounding M n ions (right panel of Fig.6) depict the spin-density of the completely spin-polarized M n t_{2g} states. The M n $d_{xz,yyz}$ {O_{Ba} $p_{x,yy}$ hybridization is responsible for the positive SD surface around O_{Ba}. The left panel of Fig.6 shows clearly that negative SD surfaces surrounding O_{Ba} and Cu ions appear due to the polarization of O_{Ba} p_z and Cu d_{3z^2-1} states, respectively, which, as it is explained above, is caused by their interaction with the spin-split unoccupied M n d_{3z^2-1} states.

Test calculations in which O_{Ba} was shifted along the line connecting M n and C u ions, while all other atom ic positions were kept xed, showed that the calculated C u



FIG. 4: (Color online) The energy band dispersion in the fat-band representation calculated within LSDA for the model 1 YBCO/1 LMO SL shown in Fig. 1. The size of a circle is proportional to the weight of the corresponding state in a Bloch wave function at a given k-point.



FIG. 5: (C olor online) A sketch of the hybridization between the occupied C u d_{3z^2-1} states and the unoccupied M n d_{3z^2-1} states split by the on-site exchange interaction e_x . The contribution of the C u d_{3z^2-1} orbitals to bonding (B) and antibonding (AB) states is shown by thick lines. The negative spin-polarization of the C u d_{3z^2-1} states appears due to their larger weight in the majority-spin AB states than in the minority-spin ones.

m om ent is very sensitive to the position of the interfacial O_{Ba} ion. The variation of the $Mn\{O_{Ba} \text{ and } Cu\{O_{Ba} \text{ distances has a twofold e ect: rst, the increase of the <math>Mn\{O_{Ba} \text{ separation weakens the } Mnd_{3z^2} \ _1\{O_{Ba} p_z \text{ hybridization, which leads to a downward shift of } P_z$

the mostly unoccupied d_{3z^2} 1 bands relative to d_{x^2} v^2 ones. The majority-spin d_{3z^2} 1 states become more populated, which provides the dom inant contribution to the increase of the M n spin m om ent from $2.75_{\rm B}$, when the optimized O_{Ba} position is used ($d_{Mn} O_{Ba} = 1.82$ A), to 3.01 $_{\rm B}$, when O $_{\rm B\,a}$ is equidistant to the M n and C u sites $(d_{Mn O_{Ra}} = 2.09 \text{ A})$. It should be noted, that in spite of the increase of the $M n \{ O_{Ba} \text{ distance, the negative } \}$ spin-polarization of the p_z states increases as O_{Ba} m oves away from Mn. This can be explained by the decrease of the energy separation between the majority-spin Mn $d_{3z^2 \ 1}$ and $0_{Ba} \ p_z$ states as a result of the downward shift of the form er and an upward energy shift of the latter. Second, strengthening of the Cu d_{3z^2} $_1\{0_{Ba} p_z\}$ hybridization due to the decrease of the C u {O $_{\rm Ba}$ distance increases the C u d_{3z^2} 1 weight in the M n d_{3z^2} 1-derived bands and, consequently, the spin-polarization of the Cu $d_{3z^2 \ 1}$ states. As O $_{Ba}$ is shifted from the optim ized position $(d_{Cu} \circ_{Ba} = 2.37 \text{ A})$ to the middle of the Cu{M n line (d_{Cu OBa} = 2.09 A), M_{Cu} increases from 0.002 to 0.036 в.

C. Origin of X M C D at C u L_{2;3} edges

The calculated Cu L₂ and L₃ XM CD spectra and the spin-polarization of Cu d_{3z^2} 1 and d_{x^2} y^2 states, i.e., the di erence of the densities of corresponding m a prity-and m inority-spin states, are plotted together in lower and





FIG. 6: (Color online) The calculated spacial distribution of the spin-density in the 1 YBCO/1 LMO super-lattice. Left and right panels show negative and positive constant-spindensity iso-surfaces, respectively. The cut is through a [100] plane, with z axis parallel to c.

upper panels of F ig. 7. In order to m ake the sim ilarities m ore clear, the spectra are plotted w ithout the life-time and instrum ental broadening and are aligned to the corresponding absorption edges which are shifted to zero energy. Figure 7 shows unam biguously that the energy dependence of the calculated XM CD signal at the Cu L_2 and L_3 edges is determ ined by the spin-polarization of the Cu d_{3z^2-1} states.

Qualitative understanding of the Cu L_{2;3} XMCD absorption spectra is provided by the analysis of the matrix elements for $2p_{1=2;3=2}$! $3d_{3=2;5=2}$ transitions. XMCD at the $L_{2,3}$ edges is mostly determined by the strength of the spin-orbit coupling of the initial 2p core states and spin-polarization of the nal3d states while the exchange splitting of the form er as well as the SO coupling of the latter are usually of m inor in portance.²⁷ Squared angularmatrix elements for the absorption of a photon with left (p=+1) or right (p=-1) circular polarization, 2 , by exciting an electron from the SO -split $p_{1=2;3=2}$ core levels to spin-and crystal-eld split d states are collected in Tables I and II. The matrix elements were calculated in the dipole approximation neglecting the SO splitting of the d states and assuming that x-rays propagate along the spin quantization axis which is parallel to z.

FIG.7: (Color online) The comparison of the calculated Cu L_2 and L_3 spectra (lower panel) and the dimension of the densities of the majority- and minority-spin Cu d_{3z^2-1} and $d_{x^2-y^2}$ states (upper panel). The unbroadened spectra are plotted relative to the corresponding absorption edges.

TABLE I: Squared angular matrix elements 2 for dipole allowed transitions at the L₂ edge from an initial core state with the total angular momentum j = 1=2 and its projection m_j to a nal 3d valence state (jfi) with the absorption of left (p = +1) or right (p = 1) circularly polarized x-rays. 2 are multiplied by 90. The intensity of unpolarized x-ray absorption and XMCD spectra are proportional to $^2_{+}$ + $^2_{-}$ and $^2_{+}$ 2, respectively.

Ϊi	p= Mj	+1	p= Mj	1 2	² ₊ + ²	2 +	2
d"yz d"zx d"xy d"3z ² 1 d"x ² y ²	1=2 1=2 1=2 1=2	3 3 12 12	1=2 1=2 1=2	3 3 4	6 6 12 4 12	0 0 12 4 12	
$\begin{array}{c} d_{\#_{Y}z} \\ d_{\#_{Z}x} \\ d_{\#_{X}y} \\ d_{\#_{3}z^2 1} \\ d_{\#_{x}z^2 y^2} \end{array}$	1=2 1=2 1=2	3 3 4	1=2 1=2 1=2 1=2	3 3 12 12	6 6 12 4 12	0 0 12 4 12	

TABLE II: Squared angular matrix elements 2 for dipole allowed transitions at the L₃ edge. The notations are the same as in Table I.

	$p = +1_{2}$		$p = 1_{2}$		2 2	2	2
Ţı	m j	+	m j	_	- + -	+	
d _{"yz}	1=2	6	1=2	6	12	0	
d _{"zx}	1=2	6	1=2	6	12	0	
d _{"xy}	1=2	6	3=2	18	24	12	
d _{"3z21}	3=2	6	1=2	2	8	4	
$d_{x^2 y^2}$	1=2	6	3=2	18	24	12	
d _{#yz}	1=2	6	1=2	6	12	0	
d _{#zx}	1=2	6	1=2	6	12	0	
d _{#xy}	3=2	18	1=2	6	24	12	
d _{#3z2 1}	1=2	2	3=2	6	8	4	
$d_{\#x^2 y^2}$	3=2	18	1=2	6	24	12	

By comparing Tables I and II we can conclude that neglecting the radial matrix elements and di erent lifetim es of $2p_{1=2}$ and $2p_{3=2}$ core holes, the unpolarized XAS intensity, proportional to $\frac{2}{4}$ + $\frac{2}{4}$, is twice as high at the L₃ edge as at the L₂ one. The corresponding XM CD signals, $\frac{2}{4}$ - $\frac{2}{4}$, are, how ever, of the same m agnitude, with the sign of the dichroism at the L₂ edge being opposite to the L₃ one. This can be clearly seen in the lower panel of Fig. 7 where the unbroadened Cu L₂ and L₃ XM CD spectra are plotted. The almost twofold di erence in the intensities of the L₂ and L₃ XM CD spectra presented in Fig. 2 appears because of the large di erence in the inverse life times of $2p_{1=2}$ ($L_2 = 1.04 \text{ eV}$) and $2p_{3=2}$ ($L_3 = 0.61 \text{ eV}$) core holes.²⁴

The dependence of the m atrix elements on the symmetry of the nal3d state can be summarized as follows: the dominant contributions to the x-ray absorption and to the dichroism, i.e., the di erence of the absorption probabilities for left and right polarized photons, $^2_+$ 2 , come from the transitions to d_{xy} and d_{x² y²} states. The transitions to d_{3z² 1} states are weaker and their contribution to the dichroism is of the opposite sign. Finally, the probabilities to excite a core 2p electron to a d_{zx} or d_{yz} state with either left or right polarized photons are equal so that these transitions do not contribute to the XMCD spectra.

It should be emphasized that the contributions to the dichroism from transitions to nal states with di erent spin projections have opposite signs. Consequently, if majority- and minority-spin d states with particular orbital character are degenerate their contributions to XMCD spectra cancel each other. This is exactly what happens to the Cu d_{x²} y² contribution to the XMCD spectra calculated for the 1 YBCO/1 LMO SL: although the density of the unoccupied Cu d_{x²} y² states is much higher than of the d_{3z²} 1 ones (see Fig. 3) and, consequently, transitions to the L₂ and L₃

In contrast to $d_{x^2-y^2}$, the unoccupied C u d_{3z^2-1} states, which, as explained in Sec. IV B, follow the dispersion of the spin-split M n d_{3z^2-1} bands, are strongly polarized due to the C u d_{3z^2-1} {O B a p_z {M n d_{3z^2-1} hybridization. A sthem inority-spin M n bands are shifted to the energies above 2 eV by the strong exchange interaction within the M n d shell (see Fig. 4), only the majority spin C u $d_{"3z^2-1}$ holes are created in the energy range up to 2 eV above ${\bf "F}_F$. A lihough the number of the $d_{"3z^2-1}$ holes is very sm all, it is su cient to produce the appreciable XM CD signal at C u $L_{2;3}$ edges.

A coording to Tables I and II the matrix elements for the transitions to the nal states of the d_{3z^2-1} character are small. It should be noted, however, that they were derived for the light propagation and magnetization directions parallel to z, i.e., to the tetragonal c axis, whereas the XMCD spectra shown in Fig. 2 were calculated for the experim entalgeom etry¹⁰ in which circularly polarized x-rays propagate along the direction of the M n m agnetization which is parallel to the a axis. The dependence of the XMCD spectra on the light propagation direction can be estim ated by expanding the Cu d_{3z^2-1} orbital in term s of cubic harm onics de ned in the rotated fram e with z^0 jpa:

$$d_{z^2} = \frac{1}{2}d_{z^2}^0 + \frac{p}{3}\frac{1}{2}d_{x^2 y^2}^0 :$$

B ecause of the appearance of the $d_{x^2 \ y^2}^{u}$ contribution in the expansion of the corresponding wave functions, the Cu L_{2;3} XM CD spectra calculated in the z^0 ja geom etry should change sign and become more intense compared to the z jp spectra. This strong orientational dependence of the Cu XM CD spectra was verified by performing calculations for the 1 YBCO/1 LM O SL with M_{Mn} jp. Indeed, due to the weakness of the matrix elements for the transitions to the d_{3z^2-1} -like nal states, the magnitude of the Cu L_{2;3} XM CD spectra calculated in this geometry is smaller and their signs are opposite compared to the spectra shown in Fig.2 which were obtained with the light propagation and M_{Mn} directions parallel to a.

D . Robustness of calculated C u ${\rm L}_{2;3}$ X M C D

The proposed explanation for the strong XM CD at the Cu L_{2;3} edges and robustness of the calculated spectra have been con m ed by a number of additional calculations. As explained in Sec. IV B, the Cu magnetization induced by the proximity to the LM O layer is sensitive to the position of O_{Ba}. This is also true for the XM CD spectra. The increase of the Cu d_{3z²} 1{O_{Ba} p_z hybridization strength with the decrease of the Cu{O_{Ba} distance leads to the growth of the Cu d_{3z²} 1 weight in the M n d_{"3z²} 1-derived bands. Because of the increased number

of Cu d_{"3z^2~1} holes the calculated Cu L_{2;3} XM CD spectra become more intense as O $_{\rm B\,a}$ shifts from M n toward Cu.

As was mentioned above the number of electrons occupying Cu (d⁹) and Mn (d³) 3d shells in the model 1 YBCO/1 LMO SL corresponds to the composition of the La_{1 x}Ca_xMnO₃ layer with x 1. By using the virtual crystal approximation we performed also LSDA calculations with the increased number of valence electrons corresponding to Ca doping of x= 2/3 and 1/3. The added electrons llmainly Cu d_{x² y²} and majority-spin Mn d_{x² y²} bands crossing the Fermi level. Due to the increase of the Fermi ienergy, the Mn d_{"3z²} 1-derived bands m oves closer to "_F but their occupation does not change. As a consequence, the change of the electron count has only a very weak e ect on the Cu XMCD spectra.

Finally, the e ect of the increase of the LMO layer thickness on the Cu L2;3 XMCD spectra was studied by perform ing LSDA calculations for 1 YBCO/n LMO (n=2, 3) superlattices with FM alignment of M n m agnetic moments. A LMO layer in these SL consists of 2 and 3 unit cells of pseudo-cubic LaM nO₃, respectively, i.e., $3 \text{ M nO}_2 + 2 \text{ LaO}$ and $4 \text{ M nO}_2 + 3 \text{ LaO}$ planes. The distance between the M nO $_2$ planes was xed to $c_{LM 0} = 3.94$ A . For ions at the interface the positions obtained from the structure optim ization for the 1 YBCO/1 LMO SL were used. In contrast to the latter, in which both M nO₂ planes are at the interface with the YBCO layer, the thicker superlattices have additionally one (n=2) or two (n=3) \bulk" M nO₂ plane(s). M n ions in these bulk M nO₂ planes are surrounded by an undistorted O₆ octahedron, with all the Mn {O distances of 1.97 A being equal to that in pseudo-cubic LaM nO $_3$.

A ssum ing that the Cu valency does not depend on the LM O layer thickness, the e ective M n d electron count in these SL increases compared to the SL with n=1 and corresponds to C a content of x= 2/3 for n= 2 and x= 1/2 for n=3. In order to separate the e ects of the LM O layer thickness and that of the varying occupation of the M n 3d shell, XM CD calculations for all three SL were perform ed for the same e ective M n d occupation corresponding to x= 2/3.

The magnetic moment of 32 $_{\rm B}$ calculated for the bulk M n ions is higher than for the interfacial ones and close to the LSDA value obtained for pseudo-cubic La_{1 x}Ca_xM nO₃ with the same x = 2/3. The moment of the interfacial M n ions and the magnetization induced on C u remain nearly constant independently of n. As a consequence, the C u L_{2;3} XM C D spectra calculated for the SL with n=1, 2, and 3 are nearly identical, which shows that they are not sensitive to the LM O layer thickness.

E. E ect of electronic correlations

The in uence of electronic correlations on the Cu $L_{2,3}$ XMCD spectra calculated for the 1 YBCO/1 LMO SL was investigated using the rotationally invariant

LSDA+U method.^{21,22} In order to understand the LSDA+U results it is worth recalling that the expression for the additional orbital dependent LSDA+U potential V_i acting on i-th localized orbital become sparticularly simple if non-spherical contributions to the screened C oulom b U and exchange J integrals are neglected:

$$V_{i} = (U \quad J) (\frac{1}{2} \quad n_{i});$$

where n_i is the occupation of the i-th orbital. Thus, the occupied (unoccupied) states are shifted downwards (upwards) by (U = J)=2.

W hen U is applied only to the M n d states its main e ect is to increase the splitting between the occupied majority- $(n_i \quad 0.9)$ and unoccupied minority-spin (n_i)

0:1) M n t_{2g} states. This causes som e increase of M_{M n} from the LSDA value of 2.8 _B to 3.0 _B for U = 3 eV and 3.3 _B for U = 5 eV. The m inority-spin d_{3z²} 1 and d_{x²} y² states with n₁ 0.2 are also shifted to higher energies. The occupation num bers of the m a prity-spin M n d_{3z²} 1 and d_{x²} y² states are close to 0.5 because of their strong hybridization with 0 p states and partial lling of the corresponding bands (see Fig. 4). As a consequence the m a prity-spin M n d_{3z²} 1 and ost una ected by U. Hence, the Cu L_{2;3} XM CD spectra, which are mostly determined by the Cu d_{"3z²} 1 M n d_{"3z²} 1 hybridization, show weak dependence on U applied to the M n d states.

LSDA+U calculations with $U = 7.5 \text{ eV}_{p}$ acting within the Cu 3d shell were performed for an 2a 2a c unit cell of the 1 YBCO/1 LMO SL. In this enlarged cell two Cu sites in each CuO₂ plane become inequivalent which enables calculations with antiferrom agnetic (AFM) ordering of Cu moments. The calculations were performed for a collinear magnetic arrangement with both Cu and Mn magnetic moments parallel to the tetragonala axis.

LSDA calculations for the double cell converge to the sam em agnetic solution which was obtained for the single cell and is characterized by FM ordering of M n m om ents and a tiny FM m om ent induced across the interface on Cu ions. However, when U = 7.5 eV is applied to the Cu d states and AFM ordering within a CuO₂ plane is allowed, Cu ions acquire a spin m om ent of 0.4 _{B} . The m om ent appears due to splitting of the partially occupied m a jority-and m inority-spin Cu d_{x² y²} states by the onsite C oulom b repulsion. The other Cu d states, including d_{3z² 1} ones, which are completely led already in LSDA calculations, are shifted 3 eV dow nwards to the bottom of 0 p bands.

Because of the proximity to FM M nO₂ planes the Cu m om ents which are parallel (0.44 $_{\rm B}$) and antiparallel (0.45 $_{\rm B}$) to M $_{\rm M\,n}$ are slightly di erent, with the difference being comparable to the LSDA m om ent induced in the Cu d_{3z^2} $_1$ chanel by the Cu d_{3z^2} $_1$ {O $_{\rm Ba}$ pz {M n d_{3z^2} $_1$ hybridization as discussed in Sec. IV B. A lthough the hybridization causes a sm all (0.01 $_{\rm B}$) di erence in the m om ents of two inequivalent M n ions which have Cu



FIG. 8: (Color online) Cu $L_{2;3}$ XMCD spectra calculated using the LSDA+U method with U=7.5 eV applied to the Cu 3d states for Cu ions with the magnetic moment parallel (dashed line) and antiparallel (dash-dotted line) to M_{Mn}. The averaged spectrum is plotted by solid line. For comparison, the LSDA spectrum from Fig. 2 is also shown (dotted line). The spectra are plotted relative to the L_3 absorption edge.

neighbors with either parallel or antiparallel m agnetization, the calculated M $_{\rm M~n}$ of 2.75 $_{\rm B}$ and 2.76 $_{\rm B}$ are very close to the LSDA value.

Figure 8 shows that the spin-polarization of the Cu d_{x^2} v^2 states a ects strongly the L_{2;3} XMCD spectra calculated for Cu ions with the moment parallel (Cu,) and antiparallel (Cu_#) to M_{Mn}. As the majority-and m inority-spin Cu d_{x^2} v^2 states are split by the on-site C oulom b repulsion, transitions to the $d_{x^2 \ y^2}$ nal states give a substantial contribution to the dichroism . In the geom etry with the x-ray propagation and m agnetization directions parallel to the c axis the contribution of the $d_{x^2 \ y^2}$ states would be the dom inant one and the Cu_ and $Cu_{\#} XM CD$ spectra would be of the same shape but opposite signs. Since the calculations were performed with M $_{\rm C\,u}$ ja the matrix elements for the transitions to the $d_{x^2 \ y^2}$ states are strongly reduced and their contribution is comparable to the d_{3z^2} 1 one, which is induced by the hybridization with FM ordered Mn and, thus, is of the same sign for both Cuions. As a result, the shapes of the Cu, and Cu, L3 XMCD spectra are different (Fig. 8), whereas the L_2 spectra are of the same sign although the Cu, and Cu, moments are antiparallel. Nevertheless, when the individual Cu, and Cu, spectra are averaged, the net Cu XMCD spectrum becomes sim ilar to the LSDA spectrum calculated for the single 1 YBCO/1 LMO cell, which is also shown in Fig. 8 for com parison sake. The magnitude of the averaged spectrum is two times smaller, which may be explained by decrease in the weight of the Cu d_{3z^2} 1 states in the m inority-spin M n d_{3z^2} 1 bands caused by their downward shift in the LSDA+U calculations. Hence, even in the presence of the sizable Cum om ent the dichroic signal at the C u L_{2,3} edges is still governed by the spinpolarization of the Cu $d_{3z^2 \ 1}$ states induced by the Cu $d_{3z^2 \ 1}$ {M n $d_{3z^2 \ 1}$ hybridization via the p states of interfacialO $_{Ba}$ ions.

Note, that if the AFM aligned Cu d_{x^2} $_{y^2}$ moments were oriented perpendicular to the M n m agnetization and, consequently, to the x-ray propagation direction they would not contribute to the dichroism, which also in this case would be determ ined by the transitions to the Cu d_{3z^2-1} states.

V. CONCLUSIONS

W e studied the electronic structure, XAS and XMCD spectra of YBCO /LMO superlattices by m eans of the ab initio PAW and fully-relativistic spin-polarized LMTO m ethods.

Our results contradict to the orbital reconstruction model, proposed in Ref.11 in order to explain weak XLD at the Cu $L_{2;3}$ edges measured in the TEY mode. In all the calculations performed in the present work the number of Cu d_{3z^2-1} holes is significantly smaller than the number of $d_{x^2-y^2}$ ones. The large difference in the number of d_{3z^2-1} and $d_{x^2-y^2}$ holes causes strong linear dichroism of the calculated Cu $L_{2;3}$ XAS.

On the other hand, the LSDA calculations reproduce very well the experimental Cu $L_{2,3}$ XM CD spectra of Ref. 10. We have shown that the theoretical XM CD spectra are proportional to the di erence of the densities of unoccupied majority-and minority-spin Cu d_{3z^2-1} states. A lthough the Cu d_{3z^2-1} -derived bands lie 2 eV below the Ferm i level, a small num ber of d_{3z^2-1} holes is created because of the Cu d_{3z^2-1} (O Ba p_z (M n d_{3z^2-1} hybridization, which induces a small Cu m agnetic moment opposite to the moment of M n ions. How ever, this tiny num ber of d_{3z^2-1} holes is su cient to produce substantial XM CD at the Cu $L_{2,3}$ edges.

The calculated Cu L_{2;3} XMCD spectra are very robust: they are not sensitive to Ca doping of the La_{1 x}Ca_xMnO₃ layer simulated using the virtual crystal approximation, nor to the LCMO layer thickness. Remarkably, the shape of the XMCD spectra obtained from LSDA+U calculations does not change much even when U = 7.5 eV is applied to the Cu d states and AFM order with the Cu moment of 0.4 B is induced in the CuO₂ plane.

A cknow ledgm ents

A uthors are thankful to G.K haliullin, C.Bernhard, H.-U.Habern eier, and J.Chakhalian for helpful discussions. V N.Antonov gratefully acknow ledges the hospitality at M ax-P lanck-Institut fur Festkorperforschung in Stuttgart during his stay there. This work was partially supported by Science and Technology Center in Ukraine (STCU), Project No. 4930.

- ¹ Z.Sefrioui, M.Varela, V.Pena, D.Arias, C.Leon, J.Santam aria, and J.E.Villegas, Appl. Phys. Lett. 81, 4568 (2002).
- ² M.Varela, A.R.L.aand S.J.Pennycook, Z.Sefrioui, and J.Santam aria, Solid State Electronics 47, 2245 (2003).
- ³ Z. Sefrioui, D. Arias, V. Pena, J. E. Villegas, M. Varela, P. Prieto, C. Leon, J. L. Martinez, and J. Santamaria, Phys. Rev. B 67, 214511 (2003).
- ⁴ T. Holden, H.-U. Habermeier, G. Cristiani, A. Golnik, A. Boris, A. Pimenov, J. Hum licek, O. I. Lebedev, G. van Tendeloo, B. Keimer, and C. Bernhard, Phys. Rev. B 69, 064505 (2004).
- ⁵ N.Haberkom, J.Guim pel, M.Sirena, L.B.Steren, W.Saldarriaga, E.Baca, and M.E.Gom ez, Appl.Phys.Lett.84, 3927 (2004).
- ⁶ J. Stahn, J. Chakhalian, C. Niederm ayer, J. Hoppler, T. Gutberlet, J. Voigt, F. Treubel, H.-U. Haberm eier, G. Cristiani, B. Keimer, and C. Bernhard, Phys. Rev. B 71, 140509 (R) (2005).
- ⁷ J. Albrecht, M. D jupmyr, S. Soltan, H.-U. Habern eier, M. R. Connolly, and S. J. Bending, New J. Phys. 9, 379 (2007).
- ⁸ V. Pena, T. Gredig, J. Santamaria, and I. K. Schuller, Phys. Rev. Lett. 97, 177005 (2006).
- ⁹ J. W. Freelanda, J. Chakhalianb, H.-U. Habern eier, G. Cristiani, and B. Keimer, Appl. Phys. Lett. 90, 242502 (2007).
- ¹⁰ J. Chakhalian, J. W. Freeland, G. Srajer, J. Strem pfer, G. Khaliullin, J. C. Cezar, T. Charlton, R. Dalgliesh, C. B. G. Cristiani, H.-U. Haberm eier, and B. Keimer, Nature Physics 2, 244 (2006).
- ¹¹ J.Chakhalian, J.W. Freeland, H.-U.Haberm eier, G.Cristiani, G.Khaliullin, M. van Veenendaal, and B.Keimer, Science 318, 1114 (2007).
- ¹² Q.Si, Phys. Rev. Lett. 78, 1767 (1997).

- ¹³ J.R.J.Soulen, J.M.Byers, M.S.Osofsky, B.Nadgomy, T.Ambrose, S.Cheng, P.R.Broussard, C.T.Tanaka, J.Nowak, J.S.Moodera, A.Barry, and J.M.D.Coey, Science 282, 85 (1998).
- ¹⁴ S.Soltan, J.A Drecht, G.Cristani, and H.-U.Habern eier, Phys. status solidi C 1, 1836 (2004).
- ¹⁵ P.E.Blochl, Phys. Rev. B 50, 17953 (1994).
- ¹⁶ J. P. Perdew, K. Burke, and M. Emzerhof, Phys. Rev. Lett. 78, 1396 (1997).
- ¹⁷ G.K resse and D. Joubert, Phys. Rev. B 59, 1758 (1999).
- ¹⁸ O.K.Andersen, Phys. Rev.B 12, 3060 (1975).
- ¹⁹ V.N.Antonov, A.Y.Perlov, A.P.Shpak, and A.N. Yaresko, J.M agn.M agn.M ater 146, 205 (1995).
- ²⁰ A. Yaresko, A. Perlov, V. Antonov, and B. Harmon, in Magnetism: A Synchrotron Radiation Approach, edited by E. Beaurepaire, H. Bulou, F. Scheurer, and J.-P. Kappler (Springer, Berlin / Heidelberg, 2006), vol. 697 of Lecture Notes in Physics, pp.121{141.
- ²¹ A. I. Liechtenstein, V. I. Anisim ov, and J. Zaanen, Phys. Rev. B 52, R5467 (1995).
- ²² A.N.Yaresko, V.N.Antonov, and P.Fulde, Phys. Rev. B 67, 155103 (2003).
- ²³ M.T.Czyzyk and G.A.Sawatzky, Phys.Rev.B 49, 14211 (1994).
- ²⁴ J.L.Campbell and T.Parr, At.Data Nucl.Data Tables 77,1 (2001).
- ²⁵ S. O kam oto and A. M illis, Nature (London) 428, 630 (2004).
- ²⁶ J.Zaanen, O.Jepsen, O.G unnarsson, A.T.Paxton, O.K. Andersen, and A.Svane, Physica C 153, 1636 (1988).
- ²⁷ V.Antonov, B.Harmon, and A.Yaresko, Electronic structure and magneto-optical properties of solids (K luwer A cadem ic Publishers, D ordrecht, Boston, London, 2004).