

A dam s and O lm sted Reply: Wang [1] makes the following points about our Letter [2]: (1) He infers that, \contrary to its title, shear banding [in [2]] emerged from monotonic curves only if there was a stress gradient", and he points out that nonquiescent relaxation was found (experimentally) after step strain in geometries without a stress gradient [3]. (2) He disagrees with the values of the parameters we used. (3) In some recent experiments the flow was homogeneous after cessation of step strain, and only subsequently developed nonquiescent macroscopic motion [3]. We only showed step strains that developed an inhomogeneity before cessation of flow, as in [4].

(1) As our title stated [2], we showed that a fluid with a monotonic constitutive curve based on Doi-Edwards (DE) theory can have signatures similar to shear banding. These signatures arise from a stress gradient (e.g. the bowed steady state velocity profile obtained in the stress gradient of a cone and plate rheometer [5] or transient banding-like profiles during startup). Flat geometries can have transient banding-like signatures: e.g. two clearly defined bands of shear rates during large amplitude oscillatory shear (LAOS) [2, 6], or inhomogeneous banding-like transients during startup flows in presence of inhomogeneous spatial fluctuations (noise) (Fig.1) [2].




FIG. 1: (color online) Startup transients for (left) a cone angle of 4 ($q = 2 \cdot 10^{-3}$); and (right) a flat geometry with noisy initial polymer shear stress $\sigma_{xy}(0)$ of a few percent, with $\tau_d = 14.8$, $\tau_R = 0.728$ and $\tau_e = 10^{-5}$, and $\tau_d = \tau_R = 10^3$.

(2) Our parameters were matched to experiment, for a nonlinear model in which the parameters τ_d and τ_R roughly correspond to their rigorously defined counterparts in linear rheology. Because we use (the best available) crude nonlinear theory, the parameters do not correspond precisely. We used $\tau_e = (G_d)' \cdot 10^{-5}$ based a plateau modulus $G' = 3\text{ kPa}$, reptation time $\tau_d = 20\text{ s}$, and solvent viscosity $\eta = 1\text{ Pa s}$ [7]. Although $\tau_d = \tau_R = 10^3$ implies too many entanglements, it fits the experimen-

tal nonlinear rheology well [5]. This inconsistency is an unsatisfactory feature of current theory.

(3) The step strain results in [2] should be compared with [4]-(Fig. 5), where the velocity profile became inhomogeneous before cessation. Fig. 2 shows a calculation in which inhomogeneities develop only after cessation of flow, during a strong recoil. This is for startup in a flat geometry, with noisy initial conditions, and resembles [4]-(Fig. 3) if there were no experimental wall slip.

Wang's newest experiments show dramatic rupture and internal fracture, despite a homogeneous velocity before cessation [3] (similar fracture planes could be inter-




FIG. 2: Recoil displacement (b) at $t = 0.08 \tau_d$ after cessation of homogeneous shear (a) at $t_{\text{stop}} = 0.0375 \tau_d$ with $\tau_d = 80$, $q = 3$ for the Rolie-Poly model with $\tau_e = 0.728$, $\tau_e = 10^{-5}$ and $q = 0$, with initial noise.

preted in [8]-(Fig. 3f), but in a cone-and-plate geometry; moreover, those data are also consistent with wall slip and simple recoil). Our calculations (Fig. 2) go some way towards modelling this phenomenon, but do not capture this rupture, and have not yet been adequately modified to incorporate slip. It remains a strong challenge to distinguish which experimental features are captured by tube models, and which (e.g. rupture) require new physical insight. One suggestion is the "elastic yielding" in [1] which may be similar to modifying the DE model to incorporate the instability of the spatial distribution of entanglements [9]. In fact, the instability in the DE model occurs when the shear rate greatly exceeds the reptation time, which is one criterion for elastic yielding postulated in [1].

J.M. Adams¹ and P.D. Olmsted²

¹Department of Physics, University of Surrey,
Guildford, GU2 7XH, United Kingdom

²School of Physics & Astronomy, University of Leeds
Leeds, LS2 9JT, United Kingdom

Received 9 October 2009

DOI: 10.1103/PhysRevLett.103.219802

PACS numbers: 61.25.he, 83.50.Ax

[1] S.-Q. Wang, Phys. Rev. Lett. XX, XXX (2009).

[2] J.M. Adams and P.D. Olmsted, Phys. Rev. Lett. 102, 067801 (2009).

[3] P.E. Boukany, S.-Q. Wang, and X.R. Wang, Macromolecules 42, 6261 (2009).

[4] S.-Q. Wang, et al., Phys. Rev. Lett. 97, 187801 (2006).

[5] P. Tapadia and S.-Q. Wang, Phys. Rev. Lett. 96, 016001 (2006).

[6] a) Y.T. Hu, et al., J. Rheol. 51, 275 (2007); b) P. Tapadia,

S. Ravindranath, and S.-Q. Wang, Phys. Rev. Lett. 96, 196001 (2006); c) L. Zhou, et al., Proceedings of the XVth International Congress on Rheology p.189 (Monterey, CA, AIP, 2008).

[7] S. Ravindranath and S.-Q. Wang, J. Rheol. 52, 957 (2008).

[8] S. Ravindranath and S.-Q. Wang, Macromolecules 40, 8031 (2007).

[9] P.G. de Gennes, Eur. Phys. J. E 23, 3 (2007).