# Evidence for two-gap superconductivity in the non-centrosymmetric compound LaNiC<sub>2</sub>

J. Chen,<sup>1</sup> J. L. Zhang,<sup>1,2</sup> L. Jiao,<sup>1</sup> Y. Chen,<sup>1</sup> L. Yang,<sup>1</sup> M. Nicklas,<sup>2</sup> F. Steglich,<sup>2</sup> and H. Q. Yuan<sup>1,\*</sup>

<sup>1</sup>Department of Physics and Center for Correlated Matter, Zhejiang University, Hangzhou, Zhejiang 310027, China

<sup>2</sup>Max Planck Institute for Chemical Physics of Solids, D-01187 Dresden, Germany

(Dated: January 24, 2022)

We study the superconducting properties of the non-centrosymmetric compound LaNiC<sub>2</sub> by measuring the London penetration depth  $\Delta\lambda(T)$ , the specific heat C(T, B) and the electrical resistivity  $\rho(T, B)$ . Both  $\Delta\lambda(T)$  and the electronic specific heat  $C_e(T)$  exhibit exponential behavior at low temperatures and can be described in terms of a phenomenological two-gap BCS model. The residual Sommerfeld coefficient in the superconducting state,  $\gamma_0(B)$ , shows a fast increase at low fields and then an eventual saturation with increasing magnetic field. A pronounced upturn curvature is observed in the upper critical field  $B_{c2}(T)$  near  $T_c$ . All the experimental observations support the existence of two-gap superconductivity in LaNiC<sub>2</sub>.

PACS numbers: 74.70.Wz; 74.20.Rp; 74.25.Op

## I. INTRODUCTION

The spatial-inversion and time-reversal symmetries of a superconductor (SC) may impose important constraints on the pairing states. Among the SCs discovered in the past, most of them possess a center of inversion symmetry. In this case, the Cooper pairs are either in an even-parity spinsinglet or odd-parity spin-triplet pairing state, constrained by the Pauli principle and parity conservation.<sup>1,2</sup> However, the tie between spatial symmetry and the Cooper-pair spins is violated in SCs lacking spatial inversion symmetry.<sup>3–7</sup> In the non-centrosymmetric (NCS) SCs, an asymmetric electrical field gradient may yield an antisymmetric spin-orbit coupling (ASOC), which splits the Fermi surface into two subsurfaces of different spin helicities, with pairing allowed both across each one of the subsurfaces and between the two. The parity operator is then no longer a well-defined symmetry of the crystal, and allows the admixture of spin-singlet and spintriplet pairing states within the same orbital channel.

NCS superconductivity has been intensively studied in a few heavy fermion compounds, e.g., CePt<sub>3</sub>Si,<sup>8-11</sup> CeRhSi<sub>3</sub>,<sup>12</sup> CeIrSi<sub>3</sub><sup>13</sup> and UIr.<sup>14</sup> In these systems, the nature of superconductivity is complicated by its coexistence with magnetism and the lack of inversion symmetry; both effects may give rise to unconventional superconductivity. It is, therefore, highly desired to search for weakly correlated, non-magnetic NCS SCs to study the pure effect of ASOC on superconductivity. It has been demonstrated that, in  $Li_2(Pd_{1-x}Pt_x)_3B$ , the spin-singlet and spin-triplet order parameters can add constructively and destructively<sup>15</sup>. The mixing ratio in this compound appears to be tunable by the strength of ASOC;<sup>15</sup>  $Li_2Pd_3B$  behaves like a BCS SC, but  $Li_2Pt_3B$  shows evidence of spin-triplet pairing state<sup>15-17</sup> attributed to an enhanced ASOC.<sup>18</sup> Recently, non-BCS-like superconductivity with a possible nodal gap structure at low temperatures was observed in  $Y_2C_3^{19}$ , in spite of its relatively weak ASOC. On the other hand, evidence of multi-gap superconductivity was shown in  $La_2C_3^{20}$  and  $Mg_{10}Ir_{19}B_{16}^{21}$ . The diversity of the superconducting states in the NCS SCs requires more systematic investigations in order to reach a unified picture.

LaNiC<sub>2</sub>, a simple metallic NCS SC,<sup>22</sup> has recently drawn considerable attention. However, the order parameter of this compound remains highly controversial. Measurements of specific heat<sup>23</sup> and NQR-1/ $T_1^{24}$  suggested that LaNiC<sub>2</sub> is a conventional BCS SC which is further supported by theoretical calculations.<sup>25</sup> On the other hand, evidence of possible nodal superconductivity was inferred from the recent penetration depth which follows  $\Delta \lambda(T) \sim T^n$   $(n \ge 2)^{26}$  and also from the early measurements of specific heat by W. H. Lee, et al.<sup>27</sup> Unconventional characteristics were also revealed from  $\mu$ SR experiments in which the absence of time-reversal symmetry was indicated.<sup>28,29</sup> In order to elucidate the pairing state of LaNiC<sub>2</sub> here, we present a systematic study of the penetration depth  $\Delta \lambda(T)$ , the electronic specific heat  $C_e(T, B)$  and the electrical resistivity  $\rho(T, B)$  on high quality polycrystalline samples. We found that the temperature dependence of both  $\Delta\lambda(T)$  and  $C_e(T)$  can be well described by a phenomenological two-gap BCS model. The residual Sommerfeld coefficient.  $\gamma_0(B)$ , increases fast at low fields and eventually saturates with increasing magnetic field. Furthermore, the upper critical field  $B_{c2}(T)$  shows an upward curvature near  $T_c$ . All these observations resemble those of MgB<sub>2</sub>,<sup>30–33</sup> strongly supporting a two-gap SC in LaNiC<sub>2</sub>.

### **II. EXPERIMENTAL METHODS**

Polycrystalline LaNiC<sub>2</sub> was synthesized by arc melting. A Ti button was used as an oxygen getter. Appropriate amounts of the constituent elements (3N-purity La, 2N-purity Ni and 3N-purity graphite) were pressed into a disk before arc-melting. The ingot was inverted and remelted for several times to ensure sample homogeneity. The derived ingot, with a negligible weight loss, was annealed at 1050°C in a vacuum-sealed quartz tube for 7 days, and then quenched into water at room temperature.

A small portion of the ingot was ground into fine powders for X-ray diffraction (XRD) measurements on a X'Pert PRO diffractometer (Cu K radiation) in the Bragg-Brentano geometry. Measurements of the electrical resistivity, specific heat and magnetization were performed in a 9T-PPMS and a 5T-MPMS (Quantum Design), respectively. Precise measurements of the London penetration depth  $\Delta\lambda(T)$  were performed utilizing a tunnel diode oscillator (TDO) technique<sup>34</sup> at a frequency of 7MHz down to 0.37K in a <sup>3</sup>He cryostat.

### **III. RESULTS AND DISCUSSION**

#### A. Sample characterizations

Fig.1 shows the XRD patterns of LaNiC<sub>2</sub> which identify it as a single phase. The Rietveld refinement confirmed an orthorhombic Amm2 structure (No. 38). The atoms of Ni (2b) and C (4e) are alternatively stacked on the NiC<sub>2</sub> plane but lose the inversion symmetry, as shown in the inset of Fig.1. The derived lattice parameters are given as a=3.9599Å, b=4.5636Å and c=6.2031Å, in good agreement with those reported in literature.<sup>22</sup>

Fig.2(a) presents the temperature dependence of the electrical resistivity  $\rho(T)$  between 2K and 300K at B=0, which shows simple metallic behavior above  $T_c$ . Observations of a large residual resistivity ratio (RRR=  $\rho_{300K}/\rho_{4K} \approx 26$ ) and a sharp superconducting transition  $(T_c^{\rho} \approx 3.5 \text{K})$  suggest a high quality of our samples. Fig.2(b) shows the temperature dependence of the specific heat C(T)/T at B=0 and the zerofield-cooling (ZFC) magnetization M(T) (B=10 Oe), respectively. A pronounced superconducting transition seen in both C(T)/T and M(T) confirms the bulk superconductivity in LaNiC<sub>2</sub>. The bulk  $T_c$ , derived from the specific heat  $(T_c^{C_p} = 2.75\text{K})$  and the magnetization  $(T_c^M = 3.1\text{K})$ , are slightly lower than the resistive  $T_c^{\rho}$ , which is likely due to the residual sample inhomogeneity. It is noted that the magnetization M(T) exhibits temperature-independent Pauli-paramagnetic behavior above  $T_c$ , ruling out any visible magnetic impurity in our samples. Furthermore, the above physical quantities were measured on different samples cut from the same batch; the con-





FIG. 2: (Color online) Temperature dependence of the electrical resistivity  $\rho(T)$  (a), specific heat C(T)/T (b, left axis) and dc magnetization M(T) (b, right axis) for LaNiC<sub>2</sub>. The electrical resistivity and specific heat are measured at zero field, and the magnetization is measured at 100e (ZFC).

sistent experimental results and fitting parameters, as shown below, again indicate a good sample quality. Based on the RRR value and the width of the superconducting transition, our samples have a quality better or compatible with the best samples reported in literature.<sup>26,27</sup> The small value of  $\gamma_n$ = 7.7mJ/molK<sup>2</sup> above  $T_c$  indicates the absence of strong electronic correlations in LaNiC<sub>2</sub>.

#### B. London penetration depth

The London penetration depth is an important superconducting parameter. The TDO-based technique can accurately measure the temperature dependence of the resonant frequency shift  $\Delta f(T)$ , which is proportional to the changes of the penetration depth, i.e.,  $\Delta\lambda(T) = G \cdot \Delta f(T)$ . Here the G factor is a constant which is solely determined by the sample and coil geometries.<sup>34</sup> Fig.3(a) presents the temperature dependence of the penetration depth  $\Delta\lambda(T)$  for LaNiC<sub>2</sub>, where G= 11Å/Hz. In the left inset,  $\Delta\lambda(T)$  is plotted over the full temperature range of our measurement from which a sharp superconducting transition can be seen. In the main figure of Fig.3(a), we show  $\Delta\lambda(T)$  at low temperatures, along with the fittings of a quadratic temperature dependence (dashed line), a conventional BCS model (dotted line) and a two-gap BCS model (solid line). For an isotropic one-gap BCS model, the penetration depth at  $T \ll T_c$  is given by:

$$\Delta\lambda(T) \approx \lambda_0 \sqrt{\frac{\pi\Delta_0}{2T}} e^{-\frac{\Delta_0}{T}},\tag{1}$$

FIG. 1: (Color online) The XRD patterns and crystal structure of  $LaNiC_2$ . Short vertical bars indicate the calculated reflection positions.

where  $\Delta_0$  is the energy gap at T=0;  $\Delta_0=1.76T_c$  for the conventional BCS SCs.

One can see from Fig.3(a) that the penetration depth at low temperatures is not well described in terms of either the



FIG. 3: (Color online) (a) Temperature dependence of the penetration depth  $\Delta\lambda(T)$  at low temperatures for LaNiC<sub>2</sub>. The left inset shows  $\Delta\lambda(T)$  in the full temperature range of our measurement. The right inset shows  $\Delta\lambda(T)$  vs.  $T^{3.7}$  in the temperature range of  $0.35 \text{K} \leq T \leq$  1K. (b) Temperature dependence of the superfluid density  $\rho_s(T) = [\lambda_0/\lambda(T)]^2$ . The inset shows  $\rho_s(T)$  from Ref.26 with  $\lambda_0 = 1230$ Å and 3940Å, together with a fit of a two-gap BCS model (solid line). In the main plots, the solid and dotted lines represent fittings of a two-gap and conventional BCS model, respectively. The dashed line in (a) shows a fit of  $\Delta\lambda(T) \sim T^2$  to the experimental data. The dashed-dotted lines in (b) present the respective contributions to  $\rho_s(T)$  from the two superconducting gaps of  $\Delta^1$  and  $\Delta^2$ .

conventional BCS model or the quadratic temperature dependence; the latter is expected for superconductors with point nodes. Instead, it can be fitted equally well by a power-law dependence of  $\Delta\lambda(T) \propto T^{3.7}$  (right inset of Fig.3(a)), or by a twogap BCS model. Practically, the penetration depth of a twogap SC can be fitted by a power-law temperature dependence with a large exponent of n>3, whose value may depend on the fitting temperature region. In the following, we will analyze the penetration depth and its corresponding superfluid density,  $\rho_s(T)$ , in terms of the phenomenological two-gap BCS model, which is further supported by the specific heat and the upper critical field (see below).

According to the phenomenological two-gap BCS model, which has been successfully applied to MgB<sub>2</sub>,<sup>30</sup> the superfluid density  $\rho_s(T)$  can be expressed as:

$$\rho_s(T) = x \rho_s(\Delta^1, T) + (1 - x) \rho_s(\Delta^2, T),$$
(2)

where x is the relative weight for  $\Delta^1$ . The normalized superfluid density for each band is given by

$$\rho_s(\Delta, T) = 1 - \frac{2}{T} \int_0^\infty f(\epsilon, T) \cdot [1 - f(\epsilon, T)] d\epsilon, \qquad (3)$$

where  $f(\epsilon, T) = (1 + e^{\sqrt{\epsilon^2 + \Delta^2(T)}/T})^{-1}$  is the Fermi distribution function. Here we adopt the following temperature dependence of the gap function:<sup>35</sup>

$$\Delta(T) = \Delta_0 \tanh\left[\frac{\pi T_c}{\Delta_0} \sqrt{a \frac{\Delta C}{C} (\frac{T_c}{T} - 1)}\right],\tag{4}$$

where  $\frac{\Delta C}{C}$  denotes the specific heat jump at  $T_c$  and a = 2/3.

In Fig.3(b), we plot the superfluid density  $\rho_s(T)$  converted from the penetration depth by  $\rho_s(T) = [\lambda_0/\lambda(T)]^2$ , where  $\lambda(T) = \lambda_0 + \Delta \lambda(T)$ . The zero-temperature penetration depth,  $\lambda_0 \approx 3940$ Å, is estimated from  $\lambda_0 = \frac{1}{\Delta_0 T_c} \sqrt{\frac{\Phi_0 B_{c2}(0)}{24\gamma_n}}$ , as derived from both the BCS and Ginzburg-Landau theories for a type-II SC.<sup>35</sup> Here we take the experimental values of  $T_c = 2.75$ K,  $B_{c2}^{C_p}(0) \approx 0.48$ T and  $\gamma_n = 7.7$ mJ/molK<sup>2</sup> from the specific heat (see below), and  $\Phi_0$  is the flux quantum. Indeed, both the penetration depth  $\Delta\lambda(T)$  and the superfluid density  $\rho_s(T)$  can be well described by the two-gap BCS model (solid lines), from which we obtained the gap parameters of  $\Delta_0^1 = 2.0T_c$ ,  $\Delta_0^2 = 1.0T_c$  and x=0.8.  $T_c = 2.7$ K is obtained from the best fit of the superfluid density which is consistent with the penetration depth drop. The individual contribution to the total superfluid density  $\rho_s(T)$  from the respective order parameters  $\Delta^1$  and  $\Delta^2$ is shown in Fig.3(b), from which one can see that the large gap has a dominant contribution. For comparison, we replot  $\rho_s(T)$  from Ref.26 in the inset of Fig.3(b) which are converted from the penetration depth data by using  $\lambda_0 = 1230$ Å (from Ref.26) and 3940Å (in this study). The superfluid density  $\rho_s(T)$  from Ref.26 is in resonable agreement with our results if  $\lambda_0 = 3940$ Å is used. Furthermore, one can also fit its superfluid density  $\rho_s(T)$  by the two-gap BCS model at temperature above 0.5K. The derived parameters of  $\Delta_0^1 = 1.9T_c$ ,  $\Delta_0^2 = 0.7T_c$ and x=0.75 are consistent with our results. As a first approximation, two-gap-like superconductivity is expected in NCS SCs with a moderate ASOC strength, in which the spin degenerate bands are split by the ASOC, but the triplet component is not yet dominant. Nevertheless, it is still possible that a weak linear term of  $\Delta \lambda(T)$  may develop at very low temperatures as seen in  $Y_2C_3$ .<sup>19</sup> At present, we cannot exclude such a possibility in LaNiC<sub>2</sub> as argued in Ref.26. More precise measurements of the penetration depth at lower temperatures are desired to resolve this issue.

### C. Specific heat

In the upper inset of Fig.4, we plot the total specific heat C(T) as a function of temperature for LaNiC<sub>2</sub>, which was obtained after subtracting the addenda contributions from the raw data. At temperatures above  $T_c$  ( $3.5K \le T \le 20K$ ), C(T) follows a polynomial expansion of  $C(T) = \gamma_n T + B_3 T^3 + B_5 T^5 + B_7 T^7$ , in which  $C_e = \gamma_n T$  and  $C_{ph} = B_3 T^3 + B_5 T^5 + B_7 T^7$  represent the electronic and phonon contributions, respectively. This yields the Sommerfeld coefficient in the normal state,  $\gamma_n = 7.7mJ/molK^2$ , and the Debye temperature  $\Theta_D = 450K$ , the latter being derived from  $B_3 = N\pi^4 R \Theta_D^{-3} 12/5$ , where R = 8.314J/molK, N=4 and  $B_3 = 0.085mJ/molK^4$ . The specific heat jump at  $T_c$ , i.e.,  $\Delta C/\gamma_n T_c = 1.05$ , is lower than the BCS value of 1.43, which might arise from the multi-gap structure as seen in MgB<sub>2</sub> or the gap anisotropy.<sup>32</sup>

In the superconducting state, the total heat capacity C is the sum of a *B*-dependent electronic contribution  $C_e$ , a *B*independent lattice contribution  $C_{ph}$  and a small *B*-dependent Schottky contribution  $C_{Sch}$ . We obtained the electronic spe-



FIG. 4: (Color online) Temperature dependence of the specific heat at zero field for LaNiC<sub>2</sub>. The upper inset shows the total specific heat C(T)/T and its polynomial fitting of  $C(T) = \gamma_n T + B_3 T^3 + B_5 T^5 + B_7 T^7$ . The main figure plots the electronic specific heat  $C_e(T)/T$  after subtracting the phonon contributions. The solid and dashed lines present fittings of a two-gap and conventional BCS model, respectively. The lower inset expands the low-*T* section of our work and also the data from Ref.27.

cific heat  $C_e$  by subtracting the *B*-independent phonon contribution  $C_{ph}$  and *B*-dependent  $C_{Sch}$  using the following two methods. The first one is to directly subtract the phonon contribution of  $C_{ph}$  from the total heat capacity by

$$C_e(B,T) = C(B,T) - C_{ph}(T).$$
 (5)

In the second method, we calculate the electronic specific heat  $C_e$  in the superconducting state by using the reference value at B = 1T where superconductivity is suppressed, i.e.,<sup>32</sup>

$$C_e(B,T) = C(B,T) - C(1T,T) + \gamma_n(1T) \cdot T.$$
 (6)

Indeed, both methods give nearly identical results of  $C_e$  at  $T < T_c$ , indicating that the *B*-dependent  $C_{Sch}$  is negligible in the temperature and magnetic field ranges of our measurements. In the following, we will present the electronic specific heat  $C_e(T)$  derived from Eq.(5).

In Fig.4, we plot the electronic specific heat  $C_e(T)/T$  of LaNiC<sub>2</sub> at zero field, which shows an exponential-type behavior at low temperatures, together with the fittings of conventional and two-gap BCS models. For a system of independent fermion quasiparticles, the entropy, *S*, can be calculated by<sup>31</sup>

$$\frac{S(\Delta, T)}{\gamma_n T_c} = -\frac{6}{\pi^2} \frac{\Delta(T)}{T_c} \int_0^\infty f(\epsilon, T) \cdot \ln f(\epsilon, T) + [1 - f(\epsilon, T)] \cdot \ln[1 - f(\epsilon, T)] d\epsilon.$$
(7)

For a two-gap BCS SC, the entropy expression can be generalized as follows:<sup>31</sup>

$$S(T) = xS(\Delta^{1}, T) + (1 - x)S(\Delta^{2}, T).$$
 (8)



FIG. 5: (Color online) Temperature dependence of the electronic specific heat  $C_e(T)/T$  at various magnetic fields for LaNiC<sub>2</sub>. The dashed horizontal line represents  $\gamma_n$ . The magnetic field increases along the arrow direction. The inset shows the electronic specific heat  $C_e(T)/T$ at magnetic fields near  $B_{c2}(0)$ .

Differentiation of Eq.(8) gives the total electronic specific heat  $C_e$  in the superconducting state by  $C_e(T) = T dS(T)/dT$ . The specific heat data of LaNiC<sub>2</sub> is fitted over a temperature range of 0.35-1.5K. The two-gap BCS model (solid line) fits much better than the conventional BCS model (dashed line), as clearly seen in the lower inset of Fig.4. The former fitting gives the parameters of  $\Delta_0^1 = 2.3T_c$ ,  $\Delta_0^2 = 1.25T_c$  and x=0.75for  $\Delta_0^1$ , which are close to those obtained from the superfluid density  $\rho_s(T)$ . For comparison, we also plot the specific heat data derived in Ref.27 with our results in the lower inset of Fig.4. Remarkably, these two sets of data are exactly the same. It is noted that the original fits of  $C_e \sim T^3$  from Ref.27 was at relatively high temperatures, and a deviation exists in the low temperature limit. For a two-gap SC, the interband coupling ensures that the two gaps open at the same  $T_c$ . Usually, the main contributions to both the electronic specific heat  $C_e$ and the superfluid density  $\rho_s$  stem from the larger gap  $\Delta^1$  at temperatures just below  $T_c$ , but the physical behavior can be modified at lower temperatures attributed to the opening of a smaller gap  $\Delta^2$ .

In Fig.5, the temperature dependence of the electronic specific heat  $C_e(T)/T$  is shown at various magnetic fields for LaNiC<sub>2</sub>. Obviously, the superconducting transition is shifted to lower temperatures, and becomes broadened with increasing magnetic field, resembling that of the two-gap SC, MgB<sub>2</sub>.<sup>32</sup> The inset in Fig.5 describes the specific heat near the upper critical field in detail. One can see that the superconducting transition still exists at B= 0.40T but vanishes at B= 0.55T. This suggests a bulk upper critical field of  $B_{c2}^{C_p}(0) < 0.55$ T, which is much lower than the resistive upper critical field ( $B_{c2}^{\rho}(0) \approx 1.67$ T, see below). The underlying reason for such a discrepancy remains unclear. Similar observations were also made for other unconventional SCs. For instance, the heavy fermion CeIrIn<sub>5</sub> shows a much larger resistive  $T_c$  ( $\approx 1.3$ K) than the bulk  $T_c$  ( $\approx 0.4$ K), resulting in a large differ-



FIG. 6: (Color online) Magnetic field dependence of the residual Sommerfeld coefficient plotted as  $\gamma_0(B)/\gamma_n$  vs.  $B/B_{c2}(0)$  for LaNiC<sub>2</sub> (this work), MgB<sub>2</sub><sup>32</sup> and Nb<sub>77</sub>Zr<sub>23</sub>.<sup>37</sup> The solid line shows the case of nodal superconductivity, i.e.,  $\gamma_0(B) \propto B^{1/2}$ .

ence in the corresponding upper critical fields.<sup>36</sup>

The residual Sommerfeld coefficient in the superconducting state,  $\gamma_0(B)$ , which describes the low-energy quasiparticle excitations, provides important insights into the superconducting pairing symmetry. In fully gapped BCS SCs, the lowlying excitations are usually confined to the vortex cores and the specific heat is, therefore, proportional to the vortex density which increases linearly with increasing magnetic field, i.e.,  $\gamma_0(B) \propto B^{.38}$  On the other hand, for a highly anisotropic or gapless SC, the quasiparticle excitations can spread outside the vortex cores which can, in fact, significantly contribute to the specific heat at low temperatures. The local supercurrent flow may give rise to a shift on the excitation energy (Doppler shift), resulting in a distinct magnetic field dependence of the density of state,  $N(E_F)$ , at the Fermi energy. In SCs with line nodes, Volovik showed that  $N(E_F) \propto B^{1/2}$ , leading to a squareroot field dependence of the residual Sommerfeld coefficient, i.e.,  $\gamma_0(B) \propto B^{1/2}$ .<sup>39</sup> In Fig.6, we present the normalized Sommerfeld coefficient,  $\gamma_0(B)/\gamma_n$ , as a function of  $B/B_{c2}(0)$  for LaNiC<sub>2</sub>. Here the values of  $\gamma_0(B)$  are determined at T = 0.35K after subtracting the small non-zero fraction at zero magnetic field. One can see that  $\gamma_0(B)$  of LaNiC<sub>2</sub> shows a fast increase at low fields and then saturates with increasing magnetic field, clearly deviating from the linear field dependence expected for a conventional BCS SC like Nb<sub>77</sub>Zr<sub>23</sub> (squares),<sup>37</sup> and also from the square-root field dependence expected for a nodal SC (solid line). The curvature of  $\gamma_0(B)$  is rather similar to that of the prototypical two-gap SC, MgB<sub>2</sub>,<sup>32</sup> and also the residual thermal conductivity  $\kappa_0/T$  of the multiband SC, PrRu<sub>4</sub>Sb<sub>12</sub>,<sup>40</sup> providing another unambiguous evidence of two-gap superconductivity for LaNiC<sub>2</sub>.

#### D. Electrical resistivity and upper critical field

Fig.7 shows the temperature dependence of the electrical resistivity  $\rho(T)$  at various magnetic fields (B= 0-1.5T) for



FIG. 7: (Color online) Temperature dependence of the electrical resistivity  $\rho(T)$  at various magnetic fields for LaNiC<sub>2</sub>.

LaNiC<sub>2</sub>. The superconducting transition is eventually suppressed, and the transition width is slightly broadened upon applying a magnetic field. The temperature dependence of the upper critical field  $B_{c2}(T)$  is plotted in the inset of Fig.8, in which  $T_c$  is determined from the mid-point of the superconducting transition and the error bars are defined by 10% and 90% of the normal-state resistivity just above  $T_c$ .

For comparison, in Fig.8 we show the normalized upper critical field,  $B_{c2}/[T_c(dB_{c2}/dT)_{T_c}]$ , vs.  $T/T_c$  for several representative SCs, i.e., LaNiC<sub>2</sub> (this study), MgB<sub>2</sub><sup>33</sup> and Li<sub>2</sub>Pt<sub>3</sub>B.<sup>41</sup> One can see that the upper critical fields  $B_{c2}(T)$  of LaNiC<sub>2</sub>, derived from both the specific heat (stars) and the resistivity (squares), follow the same scaling behavior even though the corresponding  $T_c$  is different. We fit the  $B_{c2}(T)$  data of LaNiC<sub>2</sub> with the Werthamer-Helfand-Hohenberg (WHH) theory in the dirty limit.<sup>42</sup> A clear deviation is observed at low temperatures, and the experimental value of  $B_{c2}(0)$  exceeds that of the WHH predictions. A positive curvature of  $B_{c2}(T)$  near  $T_c$  and the enhancement of  $B_{c2}(0)$ are typical features of multi-gap SCs, arising from the contributions of the small gap at low temperatures. Indeed, the upper critical field  $B_{c2}(T)$  of LaNiC<sub>2</sub> remarkably resembles that of  $MgB_2$ ,<sup>33</sup> as seen in Fig.8.

To further characterize  $B_{c2}(T)$ , we analyze it in terms of a two-gap BCS model. In the dirty limit, the upper critical field  $B_{c2}(T_c)$  takes the following form:<sup>43</sup>

$$a_0[\ln t + U(h)][\ln t + U(\eta h)] + a_1[\ln t + U(h)] + a_2[\ln t + U(\eta h)] = 0, \quad (9)$$

where  $U(x) = \psi(1/2+x) - \psi(x)$ , and  $\psi(x)$  is the di-gamma function. The asymptotic value of  $B_{c2}(0)$  can be obtained by the following quadratic equation:

$$B_{c2}(0) = \frac{\Phi_0 T_c}{2\gamma \sqrt{D_1 D_2}} e^{\frac{g}{2}},$$
  
$$g = (\frac{\lambda_0^2}{w^2} + \ln^2 \frac{D_2}{D_1} + \frac{2\lambda_-}{w} \ln \frac{D_2}{D_1})^{1/2} - \frac{\lambda_0}{w}, \qquad (10)$$



FIG. 8: (Color online) Normalized upper critical field,  $B_{c2}/[T_c(dB_{c2}/dT)_{T_c}]$ , versus  $T/T_c$  for LaNiC<sub>2</sub> (this work), MgB<sub>2</sub><sup>33</sup> and Li<sub>2</sub>Pt<sub>3</sub>B.<sup>41</sup> Here the upper critical fields for LaNiC<sub>2</sub> are taken from the middle point of the resistive drops (**■**) and the specific heat jumps ( $\bigstar$ ) at  $T_c$ . The dashed and dotted lines show the fittings of a two-gap BCS model and the WHH method, respectively. Inset: the resistive upper critical field  $B_{c2}$  versus T for LaNiC<sub>2</sub>, fitted by a two-gap BCS model.

where  $t = T/T_c$ ,  $h = B_{c2}D_1/2\Phi_0T$ ,  $\Phi_0$  is the flux quantum,  $\eta = D_2/D_1$ ,  $\lambda_{\pm} = \lambda_{11} \pm \lambda_{22}$ ,  $w = \lambda_{11}\lambda_{22} - \lambda_{12}\lambda_{21}$ ,  $\lambda_0 = (\lambda_{-}^2 + 4\lambda_{12}\lambda_{21})^{1/2}$ ,  $a_0 = 2w/\lambda_0$ ,  $a_1 = 1 + \lambda_-/\lambda_0$  and  $a_2 = 1 - \lambda_-/\lambda_0$ . Here  $D_m$  represent the intraband diffusivity tensors by nonmagnetic impurities scattering, and  $\lambda_{mm'}$  are the BCS superconducting coupling constants. As shown in Fig.8, the upper critical field  $B_{c2}(T)$  of LaNiC<sub>2</sub> can be well described by the two-gap model with the coupling constants of  $\lambda_{11}=0.02$ ,  $\lambda_{22}=0.01$ ,  $\lambda_{12}=0.001$ and  $\lambda_{21}=0.1$ , and the intraband diffusivity ratio of  $\eta=12$ . The derived upper critical field value is  $B_{c2}^{\rho}(0) \approx 1.67T$  from the electrical resistivity and  $B_{c2}^{C_p}(0) \approx 0.48T$  from the specific heat, respectively. In any case, the derived  $B_{c2}(0)$  for LaNiC<sub>2</sub> is well below the Pauli paramagnetic limit of  $B_{c2}^{P}(0)=1.86T_c \approx 6T$ , indicating an orbital pair-breaking mechanism for LaNiC<sub>2</sub>.

#### E. Discussion

As described above, two-gap BCS superconductivity in LaNiC<sub>2</sub> has been evidenced from the penetration depth  $\Delta\lambda(T)$ , the electronic specific heat  $C_e(T)$ , the residual Sommerfeld coefficient  $\gamma_0(B)$  and the upper critical field  $B_{c2}(T)$ , respectively. Such a pairing state can be qualitatively interpreted in terms of the ASOC effect as argued in many NCS SCs. In LaNiC<sub>2</sub>, calculations of the electronic structure based on the first-principles full-potential linearized augmented planewave (FLAPW) method gave a band splitting of 3.1 mRy,<sup>44</sup> which is small in comparison with the heavy fermion NCS SCs and also Li<sub>2</sub>Pt<sub>3</sub>B (see Table 1). In this case, the ASOC only has a moderate effect on the pairing state; both the spin-singlet and spin-triplet components may have comparable contributions to the pairing state, naturally leading to the

behavior of two-gap-like superconductivity.

Nevertheless, it seems that the diverse behavior of the NCS SCs, as summarized in Table 1, is difficult to be fully understood by a unified picture based on the ASOC effect. The heavy fermion systems typically possess a sizeable spinorbit coupling which results in a large band splitting too. In these compounds, an extremely large upper critical field  $B_{c2}(0)$ , well exceeding the paramagnetic limit, and evidence of a dominant spin-triplet pairing state with line nodes in the superconducting energy gap have been observed in the Ce-based materials.<sup>8–10,12,13</sup> These unconventional superconducting properties can be explained in terms of the ASOC effect, even though the strong electronic correlations and magnetism existing in these compounds may complicate the interpretation.  $Li_2(Pd_{1-x}Pt_x)_3B$  provides a model system to study the ASOC effect on superconductivity in the absence of inversion symmetry.<sup>15</sup> In Li<sub>2</sub>Pd<sub>3</sub>B, various measurements have demonstrated BCS-like superconductivity.<sup>15-18</sup> With increasing Pt concentration, which corresponds to an increase of the ASOC strength, the spin-triplet component eventually grows, showing spin-triplet superconductivity in Li<sub>2</sub>Pt<sub>3</sub>B.<sup>15–17</sup>

Following the extensive studies of NCS SCs in recent years, however, a growing number of compounds show properties which cannot be simply interpreted in terms of the ASOC effect. For example, the NCS SCs  $BaPtSi_3$ , <sup>52</sup>  $Re_3W^{53}$  and Ir<sub>2</sub>Ga<sub>9</sub>,<sup>54</sup> in which a strong ASOC is expected from their large atomic numbers, demonstrate conventional s-wave superconductivity. On the other hand, two-gap superconductivity has been shown in  $Y_2C_3$ ,<sup>19</sup> La<sub>2</sub>C<sub>3</sub>,<sup>20</sup> Mg<sub>10</sub>Ir<sub>19</sub>B<sub>16</sub>,<sup>21</sup> BiPd<sup>50,51</sup> and LaNiC<sub>2</sub> (this work). In  $Y_2C_3$ , evidence of line nodes was noticed in the low temperature limit, even though the ASOC is weak in this compound.<sup>19</sup> According to the available experiments, we are, besides Li<sub>2</sub>Pt<sub>3</sub>B, still short of examples showing spin-triplet superconductivity in NCS compounds with weak electron correlations. The ASOC can enhance the upper critical field which can nicely explain the extremely large value of  $B_{c2}(0)$  and its anisotropy in the heavy fermion NCS SCs.<sup>12,13,55</sup> However, in the weakly correlated NCS SCs like  $Li_2Pt_3B^{41}$  and  $BaPtSi_3$ ,<sup>52</sup>  $B_{c2}(0)$  is rather small even though the ASOC is strong in these compounds. Moreover, the upper critical field  $B_{c2}(T)$  of Li<sub>2</sub>(Pd<sub>1-x</sub>Pt<sub>x</sub>)<sub>3</sub>B behaves similarly at different doping concentrations and can be scaled by the corresponding  $T_c$ .<sup>41</sup> In contrast, a large upper critical field  $B_{c2}(0)$ is observed in  $Y_2C_3$ ,<sup>19</sup> La<sub>2</sub>C<sub>3</sub><sup>20</sup> and Mo<sub>3</sub>Al<sub>2</sub>C,<sup>56</sup> of which the ASOC strength is relatively weak. All these experimental facts seem to indicate that the ASOC effect may not be the sole determining parameter of the superconducting properties in NCS SCs. A systematic study, both experimental and theoretical, remains highly desired in order to elucidate the nature of superconductivity in NCS compounds.

### **IV. CONCLUSION**

In summary, we have systematically measured the low temperature London penetration depth, specific heat and electrical resistivity in order to probe the superconducting order parameter in the weakly correlated, non-centrosymmetric su-

TABLE I: Superconducting parameters in some major non-centrosymmetric superconductors. Since the ASOC strength is expected to be proportional to the square of the atomic numbers for atoms on the NCS crystalline sites, we assign the band splitting  $E_{\text{ASOC}}$  with "large" or "small" by their atomic numbers in case that no band structure calculations are available.

Material	Space Group	$T_c$ [K]	$B_{c2}(0)$ [T]	$\gamma_n  [\text{mJ/mol} \cdot \text{K}^2]$	$E_{ASOC}$	Pairing State	Ref.
CePt <sub>3</sub> Si	Tetragonal P4mm	0.75(max)	$3.2(H \parallel c), 2.7(H \perp c)$	390	200meV	singlet & triplet	6,8–10
CeIrSi <sub>3</sub>	Tetragonal I4mm	1.6(max)	$45(H \parallel c), 11(H \perp c)$	100	4meV	triplet	13,45,46
CeRhSi <sub>3</sub>	Tetragonal I4mm	1.05(max)	$30(H \parallel c), 7(H \perp c)$	110	10meV	triplet	12,47
Li <sub>2</sub> Pt <sub>3</sub> B	Cubic P4 <sub>3</sub> 32	2.6	1.9	7	200meV	triplet	15-18
Li <sub>2</sub> Pd <sub>3</sub> B	Cubic P4 <sub>3</sub> 32	7.6	6.2	9	30meV	s-wave	15-18
LaNiC <sub>2</sub>	Orthogonal Amm2	2.75	1.67	7.7	42meV	two-gap	this work,44
$Y_2C_3$	Cubic I43d	16	29	6.3	15meV	two-gap	19,48
$La_2C_3$	Cubic I43d	13.2	19	10.6	30meV	two-gap	20,49
Mg <sub>10</sub> Ir <sub>19</sub> B <sub>16</sub>	Cubic I43m	5	0.77	52.6	large	two-gap	21
BiPd	Monoclinic $P2_1$	3.8	$0.8(H \parallel b)$	4	large	two-gap	50,51
BaPtSi3	Tetragonal I4mm	2.25	0.05	5.7	large	s-wave	52
Re <sub>3</sub> W	Cubic I43m	7.8	12.5	15.9	large	s-wave	53
Ir <sub>2</sub> Ga <sub>9</sub>	Monoclinic Pc	2.25	0.025	6.9	large	s-wave	54
Rh <sub>2</sub> Ga <sub>9</sub>	Monoclinic Pc	1.95	type-I	7.9	small	s-wave	54
Mo <sub>3</sub> Al <sub>2</sub> C	Cubic P4132	9	15.7	17.8	small	s-wave	56,57
Ru <sub>7</sub> B <sub>3</sub>	Hexagonal P6 <sub>3</sub> mc	3.3	$1.7(H \parallel c),  1.6(H \perp c)$	43.7	small	s-wave	58

perconductor LaNiC<sub>2</sub>. It was found that both the penetration depth  $\Delta\lambda(T)$  and the electronic specific heat  $C_e(T)$  show exponential-like behavior at low temperatures which can be fitted by a two-gap BCS model. The upper critical field  $B_{c2}(T)$ is enhanced at low temperatures, as a result of the contributions from the small superconducting gap. The residual Sommerfeld coefficient,  $\gamma_0(B)$ , increases rapidly at low fields, and eventually gets saturated with further increasing magnetic field. All these experimental facts provide unambiguous evidence for two-gap supercoductivity for LaNiC<sub>2</sub>. We argue that such a superconducting state may arise from the moderate ASOC strength in LaNiC<sub>2</sub>, which leads to a moderate band splitting  $E_{ASOC}$  and a mixed pairing state with comparable spin-singlet and spin-triplet pairing components.

### V. ACKNOWLEDGEMENTS

We acknowledge valuable discussion with M. Sigrist, E. Bauer and M. B. Salamon. This work was supported by the Natural Science Foundation of China (Grant No. 10934005), the National Basic Research Program of China (Grant Nos. 2009CB929104, 2011CBA00103), Zhejiang Provincial Natural Science Foundation of China, the Fundamental Research Funds for the Central Universities, and the Max-Plank Society under the auspices of the Max-Plank partner group of the MPI for Chemical Physics of Solids, Dresden.

- \* Electronic address: hqyuan@zju.edu.cn
- <sup>1</sup> P. W. Anderson, J. Phys. Chem. Solids **11**, 26 (1959).
- <sup>2</sup> P. W. Anderson, Phys. Rev. B **30**, 4000 (1984).
- <sup>3</sup> L. P. Gor'kov and E. I. Rashba, Phys. Rev. Lett. **87**, 037004 (2001).
- <sup>4</sup> S. K. Yip, Phys. Rev. B **65**, 144508 (2002).
- <sup>5</sup> P. A. Frigeri, D. F. Agterberg, A. Koga, and M. Sigrist, Phys. Rev. Lett. **92**, 097001 (2004).
- <sup>6</sup> K. V. Samokhin, E. S. Zijlstra, and S. K. Bose, Phys. Rev. B 69,094514 (2004); 70, 069902(E) (2004).
- <sup>7</sup> S. Fujimoto, J. Phys. Soc. Jpn. **76**, 051008 (2007).
- <sup>8</sup> E. Bauer, G. Hilscher, H. Michor, Ch. Paul, E. W. Scheidt, A. Gribanov, Yu. Seropegin, H. Noël, M. Sigrist, and P. Rogl, Phys. Rev. Lett. **92**, 027003 (2004).
- <sup>9</sup> M. Yogi, Y. Kitaoka, S. Hashimoto, T. Yasuda, R. Settai, T. D. Matsuda, Y. Haga, Y. Õnuki, P. Rogl, and E. Bauer, Phys. Rev. Lett. **93**, 027003 (2004).
- <sup>10</sup> I. Bonalde, W. Brämer-Escamilla, and E. Bauer, Phys. Rev. Lett. **94**, 207002 (2005).
- <sup>11</sup> M. Nicklas, F. Steglich, J. Knolle, I. Eremin, R. Lackner, and E.

Bauer, Phys. Rev. B 81, 180511(R) (2010).

- <sup>12</sup> N. Kimura, K. Ito, H. Aoki, S.Uji, and T. Terashima, Phys. Rev. Lett. **98**, 197001 (2007).
- <sup>13</sup> R. Settai, Y. Miyauchi, T. Takeuchi, F. Lvy, I. Sheikin, and Y. Ōnuki, J. Phys. Soc. Jpn. **77**, 073705 (2008).
- <sup>14</sup> T. Akazawa, H. Hidaka, H. Kotegawa, T. C. Kobayashi, T, Fujiwara, E. Yamamoto, Y. Haga, R. Settai, and Y. Ōnuki, J. Phys. Soc. Jpn. **73**, 3129 (2004).
- <sup>15</sup> H. Q. Yuan, D. F. Agterberg, N. Hayashi, P. Badica, D. Vandervelde, K. Togano, M. Sigrist, and M. B. Salamon, Phys. Rev. Lett. **97**, 017006 (2006). H. Q. Yuan, M. B. Salamon, P. Badica, and K. Togano, Physica B **403**, 1138 (2008).
- <sup>16</sup> M. Nishiyama, Y. Inada, and G. Q. Zheng, Phys. Rev. Lett. 98, 047002 (2007).
- <sup>17</sup> H. Takeya, M. ElMassalami, S. Kasahara, and K. Hirata, Phys. Rev. B **76**, 104506 (2007).
- <sup>18</sup> K. W. Lee and W. E. Pickett, Phys. Rev. B **72**, 174505 (2005).
- <sup>19</sup> J. Chen, M. B. Salamon, S. Akutagawa, J. Akimitsu, J. Singleton, J. L. Zhang, L. Jiao, and H. Q. Yuan, Phys. Rev. B 83, 144529 (2011).

- <sup>20</sup> S. Kuroiwa, Y. Saura, J. Akimitsu, M. Hiyaishi, M. Miyazaki, K. H. Satoh, S. Takeshita, and R. Kadono, Phys. Rev. Lett. **100**, 097002 (2008).
- <sup>21</sup> T. Klimczuk, F. Ronning, V. Sidorov, R. J. Cava, and J. D. Thompson, Phys. Rev. Lett. **99**, 257004 (2007).
- <sup>22</sup> O. I. Bodak and E. P. Marusin, Dopov. Akad. Nauk Ukr. RSR A 12, 1048 (1979).
- <sup>23</sup> V. K. Pecharsky, L. L. Miller, and K. A. Gschneidner, Phys. Rev. B 58, 497 (1998).
- <sup>24</sup> Y. Iwamoto, Y. Iwasaki, K. Ueda, and T. Kohara, Phys. Lett. A 250, 439 (1998).
- <sup>25</sup> A. Subedi and D. J. Singh, Phys. Rev. B 80, 092506 (2009).
- <sup>26</sup> I. Bonalde, R. L. Ribeiro, K. J. Syu, H. H. Sung, and W. H. Lee, New J. Phys. **13**, 123022 (2011).
- <sup>27</sup> W. H. Lee, H. K. Zeng, Y. D. Yao, Y. Y. Chen, Physica C 266, 138 (1996).
- <sup>28</sup> A. D. Hillier, J. Quintanilla, and R. Cywinski, Phys. Rev. Lett. **102**, 117007 (2009).
- <sup>29</sup> J. Quintanilla, A. D. Hillier, J. F. Annett, and R. Cywinski, Phys. Rev. B **82**, 174511 (2010).
- <sup>30</sup> A. Carrington and F. Manzano, Physica C 385, 205 (2003).
- <sup>31</sup> F. Bouquet, Y. Wang, R. A. Fisher, D. G. Hinks, J. D. Jorgensen, A. Junod, and N. E. Phillips, Europhys. Lett. 56, 856 (2001).
- <sup>32</sup> F. Bouquet, R. A. Fisher, N. E. Phillips, D. G. Hinks, and J. D. Jorgensen, Phys. Rev. Lett. 87, 047001 (2001).
- <sup>33</sup> K. H. Müller, G. Fuchs, A. Handstein, K. Nenkov, V. N. Narozhnyi, and D. Eckert, J. Alloys Comp. **322**, L10 (2001).
- <sup>34</sup> B. D. Yanoff, Ph.D. thesis, University of Illinois at Urbana-Champaign, 2000.
- <sup>35</sup> F. Gross, B. S. Chandrasekhar, D. Einzel, K. Andres, P. J. Hirschfeld, H. R. Ott, J. Beuers, Z. Fisk, and J. L. Smith, Z. Phys. B: Condens. Matt. 64, 175 (1986).
- <sup>36</sup> T. Park, H. Lee, I. Martin, X. Lu, V. A. Sidorov, K. Gofryk, F. Ronning, E. D. Bauer, and J. D. Thompson, Phys. Rev. Lett. **108**, 077003 (2012).
- <sup>37</sup> A. Mirmelstein, A. Junod, E. Walker, B. Revaz, J. Y. Genoud, and G. Triscone, J. Supercond. **10**, 527 (1997).
- <sup>38</sup> C. Caroli, P. G. de Gennes, and J. Matricon, Phys. Rev. Lett. 9, 307 (1964).
- <sup>39</sup> G. E. Volovik, JETP Lett. **58** 469 (1993).
- <sup>40</sup> R. W. Hill, S. Y. Li, M. B. Maple, and L. Taillefer, Phys. Rev. Lett. 101, 237005 (2008).
- <sup>41</sup> D. C. Peet, G. Eguchi, M. Kriener, S. Harada, Sk. Md. Shamsuz-

zamen, Y. Inada, G. Q. Zheng, and Y. Maeno, Phys. Rev. B 84, 054521 (2011).

- <sup>42</sup> N. R. Werthamer, E. Helfand, and P. C. Hohenberg, Phys. Rev. 147, 295 (1966).
- <sup>43</sup> A. Gurevich, Phys. Rev. B **67**, 184515 (2003).
- <sup>44</sup> I. Hase and T. Yanagisawa, J. Phys. Soc. Jpn. 78, 084724 (2009).
- <sup>45</sup> H. Mukuda, T. Ohara, M. Yashima, Y. Kitaoka, R. Settai, Y. Önuki, K. M. Itoh, and E. E. Haller, Phys. Rev. Lett. **104**, 017002 (2010).
- <sup>46</sup> T. Kawai, H. Muranaka, T. Endo, N. D. Dung, Y. Doi, S. Ikeda, T. D. Matsuda, Y. Haga, H. Harima, R. Settai, and Y. Ōnuki, J. Phys. Soc. Jpn. **77**, 064717 (2008).
- <sup>47</sup> T. Terashima, M. Kimata, S. Uji, T. Sugawara, N. Kimura, H. Aoki, and H. Harima, Phys. Rev. B **78**, 205107 (2008).
- <sup>48</sup> Y. Nishikayama, T. Shishidou, and T. Oguchi, J. Phys. Soc. Jpn. 76, 064714 (2007).
- <sup>49</sup> J. S. Kim, W. Xie, R. K. Kremer, V. Babizhetskyy, O. Jepsen, A. Simon, K. S. Ahm, B. Raquet, H. Rakoto, J. M. Broto, and B. Ouladdiaf, Phys. Rev. B **76**, 014516 (2007).
- <sup>50</sup> B. Joshi, A. Thamizhavel, and S. Ramakrishnan, Phys. Rev. B 84, 064518 (2011).
- <sup>51</sup> M. Mondal, B. Joshi, S. Kumar, A. Kamlapure, S. C. Ganguli, A. Thamizhavel, S. S. Mandal, S. Ramakrishnan, and P. Raychaudhuri, e-print arXiv:1202.2454.
- <sup>52</sup> E. Bauer, R. T. Khan, H. Michor, E. Royanian, A. Grytsiv, N. Melnychenko-Koblyuk, P. Rogl, D. Reith, R. Podloucky, E. W. Scheidt, W. Wolf, and M Marsman, Phys. Rev. B 80, 064504 (2009).
- <sup>53</sup> Y. L. Zuev, V. A. Kuznetsova, R. Prozorov, M. D. Vannette, M. V. Lobanov, D. K. Christen, and J. R. Thompson, Phys. Rev. B 76, 132508 (2007).
- <sup>54</sup> K. Wakui, S. Akutagawa, N. Kase, K. Kawashima, T. Muranaka, Y. Iwahori, J. ABE, and J. Akimitsu, J. Phys. Soc. Jpn. **78**, 034710 (2009).
- <sup>55</sup> R. P. Kaur, D. F. Agterberg, and M. Sigrist, Phys. Rev. Lett. 94, 137002 (2005).
- <sup>56</sup> E. Bauer, G. Rogl, X. Q. Chen, R. T. Khan, H. Michor, G. Hilscher, E. Royanian, K. Kumagai, D. Z. Li, Y. Y. Li, R. Podloucky, and P. Rogl, Phys. Rev. B 82, 064511 (2010).
- <sup>57</sup> I. Bonalde, H. Kim, R. Prozorov, C. Rojas, P. Rogl, and E. Bauer, Phys. Rev. B 84, 134506 (2011).
- <sup>58</sup> N. Kase and J. Akimitsu, J. Phys. Soc. Jpn. **78**, 044710 (2009).