Observation of the Thermal Conductivity due to Spins in the One-Dimensional Antiferromagnetic Ising-Like Spin System $A \operatorname{Co} X_3$ ($A = \operatorname{Rb}$, Cs; $X = \operatorname{Cl}$, Br)

Yoshiharu Matsuoka¹, Takayuki Kawamata^{1*}, Koki Naruse¹, Masumi Ohno¹, Yoichi Nishiwaki², Tetsuya Kato³, Takahiko Sasaki⁴, Yoji Koike¹

¹Department of Applied Physics, Tohoku University, 6-6-05 Aoba, Aramaki, Aoba-ku, Sendai 980-8579, Japan

²Department of Physics, Saitama Medical University, Moroyama, Saitama 350-0495, Japan
 ³Faculty of Education, Chiba University, Yayoi-cho 1-33, Inageku, Chiba 263-8522, Japan
 ⁴Institute for Materials Research, Tohoku University, 2-1-1 Katahira, Aoba-ku, Sendai
 980-8577, Japan

Thermal conductivity measurements have been carried out for single crystals of the onedimensional (1D) antiferromagnetic (AF) Ising-like spin system $ACoX_3$ (A = Rb, Cs; X = Cl, Br). A shoulder originating from the thermal conductivity due to spin excitations, κ_{spin} , has been observed around 60 K in the temperature dependence of the thermal conductivity along the *c*-axis parallel to spin chains for every $ACoX_3$. To our knowledge, this is the first observation of κ_{spin} in 1D AF Ising-like spin systems. It has been found that the magnitude of κ_{spin} in $ACoX_3$ is a little smaller than those in 1D AF Heisenberg spin systems. The reason is discussed in terms of the Heisenberg-like character in $ACoX_3$.

^{*}tkawamata@teion.apph.tohoku.ac.jp

1. Introduction

The thermal conductivity in low-dimensional quantum spin systems has attracted great interest, because various remarkable anomalies associated with the low dimensionality of the spin correlation have been observed in these spin systems. In particular, the thermal conductivity due to spin excitations, κ_{spin} , has been observed markedly in one-dimensional (1D) antiferromagnetic (AF) Heisenberg spin systems,^{1–17} two-dimensional AF Heisenberg spin systems^{18–26} and a 1D ferromagnetic Heisenberg spin system also.^{27,28} It has been found that the magnitude of κ_{spin} tends to increase with increasing exchange interaction between the nearest neighboring spins in 1D AF Heisenberg spin systems.

The Hamiltonian of a 1D AF system is described using the *XXZ* Heisenberg model as follows:

$$\mathcal{H} = J \sum_{i}^{\text{chain}} \left[s_{i}^{z} s_{i+1}^{z} + \varepsilon \left(s_{i}^{x} s_{i+1}^{x} + s_{i}^{y} s_{i+1}^{y} \right) \right], \tag{1}$$

where $s = (s^x, s^y, s^z)$ is the spin, *J* the intrachain exchange interaction between the nearest neiboring spins and ε the anisotropy parameter of the spin. When spins are isotropic, namely, $\varepsilon = 1$, the spin system is called a Heisenberg one. When $\varepsilon = 0$, on the other hand, the spin system is called an Ising one. Using the spin raising and lowering operators, $s^+ = s^x + is^y$ and $s^- = s^x - is^y$, respectively, Eq. (1) is rewritten as follows:

$$\mathcal{H} = J \sum_{i}^{\text{chain}} \left[s_{i}^{z} s_{i+1}^{z} + \frac{\varepsilon}{2} \left(s_{i}^{+} s_{i+1}^{-} + s_{i}^{-} s_{i+1}^{+} \right) \right].$$
(2)

The second and third terms are so related to the propagation of spin excitations as to be likely important for the appearance of κ_{spin} . Therefore, κ_{spin} is supposed to be very small in Ising spin systems. Theoretically, in fact, this is supported.²⁹ Experimentally, no κ_{spin} has been observed in the quasi-1D AF spin system BaCo₂V₂O₈ where $\varepsilon \sim 0.5$.^{30,31}

The compound $ACoX_3$ (A = Rb, Cs; X = Cl, Br) is regarded as a quasi-1D AF Ising-like spin system where the space group of the crystal structure is $P6_3/mmc$ at room temperature. The AF spin chains consist of face-shared CoX_6 octahedra stacked along the *c*-axis, and the spin chains compose a triangular lattice in the *c*-plane. The Ising-like anisotropy of Co^{2+} spins along the *c*-axis is due to the spin-orbit interaction. The Hamiltonian of $ACoX_3$ is given by Eq. (1), where ε is estimated from Raman scattering,^{32–34} neutron scattering,^{35–37} magnetization³⁸ and ESR measurements³⁹ to be below 0.24 and smaller than that of $BaCo_2V_2O_8$, as listed in Table I. It is known that $ACoX_3$ exhibits successive phase transitions at low temperatures T_{N1} and T_{N2} , owing to the interchain interaction.^{33,40–42} The magnetic state is paramagnetic at high temperatures above T_{N1} . At intermediate temperatures between T_{N1} and T_{N2} , a partially ordered phase is formed, where two thirds of spin chains are ordered like a honeycomb lattice in the *c*-plane owing to the AF interchain interaction. At low temperatures below T_{N2} , all Co²⁺ spins are ordered, so that a ferrimagnetic order is formed. Moreover, it is known that RbCoBr₃ undergoes two structural transitions at T_{s1} and T_{s2} .⁴³ Values of T_{N1} , T_{N2} , T_{s1} and T_{s2} are listed in Table I together with those of *J* and the ratio of the interchain interaction, *J'*, to *J*.

In this paper, in order to investigate the contribution of spin excitations to the thermal conductivity in 1D AF Ising-like spin systems, we have measured the thermal conductivity of $ACoX_3$ (A = Rb, Cs; X = Cl, Br).

2. Experimental

Single crystals of $ACoX_3$ (A = Rb, Cs; X = Cl, Br) were grown by the Bridgman technique using equimolar mixture of AX and CoX_2 sealed in an evacuated quartz tube. Both of the thermal conductivity along the *c*-axis parallel to spin chains, $\kappa_{\parallel c}$, and that in the *c*-plane perpendicular to spin chains, $\kappa_{\perp c}$, were measured by the conventional steady-state method. The typical dimensions of a single crystal used for the measurements were 4 mm along the direction of heat current and $2\times 2 \text{ mm}^2$ perpendicular to the direction. One side of a single crystal was anchored on the copper heat sink with indium solder. A chip-resistance of 1 k Ω (Alpha Electronics MP1K000) was attached as a heater to the opposite side of the single crystal with Araldite epoxy adhesive. The temperature gradient across the crystal was measured with two Cernox thermometers (Lake Shore Cryotronics, CX-1050-SD). The error of the absolute value of the thermal conductivity obtained was estimated to be about 10 % on account of errors of the crystal geometry. Thermal conductivity measurements in magnetic fields up to 14 T were also carried out for RbCoCl₃ using a superconducting magnet.

3. Results and Discussion

Figure 1 shows the temperature dependence of $\kappa_{\parallel c}$ and $\kappa_{\perp c}$ of single crystals of $A \text{Co} X_3$ in zero field. It is found that a peak appears at a low temperature below 10 K in both $\kappa_{\parallel c}$ of every $A \text{Co} X_3$ and $\kappa_{\perp c}$ of RbCoCl₃, while a shoulder is observed around 60 K in only $\kappa_{\parallel c}$ of every $A \text{Co} X_3$. Since $A \text{Co} X_3$ is an insulator, the thermal conductivity is given by the sum of the contribution of phonons and spin excitations. The thermal conductivity due to phonons, κ_{phonon} , is usually more isotropic than κ_{spin} , because the anisotropy of the correlation between atoms is generally much smaller than that of the spin correlation in a low-dimensional spin system. Moreover, the temperature dependence of $\kappa_{\perp c}$ is typical of κ_{phonon} . Therefore, it is concluded that the peak at a low temperature below 10 K is due to κ_{phonon} and that the shoulder around 60 K is due to κ_{spin} . Similar temperature dependence of the thermal conductivity along spin chains has been observed in several 1D AF Heisenberg spin systems such as Sr₂CuO₃^{5,6} and SrCuO₂.⁶

In Fig. 1, it is noticed that neither sharp dip is observed at T_{N1} nor at T_{N2} for every $ACoX_3$, while a sharp dip has been observed at the magnetic transition temperature in every direction of thermal conductivity for BaCo₂V₂O₈^{30,31} and several three-dimensional magnets.^{44–47} The reason for neither sharp dip at T_{N1} nor at T_{N2} for $ACoX_3$ is not clear at present, though several low-dimensional AF spin systems such as Sr₂CuO₃^{5,6} and La₂CuO₄²⁰ have shown no sharp dip at their magnetic transition temperatures.

In Fig. 1, it is also noticed that neither clear change is observed at T_{s1} nor at T_{s2} for RbCoBr₃. Since the structural phase transitions are caused by sliding motions of spin chains along the *c*-axis, it may be reasonable that $\kappa_{\parallel c}$ is not affected by the transitions.

Here, we estimate the magnitude of κ_{spin} . Since κ_{spin} is given by the subtraction of κ_{phonon} from $\kappa_{\parallel c}$ as follows:

$$\kappa_{\rm spin}(T) = \kappa_{\parallel c}(T) - \kappa_{\rm phonon}(T), \tag{3}$$

the estimation of κ_{phonon} is necessary at first. Based on the Debye model with the relaxation time approximation, κ_{phonon} is given by

$$\kappa_{\rm phonon}(T) = \frac{k_{\rm B}}{2\pi^2 v_{\rm phonon}} \left(\frac{k_{\rm B}T}{\hbar}\right)^3 \int_0^{\Theta_{\rm D}/T} \mathrm{d}x \frac{x^4 e^x}{(e^x - 1)^2} \tau_{\rm phonon}(x, T),\tag{4}$$

where $k_{\rm B}$ is the Boltzmann constant, \hbar the Planck constant, $\Theta_{\rm D}$ the Debye temperature, $v_{\rm phonon}$ the velocity of phonons, $\tau_{\rm phonon}$ the relaxation time of the phonon with the angular frequency ω , and $x = \hbar \omega / k_{\rm B} T$.⁴⁸ The $v_{\rm phonon}$ is calculated as

$$v_{\rm phonon} = \frac{k_{\rm B}\Theta_{\rm D}}{\hbar} \left(6\pi^2 n\right)^{-1/3},\tag{5}$$

where *n* is the number density of atoms. The phonon scattering rate, τ_{phonon}^{-1} , is given by the sum of scattering rates in various scattering processes as follows:

$$\tau_{\rm phonon}^{-1}(\omega,T) = \frac{v_{\rm phonon}}{L_{\rm b}} + P\omega^4 + D\omega + U\omega^2 T \exp(-\Theta_{\rm D}/uT),\tag{6}$$

where L_b , P, D, U and u are fitting parameters. The first term represents the phonon scattering by boundaries. The second term represents the phonon scattering by point defects. The third term represents the phonon scattering by lattice distortions. The fourth term represents the phonon-phonon scattering in the umklapp process.

Using Eqs. (4)–(6) and putting Θ_D at 310 K estimated from the Mössbauer measurements,⁴⁹ the data of $\kappa_{\perp c}(T)$ in RbCoCl₃ are well fitted in a wide temperature-range as shown by the black line in Fig. 1, indicating that $\kappa_{\perp c}(T)$ is due to only $\kappa_{\text{phonon}}(T)$. The obtained parameters are listed in Table II. The estimation of $\kappa_{\text{phonon}}(T)$ in $\kappa_{\parallel c}(T)$ of $A \text{Co} X_3$ is performed by the fit of the data of $\kappa_{\parallel c}(T)$ at low temperatures below 25 K with Eqs. (4)–(6), because $\kappa_{\rm spin}(T)$ decreases markedly with decreasing temperature at low temperatures of $k_{\rm B}T \ll J$ in usual low-dimensional spin systems.¹³ In the fitting, values of Θ_D of RbCoCl₃ and CsCoBr₃ are put at those estimated from the Mössbauer measurements,⁴⁹ and those of RbCoBr₃ and CsCoCl₃ are put at the average value of those of RbCoCl₃ and CsCoBr₃, considering the weight of atoms. The value of L_b is given by the distance between two terminals of temperature on a single crystal. The best-fit results of $\kappa_{phonon}(T)$ are shown by blue solid lines in Fig. 2. Shaded areas in Fig. 2 indicate errors of $\kappa_{\text{phonon}}(T)$. Values of parameters used for the best fit are listed in Table II. It is found that values of P obtained in $\kappa_{\parallel c}$ and $\kappa_{\perp c}$ of RbCoCl₃ are very different from each other, which is unreasonable. The difference of the P value is caused by the analysis using the Debye model where the anisotropy of v_{phonon} is not taken into account. That is, the anisotropy of v_{phonon} appears to bring about the difference of the P value between $\kappa_{\parallel c}$ and $\kappa_{\perp c}$. Using Eq. (3), $\kappa_{\rm spin}(T)$ is obtained as shown by red circles in Fig. 2. It is found that $\kappa_{spin}(T)$ exhibits the maximum at a high temperature above 50 K and that the maximum value of $\kappa_{spin}(T)$ is about 3 W/Km in RbCoCl₃, 4 W/Km in CsCoCl₃, CsCoBr₃, and 0.9 W/Km in RbCoBr₃. Here, it is noted that $\kappa_{spin}(T)$ is a little underestimated, because $\kappa_{spin}(T)$ is neglected at low temperatures below 25 K. Values of $\kappa_{spin}(T)$ in RbCoBr₃ are smaller than those of $\kappa_{spin}(T)$ in the other ACoX₃. Since structural phase transitions occur at T_{s1} and T_{s2} only in RbCoBr₃, the lattice mismatch may be marked in RbCoBr₃ on account of the difference of the ionic radius between Rb⁺ and Br⁻. Therefore, the lattice mismatch may induce disorder of the lattice and suppress $\kappa_{\text{phonon}}(T)$ and $\kappa_{\text{spin}}(T)$.

Figure 3 displays the maximum values of κ_{spin} in $ACoX_3$ and several 1D AF Heisenberg spin systems^{1, 10, 17, 50, 51} plotted as a function of *J*. It is found that the maximum values of κ_{spin} in 1D AF Heisenberg spin systems tend to be proportional to *J*. This is simply understood to be due to the velocity of spin excitations, v_{spin} , being proportional to *J* in spite of the specific heat, C_{spin} , being inversely proportional to *J* at low temperatures in 1D AF Heisenberg spin systems,^{52, 53} because κ_{spin} is proportional to $C_{spin}v_{spin}^2$. It is found that the maximum values of κ_{spin} in $ACoX_3$ are located a little below the shaded zone indicating the rough proportionality between the maximum value of κ_{spin} and *J*. The bandwidth of the magnetic dispersion in an 1D Heisenberg spin system is proportional to *J*, so that v_{spin} is proportional to *J* at low temperatures. In an 1D AF quasi-Ising spin system, on the other hand, the bandwidth, namely, v_{spin} is expected to be proportional to εJ , according to Eq. (2).⁵⁴ Using values of εJ instead of those of J in Fig. 3, therefore, the maximum values of κ_{spin} in $ACoX_3$ are found to shift just into the shaded zone. Accordingly, this result strongly suggests that a little Heisenberg-like character with $\varepsilon \neq 0$ brings about a significant bandwidth, leading to the appearance of κ_{spin} even in an 1D AF Ising-like spin system. Here, it is noted that $\kappa_{\parallel c}$ of RbCoCl₃ little changes by the application of magnetic field of 14 T along the *c*-axis in a wide temperature-range of 6–140 K, as shown in Fig. 1. That is, κ_{spin} appears not to be affected by the magnetic field of 14 T. The magnetic field of 14 T may be too small to affect κ_{spin} of RbCoCl₃ being markedly observed at high temperatures around 70 K. Furthermore, it is not clear why no κ_{spin} has been observed in the quasi-1D AF spin system BaCo₂V₂O₈ in spite of the sizable value of $\varepsilon \sim 0.5$. To be more conclusive, therefore, thermal conductivity measurements in the other 1D AF Ising-like spin systems are necessary.

4. Summary

Thermal conductivity measurements have been carried out for single crystals of the 1D AF Ising-like spin system $ACoX_3$ (A = Rb, Cs; X = Cl, Br). It has been found that $\kappa_{\perp c}$ perpendicular to spin chains shows an only peak at a low temperature below 10 K and that $\kappa_{\parallel c}$ parallel to spin chains shows a shoulder around 60 K besides a peak at a low temperature below 10 K. It has been concluded that the peak is due to κ_{phonon} and that the shoulder around 60 K is due to κ_{spin} . To our knowledge, this is the first observation of κ_{spin} in 1D AF Ising-like spin systems. It has been found that the magnitude of κ_{spin} in $ACoX_3$ estimated by the subtraction of κ_{phonon} from $\kappa_{\parallel c}$ is a little smaller than those in 1D AF Heisenberg spin systems and that the magnitude of κ_{spin} tends to be proportional to εJ universally in both $ACoX_3$ and 1D AF Heisenberg spin systems. Accordingly, it has been concluded that a little Heisenberg-like character with $\varepsilon \neq 0$ brings about a significant bandwidth of spin excitations, leading to the appearance of κ_{spin} even in an 1D AF Ising-like spin system. To be more conclusive, thermal conductivity measurements in the other 1D AF Ising-like spin systems are necessary.

Acknowledgment

The thermal conductivity measurements in magnetic fields were performed at the High Field Laboratory for Superconducting Materials, Institute for Materials Research, Tohoku University.

References

- 1) H. Miike and K. Hirakawa, J. Phys. Soc. Jpn. 38, 1279 (1975).
- K. Kudo, S. Ishikawa, T. Noji, T. Adachi, Y. Koike, K. Maki, S. Tsuji, and K. Kumagai, J. Low Temp. Phys. 117, 1689 (1999).
- A. V. Sologubenko, K. Giannò, H. R. Ott, U. Ammerahl, and A. Revcolevschi, Phys. Rev. Lett. 84, 2714 (2000).
- A. V. Sologubenko, K. Giannò, H. R. Ott, U. Ammerahl, A. Revcolevschi, D. F. Brewer, and A. L. Thomson, Physica B 284-288, 1595 (2000).
- A. V. Sologubenko, E. Felder, K. Giannò, H. R. Ott, A. Vietkine, and A. Revcolevschi, Phys. Rev. B 62, R6108 (2000).
- A. V. Sologubenko, K. Giannò, H. R. Ott, A. Vietkine, and A. Revcolevschi, Phys. Rev. B 64, 054412 (2001).
- K. Kudo, S. Ishikawa, T. Noji, T. Adachi, Y. Koike, K. Maki, S. Tsuji, and K. Kumagai, J. Phys. Soc. Jpn. 70, 437 (2001).
- K. Kudo, Y. Koike, K. Maki, S. Tsuji, and K. Kumagai, J. Phys. Chem. Solids 62, 361 (2001).
- C. Hess, C. Baumann, U. Ammerahl, B. Büchner, F. Heidrich-Meisner, W. Brenig, and A. Revcolevschi, Phys. Rev. B 64, 184305 (2001).
- A. V. Sologubenko, H. R. Ott, G. Dhalenne, and A. Revcolevschi, Europhys. Lett. 62, 540 (2003).
- C. Hess, H. ElHaes, B. Büchner, U. Ammerahl, M. Hücker, and A. Revcolevschi, Phys. Rev. Lett. 93, 027005 (2004).
- 12) C. Hess, P. Ribeiro, B. Büchner, H. ElHaes, G. Roth, U. Ammerahl, and A. Revcolevschi, Phys. Rev. B **73**, 104407 (2006).
- T. Kawamata, N. Takahashi, T. Adachi, T. Noji, K. Kudo, N. Kobayashi, and Y. Koike, J. Phys. Soc. Jpn. 77, 034607 (2008).
- 14) T. Kawamata, N. Kaneko, M. Uesaka, M. Sato, and Y. Koike, J. Phys.: Conf. Ser. 200, 022023 (2010).
- 15) N. Hlubek, Dr. Thesis, Technische Universtität Dresden (2010).
- 16) N. Hlubek, P. Ribeiro, R. Saint-Martin, A. Revcolevschi, G. Roth, G. Behr, B. Büchner, and C. Hess, Phys. Rev. B 81, 020405 (2010).

- N. Hlubek, X. Zotos, S. Singh, R. Saint-Martin, A. Revcolevschi, B. Büchner, and C. Hess, J. Stat. Mech. P03006 (2012).
- 18) Y. Nakamura, S. Uchida, T. Kimura, N. Motohira, K. Kishio, K. Kitazawa, T. Arima, and Y. Tokura, Physica C 185-189, 1409 (1991).
- K. Takenaka, Y. Fukuzumi, K. Mizuhashi, S. Uchida, H. Asaoka, and H. Takei, Phys. Rev. B 56, 5654 (1997).
- 20) X. F. Sun, J. Takeya, S. Komiya, and Y. Ando, Phys. Rev. B 67, 104503 (2003).
- 21) J.-Q. Yan, J.-S. Zhou, and J. B. Goodenough, Phys. Rev. B 68, 104520 (2003).
- C. Hess, B. Büchner, U. Ammerahl, L. Colonescu, F. Heidrich-Meisner, W. Brenig, and A. Revcolevschi, Phys. Rev. Lett. 90, 197002 (2003).
- 23) C. Hess, B. Büchner, U. Ammerahl, and A. Revcolevschi, Phys. Rev. B **68**, 184517 (2003).
- 24) M. Hofmann, T. Lorenz, K. Berggold, M. Grüninger, A. Freimuth, G. S. Uhrig, and E. Brück, Phys. Rev. B 67, 184502 (2003).
- 25) C. Hess and B. Büchner, Eur. Phys. J. B 38, 37 (2004).
- 26) K. Berggold, T. Lorenz, J. Baier, M. Kriener, D. Senff, H. Roth, A. Severing, H. Hartmann, A. Freimuth, S. Barilo, and F. Nakamura, Phys. Rev. B **73**, 104430 (2006).
- 27) K. Kudo, Y. Koike, S. Kurogi, T. Noji, T. Nishizaki, and N. Kobayashi, J. Magn. Magn. Mater. 272-276, 94 (2004).
- 28) J.-H. Choi, T. C. Messina, J. Yan, G. I. Drandova, and J. T. Markert, J. Magn. Magn. Mater. 272-276, 970 (2004).
- 29) D. L. Huber and J. S. Semura, Phys. Rev. 182, 602 (1969).
- 30) Z. Y. Zhao, X. G. Liu, Z. Z. He, X. M. Wang, C. Fan, W. P. Ke, Q. J. Li, L. M. Chen, X. Zhao, and X. F. Sun, Phys. Rev. B 85, 134412 (2012).
- 31) G. Kolland, Dr. Thesis, Universität zu Köln (2013).
- 32) W. P. Lehmann, W. Breitling, and R. Weber, J. Phys. C: Solid State Phys. 14, 4655 (1981).
- 33) D. J. Lockwood, I. W. Johnstone, H. J. Labbe, and B. Briat, J. Phys. C: Solid State Phys. 16, 6451 (1983).
- 34) F. Matsubara, S. Inawashiro, and H. Ohhara, J. Phys.: Condens. Matter 3, 1815 (1991).
- 35) H. Yoshizawa, K. Hirakawa, S. K. Satija, and G. Shirane, Phys. Rev. B 23, 2298 (1981).

0/00

- 36) S. E. Nagler, W. J. L. Buyers, R. L. Armstrong, and B. Briat, Phys. Rev. B 27, 1784 (1983).
- 37) F. Matsubara and S. Inawashiro, Phys. Rev. B 43, 796 (1991).
- 38) H. Hori, H. Mikami, M. Date, and K. Amaya, Physica B 165-166, 237 (1990).
- 39) H. Shiba, Y. Ueda, K. Okunishi, S. Kimura, and K. Kindo, J. Phys. Soc. Jpn. 72, 2326 (2003).
- 40) H. Yoshizawa and K. Hirakawa, J. Phys. Soc. Jpn. 46, 448 (1979).
- 41) W. B. Yelon, D. E. Cox, and M. Eibschütz, Phys. Rev. B 12, 5007 (1975).
- 42) Y. Nishiwaki, T. Nakamura, A. Oosawa, K. Kakurai, N. Todoroki, N. Igawa, Y. Ishii, and T. Kato, J. Phys. Soc. Jpn. **77**, 104703 (2008).
- 43) K. Yamanaka, Y. Nishiwaki, K. Iio, T. Kato, T. Mitsui, T. Tojo, and T. Atake, J. Therm. Anal. Calorim. **70**, 371 (2002).
- 44) G. A. Slack and R. Newman, Phys. Rev. Lett. 1, 359 (1958).
- 45) G. A. Slack, Phys. Rev. 122, 1451 (1961).
- 46) K. Aring and A. J. Sievers, J. Appl. Phys. 38, 1496 (1967).
- 47) F. B. Lewis and N. H. Saunders, J. Phys. C: Solid State Phys. 6, 2525 (1973).
- 48) R. Berman, Thermal Conduction in Solids (Clarendon Press, Oxford, U. K., 1976).
- 49) S. Bocquet, J. B. Ward, and V. H. McCann, J. Phys. C: Solid State Phys. 21, 367 (1988).
- 50) L. S. Parfen'eva, I. A. Smirnov, H. Misiorek, J. Mucha, A. Jezowski, A. V. Prokof'ev, and W. Assmus, Phys. Solid State **46**, 357 (2004).
- M. Uesaka, T. Kawamata, N. Kaneko, M. Sato, K. Kudo, N. Kobayashi, and Y. Koike, J. Phys.: Conf. Ser. 200, 022068 (2010).
- 52) J. des Cloizeaux and J. J. Pearson, Phys. Rev. 128, 2131 (1962).
- 53) M. Takahashi, Prog. Theor. Phys. 50, 1519 (1973).
- 54) Theoretically, two kinds of spin excitations are known to exist in an 1D AF Ising-like spin system with $\varepsilon \neq 0$: one is the Villain mode with the bandwidth of $2\varepsilon J$,⁵⁵ and the other is the spin-wave mode with the bandwidth of $4\varepsilon J$.⁵⁶
- 55) J. Villain, Physica B+C 79, 1 (1975).
- 56) N. Ishimura and H. Shiba, Prog. Theor. Phys. 63, 743 (1980).

Figure captions

- Fig. 1. (Color online) Temperature dependence of the thermal conductivity along the *c*-axis, $\kappa_{\parallel c}$, in $A \text{Co} X_3$ (A = Rb, Cs; X = Cl, Br) and the thermal conductivity in the *c*-plane, $\kappa_{\perp c}$, in RbCoCl₃ in zero field. The black line is the best-fit result of $\kappa_{\perp c}$ in RbCoCl₃ using the thermal conductivity due to phonons given by Eqs. (4)–(6) with parameters listed in Table II. Red circles show $\kappa_{\parallel c}$ of RbCoCl₃ in a magnetic field of 14 T applied along the *c*-axis.
- Fig. 2. (Color online) Temperature dependence of the thermal conductivity along the *c*-axis, $\kappa_{\parallel c}$, in (a) RbCoCl₃, (b) RbCoBr₃, (c) CsCoCl₃, (d) CsCoBr₃. Blue solid lines show κ_{phonon} estimated using Eqs. (4)–(6). Shaded areas demonstrate errors of κ_{phonon} . Red circles show κ_{spin} obtained by subtracting κ_{phonon} from $\kappa_{\parallel c}$.
- Fig. 3. (Color online) Dependence on the intrachain interaction, *J*, of the maximum value of κ_{spin} in the 1D AF Ising-like spin system $ACoX_3$ (A = Rb, Cs; X = Cl, Br) (closed circles) and in 1D AF Heisenberg spin systems (open circles).^{1,10,17,50,51} Diamonds show dependence on εJ of the maximum value of κ_{spin} in $ACoX_3$. The shaded zone indicates the rough proportionality between the maximum value of κ_{spin} and *J*.

Table I. Magnetic parameters (the intrachain exchange interaction, *J*, the anisotropy parameter of spin, ε , the ratio of the interchain exchange interaction, *J'*, to *J*, the magnetic phase transition temperatures, T_{N1} and T_{N2}) and structural parameters (the structural phase transition temperatures, T_{s1} and T_{s2}) of $ACoX_3$ (A = Rb, Cs; X = Cl, Br).

	$J(\mathbf{K})$	ε	J'/J	$T_{\rm N1}$ (K)	$T_{\rm N2}({ m K})$	T_{s1} (K)	T_{s2} (K)		
RbCoCl ₃ ^a	140-152	0.091-0.15	0.02-0.11	28	11	-	-		
RbCoBr ₃ ^b	194	-	0.025	37	31	90	37		
CsCoCl ₃ ^c	126-150	0.097-0.16	0.013-0.12	21	9	-	-		
CsCoBr ₃ ^d	124–182	0.11-0.24	0.019–0.13	28	10	-	-		

^a Ref.33, 34, 38. ^b Ref.42, 43. ^c Ref.32, 34–40. ^d Ref.32, 34, 36, 38, 41.

in ACoX₃ with Eqs. (4)–(6). $\frac{\kappa \quad \Theta_{\rm D} \, ({\rm K}) \quad L_{\rm b} \, ({\rm mm}) \quad P \, (10^{-43} \, {\rm s}^3) \qquad D \, (10^{-6}) \qquad U \, (10^{-18} \, {\rm s}{\rm K}^{-1}) \qquad u}{{\rm RbCoCl}_2}$ $\frac{\kappa_{\perp c} \quad 310 \qquad 1.48 \qquad 52.5 \pm 1.9 \qquad 36.1 \pm 1.0 \qquad 39.8 \pm 0.4 \qquad 7.66 \pm 0.05}{{\rm RbCoCl}_2}$

Table II. Parameters used for the fit of the temperature dependences of the thermal conductivity, $\kappa_{\parallel c}$ and $\kappa_{\perp c}$,

RbCoCl ₃	$\kappa_{\perp c}$	310	1.48	52.5 ± 1.9	36.1 ± 1.0	39.8 ± 0.4	7.66 ± 0.05
	$\kappa_{\parallel c}$	310	2.03	0.82 ± 0.35	43.3 ± 1.3	19.0 ± 0.4	9.8 ± 0.2
RbCoBr ₃	$\kappa_{\parallel c}$	300	1.26	16.9 ± 3.8	86.0 ± 5.7	35.0 ± 1.0	10.0 ± 0.4
CsCoCl ₃	$\kappa_{\parallel c}$	300	1.65	3.6 ± 5.6	0 ± 2.5	15.5 ± 1.7	8.3 ± 0.8
CsCoBr ₃	$\kappa_{\parallel c}$	290	1.54	0.24 ± 1.40	0.08 ± 2.69	9.23 ± 0.69	8.82 ± 0.50



DRAFT



Fig. 2.

10/06



Fig. 3.

1 4 /00