Author manuscript, Published in Journal of The Electrochemical Society J. Electrochem. Soc. 2014 volume 161, issue 6, H416-H421 doi: 10.1149/2.119406jes

Enhancement of visible-light-induced photocurrent and photocatalytic activity of V and N codoped TiO₂ nanotube array films

Min Zhang^{*}, Dandan Lu, Zhihua Zhang, Jianjun Yang^{*}

Key Laboratory for Special Functional Materials of Ministry of Education, Henan University, Kaifeng 475004, PR China

Email: zm1012@henu.edu.cn,yangjianjun@henu.edu.cn

Tel: (86)371-23881358, Fax: (86)371-23881358

Abstract: Highly ordered TiO_2 nanotube arrays (TNAs) codoped with V and N were synthesized by electrochemical anodization in association with hydrothermal treatment. The samples were characterized by field emission scanning electron microscopy, X-ray diffraction and X-ray photoelectron spectroscopy. The photocurrent and photocatalytic activity of codoped TiO_2 nanotube arrays were investigated under visible light irradiation. Moreover, the production of hydroxyl

radicals (• OH) on the surface of visible light-irradiated samples is detected by a

photoluminescence technique using terephthalic acid (TA) as a probe molecule. It was found that the V+N co-doped TiO_2 nanotube arrays showed remarkably enhanced photocurrent and photocatalytic activity than undoped sample due to the V and N codoping.

Keywords:

TiO₂; phtocatalytic activity; nanotube; photocurrent

Introduction

Highly ordered TiO₂ nanotube arrays (TNAs) prepared by anodization of titanium have attracted much attention in recent years, because of their large surface area, high photocatalytic activity, vectorial charge transfer and good recyclability as well as unique nanostructure and promising application in solar light conversion as compared with conventional TiO₂ powder ¹. However, the use of nanostructured TiO₂ materials as a visible light photocatalyst is still limited, since their large bandgap of 3.2 eV can only be activated by ultraviolet radiation that constitutes only a small fraction (3%~5%) of the solar spectrum. On the other hand, the recombination rate of photogenerated electron-hole pairs is too high to be used for organic pollutant degradation in practice ².

To surmount these problems, doping of TiO₂, especially noncompensated cation-anion codoping, had been used to increase availability of visible light and improve the separation efficiency of photo-induced electrons and holes. The coupling of one dopant with the second has been proposed to enable a reduction in the number of carrier recombination centers by proposed charge equilibrium mechanism as well as enhancing visible light absorbance by increasing the solubility limit of dopants. It is generally accepted that electronic coupling between two dopants is the key to realize synergistic effects of codoping on photocatalytic activity ³. For example, Yin et al. and Long et al. separately proposed that the injection of 3*d* or 4*d* transition metals (such as Mo, W and V) can increase the solubility limits of N and the band edges of TiO₂ can be modified by co-dopants to significantly shift the valence band edge up based on density-functional theory calculations ^{4, 5}.

Among the current reports of single ion doping into anatase TiO₂, N-doping and V-doping are noteworthy. Vanadium is a transition metal with multiple characteristics which improve TiO₂ absorptivity. For example, V-doped TiO₂ with different valance state of the V and Ti ($V^{0/1+/2+/3+/4+/5+}$ and Ti^{1+/2+/3+/4+}) exhibits a difference in oxidation activity ⁶. V doping was responsible for increases of superficial hydroxyl groups and electron transfer, resulting in faster interactions between the adsorbate and adsorbent ⁷. The ionic radius of V is close to that of Ti, allowing it to be easily doped into TiO₂ ^{8,9}.

So, vanadium ion doping, as one of the best alternatives to enhance the separation efficiency of electron-hole pairs and the visible light-driven photoactivity, has attracted extensive interest.

N doping is also considered an effective approach to improve visible spectral absorption and photocatalytic activity ^{10, 11}. So the codoping of V and N into the lattice of TiO₂ is of particular significance. For example, V and N ions were reported to incorporate into anatase lattice of TiO₂ samples. And these co-doped TiO₂ photocatalysts showed enhanced photocatalytic activities for the degradation of methylene blue compared with monodoped TiO₂ ¹². Wang et al. synthesized V-N codoped TiO₂ nanocatalysts using a novel two-phase hydrothermal method applied in hazardous PCP-Na decomposition ¹³. Recently, Zou et al. investigated the energetic and electronic properties of N-V-codoped anatase TiO₂ (101) by first principles calculations to elucidate the relationship between the electronic structure and the photocatalytic performance of N-V-codoped TiO₂ ¹⁴. They also investigated the adsorption and decomposition behaviors of water molecule on the surface of N-V codoped anatase TiO₂ (101). It is found that the N–V-codoping could broaden the absorption spectrum of anatase TiO₂ to the visible-light region, and could enhance its quantum efficiency ¹⁵.

Nevertheless, few reports are currently available about V and N co-doping of TiO_2 nanotube arrays and their photoelectrochemical and photocatalytic properties as well. In this work, we adopt a sequence of electrochemical anodization and hydrothermal synthesis technique to fabricate V and N co-doped TiO_2 nanotube array films. For V and N codoped TNAs, the influence of morphology, structure and doping concentration on photoelectrochemical performance as well as photocatalytic activity for the degradation of methylene blue (denoted as MB) were investigated under visible light irradiation (\geq 420 nm).

Experimental

V, N co-doped TiO_2 nanotube arrays (TNAs) were fabricated by a combination of electrochemical anodization and a hydrothermal reaction. Firstly, highly ordered

TNAs were fabricated on a Ti substrate in a mixed electrolyte solution of ethylene glycol containing NH₄F and deionized water by a two-step electrochemical anodic oxidation process according to our previous reports ¹⁶. Then the amorphous TNAs were annealed at 500 °C for 3 h with a heating rate of 10 °C/min in air ambience to obtain crystalline phase. Interstitial nitrogen species were formed in the TNAs due to the electrolyte containing NH₄F or a lesser extent atmospheric nitrogen dissolved into the electrolyte during anodization ¹⁷. We denoted these single N-doped TNAs samples as N-TiO₂.

V and N codoped TNAs were prepared by a hydrothermal process. As-prepared N-TiO₂ was immersed in a Teflon-lined autoclave (120 mL, Parr Instrument) containing approximately 60 mL of NH_4VO_3 solution (with different concentration 0.5, 1, 3 and 5 wt %) as the source of both V and N. The samples were hydrothermally heated at 180 ° C for 5 h and then naturally cooled down to room temperature. Finally, all as-prepared samples were rinsed with deionized water and dried under high purity N₂ stream. The corresponding products (0.5%, 1%, 3%, 5%) were labeled as VN0.5, VN1, VN3, VN5.

The morphologies of the obtained samples were characterized with field emission scanning electron microscope (FESEM, FEI Nova NanoSEM 450). Phase structures of photocatalysts were analyzed by X-ray diffraction (XRD, Philips X'Pert Pro X-ray diffractometer; Cu K α radiation, λ =0.15418 nm). Surface composition of nanotube arrays was analyzed by X-ray photoelectron spectroscope (XPS) on a Kratos Axis Ultra System with monochromatic Al Ka X-rays (1486.6 eV). The binding energies (BE) were normalized to the signal for surface adventitious carbon at 284.8 eV.

Photoelectrochemical experiment was monitored by an electrochemical workstation (IM6ex, Germany). TNAs film (an active area of 4 cm^2) and platinum foil electrode were used as working electrode and counter electrode, and saturated calomel electrode (SCE) acted as reference electrode, respectively. 1 M KOH aqueous solution was used as a supporting electrolyte and purged with N₂ for 20 min before measurement to remove dissolved oxygen. A 300 W xenon lamp (PLS-SXE300,

Beijing Bofeilai Technology Co, Ltd.) with a cutoff filter ($\lambda \ge 420$ nm) was used as the visible light source. The intensity of visible light irradiated on tested samples was 16 mW · cm⁻².

MB solution was chosen as a target pollutant, with an initial concentration of 10mg/L, since it is non-biodegradable and extensively used in textile industry. TNAs films (active area of 4 cm²) were dipped into 25 mL of MB solution. A 300W xenon lamp with a cutoff filter ($\lambda \ge 420$ nm) as visible light source in the photocatalytic experiments. Prior to irradiation, the solution with TiO2 sample was magnetically stirred in the dark for 30 min to establish adsorption-desorption equilibrium. The changes of concentration were monitored for analyzing the photocatalytic activity at 30 min irradiation time intervals by measuring the absorption at 664 nm using an SP-2000 spectrophotometer. Though the amount of MB adsorption is different for different samples before light irradiaiton, the adsorption amount has been subtracted when the photocatalytic activity is calculated. The photocatalytic activity is calculated by (C_0 - C) / C_0 $\times 100\%,~C_o$ is MB concentration after adsorption–desorption equilibrium in dark, C is MB concentration after photocatalytic reaction under visible light irradiation. This calculation method of photocatalytic activity can exclude the influence of adsorption amount due to the amount of MB adsorption is different for different samples.

Terephthalic acid (denoted as TA) was used as a probe to monitor the change of hydroxyl radical content of all TNAs samples under visible light irradiation, since TA can readily react with •OH radical to generate TAOH which emits fluorescence around 426 nm under the excitation of its own absorption band at 312 nm. Experimental procedures are similar to the measurement of photocatalytic activity except that MB aqueous solution was replaced by TA aqueous solution (6 mmol·L⁻¹) with a concentration of NaOH solution (20 mmol·L–1). Photoluminescence (PL) spectra of generated TAOH were measured on a Gilden FluoroSENS fluorescence spectrometer. The content of •OH radical over different TNAs surface under visible

light irradiation was compared based on PL data.

Results and discussion

Top-view FESEM images of N-TiO₂ and VN3 samples are presented in Fig. 1. Before codoping with vanadium via hydrothermal process, the nanotubes of N-TiO₂ sample are open at the top end and have an average diameter of 110 nm (Fig. 1a), and their nanotube array structure can be clearly observed from the inset of Fig.1a. Moreover, SEM observation indicates that there is no apparent structural transformation of the TNAs sample after hydrothermal co-doping process (Fig.1b). The appropriate doping amount of V and N does not change the morphology of nanotubes. Fig. 1c shows the EDX data of codoped VN3 sample. There are N and V peaks in the EDX pattern that gave convincing evidence for the presence of nitrogen and vanadium on the surface of TiO₂ nanotube arrays. The mole ratio of N/Ti and V/Ti was estimated to be ca.12.7% and 1.8%, respectively.

Fig. 2 shows the XRD patterns of the N-TiO₂ and V, N codoped TNAs with various doping amounts. The diffraction peaks of all samples were ascribed to pure anatase TiO₂ diffraction pattern, which were consistent with the values in the standard card (JCPDS 21-1272)¹⁸. The results indicate that V and N codoping has no effect on the crystal structure and phase composition of TNAs. Moreover, no V_2O_5 phase could be observed in all the XRD patterns. Accordingly, we propose that V ions may be incorporated into the titania lattice and replaced titanium ions to form V-O-Ti bonds.

Transition metal ions as dopant incorporated into other compounds might distort the crystal lattice of the doped materials. Thus, we enlarged the anatase (101) plane of samples in the inset of Fig. 2b to check the structural change. Compared with N-TiO₂, peak position of V, N codoped TiO₂ shifted toward a higher diffraction angle gradually, suggesting that V ions might be successfully incorporated into the crystal lattice of anatase TiO₂ as vanadyl groups (V⁴⁺) or polymeric vanadates (V⁵⁺) and substituted for Ti⁴⁺, because the ionic radii of V⁴⁺(0.72 Å) and V⁵⁺(0.68 Å) were both slightly smaller than that of Ti⁴⁺(0.75 Å) ¹⁹.

Figure 3 presents the high-resolution XPS spectra of V 2p, N 1s, Ti 2p and O 1s regions for N-TiO₂ and VN3 samples. Fig. 3a shows the high resolution XPS spectra

and corresponding fitted XPS for the N 1s region of N-TiO₂ and VN3. A broad peak extending from 397 eV to 403 eV is observed for all samples. The center of the N1s peak locates at ca. 399.7 eV and 399.4 eV for N-TiO₂ and VN3 sample, respectively. These two peaks are much higher than that of typical binding energy of N1s (396.9 eV) in TiN ²⁰, indicating that the N atoms in all samples interact strongly with O atoms ²¹. The binding energy of 399.7 eV and 399.4 eV are attributed to oxidized nitrogen similar to NO_x species, meaning Ti-N-O linkage possibly formed on the surface of N-TiO₂ and VN3 samples ^{21, 22}.

Fig. 3b presents the high resolution V 2p spectra of VN3 sample. The V 2p peaks appearing at about 516.3 eV and 523.8 eV are assigned to $2p_{3/2}$ and $2p_{1/2}$ electronic states of V⁴⁺, 516.9 eV and 524.4 eV are attributed to $2p_{3/2}$ and $2p_{1/2}$ of V⁵⁺, respectively ^{23, 24}. This indicates that the V⁴⁺ and V⁵⁺ions were successfully incorporated into the crystal lattice of anatase TiO₂ and substituted for Ti⁴⁺ions, which is accordance with relevant XRD analytical results. The concentrations of V and N in VN3 derived from XPS analysis were 3.38% and 4.21% (at.%), respectively. The molar ratios of N/Ti on the surface of N-TiO₂ and VN3 were 2.89% and 14.04%, indicating obvious increase of N doping content by hydrothermal codoping with V and N.

Fig.3c and d present high-resolution spectra of Ti 2p and O1s of N-TiO2 and VN3 samples. Compared with N-TiO₂ sample, a significant negative shift is observed for Ti 2p in Fig.3c and O 1s in Fig.3d after V and N were doped into TiO₂ (VN3) by hydrothermal codoping process. One possible explanation is that Ti^{4+} has been reduced to Ti^{3+} , which results in a negative shift of binding energies of Ti 2p for the V, N codoped TiO₂ samples. On the other hand, oxygen molecules can be dissociatively absorbed on the oxygen vacancies induced by doping N, thereby leading to a slight shift to lower binding energy of O 1s of TiO₂ lattice oxygen (Ti–O–Ti)²⁵.

To investigate the effect of V, N codoping of TiO_2 nanotube arrays on charge carriers separation and electron transfer process, a series of the PEC experiments were conducted. Fig.4a shows the photocurrent-potential dependence of N-TiO₂ and V,N codoped TNAs samples under visible light irradiation. The photocurrent density of V,N codoped TNAs is significantly high than that of N-TiO₂ at all bias potential, indicating a lower recombination of photogenerated electrons and holes after V and N codoping. Moreover, enhanced photocurrent density was observed with the increase of vanadium doping amount and a highest photocurrent value of 5.8 μ A/cm² was obtained for VN3 sample. However, further increasing the doping amount, the photocurrent decreased to 1.2 μ A/cm² for VN5. It indicated that there is an optimal concentration for V,N codoping.

The generated photocurrents also increased significantly with an increase in the applied voltage. The higher the applied potential, the higher the photocurrent generated by all samples. The small observed photocurrent of N-TiO₂ sample could be ascribed to possible pollutants on electrode surfaces or impurities or species in the KOH solution. The high photocurrent conversion efficiency of V,N co-doped TiO₂ nanotube array films may be attributed to improved optical absorption and increased in the crystallinity caused by the hydrothermal co-doping process.

Furthermore, the transient photocurrents measured at fixed bias voltage of 0.8 V vs. SCE with a visible light pulse of 50s were also shown in Fig.4b. All samples showed good photoresponses and highly reproducible for numerous on–off cycles under the light on and light off conditions. V, N codoped TNAs exhibited higher photocurrents than that of N-TiO₂ under visible light irradiation. The VN3 sample exhibited highest photocurrent of about 4.5 μ A/cm². These results further inferred that V, N codoped TiO₂ nanotube arrays possess good photo-responsive to generate and separate photo-induced electrons and holes ²⁶. However, excessive vanadium content may cause a detrimental effect, which acted as recombination centers to trap the charge carriers and resulted in a low quantum yield. From above PEC experimental results optimum content of V codoped into TiO₂ nanotube arrays play an important role in maximizing the photocurrent density mainly attributed to the effective charge carriers separation and improve the charge carriers transportation.

Photocatalytic activities of all samples were evaluated by using methylene blue as the target pollutant. Fig.5a shows the degradation curves of MB over N-TiO₂ and V, N codoped TNAs under the visible light. It reveals that the order of photocatalytic activity of TNAs was VN3 > VN1 > VN0.5 > N-TiO₂> VN5. The photocatalytic activity of V, N codoped TNAs was enhanced and then decreased with an increase in the doping content of vanadium. V, N codoped TNAs possess much higher photocatalytic activity under visible light irradiation than N-TiO₂ sample except VN5 sample. The overloaded vanadium dopant of VN5 may result in channel plugging and fast recombination of hole and electron pairs ²⁷. Fig.5b shows the kinetic linear simulation curve of MB over N-TiO₂ and V, N codoped TNAs under the visible light. The decomposition kinetics was analyzed according to physical chemistry principles. The above degradation reactions followed a Langmuir–Hinshelwood apparent first order kinetics model due to the low initial concentrations of reactants. The relative concentrations of MB were fitted by the apparent first order rate equation as follows: - ln (C/C₀) = kt, Where k is the apparent reaction rate constant.VN3 sample showed the highest lowing rate in the degradation of MB with a rate constant of 0.0136 min⁻¹, which was approximately 3.60 times higher than that of N-TiO₂.

The separation efficiencies of photo-induced electrons and holes under visible light irradiation of N-TiO₂ and V, N codoped TNAs samples were further studied by detecting the production of hydroxyl radicals. Hydroxyl radicals are mainly generated from the oxidative reaction between photo-induced holes and H₂O or OH⁻, and the reductive reaction between photo-induced electrons, O₂ and H⁺. So that the amount of hydroxyl radicals produced corresponds to the separation efficiencies of photo-induced electrons and holes as well as the photocatalytic activity. Moreover, the experiment of measuring active hydroxyl radicals can avoid the dye self-photosensitization effect and prove photocatalytic activity under visible light. Therefore, to further confirm the difference of photocatalytic activity of the prepared samples, the hydroxyl radical was monitored by a PL technique using TA as the fluorescence probe on the surface of TNAs under visible light illumination.

Fig.6a shows the changes of PL spectra of TA solution with irradiation time for VN3 sample. A gradual increase in PL intensity at about 425 nm is observed with increasing irradiation time for VN3 sample. However, no PL increase was observed in the absence of visible light or TNAs. This suggests that the fluorescence is originated

from the chemical reactions between TA and \cdot OH produced at the codoped TNAs /water interface under visible light irradiation ²⁸.

Fig.6b shows the comparison of PL intensity of TA solution for N-TiO₂ and V+N codoped TNAs samples under visible light irradiation for 1h. The amount of hydroxyl radicals produced over VN3 is higher than those over all other samples, which is consistent with the photocatalytic activity result shown in Fig.5. Hydroxyl radical experiments further confirm that hydroxyl radicals are active species during photocatalytic reactions. On the other hand, the formation rate of hydroxyl radicals has a positive relation with the photocatalytic activity 29 .

Conclusions

In summary, visible light responsive TiO₂ nanotube arrays by V and N codoping are successfully fabricated by a simple two-step method. All V and N co-doped TNAs exhibit fine tubular structures after hydrothermal codoping process. XPS data indicate that N is present in the forms of Ti-N-O and V incorporates into the lattice of TiO₂ in V+N co-doped TNAs. V and N doping amount exhibit a great influence on the photocatalytic activity and photoelectrochemical properties of the TiO₂ nanotube array films. VN3 sample presents highest photocatalytic activity for MB degradation, largest formation rate of hydroxyl radicals and photocurrent under visible light irradiation due to the synergetic effects of several factors including effective separation of electron-hole pairs and remaining tubular structures. This study provides a new approach to successfully enhance visible light photocatalytic activity.

Acknowledgements

The authors thank the National Natural Science Foundation of China (no.21203054) and Program for Changjiang Scholars and Innovation Research Team in University (no. PCS IRT1126).

References

- 1. Y. C. Nah, I. Paramasivam and P. Schmuki, *ChemPhysChem*, 11, 2698 (2010).
- 2. X. Chen and S. S. Mao, *Chemical reviews*, 107, 2891 (2007).
- 3. L. G. Devi and R. Kavitha, Applied Catalysis B: Environmental, 140, 559 (2013).
- 4. R. Long and N. J. English, *Applied Physics Letters*, 94, 132102 (2009).
- 5. W.-J. Yin, H. Tang, S.-H. Wei, M. M. Al-Jassim, J. Turner and Y. Yan, *Physical Review B*, 82, 045106 (2010).
- 6. T.-D. Nguyen-Phan, M. B. Song, H. Yun, E. J. Kim, E.-S. Oh and E. W. Shin, *Applied Surface Science*, 257, 2024 (2011).
- 7. X. Liang, S. Zhu, Y. Zhong, J. Zhu, P. Yuan, H. He and J. Zhang, *Applied Catalysis B:* Environmental, 97, 151(2010).
- 8. T.-B. Nguyen, M.-J. Hwang and K.-S. Ryu, *Applied Surface Science*, 258, 7299 (2012).
- 9. B. Liu, X. Wang, G. Cai, L. Wen, Y. Song and X. Zhao, *Journal of hazardous materials*, 169, 1112 (2009).
- 10. J. Wang, D. N. Tafen, J. P. Lewis, Z. Hong, A. Manivannan, M. Zhi, M. Li and N. Wu, *Journal* of the American Chemical Society, 131, 12290 (2009).
- 11. R. Asahi, T. Morikawa, T. Ohwaki, K. Aoki and Y. Taga, Science, 293, 269 (2001).
- 12. D.-E. Gu, B.-C. Yang and Y.-D. Hu, *Catalysis Communications*, 9, 1472 (2008).
- 13. J. Liu, R. Han, Y. Zhao, H. Wang, W. Lu, T. Yu and Y. Zhang, *The Journal of Physical Chemistry C*, 115, 4507 (2011).
- 14. Z. Zhao, Z. Li and Z. Zou, *ChemPhysChem*, 13, 3836 (2012).
- 15. Z. Zhao, Z. Li and Z. Zou, The Journal of Physical Chemistry C, 117, 6172 (2013).

- M. Zhang, J. Wu, D. Lu and J. Yang, *International Journal of Photoenergy*, 2013, 471674 (2013).
- 17. O. K. Varghese, M. Paulose, T. J. Latempa and C. A. Grimes, *Nano letters*, 9, 731 (2009).
- 18. S. Dai, Y. Wu, T. Sakai, Z. Du, H. Sakai and M. Abe, *Nanoscale research letters*, 5, 1829 (2010).
- Z. Zhang, C. Shao, L. Zhang, X. Li and Y. Liu, *Journal of colloid and interface science*, 351, 57 (2010).
- 20. N. C. Saha and H. G. Tompkins, Journal of Applied Physics, 72, 3072 (1992).
- 21. Q. C. Xu, D. V. Wellia, R. Amal, D. W. Liao, S. C. Loo and T. T. Tan, *Nanoscale*, 2, 1122 (2010).
- 22. E. Wang, T. He, L. Zhao, Y. Chen and Y. Cao, Journal of Materials Chemistry, 21, 144 (2011).
- 23. G. Silversmit, D. Depla, H. Poelman, G. B. Marin and R. De Gryse, *Journal of Electron Spectroscopy and Related Phenomena*, 135, 167 (2004).
- 24. G. Silversmit, D. Depla, H. Poelman, G. B. Marin and R. De Gryse, *Surface Science*, 600, 3512 (2006).
- C. Xiao-Quan, L. Huan-Bin and G. Guo-Bang, *Materials Chemistry and Physics*, 91, 317 (2005).
- 26. M. Sun and X. Cui, *Electrochemistry Communications*, 20, 133 (2012).
- 27. S. Liu, T. Xie, Z. Chen and J. Wu, Applied Surface Science, 255, 8587 (2009).
- 28. J. Yu, G. Dai and B. Cheng, The Journal of Physical Chemistry C, 114, 19378 (2010).
- 29. J. Yu and B. Wang, Applied Catalysis B: Environmental, 94, 295 (2010).

Figure Captions

Figure 1. FESEM top views for N-TiO₂ (a) and VN3 (b) samples. EDX of VN3 sample (c).

Figure 2. XRD patterns (a) and the enlargement of the anatase (101) peaks (b) for N-TiO₂, VN0.5, VN1, VN3 and VN5 samples.

Figure 3. High-resolution XPS spectra of (a) N 1s, (b) V 2p, (c) Ti 2p and (d) O1s for N-TiO₂ and VN3 samples.

Figure 4. Photocurrent density vs applied potential curves (a) and photocurrent responses in light on-off process at applied voltage of 0.8 V (vs SCE) (b) under visible light irradiation for N-TiO₂, VN0.5, VN1, VN3 and VN5.

Figure 5. Concentration change (a) and photocatalytic degradation rate (b) of MB in the presence of N-TiO₂ and V+N codoped TiO₂ nanotube arrays under visible light irradiation.

Figure 6. (a) PL spectral changes with visible light irradiation time on VN3 sample in TA solution. (b) Comparison of PL spectra of the TiO_2 nanotube arrays before and after codoping in TA solution under visible light irradiation at a fixed 1h.





活时间(秒): 50.0 0 Cnts 0.000 keV 探测器: Octane Plus Det

Figure 1. FESEM top views for N-TiO₂ (a) and VN3 (b) samples. EDX of VN3 sample (c).

8.(

Figure 2



Figure 2. XRD patterns (a) and the enlargement of the anatase (101) peaks (b) for N-TiO₂, VN0.5, VN1, VN3 and VN5 samples.





Figure 3. High-resolution XPS spectra of (a) N 1s, (b) V 2p, (c) Ti 2p and (d) O1s for N-TiO₂ and VN3 samples.

Figure 4



Figure 4. Photocurrent density vs applied potential curves (a) and photocurrent responses in light on-off process at applied voltage of 0.8 V (vs SCE) (b) under visible light irradiation for N-TiO₂, VN0.5, VN1, VN3 and VN5.





Figure 5. Concentration change (a) and photocatalytic degradation rate (b) of MB in the presence of N-TiO₂ and V+N codoped TiO₂ nanotube arrays under visible light irradiation.

Figure 6



Figure 6. (a) PL spectral changes with visible light irradiation time on VN3 sample in TA solution. (b) Comparison of PL spectra of the TiO_2 nanotube arrays before and after codoping in TA solution under visible light irradiation at a fixed 1h.