

Optical vibrations in alkali halide crystals

Anton Stupka

January 1, 2022

*Oles Honchar Dnipropetrovsk National University, Gagarin ave., 72, 49010 Dnipropetrovsk, Ukraine
antonstupka@mail.ru*

We consider long-wave phonon-polaritons and longitudinal optical phonons in alkali-halide ionic crystals. The model of point charges that are polarized in the self-consistent electromagnetic field in a dielectric environment is used. The standard dispersion laws for both branches of phonon-polaritons and longitudinal optical phonons are obtained. The transversal optical phonon frequency is found from the electrostatic equilibrium condition. It is proved by comparison with tabular data that the found frequency coincides with the ion plasma frequency multiplied on the relation $\sqrt{(\varepsilon_\infty + 2)/(3(\varepsilon_0 - \varepsilon_\infty))}$, where ε_∞ and ε_0 are the high-frequency dielectric constant and the static one respectively.

keywords Alkali-halide ionic crystal; self-consistent electromagnetic field; long-wave oscillations; phonon-polariton; longitudinal optical phonon; electrostatic equilibrium; dielectric constant.

PACSPhonons in crystal lattices, 63.20. e, Electrostatic waves and oscillations plasma waves, 52.35.Fp, Collective effects 71.45.-d

1 Introduction

The simplest and best understood of the crystals containing two different kinds of atoms are unquestionably the alkali halides. The positive and negative ions lie on two interpenetrating cubic lattices. According to the Born theory of ionic crystals (1), there are ions with unit (positive or negative) charge, the binding being largely due to the Coulomb interaction between the ions, and the crystal being stabilized by short-range repulsive forces between nearest neighbors. The importance of taking into account an electromagnetic interaction when considering long-wave optical vibrations in ionic solids is shown in (2). Deep analysis of early theories was proposed in (3). Often an effective charges is introduced to satisfy the experimental data for optical frequencies. The Szigeti effective charge is essentially less than elementary one for the *NaCl*-type alkali halides (4). In recent works ab initio calculations are performed to find the dynamical matrix which allows to calculate the phonon frequencies of an ionic crystal (5),(6).

The long-wave acoustical properties of an alkali halide crystal are closely related with electrostatic interaction in it and transversal acoustic phonon velocity in the such crystal is defined by the electrostatic energy (7). We will show that optical phonon frequencies are defined via electrostatic properties of the alkali-halide crystal too. In the recent paper (8) the consideration of the high-frequency optical vibrations in ionic crystals with two atoms per unit cell as plasma oscillations

of point charges is proposed. Further presentation puts designed to transfer the results of (8) to low-frequency limit of phonon-polaritons.

2 Transversal optical phonon frequency

Lets consider long-wave compared with a lattice constant high-frequency oscillations in the diatomic ionic crystals that allows using the macroscopic consideration. We will consider ions as point charges but use a high-frequency permittivity ε_∞ to describes the electronic (atomic) polarization. Then each ion becomes a dipole in the external electric field. As well know, when an ion of each node is the center of cubic symmetry that allows to use the Lorentz relation for a local field. The local field acting on the ions is expressed through the mean field as follows (27.30) from (9):

$$\mathbf{E}^{loc} = (\varepsilon_\infty + 2)/3\mathbf{E}. \quad (1)$$

Elastic force is proportional to the displacement gradients that in long-wave approximation is neglected. Thermal motion of ions a fortiori is neglected, since the velocity of thermal motion less then velocity of acoustic waves. Damping will not be taken into account. Shall consider small fluctuations in non-magnetic media, then one can omit the nonlinear magnetic part of the Lorentz force. So we write the linearized equations of motion for ions in this model

$$\partial \mathbf{v}_+ / \partial t = -\omega_0^2(\mathbf{u}_+ - \mathbf{u}_-) + e\mathbf{E}^{loc}/M_+, \quad (2)$$

$$\partial \mathbf{v}_- / \partial t = -\omega_0^2(\mathbf{u}_- - \mathbf{u}_+) - e\mathbf{E}^{loc}/M_-. \quad (3)$$

This sign \pm corresponds to a charge, M_\pm is a mass, respectively, of positively and negatively charged ions, ω_0 is a resonant frequency (27.47) from (9). The full derivative with respect to time coincides with the partial one after linearization. It is convenient to introduce a relative displacement of sublattices $\mathbf{u} = \mathbf{u}_+ - \mathbf{u}_-$. As easy to see, we can obtain from equations [2] and [3]

$$\partial^2 \mathbf{u} / \partial t^2 = -\omega_0^2 \mathbf{u} + e(\varepsilon_\infty + 2)/(3M)\mathbf{E}, \quad (4)$$

where a reduced mass of a crystal unit cell $M = M_+M_-/(M_+ + M_-)$ is introduced.

Then we can write an ionic (displacement) polarization density in the linearized case

$$\mathbf{P}_i = en_0\mathbf{u}, \quad (5)$$

where ions are considered as point charges with the equilibrium density n_0 . Now we obtain the relation for the dielectric induction for an isotropic case that is linearly related to the electric field strength \mathbf{E} in the approximation of small oscillations (10),(11).

$$\mathbf{D} = \varepsilon_\infty \mathbf{E} + 4\pi \mathbf{P}_i. \quad (6)$$

On the other hand, we have the relation for the dielectric induction via the dielectric constant ε_0 for the static situation

$$\mathbf{D}_0 = \varepsilon_0 \mathbf{E}. \quad (7)$$

Then we obtain a relation between field \mathbf{E} and displacement \mathbf{u} from the equations [6] and [7] in the static case

$$\varepsilon_0 \mathbf{E} = \varepsilon_\infty \mathbf{E} + 4\pi en_0 \mathbf{u}. \quad (8)$$

The second relation between field \mathbf{E} and displacement \mathbf{u} can be obtained from the equation [4] in the static case

$$0 = -\omega_0^2 \mathbf{u} + e(\varepsilon_\infty + 2)/(3M)\mathbf{E}. \quad (9)$$

That two equations allow us to find the resonant frequency ω_0 without finding the force matrix only from the condition of electrostatic equilibrium:

$$\omega_0 = \sqrt{\frac{4\pi e^2 n_0 (\varepsilon_\infty + 2)}{3M(\varepsilon_0 - \varepsilon_\infty)}}. \quad (10)$$

As well known, the coefficient ω_0 in the [4] is correspond to the transversal optical phonon frequency (36.12) from (12).

To compare with tabulated values of frequency ω_0^{tab} it is convenient in the expression [10] to pass from the density of ions of the same sign to the mass density of the crystal ρ : $\frac{n_0}{M} = \frac{\rho}{M_+ M_-}$. Then we can write

$$\omega_0 = 1.70156 \cdot \sqrt{\frac{\rho(\varepsilon_\infty + 2)}{3M_+ M_- (\varepsilon_0 - \varepsilon_\infty)}} 10^{-9} c^{-1}. \quad (11)$$

For comparison, we use the data of Table 2.2. from (13) for longitudinal oscillation frequencies ω_0^{tab} . Values of density ρ of ionic crystals are taken from (15).

Table 1: Transversal optical frequencies of some alkali halide crystals

Crystal	$\rho \text{ g/cm}^3$	ε_0	ε_∞	$\omega_0^{tab} 10^{13} \text{Hz}$	$\omega_0 10^{13} \text{Hz}$	ω_0/ω_0^{tab}
LiF	2.64	8.9	1.9	5.783	6.25	1.08
NaF	2.79	5.1	1.7	4.502	4.93	1.10
NaCl	2.17	5.9	2.25	3.089	3.29	1.07
NaBr	3.21	6.4	2.6	2.524	2.72	1.08
KCl	1.99	4.85	2.1	2.675	2.74	1.02
KBr	2.75	4.9	2.3	2.129	2.26	1.06
KI	3.12	5.1	2.7	1.902	2.08	1.09
RbCl	2.76	4.9	2.2	2.185	2.23	1.02
RbBr	2.78	4.9	2.3	1.658	1.54	0.93
RbI	3.55	5.5	2.6	1.413	1.35	0.95
CsCl	3.97	7.2	2.6	1.865	1.72	0.92
CsBr	4.44	6.5	2.8	1.375	1.35	0.98

As shown in the Table 1, we have a good coincidence of values obtained from the formula [11] with known ones (13). The Szigeti expression (14) (see, also, (2.67) from (13)) contains an extra factor $\sqrt{(\varepsilon_\infty + 2)/3}$ comparing with [10] that worsens the agreement with experimental data.

3 Phonon-polaritons and longitudinal optical phonons

The self-consistent mean electromagnetic field must satisfy Maxwell's equations in a dielectric.

$$\partial \mathbf{D} / \partial t = c \text{rot} \mathbf{B}, \quad (12)$$

$$\partial \mathbf{B} / \partial t = -c \text{rot} \mathbf{E}. \quad (13)$$

Then we have a homogeneous system of time equations [4], [12] and [13] and the coupling equations [1], [5] and [6] for high-frequency long-wave vibrations of the ionic lattice and the self-consistent electromagnetic field.

Then we can obtain an equation for electric field waves from mentioned equations system. Lets take the derivative with respect to time of the equation [12] and substitute the derivatives $\partial \mathbf{B} / \partial t$ from [13]

$$\partial^2 \varepsilon_\infty \mathbf{E} / \partial t^2 = -c^2 \nabla \times (\nabla \times \mathbf{E}) - 4\pi e n_0 \partial^2 \mathbf{u} / \partial t^2. \quad (14)$$

In obtained equations it is convenient to pass to the Fourier-components by the following rule

$$\mathbf{E}(\mathbf{x}, t) = \int d^3 k d\omega \mathbf{E}(\mathbf{k}, \omega) e^{i\mathbf{k}\mathbf{x} - i\omega t} / (2\pi)^4. \quad (15)$$

Then we obtain from the [4]

$$\mathbf{u} = \frac{e(\varepsilon_\infty + 2)}{(\omega_0^2 - \omega^2)3M} \mathbf{E}. \quad (16)$$

Lets divide the field into potential and vortical parts $\mathbf{E} = \mathbf{E}^\parallel + \mathbf{E}^\perp$. Then we obtain linear homogeneous algebraic equations

$$-\omega^2 \mathbf{E}^\parallel = -\frac{4\pi e^2 n_0 (\varepsilon_\infty + 2)}{3\varepsilon_\infty M} \mathbf{E}^\parallel \frac{\omega^2}{\omega^2 - \omega_0^2}. \quad (17)$$

$$-\omega^2 \mathbf{E}^\perp = -\frac{c^2}{\varepsilon_\infty} k^2 \mathbf{E}^\perp - \frac{4\pi e^2 n_0 (\varepsilon_\infty + 2)}{3\varepsilon_\infty M} \mathbf{E}^\perp \frac{\omega^2}{\omega^2 - \omega_0^2}, \quad (18)$$

From [17] omitting trivial $\omega = 0$ it is obtained a longitudinal oscillations frequency

$$\omega_L^2 = \omega_0^2 + 4\pi e^2 n_0 (\varepsilon_\infty + 2) / (3M\varepsilon_\infty), \quad (19)$$

that matches to the longitudinal phonons. We can rewrite [19] using [10]

$$\omega_L^2 = \frac{4\pi e^2 n_0 (\varepsilon_\infty + 2)}{3M} \left(\frac{1}{(\varepsilon_0 - \varepsilon_\infty)} + \frac{1}{\varepsilon_\infty} \right) = \omega_0^2 \frac{\varepsilon_0}{\varepsilon_\infty}, \quad (20)$$

that is the famous Lyddane-Sachs-Teller formula (16).

From the equation [18] we obtain the upper phonon-polariton dispersion law for the high-frequency $\omega \gg \omega_0$ case

$$\omega^2 = c^2 k^2 / \varepsilon_\infty + 4\pi e^2 n_0 (\varepsilon_\infty + 2) / (3M\varepsilon_\infty). \quad (21)$$

That result is analogous to obtained in (8). Solution [21] became the photon branch for large k . On the other hand, the relation [21] is the dispersion law for transversal plasma waves (10) in ionic plasma with a multiplier $\sqrt{(\varepsilon_\infty + 2)/3}$.

In the general case we have from [18]

$$\omega^4 - \omega^2 (\omega_L^2 + c^2 k^2 / \varepsilon_\infty) + \omega_0^2 c^2 k^2 / \varepsilon_\infty = 0. \quad (22)$$

that coincides with (12.6) from (17) and gives both branches of phonon-polaritons. Now we can see that [22] has the solutions (12.7) from (17)

$$\omega^2 = \frac{1}{2}(\omega_L^2 + c^2 k^2 / \varepsilon_\infty \pm \sqrt{(\omega_L^2 + c^2 k^2 / \varepsilon_\infty)^2 - 4\omega_0^2 c^2 k^2 / \varepsilon_\infty}) \quad (23)$$

The lower branch for short waves gives the expected limit $\omega \rightarrow \omega_0$ for transversal optical phonon frequency [10].

4 Conclusion

Then, the transversal optical phonon frequency in an ionic crystal is found without using any empirical fits. Of course, an ionicity of compounds is not absolute and measurement accuracy of used dielectric constants is not very high. According to the Table 1, then we have a good coincidence of values obtained from the formula [11] with known ones. Correct dispersion laws for both branches of phonon-polaritons and longitudinal optical phonons are obtained. Given consideration generalized the work (8), where ions regarded as free charges for high frequencies.

References

- [1] (1) M. Born, K. Huang, Dynamical theory of crystal lattices (Clarendon, Oxford, 1958).
- [2] (2) Kun Huang, Proc. Roy. Soc. **A208**, 352 (1951).
- [3] (3) A. D. B. Woons, W. Cochran, B. N. Bnaczaousa, Phys. Rev. **119**, N 3, 980 (1960).
- [4] (4) B. G. Dick, JR, A. W. Overhauser, Phys. Rev. **11**, N 1, 90 (1958).
- [5] (5) Priya Sony, Alok Shukla, Phys. Rev. B **77**, 075130 (2008).
- [6] (6) Yi Wang, Shunli Shang, Zi-Kui Liu, Long-Qing Che, Phys. Rev. B **85**, 224303 (2012).
- [7] (7) A.A. Stupka, Ukr. J. Phys. **58**, N 12, 1156 (2013).
- [8] (8) A.A. Stupka, Ukr. J. Phys. **58**, N 9, 863 (2013).
- [9] (9) N.W. Ashcroft, N.D. Mermin, Solid state physics (Cengage Learning, Inc , New York, 1976).
- [10] (10) Electrodynamics of Plasma, edited by A.I. Akhiezer, (Nauka, Moscow, 1974, in Russian).
- [11] (11) L.D. Landau, E.M. Lifshitz, L.P. Pitaevskii, Electrodynamics of Continuous Media. Vol. 8 (2nd ed.), (Butterworth-Heinemann, 1984).
- [12] (12) O. Madelung, Theory of Solid (Nauka, Moscow, 1980, in Russian).
- [13] (13) J.A. Reissland, The physics of phonons (John Wiley and sons LTD, London-New York-Sydney-Toronto, 1973).
- [14] (14) B. Szigeti, Trans. Far. Soc., **45**, 155 (1949).

- [15] (15) V.A. Rabinovich, Z.Ya. Havin, A brief chemical directory (Himiya, Leningrad, 1978, in Russian).
- [16] (16) R. H. Lyddane, R. G. Sachs, and E. Teller, Phys. Rev. **59**, 673 (1941).
- [17] (17) A.S. Davydov, Theory of Solids (Nauka, Moscow, 1976, in Russian).