

Comment on arXiv:1807.08572: a plausible explanation of the giant diamagnetism found in Au-Ag nanostructures

NAVINDER SINGH*

Physical Research Laboratory, Ahmedabad, India.

navinder.phy@gmail.com

December 31, 2021

Abstract

In a recent comment (arXiv:1906.05742) on the preprint (arXiv:1807.08572) entitled "Coexistence of Diamagnetism and Vanishingly Small Electrical Resistance at Ambient Temperature and Pressure in Nanostructures", it is pointed out that the reduction of the four-probe resistance (R_{4P}) to zero value is accompanied by a rise in the two probe resistance (R_{2P}) in the same temperature range. This curious correlation between R_{4P} and R_{2P} is said to be pointing towards a non-superconducting "conductance percolation" transition (rather than "percolating superconducting transition" as proposed in the revised version of arXiv:1807.08572). The explanation offered in preprint arXiv: 1906.05742 is quite reasonable, but the author leaves open the question of giant diamagnetism. In this short comment I suggest a plausible cause of the giant diamagnetism found in nanostructures. It could be due to gapped electronic energy spectrum of nanoparticles which is due to quantum confinement effects, and that suppresses the electronic scattering mechanism leading to a very high value of Langevin diamagnetism.

In the revised version, arXiv:1807.08572, entitled "Coexistence of Diamagnetism and Vanishingly Small Electrical Resistance at Ambient Temperature and Pressure in Nanostructures", and another preprint, arXiv: 1906.02291, entitled "Current-Voltage characteristics in Ag/Au nanostructures at resistive transitions", Thapa, Pandey, and collaborators

presents detailed information about their measurements of zero resistance and diamagnetic transitions found in some of the nanostructured samples prepared by them. It is concluded that in some of the nanostructures exhibit superconducting-like transition at ambient conditions.

In a recent comment (arXiv: 1906.05742) it is suggested that the transition observed

*Cell Phone: +919662680605

by IISc team could be a percolating conductance threshold rather than a percolating superconducting transition. This is nicely explained using figure 2 in arXiv: 1906.05742 and it is argued that minute internal structural deformations due to thermal stress (on changing temperature) lead to some sort of redistribution of current channels in the nanostructure which can further lead to four probe terminals having same potential. In other words no potential difference between them! This could be quite possible and a possible signature of it is the simultaneous rise in two probe resistance when four probe resistance drops to zero (refer to figure 2 in arXiv: 1906.05742).


In this communication, I point out that the giant diamagnetic transition observed in the nanostructures does not necessarily imply superconducting transition. My main point is the following. Induced Langevin diamagnetic susceptibility when an external magnetic field is applied is given by

$$\chi_L = -N^* \frac{e^2 \langle r^2 \rangle}{6m}. \quad (1)$$

This is generally small as $\sqrt{\langle r^2 \rangle}$ is of the order of atomic radius. Now, imagine if $\sqrt{\langle r^2 \rangle}$ is stretched to the radius of a nanoparticle $\sqrt{\langle R^2 \rangle}$! Atomic radius is in Angstrom range whereas nanoparticle radius is in nanometers. Thus there could be an order of magnitude larger effect! But there are two complications: (1) there must be some mechanism which suppress the electronic scattering of electrons that

constitute surface currents, and (2) we need to estimate the number of such *long surviving* electrons at the surface of a nanoparticle. This number of surface electrons should be sizable to enhance the susceptibility (that factor N^* in equation (1)). One mechanism is the well known superconducting transition in which surface currents along the periphery of nanoparticles survive to very long time (via supercurrents). But there is another very important mechanism of suppression of electronic scattering at the surface as pointed out in[1]. It is something to do with gapped electronic states on the surface of nanoparticles. If this gap Δ is greater than $k_B T$, thermal scattering is suppressed, and surface currents can survive longer which further can lead to giant diamagnetism through equation (1), with $\langle r^2 \rangle$ replaced with $\langle R^2 \rangle$ where R is the radius of the nanoparticle. In the following we first calculate discrete electronic structure on the surface of a nanoparticle with a simple minded calculation, and then calculate the fraction of surface electrons. Next we calculate a critical radius of a nanoparticle by comparing the electronic energy gap with thermal energy. Particles with smaller radius than this critical radius can show giant diamagnetism. Then we calculate the number of surface electrons for which thermal scattering is suppressed and advance arguments why electronic scattering is suppressed when there is a gap in the excitation spectrum. Next, we will calculate susceptibility and compare that with atomic suscep-

tibility and show the possibility of giant diamagnetism. We end by discussing some important factors that are left out in these back-of-the-envelope calculations.



SURFACE STATES

Figure 1: Discrete electronic states on the surface of a nanoparticle.

Let R be the radius of a nanoparticle. Imposing periodic boundary condition on a closed orbit of a surface electron along the periphery of the nanoparticle (figure 1), we get quantized wavevectors $n\frac{2\pi}{L}$. The n th energy level is given by $E_n = \frac{n^2\hbar^2}{2mR^2}$, and the energy gap by

$$\Delta E_n = E_{n+1} - E_n = \frac{\hbar^2}{2mR^2}(2n+1). \quad (2)$$

When this gap becomes bigger than $k_B T$ for sufficiently larger n electronic scattering will be suppressed. But before working that out we need to calculate how many levels are populated at the surface, and this requires an estimate of the number of surface electrons. The number of surface electrons are estimated in the following way:

Let a be the lattice constant for the nanoparticle. And assume that area a^2 contributes one electron at the surface. Then the area $4\pi R^2$ contains $\frac{4\pi R^2}{a^2}$ electrons. In the interior of the nanoparticle, assume that volume a^3

contributes one electron. Then the volume of nanoparticle will contain $\frac{4\pi R^3}{3a^3}$ electrons. The ratio α of the number of surface electrons to the number of volume electrons is given by

$$\alpha = 3\frac{a}{R}. \quad (3)$$

If $a = 1 \text{ \AA}$ and $R = 1 \text{ nm}$, then $\alpha = 0.3$. That if there are $N = 10,000$ electrons in the interior of the nanoparticle, then 3000 will reside on the surface (there are several complicating factors which are discussed at the end of this note). A small fraction of those will be able to carry long lived surface currents. To calculate that number let us first calculate the number of filled surface energy levels (n). Clearly $2n = \alpha N$ where factor of 2 is for spin degeneracy. As $n \gg 1$, the energy gap (equation 2) for the highest filled surface levels is given by

$$\Delta E_n^* \simeq \frac{\alpha \hbar^2 N}{2mR_*^2}. \quad (4)$$

For the suppressing of scattering we must have $\Delta E_n^* > k_B T$. Thus, there is an upper limit to the radius at a given temperature

$$R^*(T) \leq \sqrt{\frac{3\hbar^2 N}{2mK_B T}} \left(\frac{a}{R}\right). \quad (5)$$

This is quite an important result but subject to some corrections (as explained in the last paragraph). If radius of a nanoparticle is less than $R^*(T)$, then it can support long lived surface currents and can show giant diamagnetism. Particles with bigger radius will not show diamagnetism.ⁱ

ⁱThis should be tested experimentally.

Next, we address the question of the suppression of the scattering rate for a gapped system. It was shown in[2] that if there is a gap in the electronic density of states around the Fermi level in a metal, the electronic scattering is exponentially suppressed:

$$\frac{1}{\tau(T)} \simeq e^{-\frac{\Delta}{k_B T}} f(T/\Theta_D). \quad (6)$$

This expression was obtained using the memory function formalism[3]. f is a scaling function and Θ_D is the Debye temperature[2]. It should not be difficult to repeat the calculation for discrete energy levels of a nanoparticles, and an expression for the scattering rate can be obtained. We assume that an expression similar to the above will be obtained which will show suppressed scattering rate. This is quite obvious, it will only change the details not the main argument (refer also to[1]).

For the calculation of diamagnetic susceptibility, we need to calculate the number of surface electrons that can support long lived surface currents. It is calculated in the following way:

The number of surface electrons for which thermal energy is of the order of the electronic energy gap is given by

$$N_{cut} = \frac{2mR^2k_B T}{\hbar^2}. \quad (7)$$

These electrons will be thermally scattered and cannot participate effectively in diamagnetizing surface currents. The electrons in which

we are interested are those which are thermally NOT scattered, and there number N^* is given by: (total number of surface electrons (αN)) - (N_{cut}) .

$$N^* = \alpha N - \frac{2mR^2k_B T}{\hbar^2}. \quad (8)$$

Collecting all this, we finally come to our main result: Diamagnetic susceptibility of the nanoparticle:

$$\chi_L^{nano} = - \left(\alpha N - \frac{2mR^2k_B T}{\hbar^2} \right) \frac{e^2 R^2}{6m}. \quad (9)$$

To get a feel for the enhanced effect let us compare it with atomic susceptibility ($\chi_L^{atomic} = N \frac{e^2 a^2}{6m}$) originating from the interior of the nanoparticle:

$$\frac{\chi_L^{nano}}{\chi_L^{atomic}} = \left(\frac{R}{a} \right)^2 \left(\alpha - \frac{2mR^2k_B T}{N\hbar^2} \right). \quad (10)$$

The second factor containing $K_B T$ is an order of magnitude small as compared to α for the relevant set of parameters. Thus it can be neglected. Substituting the value of α we get

$$\frac{\chi_L^{nano}}{\chi_L^{atomic}} \sim 3 \left(\frac{R}{a} \right) \sim 30. \quad (11)$$

This is an order of magnitude larger effect! This could be a cause behind the giant diamagnetic effect seen in IISc experiments on nanostructures. There are several important factors that we did not take into account in the above simple minded calculations. We collect those in the following paragraph (without going into their detailed calculations).

Left out important factors:

Although Fermi energies of bulk Silver and bulk Gold are the same (~ 5.5 eV), but for a nano-scaled Silver particle it is modified due to quantum confinement effects. When two metals of different Fermi energies are joined together diffusion of electrons from higher Fermi energy metal to lower Fermi energy metal happens. Thus, there must be some diffusion of electrons from bulk Gold to Silver nanoparticle, and it will renormalize the number of surface electrons on Ag nanoparticle. The factor α has to be multiplied with another factor $f_{\text{Diffusion}}$ to take into account the diffusion of electrons. There is another complicating factor. Quantum confinement is more severe in the interior of the nanoparticle (for linear dimension $2R$) than on the surface (linear dimension $2\pi R$). Thus a slight fraction of electrons would like to move to the surface, renormalizing α to αf_{conf} where f_{conf} is a factor that takes into account this quantum confinement effects. There is another factor which is the Coulomb factor. Diffusion to the surface can lead to slight charge imbalance, and there will be electron-electron interactions. This will further renormalize α to αf_{Coul} . Collecting all this α will be normalized to $\alpha f_{\text{Diffusion}} f_{\text{conf}} f_{\text{Coul}}$ (A detailed investigation is needed for the computation of these factors. Here we will not go into that). This will change the ratio of susceptibilities to

leading to some further enhancement of the effect. Thus, in conclusion, there is a possibility of giant diamagnetism without invoking superconductivity!

REFERENCES

- [1] A. Hernando, A. Ayuela, P. Crespo, and P. M. Echenique, *New J. Phys.* **16**, 073043 (2014).
- [2] Pankaj Bhalla and Navinder Singh, *Eur. Phys. J. B* **89**, 40 (2016).
- [3] Navinder Singh, *Electronic Transport Theories: From Weakly to Strongly Correlated Materials*, CRC Press (2016).

$$\frac{\chi_L^{\text{nano}}}{\chi_L^{\text{atomic}}} \sim 3 f_{\text{Diffusion}} f_{\text{conf}} f_{\text{Coul}} \left(\frac{R}{a} \right), \quad (12)$$