

Indications for Topological Physics in High- T_c Materials

Vincent E. Sacksteder IV¹

*W155 Wilson Building, Royal Holloway University of London,
Egham Hill, Egham, TW20 0EX, United Kingdom and*

*Department of Physics and Astronomy, Rutgers University, New Jersey 08854, USA**

(Dated: March 17, 2024)

Research on high- T_c superconductors has generally not focused on analysis of the topological structure of electronic bands in these materials. In this article we collate and discuss several well-known experimental observables that signal that certain signatures of topology may be present. The topological signatures suggested by experiment include dimensional reduction, electronic transport determined by loop statistics, a winding number, Weyl fermions, and others. We suggest that topology, in a wider sense than band topology, may be key to the mechanism of high- T_c superconductivity.

Topology is the study of those properties of geometrical objects which do not change when an object is deformed, but do change when it is torn or glued together. For 1-D curves topology studies their knots but not their length or shape. For a 2-D surface topology may study the edges and corners and punctures through the surface, while for 3-D volumes the volume's surface, edges, corners and again punctures may be of interest.

Topology has been used in modern condensed matter physics to understand topological insulators, Weyl fermions, and Dirac cones. Here topology is often meant and used in a way that is much more restricted than its general mathematical meaning. We will call this restricted version band topology. Band topology is rooted in a perspective that starts from momentum space, and is used to analyze the band structure that results when a material obeys lattice translational symmetry. Depending on the symmetries obeyed by a material, its band structure may be characterized by a topological invariant, an integer which is protected by a gap between the bands in the bulk of the material. The topological invariant cannot change unless the bulk band gap closes and the neighboring bands meet each other. As long the gap remains open and the topological invariant retains a non-zero value, it is guaranteed that conducting states will remain on the surface [in real space] of the material and that the surface will remain conducting. This style of topological analysis based on band structure, i.e. band topology, often assumes that scattering, disorder, electronic correlations, and electronic interactions are in some sense weak.¹⁻⁵

Topology has also been used to give an account of electronic conduction in specifically 2-D geometries, where the integer Quantum Hall effect (IQHE) and fractional Quantum Hall effect (FQHE) are found. The same combination of topology and momentum space, i.e. band topology, that we mentioned above can be applied to the IQHE.⁶ However in these systems a different style of topological analysis, based in real space, has also been successful. Success has been obtained both when interactions are weak and when they are strong. The Laughlin wave-function pioneered this success when interactions are strong. Vortex features of the wave-function in real space, combined with the specifically two dimensional

geometry, have been key to this real-space topological analysis.⁷⁻⁹

The physics community has in general shown little temptation to look for connections between band topology and the world of high T_c superconductivity and bad metals. In these materials any connection to Fermi liquids and band structure is suspect, and therefore looking at topological properties of the band structure does not seem promising. Instead the focus of research has been on the nature of the pairs which mediate high T_c superconductivity, the pairing mechanism which binds those pairs, various orderings such as charge density waves, and the nature of the strange metal state and pseudogap seen at temperatures above T_c . Neither the topological features of the quantum wave-function, nor the machinery of band gaps, topological invariants, and Dirac dispersions, seem likely to cast much light on these questions.¹⁰⁻¹²

In the particular case of the iron pnictide superconductors, there has been some interest in the presence of Dirac cones and topological phases, but the emphasis has been on exploiting the combination of topology and superconductivity for new technologies.¹³⁻²⁶

Nonetheless there are several signs that topology, in a broader sense than the band topology frequently used in condensed matter physics, may be key to understanding high- T_c superconductivity and bad metals. The goal of this article is to collect those signs known to the author into one place, with some brief but not terribly technical discussion. The hope is not to prove beyond every doubt the relevance of topology to high T_c , but instead to gather the evidence and provoke new thinking and inquiry.

Section I of this article discusses experimental reports of Fermi arcs in the cuprates, which if taken very naively indicate the presence of Weyl fermions. Next section II describes a pattern in the doping vs. temperature phase diagram of two cuprates, LSCO and YBCO. In both materials several characteristic temperatures, including the pseudogap temperature, decrease linearly with doping and converge at a common meeting point. In LSCO there are four such temperatures, while in YBCO there are at least three such temperatures. This pattern suggests that a topological winding number is at work. Section III presents two signs in the cuprates of dimensionality being reduced below the nominal 3-D character of the

cuprate materials; reduced dimensionality is a hallmark of topological states. Section IV discusses three qualitative similarities in electronic transport between topological insulators and high- T_c materials. Sections III, IV, and V analyze the linear resistance (linear in temperature and in magnetic field) seen in high T_c materials, and the connection to loops, which are topological objects. Section VI widens this analysis to several other linear relations seen in high- T_c materials, including temperature vs. the 2-D sheet density of holes, and temperature vs. superfluid phase stiffness. Section VII discusses experimental results on numerical values of the slopes of these linear relations, and also the ratio of a material's T_c to its 2-D density of holes at optimal doping. In atomic units these experimental values are all dimensionless and of order $O(1)$, suggesting that atomic units are somehow preferred by the physical mechanism of high- T_c . We discuss the possibility that this preference may reflect topological physics connected with electron-hole loops. Section VIII gives a brief comment on the Meissner effect. Lastly Section IX is a postscript listing several strategies one might use to do topology in strongly correlated materials.

I. FERMION ARCS

Many experiments on cuprates have reported that the Fermi surface is in fact four Fermi arcs: four curves which each terminate at two end points, with the end point location changing with temperature and doping.²⁷⁻³⁰ Within a weakly interacting approach it is impossible to account for Fermi arcs that are truly incomplete, at least in the bulk in the material. The difficulty is that the Fermi surface defines a boundary between the part of the Brillouin zone where all states are occupied and the part of the Brillouin zone where all states are unoccupied. If the Fermi surface is incomplete then it cannot be interpreted as the boundary between occupied and unoccupied sectors. Therefore it is widely understood that Fermi arcs, if they do exist in the cuprates, are a manifestation of strongly correlated physics. The details of how such physics would result in Fermi arcs are not well understood or agreed on.

There is, however, a well-understood way to explain Fermi arcs within the theory of weakly interacting materials and band structure. This explanation is a topological explanation, and it puts the Fermi arcs on the material's surface rather than in its bulk. The theory of how such Fermi arcs arise has a solid foundation, and has been verified by experimental observation of Fermi arcs in several topological materials.⁵ Since there is a clear theory and experimental realization of Fermi arcs in topological materials, and the theories of strongly interacting Fermi arcs are on a weaker footing, some attention should be given to the possibility that the Fermi arcs seen in the cuprates are caused by topology. This possibility apparently has not been discussed, so here we breach the question, putting it baldly.¹¹⁷ A hypothesis can not be

proven wrong until it has been considered.

The cuprates' Fermi arcs are seen at a range of temperatures above the superconducting temperature T_c and below another temperature T^* which decreases with doping. At temperatures above $T = T^*$ there is a single Fermi surface, a circle around the $[\pi, \pi]$ point in the Brillouin zone. This point is equivalent also to three other points $[\pm\pi, \pm\pi]$. At $T = T^*$ the circle separates into four arcs, with pieces missing near the boundaries of the Brillouin zone. The arc length decreases with temperature until at $T = T_c$ there remain only four Fermi points. The arc length also depends on doping.

There are several difficulties with analysis of the Fermi arcs: (1) They are observed using surface not bulk spectroscopy: ARPES or STM. These experimental tools do not see into the bulk. (2) It is very hard to get clean stable surfaces in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO) or $\text{YBa}_2\text{Cu}_3\text{O}_{6+\delta}$ (YBCO), so almost all experimental observations of Fermi arcs have been in $\text{Bi}_2\text{Sr}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+4+x}$ (BSCCO). (3) ARPES and STM report results that do not entirely agree with each other. (4) Doping is hard to control so it is hard to measure the doping dependence of the Fermi arcs. (5) Most of the spectral weight seen in ARPES is spread smoothly in energy, as is typical in strongly correlated materials. The Fermi surface signal strength, i.e. the height in the small peak interpreted as a Fermi surface, is a small fraction of the smooth background. Therefore a lot depends on how one fits the signal. (6) Some claim that the disappearance of portions of the Fermi surface is not real - it is caused by broadening [associated with temperature and interactions] which washes out the peak in the spectral density; if the broadening did not occur then the Fermi surface would remain intact. Others claim that between the two endpoints of the Fermi arc there is a second connecting arc which for various reasons is less visible to ARPES and STM, so that there are four complete Fermi surfaces, and no real Fermi arcs.²⁸⁻³⁰

We leave aside these concerns and take a naive approach to the overall story of Fermi arcs, taking at face value the claim that the Fermi surface in BSCCO really is incomplete.

The only way to explain Fermi arcs, within a weakly interacting approach, is if they reside not in the material's bulk but instead on its surface. Certain topological materials host in their bulk Weyl fermions, i.e. fermions with a well-defined chirality [either right-handed or left-handed] and obeying a Dirac cone linear energy dispersion. Weyl fermions always come in pairs, with the pair separation [within momentum space] determined by the strength of time-reversal symmetry breaking via a magnetization or magnetic field.³¹ [Inversion symmetry breaking is also an alternative to time reversal symmetry breaking.] Any number of Weyl fermion pairs can be realized in a material. On the surface of a Weyl material Fermi arcs connect each pair of Weyl fermions.⁵

In BSCCO there are four Fermi arcs, each with two end points. If the Fermi arcs seen in BSCCO are the surface

manifestation of bulk Weyl physics, then BSCCO must host eight Weyl cones in its bulk.

There is no conceptual difficulty with producing a Hamiltonian which has the same four Fermi arcs and eight Weyl cones seen in BSCCO. A simple model with the copper oxide layer's C_4 symmetry and four Fermi arcs arranged around $[\pm\pi, \pm\pi]$ has already been reported - see Fig. 3-d1 in Ref. 32. Exact reproduction of the experimental data on cuprate Fermi arcs and their dependence on doping and temperature is simply a matter of choosing a convenient Hamiltonian. The Hamiltonian's parameters must be tuned to depend on temperature and doping, in order to reproduce the fragmentation of the Fermi surface into Fermi arcs at the pseudogap temperature, and also to reproduce the reduction of the arcs to nodes at T_c .

In summary, if the experimental evidence for Fermi arcs is taken naively, then it implies that BSCCO at least, and possibly all the cuprates, are Weyl materials in the bulk, as long as the temperature lies above T_c and below the pseudogap temperature T^* . In this naive interpretation, ARPES and STM measurements on BSCCO are reporting surface not bulk Fermi arcs.

Section IX has some brief comments about how Weyl fermions might arise at long distance scales as the result of renormalization group flow from a non-Weyl Hamiltonian.

II. THE HIERARCHY OF PSEUDOGAP LINES

This author recently performed a comprehensive survey of all experimental reports of characteristic temperatures well above the superconducting transition T_c in strontium doped lanthanum cuprate (LSCO) and oxygen doped YBCO.³³ We report only characteristic temperatures at which clearly identifiable signals occur, for example opening of a pseudogap, peaks or kinks in the temperature dependence of various observables, or extinction of a diffraction peak at a particular temperature. These characteristic temperatures have been found using a wide variety of measurement techniques over a period of about three decades. The reported temperatures have been realized experimentally, rather than being derived by extrapolation from lower temperatures. We used only characteristic temperatures that were reported numerically in the original reports, rather than extracting temperatures from data ourselves. [There was one exception to this rule.] We omitted the experimental literature that focuses on ionic behavior, but were very thorough about including all other experimental data sets. The experimental corpus on characteristic temperatures from 1990 until 2018 contains twenty separate data sets from thirteen experimental groups on LSCO, and twenty-six distinct data sets on YBCO.

When the experimental corpus for LSCO is plotted all on one graph, with temperature as the y axis and hole doping as the x axis, a remarkable pattern emerges. The

reported characteristic temperatures lie on a sequence of distinct well-separated straight lines which radiate from a common intersection near the high-doping end of the superconducting dome. The highest line is associated with a peak in the magnetic susceptibility and transport signatures, the second line has symmetry breaking from tetragonal to orthorhombic crystal structure, the third line is the pseudogap transition seen in ARPES, and the fourth line is seen in transport signatures and NMR. There is some evidence suggesting lower lines as well. We call this family of lines the pseudogap family.

This family of pseudogap lines in LSCO obeys a quantization rule: starting from the highest characteristic temperature, the second temperature's slope and value are one half those of the highest temperature, the third line's slope and value are one third, and the fourth line's slope and value are one fourth.

A similar pattern is visible in YBCO. Here three well-separated lines are visible, again with a common intersection at high doping. The highest line is the pseudogap transition accompanied by symmetry breaking, the next shows nematicity in transport and also time reversal symmetry breaking, and the next is seen in transport signals. The slopes of the three YBCO lines have the same fractional relation to each other as is seen in the second, third, and fourth lines in LSCO. This suggests the existence of another higher line at twice the temperature of the highest observed line. There is some data suggestive of the higher line, but it is sparse. Possibly this is because YBCO is rarely measured above 300 K, unlike LSCO which has been measured at temperatures as high as $T = 700$ K. In any case the family of pseudogap lines observed in YBCO show the same common intersection and quantized slopes that are seen in LSCO's pseudogap family.

A pattern of lines with quantized $1/n$ slope and common intersection is known in another context: the energies of Landau levels of a fermion moving in a plane, with a Berry phase like that caused by a Dirac point.^{34,35} The analogy between the pseudogap lines and the Landau levels would require that hole doping map to the Dirac fermion's Fermi energy, and that temperature map to the Dirac fermion's magnetic field B . While this mapping is unmotivated and obscure, the observed pattern of quantized lines suggests a $U(1)$ phase and a winding number associated with that phase, i.e. the winding number is the number of times that the phase goes through 2π . For Landau levels the $U(1)$ phase is of course tied to magnetic flux. Winding numbers are one of the most elementary realizations of topology seen in physics. If the hierarchy of pseudogap lines seen in LSCO and YBCO really is caused by winding number physics, this would explain why the observed family of pseudogap temperatures is so robust against interactions.

In addition to the possible winding number discussed above, it is worth dwelling a little more on the fact that the slopes of the pseudogap lines seen in LSCO and YBCO follow a $1/n$ pattern of

$1/1, 1/2, 1/3, 1/4$. 2-D Landau levels reproduce this pattern only if the electronic motion is affected by either a Zeeman term or a Berry phase like that seen when there is a topologically protected Dirac point.³⁴ Otherwise 2-D Landau levels follow a $1/(n + 1/2)$ pattern: $(1/2)^{-1}, (3/2)^{-1}, (5/2)^{-1}, (7/2)^{-1}$. The experimental data do not support this pattern and support the $1/n$ pattern instead. The existence of a $1/n$ not $1/(n + 1/2)$ pattern in the pseudogap lines may be a hint of topological physics in the cuprates.

III. DIMENSIONAL REDUCTION

One hallmark of topology is reduced dimensionality. In a 2-D material topological states appear at the edges and corners, while in a 3-D material topological states appear at the surface, edges, and corners. When the key physics happens at a dimensionality that is smaller than the apparent dimensionality of a system, this can indicate that topology is at work.

The Copper Oxide Plane. In this respect it is interesting that the essential physics of the cuprates lies in the copper oxide CuO_2 plane, even though the actual material is 3-D. Some variation in T_c occurs as the number of CuO_2 planes is varied, but the variation in T_c is relatively weak, suggesting that it is a second order effect. In LSCO all the physics required for its high- T_c superconductivity lies in the plane, since monolayer LSCO reaches the same T_c as bulk LSCO.³⁶ The focus on 2-D physics is also reminiscent of the IQHE and FQHE systems, which also work on topological grounds.

Linear Resistance in Bad Metals May be a Sign of Quasi-1-D Conducting Channels. At temperatures above T_c the cuprate and pnictide superconductors have a resistance that increases linearly with temperature, and this linear growth continues to large temperatures without saturating. Linear-in-temperature resistance has become known as a hallmark of strong correlations, including in materials that do not superconduct. Materials with this signature are called bad metals.³⁷

In recent years experiments have found that several materials with linear-in-temperature resistance also exhibit linear-in-magnetic field resistance. This was verified in the high- T_c cuprate superconductor $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO), the high- T_c pnictide superconductor $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$, and also the heavy fermion material $\text{Yb}_{1-x}\text{La}_x\text{Rh}_2\text{Si}_2$.³⁸⁻⁴⁰ The resistance is linear in both temperature and field. It is possible that generally linear-in-field and linear-in-temperature resistance go together in strongly correlated materials. Studies of magnetoresistance in bad metals have not been common, and the data is not yet available to decide whether linear-in-field resistance is the norm in these materials.

In any case the discovery of linear-in-field resistance in the cuprates and pnictides unites the mystery of their linear resistance with the ongoing mystery of linear-in-field resistance in a wide variety of experimental realizations,

many of which have Dirac cones.^{15,16,20,41-48} Several explanations of linear-in-field resistance have been given which focused on specific mechanisms which could be responsible for linear magnetoresistance in specific materials. These include the cases of ballistic conduction when the Fermi surface has a cusp, of a 3-D Dirac cone in the presence of a strong magnetic field, of a density gradient across the sample, and of classical transport with strong sample inhomogeneities.⁴⁹⁻⁵³

In a recent work we gave a more generic explanation of linear resistance [linear both in field and in temperature].⁵⁴ Our explanation is in terms of quantum interference; it is not specific to a particular microscopic mechanism such as details of the Fermi surface. It does, however, hint that the charge carriers responsible for linear resistance may be confined to move along locally one dimensional pathways.

We argued that linear resistance is caused by the same combination of scattering and quantum interference which produces weak (anti)localization in ordinary materials. Weak (anti)localization expresses the quantum interference which occurs when an electron after several scatterings returns to its starting position, forming a loop. In this circumstance where an electron's sequence of scatterings forms a loop, a special quantum interference will occur if a hole follows the same sequence of scatterings but in the opposite order. The net effect is that disorder causes electrons and holes to form pairs called Cooperons. It is Cooperon loops [electrons following loops in one direction and holes following in the opposite direction] that mediate weak (anti)localization and alter electronic conduction.

In ordinary 2-D and 3-D materials scattering causes quantum decoherence, so that when a Cooperon completes a loop, it is unable to repeat the same loop again. This limit on Cooperon loops controls the resistance signature of weak localization - for instance in two dimensions the resistance varies logarithmically. We argued that when linear resistance is measured, one can deduce from the linear resistance that Cooperons are repeating their loops, and are not experiencing the quantum decoherence that prohibits loop repetitions in ordinary 2-D and 3-D materials.

The arguments of the above article were based entirely on analysis of the linear profile of the resistance, which does not in itself provide material for discerning which mechanism allows linear resistance materials to maintain quantum coherence even in the presence of scattering. However one way of realizing robust quantum coherence, i.e. of allowing Cooperons to repeat their loops, is if conduction is confined to move along tracks that are locally one-dimensional. There are several known ways to confine electrons to quasi-1-D channels. One such way is thin nanowires: if they are made long enough quantum interference takes over resulting in either Anderson localization or a perfectly conducting channel.⁵⁵⁻⁵⁹ Two other ways of confining electrons to quasi-1-D channels are the edges of topological insulators, and the snake states that

are generated when graphene or TIs are subjected to various control mechanisms.^{60–62} In each of these 1-D realizations quantum interference is very robust, no matter how strong the scattering may be.

In this respect we are reminded of very striking STM images of electron density on the surfaces of $\text{Ca}_{1.88}\text{Na}_{0.12}\text{CuO}_2\text{Cl}_2$, $\text{Bi}_2\text{Sr}_2\text{Dy}_{0.2}\text{Ca}_{0.8}\text{Cu}_2\text{O}_{8+\delta}$,⁶³ and $\text{Bi}_2\text{Sr}_2(\text{Ca},\text{Dy})\text{Cu}_2\text{O}_{8+x}$.⁶⁴ These experiments show electron density focused on line segments oriented along the bonds in the CuO_2 plane, which have two directions that are perpendicular to each other. The line segments can be quite long, 15 bonds or more. The STM image reveals that the plane is covered with these line segments, with apparently random length, angular orientation, and placement. Perhaps charge conduction is guided along these quasi-1-D segments, producing the quantum coherence necessary for linear resistance.

If the linear resistance seen in strongly correlated materials, including high T_c materials above T_c , is caused by quasi 1-D conduction, then this is evidence that topology may be at work in these materials. Topology is a very robust way of reducing dimensionality.

IV. QUALITATIVE SIMILARITIES TO TOPOLOGICAL INSULATORS

There are several qualitative similarities between high- T_c superconductors and topological insulators.

Resilience Against Strong Scattering. The first qualitative similarity is that in both classes of materials electronic conduction is resilient against very strong scattering. Even very strong disorder is unable to stop topologically protected conduction on the surface/edge of a TI, as long as the bulk of the TI does not conduct.^{65–67} Unlike some TIs, high T_c materials may not have strong static disorder. However high T_c materials, and strongly correlated materials, do have very strong scattering. This is seen very clearly in ARPES studies of strongly correlated materials, which show that most of the spectral weight is not at the Fermi energy, but instead washed out into a smooth background. The smooth background is evidence of very strong scattering. It is remarkable, then, that the cuprates are very good superconductors even though they also show such very strong scattering. The combination of very strong scattering with good conduction suggests that high- T_c superconductors may have something in common with TIs.

Linear Resistance. A second qualitative similarity between high- T_c materials and topological insulators is that both classes of materials are able to manifest linear resistance. In fact, of the materials where linear magnetoresistance has been reported, most either host Dirac fermions, or it has been suggested that they host Dirac fermions. Some theoretical explanation for this comes from Abrikosov's quantum theory of linear magnetoresistance, which builds on the foundational assumption that the linear resistance material hosts 3-D Dirac electrons

in its bulk. Therefore when linear magnetoresistance is reported in strongly correlated materials, it is natural to look for links between those materials and topological physics.

This sort of reasoning, from linear resistance to topology, has had some success in the case of certain pnictide superconductors where linear magnetoresistance is seen, and where both experimental evidence and theoretical work indicate the presence of Dirac cones and topological phases.^{13–26} Much of this work belongs in the category of work that we here call band topology, since the theoretical work is largely based in band theory, and many of the experiments use techniques such as quantum oscillations and ARPES which are essentially probes of band structure.^{14,21,22,24,25} We are suggesting here that the link from linear magnetoresistance to topology may have a broader relevance going beyond band-oriented analysis. The pnictides are encouraging in this respect because they are strongly correlated, and their physics goes well beyond standard band structure, as witnessed by the ongoing discrepancies between *ab initio* predictions and experimental measurements of the bands.^{68–70}

Weak Antilocalization and Fast Spin Relaxation. The third and last qualitative similarity between high- T_c materials and topological insulators is that the linear resistance always goes up, not down, with magnetic field and with temperature. This shared behavior supplies information about spin physics in both materials. As outlined above, in Ref. 54 we have argued that the linear resistance is a manifestation of cooperon physics, the same physics which produces weak localization in ordinary materials. Since the cooperon is a pairing of an electron with a hole, and since both the electron and the hole are spin 1/2 particles with two states, the cooperon is a 2×2 matrix. The four numbers in the Cooperon matrix encode both electronic charge [a singlet] and spin polarization [a triplet].

When both the charge singlet and spin triplet components of the Cooperon have similar decay times, then the Cooperon causes the resistance to decrease with magnetic field - this is called weak localization.^{71,72} In contrast, when the relaxation time of the Cooperon's spin triplet is short compared to the singlet's decay time, then the Cooperon causes the resistance to increase with magnetic field - this is called weak antilocalization. When weak antilocalization is observed instead of weak localization, i.e. when the resistance increases not decreases with field, this is an unambiguous signal that the relaxation time of the Cooperon's spin triplet is quite short. It must be so short that the Cooperon's spin polarization relaxes to zero before a Cooperon is able to return to its starting point and form a loop.

The reason why in TIs the Cooperon's spin triplet has a very short relaxation time is that TIs have very strong spin-orbit couplings.⁷³ In other words, the spin state of an electron has a very strong impact on the direction of movement that is energetically preferred by the electron. Whenever an electron scatters and therefore

changes direction, it also changes its spin state. In TIs the Cooperon's spin relaxation time is very close to the scattering time, i.e. much smaller than the time required for a Cooperon to return to its origin. We turn briefly to the diffuson, the classical partner to the cooperon. Both the diffuson and the cooperon have the same spin triplet relaxation time, so if the cooperon's spin relaxation time is short then so is the spin relaxation time of the diffuson. In summary, when weak antilocalization is observed, the role of spin polarization in long distance conduction [either via the cooperon or via the diffuson] is negligible.⁷⁴

If the linear resistance seen in high- T_c materials is really caused by the Cooperon, then it is a kind of weak antilocalization, not weak localization. This in turn implies that the relaxation time of the Cooperon's spin triplet is quite short - so short that spin polarization plays no part in long distance conduction. Moreover some very fast-acting physics must be responsible for Cooperon spin triplet relaxation in the high- T_c materials. These are very interesting qualitative similarities between the high- T_c materials and TIs, concerning both spin physics and conduction.

V. THE KEY ROLE IN LINEAR RESISTANCE OF LOOPS AND THEIR AREAS

We continue our discussion of Cooperons, which we claim are responsible for the linear resistance [linear both in field and in temperature] seen in high T_c materials above the superconducting transition. Cooperons are electron-hole pairs whose pairing is induced by scattering centers. Because of this pairing, they are able to conduct charge over distances and times that are much longer than the scattering length and time. This is in contrast to single electrons or holes, whose phase is disrupted at each scattering event and therefore are unable to conduct at scales significantly exceeding the scattering scale. The characteristic scales [both distance and time] of Cooperons are far longer than the scattering scale or the crystalline unit cell.

Because of this difference in scales, the details of the individual scattering events suffered by a Cooperon, and the kinetics of a Cooperon's movement between scattering centers, do not determine its contribution to weak (anti)localization. These details belong to length and time scales that are much shorter than the Cooperon's scale, and therefore their only influence on the Cooperon are to determine the diffusion constant, relaxation times, and similar constants describing mixing of charge and spin. Even the shape traced in real space by a Cooperon loop does not matter, because a description of this shape would necessarily refer to individual scattering events. These facts can be verified by computing the perturbative bubble diagram that describes the Cooperon.

There are only three quantities that affect the Cooperon's contribution to weak (anti)localization: the area of the loop which it traces, the statistics of which

loop areas are more probable, and the relaxation times of its charge singlet and the spin triplet components. In materials showing weak antilocalization, such as linear resistance materials including high T_c superconductors, the spin triplet relaxes very quickly leaving only the charge singlet, so there remain only two quantities which determine weak antilocalization: the loop area and the statistics of which loop areas are more probable. This information can be encoded in a probability density $P(A)$ giving the probability that a Cooperon loop has area A .⁵⁴

In materials displaying weak antilocalization the area distribution $P(A)$ contains a complete description of the WAL signature seen in electrical conduction. Magnetic field B couples to a Cooperon loop via a phase factor $\exp(i2\pi AB/\Phi_0)$, where $\Phi_0 = h/e$ is the magnetic flux quantum. Therefore, up to a multiplicative constant, the magnetoconductance signal $G(B)$ caused by WAL is equal to the sum of the phase factors of each Cooperon loop, i.e. $G(B) \propto \sum_{\text{loops}} \exp(i2\pi A_{\text{loop}} B/\Phi_0)$. This can be rewritten in terms of the area distribution:

$$G(B) \propto \int dA \exp(i2\pi AB/\Phi_0) P(A) \quad (1)$$

This focus on counting loops and their areas is a very peculiar aspect of weak antilocalization, and is very far from the feeling of most other condensed matter physics. Loops are geometrical and topological objects, and the area of a loop is also a geometrical quantity. The shape of the loops is not important, and neither are the details of the Hamiltonian that determines electronic motion. This focus on geometry rather than ordinary physics is suggestive of topology, and in fact topological insulators are one of the most significant realizations of weak antilocalization.

VI. LINEAR RELATIONS TO TWO DIMENSIONAL SHEET DENSITY

Of the two quantities determining weak antilocalization, i.e. Cooperon loop area and the number of Cooperon loops with a particular area, only the former quantity area is dimensionful. The inverse or conjugate of area is two dimensional sheet density. Because of sheet density's status as the conjugate of area, the special emphasis that weak antilocalization gives to area also applies to sheet density.

One example of the focus on sheet density is equation 1, which is a Fourier transform that starts with a probability distribution $P(A)$ that is a function of area, and ends with magnetoconductance $G(B)$ which is a function of magnetic field. The reason why this equation is mathematically correct is that B/Φ_0 has units of sheet density. When loops are the focus of attention, it is natural to expect not only their area but also sheet density to have a key role in determining experimental phenomena.

In this connection it is striking that the cuprates display several linear relations that connect sheet density to other quantities.

1. Resistance's Dependence on Temperature, Magnetic Field, and Hole Sheet Density.

- Resistance is linearly related to magnetic field in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO), $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$, and $\text{Yb}_{1-x}\text{La}_x\text{Rh}_2\text{Si}_2$ at temperatures above T_c .³⁸⁻⁴⁰ Equation 1 shows that, in the context of weak antilocalization, magnetic field is equivalent to sheet density, so the linear relation between resistance and field can be understood as a linear relation between resistance and sheet density.
- Resistance is linearly related to temperature in many bad metals, including the ones mentioned above where linearity in field has been reported.
- Ref. 75 found that the coefficient of linear-in-temperature resistance is inversely related to hole doping in four cuprates: $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO), $\text{YBa}_2\text{Cu}_3\text{O}_{6+\delta}$ (YBCO), $\text{Tl}_2\text{Ba}_2\text{CuO}_{6+\delta}$ (Tl2201), and $\text{HgBa}_2\text{CuO}_{4+\delta}$ (Hg1201). Since all four cuprates have the same copper oxide plane with the same cross-sectional area, the linear relation to hole doping is also a linear relation to the sheet density of holes. Performing this conversion from hole doping p to hole sheet density ρ_{2D} , Ref. 75's result is $R_{xx}(T) \propto T/\rho_{2D}$.
- The coefficient of the resistance's dependence on temperature has been found to be proportional to the coefficient of the resistance's dependence on magnetic field. Therefore Ref. 75's result implies that $R_{xx}(B) \propto B/\rho_{2D}$, where ρ_{2D} is hole sheet density.

2. The Pseudogap Family of Temperatures that Decrease with Hole Sheet Density.

The characteristic temperatures found well above T_c in the cuprates, including the pseudogap temperature, are linearly related to the sheet density of holes. As discussed earlier, the experimental data sets organize in four straight lines [four lines for LSCO, three or four for YBCO] that are highest at small doping and decrease with doping towards a meeting point near the the high-doping edge of the superconducting dome. This suggests the presence of a sheet density that is high at low hole sheet density and decreases as hole sheet density increases.

3. Temperatures that Increase with Hole Sheet Density.

Ref. 33's appendix A reports six data sets with characteristic temperatures that increase as the hole sheet density increases. Five of these, measured with ARPES, the thermoelectric power, and the magnetic susceptibility, seem to be direct manifestations of the density of mobile holes because they intercept $T = 0$ near the low doping edge

of the superconducting dome.⁷⁶⁻⁷⁹ The sixth data set, a pairing temperature measured using magnetic hysteresis, extrapolates to $T = 0$ at a lower doping $p = 0.023$, presumably because of a sensitivity to pinned holes.^{80,81}

4. T_c 's Dependence on Superfluid Phase Stiffness.

In Ref.⁸², Bozovic et al measured the 2-D superfluid phase stiffness ρ_s in LSCO thin films at many different dopings on the overdoped side of the phase diagram. Phase stiffness is given in units of temperature, but this is artificial - the definition of phase stiffness contains a factor of k_B . Bozovic et al's phase stiffness experiments were probes not of temperature but instead of a 2-D [sheet] density, which was obtained by measuring the magnetic inductance between two coils. The inductance is sensitive to the length scales of the coils themselves and of the superconducting order parameter in the superconducting film interposed between the coils. Bozovic et al reported that T_c is linearly related to the $T = 0$ value of ρ_s . Bozovic et al's data also shows that in most of the superconducting sector of the phase diagram ρ_s is linearly related to temperature T .

In summary, in the bad metal regime above T_c there are linear relations between hole sheet density, magnetic field, temperature as a thermodynamic quantity, and the several characteristic temperatures found above T_c including the pseudogap temperature. The linear resistance is controlled by ratios of these quantities. Below T_c there is a linear relation between superfluid phase stiffness ρ_s and temperature, and ρ_s 's value at $T = 0$ is linearly related to T_c .

These experimental results show some kind of equivalence between hole sheet density, superfluid phase stiffness which is a sheet density, magnetic field which is a sheet density after division by Φ_0 , temperature as a thermodynamic quantity, and several characteristic temperatures including both the pseudogap temperature and also T_c . The linearity of these relations suggests that the equivalence between these quantities may be true in a sense that is mathematically and physically precise.

These results can also be read as saying that hole sheet density controls the phase diagram of the cuprates. As we discussed earlier, sheet density is conjugate to area, and both are geometric quantities. It is very striking to see a geometric quantity such as sheet density or area control the phase diagram. This complete ascendancy of geometry over all other kinds of physics, especially at temperatures above T_c , strongly suggests that topology is a key determinant of the cuprate phase diagram.

VII. ATOMIC UNITS AND NUMEROLOGY

The linear relations between sheet density and other quantities bear closer examination, because their units

and the numerical values of their slopes indicate that in the cuprates the system of atomic units $m_e = e = \hbar = 1$, supplemented with $k_B = 1$, is somehow preferred over other systems of units.

A. Atomic Units are Preferred in the Cuprates

There are two senses in which atomic units seem to be preferred by the cuprates. Firstly, in atomic units energy, magnetic field, and temperature all have the same units as sheet density, so that linear relations between these quantities are natural in the sense of having slopes that are unitless.

- The magnetic flux quantum $\Phi_0 = 2\pi\hbar/e$ is unitless with numerical value of 2π , giving magnetic field units of sheet density.
- In atomic units momentum \vec{p} has units of inverse length, so energy $E \propto |\vec{p}|^2/2m_e$ has units of sheet density.
- When $k_B = 1$ temperature is equivalent to energy, and has units of sheet density.

Linear relations between these quantities, such as the linear experimental relations which we have discussed above, are more natural when they all have the same units.

The second sense in which atomic units seem to be preferred by the cuprates is that in atomic units the linear relations have slopes that are of order $O(1)$. This contrasts with other systems of units where the slopes have numerical values that are different from 1 by orders of magnitude. In subsection VII C we will list the numerical values of these slopes. In some cases the slopes seem to have integer values, in atomic units.

Moreover, in several cuprates and pnictides the value of T_c at optimal doping is comparable to the sheet density of hole pairs, within a factor of ten - we give examples in subsection VII D.

These numerical happenstances are especially remarkable because the definition of the system of atomic units [as opposed to other units] was motivated by considerations that do not concern cuprate superconductivity. Although excessive attention to numerical values can be simply numerology, the discovery that so many slopes are of order one should stimulate thought about whether there may be some physical reason why atomic units might be preferred.

B. Significance of Atomic Units

Atomic units do have a physical significance which distinguishes them from other systems of units. Specifically, when the electron mass m_e and the elementary charge e are set to one, the only properties that electrons retain are their paths in space-time, and their spin. (The

charge operator simply counts electron paths, and has a subsidiary role.)

The space-time paths which we are discussing are those of Feynman's formulation of quantum mechanics as a sum over paths.⁸³ In this formulation an electron follows not just one path, but instead many paths which fully explore the sample in which the electron is moving. All of these many paths are summed to determine the evolution of $|\psi\rangle$, the electronic state. We are not discussing the semiclassical paths of an electron's average motion. For instance, in a magnetic field an electron's average position executes well-defined circular loops around the axis of the magnetic field, and one can measure this cyclotron motion. This is not the sort of path we are talking about. Instead we are talking about the infinitely many quantum mechanical paths, tracing many complex trajectories and fully exploring the sample, which sum up to produce the average cyclotron motion.

Charge conservation tells us that no electron's space-time path begins or ends in isolation. Instead when an electron is produced, a hole/positron is also produced, and likewise each electron is annihilated only when a hole is annihilated. At each of the two endpoints of an electron's path one always finds endpoints of hole paths, and vice versa. One can follow from an electron path to the path of one of its two adjoining holes, and from that hole's path to another electron path, etc. If one keeps following from electron to hole, to electron, etc., eventually these paths will compose to form a loop in space-time. Loops are the only option because it is impossible for an electron or hole path to end in isolation. In other words, electron paths should always be considered in conjunction with hole paths, taking account that they they always form loops in space-time.

Electrons and holes are geometric objects - they are simply space-time loops that carry spin. They are also topological objects, since loops can be knotted, braided, etc. Atomic units accentuate this geometric and topological meaning.

In a material with fast spin-relaxation, the electron is effectively spinless. In this case space-time loops give a complete description of electrons and holes; they are purely geometric/topological objects, without any additional properties.

Setting $\hbar = 1$ also has a geometric significance - it focuses attention on the noncommutation between position/time on one hand and translations (of position or time) on the other hand.

If in high T_c materials atomic units are in some sense preferred over other systems of units, this is an indication that geometry, and topology, govern these materials.

C. Numerical Values of the Slopes

In this subsection we report the numerical values of the slopes of the linear relations between temperature, magnetic field, hole sheet density, resistance, and superfluid

phase stiffness. The point is that in atomic units these slopes are all of order $O(1)$, and some of the slopes may be integers.

1. Resistance's Dependence on Temperature, Magnetic Field, and Hole Sheet Density.

- Ref. 75 reports the coefficient of linear-in-temperature resistance in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO), $\text{YBa}_2\text{Cu}_3\text{O}_{6+\delta}$ (YBCO), $\text{Tl}_2\text{Ba}_2\text{CuO}_{6+\delta}$ (Tl2201), and $\text{HgBa}_2\text{CuO}_{4+\delta}$ (Hg1201). The authors report that the resistance is $R_{xx}/(k_B T) = \pi \times 64 a_0^2 \times p^{-1}$, where p is the hole doping. [This is after conversion of the data in Figure 5b to atomic units - in the article's units it is $R/(k_B T) = p^{-1} \times 2.6 \Omega / \text{K}$]. Using the dimensions of the CuO_2 plane¹¹⁸ to convert from hole doping to hole sheet density ρ_{2D} obtains $R_{xx} = 3.8 k_B T / \rho_{2D}$. Defining the slope coefficient $\alpha = dR/d(k_B T)$, this is $R_{xx} = \alpha k_B T$ and $\alpha = 3.8 / \rho_{2D}$. The numerical value of 3.8 is remarkable for being of order $O(1)$, and for being the same as the integer 4 within experimental errors.
 - The factor of 3.8 seen in $R_{xx} = 3.8 k_B T / \rho_{2D}$ and $R_{xx} = 3.8 \mu_B B / \rho_{2D}$ is equal to the integer value 4, within experimental errors. Ref. 54 accounts for the 4 with a factor of 2 from the 2 in $k_B T = E = p^2 / 2m_e$. Another factor of 2 comes from the difference between sheet density of carriers and sheet density of Cooper pairs. However Ref. 54 does not provide any argument excluding the possibility of additional multiplicative factors.
- Resistance also depends linearly on magnetic field B , i.e. $R(B) = \beta \mu_B B$. Here μ_B is the Bohr magneton and equals 1/2 in atomic units, and β measures the slope of linear-in-magnetic-field resistance.
 - The slope in temperature can be compared to the slope in magnetic field by calculating the ratio $\gamma = \alpha / \beta = (dR/d(k_B T)) / (dR/d(\mu_B B))$.
 - Recently an experiment on the high- T_c pnictide superconductor $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ measured that this ratio $\gamma = \alpha / \beta = 1$ is identical to one in atomic units, within the experimental error bar of 7%.³⁸ This numerical value of unity is remarkable, and is specific to the choice of atomic units.
 - Further studies of the cuprate $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ and of $\text{Yb}_{1-x}\text{La}_x\text{Rh}_2\text{Si}_2$ near optimal doping have found that γ varied slowly with doping, with values between 0.7 and 2.3.^{38,39} These values

of γ correspond to linear magnetoresistance coefficients between 1.5 and 5.5; $R_{xx} = [1.5, 5.5] \times \mu_B B / \rho_{2D}$.

- If $\gamma = 1$, as found in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$, then the magnetoresistance is $R_{xx} = 3.8 \mu_B B / \rho_{2D}$. This number is remarkable for being of order $O(1)$.

2. The Pseudogap Family of Characteristic Temperatures that Decrease with Hole Sheet Density.

Ref. 33 gathers all experimental reports on characteristic temperatures above T_c in LSCO and YBCO, and finds that they coincide on families of straight lines with quantized slopes. Here we report the slopes of the lines, which are of order $O(1)$. We also report the values of these characteristic temperatures at zero doping. The ratio of the zero doping temperatures to the characteristic temperature $T = 6000 \text{ K}$ associated with the cuprate unit cell is of order $O(1)$.

- The pseudogap family in LSCO has slopes equal to $dT/d\rho_{2D} = -0.64 \times [1, 1/2, 1/3, 1/4]$.
- The pseudogap family in YBCO has slopes equal to $dT/d\rho_{2D} = -0.78 \times [1/2, 1/3, 1/4]$. There may also be a higher pseudogap line with slope -0.78×1 , but insufficient data is available for high temperatures in YBCO.
- The pseudogap lines in both LSCO and YBCO extrapolate to zero hole density at temperature $T(\rho_{2D} = 0) = 1000 \text{ K} \times [1, 1/2, 1/3, 1/4]$. Converting to atomic units, this temperature is $T(\rho_{2D} = 0) = 1000 \text{ K} = \frac{1}{6.0} \times \rho_A$, where $\rho_A = A^{-1} = 6000 \text{ K}$ is the sheet density associated with the unit cell of the cuprate copper oxide plane, which has area $A = 53a_0^2$. In the other words, the ratio of the pseudogap temperature at zero doping $T(\rho_{2D} = 0)$ to the characteristic sheet density ρ_A of the CuO_2 plane is a factor of $\frac{1}{6.0}$.

The numerical values of $-0.64, -0.78, 1/6.0$ are specific to atomic units, and are remarkable for being of order $O(1)$.

3. Temperatures that Increase with Hole Sheet Density.

Ref. 33 Appendix reports six experimental temperature data sets that rise linearly with hole sheet density. Five of these extrapolate to $T = 0$ near the underdoped limit of the superconducting dome, i.e. in the interval $p = [0.049, 0.081]$, which suggests that these temperatures are direct manifestations of the sheet density of mobile holes. A sixth data set extrapolates to $T = 0$ at a lower doping $p = 0.023$, presumably because of a sensitivity to pinned holes.⁸⁰ The slopes $dT/d\rho_{2D}$ of these data sets, in atomic units where they are unitless, are all of order $O(1)$:

- $dT/d\rho_{2D} = 1.02$ for a coherence temperature measured using angularly integrated ARPES.⁷⁶
 - $dT/d\rho_{2D} = 0.27$ for a temperature where a Gaussian peak is extinguished in ARPES.⁷⁷
 - $dT/d\rho_{2D} = 0.35$ and 0.21 for the beginning and end of a linear regime in the thermoelectric power.⁷⁸
 - $dT/d\rho_{2D} = 0.13$ for a Weiss temperature measured using nuclear quadrupole resonance.⁷⁹
 - $dT/d\rho_{2D} = 0.64$ for a pairing temperature detected using hysteresis in the low field magnetization.^{80,81}
4. **T_c 's Dependence on Superfluid Phase Stiffness.** Bozovic et al measured the phase stiffness ρ_s as a function of temperature and doping.³⁶ The phase stiffness is reported in units of Kelvin, but the actual experimental technique is a measurement of geometric quantities not temperature. Therefore finding an equivalence between sheet density and temperature is a highly non-trivial result.
- Figure 1 in Bozovic et al's Ref. 36 demonstrates that ρ_s is linear in T through most of the phase diagram, except at high temperatures close to T_c . Bozovic et al provided the data for Figure 1 as a supplement to the article. Using this data, we calculate the slope $d\rho_s/dT$ by subtracting the value of ρ_s at $T = 10$ K from its value at $T = 20$ K in all the odd-numbered samples [22 samples] with $T_c \geq 20$ K. The maximum value of $\Delta\rho_s$ in this range is 23.53 K and the minimum value is 19.36 K. This gives the slope $d\rho_s/dT \approx -2.15 \pm 0.2$, which is remarkable for being equal within experimental scatter to the integer value $d\rho_s/dT = -2$.
 - $\rho_s(T)$ is linear in T at most temperatures, but steepens near T_c . This results in a linear relation between T_c [at $\rho_s = 0$] and ρ_s 's value at $T = 0$, which Bozovic et al report as $d\rho_{s0}/dT_c = (0.37 \pm 0.02)^{-1} = 2.7 \pm 0.15$.³⁶

D. Superconducting T_c vs. Hole Sheet Density

It is natural in atomic units to compare sheet density to temperature, and holes are key to cuprate superconductivity. Therefore we examine whether the sheet density of hole pairs can be used to estimate T_c at optimal doping. For each of the following compounds we report the ratio of optimal T_c to the sheet density of hole pairs $\rho_{holes}/2$. We also report the same ratio, but with electron pairs rather than hole pairs, for several pnictides. In each case the ratio is of order $O(1)$.

- **YBCO and LSCO:** The optimal doping is about $p = 0.16$ and the in plane lattice spacing is about 3.84 Angstroms; therefore the the sheet density of hole pairs is $\rho_{holes}/2 = 480$ K. In comparison, in YBCO optimal T_c is about 94.3 K⁸⁴, and in LSCO it is 41.6 K.³⁶ Taking the ratio of optimal T_c to $\rho_{holes}/2$, one obtains 0.20 in YBCO and 0.09 in LSCO.
- **BSCCO:** In Bi-2223 the optimal doping is near $p = 0.17$ [the optimal doping for Bi-2212] and the in plane lattice spacing is near 5.41 Angstroms; therefore the the sheet density of hole pairs is $\rho_{holes}/2 = 510$ K.⁸⁵ In comparison, optimal T_c is 108 K at ambient pressure, and $T_c = 136$ K at a pressure of 36 GPa.⁸⁶ Taking the ratio of optimal T_c to $\rho_{holes}/2$, one obtains 0.21 at ambient pressure and 0.27 under pressure.
- **HgBaCaCuO:** In Hg-1223 the optimal doping is near $p = 0.13$ [the optimal doping for Hg-1201] and the in plane lattice spacing is about 3.86 Angstroms; therefore the the sheet density of hole pairs is $\rho_{holes}/2 = 385$ K.^{87,88} In comparison, optimal T_c is 130 K at ambient pressure, and $T_c = 164$ K at a pressure of 45 GPa.^{89,90} Taking the ratio of optimal T_c to $\rho_{holes}/2$, one obtains 0.34 at ambient pressure and 0.43 under pressure.
- **FeSe on SrTiO₃:** We also discuss FeSe, which is a parent compound for the iron pnictide superconductors. Bulk FeSe has $T_c = 9$ K, but when a monolayer of FeSe is supported by a SrTiO₃ substrate T_c rises to 65 K or higher. The optimal doping is $p = 0.12$ electrons per iron atom¹¹⁹ and the in plane lattice spacing is 3.90 Angstroms; therefore the the sheet density of electron pairs is $\rho_{electrons}/2 = 350$ K.⁹¹ In comparison, optimal T_c is 65 K or higher, although $T_c = 109$ K has also been reported. Taking the ratio of optimal T_c to $\rho_{electrons}/2$, one obtains 0.19.
- **ReFeAsO_{1-x}H_x(F_x) (Re=La,Ce,Sm and Gd):** The members of this family of pnictides show similar doping vs. T_c phase diagrams.⁹²⁻⁹⁴ Here we concentrate on LaFeAsO_{1-x}H_x. At a pressure of 6 GPa and an optimal doping of $x = 0.18$ this compound reaches $T_c = 52$ K. T_c is weakly dependent on x between $x = 0.08$ and $x = 0.40$. (In other members of the family very similar temperatures and dopings are found, but at ambient pressure not at 6 GPa.) The in-plane lattice spacing is 4.035 Angstroms; therefore the sheet density of pairs is $\rho/2 = 490$ K. Taking the ratio of optimal T_c to $\rho/2$, one obtains 0.11 at optimal doping, or 0.24 at the lower end of the superconducting dome, or 0.05 at the high doping end of the dome.

In summary, the sheet density of hole pairs overestimates the optimal T_c , but in the cuprates and pnictides

the two numbers are often within an order of magnitude of each other. In other words, $T_c/(\rho_{holes}/2)$ is often between 0.1 and 1. While this level of agreement is not satisfactory as a predictive tool, it is still an indicator that atomic units are preferred by the cuprates.

The same point that optimal T_c is of the same order as sheet density can be made using the Roeser-Huber equation.^{95,96} This equation claims that there exists experimentally a simple relation between optimal T_c and the spacing between charge carriers. In atomic units the Roeser-Huber equation reads as $x^2 \times T_c = 0.785 \times n^{2/3}$, where x is a distance between charge carriers, so $1/x^2 = \rho_x$ is a sheet density. $n = 1, 2, 3$ is the number of CuO_2 planes in the unit cell. Reformulating the Roeser-Huber equation in terms of sheet density ρ_x rather than carrier spacing x , it reads as $T_c = 0.785 \times n^{2/3} \times \rho_x$. In other words, it states that T_c is linearly related to a sheet density ρ_x by a coefficient of order $O(1)$. The authors who advanced the Roeser-Huber equation chose the value of x for each material based on considerations about the crystallography of the material. Agreement of a few percent between the Roeser-Huber equation and experimental T_c 's was claimed for many cuprate and pnictide compounds.

Our point in mentioning the Roeser-Huber equation is: it could not work even within an order of magnitude, much less the claimed few percent, if T_c/ρ_{2D} were not of order $O(1)$ in atomic units. Although the case by case choice of the charge carrier spacing x can be questioned, still the chosen values of x were related to the lattice spacing, and therefore the tuning of x cannot be responsible for the order of magnitude agreement of optimal T_c and ρ_{2D} . The Roeser-Huber equation confirms that T_c/ρ_{2D} really is of order $O(1)$ in atomic units.

E. Significance of Integer Values.

The slopes listed above include three numbers which are very close to integer values:

1. In $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ the slope of the magnetic field dependence is the same as the slope of the temperature dependence; $\gamma = \alpha/\beta$ is identical to one in atomic units, within the experimental error bar of 7%.³⁸
2. Bozovic et al's article showed that the superfluid phase stiffness ρ_s is related to temperature by the integer -2 [within experimental scatter]; $d\rho_s/dT = -2$.³⁶
3. Barisic et al report that $R_{xx} = 3.8k_B T/\rho_{2D}$. 3.8 is very close to the integer 4, so perhaps the correct relation is $R_{xx} = 4k_B T/\rho_{2D}$.⁷⁵

When experimental data produces integer values, this asks very strongly for our attention. One must ask whether some physical mechanism guards the integer value from the many processes that could modify it. One

of the simplest and most convincing ways to make an integer value resilient against interactions and other processes is to use topology, for instance via a winding number.

VIII. MEISSNER PHYSICS

It should be mentioned that even conventional superconductivity has features that seem reminiscent of topology: a contrast between bulk physics and surface physics, and guaranteed conduction on the surface. Where a TI bulk band gap expels charge carriers from the bulk, superconductors expel magnetic field from the bulk. In a TI charge conduction on the surface is guaranteed by topology and the bulk gap, while in a superconductor Meissner currents on the surface are required in order to expel magnetic field from the bulk.

While a comparison between topology and conventional superconductors is in some respects attractive, this comparison has two fundamental difficulties. The first is that superconductors can not be directly compared to TIs, since one does not allow charge conduction in the bulk and the other does. Perhaps the solution to this difficulty is think of Weyl materials instead of TIs. The second and more profound difficulty is that this sort of reasoning can be used to suggest that ordinary conductors have topological features. Ordinary conductors expel electric fields from their bulk, and use surface charge accumulation to achieve that expulsion.

IX. POSTSCRIPT: HOW TO DO TOPOLOGY IN A STRONGLY INTERACTING MATERIAL

Band topology is not a terribly promising tool for understanding high T_c materials, because these materials are so strongly interacting that the concepts of bands and Fermi surfaces are not reliable. Nonetheless the evidences reviewed in this article suggest that topology may be important. Here we briefly outline a few possible directions for doing topology without band structure. This is not an exhaustive list.

- **Focus on Many-Particle Aspects.** One approach is to attack strong interactions head-on: first write an interacting hamiltonian or a many-particle ground state, and then within this context work on developing a topological perspective. One example of this approach is development of many-body topological invariants, where the idea is to develop mathematical machinery for analyzing a multiparticle ground state and determining whether it implements topological order. For examples of this work see Refs. 3,97,98.

Another example is the Kitaev model, whose solutions are spin liquids, and are intrinsically topological. The Kitaev model can be solved exactly when

it is on a honeycomb lattice. Depending on the lattice, the Kitaev model implements nodal lines, Dirac cones, Majorana Fermi surfaces, or Weyl nodes.⁹⁹

While this approach is perhaps the most obvious, it might not always be the most productive. The challenges and technology of topology [either in the mathematical sense or the physics sense] are relatively well understood, in comparison to those of strong correlations and interactions. Therefore attacking the combination of topology with strong interactions by concentrating on strong interactions first may deliver practical results more slowly than starting with the aspects of this combination that are relatively tractable.

- **Focus on Broken Translational Invariance and the Absence of Band Structure.** Another approach is to focus on how to do topology when translational invariance is broken by scattering and therefore there is no band structure. The source of scattering can be static, i.e. disorder, or it can be dynamic, i.e. interactions. If the characteristic time scale of interactions and their fluctuations is longer than that of electron motion, then the effects of the two types of scattering may be similar.

Topological properties can be extraordinarily resilient against scattering. This can be observed by directly calculating topological invariants using formalisms which admit formulations that are independent of band structure and can be calculated in disordered materials.^{100–102}

Resilience against scattering can also be observed by measuring conduction and the energy-resolved density of states, neither of which is tied to translational invariance. The next three points discuss this in more detail:

- **Conduction.** Topology can guarantee conduction on the surface of a material even when scattering completely erases the band structure and band gap both on the surface and in the bulk; the only requirement is that the bulk must not conduct, which can be arranged by making it sufficiently disordered.^{65,66,103}
Topology can also guarantee conduction in the bulk of a material, if the Fermi energy is tuned to a topological phase transition. Because topological numbers cannot change without conduction through the bulk, at a topological phase transition the bulk is guaranteed to conduct.^{65,66}
- **Density of States as a Function of Energy.** The characteristic signature of a Dirac cone [constant density of states for 1-D edge states, linear in energy for 2-D surface states, quadratic in energy for 3-D bulk states] can

be maintained by topology even when scattering is so strong that there is no dispersion relation between momentum and energy. In this case the only effect of scattering on the density of states is to multiply by a constant, corresponding to multiplying the Fermi velocity by a constant.^{67,104} This result applies within a phase, while at boundaries between two phases non-trivial scaling relations may control the DOS.¹⁰⁵

- **Effective Models.** In topological insulators the effects of scattering on the density of states and conduction can be summarized by renormalizing the parameters of a disorder-free Dirac hamiltonian. In other words, even when translational invariance is completely absent and there is no dispersion correlating momentum with energy, topology’s invisible hand can ensure that the material acts as if a scattering-free Dirac particle were present.^{67,104}

Weyl materials take this a step further. In 3-D Dirac materials disorder is an irrelevant operator, so its effect on the Weyl cone [except at the Weyl point itself] can be made arbitrarily small by going to large enough distance scales and small enough momentum scales.^{106,107} For some observables such as conductance disorder may have no effect at all.¹⁰⁸

- **Renormalization Group Flow to Weyl Semimetals.** A material’s properties at long length scales may be much different than its properties at short length scales. For example, recent work has suggested that materials with spin-orbit coupling, magnetic impurities, and disorder may naturally flow into a Weyl semimetal phase.¹⁰⁹ Topological insulators with magnetic impurities can also flow into a Weyl semimetal phase as the system’s length scale is increased.¹¹⁰ This sort of scenario could produce a Weyl phase and Fermi arcs in the cuprates even if at short distances there are no Dirac or Weyl fermions.

Moreover when stacks of 2-D TIs are coupled together into a 3-D material, they can form Weyl semimetals or topological insulators.^{111,112} If there were something topological at work in individual cuprate copper oxide layers, for instance a Chern-Simons term or some kind of vortices, then possibly when the layers are stacked they could produce a Weyl phase and Fermi arcs.^{113–115}

- **Electron/hole loops.** As briefly outlined earlier in this text, weak (anti)localization is caused by Cooperons tracing loops. We also briefly discussed the fact that electrons and holes form loops in space-time, which gives a perspective on electronic transport that is founded on charge conservation and therefore is very solid. These loops are

an elementary topological object. Studies of how the space-time loops of electrons and holes can be braided or knotted or woven together may be able to offer new insight into strongly correlated electron transport.

We used an analysis of Cooperon loops and their areas to understand linear resistance. A key step in the analysis was that weak antilocalization not weak localization is seen experimentally, which implies that spin relaxes very quickly, long before a loop is completed. This obtained a simplification: in the case of weak antilocalization, the loops are spinless. Further work is needed on generalizing this loop analysis to systems where spin polarization persists longer and its effects on transport can

not be neglected.

Acknowledgments

We acknowledge the hospitality of J. Zaanen and the Instituut Lorentz in Leiden, A. Leggett and the UIUC, and G. Kotliar and Brookhaven National Laboratory. We are also thankful for helpful discussions with I. Bozovic, Jie Wu, A. Bollinger, I. Vishik, M. Hoesch, M. Watson, L. Rhodes, M. Norman, P. Johnson, S. Hayden, G. Parisi, P. Hasnip, A. Petrovic, K.-S. Kim, A. Ho, J. Saunders, L. Levitin, J. Koelzer, T. Schapers, C. Beenakker, Alex Lau, Quansheng Wu, M. Sulangi, K. Schalm, V. Cheianov, T. Ziman, P. Coleman, and M. Ma.

* Electronic address: vincent@sacksteder.com

- ¹ M. Z. Hasan and C. L. Kane, Rev. Mod. Phys. **82**, 3045 (2010), URL <https://link.aps.org/doi/10.1103/RevModPhys.82.3045>.
- ² X.-L. Qi and S.-C. Zhang, Rev. Mod. Phys. **83**, 1057 (2011), URL <https://link.aps.org/doi/10.1103/RevModPhys.83.1057>.
- ³ C.-K. Chiu, J. C. Y. Teo, A. P. Schnyder, and S. Ryu, Rev. Mod. Phys. **88**, 035005 (2016), URL <https://link.aps.org/doi/10.1103/RevModPhys.88.035005>.
- ⁴ A. Bansil, H. Lin, and T. Das, Rev. Mod. Phys. **88**, 021004 (2016), URL <https://link.aps.org/doi/10.1103/RevModPhys.88.021004>.
- ⁵ N. P. Armitage, E. J. Mele, and A. Vishwanath, Rev. Mod. Phys. **90**, 015001 (2018), URL <https://link.aps.org/doi/10.1103/RevModPhys.90.015001>.
- ⁶ D. J. Thouless, M. Kohmoto, M. P. Nightingale, and M. den Nijs, Phys. Rev. Lett. **49**, 405 (1982), URL <https://link.aps.org/doi/10.1103/PhysRevLett.49.405>.
- ⁷ M. E. Cage, K. Klitzing, A. M. Chang, F. Duncan, M. Haldane, R. B. Laughlin, A. M. M. Pruisken, and D. J. Thouless, *The quantum Hall effect* (Springer Science & Business Media, 2012).
- ⁸ H. L. Stormer, D. C. Tsui, and A. C. Gos-sard, Rev. Mod. Phys. **71**, S298 (1999), URL <https://link.aps.org/doi/10.1103/RevModPhys.71.S298>.
- ⁹ A. Pruisken, International Journal of Modern Physics B **24**, 1895 (2010).
- ¹⁰ G. R. Stewart, Rev. Mod. Phys. **83**, 1589 (2011), URL <https://link.aps.org/doi/10.1103/RevModPhys.83.1589>.
- ¹¹ B. Keimer, S. A. Kivelson, M. R. Norman, S. Uchida, and J. Zaanen, Nature **518**, 179 (2015).
- ¹² G. Stewart, Advances in Physics **66**, 75 (2017).
- ¹³ T. Morinari, E. Kaneshita, and T. Tohyama, Phys. Rev. Lett. **105**, 037203 (2010), URL <https://link.aps.org/doi/10.1103/PhysRevLett.105.037203>.
- ¹⁴ P. Richard, K. Nakayama, T. Sato, M. Neupane, Y.-M. Xu, J. H. Bowen, G. F. Chen, J. L. Luo, N. L. Wang, X. Dai, et al., Phys. Rev. Lett. **104**, 137001 (2010), URL <https://link.aps.org/doi/10.1103/PhysRevLett.104.137001>.
- ¹⁵ D. Bhoi, P. Mandal, P. Choudhury, S. Pandya, and V. Ganesan, Applied Physics Letters **98**, 172105 (2011).
- ¹⁶ Y. Tanabe, K. K. Huynh, S. Heguri, G. Mu, T. Urata, J. Xu, R. Nouchi, N. Mitoma, and K. Tanigaki, Phys. Rev. B **84**, 100508 (2011).
- ¹⁷ A. Lau and C. Timm, Phys. Rev. B **88**, 165402 (2013), URL <https://link.aps.org/doi/10.1103/PhysRevB.88.165402>.
- ¹⁸ I. Pallecchi, F. Bernardini, F. Caglieris, A. Palenzona, S. Massidda, and M. Putti, The European Physical Journal B **86**, 338 (2013).
- ¹⁹ A. Lau and C. Timm, Phys. Rev. B **90**, 024517 (2014), URL <https://link.aps.org/doi/10.1103/PhysRevB.90.024517>.
- ²⁰ Y. Sun, S. Pyon, and T. Tamegai, Phys. Rev. B **93**, 104502 (2016).
- ²¹ S. Y. Tan, Y. Fang, D. H. Xie, W. Feng, C. H. P. Wen, Q. Song, Q. Y. Chen, W. Zhang, Y. Zhang, L. Z. Luo, et al., Phys. Rev. B **93**, 104513 (2016), URL <https://link.aps.org/doi/10.1103/PhysRevB.93.104513>.
- ²² S. Kanayama, K. Nakayama, G. N. Phan, M. Kuno, K. Sugawara, T. Takahashi, and T. Sato, Phys. Rev. B **96**, 220509 (2017), URL <https://link.aps.org/doi/10.1103/PhysRevB.96.220509>.
- ²³ Z.-G. Chen, L. Wang, Y. Song, X. Lu, H. Luo, C. Zhang, P. Dai, Z. Yin, K. Haule, and G. Kotliar, Phys. Rev. Lett. **119**, 096401 (2017), URL <https://link.aps.org/doi/10.1103/PhysRevLett.119.096401>.
- ²⁴ T. Terashima, H. T. Hirose, D. Graf, Y. Ma, G. Mu, T. Hu, K. Suzuki, S. Uji, and H. Ikeda, Phys. Rev. X **8**, 011014 (2018), URL <https://link.aps.org/doi/10.1103/PhysRevX.8.011014>.
- ²⁵ P. Zhang, Z. Wang, X. Wu, K. Yaji, Y. Ishida, Y. Kohama, G. Dai, Y. Sun, C. Bareille, K. Kuroda, et al., Nature Physics **15**, 41 (2019).
- ²⁶ N. Hao and J. Hu, National Science Review **6**, 213 (2019).
- ²⁷ M. Norman, H. Ding, M. Randeria, J. Campuzano, T. Yokoya, T. Takeuchi, T. Takahashi, T. Mochiku, K. Kadowaki, P. Guptasarma, et al., Nature **392**, 157 (1998).
- ²⁸ I. Vishik, Reports on Progress in Physics **81**, 062501 (2018).
- ²⁹ A. Yazdani, E. H. da Silva Neto, and P. Aynajian, Annual Review of Condensed Matter Physics **7**, 11 (2016).
- ³⁰ A. Kordyuk, Low Temperature Physics **41**, 319 (2015).
- ³¹ K.-M. Kim, D. Shin, M. Sasaki, H.-J. Kim, J. Kim,

- and K.-S. Kim, Phys. Rev. B **94**, 085128 (2016), URL <https://link.aps.org/doi/10.1103/PhysRevB.94.085128>.
- ³² L. Li, H. H. Yap, M. A. N. Araújo, and J. Gong, Phys. Rev. B **96**, 235424 (2017), URL <https://link.aps.org/doi/10.1103/PhysRevB.96.235424>.
 - ³³ V. Sacksteder, Journal of Superconductivity and Novel Magnetism pp. 1–18 (2020).
 - ³⁴ G. P. Mikitik and Y. V. Sharlai, Phys. Rev. Lett. **82**, 2147 (1999), URL <https://link.aps.org/doi/10.1103/PhysRevLett.82.2147>.
 - ³⁵ Z. Wang, Z.-G. Fu, S.-X. Wang, and P. Zhang, Phys. Rev. B **82**, 085429 (2010), URL <https://link.aps.org/doi/10.1103/PhysRevB.82.085429>.
 - ³⁶ I. Božović, X. He, J. Wu, and A. Bollinger, Nature **536**, 309 (2016).
 - ³⁷ N. E. Hussey, K. Takenaka, and H. Takagi, Philosophical Magazine **84**, 2847 (2004).
 - ³⁸ I. M. Hayes, R. D. McDonald, N. P. Breznay, T. Helm, P. J. Moll, M. Wartenbe, A. Shekhter, and J. G. Analytis, Nature Physics **12**, 916 (2016).
 - ³⁹ P. Giraldo-Gallo, J. A. Galvis, Z. Stegen, K. A. Modic, F. F. Balakirev, J. B. Betts, X. Lian, C. Moir, S. C. Riggs, J. Wu, et al., arXiv preprint arXiv:1705.05806 (2017).
 - ⁴⁰ R. Kumar, S. Singh, and S. Nair, arXiv preprint arXiv:1801.03768 (2018).
 - ⁴¹ S. X. Zhang, R. D. McDonald, A. Shekhter, Z. X. Bi, Y. Li, Q. X. Jia, and S. T. Picraux, Applied Physics Letters **101**, 202403 (2012).
 - ⁴² W. Zhang, R. Yu, W. Feng, Y. Yao, H. Weng, X. Dai, and Z. Fang, Phys. Rev. Lett. **106**, 156808 (2011).
 - ⁴³ X. Wang, Y. Du, S. Dou, and C. Zhang, Phys. Rev. Lett. **108**, 266806 (2012).
 - ⁴⁴ J. Feng, Y. Pang, D. Wu, Z. Wang, H. Weng, J. Li, X. Dai, Z. Fang, Y. Shi, and L. Lu, Phys. Rev. B **92**, 081306 (2015).
 - ⁴⁵ F. Kisslinger, C. Ott, C. Heide, E. Kampert, B. Butz, E. Spiecker, S. Shallcross, and H. B. Weber, Nature Physics **11**, 650 (2015).
 - ⁴⁶ C. Zhang, C. Guo, H. Lu, X. Zhang, Z. Yuan, Z. Lin, J. Wang, and S. Jia, Phys. Rev. B **92**, 041203 (2015).
 - ⁴⁷ K. Wang, D. Graf, and C. Petrovic, Phys. Rev. B **89**, 125202 (2014).
 - ⁴⁸ X. Xu, W. H. Jiao, N. Zhou, Y. Guo, Y. K. Li, J. Dai, Z. Q. Lin, Y. J. Liu, Z. Zhu, X. Lu, et al., Journal of Physics: Condensed Matter **27**, 335701 (2015).
 - ⁴⁹ J. Fenton and A. J. Schofield, Phys. Rev. Lett. **95**, 247201 (2005).
 - ⁵⁰ A. E. Koshelev, Phys. Rev. B **88**, 060412 (2013).
 - ⁵¹ A. A. Abrikosov, Phys. Rev. B **58**, 2788 (1998).
 - ⁵² T. Khouri, U. Zeitler, C. Reichl, W. Wegscheider, N. E. Hussey, S. Wiedmann, and J. C. Maan, Phys. Rev. Lett. **117**, 256601 (2016).
 - ⁵³ M. M. Parish and P. B. Littlewood, Nature **426**, 162 (2003).
 - ⁵⁴ V. Sacksteder, arXiv preprint arXiv:1801.02663 (2018).
 - ⁵⁵ K. Ishii, Progress of Theoretical Physics Supplement **53**, 77 (1973).
 - ⁵⁶ B. Simon and T. Spencer, Communications in Mathematical Physics **125**, 113 (1989).
 - ⁵⁷ C. W. J. Beenakker, Rev. Mod. Phys. **69**, 731 (1997), URL <https://link.aps.org/doi/10.1103/RevModPhys.69.731>.
 - ⁵⁸ T. Ando and H. Suzuura, Journal of the Physical Society of Japan **71**, 2753 (2002).
 - ⁵⁹ Y. Takane, Journal of the Physical Society of Japan **73**, 1430 (2004).
 - ⁶⁰ L. Oroszlány, P. Rakytá, A. Kormányos, C. J. Lambert, and J. Cserti, Phys. Rev. B **77**, 081403 (2008).
 - ⁶¹ T. K. Ghosh, A. De Martino, W. Häusler, L. Dell’Anna, and R. Egger, Phys. Rev. B **77**, 081404 (2008).
 - ⁶² J. R. Williams and C. M. Marcus, Phys. Rev. Lett. **107**, 046602 (2011).
 - ⁶³ Y. Kohsaka, C. Taylor, K. Fujita, A. Schmidt, C. Lupien, T. Hanaguri, M. Azuma, M. Takano, H. Eisaki, H. Takagi, et al., Science **315**, 1380 (2007).
 - ⁶⁴ C. V. Parker, P. Aynajian, E. H. da Silva Neto, A. Pushp, S. Ono, J. Wen, Z. Xu, G. Gu, and A. Yazdani, Nature **468**, 677 (2010).
 - ⁶⁵ L. Chen, Q. Liu, X. Lin, X. Zhang, and X. Jiang, New Journal of Physics **14**, 043028 (2012).
 - ⁶⁶ D. Xu, J. Qi, J. Liu, V. Sacksteder, X. C. Xie, and H. Jiang, Phys. Rev. B **85**, 195140 (2012), URL <https://link.aps.org/doi/10.1103/PhysRevB.85.195140>.
 - ⁶⁷ V. Sacksteder, T. Ohtsuki, and K. Kobayashi, Phys. Rev. Applied **3**, 064006 (2015), URL <https://link.aps.org/doi/10.1103/PhysRevApplied.3.064006>.
 - ⁶⁸ M. D. Watson, T. K. Kim, L. C. Rhodes, M. Eschrig, M. Hoesch, A. A. Haghighirad, and A. I. Coldea, Phys. Rev. B **94**, 201107 (2016), URL <https://link.aps.org/doi/10.1103/PhysRevB.94.201107>.
 - ⁶⁹ A. I. Coldea and M. D. Watson, Annual Review of Condensed Matter Physics **9**, 125 (2018).
 - ⁷⁰ L. C. Rhodes, M. D. Watson, A. A. Haghighirad, D. V. Evtushinsky, and T. K. Kim, arXiv preprint arXiv:2004.04660 (2020).
 - ⁷¹ S. Hikami, A. I. Larkin, and Y. Nagaoka, Progress of Theoretical Physics **63**, 707 (1980).
 - ⁷² G. Bergman, Phys. Rev. Lett. **48**, 1046 (1982), URL <https://link.aps.org/doi/10.1103/PhysRevLett.48.1046>.
 - ⁷³ V. E. Sacksteder, S. Kettemann, Q. Wu, X. Dai, and Z. Fang, Phys. Rev. B **85**, 205303 (2012), URL <https://link.aps.org/doi/10.1103/PhysRevB.85.205303>.
 - ⁷⁴ J. Chen, X. Y. He, K. H. Wu, Z. Q. Ji, L. Lu, J. R. Shi, J. H. Smet, and Y. Q. Li, Phys. Rev. B **83**, 241304 (2011), URL <https://link.aps.org/doi/10.1103/PhysRevB.83.241304>.
 - ⁷⁵ N. Barišić, M. K. Chan, Y. Li, G. Yu, X. Zhao, M. Dressel, A. Smontara, and M. Greven, Proceedings of the National Academy of Sciences **110**, 12235 (2013).
 - ⁷⁶ M. Hashimoto, T. Yoshida, K. Tanaka, A. Fujimori, M. Okusawa, S. Wakimoto, K. Yamada, T. Kakeshita, H. Eisaki, and S. Uchida, Phys. Rev. B **79**, 140502 (2009), URL <https://link.aps.org/doi/10.1103/PhysRevB.79.140502>.
 - ⁷⁷ U. Chatterjee, D. Ai, J. Zhao, S. Rosenkranz, A. Kaminski, H. Raffy, Z. Li, K. Kadowaki, M. Randeria, M. R. Norman, et al., Proceedings of the National Academy of Sciences **108**, 9346 (2011).
 - ⁷⁸ J. S. Kim, B. H. Kim, D. C. Kim, and Y. W. Park, Journal of superconductivity **17**, 151 (2004).
 - ⁷⁹ S. Ohsugi, Y. Kitaoka, K. Ishida, and K. Asayama, Journal of the Physical Society of Japan **60**, 2351 (1991).
 - ⁸⁰ C. Panagopoulos, M. Majoros, T. Nishizaki, and H. Iwasaki, Phys. Rev. Lett. **96**, 047002 (2006), URL <https://link.aps.org/doi/10.1103/PhysRevLett.96.047002>.
 - ⁸¹ C. Panagopoulos, M. Majoros, and A. P. Petrović, Phys. Rev. B **69**, 144508 (2004), URL <https://link.aps.org/doi/10.1103/PhysRevB.69.144508>.

- ⁸² I. Božović, X. He, J. Wu, and A. Bollinger, *Nature* **536**, 309 (2016).
- ⁸³ R. P. Feynman and A. R. Hibbs, *Quantum mechanics and path integrals* (McGraw-Hill, 1965).
- ⁸⁴ R. Liang, D. A. Bonn, and W. N. Hardy, *Phys. Rev. B* **73**, 180505 (2006), URL <https://link.aps.org/doi/10.1103/PhysRevB.73.180505>.
- ⁸⁵ F. Jean, G. Collin, M. Andrieux, N. Blanchard, and J.-F. Marucco, *Physica C: Superconductivity* **339**, 269 (2000).
- ⁸⁶ X.-J. Chen, V. V. Struzhkin, Y. Yu, A. F. Goncharov, C.-T. Lin, H.-k. Mao, and R. J. Hemley, *Nature* **466**, 950 (2010).
- ⁸⁷ A. M. Balagurov, D. V. Sheptyakov, V. L. Aksenov, E. V. Antipov, S. N. Putilin, P. G. Radaelli, and M. Marezio, *Phys. Rev. B* **59**, 7209 (1999), URL <https://link.aps.org/doi/10.1103/PhysRevB.59.7209>.
- ⁸⁸ J. Z. Wu, *Physica C: Superconductivity* **493**, 96 (2013).
- ⁸⁹ A. Schilling, M. Cantoni, J. Guo, and H. Ott, *Nature* **363**, 56 (1993).
- ⁹⁰ L. Gao, Y. Y. Xue, F. Chen, Q. Xiong, R. L. Meng, D. Ramirez, C. W. Chu, J. H. Eggert, and H. K. Mao, *Phys. Rev. B* **50**, 4260 (1994), URL <https://link.aps.org/doi/10.1103/PhysRevB.50.4260>.
- ⁹¹ D. Huang and J. E. Hoffman, *Annual Review of Condensed Matter Physics* **8**, 311 (2017).
- ⁹² X. Chen, P. Dai, D. Feng, T. Xiang, and F.-C. Zhang, *National Science Review* **1**, 371 (2014).
- ⁹³ H. Takahashi, H. Soeda, M. Nukii, C. Kawashima, T. Nakanishi, S. Imura, Y. Muraba, S. Matsuishi, and H. Hosono, *Scientific reports* **5**, 1 (2015).
- ⁹⁴ H. Hosono, A. Yamamoto, H. Hiramatsu, and Y. Ma, *Materials today* **21**, 278 (2018).
- ⁹⁵ H. Roeser, F. Hetfleisch, F. Huber, M. von Schoenemark, M. Stepper, A. Moritz, and A. Nikoghosyan, *Acta Astronautica* **62**, 733 (2008).
- ⁹⁶ M. R. Koblishka, S. Roth, A. Koblishka-Veneva, T. Karwoth, A. Wiederhold, X. L. Zeng, S. Fasoulas, and M. Murakami, *Metals* **10**, 158 (2020).
- ⁹⁷ T. Senthil, *Annu. Rev. Condens. Matter Phys.* **6**, 299 (2015).
- ⁹⁸ H. Shapourian, K. Shiozaki, and S. Ryu, *Phys. Rev. Lett.* **118**, 216402 (2017), URL <https://link.aps.org/doi/10.1103/PhysRevLett.118.216402>.
- ⁹⁹ M. Hermanns, I. Kimchi, and J. Knolle, *Annual Review of Condensed Matter Physics* **9**, 17 (2018).
- ¹⁰⁰ Z. Xu, L. Sheng, D. Y. Xing, E. Prodan, and D. N. Sheng, *Phys. Rev. B* **85**, 075115 (2012), URL <https://link.aps.org/doi/10.1103/PhysRevB.85.075115>.
- ¹⁰¹ Z. Yi-Fu, Y. Yun-You, J. Yan, S. Li, S. Rui, S. Dong-Ning, and X. Ding-Yu, *Chinese Physics B* **22**, 117312 (2013).
- ¹⁰² E. Prodan, T. L. Hughes, and B. A. Bernevig, *Phys. Rev. Lett.* **105**, 115501 (2010), URL <https://link.aps.org/doi/10.1103/PhysRevLett.105.115501>.
- ¹⁰³ Y.-Y. Zhang, R.-L. Chu, F.-C. Zhang, and S.-Q. Shen, *Phys. Rev. B* **85**, 035107 (2012), URL <https://link.aps.org/doi/10.1103/PhysRevB.85.035107>.
- ¹⁰⁴ Q. Wu, L. Du, and V. E. Sacksteder, *Phys. Rev. B* **88**, 045429 (2013), URL <https://link.aps.org/doi/10.1103/PhysRevB.88.045429>.
- ¹⁰⁵ K. Kobayashi, T. Ohtsuki, K.-I. Imura, and I. F. Herbut, *Phys. Rev. Lett.* **112**, 016402 (2014), URL <https://link.aps.org/doi/10.1103/PhysRevLett.112.016402>.
- ¹⁰⁶ R. Shindou and S. Murakami, *Phys. Rev. B* **79**, 045321 (2009), URL <https://link.aps.org/doi/10.1103/PhysRevB.79.045321>.
- ¹⁰⁷ P. Goswami and S. Chakravarty, *Phys. Rev. Lett.* **107**, 196803 (2011), URL <https://link.aps.org/doi/10.1103/PhysRevLett.107.196803>.
- ¹⁰⁸ K. Kobayashi, T. Ohtsuki, and K.-I. Imura, *Phys. Rev. Lett.* **110**, 236803 (2013), URL <https://link.aps.org/doi/10.1103/PhysRevLett.110.236803>.
- ¹⁰⁹ K.-M. Kim, J. Kim, S.-W. Kim, M.-H. Jung, and K.-S. Kim, *Phys. Rev. B* **98**, 205133 (2018), URL <https://link.aps.org/doi/10.1103/PhysRevB.98.205133>.
- ¹¹⁰ K.-M. Kim, Y.-S. Jho, and K.-S. Kim, *Phys. Rev. B* **91**, 115125 (2015), URL <https://link.aps.org/doi/10.1103/PhysRevB.91.115125>.
- ¹¹¹ Y. Yoshimura, W. Onishi, K. Kobayashi, T. Ohtsuki, and K.-I. Imura, *Phys. Rev. B* **94**, 235414 (2016), URL <https://link.aps.org/doi/10.1103/PhysRevB.94.235414>.
- ¹¹² K. Kobayashi, Y. Yoshimura, K.-I. Imura, and T. Ohtsuki, *Phys. Rev. B* **92**, 235407 (2015), URL <https://link.aps.org/doi/10.1103/PhysRevB.92.235407>.
- ¹¹³ T. Morinari, *Journal of the Physical Society of Japan* **70**, 1472 (2001).
- ¹¹⁴ T. Morinari, *Superconductor Science and Technology* **16**, 624 (2003).
- ¹¹⁵ S.-P. Kou, X.-L. Qi, and Z.-Y. Weng, *Phys. Rev. B* **71**, 235102 (2005), URL <https://link.aps.org/doi/10.1103/PhysRevB.71.235102>.
- ¹¹⁶ S. He, J. He, W. Zhang, L. Zhao, D. Liu, X. Liu, D. Mou, Y.-B. Ou, Q.-Y. Wang, Z. Li, et al., *arXiv preprint arXiv:1207.6823* (2012).
- ¹¹⁷ We did many detailed and lengthy searches of citations of the original article on Fermi arcs in cuprates²⁷, and found no discussion of the possibility that these might be associated with Weyl fermions.
- ¹¹⁸ We use 13.14 Angstroms and $a \approx 3.82$ Angstroms for the lattice parameters of LSCO.
- ¹¹⁹ Figure 2h of Ref. 116 gives the optimal doping between $p = 0.11$ and $p = 0.12$ electrons per iron atom.