Superconductor-insulator transition induced by pressure within the X-boson approach \star

Lizardo H. C. M. Nunes^a, M. S. Figueira^a, E. V. L. de Melllo^a

^aInstituto de Física da Universidade Federal Fluminense Av. Litorânea s/n, 24210-340 Niterói, Rio de Janeiro, Brasil. C.P.100.093

Abstract

The pressure induced superconducting phase diagram is calculated for an extension of the periodic Anderson model (PAM) in the $U = \infty$ limit taking into account the effect of a nearest neighbor attractive interaction between f-electrons. We analyze the role of the chemical potential compared to several plots of the the f-band density of states and we also found a superconductor-insulator transition induced by pressure when the chemical potential crosses the hybridization gap.

Key words: Superconductivity, heavy fermions, insulator-superconductor transition PACS: 71.10-w, 74.70.Tx, 74.20.Fg, 74.25.Dw, 74.72.2h, 75.30.Mb

1. Introduction

Recently, we have used the X-boson method [1] to obtain the superconducting phase diagram of the PAM in the $U \to \infty$, where U is the on-site Coulomb repulsion, plus a nearest neighbor attractive interaction between the localized f-electrons. As charge carriers are added to the system [2] superconductivity was found both for configurations where the system presented intermediate valence (IV) and heavy fermion (HF) behavior, as experimentally observed[3]. Moreover, we have recovered the three characteristic regimes of the PAM: Kondo, IV and magnetic; which cannot be found for the same model by the slave-boson treatment[3], since it breaks down when the f-occupation number $N_f \rightarrow$ 1. In this paper we use the same approach to study the pressure induced superconducting phase diagram of the heavy fermion systems.

2. The Method

In our approach we consider the energy of the localized *f*-electrons site independent, $E_{f,j,\sigma} = E_f$, and impose a constant hybridization, $V = V_{j,\sigma,\mathbf{k}}$,

$$H = \sum_{\mathbf{k},\sigma} \epsilon_{\mathbf{k},\sigma} c^{\dagger}_{\mathbf{k},\sigma} c_{\mathbf{k},\sigma} + \sum_{\mathbf{k},\sigma} \tilde{E}_{f} X_{\mathbf{k},\sigma\sigma} + \sum_{\mathbf{k},\sigma} V(X^{\dagger}_{\mathbf{k},\mathbf{0}\sigma} c_{\mathbf{k},\sigma} + c^{\dagger}_{\mathbf{k},\sigma} X_{\mathbf{k},\mathbf{0}\sigma}) + \sum_{\mathbf{k},\mathbf{k}'} W_{\mathbf{k},\mathbf{k}'} b^{\dagger}_{\mathbf{k}} b_{\mathbf{k}'} + N_{s} \Lambda \left(R - 1\right) , \qquad (1)$$

where the operator $b_{\mathbf{k}}^{\dagger} = X_{\mathbf{k},\mathbf{0}\sigma}^{\dagger}X_{-\mathbf{k},\mathbf{0}\overline{\sigma}}^{\dagger}$, creates Cooper pairs. The matrix element $W_{\mathbf{k},\mathbf{k}'}$ is the superconducting coupling. Since we only consider an isotropic *s*-wave superconducting gap, $W_{\mathbf{k},\mathbf{k}'}$ is reduced to the wellknown BCS interaction. Also, the operator $X_{\mathbf{k},\sigma\sigma'}$ is the Hubbard operator. The variational parameter $R = 1 - \sum_{\sigma} \langle X_{\sigma\sigma} \rangle$, introduced by the X-boson approach, modifies the approximate GF so that it minimizes an adequate thermodynamic potential while being forced to satisfy the "completeness" relation $n_0 + n_{\sigma} + n_{\overline{\sigma}} = 1$,

19 December 2021

^{*} We acknowledge Prof. M. E. Foglio (Unicamp) for helpful discussions and the financial support from the Rio de Janeiro State Research Foundation (FAPERJ) and National Research Council (CNPq).

Email address: lizardo@if.uff.br (Lizardo H. C. M. Nunes).

where $n_{j,a} = \langle X_{j,aa} \rangle$. Within the X-boson method the Lagrange multiplier Λ is chosen so that the "completeness" is satisfied and the energy of the *f*-electrons are renormalized by $\tilde{E}_f = E_f + \Lambda$.

At $T = T_c$ the Green's functions (GFs) yield to the result found in the chain approximation (CHA) of the PAM, [1] but now with the localized energy levels E_f and $D_{\sigma} = R + n_{\sigma}$ renormalized, and the self-consistent equation for T_c is [2]

$$1 = -\frac{W}{\beta_c} \sum_{n,\mathbf{k}} \left| \mathcal{G}_{\sigma}^{ff}(-\mathbf{k},\omega_n) \right|_{T=T_c}^2, \qquad (2)$$

which is solved constrained to the "completeness" relation and for a constant conduction density of states, $\rho(\epsilon_{\mathbf{k}}) = 1/2D$, only defined for the interval $-D \leq \epsilon_{\mathbf{k}} - \mu \leq D$. The pressure induced phase diagram is obtained following a scheme proposed by Bernhard and Lacroix[4] assuming that the ratio V/D is constant. Indeed, one expects that the local parameters E_f and Udo not change with pressure, while D and V should increase with pressure. The total electron number $N_t =$ $N_f + N_c$, is kept constant and the chemical potential is calculated self-consistently while the electrons are allowed to transfer between bands.

3. Results and Discussion

We choose the parameters to characterize a typical Kondo regime. We set $E_f = -0.15$ below the chemical potential potential $\mu = 0$ and W corresponds to 5% of the bandwidth 2D. Within the X-boson approach and



Fig. 1. (a) The pressure induced superconducting phase diagram for V/D = 0.2 and $N_t = 1.73$. (b) The onset shows the occupation numbers for the *f*-electrons N_f and the conducting electrons N_c as a function of the hybridization V. (c)-(d) The same as in (a)-(b) but for $N_t = 1.66$.

for every set of parameters used, as N_t is kept constant and V increases, N_c also increases. Hence, electrons are removed from the *f*-band and placed in the conducting band, as can be seen in Figs. 1.b and 1.d. Since Cooper pairing occurs only between the f electrons, as N_f decreases, T_c also decreases. Moreover, our results



Fig. 2. Plots of the *f*-band density of states $\rho_f(\omega)$ (filled line) and the *c*-band density of sates $\rho_c(\omega)$ (short dashed lines) for (a)-(c) $N_t = 1.73$ and (d)-(f) $N_t = 1.73$ for V/D = 0.2compared to the values of the chemical potential μ (vertical dashed line).

for the superconducting phase diagram can be inferred from the behavior of the chemical potential compared to several plots of the the f-band density of states. Indeed, our previous results [2] show that the existence of superconductivity is constrained to a region where the f-band densities of states $\rho_f(\mu)$ at $\omega = \mu$ is sufficiently high while high $\rho_f(\mu)$ usually implicates higher values of T_c . For low V the f-band density of states is located in a narrower region of the bandwidth, since the electrons are more localized, the two peaks of the density of states are sharp and the distance between them is small, as V increases, the f-band density of states takes up smaller values and the distance between peaks are broadened, as can be seen in Fig. 2. Hence, for $N_t =$ 1.73 and based on the arguments above, the function $T_c(V)$ have a single maximum. For $N_t = 1.66$ superconductivity is suppressed when μ crosses the hybridization gap and the system presents a superconductorinsulator transition induced by pressure. Recently the same kind of transition was experimentally observed for the spinel compound $CuRh_2S_4[5]$.

References

- R. Franco, M. S. Figueira and M. E. Foglio, Phys. Rev. B 66, 045112 (2002), and references therein.
- [2] Lizardo H. C.M.Nunes, M. S. Figueira, E. V. L. de Mello, cond-mat/0301126, to be appeared in Phys. Rev. B.
- [3] M. A. N. Araújo, N. M. R. Peres, P. D. Sacramento, and V. R. Vieira, Phys. Rev. B 62, 9800 (2000), and references therein.
- [4] Ben Hur Bernhard and Claudine Lacroix, Phys. Rev. B. 60, 12149 (1999).

[5] Masakazu Ito et al. , cond-mat/0211232.