# Wall cratering upon high velocity normal dust impact

Panagiotis Tolias<sup>a</sup>, Marco De Angeli<sup>b</sup>, Dario Ripamonti<sup>c</sup>, Svetlana Ratynskaia<sup>a</sup>, Giulio Riva<sup>c</sup>, Giambattista Daminelli<sup>c</sup> and Monica De Angeli<sup>b</sup>

> <sup>a</sup> Space and Plasma Physics - KTH Royal Institute of Technology, Teknikringen 31, 10044 Stockholm, Sweden <sup>b</sup>Institute for Plasma Science and Technology, CNR, via Cozzi 53, 20125 Milano, Italy <sup>c</sup>Institute of Condensed Matter Chemistry and Energy Technologies, CNR, via Cozzi 53, 20125 Milano, Italy

#### Abstract

Abstract
Dust-wall high velocity impacts, triggered by runway electron dissipation, constitute an important source of gross erosion. Normal high velocity mechanical impacts of micrometer tragsten dist on bulk traggered plates have been reproduced in a controlled manner by light gas gun shooting systems. Fost-mortem surface analysis revealed that three erosion regimes of reliable empirical damage laws in the latter regime, which can be employed for erosion estimates in future reactors. *Keywords*: dust in tokamaks, mechanical impacts, high velocity range, damage laws, impact bonding **1 throuction**The presence of dust in fusion devices has important optic of magnitude compared to csisting devices and plate stratic and and safety implications, especially in future fusion reactors. The first group can be abstruction of a reliable empirical damage laws in tokamaks [1, 2, 3]. Hence, the dist damage in the sion community[4, 5, 6, 7, 8, 9] but wall mechanical inpacts have gameged to constraine trags of inclusions are prepared that are accelerated to device and plate transport, production but stransports, production within the fusion community[4, 5, 6, 7, 8, 9] but wall mechanical inpacts have gameged in tokamaks [10]. As a compared to have damage in tokamaks [10]. As a compared to have damage in tokamaks [10]. As a compared to have damage in tokamaks [10]. As a compared to have damage in tokamaks [10]. As a compared to have damage in tokamaks [10]. As a compared to have damage in the dust preparation could shave a survivability [11], play a pivotal role in the formation, and set were deviced in dimense transport, production at mechanical inpacts have game group to have four present to high speeds (500–200 m/s) toras a four group moment (PC) damage [1].
Mortand have dust dynamics in tokamaks [10]. As a compared to a size inpact shave been revealed to control dimense to high speeds (500–200 m/s) toras a four group moment (PC) damage [1].

investigation has concentrated on the high velocity range,  $200 \lesssim v_{\rm imp}[{\rm m/s}] \lesssim 4000$ , that is characterized by strong dust deformations and shallow crater formation [21]. It has been recently concluded that the high velocity range is attainable for tokamak dust[13]. Thus, high velocity impacts constitute an unexplored source of gross wall erosion and an up-to-now unidentified mechanism of dust destruction.

The above naturally bring forth the question of whether

cuss its relevance to dust in tokamaks. It is worth pointing out that each velocity range limit depends not only on the material composition but also on the dust size and dust & wall temperature. Thus, the limits stated below should be deemed as indicative. The discussion is also applicable to oblique impacts, but not to molten projectiles or targets.

In the low-to-moderate velocity range,  $v_{\rm imp} \lesssim 200$ m/s, the mechanical impact induces weak plastic deformations to the projectile and the target [22]. Two regimes can be distinguished; the *sticking regime* of  $v_{\rm imp} \leq 5 \,\mathrm{m/s}$ where the irreversible adhesive work performed during the near-elastic impact dissipates the incident kinetic energy of the projectile and thus leads to immobilization [23], the *inelastic rebound regime*  $5 \leq v_{\rm imp}[{\rm m/s}] \leq 200$  where the projectile rebounds with a decreased kinetic energy due to adhesive work, plastic dissipation and frictional losses [24]. This is the most typical range for tokamak dust that has been studied experimentally and theoretically for fusionrelevant materials [14, 15, 16, 17]. In particular, a unified analytical description has been achieved for both regimes by combining an elastic-perfectly plastic adhesive impact mechanics model [25] with a rigid sliding body model [26].

In the high velocity range,  $200 \leq v_{imp}[m/s] \leq 4000$ , the mechanical impact induces strong plastic deformations, surface melting and partial fragmentation to both the projectile and target [27]. Three regimes can be distinguished; the deformation regime of 200  $\lesssim v_{\rm imp} [{\rm m/s}] \lesssim 500$  that is accompanied by severe projectile flattening & shallow target crater formation [28], the bonding or cold spray regime of 500  $\lesssim v_{\rm imp}[{\rm m/s}] \lesssim 1000$  that is characterized by the adhesion of the projectile on the target, which can be realized by various mechanisms such as localized melting, adiabatic shear instability, viscous interlocking and interfacial amorphization [29, 30, 31, 32, 33], the partial disintegration regime of  $1000 \leq v_{\rm imp} [{\rm m/s}] \leq 4000$  that is accompanied by material splash ejection and partial fragmentation [27]. It has been recently demonstrated that the high velocity range is relevant for the solid dust that is produced by explosive dissipation of runaway electrons on PFCs. In particular, postmortem and in situ evidence from FTU (2013 shutdown and 2019 decommisioning), strongly supported by dust dynamics simulations and dedicated laboratory tests, revealed that the dissipation of runaway electrons on the equatorial poloidal limiter led to the generation of very fast solid dust that generated multiple shallow craters upon impact on the adjacent toroidal limiters [13].

In the hyper-velocity range of  $v_{\rm imp} \gtrsim 4000 \, {\rm m/s}$ , the impact velocity is comparable or larger than the compressive sound speeds of the projectile and the target [21]. This triggers the emergence of strong shockwaves, upon whose sudden compaction extreme transient pressures and temperatures arise at the collision zone. Upon shockwave release, both materials extensively vaporize while the localized energy is large enough to cause atomic excitation and partial ionization [34]. As a result, hyper-velocity impacts are accompanied by strong electrostatic [34, 35] and spectroscopic signals [36, 37]. In addition, the emerging craters feature excavated volumes that by far exceed the volume of the projectile. Finally, very high velocity solid ejecta can be released that cause further damage to the surrounding material [38]. Solid evidence of hypervelocity impacts have been obtained in FTU that concerned the in-situ detection of dust impact ionization by electrostatic probes and the post-mortem observation of craters [18, 19, 20]. However, considering the typical initial dust velocity distributions



Figure 1: Image of a damaged bulk W target after the high velocity impact of spherical W dust (here  $D_{\rm d} = 51\,\mu{\rm m}$  and  $v_{\rm imp} = 2075\,{\rm m/s}$ ) together with magnified SEM images of two regions that have been included in the statistical crater analysis.

Table I: W-on-W impacts realized by the one- and two-stage light gas gun. In what follows,  $D_{\rm d}$  denotes the mean dust diameter,  $v_{\rm imp}$  the impact velocity, # the crater statistics,  $D_{\rm c}$  the measured crater diameter,  $\sigma_{\rm D}$  the standard deviation in the crater diameter,  $H_{\rm c}$  the measured crater depth,  $\sigma_{\rm H}$  the standard deviation in the crater depth. The negative sign in the crater depth is indicative of impact bonding.

$D_{\rm d}$	v <sub>imp</sub>	#	$D_{\rm c}$	$\sigma_{ m D}$	H <sub>c</sub>	$\sigma_{ m H}$
$(\mu m)$	(m/s)		$(\mu m)$	$(\mu m)$	$(\mu m)$	$(\mu m)$
51	660	97	74.2	15.5	+7.5	3.3
51	984	83	73.0	15.3	-13.3	3.9
51	1565	62	84.0	17.7	+14.9	5.7
51	2075	73	99.3	20.9	+32.2	5.1
51	2506	47	106.1	22.3	+40.4	5.3
51	2561	36	107.8	22.9	+38.4	7.1
51	3128	37	115.7	24.4	+50.0	6.7
63	596	110	84.2	17.5	+8.1	3.2
63	764	64	89.0	18.4	-26.3	4.2
63	1012	63	89.2	18.2	-14.3	4.6
63	1534	72	97.8	20.5	+21.4	6.4
63	2039	78	119.0	24.8	+43.3	7.3
63	2485	37	129.3	26.8	+51.1	8.1
63	2500	45	130.9	27.4	+47.5	8.2
63	3108	33	142.0	35.1	+62.4	11.3
63	3190	36	149.3	30.8	+66.6	8.2
76	583	99	104.9	21.3	+8.7	3.2
76	997	48	108.2	22.2	-16.8	5.8
76	1563	57	121.8	26.6	+31.6	10.5
76	2033	35	143.3	29.4	+50.1	7.3
76	2058	43	145.6	30.7	+48.1	5.8
76	2513	25	153.8	31.4	+64.4	8.9
76	2551	36	152.6	33.4	+65.3	10.7
76	3069	27	180.7	42.3	+81.9	14.2
76	3126	20	180.0	38.4	+80.1	9.2



Figure 2: SEM images of the three erosion regimes that are realized in high velocity W-on-W normal dust-wall impacts for a given spherical dust size  $(D_d = 63 \,\mu\text{m})$ : (a) **plastic deformation regime** (here for  $v_{imp} = 596 \,\text{m/s}$ ), tilted image at 45°, (b) **impact bonding regime** (here for  $v_{imp} = 764 \,\text{m/s}$ ), tilted image at 45°, (c) **partial disintegration regime** (here for  $v_{imp} = 1563 \,\text{m/s}$ ), normal image at 90°.

and given the generally restricted acceleration lengths, no acceleration mechanisms are currently known that can lead to impact speeds within the hyper-velocity range [4, 8].

### 3. Experimental

High-sphericity low internal porosity W dust was supplied by "TEKNA Advanced Materials Inc". The original batch had a nominal size distribution of  $45 - 90 \,\mu\text{m}$ . From this polydisperse batch, three nearly monodisperse dust subpopulations were meshed out using a sequence of six sieves with nominal sizes of 80, 75, 71, 63, 56, 50  $\mu\text{m}$ . The mean W dust diameters are  $51(\pm 5)\mu\text{m}$ ,  $63(\pm 5)\mu\text{m}$  and  $76(\pm 5)\mu\text{m}$ , sizes that are comparable to the most probable sizes of the fast Mo solid dust that was observed in FTU [13]. The bulk square W targets have 23 mm length and 4 mm thickness.

High velocity dust-wall impacts are realized by means of a light gas gun system [39, 40]. In the two stage configuration, the first stage is a high pressure reservoir connected to the second stage with a fast valve. The second stage (or pump tube) is a cylinder in which the light gas is fed at relatively low pressure and compressed by a free piston following the fast valve operation. The compressed light gas rapidly expands into the launch tube, which has a smaller diameter than the pump tube, simultaneously accelerating a macro-scale projectile (or sabot) that features a cavity loaded with micrometer dust. The dust particles are separated from the sabot at the end of the launch tube, where the latter collides on a diaphragm. The dust particles free stream with high velocities into a vacuum chamber that features the target. Impact speeds that cover the range of  $1000 \leq v_{\rm imp} [{\rm m/s}] \leq 3500$  have been realized by employing different light gases (nitrogen or hydrogen) and setting different initial pressures for the first (20 - 40 bar) & second (0.8 - 1.2 bar) stage. In the single stage configuration, the high-pressure hydrogen reservoir is directly connected to the launch tube without an intervening piston and the achieved impact speeds lie within  $400 \leq v_{\rm imp} [{\rm m/s}] \leq 1000$ .

The dust speed is measured through the dust transit time between two laser sheets with an uncertainty that is generally less than  $\pm 1\%$ . This measurement error primarily originates from the relatively large thickness of the individual beams (1 mm) when compared to the beam spacing (100 mm). The above optical method was preferred over the time-of-flight method [40, 41], where the start trigger is provided by the muzzle flash caused by sabot ejection from the barrel and the stop trigger is given by the impact flash, whose precision is about  $\pm 3\%$ .

Overall, 34 impact tests were performed with the three dust sub-populations and impact speeds covering the entire high velocity range. By default, the light gas gun acceleration method leads to a very large number of W-on-W impacts. However, the useful crater statistics are rather restricted, since the central target spot features many overlapping craters that need to be excluded from the analysis, see figure 1 for an example. Naturally, it is possible to minimize the central spot by loading less dust on the sabot, but this compromises the accuracy of the speed measurement and does not necessarily improve statistics. From the 34 shot samples, 25 featured a large enough number of isolated craters suitable for statistical analysis (Table I).

The shot W-on-W samples were first mapped by means of a Scanning Electron Microscope (SEM), at low magnification and at high resolution, in order to statistically estimate the average value of the crater diameter at different impact conditions. The crater depth was then measured with a precision optical microscope (Leitz Wetzlar Ortolux) of  $0.5 \,\mu$ m sensitivity. Moreover, few craters from each shot sample were mapped with a mechanical profiler (KLA-Tencor mod. P-15) in order to verify the precision of the above techniques. The instrumental uncertainty was estimated to be  $\pm 3 \,\mu$ m for the crater depth (optical) and  $\pm 15\%$  for the crater diameter (SEM). The average values and standard deviations of the crater dimensions (instrumental and statistical errors) are listed in Table I.

Since the impact speeds varied from 583 m/s to 3190 m/s, all three impact regimes of the high velocity range were observed for all the three dust sub-populations. Characteristic examples are illustrated in figure 2.

## 4. Analysis

### 4.1. Empirical damage laws

Impact damage laws are empirical correlations of the crater diameter and crater depth as a function of the target and projectile material properties, impact speed, impact angle



Figure 3: The crater diameter (top panel) and the crater depth (bottom panel) in the *partial disintegration regime* as function of the normal W-on-W speed for three spherical W dust sub-populations. Experimental results (purple symbols with error bars) and empirical fits of the general form  $D_c$ ,  $H_c = av_{imp}^b$  (solid black lines) with a a dust size-dependent fitting parameter and b a dust size-independent fitting parameter.

and dust size [42, 43, 44]. Systematic hyper-velocity dust impact experiments have led to the formulation of empirical damage laws that are applicable in quite extended impact speed and dust size ranges [42, 43, 44, 45, 46, 47, 48]. Considering their validity for various target-projectile combinations, such general damage laws are of rather limited accuracy, especially in the high velocity impact range. In what follows, we shall utilize our extensive W-on-W experimental data in order to extract empirical damage laws that are valid within the disintegration regime of the high velocity range,  $1 \leq v_{\rm imp} [\rm km/s] \leq 3.5$ .

The experimental crater depth and crater diameter data are fitted in the standard power law form of  $\alpha (D_d)^\beta (v_{imp})^\gamma$ with  $\alpha, \beta, \gamma$  the fitting parameters. A three-step procedure is adopted. First, the crater characteristics for each of the three sub-populations are least square fitted to the expression  $a_i(v_{imp})^{\gamma_i}$ , with i = 1, 2, 3. Then, an optimal unique  $\gamma$ exponent is chosen and the crater characteristics for each of the three sub-populations are now least square fitted to the expression  $a_i(v_{imp})^\gamma$ , see figure 3. Finally, the  $\{a_i\}$ dataset is least square fitted to the expression  $\alpha (D_d)^\beta$ . Overall, this leads to the empirical damage laws

$$D_{\rm c} = 0.0257 (D_{\rm d})^{1.02} (v_{\rm imp})^{0.550}, \qquad (1)$$

$$H_{\rm c} = 0.0000107 (D_{\rm d})^{1.31} (v_{\rm imp})^{1.268}, \qquad (2)$$

where  $D_{\rm c}$ ,  $H_{\rm c}$ ,  $D_{\rm d}$  are measured in  $\mu \rm m$  and  $v_{\rm imp}$  in m/s. The mean absolute relative fitting error is 2.1% for the crater diameter and 7.1% for the crater depth.

An established general damage law for the crater depth, appropriate for metallic dust exceeding 50  $\mu$ m and impact speeds within  $2 \leq v [\text{km/sec}] \leq 12$ , reads as [42, 43, 44]

$$H_{\rm c} = 5.24 \frac{D_{\rm d}^{19/18}}{h_{\rm t}^{1/4}} \left(\frac{\rho_{\rm d}}{\rho_{\rm t}}\right)^{1/2} \left(\frac{v_{\rm imp}}{c_{\rm t}}\right)^{2/3},\qquad(3)$$

where  $H_{\rm c}$  is the crater depth in cm,  $D_{\rm d}$  the dust diameter



Figure 4: The crater depth in the *partial disintegration regime* of the high velocity range as a function of the W-on-W impact speed for two dust sizes. Comparison of the predictions of our specific damage law, Eq.(2), with the general damage law, Eq.(3).

in cm,  $h_t$  the target's Brinell hardness number,  $\rho_d$ ,  $\rho_t$  the mass densities of the dust and the target,  $c_t$  the target's sound speed and  $v_{imp}$  the dust impact speed. It is evident from the exponents that the general damage law exhibits a weaker dependence on both the dust size and the impact speed than the W-on-W damage law. More specifically, as discerned from figure 4, the general damage law significantly underestimates the crater depth for large dust sizes and high impact speeds. This confirms the importance of target-projectile specific damage laws as those of Eqs.(1,2).

Finally, empirical damage laws allow for an estimate of the excavated volume provided that an additional assumption is made for the geometry of the crater. As expected from symmetry considerations arising from the high dust sphericity, local target planarity and normal nature of the impact, the crater geometry can be well-approximated by a spherical cap. This has been consistently observed in the laboratory impact tests, see figure 5, and is consistent with the experimental hyper-velocity literature [49, 50]. Thus, the excavated volume can be approximated by

$$V_{\rm c} = \frac{1}{6} \pi H_{\rm c} \left( \frac{3}{4} D_{\rm c}^2 + H_{\rm c}^2 \right) \,. \tag{4}$$

Some characteristic examples are provided in figure 6. Note that the excavated material from a single impact crater is much larger than the excavated material from a single unipolar arc crater [51, 52], but much smaller than the material excavated during an edge-localized mode or major disruption driven melt event [53].

# 4.2. Critical velocities

Here, we shall discuss the transition between the high velocity regimes for normal W-on-W impacts, which dictates the applicability limits of our empirical damage laws.

The critical erosion velocity  $v_{\text{crit}}^{\text{ero}}$  is the transition velocity between the bonding and disintegration regimes of the high velocity range. An analytical expression has been derived for  $v_{\text{crit}}^{\text{ero}}$  that associates the transition with the impact kinetic energy that triggers melting [27]. A first-order energy balance analysis that contains a number of approximations leads to the expression [27]

$$v_{\rm crit}^{\rm ero} = \left(\frac{20e_{\rm th}I_{\rm melt}}{\rho_{\rm d}\sqrt{D_{\rm d}}}\right)^{2/5}$$

where  $e_{\rm th} = \sqrt{\rho_{\rm d} k_{\rm d} c_{\rm pd}}$  is the so-called thermal effusivity with  $k_{\rm d}$  the thermal conductivity and  $c_{\rm pd}$  the specific isobaric heat capacity, where  $I_{\rm melt} = T_{\rm m} - T_0 + \Delta h_{\rm f}/c_{\rm pd}$  is a melting index with  $T_{\rm m} = 3695$  K the melting point of W,  $T_0 = 300$  K the room temperature and  $\Delta h_{\rm f}$  the latent heat of fusion. This expression should be expected to underestimate the critical erosion velocity but has exhibited a good agreement with dedicated Sn, Bi, Zn, Ti experiments [27].

The critical bonding velocity  $v_{\text{crit}}^{\text{bond}}$  is the transition velocity between the deformation and bonding regimes of the high velocity range. A closed-form correlation is available for  $v_{\text{crit}}^{\text{bond}}$  that is based on numerical simulations within the assumption that impact bonding can be attributed solely to the onset of adiabatic shear instabilities [29]. Additional numerical modelling and experimental results allowed the consideration of size effects in the original expression [30]. The final expression reads as [29, 30]

$$v_{\text{crit}}^{\text{bond}} = \left[667 - 0.014\rho_{\text{d}} + 0.08(T_{\text{m}} - T_{0}) + 10^{-7}\sigma_{\text{y}}\right] (D_{\text{d}})^{-0.07}$$

where all quantities are in SI units and  $\sigma_y$  denotes the yield strength. It is worth pointing out that the adopted size exponent is a factor of two less than its traditional value [30] in accordance with state-of-the-art experiments [31].

In figure 7, the two W-on-W critical velocities are plotted as a function of the dust size. The room temperature recommendations of Ref.[54] have been followed for the W thermophysical properties. Velocity-size combinations that have been experimentally verified to lead to impacts that belong to the deformation and bonding regimes have also been included. It is evident that the aforementioned general expressions underestimate both critical velocities.



Figure 5: SEM images of high velocity W-on-W normal dust impacts that fall into the *partial disintegration regime* for different dust sizes and different impact speeds: (a)  $D_{\rm d} = 51 \,\mu {\rm m}, v_{\rm imp} = 1506 \,{\rm m/s},$  (b)  $D_{\rm d} = 63 \,\mu {\rm m}, v_{\rm imp} = 3190 \,{\rm m/s},$  (c)  $D_{\rm d} = 76 \,\mu {\rm m}, v_{\rm imp} = 2033 \,{\rm m/s}.$ 



Figure 6: The excavated volume predictions of the empirical damage laws for the crater diameter and the crater depth in the *partial disintegration regime* under the spherical cap assumption. Excavated volume as a function of the impact speed for various W dust sizes.



Figure 7: Critical erosion (purple line) and bonding velocities (blue line) versus the dust size for normal W-on-W impacts. Impacts within the deformation (green stars) and bonding regime (red circles).

#### 5. Summary and future work

The first experimental study of high velocity W dust - W wall impacts, relevant for cascade-like PFC damage triggered by runaway electron incidence, has been performed. Controlled normal high velocity impacts have been realized with a light gas dust gun. Surface analysis allowed the identification of three wall damage regimes (plastic deformation, bonding, partial disintegration) and the extraction of empirical damage laws for the most harmful disintegration regime. Future work will focus on the extension of the impact dataset to obtain more accurate damage laws, the determination of the critical velocities that demarcate the damage regimes and the consideration of oblique impacts.

#### Acknowledgments

The work has been performed within the framework of the EUROfusion Consortium, funded by the European Union via the Euratom Research and Training Programme (Grant Agreement No 101052200 - EUROfusion). Views and opinions expressed are however those of the authors only and do not necessarily reflect those of the European Union or European Commission. Neither the European Union nor the European Commission can be held responsible for them.

### References

- G. Federici, C. H. Skinner, J. N. Brooks, J. P. Coad *et al.*, *Nucl. Fusion* **41** (2001) 1967.
- [2] J. P. Sharpe, D. A. Petti and H.-W. Bartels, Fusion Eng. Des. 63-64 (2002) 153.
- [3] J. Roth, E. Tsitrone, A. Loarte, Th. Loarer et al. J. Nucl. Mater. 390-391 (2009) 1.
- [4] S. I. Krasheninnikov, R. D. Smirnov and D. L. Rudakov, Plasma Phys. Control. Fusion 53 (2011) 083001.
- [5] P. Tolias, S. Ratynskaia, M. De Angeli, G. De Temmerman et al., Plasma Phys. Control. Fusion 58 (2016) 025009.
- [6] J. T. Holgate, L. Simons, Y. Andrew and C. K. Stavrou, *Europhys. Lett.* **127** (2019) 45004.
- [7] M. De Angeli, E. Lazzaro, P. Tolias, S. Ratynskaia et al., Nucl. Fusion 59 (2019) 106033.
- [8] S. Ratynskaia, L. Vignitchouk and P. Tolias, Plasma Phys. Control. Fusion 64 (2022) 044004.
- [9] S. Ratynskaia, A. Bortolon and S. I. Krasheninnikov, *Rev. Mod. Plasma Phys.* (2022) accepted.

- [10] S. Ratynskaia, L. Vignitchouk, P. Tolias, I. Bykov et al., Nucl. Fusion 53 (2013) 123002.
- [11] A. Shalpegin, L. Vignitchouk, I. Erofeev, F. Brochard et al., Plasma Phys. Control. Fusion 57 (2015) 125017.
- [12] L. Vignitchouk, S. Ratynskaia, P. Tolias, R. A. Pitts et al., Nucl. Fusion 58 (2018) 076008.
- [13] M. De Angeli, P. Tolias, S. Ratynskaia, D. Ripamonti et al., Nucl. Fusion (2022) submitted; arXiv:2206.13573.
- [14] L. Vignitchouk, P. Tolias and S. Ratynskaia, Plasma Phys. Control. Fusion 56 (2014) 095005.
- [15] S. Ratynskaia, P. Tolias, A. Shalpegin, L. Vignitchouk et al., J. Nucl. Mater. 463 (2015) 877.
- [16] A. Shalpegin, F. Brochard, S. Ratynskaia, P. Tolias et al., Nucl. Fusion 55 (2015) 112001.
- [17] P. Tolias, S. Ratynskaia, A. Shalpegin, L. Vignitchouk et al., Nucl. Mater. Energy 12 (2017) 524.
- [18] C. Castaldo, S. Ratynskaia, V. Pericoli, U. de Angelis et al., Nucl. Fusion 47 (2007) L5
- [19] S. Ratynskaia, C. Castaldo, K. Rypdal, G. Morfill et al., Nucl. Fusion 48 (2008) 015006
- [20] S. Ratynskaia, C. Castaldo, E. Giovannozzi, D. Rudakov et al., Plasma Phys. Control. Fusion 50 (2008) 124046
- [21] S. V. Klinkov, V. F. Kosarev and M. Rein, Aerosp. Sci. Technol. 9 (2005) 582.
- [22] W. Stronge, *Impact Mechanics* (Cambridge University Press, Cambridge, 2000).
- [23] W. John, Aerosol Sci. Technol. 23 (1995) 2
- [24] R. M. Brach, P. F. Dunn and X. Li, J. Adhes. **74** (2000) 227
   [25] C. Thornton and Z. Ning, Powder Technol. **99** (1998) 154.
- [26] D. Gorham and A. Kharaz, Powder Technol. 112 (2000) 193.
- [27] M. Hassani-Gangaraj, D. Veysset, K. A. Nelson and C. A. Schuh, Nat. Commun. 9 (2018) 5077.
- [28] M. Hassani-Gangaraj, D. Veysset, K. A. Nelson and C. A. Schuh, *Phys. Rev. Lett.* **119** (2017) 175701.
- [29] H. Assadi, F. Gärtner, T. Stoltenhoff and H. Kreye, Acta Mater. 51 (2003) 4379.
- [30] T. Schmidt, F. Gärtner, H. Assadi and H. Kreye, Acta Mater. 54 (2006) 729.
- [31] M. Hassani-Gangaraj, D. Veysset, K. A. Nelson and C. A. Schuh, Scr. Mater. 145 (2018) 9.
- [32] M. Hassani-Gangaraj, D. Veysset, K. A. Nelson and C. A. Schuh, Appl. Surf. Sci. 476 (2019) 528.
- [33] Y. Sun, D. Veysset, K. A. Nelson and C. A. Schuh, Appl. Phys. Lett. 117 (2020) 134105.
- [34] M. J. Burchell, M. J. Cole, J. A. M. McDonnell and J. C. Zarnecki, Meas. Sci. Technol. 10 (1999) 41.
- [35] N. Lee, S. Close, D. Lauben, I. Linscott et al. Int. J. Impact Eng. 44 (2012) 40.
- [36] G. Eichhorn, Planet. Space Sci. 24 (1976) 771.
- [37] D. Heunoske, M. Schimmerohn, J. Osterholz and F. Schäfer, Procedia Eng. 58 (2013) 624.
- [38] G. Eichhorn, Planet. Space Sci. 26 (1978) 469.
- [39] G. Riva and A. Reggiori, Fusion Technol. 15 (1989) 143.
- [40] D. Veysset, J.-H. Lee, M. Hassani, S. Kooi, E. Thomas and K. Nelson, Appl. Phys. Rev. 8 (2021) 011319.
- [41] F. K. Schäfer, T. Geyer, E. E. Schneider, M. Rott and E. Igenbergs, Int. J. Impact Eng. 26 (2001) 683.
- [42] N. Pailer and E. Grün, Planet. Space Sci. 28 (1980) 321.
- [43] B. G. Cour-Palais, Int. J. Impact Eng. 5 (1987) 221.
- [44] L. Berthoud and J. C. Mandeville, Proceedings of the First European Conference on Space Debris (1993) 459.
- [45] M. Lambert, Adv. Space Res. **19** (1997) 369.
- [46] K. R. Housen and K. A. Holsapple, *Icarus* **211** (2011) 856.
- [47] F. Hörz, Meteorit. Planet. Sci. 47, (2012) 763.
  - [48] A. J. Gemer, Z. Sternovsky, D. James and M. Horanyi, *Planet. Space Sci.* 183 (2020) 104628.
  - [49] D. E. Gault, The Moon 6 (1973) 32.
  - [50] J. R. Baker, Int. J. Impact Eng. 17 (1995) 25.
  - [51] H. T. C. Kaufmann, C. Silva and M. S. Benilov, Plasma Phys. Control. Fusion 61 (2019) 095001.
  - [52] V. Rohde, M. Balden, R. Neu and the ASDEX Upgrade Team,

- Nucl. Mater. Energy 29 (2021) 101083.
  [53] S. Ratynskaia, E. Thorén, P. Tolias, R. A. Pitts et al., Nucl. Fusion 60 (2020) 104001.
  [54] P. Tolias, Nucl. Mater. Energy 13 (2017) 42.