

# Nonphononic spectrum of two-dimensional structural glasses

Edan Lerner<sup>1\*</sup> and Eran Bouchbinder<sup>2†</sup>

<sup>1</sup>*Institute of Theoretical Physics, University of Amsterdam,  
Science Park 904, 1098 XH Amsterdam, the Netherlands*

<sup>2</sup>*Chemical and Biological Physics Department, Weizmann Institute of Science, Rehovot 7610001, Israel*

Extensive numerical work from recent years has established that the low-frequency nonphononic vibrational spectrum of structural glasses follows a  $\sim \omega^4$  scaling with angular frequency  $\omega$  [1]. This universal quartic ( $\sim \omega^4$ ) law featured by the nonphononic spectrum has been shown to be independent of details of the interparticle interaction potential [2], glass formation protocol [3], and spatial dimensions  $d \geq 2$  [4, 5]. Furthermore, indirect evidence for the quartic scaling of the nonphononic spectrum of two-dimensional structural glasses has been presented in [1, 6–8]. In [4, 7], it has been shown that in two-dimensional structural glasses, the prefactor  $\omega_g^{-5}$  of the quartic  $\sim \omega^4$  law is  $N$ -dependent, scaling as  $\omega_g^{-5} \sim (\sqrt{\log N})^5$ , where  $N$  denotes the number of particles in a glass.

At the same time, deviations from the quartic scaling of the nonphononic spectrum have been reported for three-dimensional (3D) structural glasses in [9, 10], depending on the system size and formation protocol of the glasses studied. These previous works associated these deviations with a glassy length  $\xi_g$  — on the order of a few interparticle distances —, and established the nonphononic spectrum of glasses whose linear size sufficiently exceeds  $\xi_g$  features the universal quartic law  $\sim \omega^4$  [1, 4]. The length  $\xi_g$  has been shown to be glass-formation-protocol dependent [3] — decreasing for lower-energy, more stable glasses — fully consistent with previously observed deviations [9, 10] in the exponent  $\beta$  of the nonphononic spectrum  $\sim \omega^\beta$  from the apparently universal value  $\beta=4$  [1].

Recently, in [11, 12] it was argued that the nonphononic spectrum of *two-dimensional* (2D) structural glasses rather follows  $\sim \omega^\beta$  with  $\beta < 4$ , presumably casting doubt on the validity of previous observations and claims [1, 4, 6, 7]. Here, we study the nonphononic spectrum of two-dimensional structural glasses, and show that (i) the exponent  $\beta$  is glass-formation-protocol *and* system-size dependent, as seen previously for structural glasses in three dimensions [9, 10], and (ii) the scaling  $\omega_g \sim 1/\sqrt{\log N}$  put forward in [4, 7] is consistent with numerical observations presented below.

We simulate a generic glass-forming model in 2D — also studied in [11, 12] — in which point-like particles interact via an inverse-power-law potential that is smoothed at a cutoff distance up to two derivatives,

see e.g. [7] for the model’s details. We prepare ensembles of glasses by (i) instantaneously quenching high-temperature liquid states to zero temperature (as done in [11, 12]), and (ii) by annealing liquids for  $10^4$  simulational time units (described, e.g., in [7]) at temperature  $T = 0.5$ , which is approximately the (computer) glass transition temperature of our studied glass-forming model. Each of these annealing runs are followed by an instantaneous quench to zero temperature, to form a glass (termed “well-annealed” in Fig. 1). The ensemble sizes can be found in [13].

In Fig. 1, we present our results; panels (a) and (c) show the raw vibrational spectra  $\mathcal{D}(\omega; N)$  of our pair of glass ensembles, respectively, as indicated in the figure legends. A clear system-size dependence is apparent in both ensembles. We further find that the exponent featured by the low-frequency power-law regime of  $\mathcal{D}(\omega; N)$  drops below 4 for smaller, quickly quenched glasses, cf. Fig. 1c, consistent with observations in 3D [9, 10]. That is, we find that  $\beta(N) < 4$  increases with the system size  $N$ , from  $\beta \simeq 3.2$  for  $N = 36$  to  $\beta \simeq 3.6$  for  $N = 1600$ . In panels (b) and (d), we show that rescaling both axes according to the  $N$  dependence of the nonphononic-excitations’ characteristic scale  $\sim 1/\sqrt{\log N}$  as put forward in [4, 7] leads to a convincing data collapse, confirming that the nonphononic VDoS of 2D glasses is indeed  $N$  dependent. In Fig. 2, we present the cumulative distributions  $\mathcal{C}(\omega) \equiv \int_{0^+}^{\omega} \mathcal{D}(\omega') d\omega'$  showing again that  $\beta$  features both glass-formation protocol and system-size dependencies. We note that the  $N$  dependence of the exponent  $\beta(N)$  also appears to be consistent with the results presented in the Supplemental Material file of [11, 12] (which can be found at [14]). For example, in Fig. 2b therein the cumulative density of states normalized by  $\omega^{4.5}$  is presented for various system sizes  $N$ , for a computer glass model closely related to the one used in this note. For  $N = 3600$ , the data feature a low-frequency plateau, which corresponds to  $\beta = 4.5 - 1 = 3.5$ . For  $N \leq 786$ , however, the data curve up with decreasing  $\omega$ , indicating an exponent  $\beta$  of value smaller than 3.5, consistently with the  $N$  dependence of  $\beta(N)$  we found.

Our data demonstrate the difficulty to accurately determine the value of the exponent  $\beta$  appearing in the low-frequency  $\sim \omega^\beta$  scaling of the nonphononic spectrum of two-dimensional structural glasses. The proper determination of  $\beta$  in the thermodynamic limit requires careful finite-size tests (see, e.g. [10] for three-dimensional glasses), which are particularly hard to conduct in two-dimensions due to the abundance of low-frequency

\* e.lerner@uva.nl

† eran.bouchbinder@weizmann.ac.il




FIG. 1. (a) The VDoS  $\mathcal{D}(\omega; N)$  of well-annealed computer glasses (see text for details) vs.  $\omega/\omega_0$ , for various system sizes  $N$  (see legend), where  $\omega_0 \equiv c_s/a_0$  with  $c_s$  being the shear wave speed and  $a_0$  an interparticle distance. Note that the 4:1 and 3.6:1 scaling triangles correspond to the lines going through the  $N=1600$  and  $N=36$  data, respectively, demonstrating a systematic variation of the exponent  $\beta$  with  $N$ . (b) The same data as in panel (a), but here plotting  $(\omega_0/\sqrt{\log N})\mathcal{D}(\omega; N)$  vs.  $\omega/(\omega_0/\sqrt{\log N})$ . (c) The same as panel (a), but for glasses formed by an infinitely fast quench,  $\dot{T} \rightarrow \infty$ . Note that the 3.6:1 and 3.2:1 scaling triangles correspond to the lines going through the  $N=1600$  and  $N=36$  data, respectively, demonstrating again a systematic variation of the exponent  $\beta$  with  $N$ . (d) The same as panel (b), but for the data shown in panel (c).

phononic modes that obscure the nonphononic spectrum (see elaborate discussion on this issue in [15]). In this context, we note that in [1] systems of  $N=25600$  particles were employed — together with a nonlinear-excitation analyses [1]—, in order to show (via simulations and extreme-value-statistics arguments) that  $\beta=4$  in two-dimensional glasses, even if the latter were formed by

an instantaneous quench from high-temperature liquid states. Our results, taken together with the data presented in [1, 4, 6, 7], support that  $\beta=4$  is the universal value characterizing the nonphononic spectrum of structural glasses in the thermodynamic limit, including in two-dimensions.

- 
- [1] E. Lerner and E. Bouchbinder, Low-energy quasilocalized excitations in structural glasses, *J. Chem. Phys.* **155**, 200901 (2021).
- [2] D. Richard, K. González-López, G. Kapteijns, R. Pater, T. Vaknin, E. Bouchbinder, and E. Lerner, Universality of the nonphononic vibrational spectrum across different classes of computer glasses, *Phys. Rev. Lett.* **125**, 085502 (2020).
- [3] C. Rainone, E. Bouchbinder, and E. Lerner, Pinching a glass reveals key properties of its soft spots, *Proc. Natl. Acad. Sci. U.S.A.* **117**, 5228 (2020).
- [4] G. Kapteijns, E. Bouchbinder, and E. Lerner, Universal nonphononic density of states in 2d, 3d, and 4d glasses, *Phys. Rev. Lett.* **121**, 055501 (2018).
- [5] M. Shimada, H. Mizuno, L. Berthier, and A. Ikeda, Low-frequency vibrations of jammed packings in large spatial dimensions, *Phys. Rev. E* **101**, 052906 (2020).
- [6] J. Zylberg, E. Lerner, Y. Bar-Sinai, and E. Bouchbinder, Local thermal energy as a structural indicator in glasses, *Proc. Natl. Acad. Sci. U.S.A.* **114**, 7289 (2017).




FIG. 2. (a) The cumulative distributions  $C(\omega/\omega_0) \equiv \int_{0+}^{\omega/\omega_0} \mathcal{D}(\omega'/\omega_0) d(\omega'/\omega_0)$  of well-annealed computer glasses plotted vs.  $\omega/\omega_0$ , for various system sizes as indicated by the legend. (b) The same data as in panel (a), but here plotting  $(\omega/\omega_0)^{-4.6} C(\omega/\omega_0)$  vs.  $\omega/(\omega_0/\sqrt{\log N})$ . (c) The same as panel (a), but for glasses formed by an infinitely fast quench,  $\dot{T} \rightarrow \infty$  (d) Here we plot  $(\omega/\omega_0)^{-4.2} C(\omega/\omega_0)$  vs.  $\omega/(\omega_0/\sqrt{\log N})$  for the data shown in panel (c). A clear  $N$ -dependence of the exponent  $\beta$  is seen in this representation.

- [7] E. Lerner and E. Bouchbinder, A characteristic energy scale in glasses, *J. Chem. Phys.* **148**, 214502 (2018).
- [8] G. Kapteijns, D. Richard, E. Bouchbinder, and E. Lerner, Elastic moduli fluctuations predict wave attenuation rates in glasses, *J. Chem. Phys.* **154**, 081101 (2021).
- [9] E. Lerner and E. Bouchbinder, Effect of instantaneous and continuous quenches on the density of vibrational modes in model glasses, *Phys. Rev. E* **96**, 020104 (2017).
- [10] E. Lerner, Finite-size effects in the nonphononic density of states in computer glasses, *Phys. Rev. E* **101**, 032120 (2020).
- [11] L. Wang, G. Szamel, and E. Flenner, Low-frequency excess vibrational modes in two-dimensional glasses, *Phys. Rev. Lett.* **127**, 248001 (2021).
- [12] L. Wang, G. Szamel, and E. Flenner, Erratum: Low-frequency excess vibrational modes in two-dimensional glasses [physical review letters 127, 248001 (2021)], *Phys. Rev. Lett.* **129**, 019901 (2022).
- [13] We created about 3.8M, 2.1M, 427K, and 94K independent, well-annealed glassy samples, and about 14M, 12M, 6.8M and 2.8M independent, instantaneously quenched glassy samples of sizes  $N = 36, 64, 196$ , and  $1600$ , respectively.
- [14] The Supplemental Material file of [11, 12] can be downloaded [here](#).
- [15] E. Bouchbinder and E. Lerner, Universal disorder-induced broadening of phonon bands: from disordered lattices to glasses, *New J. Phys.* **20**, 073022 (2018).