Magnetocrystalline Anisotropy and Magnetocaloric Effect Studies on the Room-temperature 2D Ferromagnetic Cr₄Te₅

Shubham Purwar,¹ Susmita Changdar,¹ Susanta Ghosh,¹ and S. Thirupathaiah^{1,*}

¹Department of Condensed Matter and Materials Physics,

S. N. Bose National Centre for Basic Sciences, Kolkata, West Bengal, India, 700106.

(Dated: April 5, 2024)

We present a thorough study on the magnetoanisotropic properties and magnetocaloric effect in the layered ferromagnetic Cr_4Te_5 single crystals by performing the critical behaviour analysis of magnetization isotherms. The critical exponents β =0.485(3), γ =1.202(5), and δ =3.52(3) with a Curie temperature of $T_C \approx 340.73(4)$ K are determined by the modified Arrott plots. We observe a large magnetocrystalline anisotropy K_u =330 kJ/m³ at 3 K which gradually decreases with increasing temperature. Maximum entropy change $-\Delta S_{max}^{max}$ and the relative cooling power (RCP) are found to be 2.77 J/kg-K and 88.29 J/kg, respectively near T_C when the magnetic field applied parallel to *ab*-plane. Rescaled $-\Delta S_M(T,H)$ data measured at various temperatures and fields collapse into a single universal curve, confirming the second order magnetic transition in this system. Following the renormalization group theory analysis, we find that the spin-coupling is of 3D Heisenberg-type, $\{d:n\} = \{3:3\}$, with long-range exchange interactions decaying as $J(r) = r^{-(d+\sigma)} = r^{-4.71}$.

I. INTRODUCTION

Investigation of the low dimensional magnetic materials with ferromagnetic ordering at room temperature has gained a lot of research interests in recent days due to their potential applications in the magnetic refrigeration and spintronic devices [1-4] for which the materials with strong magentocrystalline anisotropy are crucial [5, 6]. In this regard, the van der Waals (vdW) magnets are of great interest from the fundamental science and advanced technological point of view due to their peculiar 2-dimensional (2D) magnetic properties [7–10] and strong magnetocrystalline anisotropy [11]. Usually, the Heisenberg-type ferromagnet does not exist with intrinsic long-range magnetic ordering at finite temperature in the 2D limit due to dominant thermal fluctuations [12]. But the single domain anisotropy or the exchange anisotropy can remove these limitations and allow the long-range magnetic ordering to obtain a 2D Ising-like ferromagnet [13]. In this way, 2D ferromagnetism has been found experimentally in many vdW materials such as $Cr_2Ge_2Te_6$ ($T_C \approx 61$ K) [14], $Cr_2Si_2Te_6$ ($T_C \approx 32$ K) [15], Fe₃GeTe₂ (T_C \approx 215 K) [9], and CrI₃ (T_C \approx 45 K) [13], but the long-range FM ordering far below the room temperature limiting their usage in technology. However, a very few systems such as MnP ($T_{\rm C} \approx 303$ K) show room temperature 2D ferromagnetism in the bulk phase [16]. Thus, searching for new 2D room-temperature FM materials with large magnetocrystalline anisotropy is crucial for the realization of potential technological applications [1, 2]. Further, magnetocaloric effect (MCE) in room-temperature FM vdW materials with maximum entropy change $-\Delta S_M^{max}$ is of recent research interests due to their potential applications in the environmental friendly magnetic refrigeration [17]. There exists quite a few 2D FM systems showing significant - $\Delta S_{\rm M}^{max}$ such as $Fe_{3-x}GeTe_2~(1.1~J/kg-K~at~5~T)$ [18], Cr_5Te_8 (1.6 J/kg-K at 5 T) [19], $Cr_2Si_2Te_6$ (5.05 J/kg-K at 5 T),



FIG. 1. (a) X-ray diffraction pattern of Cr_4Te_5 single crystals. Inset in (a) shows photographic image of single crystals. (b). Schematic diagram of Cr_4Te_5 crystal structure. (c) Energy dispersive X-ray spectroscopy and scanning electron microscopy image (inset) of Cr_4Te_5 single crystal showing the chemical composition and crystal morphology, respectively.

and $Cr_2Ge_2Te_6$ (2.64 J/kg-K at 5 T) [20].

A Recent theoretical study suggested that the layered Cr_xTe_y systems are potential candidates to realize the muchanticipated room-temperature 2D ferromagnetism in the bulk [21]. Since then, variety of Cr_xTe_y compounds have been grown experimentally and studied for their peculiar 2D ferromagnetism, including, CrTe [22], Cr₂Te₃ [23],

^{*} setti@bose.res.in

Cr₃Te₄ [24], Cr₄Te₅ [25], and Cr₅Te₈ [26]. Out of these, Cr₄Te₅ has been reported to show highest $T_C \approx 318$ K among this family of compounds, to date in the bulk form. Generally, Cr_xTe_y compounds possess alternating stacks of CrTe₂ layers intercalated by the Cr layers (excess) along the c-axis [27]. Importantly, it is that the intercalated Cr concentration plays a crucial role in the crystal structure formation, magnetic structure, and transport properties of these compounds[28– 31].

In this contribution, we present magnetic properties, critical behaviour analysis, and anisotropic magnetocaloric effect associated with room temperature ferromagnetism in Cr_4Te_5 single crystals. Magnetization M(T) data suggest ferromagnetic ordering at a $T_{\rm C}$ of \approx 338 K with strong magnetic anisotropy below T_C between the field applied parallel to *ab*-plane and parallel to c-axis. As a result, we find a large temperature dependent magnetocrystalline anisotropy (K_{u} =330 kJ/m³) at 3 K with *ab*-plane as the easy magnetization plane. Further, the universal scaling of magnetocaloric effect suggests a second order magnetic phase transition in this system. The critical exponents derived from the magnetocaloric effect are in good agreement with the values obtained from the critical analysis. The renormalization group theory analysis suggests 3D Heisenberg-type magnetic interactions in this system.

II. EXPERIMENTAL DETAILS

High quality single crystals of Cr_4Te_5 were grown by the chemical vapor transport (CVT) technique with iodine as a transport agent. Stoichiometric mixtures of Cr (99.99%, Alfa Aesar) and Te (99.99%, Alfa Aesar) powders were mixed in a molar ratio of 5:5, added with iodine (3 mg/cc), and sealed into an evacuated quartz tube under Ar atmosphere. The tube was placed in a gradient-temperature horizontal two-zone tube furnace for about 15 days with one end, containing powder mixture (source), maintained at 1000° C and the other end kept at 820° C (sink), as per the procedure described earlier [32]. The as-grown single crystals were large in size $(5 \times 5 \text{ mm}^2)$ and were looking shiny. Photographic image of a typical single crystal is shown in the inset of Fig. 1(a). X-ray diffraction (XRD) was performed on the single crystals using Rigaku X-ray diffractometer (SmartLab, 9kW) with Cu K_{α} radiation of wavelength 1.54059 Å. Surface morphology and elemental analysis of the single crystals were done using the scanning electron microscopy (SEM) and energy dispersive X-ray spectroscopy (EDXS), respectively. The EDXS measurements suggest an actual chemical composition of Cr_{3.98}Te₅. Hereafter, for convenience, we use nominal composition formula of Cr₄Te₅ wherever required. Magnetic measurements [M(T)] and M(H) were carried out using physical property measurement system (9 Tesla-PPMS, DynaCool, Quantum Design).



FIG. 2. Temperature dependent magnetization M(T) data measured in the zero-field-cooled and field-cooled modes with the magnetic fields (H = 200 and 4000 Oe) applied in the *ab*-plane (a) and along the c-axis (b). Field dependent magnetization M(H) data measured for H || ab (c) and H || c (d) at various sample temperatures.

III. RESULTS AND DISCUSSION

Figure 1(a) shows X-ray diffraction (XRD) pattern of Cr_4Te_5 single crystal. In the XRD pattern, we find intensity peaks of (001) Bragg plane, indicating the crystal growth plane along the c-axis. We further notice that the (001) Bragg peak position is shifted to lower 2θ values compared to the other Cr_xTe_y compounds [33, 34] as excess Cr atoms are intercalated between two CrTe₂ layers, leading to increase in the lattice parameters [35]. Thus, the intercalated Cr atoms (Cr-vacancies) sandwiched between two CrTe₂ layers create van der Waals gap as schematically shown in Fig. 1(b).

A. Magnetization Measurements

To explore the magnetic properties of Cr_4Te_5 , magnetization as a function of temperature M(T) and field M(H) were measured with the field applied parallel to *ab*-plane (H || ab) and c-axis (H || c). Figs. 2(a) and 2(b) show M(T) of Cr_4Te_5 measured with magnetic fields of 200 and 4000 Oe for both H || ab and H || c orientations, respectively. Paramagnetic (PM) to ferromagnetic (FM) transition is clearly visible at a Curie temperature of $T_C \approx$ 338 K when measured with 200 Oe for both the orientations in zero-field-cooled (ZFC) and field-cooled (FC) modes.



FIG. 3. Magnetization isotherms measured around T_C for (a) H \parallel ab and (b) H \parallel c. (c) Temperature dependent magnetocrystalline anisotropy (K_u). Bottom inset in (c) shows the saturation magnetization M_s and top inset in (c) shows saturation magnetic field H_s estimated below T_C . (d) Ratios of $[M_s/M_s(310 \text{ K})]^{n(n+1)/2}$ with n =1, 2, and 4 (right-axis) overlapped with magnetocrystalline anisotropy (left-axis).

The Curie temperature 338 K found in this study is higher than any known composition in the Cr_xTe_y family in their bulk phase [25, 36]. Splitting in the M(T) curves between ZFC and FC data at T_C is attributed to the competition between FM and AFM phases at low temperatures [37, 38]. Interestingly, as shown in the inset of the Fig. 2(b), below T_C , the magnetization M(T) increases with decreasing temperature for H || ab, while it decreases with decreasing temperature for H || c. This observation clearly hints at a significant magnetic anisotropy in this system which is temperature dependent [26].

Next, Figs. 2(c) and 2(d) show the magnetization isotherms M(H) measured for H || ab and H || c at various temperatures, respectively. In contrast to the other Cr_xTe_y systems where the easy-axis is along c-axis [37, 39, 40], Cr_4Te_5 has the easy-axis on the *ab*-plane as the magnetization saturation occurs at an applied field of 0.5 T for H || ab, while 1.9 T is required to attain the magnetization saturation for H || c at 3 K. This observation is in agreement with a previous study on Cr_4Te_5 [25]. On the other hand, as can be seen from Figs. 2(c) and 2(d), the saturation magnetization (M_s) gradually decreases with increasing temperature and at \approx 338 K the long-range magnetic order is suppressed in both orientations. Inset in Fig. 2(d) demonstrates the magnetization sat 3 K.

B. Magnetocrystalline Anisotropy

We studied the magnetocrystalline anisotropy (K_{u}) using the Stoner-Wolfarth model [41] with the help of magnetization isotherms shown in the Figs. 3(a) and 3(b) for both H || ab and H || c, respectively, measured around $T_{\rm C}$. The magnetocrystalline anisotropy is calculated by using the formula $2K_u/M_s = \mu_0 H_s$, where μ_0 is the vacuum permeability, M_s is the saturation magnetization, and H_s is the field at which saturation magnetization occur [42]. Both H_s and M_s are considered experimentally from the isotherms shown in Figs. 3(a) and 3(b) to obtain K_u . Fig. 3(c) depicts the temperature dependent K_u estimated from the experimental data. We find $K_u = 78.11 \text{ kJ/m}^3$ at T = 310 K which gradually decreases with increasing temperature and reaches to 23.73 kJ/m³ at $T_{\rm C}$ (338 K). On the other hand, we estimate $K_{\rm u}$ \approx 330 kJ/m³ at 3 K that is much larger than the K_u values of other 2D magnetic systems such as $CrBr_3$ ($\approx 86 \text{ kJ/m}^3$ at 5 K) [43], $Cr_2Ge_2Te_6 \approx 20 \text{ kJ/m}^3$ at 2 K) [20], and $Cr_2Si_2Te_6~(\approx 65~kJ/m^3$ at 2 K) [20] and comparable to the $K_{\rm u}$ values of CrI_3 (300 kJ/m^3 at 5 K) [43] and Fe_4GeTe_2 (250 kJ/m³ at 80 K) [20]. Though Fe₃GeTe₂ shows extremely large magnetocrystalline anisotropy of 1460 kJ/m³ at 2 K [44], it's Curie temperature is much below the room temperature $(T_{C}=220 \text{ K})$ [45]. Thus, our studied sample of Cr₄Te₅ having large K_u value of $\approx 330 \text{ kJ/m}^3$ above room temperature looks promising candidate from the technological point of view.

Since the magnetic anisotropy expectation value $\langle K^n \rangle$ is directly proportional to $M_s^{n(n+1)/2}$, as per the classical theory of magnetism [46, 47], we plotted $[M_s(T)/M_s(310)]^{n(n+1)/2}$ for n=1, 2, and 4. Here, n=1 represents intrinsic anisotropy, n=2 represents uniaxial anisotropy, and n=4 represents cubic anisotropy, giving rise the exponents 1, 3, and 10, respectively. Thus, in Fig. 3(d), we plotted $[M_s(T)/M_s(310)]$, $[M_s(T)/M_s(310)]^3$, and $[M_s(T)/M_s(310)]^{10}$ ratios as a function of temperature. Most importantly, in Fig. 3(d), the overlapped $K_{\mu}(T)$ of Fig. 3(c) matches very well with $[M_s(T)/M_s(310)]^3$ ratio, confirming the dominant uniaxial anisotropy in this system that is strongly temperature dependent. The temperature dependent K_u is found to be originated from the fluctuating local spin clusters those are activated from the thermal energy [46, 47]. A recent study on Cr₅Te₈ shows temperature dependent uniaxial anisotropy but mixed with a small component of cubic anisotropy as well [19]. Nevertheless, our observations suggest that Cr_4Te_5 is a stronger magnetocrystalline anisotropic system compared to it's sister compound Cr₅Te₈.

C. Critical Behaviour Analysis

Scaling hypothesis suggests that the second order phase transition in a magnetic system around $T_{\rm C}$ can be described by a set of critical exponents and magnetic equations of the state [48]. Thus, the spontaneous magnetization $M_{\rm sp}$ below $T_{\rm C}$, inverse susceptibility χ_0^{-1} above $T_{\rm C}$, and magnetization isotherms $M({\rm H})$ at $T_{\rm C}$ are characterized by the critical exponents β , γ , and δ , respectively. Mathematical equations



FIG. 4. (a) Arrott plot ($M^2 vs H/M$). Modified Arrott plot from (b) 3D XY model, (c) 3D Ising model, (d) 2D Ising model, (e) 3D Heisenberg model, and (f) Tricritical meanfield model.

governing the critical exponents are given by,

$$M_{\rm sp}(T) = M_0 (-\varepsilon)^\beta \text{ for } \varepsilon < 0, T < T_c,$$
(1)

$$\boldsymbol{\chi}_0^{-1}(\mathrm{T}) = (\mathrm{h}_0/\mathrm{m}_0)\boldsymbol{\varepsilon}^{\boldsymbol{\gamma}}, \text{ for } \boldsymbol{\varepsilon} > 0, \mathrm{T} > \mathrm{T_c}$$
 (2)

$$M = DH^{1/\delta}$$
, for $\varepsilon = 0, T = T_c$, (3)

where $\varepsilon = (T - T_C)/T_C$ is the reduced temperature, M₀, h_0/m_0 , and D are the critical amplitudes[49]. In order to obtain the critical exponents β , γ , and δ as well as the exact value of $T_{\rm C}$, we first did the Arrott-plot M^2 vs. H/M as shown in Fig. 4(a). However, this method does not produce the required parallel linear curves at higher fields, particularly below T_C [50]. Therefore, we used the modified Arrott-plot (MAP) technique and plotted $M^{1/\beta}$ vs. $(H/M)^{1/\gamma}$ for various models around T_C. Fig .4(b) shows MAP for 3D XY model ($\beta = 0.345, \gamma = 1.316$) [51], Fig. 4(c) shows MAP for 3D Ising model ($\beta = 0.325, \gamma = 1.241$) [52], Fig. 4(d) shows MAP for 2D Ising model ($\beta = 0.125, \gamma =$ 1.75) [53], Fig. 4(e) shows MAP for 3D Heisenberg model $(\beta = 0.365, \gamma = 1.386)$ [52], and Fig. 4(f) shows MAP for Tricritical meanfield model ($\beta = 0.25, \gamma = 1$) [54]. As can be seen from Figs. 4(b)-4(f), none of these models can actually produce the required parallel linear curves at higher magnetic fields from their respective critical exponents, confirming that a single theoretical model cannot properly describe the magnetic interactions present in Cr_4Te_5 . Thus, we used the modified Arrott-plot technique in an iterative method in the vicinity of T_C to produce parallel linear curves as shown in Fig. 5(a) [55, 56]. This procedure gives $\chi_0^{-1}(T)$ and $M_{sp}(T)$ as the intercepts on the x-axis and y-axis, respectively. Fig. 5(b) depicts M_{sp} and χ_0^{-1} plotted as a function of temperature derived from Fig. 5(a). From Eqs. 1 and 2 we estimate the critical exponents $\beta = 0.485(3)$ with $T_C = 340.73(4)$ K and $\gamma = 1.202(5)$ with $T_C = 340.85(4)$ K. The estimated T_C values are very close to the value of 338 K obtained from the M(T) data [see Figs. 2(a-b)]. Further, the critical exponents can be found more accurately using the Kouvel-Fisher (KF) plots [57], governed by the below equations.

$$M_{sp}(T)[dM_{sp}(T)/dT]^{-1} = (T - T_c)/\beta,$$
 (4)

$$\chi_0^{-1}(T)[d\chi_0^{-1}(T)/dT]^{-1} = (T - T_c)/\gamma,$$
 (5)

Fig. 5(c) depicts the Kouvel-Fisher plots fitted with the Eqs. 4 and 5 below and above $T_{\rm C}$. From the KF method fitting we derive the critical exponents $\beta = 0.479(6)$ with $T_{\rm C} = 340.55(2)$ K and $\gamma = 1.196(6)$ with $T_{\rm C} = 340.85(3)$ K. The values of β and γ obtained from the KF method are in good agreement with the values obtained from the MAP method. In addition, the exponent δ has been calculated using the Widom scaling relation, $\delta = 1 + (\gamma/\beta)$ [58]. Thus, $\delta = 3.478$ and δ



FIG. 5. (a) Modified Arrott plot of $M^{1/\beta}$ vs $(H/M)^{1/\gamma}$ at high field values. (b) Temperature dependent spontaneous magnetization $M_{\rm sp}(T)$ (left-axis) and inverse initial susceptibility $\chi_0^{-1}(T)$ (right-axis). (c) Kouvel-Fisher plot of temperature dependent $M_{\rm sp}(T)[dM_{\rm sp}(T)/dT]^{-1}$ (left-axis) and $\chi_0^{-1}(T)[d\chi_0^{-1}(T)/dT]^{-1}$ (right-axis). (d) Isothermal magnetization M(H) at $T_C\approx 340.5~K.$ Inset in (d) shows M(H) plot in the log-log scale.

= 3.497 are calculated from MAP and KF plots, respectively. Importantly, the δ values obtained from both MAP and KF methods are close to the value δ = 3.52(3) obtained using the critical isotherm (CI) following the Eq. 3 as shown in Fig. 5(d). All the experimentally derived critical exponents are summarized in the Table II. Note here that, although the critical exponents obtained from MAP and KF techniques are close, we used the critical exponents of MAP for further discussions. Therefore, the critical exponent β =0.485(3) obtained from this study is close to the meanfield-model value of β =0.5 and γ =1.202(5) is close to the 3D Heisenberg-model value of γ =1.386.

Further, to verify the accuracy of critical exponents and critical temperature obtained from MAP and KF methods, we employed scaling analysis [48]. The scaling equations of the state for magnetic systems are given by,

$$M(H,\varepsilon) = \varepsilon^{\rho} f_{\pm}(H/\varepsilon^{\rho+\gamma})$$
(6)

Above equation can be write as well,

$$\mathbf{m} = \mathbf{f}_{\pm}(\mathbf{h}) \tag{7}$$

where $m = \varepsilon^{-\beta} M(H, \varepsilon)$ is the normalized magnetization and $h = H\varepsilon^{-(\beta+\gamma)}$ is the normalized field. For the correct β and γ values obtained from the MAP and KF methods, following the scaling hypothesis, the scaled magnetization m and field h should fall on two different branches of the universal curves when plotted using the Eq. 6 and Eq. 7. One branch for T<T_C and another branch for T>T_C, as shown in Figs. 6(a) and 6(b). Since all the curves shown in Figs. 6(a) and 6(b) overlap with respective universal curves, the scaling hypothesis reaffirms the reliability of the derived critical exponents using the MAP and KF methods.

TABLE I. Obtained critical parameters following the renormalization group theory analysis

${d:n}$	γ	β	σ	δ	
{2:1}	1.20	0.38	1.22	4.158	
{2:2}	1.20	0.41	1.19	3.927	
{2:3}	1.20	0.55	1.05	3.182	
{3:2}	1.20	0.405	1.79	3.963	
{3:3}	1.20	0.46	1.71	3.609	

Next, the renormalization group (RG) theory analysis suggest that the long- and short- range exchange interactions decay with the distance r as $J(r) = r^{-(d+\sigma)}$ and $J(r) = e^{-r/b}$, respectively [53]. Here, d is the spatial dimensionality, σ is a positive constant, and b is spatial scaling factor. The relation between the critical exponent γ and σ is given by,

$$\gamma = 1 + \frac{4}{d} \frac{(n+2)}{(n+8)} \Delta \sigma + \frac{8(n-4)(n+2)}{(n+8)^2 d^2} \\ * [\frac{2(7n+20)G(d/2)}{(n+8)(n-4)} + 1] \Delta \sigma^2$$
(8)

where $\Delta \sigma = \sigma - d/2$, $G(d/2) = 3 - 0.25 * (d/2)^2$. n and d are the spin and spatial dimensionality of the system. By considering the experimental γ value of 1.196(6), following the RG theory, we have calculated the critical exponent β and local exponent σ for various sets of {d : n} values and are tabulated in Table I. From this, we find that the critical exponent β and δ obtained using the 3D Heisenberg-model of {d = 3 : n = 3} are close to the experimentally obtained values of the critical exponents. Thus, the long-range exchange interactions in Cr₄Te₅ decays as J(r) = r^{-(d+\sigma)} = r^{-4.71} for d = 3 and σ =1.71.

D. Magnetocaloric Effect

In order to explore the magnetocaloric effect (MCE), we analyzed the field dependent isotherms M(H) taken at different temperatures [see Figs. 3(a) and 3(b)] in the vicinity of T_C for both H|| ab and H|| c orientations. Magnetocaloric effect is an intrinsic property of a ferromagnetic system, causing heating or cooling adiabatically under the applied magnetic fields [59]. Thus, a magnetic entropy change $\Delta S_m(T,H)$ is induced in the presence of magnetic fields which is represented by the formula,

$$\Delta S_{\rm m}(T,H) = \int_{\rm o}^{\rm H} (\frac{\partial S}{\partial H})_{\rm T} dH = \int_{\rm o}^{\rm H} (\frac{\partial M}{\partial T})_{\rm H} dH \qquad (9)$$

where $(\frac{\partial S}{\partial H})_T = (\frac{\partial M}{\partial T})_H$ based on Maxwell's relation. In case of magnetization measured at small discrete field and



FIG. 6. (a) and (b) are the normalized magnetization M and m^2 plotted as a function of re-normalized field h below and above T_C . See the text for more details.

temperature intervals, $\Delta S_m(T, H)$ could be written as

$$\Delta S_{m}(T,H) = \frac{\int_{0}^{H} M(T_{i+1},H) dH - \int_{0}^{H} M(T_{i},H) dH}{T_{i+1} - T_{i}}$$
(10)

Figs. 7(a) and 7(b) show - $\Delta S_m(T, H)$ plotted as a function temperature under various magnetic fields up to 5 T taken with a step size of 1 T for both $H \parallel ab$ and $H \parallel c$ orientations, respectively. All - $\Delta S_m(T,H)$ curves show a maximum change in entropy with a broad peak at around T_{C} as seen from Figs. 7(a) and 7(b). Further, we observe that the value of - $\Delta S_m(T, H)$ and RCP increase monotonically with field for $H \parallel ab$ as shown in Fig. 7(c). Under an applied field of 5 T, the maximum of $-\Delta S_m(T, H)$ is about 2.78 J kg⁻¹ K⁻¹ for H|| ab and is about 2.58 J kg⁻¹ K⁻¹ for H|| c. These - $\Delta S_m(T,H)$ values taken at 5 T are comparable to the other 2D ferromagnetic systems such as $Cr_2Ge_2Te_6$ (2.64 J kg⁻¹ $K^{-1})$ [20] and $Cr_5Te_8~(2.38~J~kg^{-1}~K^{-1})$ [19], larger than the values of $Fe_{3-x}GeTe_2~(1.14~J~kg^{-1}~K^{-1})$ [60] and $CrI_3~(1.56J$ kg^{-1} K⁻¹) [61], and smaller than the values of CrB₃ (7.2 J $kg^{-1} K^{-1}$) [62] and $Cr_2Si_2Te_6$ (5.05 J $kg^{-1} K^{-1}$) [20]. Further, $-\Delta S_m(T,H)$ of the studied Cr_4Te_5 are in good agreement with the earlier reported values of 2.58 J $kg^{-1}~K^{-1}$ and 2.42 J kg^{-1} K^{-1} for $H \parallel ab$ and $H \parallel c$, respectively [25].

To estimate the relative cooling power (RCP), we employed the relation RCP = $-\Delta S_M^{max} \times \delta T_{FWHM}$, where $-\Delta S_M^{max}$ is the maximum entropy change near T_C and δT_{FWHM} is the full width at half maximum of the peak [63]. The calculated RCP in Cr_4Te_5 is of 88.29 J kg⁻¹ at around T_C with an applied field of 5 T parallel to *ab*-plane. The RCP value of Cr_4Te_5 obtained in this study is comparable to the RCP value obtained in the other 2D systems such as $Cr_2Ge_2Te_6$ (87 J kg⁻¹)[20], but smaller than the values obtained from Cr_5Te_8 (131.2 J kg⁻¹) [19], CrI_3 (122.6 J kg⁻¹) [61], $Cr_2Si_2Te_6$ (114 J kg⁻¹) [20], Fe_{3-x}GeTe₂(113 J kg⁻¹) [60], and $CrBr_3(191.5$ J kg⁻¹) [62].

In addition, both $-\Delta S_M^{max}$ and RCP are related by the power law of magnetic field as given below [63, 64],

$$-\Delta S_{\rm M}^{\rm max} = a {\rm H}^{\rm p} \tag{11}$$

$$RCP = bH^q \tag{12}$$

where p and q are the exponents. At $T=T_{\rm C}$, they can be written as

$$p = 1 + \frac{\beta - 1}{\beta + \gamma} \tag{13}$$

$$q = 1 + \frac{1}{\delta} \tag{14}$$

TABLE II. Critical exponents of Cr_4Te_5 . The MAP, KF, and CI represent modified Arrott plot, the Kouvel-Fisher plot, and critical isotherm, respectively.

Technique	β	γ	δ	р	q
$\text{-}\Delta S_{M}^{\max}$				0.70	
RCP					1.27
MAP	0.485	1.202	3.472	0.695	1.288
KFP	0.479	1.196	3.515	0.683	1.285
CI			3.52		1.284

Fig. 7(c) summarizes the field dependence of $-\Delta S_M^{max}$ and RCP. The fit of $-\Delta S_M^{max}$ by the Eq. 11 yields p=0.70. This is in very good agreement with the p value of 0.689(4) obtained from the Eq. 13. Similarly, the field dependence of RCP is fitted by the Eq. 12, yielding to q = 1.27 that is close to the value of 1.28(1) obtained from the Eq. 14 using the critical exponent of δ derived from the magnetic isotherms. Fig. 7(d) displays the temperature dependence of p at 5 T. The p(T) curve follows universal behaviour across T_C as it reaches to the value 1 for T < T_C [65]. On other hand, well above T_C, p reaches to 2 as a consequence of the Curie-Weiss law [65]. At T = T_C, p(T) has a minimum value of 0.7, consistent with the minimum value of 0.75 as per the universal curve [64]. Overall, temperature dependence of p pase transition [64].

Next, we performed the scaling analysis of MCE following the procedure given by Franco *et. al.* [64, 66]. The scaling analysis of - $\Delta S_m(T, H)$ is constructed by normalizing the - $\Delta S_m(T, H)$ curves with respect to the maximum of - ΔS_M^{max} [$\frac{\Delta S_m(T, H)}{\Delta S_M^{max}}$]. The reduced temperature (θ_{\mp}) is defined by choosing two reference temperatures ($T_{r1} \leq T_C$ and $T_{r2} > T_C$), satisfying the condition, $\frac{\Delta S_m(T_{r1} < T_C)}{\Delta S_M^{max}} = \frac{\Delta S_m(T_{r2} > T_C)}{\Delta S_M^{max}} = h$. Here, h is a scaling constant having the values within the range of 0 < h < 1. Then, the rescaled temperature θ_{\mp} can be written as

$$\theta_{-} = (T_{C} - T) / (T_{r1} - T_{C}), T \le T_{C}$$
 (15)

$$\theta_{+} = (T - T_{C}) / (T_{r2} - T_{C}), T > T_{C}$$
 (16)

Following MCE scaling analysis, all the curves of $\Delta S_m / \Delta S_M^{max}$ plotted as a function of reduced temperature θ at various magnetic fields collapse into a single curve as shown in Fig.7(e). This, confirms the second order magnetic phase transition in Cr₄Te₅ [67–69]. Moreover, it can be seen that



FIG. 7. The calculated magnetic entropy $-\Delta S_m$ as a function of temperature at different magnetic field. (a) H || ab, (b) H || c, (c) Field dependence of maximum magnetic entropy changes $(-\Delta S_M^{max})$ (left axis) and relative cooling power (RCP) (right axis), (d) The exponent p as function of temperature obtained from the fitting of field dependent isothermal magnetic entropy change at various temperature, (e) The normalised magnetic entropy changes as a function of rescaled temperature θ at different field, Inset shows T_r vs $H^{1/\Delta}$ with $\Delta = \beta + \gamma$, (f) Rotational magnetic entropy change $(-\Delta S_M^R)$ as a function of temperature.

the universal curve of MCE is independent of the applied magnetic field and temperature as it generally determined by the intrinsic magnetization of the system [64]. Next, the reference temperatures T_{r1} and T_{r2} linearly depends on $H^{1/\Delta}$ with $\Delta = \beta + \gamma$ as shown in the inset of Fig. 7(e). The rotational magnetic entropy changes (ΔS_M^R) can be calculated using the formula $\Delta S_M^R(T,H) = \Delta S_m(T,H_{ab}) - \Delta S_m(T,H_c)$. Fig. 7(f) depicts the temperature dependence of $-\Delta S_M^R(T,H)$. From Fig. 7(f) we can find a maximum of $-\Delta S_M^R(T,H)$ at around T_C when derived at a field interval of 0.2 T. The maxima of $-\Delta S_M^R(T,H)$ shifts to lower temperatures with increasing field intervals and for 2 T of field interval no maxima is found down to 315 K. This behaviour is generally found in the systems with strong magnetic anisotropy [19].

Finally, before concluding, we would like to compare our results with the existing literature on the composition of Cr_4Te_5 . Till date there exits two studies on this system, (i) in the bulk phase [25] and (ii) in thinfilm phase [70]. The Curie temperature of 338 K observed from our M(T) study is higher than the Curie temperature of ≈ 320 K previously reported in both the bulk and thinfilm phases. It is known that in Cr_xTe_y systems the Curie temperature depends on various parameters such as sample thickness, sample composition, and on the method of preparation [71, 72]. The critical exponents of β =0.485(3) and γ =1.202(5) are close to the meanfield-like

and 3D Heisenberg-like interactions, respectively, while the critical exponents of β =0.388 and γ =1.29 as reported in Ref. [25] in the bulk phase are found to be close to the 3D Heisenberg-like and meanfield-like interactions, respectively. On the other hand, the critical exponent found in the thinfilm phase β =0.491 is close to the meanfield-like interactions, consistent with our observations [70]. Such a mixed phase interactions are reported in many other 2D Ferromagnets such as in Fe_{0.26}TaS₂ (β = 0.459, γ = 1.205) [73] and Co_{0.22}TaS₂ (β = 0.43, γ = 1.15) [74]. Nevertheless, the renormalization group theory analysis suggests the 3D Heisenberg-type magnetic interactions in the studied system when estimated using the experimental γ value of 1.202.

IV. SUMMARY

To summarize, we thoroughly studied the magnetic anisotropy and magnetocaloric effect associated with critical exponent analysis of Cr_4Te_5 . The critical exponents of β , γ , and δ obtained from the modified Arrot-plot and Kouvel-Fisher techniques match very well. Scaling analysis of the magnetic entropy change confirms the second order magnetic phase transition in this system. Strong uniaxial magnetocrystalline anisotropy found in this system could stabilize the long-range FM ordering within few layers. The renormalization group theory analysis suggests 3D Heisenberg-type magnetic interactions in Cr_4Te_5 .

V. ACKNOWLEDGEMENTS

Authors thank SERB (DST), India for financial support (Grant No. SRG/2020/000393). S.C. and S.G. acknowledge University Grants Commission (UGC), India for the PhD fellowship.

- [1] Y. Deng, Y. Yu, Y. Song, J. Zhang, N. Z. Wang, Z. Sun, Y. Yi, Y. Z. Wu, S. Wu, J. Zhu, *et al.*, Gate-tunable room-temperature ferromagnetism in two-dimensional Fe₃GeTe₂, Nature 563, 94 (2018).
- [2] B. Wang, Y. Zhang, L. Ma, Q. Wu, Y. Guo, X. Zhang, and J. Wang, MnX (X= P, As) monolayers: a new type of twodimensional intrinsic room temperature ferromagnetic halfmetallic material with large magnetic anisotropy, Nanoscale 11, 4204 (2019).
- [3] A. K. Geim and I. V. Grigorieva, Van der waals heterostructures, Nature 499, 419 (2013).
- [4] J. T. Heron, M. Trassin, K. Ashraf, M. Gajek, Q. He, S. Y. Yang, D. E. Nikonov, Y.-H. Chu, S. Salahuddin, and R. Ramesh, Electric-field-induced magnetization reversal in a ferromagnetmultiferroic heterostructure, Phys. Rev. Lett. **107**, 217202 (2011).
- [5] H. Liu, Y. Zhang, O. E. Glukhova, G. Zhang, L. Wang, J. Zhao, and J. Gao, Interlayer hopping kinetics of vacancies in cri3 layers leading to monolayer/bilayer heterostructures, Advanced Materials Interfaces 9, 2200626 (2022).
- [6] A. Soumyanarayanan, N. Reyren, A. Fert, and C. Panagopoulos, Emergent phenomena induced by spin– orbit coupling at surfaces and interfaces, Nature 539, 509 (2016).
- [7] C. Gong, L. Li, Z. Li, H. Ji, A. Stern, Y. Xia, T. Cao, W. Bao, C. Wang, Y. Wang, *et al.*, Discovery of intrinsic ferromagnetism in two-dimensional van der waals crystals, Nature 546, 265 (2017).
- [8] K. L. Seyler, D. Zhong, D. R. Klein, S. Gao, X. Zhang, B. Huang, E. Navarro-Moratalla, L. Yang, D. H. Cobden, M. A. McGuire, *et al.*, Ligand-field helical luminescence in a 2D ferromagnetic insulator, Nature Physics 14, 277 (2018).
- [9] Z. Fei, B. Huang, P. Malinowski, W. Wang, T. Song, J. Sanchez, W. Yao, D. Xiao, X. Zhu, A. F. May, *et al.*, Two-dimensional itinerant ferromagnetism in atomically thin Fe₃GeTe₂, Nature materials 17, 778 (2018).
- [10] M. Gibertini, M. Koperski, A. F. Morpurgo, and K. S. Novoselov, Magnetic 2d materials and heterostructures, Nature nanotechnology 14, 408 (2019).
- [11] H. L. Zhuang, P. R. C. Kent, and R. G. Hennig, Strong anisotropy and magnetostriction in the two-dimensional stoner ferromagnet fe3gete2, Phys. Rev. B 93, 134407 (2016).
- [12] N. D. Mermin and H. Wagner, Absence of ferromagnetism or antiferromagnetism in one- or two-dimensional isotropic heisenberg models, Phys. Rev. Lett. 17, 1133 (1966).
- [13] B. Huang, G. Clark, E. Navarro-Moratalla, D. R. Klein, R. Cheng, K. L. Seyler, D. Zhong, E. Schmidgall, M. A. McGuire, D. H. Cobden, W. Yao, D. Xiao, P. Jarillo-Herrero, and X. Xu, Layer-dependent ferromagnetism in a van der Waals crystal down to the monolayer limit, Nature 546, 270 (2017).
- [14] Y. Liu and C. Petrovic, Critical behavior of quasi-twodimensional semiconducting ferromagnet Cr₂Ge₂Te₆, Phys. Rev. B 96, 054406 (2017).

- [15] T. J. Williams, A. A. Aczel, M. D. Lumsden, S. E. Nagler, M. B. Stone, J.-Q. Yan, and D. Mandrus, Magnetic correlations in the quasi-two-dimensional semiconducting ferromagnet CrSiTe₃, Phys. Rev. B **92**, 144404 (2015).
- [16] X. Sun, S. Zhao, A. Bachmatiuk, M. H. Rümmeli, S. Gorantla, M. Zeng, and L. Fu, 2D Intrinsic Ferromagnetic MnP Single Crystals, Small 16, 2001484 (2020).
- [17] L. M. Moreno-Ramírez and V. Franco, Reversibility of the magnetocaloric effect in the bean-rodbell model, Magnetochemistry 7, 10.3390/magnetochemistry7050060 (2021).
- [18] V. Y. Verchenko, A. A. Tsirlin, A. V. Sobolev, I. A. Presniakov, and A. V. Shevelkov, Ferromagnetic order, strong magnetocrystalline anisotropy, and magnetocaloric effect in the layered telluride Fe₃GeTe₂, Inorganic Chemistry 54, 8598 (2015), pMID: 26267350.
- [19] Y. Liu, M. Abeykoon, E. Stavitski, K. Attenkofer, and C. Petrovic, Magnetic anisotropy and entropy change in trigonal Cr₅Te₈, Phys. Rev. B 100, 245114 (2019).
- [20] Y. Liu and C. Petrovic, Anisotropic magnetic entropy change in $Cr_2X_2Te_6$ (X = Si and Ge), Phys. Rev. Materials 3, 014001 (2019).
- [21] Y. Zhu, X. Kong, T. D. Rhone, and H. Guo, Systematic search for two-dimensional ferromagnetic materials, Phys. Rev. Materials 2, 081001 (2018).
- [22] T. Eto, M. Ishizuka, S. Endo, T. Kanomata, and T. Kikegawa, Pressure-induced structural phase transition in a ferromagnet CrTe, Journal of Alloys and Compounds 315, 16 (2001).
- [23] F. Wang, J. Du, F. Sun, R. F. Sabirianov, N. Al-Aqtash, D. Sengupta, H. Zeng, and X. Xu, Ferromagnetic Cr₂Te₃ nanorods with ultrahigh coercivity, Nanoscale 10, 11028 (2018).
- [24] B. Hessen, T. Siegrist, T. Palstra, S. Tanzler, and M. Steigerwald, Hexakis (triethylphosphine) octatelluridohexachromium and a molecule-based synthesis of chromium telluride, Cr_3Te_4 , Inorganic chemistry **32**, 5165 (1993).
- [25] L.-Z. Zhang, A.-L. Zhang, X.-D. He, X.-W. Ben, Q.-L. Xiao, W.-L. Lu, F. Chen, Z. Feng, S. Cao, J. Zhang, and J.-Y. Ge, Critical behavior and magnetocaloric effect of the quasi-twodimensional room-temperature ferromagnet Cr₄Te₅, Phys. Rev. B 101, 214413 (2020).
- [26] Y. Wang, J. Yan, J. Li, S. Wang, M. Song, J. Song, Z. Li, K. Chen, Y. Qin, L. Ling, H. Du, L. Cao, X. Luo, Y. Xiong, and Y. Sun, Magnetic anisotropy and topological Hall effect in the trigonal chromium tellurides Cr₅Te₈, Phys. Rev. B 100, 024434 (2019).
- [27] J. Dijkstra, H. H. Weitering, C. F. van Bruggen, C. Haas, and R. A. de Groot, Band-structure calculations, and magnetic and transport properties of ferromagnetic chromium tellurides (CrTe, Cr₃Te₄, Cr₂Te₃), Journal of Physics: Condensed Matter 1, 9141 (1989).

- [28] Z.-L. Huang, W. Bensch, D. Benea, and H. Ebert, Anion substitution effects on structure and magnetism in the chromium chalcogenide Cr5Te8—Part I: Cluster glass behavior in trigonal Cr(1+x)Q2 with basic cell (Q=Te, Se; Te:Se=7:1), J. Solid State Chem. 177, 3245 (2004).
- [29] Z.-L. Huang, W. Bensch, S. Mankovsky, S. Polesya, H. Ebert, and R. K. Kremer, Anion substitution effects on structure and magnetism of the chromium chalcogenide Cr₅Te₈ Part II: Cluster-glass and spin-glass behavior in trigonal Cr(1+x) Q2 with basic cells and trigonal Cr(5+x) Q8 with superstructures (Q=Te, Se; Te:Se=6:2), J. Solid State Chem. **179**, 2067 (2006).
- [30] J. Wontcheu, W. Bensch, S. Mankovsky, S. Polesya, H. Ebert, R. K. Kremer, and E. Brücher, Anion substitution effects on the structure and magnetism of the chromium chalcogenide Cr5Te8—Part III: Structures and magnetism of the hightemperature modification Cr(1+x)Q2 and the low-temperature modification Cr(5+x)Q8 (Q=Te, Se; Te:Se=5:3), J. Solid State Chem. 181, 1492 (2008).
- [31] H. Ipser, K. L. Komarek, and K. O. Klepp, Transition metalchalcogen systems viii: The CrTe phase diagram, Journal of the Less Common Metals 92, 265 (1983).
- [32] T. Hashimoto, K. Hoya, M. Yamaguchi, and I. Ichitsubo, Magnetic properties of single crystals $\text{Cr}_{2-\delta}$ Te₃, Journal of the Physical Society of Japan **31**, 679 (1971).
- [33] Y. Liu and C. Petrovic, Critical behavior of the quasi-twodimensional weak itinerant ferromagnet trigonal chromium telluride $Cr_{0.62}$ Te, Phys. Rev. B **96**, 134410 (2017).
- [34] X. Zhang, T. Yu, Q. Xue, M. Lei, and R. Jiao, Critical behavior and magnetocaloric effect in monoclinic Cr₅Te₈, Journal of Alloys and Compounds **750**, 798 (2018).
- [35] A. L. Coughlin, D. Xie, X. Zhan, Y. Yao, L. Deng, H. Hewa-Walpitage, T. Bontke, C.-W. Chu, Y. Li, J. Wang, *et al.*, Van der Waals Superstructure and Twisting in Self-Intercalated Magnet with Near Room-Temperature Perpendicular Ferromagnetism, Nano letters 21, 9517 (2021).
- [36] L.-Z. Zhang, Q.-L. Xiao, F. Chen, Z. Feng, S. Cao, J. Zhang, and J.-Y. Ge, Multiple magnetic phase transitions and critical behavior in single crystal Cr₅Te₆, Journal of Magnetism and Magnetic Materials **546**, 168770 (2022).
- [37] L.-Z. Zhang, X.-D. He, A.-L. Zhang, Q.-L. Xiao, W.-L. Lu, F. Chen, Z. Feng, S. Cao, J. Zhang, and J.-Y. Ge, Tunable curie temperature in layered ferromagnetic Cr_{5+δ}Te₈ single crystals, APL Materials 8, 031101 (2020).
- [38] Z.-L. Huang, W. Kockelmann, M. Telling, and W. Bensch, A neutron diffraction study of structural and magnetic properties of monoclinic Cr₅Te₈, Solid State Sciences **10**, 1099 (2008).
- [39] J. Yan, X. Luo, G. Lin, F. Chen, J. Gao, Y. Sun, L. Hu, P. Tong, W. Song, Z. Sheng, W. Lu, X. Zhu, and Y. Sun, Anomalous hall effect of the quasi-two-dimensional weak itinerant ferromagnet Cr_{4.14}Te₈, EPL (Europhysics Letters) **124**, 67005 (2019).
- [40] R. Mondal, R. Kulkarni, and A. Thamizhavel, Anisotropic magnetic properties and critical behaviour studies of trigonal Cr₅Te₈ single crystal, Journal of Magnetism and Magnetic Materials 483, 27 (2019).
- [41] E. C. Stoner and E. Wohlfarth, A mechanism of magnetic hysteresis in heterogeneous alloys, Philosophical Transactions of the Royal Society of London. Series A, Mathematical and Physical Sciences 240, 599 (1948).
- [42] B. D. Cullity and C. D. Graham, *Introduction to magnetic materials* (John Wiley & Sons, 2011).
- [43] N. Richter, D. Weber, F. Martin, N. Singh, U. Schwingenschlögl, B. V. Lotsch, and M. Kläui, Temperature-dependent magnetic anisotropy in the layered magnetic semiconductors CrI₃ and CrBr₃, Phys. Rev.

Materials 2, 024004 (2018).

- [44] N. León-Brito, E. D. Bauer, F. Ronning, J. D. Thompson, and R. Movshovich, Magnetic microstructure and magnetic properties of uniaxial itinerant ferromagnet fe3gete2, Journal of Applied Physics 120, 083903 (2016).
- [45] N. León-Brito, E. D. Bauer, F. Ronning, J. D. Thompson, and R. Movshovich, Magnetic microstructure and magnetic properties of uniaxial itinerant ferromagnet Fe₃GeTe₂, J. Appl. Phys. **120**, 083903 (2016).
- [46] C. Zener, Classical theory of the temperature dependence of magnetic anisotropy energy, Phys. Rev. 96, 1335 (1954).
- [47] W. Carr Jr, Temperature dependence of ferromagnetic anisotropy, Physical Review 109, 1971 (1958).
- [48] H. E. Stanley, *Phase transitions and critical phenomena*, Vol. 7 (Clarendon Press, Oxford, 1971).
- [49] M. E. Fisher, The theory of equilibrium critical phenomena, Reports on progress in physics 30, 615 (1967).
- [50] A. Arrott, Criterion for Ferromagnetism from Observations of Magnetic Isotherms, Phys. Rev. 108, 1394 (1957).
- [51] J. C. Le Guillou and J. Zinn-Justin, Critical exponents from field theory, Phys. Rev. B 21, 3976 (1980).
- [52] S. Kaul, Static critical phenomena in ferromagnets with quenched disorder, Journal of magnetism and magnetic materials 53, 5 (1985).
- [53] M. E. Fisher, S.-k. Ma, and B. G. Nickel, Critical Exponents for Long-Range Interactions, Phys. Rev. Lett. 29, 917 (1972).
- [54] D. Kim, B. Revaz, B. L. Zink, F. Hellman, J. J. Rhyne, and J. F. Mitchell, Tricritical Point and the Doping Dependence of the Order of the Ferromagnetic Phase Transition of La_{1-x}Ca_xMnO₃, Phys. Rev. Lett. 89, 227202 (2002).
- [55] A. Arrott and J. E. Noakes, Approximate Equation of State For Nickel Near its Critical Temperature, Phys. Rev. Lett. 19, 786 (1967).
- [56] A. K. Pramanik and A. Banerjee, Critical behavior at paramagnetic to ferromagnetic phase transition in $Pr_{0.5}Sr_{0.5}MnO_3$: A bulk magnetization study, Phys. Rev. B **79**, 214426 (2009).
- [57] J. S. Kouvel and M. E. Fisher, Detailed magnetic behavior of nickel near its curie point, Phys. Rev. 136, A1626 (1964).
- [58] B. Widom, Degree of the critical isotherm, The Journal of Chemical Physics 41, 1633 (1964).
- [59] V. K. Pecharsky and K. A. Gschneidner Jr, Magnetocaloric effect and magnetic refrigeration, Journal of Magnetism and Magnetic Materials 200, 44 (1999).
- [60] Y. Liu, J. Li, J. Tao, Y. Zhu, and C. Petrovic, Anisotropic magnetocaloric effect in Fe_{3-x}GeTe₂, Sci. Rep. 9, 13233 (2019).
- [61] Y. Liu and C. Petrovic, Anisotropic magnetocaloric effect in single crystals of CrI₃, Phys. Rev. B 97, 174418 (2018).
- [62] X. Yu, X. Zhang, Q. Shi, S. Tian, H. Lei, K. Xu, and H. Hosono, Large magnetocaloric effect in van der Waals crystal CrBr₃, Front Phys-beijing 14, 10.1007/s11467-019-0883-6 (2019).
- [63] K. Gschneidner Jr, V. Pecharsky, A. Pecharsky, and C. Zimm, Recent developments in magnetic refrigeration, in *Materials science forum*, Vol. 315 (Trans Tech Publ, 1999) pp. 69–76.
- [64] V. Franco, J. Blázquez, and A. Conde, Field dependence of the magnetocaloric effect in materials with a second order phase transition: A master curve for the magnetic entropy change, Applied physics letters 89, 222512 (2006).
- [65] V. Franco, R. Caballero-Flores, A. Conde, Q. Dong, and H. Zhang, The influence of a minority magnetic phase on the field dependence of the magnetocaloric effect, Journal of Magnetism and Magnetic Materials 321, 1115 (2009).

- [66] V. Franco, C. Conde, J. Blázquez, A. Conde, P. Švec, D. Janičkovič, and L. Kiss, A constant magnetocaloric response in FeMoCuB amorphous alloys with different Fe/B ratios, Journal of applied physics 101, 093903 (2007).
- [67] H. Oesterreicher and F. Parker, Magnetic cooling near curie temperatures above 300 k, Journal of applied physics 55, 4334 (1984).
- [68] J. Y. Law, V. Franco, L. M. Moreno-Ramírez, A. Conde, D. Y. Karpenkov, I. Radulov, K. P. Skokov, and O. Gutfleisch, A quantitative criterion for determining the order of magnetic phase transitions using the magnetocaloric effect, Nature communications 9, 1 (2018).
- [69] V. Franco, J. Law, A. Conde, V. Brabander, D. Karpenkov, I. Radulov, K. Skokov, and O. Gutfleisch, Predicting the tricritical point composition of a series of LaFeSi magnetocaloric alloys via universal scaling, Journal of Physics D: Applied Physics 50, 414004 (2017).
- [70] J. Wang, W. Wang, J. Fan, H. Zheng, H. Liu, C. Ma, L. Zhang, W. Tong, L. Ling, Y. Zhu, and H. Yang, Epitaxial growth and room-temperature ferromagnetism of quasi-2D layered Cr₄Te₅

thin film, J. Phys. Appl. Phys. 55, 165001 (2022).

- [71] H. Li, L. Wang, J. Chen, T. Yu, L. Zhou, Y. Qiu, H. He, F. Ye, I. K. Sou, and G. Wang, Molecular Beam Epitaxy Grown Cr₂Te₃ Thin Films with Tunable Curie Temperatures for Spintronic Devices, ACS Appl. Nano Mater. 2, 6809 (2019).
- [72] I. H. Lee, B. K. Choi, H. J. Kim, M. J. Kim, H. Y. Jeong, J. H. Lee, S.-Y. Park, Y. Jo, C. Lee, J. W. Choi, S. W. Cho, S. Lee, Y. Kim, B. H. Kim, K. J. Lee, J. E. Heo, S. H. Chang, F. Li, B. L. Chittari, J. Jung, and Y. J. Chang, Modulating Curie Temperature and Magnetic Anisotropy in Nanoscale-Layered Cr₂Te₃ Films: Implications for Room-Temperature Spintronics, ACS Appl. Nano Mater. 4, 4810 (2021).
- [73] C. Zhang, Y. Yuan, M. Wang, P. Li, J. Zhang, Y. Wen, S. Zhou, and X.-X. Zhang, Critical behavior of intercalated quasi-van der Waals ferromagnet Fe_{0.26}TaS₂, Phys. Rev. Materials 3, 114403 (2019).
- [74] Y. Liu, Z. Hu, E. Stavitski, K. Attenkofer, and C. Petrovic, Magnetic critical behavior and anomalous Hall effect in $2H-Co_{0.22}TaS_2$ single crystals, Phys. Rev. Research 3, 023181 (2021).