Reentrant spin glass transition in $La_{0.96} _{y}N d_{y}K_{0.04}M nO_{3}$: origin and e ects on the colossalm agnetoresistivity

R.Mathieu¹, P.Svedlindh¹, and P.Nordblad¹

¹ Departm ent of M aterials Science, Uppsala University, Box 534, SE-751 21 Uppsala, Sweden

PACS.75.30.Vn { Colossalm agnetoresistance. PACS.75.50.Lk { Spin glasses and other random m agnets.

A bstract. { M agnetic, electric and structural properties of $La_{0:96}$ $_{\rm Y}N d_{\rm Y}K_{0:04}M nO_{3+}$ with 0 y 0.4 have been studied experimentally. A disordered m agnetic state is formed as La is substituted by N d, rejecting the competition between ferrom agnetic (FM) double exchange and antiferrom agnetic superexchange interactions. Key structural parameters are identiated and correlated with changes in m agnetic and electric properties. By application of a large m agnetic eld, spin disorder scattering is removed, creating a new m agnetoresistance peak at a tem perature lower than the rst near-T_c peak. T in e dependent zero- eld-cooled m agnetisation m easurements have been performed for y=0.4 around this tem perature. A reentrant spin glass (R SG) transition is evidenced, with low eld ageing properties in both the R SG and FM phases, similar to those observed in archetypal spin glass m aterials.

Introduction. { The doped m anganite com pounds $R_1 \vee A_v M$ nO₃ (R = rare earth; A = alkaline earth) have been intensively investigated concerning their colossalm agnetoresistance (CMR) properties [1]. Sin ultaneous ferrom agnetic (FM) and m etallic properties in these m anganese oxides are attributed to double exchange [2] (DE) interaction between pairs of M n³⁺ ($t_{\alpha}^{3}e_{\alpha}^{1}$) and M n^{4+} ($t^3_{2\alpha}$) ions. Substitution of cations with di erent sizes at the rare earth sizes results in lattice distortions that may in uence the ferrom agnetic DE and the antiferrom agnetic (AFM) superexchange interactions di erently, for instance increasing the importance of the AFM interactions with respect to the FM interactions. This can create various form s of m agnetic disorder, thereby also a ecting the transfer integral for itinerant e_r electrons which depends on the relative spin orientation of the localized t_{2g} m om ents; $t_{ij} / \cos(t_{ij}=2)$, where $_{ij}$ is the angle between moments i and j β]. In system s with ferrom agnetic DE interaction dom inating, the AFM interactions may still cause magnetic disorder and frustration and the system is in this case expected to show a low temperature reentrant spin glass (RSG) phase [4,5]. When such a system is cooled from a high temperature, it rst exhibits a transition from a param agnetic (PM) to a ferror agnetic (FM) phase. If the cooling proceeds, a transition to a RSG phase occurs. Indications of such a transition have already been reported for CMR compounds, but without presenting convincing experimental evidences for its existence. U sually, the authors consider that a low temperature cusp in the zero-eld-cooled

c EDP Sciences

EUROPHYSICS LETTERS

(ZFC) magnetisation, leading to a di erence between the ZFC and eld cooled (FC) magnetisation curves at low tem peratures, is enough to evidence a low tem perature RSG phase [6{9]. A c-susceptibility m easurem ents are som etim es added; a frequency dependent ac-susceptibility is then attributed to the RSG phase [10{12]. But, even if these features are indicative of a deviation from a perfectly ordered ferrom agnetic state, they are not su cient to prove a low temperature RSG phase. Moreover, it is possible to envisage other disordered magnetic phases resulting from a competition between ferrom agnetic DE and antiferrom agnetic superexchange interactions. Low temperature spin canted AF and FM phases were suggested in the pioneering work of de Gennes [3]. More recent work indicates that the canted phase is unstable against electronic phase separation and the form ation of hole rich ferrom agnetic and hole undoped antiferrom agnetic regions [13,14]. Thus, other and com plem entary experiments must be performed to dissolve the details of the magnetic phase diagram of the manganese perovskites. For example in a disordered and frustrated magnetic system like a spin glass, the zero-eld cooled (ZFC) magnetisation relaxes in a characteristic way if the tem perature is kept constant; therefore tim e-dependent ZFC m agnetisation m easurem ents m ay be used to study the evolution of the spin con quration and the possible occurrence of a RSG phase. In the present study, we investigate e ects of ion size m ism atch induced by replacing La^{3+}

with N d³⁺ in the manganese oxide La_{0:96} $_{y}N d_{y}K_{0:04}M$ nO₃₊ . A RSG phase transition, creating a second peak in the magnetoresistance when applying a su ciently large magnetic eld, is revealed from ZFC relaxation measurements. The results give evidence in support of a recent proposal that the AFM superexchange interaction is one mechanism responsible for spin disorder and that the DE ferrom agnetic interaction is more strongly a ected by a variation of the M n O M n bond with cation substitution [15].

Samples and Experiments. { Single-phase La_{0.96} yN dyK 0:04 M nO 3+, with y ranging from 0 to 0.4 in steps of 0.1 were prepared by solid state reaction between La₂O 3, N d₂O 3, M nO 2 and K₂CO 3 in stoichiom etric proportions. Substitution of N d³⁺ at the La³⁺ site, N d³⁺ having a smaller ionic radius, m odi es the M n O M n bond angle and the M n O bond length. Structure and composition of the obtained compounds were checked by room temperature x-ray di raction (X R D) on a high resolution STOE transm ission di ractom eter equipped with a position-sensitive detector. The scanning range was 10°-90° and C uK 1 radiation was used for all data collections. We observe a change in structure from rhom bohedral R 3C to orthorhom bic P nm a; Table I gives a sum m ary of the structural data; the change from R 3C to P nm a at an average A -site ionic radius < $r_A > = 1.225$ A is in full agreem ent with earlier reports [16]. For y = 0:1, with < $r_A > = 1.224$ A, it was necessary to include a m ixture of the rhom bohedral and the orthorhom bic structures in the rements.

Low eld ac-susceptibility measurements, $(f;T) = {}^{0}(f;T) + {}^{00}(f;T)$, were performed in a LakeShore ac-susceptom eter. Measurements of resistivity and magnetoresistance were performed using a M aglab 2000 system from 0 xford Instruments; the magnetoresistance is dened as $(R_0 R_H)=R_0$. Finally, time dependent ZFC magnetisation measurements were performed in a non-commercial SQUID magnetometer [17]. The sample was cooled in zero eld from a temperature above T_c to the measurement temperature. A fler a waiting time (t_w), a weak magnetic eld (H = 0.05 to 10 e) was applied and the magnetisation M (t) recorded vs. observation time t. The relaxation rate, dened as S(t) = H 1 dM /dlog t, was derived from these measurements.

Results and discussion. { The main frame of Fig. 1 shows $^{0}(f)$ and $^{00}(f)$ vs. tem - perature for the y = 0 and y = 0.4 samples. The Curie temperature (T_{c}), de ned from the in ection point in $^{0}(f)$ decreases with increasing Nd doping. At the same time, a frequency

2

dependent knee is created in the in-phase component of the ac-susceptibility at a temperature $T_f(f) < T_c$, corresponding to a large and likewise frequency dependent peak in the out-of-phase component; T_f (f) decreases with increasing Nd doping. This more pronounced frequency dependence of indicates that the magnetic state is more disordered at low tem peratures. The magnetic disorder is a consequence of changes in the crystal structure induced by replacing La^{3+} with Nd^{3+} . The smaller M n O M n bond angle (cf. Table I) will a ect (decrease) not only the DE hopping integral between e_{a} (M n)-2p (O)- e_{a} (M n) orbitals but also the AFM superexchange hopping integral between $t_{2q} (M n) - 2p$ (0) $- t_{2q} (M n)$ orbitals. However, due to the nature of the dp hybridization, the AFM interaction is expected to be less in uenced by changes in bond angle and will thus, relative to the FM DE interaction, increase in importance. The strong e ect on the DE interaction is con med by the variation of the ferrom agnetic transition tem perature with bond angle presented in the insert of Fig. 1. In passing we note that disorder in the magnetic interactions may lead to one of several possible, distinctly di erent m agnetic states; a spin canted state β , a state with electronic phase separation between ferrom agnetic and antiferrom agnetic regions [13,14], or a RSG state [4]. It is in portant to realize that these possible magnetic states are expected to display quite different magnetic and electrical behaviors, som ething which will discussed more in detail below. Fig. 2 (a) presents the zero- eld resistivity vs. tem perature for all sam ples. A m etal-insulator (M-I) transition occurs for N d dopings y = 0 and y = 0:1 at a tem perature close to T_c . As the Nd doping further increases the resistivity increases and no clear M -I transition is observed; the resistivity at low tem peratures increases with decreasing tem perature. By application of a large magnetic eld, the spin disorder scattering induced by competing FM and AFM interactions is rem oved, creating a new magnetoresistance peak at a tem perature lower than the

rst near-T_c peak (see Fig. 2 (b)); for y=0.4, this second peak is larger in m agnitude than the rst one. The second peak in the magnetoresistance appears at a tem perature close to $T_{\rm f}$ (f), suggesting a correlation between these di erent experim ental observations. This is con med re-measuring⁰⁰ with a superimposed dc eld, as shown in Fig. 3. The dissipation is strongly suppressed by the dc eld; at $H_{dc} = 10^3$ Oe, the frequency dependent (cf. insert of Fig. 3) peaks in 00 are still observed, shifted slightly to lower temperature, while at H $_{\rm dc}$ = 10⁴ Oe, the dissipation is very weak and the RSG like features are no longer observed. This indicates that, since the second peak in the magnetoresistance at T_{f} continues to develop increasing the eld further (cf. Fig. 2 (b)), weak magnetic disorder remains, in the sense that the spin system is not fully collinear even after suppressing the slow spin dynamics of the RSG phase. The frequency dependence of the ac-susceptibility and the absence of a M-I transition for larger Nd dopings suggest that the ferrom agnetic spin arrangem ent and the electronic con quration are perturbed. A transition from a FM metallic to an AFM partially charge ordered state with electronic phase separation of antiferro- and ferrom agnetically ordered regions will result in a sharp decrease of 0 at the transition temperature as well as a likewise sharp increase of the resistivity [18]. M oreover, in partially charge ordered systems, application of a magnetic

eld drastically m odi es the transport behavior; a relatively m odest m agnetic eld w ill turn the insulating state to a m etallic state [18,19]. These characteristics are not observed in the presently investigated m anganite system.

A nother explanation for the observed spin-disorder is that a spin glass phase appears at low tem peratures. One actually refers to a reentrant spin glass phase since the disordered m agnetic phase appears at tem peratures below where an ordered (ferrom agnetic) phase rst appears. This kind of sam ples have been extensively studied in the past, and it has been shown that RSG sam ples exhibit sim ilar relaxation properties as conventional spin glasses [20]. In particular, the time dependence of the ZFC m agnetisation depends on the time t_w used to equilibrate the spin system before applying a magnetic eld. This dependence is revealed by an in ection

EUROPHYSICS LETTERS

point in the M (t) vs. log (t) curve, corresponding to a maximum in the relaxation rate S (t) curve, at an observation time close to the waiting time t t_w . The phenom enon is called ageing, and is an inherent property of disordered and frustrated spin system s, while this property is not expected to be part of the spin canted phase originally described by de G ennes [3].

T in e dependent ZFC m agnetisation m easurem ents have been perform ed for the sam ple y=0.4 to study the behavior of the m agnetic relaxation at tem peratures both below and above the tem perature where the disordered m agnetic state appears. Fig. 4 (a) shows the relaxation rate S (t) for T = 50K (below T_f(f)) and T = 110K (above T_f(f)), for di erent m agnetic

elds. The sample displays clear ageing behavior at both temperatures, with a waiting time dependence similar to that observed for ordinary spin glasses [20] as shown in the insert of Fig. 4, explicitly proving the RSG nature of the low temperature transition. The magnitude of the observed ageing phenomenon as well as the magnitude of the peak in $^{(0)}(T)$ prove the e ect to be intrinsic to the material rather than conned to a possible spin disorder at grain boundaries. A loo, as shown in Fig. 4 (b) the relaxation rate for T = 50K indicates linear response of the magnetisation up to (relatively) high elds in the RSG phase. In the ferrom agnetic phase (see Fig. 4 (b)), the response is non-linear even in weak magnetic elds and the ageing phenomenon is gradually suppressed when increasing the magnetic eld, as it has also been observed in conventional reentrant spin glass materials [21].

Conclusion. { The resistivity of the La_{0:96} $_{y}N d_{y}K_{0:04}M nO_{3+}$ system increases with increasing y while the C urie tem perature decreases, both observations indicating a lesser degree of FM double exchange interaction in favor of AFM superexchange interaction. The competition between FM and AFM exchange interactions results in spin disorder and frequency dependent characteristics of the ac-susceptibility; a frequency dependent peak in $^{00}(f;T)$ is observed at a tem perature $T_f(f) < T_c$. The spin disorder is also evidenced by a second m agnetoresistance peak at a tem perature close to $T_f(f)$. Time dependent ZFC m agnetisation m easurements show ageing phenomena, both below and above $T_f(f)$, revealing the identity of the low tem perature disordered m agnetic state to be a reentrant spin glass phase. These results show the significance of the AFM superexchange interaction between localized $\xi_g(M n)$ m om ents and how by substitution of cations it is possible to control its m agnitude relative to the m agnitude of the ferror agnetic DE interaction.

Financial support from the Swedish Natural Science Research Council (NFR) is acknow hedged. The authors are grateful to Y.Guo for sample preparation and to Prof. Y.Anderson for help with structural analysis.

REFERENCES

- [1] A.P.Ramirez, J.Phys.: Condens. Matter, 9 (1997) 8171
- [2] C.Zener, Phys. Rev., 82 (1951) 403
- [3] P.-G. de Gennes, Phys. Rev., 118 (1960) 141
- [4] K.Jonason, J.M attsson, P.Nordblad, Phys. Rev. B, 53 (1996) 6507
- [5] K.Jonason, J.M. attson, P.Nordblad, Phys. Rev. Lett., 77 (1996) 2562
- [6] T.Terai, T.Kakeshita, T.Fukuda, T.Saburi, N.Takamoto, K.Kindo, M.Honda, Phys.Rev.B, 58 (1998) 14908
- [7] X.J.Fan, J.H.Zhang, X.G.Li, W.B.Wu, J.Y.Wan, T.J.Lee, and H.C.Ku, J.Phys.: Condens. Matter, 11 (1999) 3141–3148
- [8] J. Zhang, F. Wang, P. Zhang, and Q. Yan, Jour. of Appl. Phys., 86 (1999) 1604

R.M athieu, P.Svedlindh, and P.Nordblad: Reentrant spin glass transition in La0:96 yN dyK 0:04 M nO 3: origin and ef

- [9] J.B.Shi, F.C.W u, C.T.Lin, Appl. Phys. A, 68 (1999) 577-581
- [10] J-W .Cai, C.W ang, B-G.Shen, J-G.Zhao, and W -S.Zhan, Appl. Phys. Lett., 71 (1997) 12
- [11] A.Sundaresan, A.Maignan, and B.Raveau, Phys. Rev. B, 56 (1997) 5092
- [12] J.C.Nie, J.H.W ang, B.R.Zhao, J.M agn.M agn.M ater., 192 (1999) L379-L385
- [13] J.Riera, K.Hallberg, and E.Dagotto, Phys. Rev. Lett., 79 (1997) 713
- [14] S.Yunoki, J.Hu, A.L.Malvezzi, A.Moreo, N.Furukawa, and E.Dagotto, Phys. Rev. Lett., 80 (1998) 845
- [15] Hongsuk Yi, Jaejun Yu, and Sung-Ik Lee, Phys. Rev. B, 61 (2000) 428
- [16] P.G.Radaelli, G.Iannone, M.Marezio, H.Y.Hwang, S-W. Cheong, J.D. Jorgensen and D.N.Argyriou, Phys. Rev. B, 56 (1997) 8265
- [17] J. Magnusson, C. D jurberg, P. Granberg, and P. Nordblad, Rev. Sci. Instrum., 68 (1997) 3761
- [18] Y.Tomioka, A.Asamitsu, Y.Moritomo, H.Kuwahara, and Y.Tokura, Phys. Rev. Lett., 74 (1995) 5108
- [19] Y. Tomioka, A. Asamitsu, H. Kuwahara, Y. Moritomo and Y. Tokura, Phys. Rev. B, 53 (1996) R1689
- [20] P.Svedlindh, P.Granberg, P.Nordblad, L.Lundgren, H.S.Chen, Phys. Rev. B, 35 (1987) 268
- [21] K.Jonason, P.Nordblad, J.Magn. Magn. Mater., 177-181 (1998) 95
- [22] R.D.Shannon, Acta Cryst., A 32 (1976) 751

Table I { Structural data for all compositions: average A-site ionic radius < r_A > (A), average bond length M n O (A), bond angle M n O M n (degrees), and Curie temperature T_c (K); < r_A > is calculated using data from [22].

У	Struct.	< r _A $>$	< d _{M n 0} >	Mn O Mn	$T_{\rm c}$
0	R –3C	1,229	2.080	160.73	252
0.1	(R-3C,Pnma)	1,224	(1 . 970 , 1 . 973)	(159.75,160.11)	240
0.2	Pnm a	1,218	1.977	158.23	182
0.3	Pnm a	1,213	1.976	157.98	165
0.4	Pnm a	1.208	1.972	157.97	167



Fig.1 { In-phase component of the ac-susceptibility for y=0 and y=0.4. For y=0.4, the out-of-phase component is added, and two frequencies are presented (f = 125 H z and 1000 H z in dotted lines). The insert shows the variation of T_c with the M n O M n bond angle.



Fig. 2 { Tem perature dependence of (a) zero magnetic eld resistivity (log. scale) and (b) magnetoresistance for $H = 5 \ 10^4$ O e; the magnetic eld is perpendicular to current.



Fig.3 { Out-ofphase component of the ac-susceptibility for y=0.4. H_{ac}=10e, and f=125 Hz. A dc eld H_{dc} is superimposed. The inset shows the frequency dependence of the low temperature peak for H_{ac}=10e and H_{dc}=10000e.



Fig. 4 { Relaxation rate S (t) at T = 50K (a) and T = 110K (b) for di erent applied probing elds; $t_w = 1000$ s. The insert shows the waiting time dependence of S (t) for both temperatures; three di erent waiting times are used: $t_w = 100s$ (open circles), 1000s (line) and 10000s (led circles); H_{dc}=0.1 Oe.