

Fulde-Ferrell-Larkin-Ovchinnikov state in d -wave superconductors

K. Maki ^a H. Won ^{b,*},¹

^a*Department of Physics and Astronomy, University of Southern California, Los Angeles, CA 90089-0484, USA*

^b*Department of Physics, Hallym University Chunchon 200-702, South Korea*

Abstract

The Fulde-Ferrell-Larkin-Ovchinnikov (FFLO) state can be found in layered d -wave superconductors such as high T_c cuprates and κ -(ET)₂ salts in a planar magnetic field. We show the superconducting order parameter forms two dimensional crystalline lattice in the FFLO state for d -wave superconductors. Also the quasi-particle density of states and the thermodynamics of FFLO state are constructed. Therefore STM or NMR will provide a definitive test for the existence of the FFLO state.

Key words:

d -wave superconductivity, Layered materials, Fulde-Ferrell-Larkin-Ovchinnikov state

When the Pauli paramagnetism or the Zeeman term dominates the orbital effect, the superconducting state in a magnetic field enters in a new state where the superconducting order parameter varies periodically in space[1,2]. However the realization of this condition is extremely difficult in the classical s -wave superconductors. First of all the system has to be in the superclean limit where the quasiparticle mean free path l is much longer than the coherence length ξ . Second the system has to have the Ginzberg Landau parameter κ much larger than the unity. Indeed these two conditions appear to be met readily in d -wave superconductors like high T_c cuprate superconductors and organic superconductors like κ -(ET)₂ salts and λ -(ET)₂ salts [3].

* Corresponding Author: Dept. of Physics, Hallym University, Chunchon 200-702, South Korea. Phone:(+82)-(33)240-1417, Fax:(+82)-(33) 254-2873, Email:hkwon@sun.hallym.ac.kr

¹ HW acknowledges the support from the Korean Science and Engineering Foundation(KOSEF) through the Grant No. 1999-2-114-005-5.

Earlier we have shown that the region of the Fulde-Ferrell-Larkin-Ovchinnikov (FFLO) state in d -wave superconductors is much more extended than the corresponding one in s -wave superconductors [4]. In the mean time a possible observation of the FFLO state in κ -(BEDT-TTF)₂Cu(NCS)₂ in a planar magnetic field has been reported [3]. Indeed in the pure Pauli limiting case we expect the upper critical field $H_{c2}(t, \theta)$ is independent of the direction of the magnetic field as long as \mathbf{H} lies in the conducting plane [4].

The object of this paper is to extend the earlier analysis to construct the free energy associated with FFLO state. Indeed in the limit of $T \rightarrow 0$, following Larkin and Ovchinnikov we can show that the two dimensional periodic solution $\Delta(\mathbf{r}) \sim \cos(qx) + \cos(qy)$ is the most stable. Also we obtain simple expression of the quasiparticle density of states, the specific heat, the magnetic susceptibility and T_1^{-1} in NMR which should be readily accessible experimentally.

In Fig.1 we show the magnetic phase diagram of d -wave superconductors. As is readily seen, the direction of \mathbf{q} in the most stable FFLO state switches from $\mathbf{q} \parallel (1, 0, 0), (0, 1, 0)$, etc. (the direction of 4 maximum gaps) in the limit of $T = 0$ to $\mathbf{q} \parallel (1, 1, 0), (1, -1, 0)$, etc. (the direction of 4 nodes) for $T > 0.05 T_c$. In the first region (i.e. \mathbf{q} is the direction of one of 4 maximum gaps) $q = 2\frac{h}{v_F}$ at $T = 0$, where $h = \mu_B H$, while in the second region (i.e. $\mathbf{q} \parallel (1, 1, 0)$, etc.) $q \simeq 2.42\frac{h}{v_F}$. At $T = 0$ K the upper critical field is given by $h_0 = \frac{\pi}{\gamma} T_c \exp(\frac{1}{4} \cos(4\theta))$ with $q = 2\frac{h}{v_F}$ and $\theta = 0$, where θ is the angle between \mathbf{q} and the a -axis. Here γ is the Euler constant.

Then following [2] we construct the equation for $\Delta(\mathbf{r})$, assuming that $\Delta(\mathbf{r}) = \sum_m \Delta_m e^{i\mathbf{q}_m \cdot \mathbf{r}}$, as

$$\Delta_n^* = \sum_m \{ (2 - \delta_{mn}) |\Delta_m|^2 \Delta_n \hat{J}(q_n, q_m) + (1 - \delta_{mn} - \delta_{-mn}) \Delta_m^* \Delta_{-m}^* \Delta_n J(q_n, q_m) \} \quad (1)$$

where $J(q_n, q_m)$ and $\tilde{J}(q_n, q_m)$ are defined in the same way as in [2]. But here we generalized their treatment to the d -wave superconductivity. Both $J(q_n, q_m)$ and $\tilde{J}(q_n, q_m)$ depend on only angle between \mathbf{q}_m and \mathbf{q}_n . We have $h^2 J(0) = -15.5$, $h^2 J(\pi) = 3/2$, $h^2 J(\pi/2) = 3.0$ and $h^2 \tilde{J}(\pi/2) = 5/6$

Then we can solve for different forms for the lattice. Here are;

- (a) $\Delta(\mathbf{r}) \sim e^{i\mathbf{q} \cdot \mathbf{r}}$, we have $|\Delta|^2 = -0.065 h_0 (h_0 - h)$
- (b) $\Delta(\mathbf{r}) \sim \cos(qx)$, we have $|\Delta|^2 = -0.08 h_0 (h_0 - h)$
- (c) $\Delta(\mathbf{r}) \sim \cos(qx) + \cos(qy)$, we have $|\Delta|^2 = \frac{6}{7} h_0 (h_0 - h)$

Therefore the solution (c) is the only one which is stable in the layered d -wave superconductors. Limiting ourselves to d -wave superconductors in a planar magnetic field, we conclude the two dimensional periodic solution, i.e. 2 di-

mensional square lattice, is the most stable one in the limit $T \rightarrow 0$ K. This is in a sharp contrast to the case of 3D s -wave superconductors where a stripe-like state is favored [2].

The quasiparticle density of states in the vicinity of $h = h_0$ is given by

$$N(E)/N_0 \simeq 1 + \frac{\Delta^2}{4} \sum_{\pm} \left\langle \frac{\cos^2(2\phi)}{[E \pm h + \frac{vq}{2} \cos \phi]^2} \right\rangle = 1 + \frac{\Delta^2}{2h^2} J\left(\frac{E}{h}, \frac{vq}{2h}\right) \quad (2)$$

and

$$J(\varepsilon, p) = \frac{1}{2} \sum_{\pm} \text{Re} \left\{ \frac{|\varepsilon \pm 1|}{[(\varepsilon \pm 1)^2 - p^2]^{3/2}} + \frac{4}{p^4} \left[(3(\varepsilon \pm 1)^2 - \frac{p^2}{2}) - (3(\varepsilon \pm 1)^2 - 2p^2) \frac{|\varepsilon \pm 1|}{\sqrt{(\varepsilon \pm 1)^2 - p^2}} \right] \right\} \quad (3)$$

and

$$J(0, p) = \text{Re} \frac{1}{(1 - p^2)^{3/2}} + \frac{4}{p^4} \left(3 - \frac{p^2}{2} - (3 - 2p^2) \text{Re} \frac{1}{\sqrt{1 - p^2}} \right) \quad (4)$$

In Fig.2 we show the density of state for $p(= vq/2h) = 1, 1.1$ and 1.21 . As readily seen from Eq.(2) $N(E)$ diverges for $E = (p-1)h$ and $E = (p+1)h$ where $p = vq/2h$ for $p \geq 1$. When $p = 1$, $N(E)$ diverges at $E = 0$ and $E = \pm 2h$. On the other hand when $p > 1$, the density of states at Fermi energy is given by

$$N(0)/N_0 = 1 + 2\left(\frac{\Delta}{h}\right)^2 p^{-4} \left(3 - \frac{p^2}{2} \right) \quad (5)$$

$N(0)$ can be accessible through the spin susceptibility at $T = 0$ K, $\chi/\chi_n = N(0)/N_0$, or the nuclear spin lattice relaxation rate at $T = 0$ K, $T_1^{-1}/T_{1n}^{-1} = (N(0)/N_0)^2$ etc. It is shown in the inset of Fig.2. Also for $p > 1$, $N(E)$ has two peak at $E = (p-1)h$ and $E = (p+1)h$. These peaks should be detectable by STM for example. Therefore the presence of 2 peaks provides a clear sign of FFLO in d -wave superconductors.

References

- [1] P. Fulde and R. A. Ferrell, Phys. Rev. 185 (1964) A550.
- [2] A.I. Larkin and Yu. N. Ovchinnikov, Sov. Phys. JETP 20 (1965) 762.




Fig. 1. The phase diagram of FFLO state in d -wave superconductor. The solid line describes the critical magnetic field for $\mathbf{q} \parallel (1,0,0)$, while the broken line for $\mathbf{q} \parallel (1,1,0)$. The dotted line is the 1st order transition line for the uniform state. Δ_{0d} is the d -wave superconducting order parameter at $T = 0$.

[3] M.S. Nam et al., J. Phys. Cond. Mat. 11 (1999) L477; J.Singleton et al., cond-mat/0105335.

[4] K. Maki and H. Won , Czech. J. Phys. 46, S2 (1996) 1033.




Fig. 2. The density of state in Eq.(2) for $\frac{vq}{2h}(\equiv p) = 1, 1.1$ and 1.21 is shown. $J(0, p) = 2h^2/\Delta^2(N(0)/N_0 - 1)$ is shown in the inset.