

Comment on "History Effects and Phase Diagram near the Lower Critical Point in  $\text{YBa}_2\text{Cu}_3\text{O}_7$  Single Crystals":

A lower critical point  $B_{lc}$  of the first order transition line  $B_m(T)$  signaled by a magnetization jump often appears in  $\text{YBa}_2\text{Cu}_3\text{O}_7$  (YBCO) at a magnetic field in tesla range, for example, as a result of enhanced extrinsic point disorder [1]. Recently, Zhukov et al. [2] have found in their magnetization data the presence of  $B_{lc}$  and of a history effect in lower fields than  $B_{lc}$ . To try to explain  $B_{lc}$  increasing [2,3] with decreasing oxygen deficiency acting as an extrinsic pinning disorder, they have invoked an intrinsic pinning disorder, of electronic origin, increasing with decreasing  $\kappa$  by assuming  $B_{lc}$  as well as the upper critical point  $B_{uc}$  to be induced by some (static) disorder. However, since both  $B_{uc}$  and  $B_{lc}$  decrease with increasing  $\kappa$  [3], a comprehensive understanding of the phase diagram based on the argument in ref2 would require such an unacceptable assumption that  $B_{lc}$  is controlled by the intrinsic disorder, while  $B_{uc}$  is mainly determined by the extrinsic one.

It is well accepted at present that the macroscopic properties in vortex states of real type II superconductors should be described based on the Ginzburg-Landau (GL) model characterized by three material parameters, i.e., the fluctuation strength, anisotropy (dimensionality), and pinning strength. Since a single pinning strength describes possible point-like disorders altogether in GL theory, the doping dependences of  $B_{lc}$  and  $B_{uc}$  cannot be understood consistently even if artificially introducing [2] a couple of different pinning disorders. Below, we briefly point out that the dependences of the critical points on  $\kappa$  [2,3] and on an extrinsic pinning disorder [1] can be explained altogether within the GL theory [4,5] if taking account of the fact that the mass anisotropy and the fluctuation strength ( $\propto T$ ) increase with increasing  $\kappa$ , where  $T$  is the in-plane penetration depth. First, we note that  $B_{uc}$  is generally believed [4] to decrease with increasing an effective pinning strength  $D_{pe}$  (a relative strength of point disorder to the fluctuation strength) which is effectively enhanced by increasing fields. This statement is valid particularly in type II limit where the magnetic screening, important near  $H_{c1}$ , is neglected. Assuming the type II limit in the field range far above  $H_{c1}$  where the two critical points were detected [2,3] in YBCO is safely valid. Rather, in our theory [5], the appearance of  $B_{lc}$  is based on the fact [4] that, in layered systems, the vortex-glass (VG) transition curve  $B_{VG}(T)$  in type II limit can lie above the  $B_m(T)$ -line (defined in clean limit) in lower fields only because of a difference in their  $T$ -dependences. Since the Ohmic resistance vanishes at  $B_{VG}(T)$  possibly corresponding to  $B_p(T)$  in ref2, the  $B_m(T)$ -line in  $B < B_{lc}$  lies within a glass phase. Namely, the superconducting transition in  $B < B_{lc}$  is a continuous VG transition,

and  $B_m(T)$  is not realized there as the thermal first order transition signaled by a jump of reversible magnetization. Up to the lowest order in the bare pinning strength, the resulting lower critical point is estimated as

$$B_{lc}' \propto c_L H_{c2}(0) \left[ \frac{\kappa_0^2 d}{16 \kappa^2 T(0) k_B T_c} - \frac{\kappa_0^4}{d^4} D_{pe}^6 \right]; \quad (1)$$

where  $d$  the layer spacing,  $\kappa_0$  the in-plane coherence length, and  $c_L$  is a constant taking a value between  $10^{-2}$  and  $10^{-3}$ . The inverse of parameter combination in the bracket measures the fluctuation strength per layer. In contrast to  $B_{uc}$ , the primary origin of  $B_{lc}$  decreasing [2,3] with increasing  $\kappa$  is, according to eq.(1), its remarkable dependence on  $\kappa$  and  $T(0)$  both of which increase with increasing  $\kappa$ . Although it is not straightforward to predict a  $B_{lc}$ 's sample dependence because it depends competitively on all of the three material parameters, nevertheless we note that, by assuming  $\kappa \approx 8$  for the fully-oxidized case and, for brevity, other parameters to have no doping dependences,  $B_{lc}$  may stay in tesla range on the overdoped side. Eq.(1) may be insufficient in quantitatively explaining lower  $B_{lc}$  values in optimally doped samples where the higher Landau level fluctuations neglected in obtaining eq.(1) are no longer negligible below 1.7 (T) [6]. Nevertheless, the  $\kappa$ -dependence of eq.(1) is qualitatively consistent not only with the absence (in accessible fields) of  $B_{lc}$  in BSCCO and underdoped YBCO with quite large  $\kappa$ -values but also with a  $\kappa$ -dependence of  $B_{lc}$  suggested from optimally-doped and three overdoped YBCO samples [3].

Further, according to recent works [7], a  $B_{lc}$  of several tesla is present in the parallel field case even in underdoped YBCO. This fact is compatible not with the interpretation invoking an intrinsic disorder [2] negligible in underdoped YBCO but only with the present theory based on the GL model with extrinsic disorder [8].

We are grateful to T. Nishizaki for informative discussion.

Ryusuke Ikeda  
Department of Physics,  
Kyoto University, Kyoto 606-8502, Japan

- 
- [1] L.M. Paulius et al., Phys. Rev. B 61, R11910 (2000).
  - [2] A.A. Zhukov et al., Phys. Rev. Lett. 87, 017006 (2001).
  - [3] T. Nishizaki et al., Physica (Amsterdam) C 341-348, 957 (2000); T. Nishizaki, private communication.
  - [4] R. Ikeda, J. Phys. Soc. Jpn. 65, 3998 (1996).
  - [5] R. Ikeda, J. Phys. Soc. Jpn. 70, 219 (2001); in Studies of High Temperature Superconductors (ed. by A.N. Narlikar, Nova Science Publishers, 2001) Vol.37, Ch.2.
  - [6] R. Ikeda, J. Phys. Soc. Jpn. 64, 1683 (1995).

- [7] B. Lindqvist et al, Phys. Rev. B 64, 060503 (2001); S. N. Gordeev et al, Phys. Rev. Lett. 85, 4594 (2000).
- [8] R. Ikeda, cond-mat/0110194.