

uid density of the dSC coexisting with the dDW order was previously studied [13, 14], but the question of the renormalization factor Z_e was not addressed. Although we studied a specific system, our results can be applied to more general situation where a superconducting order coexists with another order parameter with the same internal symmetry.

In the next section, we compute the current-current correlation function in the coexisting dSC and dDW states. Those who are not interested in the details can skip the next section and jump to section III. In the third section, we provide the analytical expression of and extract the value of Z_e . We compare our results with the consequences of other existing theories and discuss further implications in the final section.

II. SUPERFLUID DENSITY IN THE COEXISTING dDW AND dSC STATES

In the phase where the dSC and dDW coexist, the quasiparticles keep the Dirac spectrum as the case of dSC. In particular, when the chemical potential is zero or $< T_{min}(0; W_0)$, the low energy nodal spectrum is well described by changing the gap velocity v to $v = \frac{v_F}{\sqrt{1 + v_W^2}}$ where $v_W = W_0 a = \frac{2}{3}$ and W_0 is the maximum value of the dDW order parameter. In this case, the gap velocity measured in ARPES will correspond to v . The density of states will be also modified, but in a trivial fashion; v is replaced by v . Thus one may expect that the coefficient of the linear temperature dependence of the superfluid density is simply given by $\rho_s = (\ln 2)v_F = (2/3)v$. If this is the case, we will not be able to extract an independent information about v_W and practically $Z_e = 1$; experiments will not be able to tell the difference between the simple dSC state and the coexisting dSC/dDW states. We show below that this is not the case. Z_e has an independent information about v_W and in general it is not unity. The deviation from $Z_e = 1$ is in fact due to the existence of the dDW order parameter.

We derive the result described above by directly computing the current-current correlation function in a mean-field theory. We start from the mean-field Hamiltonian given by

$$H = \sum_{\mathbf{k}} \left(\epsilon_{\mathbf{k}} - \mu \right) c_{\mathbf{k}}^\dagger c_{\mathbf{k}} + \sum_{\mathbf{k}} iW_{\mathbf{k}} c_{\mathbf{k}}^\dagger c_{\mathbf{k}+\mathbf{Q}}; \quad (3)$$

The paramagnetic contribution contains the information about Z_e and can be obtained from

$$\chi_{xx}(\mathbf{q}; i\omega) = \frac{1}{T} \sum_{\mathbf{k}} \sum_{\mathbf{k}'} \sin k_x \sin(k_x + k_y) \text{Tr} [G(\mathbf{k}; i\omega_n) (\gamma_3 I) G(\mathbf{k} + \mathbf{q}; i\omega_n + i\omega_m) (\gamma_3 I)] \\ + \frac{1}{T} \sum_{\mathbf{k}} \sum_{\mathbf{k}'} \sin k_x \sin(k_x + k_y) \text{Tr} [G(\mathbf{k}; i\omega_n) (\gamma_2 \gamma_3) G(\mathbf{k} + \mathbf{q}; i\omega_n + i\omega_m) (\gamma_2 \gamma_3)]; \quad (12)$$

where

$$G^{-1}(\mathbf{k}; i\omega_n) = i\omega_n I + \epsilon_{\mathbf{k}} \gamma_3 \gamma_2 + W_{\mathbf{k}} \gamma_2 I + \epsilon_{\mathbf{k}} \gamma_3 \gamma_1; \quad (13)$$

$$+ \sum_{\mathbf{k}} \left(\epsilon_{\mathbf{k}} - \mu \right) c_{\mathbf{k}}^\dagger c_{\mathbf{k}} + \sum_{\mathbf{k}} iW_{\mathbf{k}} c_{\mathbf{k}}^\dagger c_{\mathbf{k}+\mathbf{Q}}; \quad (3)$$

where

$$\epsilon_{\mathbf{k}} = \frac{t}{2} (\cos k_x + \cos k_y); \quad (4)$$

$$W_{\mathbf{k}} = \frac{W_0}{2} (\cos k_x - \cos k_y); \quad (5)$$

$$W_{\mathbf{k}} = \frac{W_0}{2} (\cos k_x - \cos k_y); \quad (6)$$

Here $\epsilon_{\mathbf{k}}$ and $iW_{\mathbf{k}}$ are the order parameters of the dSC and dDW respectively. Using the Nambu basis defined as follows,

$$\Psi_{\mathbf{k}} = (c_{\mathbf{k}}^\dagger, c_{\mathbf{k}+\mathbf{Q}}^\dagger, c_{\mathbf{k}}, c_{\mathbf{k}-\mathbf{Q}}); \quad (7)$$

the current operator can be written as

$$j_x(\mathbf{q}) = \frac{t}{2} \sum_{\mathbf{k}} \sin(k_x + q_x) \Psi_{\mathbf{k}}^\dagger (\gamma_3 I) \Psi_{\mathbf{k}+\mathbf{q}} \\ + iW_0 \sum_{\mathbf{k}} \sin(k_x + q_x) \Psi_{\mathbf{k}}^\dagger (\gamma_2 \gamma_3) \Psi_{\mathbf{k}+\mathbf{q}}; \quad (8)$$

where $\gamma_i = \sigma_i$. Here σ_i 's and τ_i 's are the Pauli matrices and $i, j = 1, 2, 3$.

The superfluid density can be computed from the current-current correlation function, [15]

$$\rho_s(T) = \frac{1}{h} K_x i \lim_{\omega \rightarrow 0} \lim_{q \rightarrow 0} \chi_{xx}(\mathbf{q}; i\omega); \quad (9)$$

where $h K_x i$ is the diamagnetic contribution and $\chi_{xx}(\mathbf{q}; i\omega)$ is the paramagnetic current-current correlation function. The diamagnetic part can be computed as

$$h K_x i = \sum_{\mathbf{k}} \frac{\epsilon_{\mathbf{k}} + W_{\mathbf{k}}}{\epsilon_{\mathbf{k}}} \sin k_x \\ - \frac{k_x}{E_{1k}} \tanh \frac{E_{1k}}{2T} + \frac{k_x + W_{\mathbf{k}}}{E_{2k}} \tanh \frac{E_{2k}}{2T}; \quad (10)$$

where

$$E_{1k;2k} = \frac{q}{\sqrt{(\epsilon_{\mathbf{k}})^2 + \frac{q^2}{4}}}; \quad (11)$$

Here $\omega_m = 2m T$ and $\omega_n = (2n + 1) T$ are the bosonic and fermionic Matsubara frequencies. Notice that the cross-terms proportional to ω_0 cancel out each other.

After the frequency sum, the correlation function has the following form. The first term, χ_{xx}^t , of Eq.12 which comes from the conventional current proportional to t is obtained as follows by taking $\omega \rightarrow 0$ first and $q \rightarrow 0$ later.

$$\begin{aligned} \chi_{xx}^t = & \sum_k \frac{t^2 \sin k_x \sin (k_x + q_k)}{2} \left[1 + \frac{A_1}{E_{1k} E_{1k+q}} \frac{2W_k^2}{2} \right] + \frac{B_1}{E_{1k} E_{1k+q}} \frac{f(E_{1k+q})}{E_{1k+q}} \frac{f(E_{1k})}{E_{1k}} \\ & + \frac{1}{E_{1k} E_{1k+q}} \frac{A_1}{2} \frac{2W_k^2}{2} \left[1 + \frac{B_1}{E_{1k} E_{1k+q}} \frac{f(E_{1k+q}) + f(E_{1k})}{E_{1k+q} + E_{1k}} \right] \\ & + \frac{1}{E_{2k} E_{2k+q}} \left[1 + \frac{A_2}{2} \frac{2W_k^2}{2} \right] + \frac{B_2}{E_{2k} E_{2k+q}} \frac{f(E_{2k+q})}{E_{2k+q}} \frac{f(E_{2k})}{E_{2k}} \\ & + \frac{1}{E_{2k} E_{2k+q}} \frac{A_2}{2} \frac{2W_k^2}{2} \left[1 + \frac{B_2}{E_{2k} E_{2k+q}} \frac{f(E_{2k+q}) + f(E_{2k})}{E_{2k+q} + E_{2k}} \right] ; \end{aligned} \quad (14)$$

where $f(x) = 1/(e^{x/T} + 1)$ is the Fermi function and

$$\begin{aligned} A_{1/2} &= \frac{2}{k} + \frac{2}{k} W_k^2 + 2 \frac{2}{k}; \\ B_{1/2} &= \frac{2}{k} W_k^2 - k; \end{aligned} \quad (15)$$

On the other hand, the second term, χ_{xx}^w , of Eq.12 comes from the additional contribution to the current due to the existence of the dDW order parameter. After taking $\omega \rightarrow 0$ first and $q \rightarrow 0$ later, we get

$$\begin{aligned} \chi_{xx}^w = & \sum_k \frac{W_0^2 \sin(k_x) \sin(k_x + q_k)}{2} \left[1 + \frac{A_1^0}{E_{1k} E_{1k+q}} + \frac{2W_k^2}{2} \right] + \frac{B_1}{E_{1k} E_{1k+q}} \frac{f(E_{1k+q})}{E_{1k+q}} \frac{f(E_{1k})}{E_{1k}} \\ & + \frac{1}{E_{1k} E_{1k+q}} \frac{A_1^0}{2} + \frac{2W_k^2}{2} \left[1 + \frac{B_1}{E_{1k} E_{1k+q}} \frac{f(E_{1k+q}) + f(E_{1k})}{E_{1k+q} + E_{1k}} \right] \\ & + \frac{1}{E_{2k} E_{2k+q}} \left[1 + \frac{A_2^0}{2} \frac{2W_k^2}{2} \right] + \frac{B_2}{E_{2k} E_{2k+q}} \frac{f(E_{2k+q})}{E_{2k+q}} \frac{f(E_{2k})}{E_{2k}} \\ & + \frac{1}{E_{2k} E_{2k+q}} \frac{A_2^0}{2} \frac{2W_k^2}{2} \left[1 + \frac{B_2}{E_{2k} E_{2k+q}} \frac{f(E_{2k+q}) + f(E_{2k})}{E_{2k+q} + E_{2k}} \right] ; \end{aligned} \quad (16)$$

where

$$A_{1/2}^0 = \frac{2}{k} + \frac{2}{k} + W_k^2 - 2 \frac{2}{k}; \quad (17)$$

Therefore, the superfluid density can be obtained from Eq.9, where $\chi_{xx} = \chi_{xx}^t + \chi_{xx}^w$.

III. VALUE OF THE "QUASIPARTICLE CHARGE" FROM SUPERFLUID DENSITY

At low temperatures, the leading paramagnetic contribution comes from the nodal quasiparticles and we can obtain the low energy quasiparticle dispersion by expanding ϵ_k near ϵ_F , and ϵ_k, W_k near the node as follows.

$$\begin{aligned} \epsilon_k &= v_F p_+; \\ \epsilon_k &= v_F p_-; \\ W_k &= v_W p_-; \end{aligned} \quad (18)$$

where $p_+ = (p_x + p_y)/\sqrt{2}$ and $p_- = (p_x - p_y)/\sqrt{2}$ with the momentum p , measured from k_F . Here, $v_F = \partial \epsilon / \partial p$,

$v_- = v_0 a = \sqrt{2} p_-$, and $v_W = W_0 a = \sqrt{2} p_-$. When $T = 0$ or $T < T_c$, the quasiparticle dispersion can be well described by

$$\epsilon_{1k/2k}^2 = v_F^2 p_+^2 + (v^2 + v_W^2) p_-^2; \quad (19)$$

Notice that the corresponding density of states has the following form.

$$N(\epsilon) = \frac{\epsilon}{2 v_F \sqrt{v^2 + v_W^2}}; \quad (20)$$

Therefore, the specific heat as well as the measured gap velocity in ARPES will be given by the combination of v_W and v through $\sqrt{v^2 + v_W^2}$. Now it is clear that the leading linear temperature dependence of the superfluid density comes from the term with $d\epsilon(E_{1k})/d\epsilon(E_{1k})$ factor. The coefficient of the linear temperature dependence, ρ_s , is obtained as

$$\rho_s = \frac{\ln 2}{2} \frac{v_F}{\sqrt{v^2 + v_W^2}} \left[1 - \frac{v_W^2}{2(v^2 + v_W^2)} \right] + O\left(\frac{W_0^2}{T^2}\right); \quad (21)$$

Comparing Eq.21 and Eq.2, and replacing v by the measured gap velocity, $\frac{v}{\sqrt{v^2 + v_W^2}}$, we find

$$Z_e^2 = 1 - \frac{v_W^2}{2(v^2 + v_W^2)}; \quad (22)$$

where we neglect $O(W_0^2 = t^2)$ terms. From the above result, one can easily see that $1=2 - Z_e^2 \rightarrow 1$. If $W_0 \rightarrow 0$, then $Z_e^2 \rightarrow 1=2$, while in the opposite case $W_0 \rightarrow W_0$ or $W_0 \rightarrow 0$, we get $Z_e^2 \rightarrow 1$. Therefore, Z_e varies from $1=\sqrt{2}$ ($= 0.71$) to 1 which is curiously close to the values in cuprates obtained by Ioffe and Millis [1].

In the discussion above, we assumed $T < T_c$. In the opposite limit, $T > T_c$, the low energy quasiparticle dispersion is better described by

$$E_{1k}^2 = (v_F p_x)^2 + (v p_y)^2 \quad (23)$$

which does not have any information about W_k , the dDW order parameter. This is due to the fact that the quasiparticles recognize the presence of the dDW gap only when their energy scale becomes larger than the chemical potential. Carrying out the explicit computation of the current-current correlation function, we verified that the coefficient of the linear temperature dependence of the superfluid density is given by Eq.2 with $Z_e = 1$. [14] Therefore, there is a cross-over in the value of Z_e to unity when $T > T_c$ while $Z_e \neq 1$ for $T < T_c$. At the half-doping ($x = 0$), Z_e is in general not unity. At any rate, if x is smaller than T_c in the experimentally relevant temperature range, the value of Z_e is given by Eq.22.

IV. CONCLUSION

In the strong coupling regime, the coupling between the supercurrent and the quasiparticles can be strongly

renormalized by quasiparticle interactions and lead to the deviation of Z_e from the BCS value ($Z_e = 1$). Here we show that the deviation from $Z_e = 1$ can also occur in the weak coupling regime when the superconducting order coexists with an additional order parameter with the same internal symmetry. We have shown that in the case of the coexisting dSC and dDW states, the "quasiparticle charge" is given by $Z_e = 1 - \frac{v_W^2}{2(v^2 + v_W^2)}$ when the chemical potential is zero or $< T_c$, where v_W and v are the gap velocities determined by the maximum gaps of the dDW and dSC order parameters. Thus Z_e varies from $1=\sqrt{2}$ to 1. The deviation of Z_e from the unity is a good measure of the additional coexisting order parameter. Our result of $Z_e \neq 1$ is also applicable to the systems where a superconducting order parameter coexists with another order parameter with the same internal symmetry; e.g., p-wave superconductor coexisting with p-density wave, although the expression of Z_e would be different for different systems.

Our results suggest that the determination of the value of Z_e alone will not sharply distinguish two possibilities; Mott physics and the existence of a hidden or an additional order parameter. However, if there exists a superconductor far away from a Mott insulator while it exhibits $Z_e < 1$, one would strongly suspect that there might exist a hidden order parameter. The direct relevance of our results for the coexisting dSC and dDW states to cuprates has to be discussed in conjunction with other experimental data and it is beyond the scope of this paper.

Acknowledgments: This work was supported in part by Canadian Institute for Advanced Research (H.Y.K. and Y.B.K.) and Alfred P. Sloan Foundation (Y.B.K.).

-
- [1] L.B. Ioffe and A.J. Millis, cond-mat/0112509
[2] A.I. Larkin, JETP 14, 1498 (1964).
[3] A.J. Leggett, Phys. Rev. 140, A1869 (1965).
[4] It was proposed that the d-density wave (dDW) may exist in underdoped cuprates as a "hidden order parameter" and may be responsible for the pseudogap phenomena. [5, 6, 7]
[5] S. Chakravarty, B. Laughlin, D. Morr, and C. Nayak, Phys. Rev. B 63, 94503 (2001).
[6] S. Chakravarty and H.-Y. Kee, Phys. Rev. B 61, 14821 (2000).
[7] The staggered flux phase was first discussed in I. A. A. Eck and J.B. Marston, Phys. Rev. B 37, 3774 (1988)
[8] P.A. Lee and X.-G. Wen, Phys. Rev. Lett. 78, 4111 (1997).
[9] X.-G. Wen and P.A. Lee, Phys. Rev. Lett. 80, 2193 (1998).
[10] Y. Uemura et al., Phys. Rev. Lett. 62, 2317 (1989).
[11] A.J. Millis, S.M. Girvin, L.B. Ioffe, and A.I. Larkin, J. Phys. Chem. Solids 59, 1742 (1998).
[12] G.K. Othman and J. Liu, Phys. Rev. B 38, 5142 (1988).
[13] S. Tewari, H.-Y. Kee, C. Nayak, and S. Chakravarty, Phys. Rev. B 64, 224516 (2001).
[14] Q.H. Wang, J.H. Han, and D.H. Lee, Phys. Rev. Lett. 87, 077004 (2001); They discussed the behavior of ρ and concluded that it has the same form as that of dSC. We showed that ρ has a different form when $T = 0$ or $T < T_c$. We believe that their conclusion of diverging ρ as $T \rightarrow 0$ is not correct because the upper cutoff of the Dirac dispersion is given by μ , thus the linear temperature dependence occurs only when $T < \mu$. As μ goes to zero, the linear temperature dependence of the superfluid density simply disappears.
[15] See for example, J. R. Schrieffer, "Theory of Superconductivity" (Benjamin/Cummings, Reading, Massachusetts, 1964).