## Theory of H alf M etal-Superconductor H eterostructures

M. Eschrig<sup>1</sup>, J. Kopu<sup>1</sup>, J. C. Cuevas<sup>1</sup>, and Gerd Schon<sup>1;2</sup>

<sup>1</sup> Institut fur Theoretische Festkorperphysik, Universitat Karlsruhe, 76128 Karlsruhe, Germany

<sup>2</sup>Forschungszentrum Karlsruhe, Institut fur Nanotechnologie, 76021 Karlsruhe, Germany

(D ated: June 17, 2002)

W e investigate the Josephson coupling between two singlet superconductors separated by a halfm etallic magnet. The mechanism behind the coupling is provided by the rotation of the quasiparticle spin in the superconductor during relation events at the interface with the half metal. Spin rotation induces triplet correlations in the superconductor which, in the presence of surface spin- ip scattering, result in an indirect Josephson e ect between the superconductors. W e present a theory appropriate for studying this phenom enon and calculate physical properties for a superconductor/half metal/superconductor (S/HM /S) heterostructure.

PACS num bers: PACS num bers: 74.50.+ r,73.40.-c,73.63.-b,74.80Dm

Introduction: The interplay between superconductivity and spin-polarized m aterials has potential applications in the emerging eld of spin electronics. For this purpose, a high degree of spin polarization of the m aterials in contact with superconducting regions is desirable. The recently discovered half m etals are ideal m aterials in this respect [1]. In half m etals electronic bands exhibit insulating behavior for one spin direction and m etallic behavior for the other. They are thus com pletely spin-polarized m agnets. Half m etallic behavior has been found experim entally in the m anganese perovskite  $La_{0:7}Sr_{0:3}M nO_3$ [2, 3] and in CrO<sub>2</sub> [4]. The perovskite is particularly interesting because of its ability to form high-quality heterostructures with high-T<sub>c</sub> cuprate superconductors [5].

The superconducting proxim ity e ect in spin-polarized m aterials has attracted considerable attention recently in the context of superconductor/ferrom agnet heterostructures [6, 7, 8, 9, 10, 11]. The singlet pairing am plitude shows oscillations with a wave vector m atching the spin splitting of the Ferm i wave vectors in the ferrom agnet [11, 12]. The magnitude of this proxim ity e ect decreases with increasing spin polarization. In the extrem e case of a completely spin-polarized m aterial the singlet proxim ity e ect is absent. Consequently, the Josephson current between two singlet superconductors separated by a half m etal is expected to be exactly zero. In this Letter we show that this is not necessarily the case. W e propose a m echanism which leads to a nonvanishing S/HM /S Josephson e ect.

The indirect Josephson e ect requires the interplay of two separate interface e ects: spin mixing (or spin rotation) and spin-ip scattering. The form er, represented by the phase di erence between waves of opposite spin orientations re ected from a spin-active interface, introduces triplet correlations at the superconducting side of the S/HM boundary. The latter mediates these correlations to the halfm etallic side. To illustrate the spinmixing e ect, consider the re ection of two quasiparticles,  $J^{*}i_{k}$  and  $J^{*}i_{k}$ , from a halfm etallic material (which de nes the spin quantization axis). The re ected am pli-

tudes for opposite spins di er in phase,  $J'i_k = e^{i} = 2J'i_k$ ,  $\#i_k = e^{i = 2} \#i_k$  [13]. In a superconductor, incoming quasiparticles (k) near the interface form pairs with outgoing quasiparticles ( k). As  $J_{i}$  #i<sub>k</sub> #i Tik transe<sup>i</sup> ∄i<sub>k</sub> ]"i<sub>k</sub>, form s under re ection into  $e^{i} J_{k} \# i_{k}$ pairing states near such interfaces are singlet-triplet m ixtures. This property of spin mixing is intrinsic to any spin-active interface. If, additionally, spin- ip scattering is present at the S/HM interface, the resulting triplet am plitudes induce equal-spin pairing correlations in the half metal, leading to an S/HM /S Josephson e ect. Spin-ip scattering is expected to be enhanced e.g. due to local variations of the spin quantization axis [7], or di usion ofm agneticm om ents. The im portance of these processes was pointed out by recent experim ents [14].

The indirect proximity e ect introduced above can also be relevant for strong ferrom agnets. In the conventional description, the dispersions for spin-up and spin-down bands in ferrom agnets are assumed to be identical apart from an energy splitting, given by an elective exchange ekd h [6, 7]. The range of the spin-singlet proximity e ect is drastically reduced by a strong exchange ekd. In contrast, no such suppression occurs in the case of the indirect proximity elect.

Theory: O ur treatment is based on the quasiclassical theory of superconductivity [15]. This theory is form ulated in terms of G reen's functions (propagators) which are matrices in N am bu-G or'kov particle-hole space and in spin space. The quasiclassical propagator,  $\hat{g}(\hat{k};R;)$  depends on energy , position R, and the direction  $\hat{k}$  of the momentum on the Ferm i surface. Its particle-hole diagonal and o -diagonal elements are denoted by spin matrices g and f. The quasiclassical propagator satis es the E ilenberger equation [15]

$$\hat{3}$$
  $\hat{3} + iv_f + iv_f = 0$  (1)

with the Fermi velocity,  $v_f(\hat{k})$ , and the singlet order parameter  $\hat{R}$ ). It is essential for our purpose to determine the spatial variation of the order parameter near

h

the interface region in accordance with the triplet correlations, which decay into the superconducting region on the coherence length scale. In order to ensure current conservation in the whole system we obtain the spatial variation of (R) self-consistently,

$$(R) = \int_{a}^{Z} \frac{d}{2i} hf(\hat{k}; R; ) i_{\hat{k}} \tanh \frac{1}{2T} : (2)$$

The coupling constant and the cut-o energy  $_{\rm c}$  are eliminated in favor of the transition temperature T<sub>c</sub> in the usual manner. The quasiclassical G reen's functions are normalized according to  $\hat{g}^2 = {}^2\hat{1}$  [15].

Boundary conditions: A standard method to treat boundary conditions for spin active interfaces is a scattering matrix formulation [6, 17, 18]. However, for the present problem, where the number of spin channels on one side of the interface di ers from that on the other, it would be necessary to use the form ulation by M illis et al. [17] which is rather involved. For this reason we proceed with an alternative but equivalent approach [20]. It allow sus to derive explicit quasiclassical boundary conditions in term s of an auxiliary G reen's function,  $\hat{g}^0$ , which solves the boundary condition for an impenetrable interface and is easy to obtain. The impenetrable interface is characterized by two surface scattering matrices,  $\hat{S}$  and  $\underline{\hat{S}}$ , on either side of the interface. The resulting propagators on the two sides are denoted by  $\hat{g}^0$  and  $\hat{g}^0$  , respectively. At the boundary, incom ing propagators,  $\hat{g}_{\mathrm{in}}^0$  , are connected with outgoing ones,  $\hat{g}_{out}^0$ , via the surface scattering m atrices by  $\hat{g}_{out}^0 = \hat{S}\hat{g}_{in}^0 \hat{S}^y$  [13]. Particle conservation requires unitarity,  $\hat{S}^{y} = \hat{S}^{1}$ . We include the transmission processes through the interface via an e ective hopping amplitude ^ in a t-m atrix approximation. W e assum e translational invariance in the plane of the interface. The quasiclassical hopping amplitudes from left to right di er in general for incom ing and outgoing quasiparticles. However, the requirem ent of current conservation leads to relations between these elements as shown in Fig. 1.

The quasiclassical t-m atrix equations read

$$\hat{t}_{in} = \hat{\underline{g}}_{out}^{0} \hat{\gamma}^{y} \hat{1} + \hat{g}_{in}^{0} \hat{t}_{in} ; \quad \hat{t}_{out} = \hat{S} \hat{t}_{in} \hat{S}^{y}; \quad (3a)$$

$$\underline{\mathbf{f}}_{\text{out}} = {}^{\text{A}}\mathbf{\hat{g}}_{\text{in}}^{0} \wedge \mathbf{\hat{1}} + \underline{\mathbf{\hat{g}}}_{\text{out}}^{0}\underline{\mathbf{f}}_{\text{out}} ; \quad \underline{\mathbf{\hat{f}}}_{\text{in}} = \underline{\hat{\mathbf{S}}}^{\text{A}}\underline{\mathbf{\hat{f}}}_{\text{out}}\underline{\hat{\mathbf{S}}} : \quad (3b)$$

On each side of the interface, the t m atrix describes the m odi cations of the quasiclassical propagators due to virtual hopping processes to the opposite side. F inally, we express the full propagator in terms of the decoupled solution  $g^0$ , leading to the boundary conditions for incom – ing and outgoing propagators,

$$\hat{g}_{in} = \hat{g}_{in}^{0} + \hat{g}_{in}^{0} + i\hat{1}\hat{f}_{in} \hat{g}_{in}^{0} \quad i\hat{1}; \qquad (4a)$$

$$\hat{g}_{out} = \hat{g}_{out}^0 + \hat{g}_{out}^0$$
 if  $\hat{t}_{out} \hat{g}_{out}^0 + if$ ; (4b)



FIG.1: Scattering geom etry illustrating the scattering channels and the corresponding transfer am plitudes for the model discussed in the text.

and sim ilarly for  $\underline{g}_{in}$  and  $\underline{g}_{out}$  [21, 22]. In the appropriate lim iting cases these boundary conditions reduce to those published previously [16, 17, 18, 19, 20].

For reference, we also present the corresponding full scattering matrix which would enter the boundary conditions of Ref. [17]. W ithout loss of generality it can be written in the form

$$\hat{S} = \begin{array}{ccc} \hat{S}_{11} & \hat{S}_{12} \\ \hat{S}_{21} & \hat{S}_{22} \end{array} = \begin{array}{cccc} \hat{S} & 0 & \hat{r} & \hat{d} & \hat{1} & 0 \\ 0 & \hat{1} & \hat{d}^{y} & \hat{r} & 0 & \hat{S} \end{array}$$
(5)

with the transm ission matrix  $\hat{d} = (1 + 2^{4y})^{1} 2^{4}$ , and the rejection matrices on either side of the interface,  $\hat{r} = (1 + 2^{4y})^{1} (1 - 2^{4y}), \hat{r} = (1 + 2^{4y})^{1} (1 - 2^{4y})$ .

The particle-hole structures of the surface scattering matrix and the hopping amplitude are  $\hat{S} = \text{diag}[S;S]$  and  $^{\circ} = \text{diag}[S^{\gamma} S^{\gamma}]$ . The above equations are for general spin structures. In the following, is a 2x1 spin matrix, S a 2x2 spin matrix, and <u>S</u> a spin scalar.

S/HM /S structure: W e study a heterostructure consisting of a half m etal,  $L_{\rm H} < x < L_{\rm H}$ , between two superconductors,  $L < x < -L_{\rm H}$  and  $L_{\rm H} < x < L$ . We investigate the equilibrium supercurrent due to a phase di erence between the superconductors,  $(L) = (-L)e^{-1}$ .

As mentioned above, band splitting in the interface region results in a relative spin phase for quasiparticles with spin along the quantization axis of the half metal (for quasiparticles with spin in the perpendicular plane the corresponding e ect is a spin rotation around the quantization axis) [13]. This e ect can be described by a scattering matrix  $\hat{S} = \exp(i_z=2)\hat{1}$  at the superconducting side of the interface, where de ness a spin-rotation angle and  $_z$  denotes the Pauli spin matrix [13, 18]. Generally, the value of depends on the angle of in pact, [13] and can approach values of the order of for strong band splitting [23]. For de niteness, we present results for  $= 0.75 \cos .$  On the half metallic side the scattering matrix has no spin structure,  $\hat{S} = \hat{1}$ .

The t-m atrix equations are parameterized by the hopping amplitude ^ and the scattering matrices  $\hat{S}$ ,  $\hat{S}$ , which are the phenom enological parameters characterizing the interface in our theory. We use =  $(1 + S^y)_0 \cos$ , where  $_0 = ($ ""; #")<sup>T</sup> is determined by the two spin



FIG.2: Self-consistent order parameter and triplet correlations in an S/HM/S heterostructure for a zero junction and a junction. The relative signs of the pairing correlations in the s-wave singlet and three p-wave triplet channels are indicated. A zero junction for the singlet order parameter leads to a relative phase di erence of for the triplet correlations, and vice versa. The calculations are for temperature  $T = 0.05T_c$ , and for  $\#^{*} = "" = 0.7$ .

scattering channels from the superconductor to the halfm etallic spin-up band. W ith this choice the spin rotation during transm ission is half of the spin rotation during reection. The cos factor accounts for the reduced transm ission at large impact angles. We present results for  $_{\#}$ "= "" = 0:7 and 0:1, 2 "" = 1:0, 2L<sub>H</sub> = 3<sub>0</sub> (with the coherence length  $_0$  = v<sub>f</sub>=2 T<sub>c</sub>), L  $_{L_H}$ , and cylindrical Ferm i surfaces (calculations using spherical Ferm i surfaces lead to sim ilar results). We iterate Eqs. (1) and (2) until self-consistency is achieved, with the boundary conditions (3) and (4) at the two interfaces. All our calculations are in the clean lim it.

In Fig.2 we present the spatial modulation of the singlet order parameter and the triplet pairing correlations for an S/HM /S heterostructure. We compare results for a zero junction ( = 0) and a junction ( = ). The spin-rotation e ect at the superconducting side of the interface leads to local triplet correlations in the superconductor of the form  $f_{"\#} + f_{\#"}$ . We quantify the triplet pairing correlations by the integral

$$F_{tripl}(x) = \int_{a}^{2} \frac{d}{2i} h(\hat{k}) f(\hat{k};x;)_{k} \tanh \frac{1}{2T} ; (6)$$

where  $(\hat{k})$  projects out the p-wave pairing amplitude, and is equal to the cosine of the angle between  $\hat{k}$  and the surface normal. Spin- ip scattering induces a F<sub>""</sub> amplitude in the half metal, and leads to both F<sub>""</sub> and F<sub>##</sub> amplitudes in the superconductor. The correlations are shown in Fig. 2 for all three spin-triplet channels. Triplet correlations extend into the superconductor up to a few coherence lengths from the interface, leading to



FIG.3: Critical Josephson current density as a function of tem perature for an S/HM /S heterostructure. The two curves are for  $_{\#^{*}}=_{""}=0.1$  (dashed) and  $_{\#^{*}}=_{""}=0.7$  (full lines). The inset shows the current-phase relationships for  $_{\#^{*}}=_{""}=0.7$  for tem peratures  $T=T_{\rm c}=0.05$  (dashed), 0.2;0.3;0.4;0.5 (full lines from bottom to top). The unit is the Landau critical current density  $J_{\rm L}=ev_{\rm f}N_{\rm f}$  0, with the zero tem perature bulk superconducting gap  $_{0}=1.76T_{\rm c}$ .

a suppression of the singlet order param eter near the interface. We also show schem atically the s and p orbitals for a zero junction and a junction. The alignment of the p orbitals is determined by the direction of the surface norm al. A s a consequence, the relative sign between the p orbitals is opposite to that of the s orbitals. A s will be shown below, this leads to a reversal of the current direction from that expected for a superconductor/norm al m etal/superconductor junction.

W e now turn to the halfm etallic region in Fig. 2. The spatial distribution of the proxim ity-induced F<sup>\*\*\*</sup> am plitude shows a sign change at x = 0 in the case of zero junction, but not for a junction. As a result, the junction is expected to be more stable than the zero junction. Indeed, our num erical calculations show that the junction corresponds to the free-energy minimum for all tem peratures. The equal-spin correlations decay slow ly into the halfmetal, e.g. F<sup>\*\*\*</sup> (x = 0) / 1=L<sub>H</sub> in the junction. This behavior is similar to that observed in norm alm etal/superconductor structures.

In Fig. 3 we show the Josephson critical current as a function of tem perature. The current density,

$$J = \int_{1}^{Z_{1}} d \ln v_{f}(\hat{k}) N_{*}(\hat{k}; )_{\hat{k}} n_{f}(); \qquad (7)$$

is expressed in terms of the angle-resolved density of states at the Fermi surface in the half metal, N  $_{\rm H}$  =

 $N_{\rm f}~\text{Im}~(g_{""})=$  , the electronic charge e, and the Ferm i distribution function  $n_{\rm f}$ . In the inset of Fig. 3 we show the current-phase relationship for di erent tem peratures. The current is negative for a positive phase di erence .



FIG. 4: Density of states at  $T = 0.05T_c$  for quasiparticles with norm alim pact at the half-metallic side of the left interface (x =  $L_H$ ), for a) spin ip rate  $_{\#}$  = "" = 0:1 and phase di erence = 0:5, and b)  $_{\#}$ " = "" = 0:7 and = 0.2. The corresponding Josephson currents are close to the critical values. Shown are both states carrying current in positive (full lines) and negative directions (dashed lines).

For each temperature we determ ine the critical current from the maximum current magnitude in the current-phase relationship. The critical current has a  $(1 \ T=T_c)^2$  dependence near  $T_c$ . This is a consequence of the fact that the order parameter at the interface varies linearly with  $1 \ T=T_c$ , in contrast to the bulk  $(1 \ T=T_c)^{1=2}$  behavior. At low temperatures the critical current passes through a maximum and then decreases again. This anom aly is due to the interplay between current-carrying states, as we proceed to explain.

W e discuss the di erent contributions to the Josephson current coming from the spectral features in the momentum-resolved density of states N. in the half m etal. The total current through the interface is dom inated by quasiparticle trajectories parallel to the surface norm al. In Fig. 4 we com pare the spectrum of such quasiparticles for incom ing and outgoing m om enta at the halfm etallic side of the left interface. We present results for # = = 0:1 and # = = 0:7. In both cases there is a continuum around the chemical potential (= 0). On either side of this continuum there is a gap, followed by either additional continuum branches, or by Andreev bound states. The Andreev bound states in Fig. 4b are closely related to the surface Andreev states discussed in Refs. 18, 23. According to Eq. (7), the current is obtained by multiplying the curves in Fig. 4 with the Ferm i function. At not too low tem peratures the Josephson current is dom inated by the negative-energy features below the continuum at the chemical potential. These features carry current in negative direction, explaining the negative sign of the Josephson current for positive phase di erence. Below a certain tem perature, the corresponding states are fully populated, and the tem perature dependence of the Josephson current is dom inated by the low energy continuum around the chem icalpotential. The current carried by this low -energy band is positive and increases with decreasing tem perature, leading

to the decrease of the magnitude of the critical Josephson current at low temperatures in Fig. 3.

Conclusions: We have presented a theory for half m etal-superconductor heterostructures and have investigated the Josephson coupling through a half-m etallic layer with a thickness of several coherence lengths. The Josephson coupling is induced by triplet pairing correlations in the superconductor. These triplet correlations are coupled to the singlet superconducting order param eter via a spin-rotation e ect, which occurs when quasiparticles in the superconductor are rejected from a spinpolarized m edium . W e have perform ed self-consistent numerical calculations for this problem, and found a lowtem perature anom aly in the tem perature behavior of the critical Josephson current. This anom aly is a robust feature, which is not very sensitive to parameter variations. W e discuss the Andreev excitation spectrum in the half m etallic region, and explain the tem perature variation of the Josephson current in terms of this spectrum.

This work was supported by the Deutsche Forschungsgem einschaft within the Center for Functional Nanostructures.

- W. E. Pickett and J. S. Moodera, Physics Today, 39 (2001).
- [2] J.H. Park et al, Nature 392, 794 (1998).
- [3] R.J. Soulen Jr. et al., Science 282, 85 (1998).
- [4] Y.Jietal, Phys. Rev. Lett. 86, 5585 (2001).
- [5] C.-C.Fu, Z.Huang, and N.-C.Yeh, Phys. Rev. B 65, 224516 (2002).
- [6] M JM.de Jong and C W J.Beenakker, Phys.Rev.Lett. 74,1657 (1995); V J.Falko, A F.Volkov, and C J.Lam – bert, Phys.Rev.B 60, 15394 (1999).
- [7] F S.Bergeret, A F.Volkov, and K B.E fetov, Phys.Rev. Lett.86,4096 (2001); A.K adigrobov, R.I.Skekhter, and M.Jonson, Europhys.Lett.54,394 (2001).
- [8] M.Giroud et al, Phys. Rev. B 58, R11872 (1998).
- [9] V.T. Petrashov et al, Phys. Rev. Lett. 83, 3281 (1999).
- [10] D. Huertas Hemando, Yu.V. Nazarov and W. Belzig, Phys. Rev. Lett. 88, 047003 (2002).
- [11] T.Kontos et al, Phys. Rev. Lett. 89, 137007 (2002).
- [12] A.Buzdin, Phys. Rev. B 62, 11377 (2000).
- [13] T. Tokuyasu, JA. Sauls, and D. Rainer, Phys. Rev. B 38, 8823 (1988).
- [14] S.K reuzer et al, Appl.Phys.Lett.80,4582 (2002).
- [15] G. Eilenberger, Z. Phys. 214, 195 (1968); A. I. Larkin and Y N. Ovchinnikov, Sov. Phys. JETP 28, 1200 (1969).
- [16] A.V. Zaitæv, Sov. Phys. JETP 59, 1015 (1984); A.L. Shelankov, Sov. Phys. Solid State 26, 981 (1984).
- [17] A. M illis, D. Rainer, and J.A. Sauls, Phys. Rev. B 38, 4504 (1988).
- [18] M.Fogelstrom, Phys. Rev. B 62, 11812 (2000).
- [19] M. Eschrig, Phys. Rev. B 61, 9061 (2000); A. Shelankov and M. Ozana, Phys. Rev. B 61, 7077 (2000).
- [20] J.C. Cuevas and M. Fogelstrom, Phys. Rev. B 64, 104502 (2001).
- [21] Current conservation follows from these boundary conditions by verifying  $Tr[^{3}(\hat{g}_{in} + \underline{\hat{g}}_{in} \hat{g}_{out} \underline{\hat{g}}_{out})] = 0.$
- [22] Eqs. (3a) { (4b) also can be used for Keldysh-Green's functions in non-equilibrium Keldysh form alism . M atrix products then include time convolutions.

[23] Yu S.Barash and I.V.Bobkova, Phys. Rev. B 65, 144502 (2002).