

Three component model of pseudogap state for high temperature superconductors

Sergeeva G. G.¹, Vakula V. L.²

¹ National Science Center "K harkov Institute of Physics and Technology", Akademicheskaya st. 1, 61108, K harkov, Ukraine

² B.Verkin Institute for Low Temperature Physics and Engineering of the National Academy of Sciences of Ukraine, 47 Lenin Ave., K harkov 61103, Ukraine

Abstract

For underdoped cuprates HTS three component model of pseudogap state is proposed where it is shown that at $T < T^*$ in the addition to Jahn-Teller small polarons (with total spin 1/2) and holes the zero dimensional superconducting fluctuations are developing in copper-oxygen planes. These fluctuations are the local "hole-Jahn Teller small polaron" pairs with BCS pairing. At $T < T^*$ (T^* is the pseudogap temperature) the crossover of three-dimensional charge to "two-dimensional" one occurs, and the polaron shift of the energy leads to the compensation of Coulomb repulsion between polaron and hole and to their on-site attraction in copper-oxygen planes. Some experimental evidences of the local "hole-polaron" pairing at $T < T^*$ are discussed.

1. Despite of the intensive researches of the nature of high temperature superconductivity (HT superconductivity) the questions about pairing mechanism and about the nature and number of carriers remain open. Today for normal state of underdoped high temperature superconductors (UD HTS) the two-component model of carriers we can consider as firmly established fact: at $T > T^*$ the small polarons and holes are the heavy and light carriers respectively. Here T^* is the temperature of the transition in pseudogap state (PGS) when CuO_2 planes are in stripe state. For normal state ones of the first evidences of coexisting these two carrier types were the measurements of optical conductivity for UD HTS [1-3]. Later the spin susceptibility measurements for $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ [4] let to determine the doping dependence of the part for each carrier, but the polaron state (it is polaron or bipolaron) was undetermined. This question for cuprates HTS is of fundamental importance because namely the existing of Jahn Teller small polarons (JT SP) for doped antiferromagnets (AF) with large values of dielectric constant and strong oscillations of oxygen ions [5] was initial point for HTS searches. At the doping the extra holes are localized on the transition metal ions that leads to the change of their valence and to strong JT distortions. At the doping increase and at the temperature decrease the transition of AF into metal occurs with two carrier types and with the of principle possibility of superconducting transition (SCT) with enough high value of T_c .

Now it is clear that the understanding of the PGS nature at $T > T^* > T_c$ furnish the clue to HT superconductivity. Next two circumstances are the reason for this supposition:

1) the change of the density of state begin at $T = T_c$ and goes on up to T_c ; 2) at $T = T_c$ coherent superconducting state is forming but noticeable change of the density of state does not observe (see refs. in [6]). Under BEC theory for polarons in ref.[6] three component model of PGS was proposed in which bipolarons were the third component. In this paper it is discussed the supposition that at $T \leq T_c$ the BCS pairing states of hole and JT SP are the third component for PGS.

2. For UD HTS the coexisting of JT SP and holes at $T > T_c$ stimulates the interest to the studying the possibility of their pairing. In Refs.[7-8] the possibility of such pairing was shown. At that for HTS the mechanism of the suppression of on-site Coulomb repulsion U for two particles is the main problem. At the first E.K.Kudinov [8] for two component model of carriers show the principle possibility of their on-site attraction: i) JT SPs lead to the band narrowing and to the polaron shift of the energy $E_p = g_{JT}^2/2M\omega^2$, ii) at $(-E_p + U) < 0$ both as the compensation of Coulomb repulsion and so the on-site attraction between the hole and JT SP take place. At that all many particles interactions between the hole and JT SP are exponential renormalized. Here g_{JT} is a elastic constant of JT interactions (JTI) of holes with oscillating oxygen ions. JT SP is a hole in CuO_2 plane bounded by means JTI with complex of two neighboring $\text{Cu}^{+2} + 4\text{O}^{2-}$ "square" with common oxygen ion. The the diagonals of these squares are distorted by Q_2 phonon mode. Total spin of JT SP is equal $1/2$, and spins of two Cu^{+2} are antiparallel (a polaron with parallel spins of two Cu^{+2} is bound three spin polaron bound [9]). As it shown by Kudinov the pairing of hole and JT SP in model BCS leads to SCT in CuO_2 plane with the temperature $T_{cr} = E_p + U/2$. At that the pair "hole-JT SP" is localized by the $\text{Cu} - \text{O}$ complex of JT SP and is local pair with correlation length $\lambda_{ab} \leq 2R_{\text{Cu}-\text{O}}$ ($R_{\text{Cu}-\text{O}}$ is the distance between Cu^{+2} and O^{2-} in CuO_2 plane).

Exponential renormalization of all interactions leads to exponential small contribution in energy of bipolaron pairing relatively with the contribution of the "hole-JT SP" pairs [8]. This means that the bipolaron pairing is realized but for SCT it is not important. But the bipolaron pairing of bound three spin polarons can has crucial meaning in first stage of the stripe forming [10].

3. For UD HTS at incoherent interlayer tunnelling the charge transfer along c-axis is the result of thermal fluctuations $k_B T > t_c^2/t_{ab}$, where t_c and t_{ab} are the probability of the charge transfer along c-axis and in CuO_2 plane, k_B is the Boltzmann constant. At the lowering temperature the thermal fluctuations cut down the interlayer tunnelling, and at $T = t_c^2/(k_B t_{ab})$ the crossover from three-dimensional charge to two-dimensional one occurs. At $T = T_{cr}$ this dimensional crossover is accompanied by pairing JT SP and holes in CuO_2 plane. The measurements of optical conductivity are the convincing evidence of such pairing where it is shown that at T_c the c-axis component of electronic kinetic energy and carriers mass twice increase [11]. The lowering temperature $T < T_c$ leads to the growth of number "hole-JT SP" pairs n_{hp} (the distance between which is greater than their correlation length λ_{ab}), i.e. to zero-dimensional (0D) superconducting fluctuations (SCF) [12-13]. Further lowering temperature leads to the increasing of n_{hp} and λ_{ab} , so that at big enough λ_{ab} local pairs begin overlap and the two transitions occur: at first to two-dimensional (2D) SCF, and at more low temperature to three-dimensional (3D) SCF [12-14]. At that holes number, n_h , and polarons number, $n_p \geq n_h$, are decreasing that is according with the observation of the absence of noticeably change density of states at T_c [6]. For example, at the Hall effect measurements for $\text{YBa}_2\text{Cu}_3\text{O}_{6+x}$ ($T_c = 87\text{K}$) was found out that n_h decreases twice at lowering the temperature from 240K up to 100K :

$n_h(240K) \approx 5.4 \cdot 10^{19} \text{ cm}^{-3}$, and $n_h(100K) \approx 2.7 \cdot 10^{19} \text{ cm}^{-3}$ [15].

The transition to 2D SCF with the dependence $\bar{\epsilon}_{ab}(T) = \bar{\epsilon}_{ab}(T=T_{2D} - 1)^{1/2}$ leads to the semiconducting dependence of the c-axis resistivity with the probability of the charge transfer which is depending on the temperature [14]

$$t_c(T) \propto \frac{\bar{\epsilon}_c^{-2}}{\bar{\epsilon}_{ab}^{-2}}(T=T_{2D} - 1); \quad (1)$$

where T_{2D} is the temperature of the two-dimensional SCT for the isolated CuO_2 plane, $\bar{\epsilon}_c, \bar{\epsilon}_{ab}$ are the values of the correlation lengths at T_{2D} , and E_F is Fermi energy. At the lowering of the temperature $t_c(T)$ decreases, and at

$$t_c(T_c) = T_c = E_F \quad (2)$$

SCT occurs according to the scenario Kats at $T_c > T_{2D}$ [16]: from the beginning two-dimensional crossovers 0D SCF \rightarrow 2D SCF \rightarrow 3D SCF, and then occurs three-dimensional SCT with coherent charge transfer along c-axis [13-15,17]. As we can see from (1) and (2) [10]

$$T_{2D} < T_c \leq \frac{\bar{\epsilon}_c^{-2} E_F T_{2D}}{\bar{\epsilon}_c^{-2} E_F \bar{\epsilon}_{ab}^{-2} T_{2D}} \quad (3)$$

Thus, SCT has two-dimensional character with limited region of three-dimensional SCF. For example, as it was shown from the analysis of the resistivity measurements in single crystal Bi-2212 with $T_c \approx 80K$ [14], the region of (0D SCF + 2D SCF) $\approx 120K$, and the region 3D SCF $\approx 10K$.

4. For HT superconductivity the conclusion about the decisive role of JT-SP qualitatively comes to an agreement with the dependence on the doping of the part of each carriers type relatively of total carriers number: in Ref.[4] it was shown that the value of T_c (at the "hole-JT-SP" pairing $T_c \propto n_h \propto n_p$) amount to T_{cmax} at the concentration 0.15 on ion Cu_{+2} when the part of polarons is 0.6, and the part of holes is 0.4.

The measurements of the resistivity also evidence about the coexistence of carriers and local pairs "hole-JT-SP" [13-15,17] in PGS. The studying of optical conductivity [15,17] shown that interactions of optical pairs with carriers are weak, and the contributions of 0D, 2D and 3D SCF into conductivity are been identified.

One more convincing example of the coexistence of the holes, polarons and local pairs "hole-JT-SP" in PGS is the observation of a doublet structure of two-magnon absorption band at 2.145 eV and 2.28 eV in a metal $\text{LnSYBa}_2\text{Cu}_3\text{O}_{6+x}$ ($x \approx 0.85$), $T_c \approx 87.4K$ [18]. The doublet structure was observed at $T < T_c$ for PGS and for superconducting state (SCS). Its first component with energy $\hbar\omega_{CT} + 3J$ is identical to that which was observed in doped AF with $x = 0.3$, and was caused by polaron two-magnon absorption at interband transition of polaron (here $J \approx 0.13\text{eV}$ is the exchange energy, $\hbar\omega_{CT}$ is transfer energy). As it is known, in metal phase of the sample at $T > T_c$ this component is not observed, and in Ref.[18] at lowering the temperature it is observed only at $T < T_c$ in both PGS and SCS. Second component of the doublet with $\hbar\omega_{CT} + 4J$ is observed only at $T < T_c$. We conjecture that this component was caused by the fulfillment of the condition of the "triple resonance" at polaron two-magnon absorption, similar that at Raman scattering for undoped AF [19-20]. JT-SP absorbs of photon (with energy $\hbar\omega$) and transfer into valence band. Two transfers of the charge with energy t (between Cu^{+2} and

oxygen ion within JT SP complex, there and back) lead to the radiation of two magnons with the frequencies ω_q ; ω_q at the resonance condition

$$\omega = \omega_{CT} + 2t + \omega_q + \omega_q : \quad (4)$$

For UD HTS at $T > T_c$ this condition is not practicable with taken into account the interactions between holes and polarons, but both incoherent holes and polaron two-magnon absorption lead to an essential asymmetry and big width of right hand of two-magnon absorption band (the so-called background): for $YBa_2Cu_3O_{6.1}$ up to $\omega = 3\text{eV}$ [18-20]. At $T < T_c$ holes and part of JT SP n_p n_h are in pairing state, and for unpaired part of polarons $(n_p - n_h)_{T < T_c}$ resonance condition (4) takes place in both PGS and SCS.

The observation of doublet structure of two-magnon absorption band evidences about the existence of the polarons in PGS and SCS, and about essential charge heterogeneity of SCS (the same as for PGS). A doublet structure of two-magnon absorption band for SCS is an indirect evidence of d-wave symmetry of superconducting order parameter for UD HTS as well: at $T < T_c$ some part of unpaired polaron $(n_p - n_h)_{T < T_c}$ percolates through the direction of wave vector where the order parameter is equal zero.

To summarize, in this paper we show that for high temperature superconductivity of cuprates the coexistence in normal state of holes and Jahn-Teller small polarons is fundamentally important, but the decisive role belong the latter which at strong Jahn-Teller interactions (for Cu^{+2} this energy is $\sim 1.2\text{eV}$) lead to polaron shift of energy, and to the possibility of the compensation of Coulomb repulsion between polaron and hole, at which on-site attraction of holes and polarons in CuO_2 planes and BCS pairing takes place.

References

1. J.O renstein, G A Thom as, A J M illis et al. PhysRev. B 42, 6342, 1990.
2. S U chida, T Ido, H Takagi et al., PhysRev. B 40, 7942, 1991.
3. X .X .B i and P C Eklund, PhysRev. Lett. 70, 2625, 1993.
4. K A M uller, G .M Zhao, K K onder, and H K eller, JPhys.: Condens. M atter, 10, L291 (1998).
5. K H Hock, H N ikisch, and H Thom as, Helv PhysActa 56, 237 (1983).
6. D M ihailovic, J D em sar, B Podobnik, V V Kabanov, J E Jvetts, G A Vagner, and L M echin, J Superconductivity, 12, 33 (1999).
7. A F Barabanov, L A M aksim ov, A V M iheenkov, JET hP Lett. 74, 674 (2001).
8. E I K udimov, 44, 667 (2002).
9. B I K ochelaev, J Superconductivity, 12, 53 (1999).
10. G G Sergeeva, Voprosy Atom noj Nauki i Tehniki, 2001, N 6, p 375
11. D N Basov, C C Hom es, E J Singley et al. PhysRev B 63, 134514, (2001).
12. I O Kulik, A G Pedan, Fizika N izkih Tem peratur (Russian) 14, 700 (1988).
13. G Balestrino, M M arinelli, and E M ilani, A A Varlam ov, and L Yu, PhysRev B 47, 8936 (1993).
14. G G Sergeeva, V Yu G onchar, A V Voytsenya, Fizika N izkih Tem peratur (Russian) 27, 634, (2001).
15. A L Solovjov, H -U Haberm eier, and T Haage, Low Temp Physics (FNT) 28, N 2, 144 (2002)
16. E I K ats, JETPH (Russian) 56, 1675 (1965).

- 17 A L Solov'ov, H-U Habermeyer, and T Haage, Low Temp Physics (FNT) 28, N1, 24 (2002).
18. V.V Eremenko, V N Samovarov, V L Vakula, M Yu Libin, S A Uyutnov, V M Rashkovan, Low Temp Physics (FNT) 27, N 11, 1327 (2001)
19. A Chubukov, D Frenkel, PhysRev. Lett. 74, 3057, 1995.
20. D K Morr, A V Chubukov, A P Kampf, G Blumberg, PhysRev. B 54, 11930, (1996).