

**Comment on the paper: "Water content and its effect on
ultrasound propagation in concrete- the possibility of NDE".
Ultrasonic 38(2000) 546-552 by Etsuzo Ohdaira and Nobuyoshi
Masuzawa**

Manuel Rodriguez Gonzalez*, Rolando Bonal Caceres[†]

Departamento de Fisica. Universidad Central de Las Villas. Santa Clara. CP: 54830 Villa Clara.

Cuba

(March 22, 2022)

Abstract

The fundamental application of the ultrasonic pulse velocity method (UPV) in the study of concrete, consist in the analysis and estimation of the mechanical properties (compressive strength). The precission of the estimation may be dependent on the incidence of various factors, one of which is the water content acquired by the sample of concrete. In Ref [1] a lineal dependence of the UPV in terms of the water content for different dosifications of concrete is proposed. This paper presents an analysis of that dependence proving that an exponential model describes better the behavior of the velocity as function of water content.

*mrg@mfc.uclv.edu.cu

[†]bonal@mfc.uclv.edu.cu

I. INTRODUCTION

Concrete is one of the most important materials used in the development of a country's infrastructure. Each year, thousands of tons of concrete is used in the restoration and rehabilitation of buildings. The development of the construction industry has helped in finding more effective and economic methods of inspection, which permit quicker and more reliable control. For this reason, the application of non destructive test methods is becoming more widely used in the industry, among them the ultrasound Ref [2–4]. Nevertheless, the effective application of the method in the study of concrete depends on the knowledge of a series of factors that affect the pulse velocity as well as the mechanical parameters Ref [5]. One of these factors is the water content of the concrete, in terms of which the ultrasonic pulse velocity can increase or decrease significantly, while the variations in the compressive strength remains insignificant Ref [6]. The incidence of this factor can bring about imprecision in the estimation of the mechanical properties, specifically the strength of the concrete. The results obtained in Ref [1] are being analyzed in this paper and a model adequately describing the behavior of the velocity in terms of the water content is presented.

II. METHODS OF MEASUREMENT

In the work Ref [1], cylindrical samples of 200x100mm (diameter) are used for various dosifications. The specimen is situated on the scale to measure the variation of the water content according to weight lost (until weight is constant). The transducer are attached using the transmission method, which allows the measurement of the velocity in terms of the water content.

III. DISCUSSION OF THE RESULTS.

In Ref [1], it is proposed that behaviour of the velocity as function of the concentration of water shows a lineal behavior, which is not particularly precise. If the linear model is

considered , it must be admitted that an increase in the concentration, in the absorption process, would always provoke an increase in velocity which would not always be possible from the physical point of view because the saturation process is asymptotic, meaning that the velocity must reach an asymptotic maximum. In figures 1,2,3, the non linnear tendency of the process is shown. From the calculation of the probability of the goodness of fit it is observed that in all cases , there are no significant differences among velocity for a significance level of 5

It is then necessary to find a model which adequately describes the phenomenon under study. In spite of the fact that a 3 rd order polynomial describes this process rather well from a statistical point of view, it lacks common sense when seen from a physical point of view. We have a phenomenon in which the extreme values have an asymptotic behavior as a result of the drying process of the sample. As it is known, the increase of water in the material results in the increase in the velocity of ultrasonic signal. So, if it is taken into account that the material has a saturation point which is reached asymptotically, then the velocity also has a maximum value reached asymptotically. The former considerations can be written as follows:

Although the decrease in the concentration is proportional to the decrease in velocity, this decrease is greater while the velocity moves further away from a certain maximum value

This affirmation can be expressed by the following differential equation:

$$\frac{dV}{dC} = k(V_0 - V) \quad (1)$$

And the solution is:

$$V = V_0 - A_0 e^{-kx} \quad (2)$$

Where: the integration constant A0 is considred negative in terms of the observations made the experiment. v-velocity V0, A0 parameters of the model C-water content K-parameter of the model

Adjusting for each one the proportions , the following coefficients are obtained

Parameters Test Piece A-1 Test Piece B-1 Test Piece C-1

V_0	4487.58235	4406.20072	4234.08337
A_0	553.01462	523.59085	429.80387
$\frac{1}{k}$	2.88231	2.20381	3.07733
R^2	0.97	0.97	0.92

In all cases , the models converge rapidly.

From (2) it is observed that as concentration decreases, velocity decreases gradually and as C tends to zero , velocity assumes its minimum value, analogously , as C tends to infinite, velocity achieves its maximum value, describing a gradual process which corresponds with the capillary desorbption and diffusion phenomenon, which depends on time and concentration gradient. There are two stages involved in this drying process: initially capillarity, where the free water molecules rise to the pores surface and evaporate into the surrounding air, and the diffusion period, which is responsible for the evaporation of water trough the fine pores. In order to know how capillarity varies with time and concentration, it is necessary to solve the following equations for specific boundary condition of the desorbption process Ref [7–11]

$$\frac{\partial \theta}{\partial t} = \nabla D \nabla \theta \quad (3)$$

Where D-capillary diffusivity t-time θ — concentration of water.

Capillarity as well as diffusion, depend in great measure on the porosity of the medium. Therefore the coefficients are specific for each type of concrete.

Although the loss of water accompanied by contractions corresponds to a cause and effect situation, their relationship is not a simple one. When concrete begins to dry up, the water lost first is the free water molecules contained in the capillaries , which practically produces no contraction Ref [11]. For this reason , the first experimental point where a sudden variation of velocity occurs can be rejected.

Bearing in mind what has been said so far, an the existing dependence between velocity and the acoustic characteristic of the medium , it can then be understand why velocity

varies with the sample water content Ref [12–16]. There is a significant difference between the acoustic impedance of the air which exists initially in the superficial pores and that of the water which is absorbed in the course of time, in other words, if the pores are filled with air, the medium is denser, which favors the propagation of the high-frequency components which are more sensitive to these changes. As observed in Ref [1], on obtaining the frequency spectrum, the value of the fundamental component decreases (attenuates) as the concentration of water decreases. However, the acoustic impedance of water and air are small in comparison with impedance of concrete. Why is it then that this variation in velocity occurs? It is logical that the wave is propagated preferably through the solid matrix, but if the number of pores is very high, then velocity is affected by the presence of pores. Besides, water penetrates through a distance of 3-4 cm in the interior of the sample. This implies that all the area near the surface is saturated and its dimensions are of the order of the wavelength of the fundamental component, meaning that for velocities above 4000 m/s and frequencies of the order of 55- 100 KHz, the wavelength of the fundamental component is about 4-6 cm, the entire pulse front being affected by the presence of water.

It is important to demonstrate that the relative error of estimated velocity can be calculated from the model for any given concentration using the following expression:

$$\delta V = 0.0108895 + \frac{-0.96646 - 0.0092429C}{-0.123232 + e^{0.3469446C}} \quad (4)$$

where: δV — relative error of velocity C — concentration.

This error, as observed in Figure 4, it is approached to one percent in the low water content zone and diminishes with the increase of concentration as a consequence of the asymptotic tendency of the saturation process.

It is known that the fundamental objective of the application of ultrasound in the study of concrete is to correlate velocity with compressive strength Ref [17–21], however when the humidity condition changes as has been analyzed, the behavior of the strength is not analogous to that of velocity, it practically maintains an almost constant value, as shown in Ref [6] for this reason, it is very important to keep in mind that high velocity does not always

imply that values of strength will also be high, so mistakes can be made in the estimation of strength. In Figure 5 it is shown the tendency of estimated strength using the expression (5) Ref [22], employing the value of experimental velocity obtained in Ref [1], the velocity estimated using the linear model proposed in Ref [1] and velocity estimated through the exponential model proposed in this work. In all cases velocity increases with water content. It is observed that estimated strength also augments with water content, which is incorrect. That's why to estimate the strength from velocity it is necessary to know moisture percent of the sample.

$$R = aV - b \quad (5)$$

where: R- compressive strength (Mpa) a,b-parameters of the model V-velocity

In this case we employ a=0.0447 y b= 149.67 Ref [23]

IV. CONCLUSIONS

It is proven physically and statistically that the model which best describes the behaviour of velocity with respect to water concentration is the decreasing exponential model, from which the compressive strength can be estimated with a good confidence.

REFERENCES

- [1] Etsuzo Ohdaira and Nobuyoshi Masuzawa, "Water content and its effect on ultrasound propagation in concrete- the possibility of NDE". Ultrasonic 38(2000).
- [2] Kathleen Wilson, Winter Quarter "Literature Search: Methods of testing the Moisture Content of Concrete as it cure". 1999.
- [3] Andej Galan "Combined Methods of Ultrasound testing". Elsevier. 1990
- [4] Malhotra VM, Carino N.J "CRC handbook on non Destructive testing of concrete" CRC Press 1991.
- [5] Sandor Popovics " The behavior of ultrasonic pulse in concrete" Cement and Concrete Research. Vol 20. 1990
- [6] Manuel Rodriguez "Influencia de la humedad del concreto sobre el valor de la velocidad del pulso ultrasnico" Cemento -Hormign. Espaa. Marzo 1999. No 795.
- [7] Nicos S. Martys " Survey of concrete transport ptoperties an their measurement". 1995. Departament of Commerce National Institute of Standarts and Technology.
- [8] C. Hall " Barrier perfomance of concrete : Review of fluid transport theory" Materials and Structures ,22, 291-306, 1994.
- [9] C.Hall " Water sortivity of mortars and concrete: review"of Magazine of Concrete Research , 41 51-61, 1989.
- [10] S. Kelham " A water absoption test for concrete"Magazine ffor Concrete Research ,40, 106-110, 1988.
- [11] WJ. Ma Carter, H Ezirim and M. Ermerson " Adsorption of water and cholride in concrete". Magazine of Concrete Research 44, 31-37, 1992.
- [12] Popovics, S., and Popovics, J. S., "Potential ultrasonic Techniques Based on Surface Waves and Attenuation for Damage Evaluation in Concrete - A Review," Diagnosis of

- Concrete Structures, T. Javor, Editor, Proceeding of the International RILEM - IMEKO Conference, Experteentrum, Bratislava, 1991. pp. 101 - 104.
- [13] Popovics, J.S., Song, W., Ghandehari, M., Subramaniam, K.V., Achenbach, J.D. and Shah, S.P., (1999), "Application of surface wave transmission measurements for crack depth determination in concrete," accepted for publication in ACI Materials Journal.
- [14] Popovics, J.S. , "Are Advanced Ultrasonic Techniques Suitable for Concrete? - An Exploratory Investigation," Proceedings, Nondestructive Evaluation of Civil Structures and Materials, B. A. Suprenant, et al., Editors, University of Colorado, Boulder, Colorado, October 1990. pp. 327 - 339.
- [15] Popovics S, K. Komlos*, J. Popovics "Comparison of DIN/ISO 8047 (Entwurf) to Several Standards on Determination of Ultrasonic Pulse Velocity in Concrete". NDT.net-April 1997, Vol 2, No 04
- [16] Popovics S. "EDUCATIONAL AND RESEARCH PROBLEMS OF NDT OF CONCRETE STRUCTURES. NDTISS' 99
- [17] Burr Eberhard, Norbert Gold, Christian U. Grosse, Hans-Wolf Reinhardt "Simulation of Ultrasonic Flaw-detection in Concrete with a varying Percentage of Air Inclusions NDTnet. February 1998, Vol 3, No 2.
- [18] Di Maio Angel , " Evaluacin de la resistencia del hormign mediante mtodos nodestruc-tivos." Asosiacin Argentina de Tecnologia del Hormign.1997.
- [19] Di Mio Angel , " Break -Off test for high Strenght Concret" ASTM Journal Cement, Concrete and Aggregates 1996.
- [20] Ferreira, Almir P. and Castro, Protasio F." Application of NDT to Concrete Strength Estimation" NDT.net.2000, vol5, No2.
- [21] Ibrahim A.E. Shehata, Ana Catarina Evangelista, Ldia C. D. Shehata, UFRJ, "Com-

parison between Nondestructive Methods for Concrete Strength. NDTISS' 99

- [22] Rhoon K.K, Wee T.H " Development of stadistical quality assurance criterion for concrete using ultrasonic pulse velocity method". ACI Materials Journal , octuber 1999.
- [23] Manuel Rodrguez " Estimacin de las propiedades fsico- mecnicas del concreto utilizando tcnicas ultrasnicas" PhD Thesis. La Habana. 2001.







