

non-Local Quantum Criticality in $\text{Ce}(\text{Ru}_{1-x}\text{Fe}_x)_2\text{Ge}_2$ ($x = x_c = 0.76$)

W. M. M. J. Montfrooij¹⁾, M. C. A. Aronson¹⁾, B. D. Rainford²⁾, J. A.

Mydosh³⁾, A. P. Murani⁴⁾, P. Haen⁵⁾, and T. Fukuhara⁶⁾

¹⁾ University of Michigan, Ann Arbor, MI 48109, USA

²⁾ University of Southampton, Southampton SO17 1BJ, United Kingdom

³⁾ Leiden University, 2300 RA Leiden, the Netherlands

⁴⁾ Institute Laue-Langevin, F-38042, Grenoble Cedex 9, France

⁵⁾ CRTBT-Grenoble, BP 166, F-38061, Grenoble, France

⁶⁾ Faculty of Engineering, Toyama Prefectural University, Toyama 939-0398, Japan.

Abstract

We present the results of inelastic neutron scattering measurements, performed near the antiferromagnetic quantum critical point in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$. Both local and long range fluctuations of the local moments are observed, but due to the Kondo effect only the latter are critical. We propose a phenomenological expression which fits the energy E , temperature T and wave vector q dependences of the generalized susceptibility $\chi(q; E, T)$, describing the non-Fermi liquid $E = T$ scaling found at every wave vector.

PACS numbers: 71.27.+a, 75.40.Gb and 75.30.Fv

The stability of magnetic order among moments exchange coupled to the conduction electrons in a metal arises from the dynamic competition of two forces: the Kondo compensation of the moments, and long range intermoment coupling driven by the RKKY interaction, both depending on the strength of the exchange interaction J . An extensive body of experimental evidence has been compiled [1, 2] which shows that magnetic order is initially stabilized by increasing J , but that ultimately magnetic order terminates at a zero temperature quantum critical point (QCP) for a critical value J_c , yielding a magnetically enhanced but paramagnetic Fermi liquid phase for larger values of J .

Two different scenarios have been proposed to explain this generic phase diagram. In the first view [3, 4, 5], magnetic order at the QCP is a spin density wave (SDW) instability of the Fermi surface, as it is preceded by moment compensation below a Kondo temperature T_K which is finite at $J = J_c$. As for a conventional second order phase transition occurring at finite temperature, only the long wavelength fluctuations of the order parameter are critical in this scenario, leading to Lorentzian energy and wave vector dependences in the vicinity of the ordering wave vector q [3, 4]. In the second view [5, 6, 7], known as the local moment scenario, both T_K and the magnetic ordering temperature are zero at the QCP. Complete Kondo compensation of moments is thus only possible in the paramagnetic phase for $J > J_c$. Magnetic order, which occurs for $J < J_c$, consequently involves moments which are both long-lived and spatially localized. Here, the competition between Kondo screening and long range order leads to local as well as long wavelength degrees of freedom, and both can be critical near the QCP. The experimental signatures of the local moment scenario are an anomalous energy dependence for all wave vectors [7], as well as the absence of Kondo compensation at any temperature scale when $J = J_c$.

Despite the very different roles for moment compensation in these two theoretical scenarios, it is in practice difficult to distinguish them, since experiments are necessarily performed over a range of finite temperatures and on real materials with disorder and compositional inhomogeneities. Neutron scattering experiments have been central to this explication, although to date they have only been carried out on two systems with $T = 0$ phase transitions, $\text{CeCu}_{6-x}\text{Au}_x$ ($x = x_c = 0.1$) [6] and $\text{UCu}_{5-x}\text{Pd}_x$ ($x = 1.15$) [8, 9]. In both materials, strong scattering in the experimental energy window implies the presence of localized magnetic moments, while the modulation of the static susceptibility χ_q reveals the presence of residual magnetic interactions among these moments. Different arguments are presented for the two

materials which support the view that the local degrees of freedom and not the long range coupling control the critical behavior. Direct comparison of χ_q at different T in $UCu_5 \times Pd_x$ ($x=1,1.5$) [8] shows that these interactions are almost unaffected by lowered temperature, while χ_q measured at the largest q , representing the local susceptibility, diverges as $T \rightarrow 0$. Excitations at every q display anomalous energy dependences as well as $E=T$ scaling.

A different depiction of quantum critical behavior is found in $CeCu_{5.9}Au_{0.1}$, where the commensurate roles of temperature, energy, and wave vector in tuning the dynamic susceptibility $\chi(q;E;T)$ to criticality are reflected in a generalized Curie-Weiss expression [6], $\chi(q;E;T)^{-1} = \chi_q + (iaE + T)$. While the longest lived and longest ranged fluctuations occur for $q=q_c$, the propagation wave vector of the parent antiferromagnetic (AF) phase where the Weiss field χ_q vanishes, anomalous E and T dependences are found at every wave vector, as well as $E=T$ scaling when $q=q_c=0$. A dynamical mean-field model has been developed [7] which argues that the $T=0$ phase transition in $CeCu_{5.9}Au_{0.1}$ is actually driven by fluctuations on the shortest length scales, providing an operational definition of local criticality.

We present here the results of a neutron scattering study on a new system, $Ce(Ru_{0.24}Fe_{0.76})_2Ge_2$, which has been doped to an AF QCP. Localized moments are also present in this system, although they experience substantial Kondo compensation. Both local and long wave length fluctuations are found at all temperatures, although only the latter are truly critical. Accordingly, we argue that $Ce(Ru_{0.24}Fe_{0.76})_2Ge_2$ is the first example of a quantum critical system in which the $T=0$ instability is SDW-like. non-Fermi liquid (nFL) $E=T$ scaling is found at all temperatures and wave vectors, but neither the generalized Curie-Weiss expression [6] nor the Lorentzians of the mean field SDW model [4] describe our data. We propose instead a new phenomenological expression for $\chi(q;E;T)$ which is only critical on the longest length scales.

The phase diagram obtained from both pressurization [10] and Fe doping studies of $CeRu_2Ge_2$ (Fig. 1a) fulfills the basic requirement for the SDW scenario, displaying an AF QCP accompanied by a finite Kondo temperature. $CeRu_2Ge_2$ is a ferromagnet (FM) [11, 12, 13] with a Curie temperature of 8 K. Under pressure, ferromagnetism is supplanted by two AF phases, which in turn vanish at a critical pressure of 67 kbar. Substantial moment compensation is observed at the critical pressure, where T_K is estimated to be 15 K. Further increase of the pressure stabilizes a Fermi liquid phase over an expanding range of

temperatures. Inelastic neutron scattering experiments cannot be performed at these high pressures, so it is significant that a similar sequence of phases is observed in the doping series $\text{Ce}(\text{Ru}_{1-x}\text{Fe}_x)_2\text{Ge}_2$ (see Fig. 1a) and for $\text{CeRu}_2(\text{Si}_{1-x}\text{Ge}_x)_2$ [10]. The FM phase boundary is only qualitatively reproduced by the resistivity data [12], but the AF phase boundary, taken from our ac and dc susceptibility measurements reproduces the pressure results. The AF QCP occurs for a critical Fe concentration $x_c = 0.76 \pm 0.05$ [14].

We prepared a 30 g polycrystalline sample of $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ for neutron scattering experiments by arc-melting, followed by a two week anneal at 1000 °C. Microprobe measurements verified that the intended composition varies by only a few percent across a representative piece cut from the neutron scattering sample. Isolated regions of an impurity phase, CeGe_2 , were also found, occupying no more than 2% of the sample volume. Neutron diffraction experiments found AF correlations below 5 K, although no bulk phase transition was observed down to 1.7 K [15]. We conclude that our sample is very close to the $x_c = 0.76$ QCP.

Neutron scattering experiments were carried out at the IN6 time-of-flight spectrometer at the Institute Laue-Langevin, using an incident neutron wavelength of 5.12 Å. The data were corrected for self-attenuation and neutron absorption, and the magnetic components were separated from the non-magnetic components (Bragg peaks, phonon and multiphonon contributions, and nuclear incoherent scattering) using a non-magnetic reference sample, LaRu_2Ge_2 . Fig. 1b shows the absolutely normalized dynamic structure factor $S(\mathbf{q}; E)$ obtained from this process for $T = 7.5$ K.

The strong scattering found at all \mathbf{q} in Fig. 1b attests to the intrinsically localized character of the fluctuating moments in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$. A quantitative measure of this localized moment is obtained by direct integration of $S(\mathbf{q}; E; T)$ over the energies accessed in this experiment, yielding a fluctuating moment of $0.8 \mu_B$ at 20 K. Since this is a substantial fraction of the $1.74 \mu_B$ expected for the crystal field split groundstate of the Ce^{3+} ions [13], we conclude that these moments are long lived on the time scales of our experiment, with a substantial degree of spatial localization at all T .

The scattering is strongly enhanced at the smallest \mathbf{q} , revealing the presence of long-ranged interactions among these moments at low temperature. In order to analyze these interac-

tions, we extract χ_q using the Krammers-Kronig relation:

$$\chi_q = \frac{1}{\pi} \int_{-\infty}^{\infty} \frac{\chi''(q; E) dE}{E} = \frac{1}{\pi} \int_{-\infty}^{\infty} \frac{S(q; E) (1 - e^{E/k_B T}) dE}{E}; \quad (1)$$

where k_B is Boltzmann's constant. We can expand the range of energies available from the neutron scattering experiment, and improve the accuracy of the Krammers-Kronig transformation by fitting the measured $\chi''(q; E)$ to a modified Lorentzian line shape, described below. The static susceptibility χ_q deduced from this analysis is plotted at several temperatures in Fig. 1c, revealing two striking features, also evident in the corrected $S(q; E)$ data shown in Fig. 1b. First, for all T and $q > 1 \text{ \AA}^{-1}$, χ_q is virtually independent of q . As we will show below, the line shape as a function of E is independent of q in this q -range. Both observations indicate that this q -independent susceptibility describes the local response of spatially localized magnetic moments to fluctuating magnetic fields. χ_q also shows a pronounced enhancement at small q , which increases with decreasing T . We attribute this to the growth of critical correlations associated with incipient AF-order, at the small and incommensurate propagation vector $0.2-0.1 \text{ \AA}^{-1}$ implied by the onset of AF-order at satellite positions ($q = 1.56, 1.74 \text{ \AA}^{-1}$) around the (101) Bragg reflection ($q = 1.64 \text{ \AA}^{-1}$), found in our neutron diffraction experiments [15].

χ_q shows clear signs of moment compensation by the Kondo effect at the lowest T . The temperature dependences of $\chi_q(T)$ for representative q -values are plotted in Fig. 2a, including the uniform ($q = 0$) susceptibility $\chi_0(T)$, obtained from a dc susceptibility measurement [16] on a 35 mg piece taken from the neutron scattering sample. We find that $\chi_0(T)$ increases with decreasing temperature, displaying the hallmark power law behavior for $T < 20 \text{ K}$ found in many nFL systems: $\chi_0(T) = C_0/(T + T_W)$. Here, the Weiss-temperature $T_W = 0.9 \pm 0.2 \text{ K}$, $C_0 = 0.87 \pm 0.03 \text{ m}^2/\text{B} \text{ eV}^{0.49}$ and $\gamma = 0.51 \pm 0.01$. Since T_W is non zero, we see that $\chi_0(T)$ does not truly diverge as $T \rightarrow 0$. The absence of divergence is even more evident in the local susceptibility which is found by integrating χ_q over the experimental q -range, $\chi_{\text{loc}}(T) = \int_0^{q_{\text{max}}} \chi_q(T) dq = (4/3) \chi_{\text{max}}^3$, which is indistinguishable from χ_q for $q > 1 \text{ \AA}^{-1}$, saturates for $T < 5 \text{ K}$ (see Fig. 2a). Further evidence [17] for partial Kondo compensation comes from the 25% reduction in scattered intensity as the temperature is lowered from 20 K to 1.8 K (see Fig. 2a), despite a simultaneous narrowing of the energy line width.

The dynamic response in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ is dramatically different from those found in fluctuating moment systems far from quantum critical points. Like previous neutron scat-

tering studies on Kondo lattice systems [13, 18, 19, 20, 21, 22], the dynamic response in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ is broad and quasi-elastic. However, Fig. 2b shows that the Lorentzian line shape [13, 18, 19, 20, 21, 22] common to Kondo lattices agrees very poorly with our measured $\chi''(\mathbf{q}; E)$, both for a small wave number, 0.35 \AA^{-1} where the moments are interacting, and at a large wave number 1.15 \AA^{-1} where the response is purely local. We find instead that at all E , for all T from 1.9 K – 200 K , and for the complete \mathbf{q} -range probed in our experiment that our data can be satisfactorily described by a simple phenomenological expression: $\chi''(\mathbf{q}; E) = \chi''_{\mathbf{q}}(T) \cdot [1 - \delta(E - \epsilon_{\mathbf{q}}(T))]$.

The observed line shape $\chi''(\mathbf{q}; E)$ is controlled by an energy scale $\epsilon_{\mathbf{q}}(T)$, and by a dynamical exponent $\alpha = 0.15 \pm 0.05$. The temperature dependence of $\epsilon_{\mathbf{q}}(T)$ which we extract from these fits is plotted for two values of \mathbf{q} in Fig. 2c. For $\mathbf{q} = 1.15 \text{ \AA}^{-1}$, $\epsilon_{\mathbf{q}}(T)$ has the familiar T -dependence of a Kondo impurity system, initially decreasing with T before saturating and increasing weakly below T_K , which we identify as 5 K . Dynamics on this local length scale are consequently not critical. In contrast, $\epsilon_{\mathbf{q}}$ determined for $\mathbf{q} = 0.35 \text{ \AA}^{-1}$ approaches zero with decreasing T , as expected for critical slowing-down associated with the $T = 0$ phase transition. With the exception of the lowest T at the largest \mathbf{q} , $\epsilon_{\mathbf{q}}$ is approximately linear in T , $\epsilon_{\mathbf{q}} = \epsilon_0 + a_{\mathbf{q}}T$. The \mathbf{q} -dependence of $\epsilon_{\mathbf{q}}$ is shown in Fig. 2d, demonstrating that dynamic criticality, i.e. $\epsilon_{\mathbf{q}} \rightarrow 0$, can only be achieved if $\mathbf{q} \rightarrow 0$. For $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ this occurs as \mathbf{q} approaches the propagation wave vector of incipient AF order, $0.2 \pm 0.1 \text{ \AA}^{-1}$. We conclude that at all temperatures $\chi''(\mathbf{q}; E; T)$ is dominated at short length scales by the excitations of individual Kondo moments, while the long-wave length fluctuations become increasingly long-lived and ultimately critical as $T \rightarrow 0$.

A random phase approximation (RPA) analysis of $\epsilon_{\mathbf{q}}(T)$ shows that the singular behavior found near the QCP in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ requires the collaboration of both local and long-range dynamical correlations. The long-range correlations are graphically demonstrated in Fig. 3a, where we have plotted $\chi''_{\text{loc}}(T)/\epsilon_{\mathbf{q}}(T)$ at several temperatures. An increasing suppression of $\chi''_{\text{loc}}/\epsilon_{\mathbf{q}}$ is observed at small \mathbf{q} as the temperature is lowered, signalling the growth of long range AF coupling. An estimate of this coupling, $U_{\mathbf{q}}(T)$ can be obtained in the RPA approximation by noting that $\chi''_{\text{loc}}(T) = \epsilon_{\mathbf{q}}(T) = 1 - U_{\mathbf{q}}(T) \chi''_{\text{loc}}(T)$. $U_{\mathbf{q}}$ deduced from this analysis at 4.4 K is plotted in the inset of Fig. 3a, demonstrating that the interactions are long ranged, rapidly vanishing for wave vectors larger than 0.6 \AA^{-1} . As shown in Fig. 3b, the temperature dependences of $U_{\mathbf{q}}$ are very different for large and

small q . U ($q = 0.55 \text{ \AA}^{-1}$) is almost temperature independent, while U ($q = 0.275 \text{ \AA}^{-1}$) increases almost a factor of four between 20 K and 1.5 K. In contrast, $\chi_{\text{loc}}(T)$ initially increases with decreasing temperature, but ultimately saturates below 5 K. This RPA analysis reveals that local fluctuations initially provide a bias towards criticality in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$, but ultimately it is the intermoment coupling $U_q(T)$ which actually drives criticality. A similar conclusion was reached for U_2Zn_{17} [21], a heavy fermion antiferromagnet with a Neel temperature $T_N = 9.7$ K. However, neither a departure from Lorentzian line shape, nor any other nFle effects were observed in this system, which is not at a QCP.

The modified Lorentzian introduced above and the observed T -linearity of $\chi_q(T)$ implies that our data should also display nFle $\chi_q(T) = (T + \chi_q)$ scaling. To confirm this, we have plotted $\chi_q(E)(T + \chi_q)^{0.51}$ for $q = 0.35, 0.55, 1.35$ and 1.75 \AA^{-1} as functions of $E/k_B(T + \chi_q)$ in Fig. 4. An excellent collapse of the data taken at different temperatures is observed at each q , spanning three orders of magnitude in the scaling variable $E/k_B(T + \chi_q)$. The exponent 0.51 is taken from the temperature dependence of $\chi_0(T)$, as was also found in the locally critical systems UCu_4Pd [8, 9] and $\text{CeCu}_{5.9}\text{Au}_{0.1}$ [6]. Unlike those systems, we find in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ that the dynamical scaling function itself requires a second exponent $\alpha = 0.15$.

Our neutron scattering measurements have established that there are local moments present in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ which experience increasing AF coupling as $T \rightarrow 0$. Although fluctuations of these moments are observed on every length scale, χ_q only diverges at the residual ordering wave vector of the nearby AF phase. Correspondingly, we observe a substantial Kondo suppression of the local fluctuations below 20 K. The dominance of the long wavelength correlations at the lowest temperatures, and the finite Kondo temperature at the QCP together imply that the $T = 0$ antiferromagnetic transition in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ is a collective instability of the strongly interacting quasiparticles, and is not locally critical. The mean field view of such a phase transition requires a single diverging length scale with an accompanying diverging time scale, leading to Lorentzian lineshapes for χ in energy and wave vector. We find instead that the susceptibility $\chi(q; E; T)$ is well described by a modified Lorentzian expression, encompassing the $E = T$ scaling which we observe at every wave vector.

We acknowledge stimulating discussions with P. Coleman, A. J. Millis, and Q. M. Si. MCA thanks T. Gortenmulder and R. Hendrikx for invaluable technical assistance, and

acknowledges the hospitality of the M SM group at Leiden during the early stages of this project. We thank I. P. Swainson for carrying out the neutron diffraction measurements. Work at the University of Michigan was supported by NSF-DMR-997300.

-
- [1] G. R. Stewart, *Rev. of Mod. Physics* 73, 797 (2001).
 - [2] S. Sachdev, *Quantum Phase Transitions* (Cambridge University Press, Cambridge, England, 1999).
 - [3] J. A. Hertz, *Phys. Rev. B* 14, 1165 (1976).
 - [4] A. J. Millis, *Phys. Rev. B* 48, 7183 (1993); private communication.
 - [5] P. Coleman, *Physica B* 259-261, 353 (1999).
 - [6] A. Schroder et al., *Nature* 407, 351 (2000).
 - [7] Q. Si et al., *Nature* 413, 804 (2001).
 - [8] M. C. Aronson et al., *Phys. Rev. Lett.* 75, 725 (1995).
 - [9] M. C. Aronson et al., *Phys. Rev. Lett.* 87, 197205 (2001).
 - [10] S. Sullow et al., *Phys. Rev. Lett.* 82, 2963 (1999).
 - [11] H. Rietchel et al., *J. Magn. Magn. Mater.* 76-77, 105 (1988); A. Boehm et al., *J. Magn. Magn. Mater.* 76-77, 150 (1988).
 - [12] M. B. Fontes et al., *Phys. Rev. B* 53, 11678 (1996).
 - [13] B. D. Rainford and S. J. Dakin, *Phil. Mag. B* 65, 1357 (1992).
 - [14] This value is below the estimate of Fontes et al. [12], however, their results are not inconsistent with $x_c = 0.76$.
 - [15] W. Montfrooij et al., unpublished.
 - [16] ϕ_0 in $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ has substantial anisotropy, reflecting preferred orientation and/or Ising-like behavior. However, we only use the T-dependence of ϕ_0 in our analysis, not its absolute value.
 - [17] N. E. Bickers, D. L. Fox and J. W. Wilkins, *Phys. Rev. B* 36, 2036 (1987).
 - [18] M. Loewenhaupt et al., *Journal de Physique* 40, C4-142 (1979).
 - [19] G. Aeppli, E. Bucher and G. Shirane, *Phys. Rev. B* 32, 7579 (1985).
 - [20] A. I. Goldman et al., *Phys. Rev. B* 33, 1627 (1986).
 - [21] C. Broholm et al., *Phys. Rev. Lett.* 58, 917 (1987).

[22] U. Walter, M. Loewenhaupt, E. Holland-Moritz and W. Schlabit, Phys. Rev. B 36, 1981 (1987).

FIG. 1: (a): The magnetic phase diagram for CeRu_2Ge_2 as functions of pressure [10] (dashed lines) and Fe doping (—: FM phase boundary [12], ? : AF phase boundary, present work). Filled circles represent the pressure dependent Kondo temperature, which is finite at the QCP [10]. The solid lines are guides to the eye. The electrical resistivity is quadratic in temperature [10] in the shaded part of the phase diagram (FL). (b): The fully corrected $S(q;E)$ for $\text{Ce}(\text{Ru}_{0.24}\text{Fe}_{0.76})_2\text{Ge}_2$ as a function of neutron momentum transfer $\sim q$ and energy transfer E , for $T = 7.5$ K. (c): The static susceptibility χ_q for $T = 2.9$ K (—), 7.5 K (?) and 15.2 K (4). Note the incipient AF order around the (101) Bragg peak ($q = 1.64 \text{ \AA}^{-1}$) at 2.9 K.

FIG. 3: (a): $\chi_{\text{loc}}(T)/\chi_q(T)$ as a function of q for $T = 1.9$ K (), 4.4 K (4), 7.5 K (), and 15.2 K (?). As explained in the text, this quantity is directly related to the interaction U_q , which is plotted in the inset for $T = 4.4$ K. (b): While the temperature divergence of $\chi_{\text{loc}}(?)$ is cut off below 5 K by the Kondo effect, $U(q = 0.275 \text{ \AA}^{-1})$ () increases monotonically to the lowest T . For $q = 0.55 \text{ \AA}^{-1}$ (), U_q is T -independent.

FIG. 4: Scaling of the dynamic response for various q -values. The neutron scattering data $\chi''(q; E)$ have been multiplied by $(T + T_w)$ ($T_w = 0.51$, see text), and displayed versus the reduced variable $E = (T + T_w)\chi_q$, with χ_q as in Fig. 2d. Note that the various q -values are offset by half a decade along the vertical axis. The temperatures range from 1.9 K (darkest symbols) to 200 K (lightest symbols), and there is substantial overlap in $E = (T + T_w)\chi_q$ among the 11 temperatures displayed in this figure. Every scaling curve represents about 3000 independent data points.

FIG. 2: (a): $\chi_q(T)$ for $q = 0.35 \text{ \AA}^{-1}$ (), for $q = 0.45 \text{ \AA}^{-1}$ (4) and integrated over all q , $\chi_{\text{loc}}(T)$ (?). The solid line is the $q = 0$, dc susceptibility χ_0 . Also shown (, in $\frac{2}{B}$) is the average of $S_q(T)$ over $1 < q < 1.8 \text{ \AA}^{-1}$, demonstrating the onset of Kondo-screening at $T \approx 20$ K. (b): $\chi''(q; E)/E$ for $q = 0.35 \text{ \AA}^{-1}$ () and $q = 1.15 \text{ \AA}^{-1}$ () at $T = 4.4$ K. The data at $q = 1.15 \text{ \AA}^{-1}$ have been divided by 2 for the sake of plotting clarity. The solid lines are the best fits to the modified Lorentzian line shape described in the text, with $\gamma = 0.15$. The dashed curve is the best fit Lorentzian line shape ($\gamma = 1$). (c): The energy linewidth χ_q of $\chi''(q; E)/E$ for $q = 0.35 \text{ \AA}^{-1}$ () and $q = 1.15 \text{ \AA}^{-1}$ (). (d): q -dependence of the residual linewidth χ_q , explained in the text. Also shown is χ_w at $q = 0$.







