arXiv:cond-mat/0208056v2 [cond-mat.mtrl-sci] 20 Oct 2002

Magneto- and Electrotransport Properties of $Nd_{0.67}Sr_{0.33}Mn_{1-x}Fe_xO_3$ (x = 0.00, 0.05)

Chang Yoke Ling[a*] C. K. Ong[a]

[a] *Department of Physics, Center for Superconducting and Magnetic Materials, National University of Singapore, 2 Science Drive 3, 117542 Singapore, Singapore*

Abstract

Simultaneous studies on the magnetic and electrotransport properties of $Nd_{0.67}Sr_{0.33}Mn_{1-x}Fe_xO_3$ polycrystalline bulk and epitaxial thin films (x = 0.00 and 0.05) have been carried out. A magnetoresistance (MR) as high as $\sim$ 33% is observed for $Nd_{0.67}Sr_{0.33}MnO_3$ bulk at the metal-insulator transition (MIT) temperature (T_p) of 273 K in a magnetic field (**H**) of 10 kOe. Fe substitution at Mn sites reduces the ferromagnetic (FM) ordering temperature (T_c) and leads to an overall increase in MR. MR as high as $\sim$ 90% is observed for thin film (x = 0.05) at **H** = 10 kOe with T_p = 100 K while the corresponding bulk has a MR of only $\sim$ 43%. Low field MR in epitaxial thin films also display a pronounced anisotropy effect compared to bulk materials.

71.30.+h, 71.38.-k, 73.43.Qt, 75.30.Vn

Typeset using REVTEX

*corresponding author: scip0068@nus.edu.sg