D ipolar interaction between two-dimensional magnetic particles

Paolo Politi^{1,2}, and Maria Gloria Pini^{1,y}

¹ Istituto di Fisica Applicata \N ello Carrara", Consiglio Nazionale delle Ricerche, Via Panciatichi 56/30, I-50127 Firenze, Italy

² Istituto Nazionale per la Fisica della Materia, UdR Firenze,

Via G. Sansone 1, I-50019 Sesto Fiorentino, Italy

(D ated: M arch 22, 2022)

We determ ine the elective dipolar interaction between single dom ain two-dimensional ferrom agnetic particles (islands or dots), taking into account their nite size. The rst correction term decays as $1=D^5$, where D is the distance between particles. If the particles are arranged in a regular two-dimensional array and are magnetized in plane, we show that the correction term reinforces the antiferrom agnetic character of the ground state in a square lattice, and the ferrom agnetic one in a triangular lattice. We also determ ine the dipolar spin-wave spectrum and evaluate how the Curie tem perature of an ensemble of magnetic particles scales with the parameters de ning the particle array: height and size of each particle, and interparticle distance. Our results show that dipolar coupling between particles might induce ferrom agnetic long range order at experimentally relevant tem peratures. How ever, depending on the size of the particles, such a collective phenom enon may be disguised by superparam agnetism.

PACS numbers: 75.75.+ a, 75.30 D s, 77.80 Bh, 75.20.-g

I. IN TRODUCTION

In this paper we are interested in two-dim ensionalm agnetic particles interacting through the long range dipolar forces. These particles have a two-dim ensional character in two respects: rst, because they are platelet shaped, that is to say their thickness t is much sm aller than their linear size L; second, because they are arranged on a two dim ensional substrate.

They can be obtained, e.g., growing by Molecular Beam Epitaxy (MBE) a magnetic element on a high symmetry substrate. In this case, grow this driven by surface di usion, nucleation and aggregation! in the submonolayer regime, the magnetic overlayer is made up of an ensemble of atom ically thick islands that generally are not uniform in size neither arranged in a regular array. The distribution of islands may be regular if nucleation (and therefore island form ation) takes place on a reconstructed surface,² or on a network of dislocations.³ A Itematively, particles can be produced via lithographic techniques:⁴ in this case, they are much bigger in size and their distribution is generally uniform.

In the following, small particles obtained by MBE growth in the submonolayer regime will also be called islands and large particles obtained by lithographic techniques will also be called dots. Particle is a generic term for both cases.

Each particle is made up of a large number N of spins which interact ferrom agnetically through the strong intra-particle exchange interaction. In an island, N

 10^2 10^4 , while in a dot N may be several orders of magnitude greater.

Su ciently sm all particles are expected to be in a single dom ain state, even if their actualm agnetic state m ay depend on several factors: the shape of the particle, the strength of the anisotropies, the single crystal or polycrystalline character of the particle, and so on. In this paper we are assuming that particles are in a single domain state and have a crystalline structure. W ithin these hypotheses, the magnetic state of an isolated particle is

xed, rst of all, by the balancing between dipolar interaction (which has an easy-plane e ect) and possible anisotropies favouring the direction perpendicular to the plane (z direction, in the following). In the absence of quartic and higher order anisotropies a canted con guration is im possible and the resulting e ect may be easyaxis or easy-plane only.

The e ect of dipolar interaction between spins belonging to the same (ultrathin) particle has been studied in a previous paper.⁵ We showed that in-plane shape anisotropy is weak: this means that if the magnetization of the particle is within the Im plane, its orientation is expected to be settled by the sym metry of the underlying lattice (through magnetocrystalline anisotropies) rather than by the shape of the particle (through the intraparticle dipolar coupling). Such a feature was indeed experimentally observed in MBE-grown Co on Cu (100) ultrathin particles.⁶

In this paper we aim to study the interparticle dipolar interaction and to address the following questions:

i) A ssum ing the particle to be in a single dom ain state, how is the dipolar interaction between particles modi ed by their nite size?

ii) A ssum ing the particles to be arranged in a regular array, is the dipolar ferrom agnetic (FM) state a stable con quration?

iii) If the ground state is ferrom agnetic, is it stable at nite tem perature and what is the value of the Curie tem perature?

The previous questions are addressed in Sections II, III and IV, respectively; in Section V the conclusions are drawn.



FIG.1: I_1 and I_2 are two generic interacting particles. Each spin of the rst particle, located in \mathcal{R}_1 , interacts with each spin of the second particle, located in \mathcal{R}_2 . Using reference frames centered in the centers of mass of the particles, the spatial positions of the two spins are r_1 ; r_2 so that the distance between the two spins can be expressed as $\mathcal{R}_{12} = \mathcal{R}_2$ $\mathcal{R}_1 = \mathcal{D} + r_2$ r_1 $\mathcal{D} + r$.

II. EFFECTIVE D IPOLAR INTERACTION BETW EEN PARTICLES

In the following we are going to consider two particles $I_1; I_2$ of any shape (see Fig. 1), with linear sizes $L_1; L_2$ and thicknesses $t_1; t_2$. Each particle is a discrete collection of spins and it is supposed to be in a single dom ain state: each spin of the two particles is indicated by s_1 and s_2 , respectively. The elective dipolar interaction between the two particles is evaluated by taking the interaction between a spin s_1 located in R_1 , a spin s_2 located in R_2 and summing up on all them:

$$E_{dip} = \frac{1}{2} \frac{t_1 t_2}{c_0^2} X X \frac{*}{R_{12}^3} \frac{s_1 2}{R_{12}^3} 3 \frac{(s_1 R_{12})(s_2 R_{12})}{R_{12}^5}$$
(1)

where $= g^2 \frac{2}{B}$ (g is the gyrom agnetic factor and $_B$ the Bohrm agneton) and c_0 is the interplane distance in the z direction. In the previous expression, we have supposed that the thickness of each particle is much smaller than its linear size, t L. In this hypothesis, E_{dip} is just linear in the numbers of atom ic planes, $t_1=c_0$ and $t_2=c_0$, and R_{12} are two dimensional vectors.

As explained in Appendix A, the two quantities appearing in square brackets in Eq. (1) can be expanded in the ratio r=D, where D is the distance between the centers of m ass of the particles and $r = r_2$ r_1 (see Fig.1). The elective dipolar interaction between two particles at distance D takes the approximate form :

$$E_{dip} = E_{dip}^{(0)} + E_{dip}^{(2)}$$
 (2)

where E $_{\rm dip}^{(0)}$ is the zero-order coupling and E $_{\rm dip}^{(2)}$ takes into

account the nite size of the particles:

$$E_{dip}^{(0)} = \frac{1}{2} - \frac{S_1 S_2}{D^3} - 3 \frac{(S_1 D)(S_2 D)}{D^5}$$
(3)

$$E_{dip}^{(2)} = \frac{9I_{12}}{4} \frac{S_1^2 S_2^2}{D^5} + \frac{3I_{12}}{4} \frac{S_1^k S_2^k}{D^5} - 5 \frac{(S_1^k D)(S_2^k D)}{D^7}$$
(4)

Each particle behaves as a single spin $S = N \, s$, where N is the total number of spins in the particle. If L is the linear dimension of a particle and t its thickness, denoting by a_0 the in-plane atom ic distance, one has $N = (L=a_0)^2$ (t=c_0), where is a geometric factor, depending on the shape of the particle and the lattice structure. The correction terms included in $E_{dip}^{(2)}$ decay with distance as 1=D⁵, whilst the usual dipolar interaction decays as 1=D³. More precisely, $E_{dip}^{(2)}$ is a factor I_{12} =D² sm aller than $E_{dip}^{(0)}$, where $I_{12} = \frac{1}{2} (I_1 + I_2)$ is the sem isum of the \m oments of inertia" I_i of the two particles (see Appendix A).

In the continuum approximation, we have the following expressions. For a square particle of side L, I = $L^2=6$; for a circular particle of radius , I = $^2=2$; for a triangular (equilateral) particle of side L, I = $L^2=12$.

F inally, we would like to remark that the isotropic coupling term, proportional to $(S_1 \ S_2)$, has different correction terms according to the orientation of the spins: see Eq. (4). In other words, such a term is no more isotropic once the nite size of the particle is taken into account.

In Fig. 2 we compare the exact dipolar coupling $E_{\rm dip}$ (symbols) with the zero order approximation $E_{\rm dip}^{(0)}$ (dashed lines) and with the second order approximation $(E_{\rm dip}^{(0)} + E_{\rm dip}^{(2)})$ (full lines), in two cases: i) the particles are magnetized perpendicularly to the plane, along the \hat{z} axis (positive coupling energies), and ii) the particles are magnetized in plane along the \hat{x} axis (negative coupling energies). We can see that the second order approximation is fairly good except at very small distances: the smallest allowed distance between centers (without superposing the particles) is $D_{\rm min} = \frac{1}{2}(L + a_0) = 29:7a_0$, where $L = 20a_0$ is the side of the square particle. The smallest value of D plotted in Fig.2 is $D = 30a_0$.

In order to understand which con gurations are energetically favoured, let us start by considering just a couple of spins $S_1; S_2$, located in plane along the x axis. The dipolar coupling can be generally written as

$$E_{12} \qquad E_{12}^{(0)} + E_{12}^{(2)} \\ \sim_{0} (S_{1} S_{2} 3S_{1}^{x}S_{2}^{x}) \\ + \sim_{2} (2S_{1}^{z}S_{2}^{z} + S_{1} S_{2} 5S_{1}^{x}S_{2}^{x})$$

where the explicit expressions of \sim_0 and \sim_2 , depending on the distance between spins and on the size of the particles, are irrelevant. We observe that S_1 ; S_2 m ay be either



FIG. 2: D polar energy between two square particles, one monolayer thick, of side L = $20a_0$ on a square lattice (21 spins per side). The centers of the two particles have the coordinates (0,0) and (D = 2;D = 2). The sides of the squares are parallel to the axis $\hat{x};\hat{y}$. Positive and negative energies refer to spins parallel to \hat{z} and \hat{x} , respectively. The exact calculation E_{dip} (symbols) is compared with E_{dip}⁽⁰⁾ (dashed lines) and (E_{dip}⁽⁰⁾ + E_{dip}⁽²⁾) (full lines). Inset: the case of spins parallel to \hat{x} , in a log-log scale.

veritable spins $s_1; s_2$ or they may represent the elective spins of two particles $S_1; S_2$: in the former case one has $\sim_2 = 0$, while in the latter \sim_2 is the correction due to the nite sizes of the particles.

Both $E_{12}^{(0)}$ and $E_{12}^{(2)}$ are the sum of competitive interactions. For the sake of de niteness, let us consider $E_{12}^{(2)}$. The sum $2S_1^z S_2^z + S_1 \quad S_2$ favours an antiferrom agnetic (AFM) alignment of the spins in the 2 direction, perpendicular to their joining vector. The term $5S_1^x S_2^x$ favours a ferrom agnetic (FM) alignment along the x axis. The energy of the former conguration is \mathcal{J}_2 and the energy of the latter one is 4^{\sim}_2 . A sproved in Appendix B, where a more detailed discussion is given, the latter conguration is the ground state indeed.

In conclusion, two spins interacting through the dipolar coupling m in in ize their energy by ordering ferrom agnetically along the joining line.

We are now going to discuss the more complex case of a two dimensional lattice of spins. It is well known⁷ that in the presence of a direct exchange interaction, the system is ferrom agnetic and magnetized in the plane, because of an easy-plane e ect of $E_{\rm tip}$. If such an exchange interaction is absent, the easy-plane e ect survives, but the actual conguration in the plane strongly depends on the lattice structure.⁸ It is useful to explain the origin of such a dependence on the spin arrangement.

We have seen that spins would like to point along the line joining them : in a two dimensional lattice it is im possible, of course, to full lithis requirement for all couples of spins. It is possible, however, for a chain of spins: so, we can start by addressing the nature of the coupling between chains.^{9,10} Let us consider a ferror agnetic chain of spins along the \hat{y} axis of the plane and evaluate the dipolar eld \mathbf{H}_{dip} generated at a point at distance d. Spins are oriented in the + \hat{y} direction and $\mathbf{H}_{dip} = \mathbf{H}_{dip} \mathbf{y}$. In the continuum approximation,

$$H_{dip} = \frac{1}{2} S \begin{bmatrix} Z + 1 \\ s \end{bmatrix} dy \frac{1}{r^{3}} \frac{y^{2}}{r^{5}}$$
$$\frac{3}{4} S I \begin{bmatrix} z^{1} + 1 \\ 1 \end{bmatrix} dy \frac{1}{r^{5}} \frac{y^{2}}{r^{7}}$$

where $r = \frac{P}{y^2 + d^2}$.

Both integrals have the form $dy(\frac{1}{r^{3+n}} (3+n)\frac{y^2}{r^{5+n}})$. It is su cient to integrate by parts the term $1=r^{3+n}$ to prove that the integral vanishes for any n and for any d. Therefore, in the continuum approximation $H_{dip} = 0$.

A n exact calculation on a discrete lattice gives a nite value for H $_{\rm dip}$, but its sign depends on the actual lattice structure. Therefore, the reason for the sensitivity of the ground state on the spin arrangement is clear. D ipolar interaction favours the form ation of spin chains magnetized ferrom agnetically along the chain: these chains are very weakly coupled, in the continuum approximation being even uncoupled. The sign of the coupling and therefore the nature of the ground state do depend on the lattice structure.

In the next Section we are going to analyze the nature of the ground state and to study the spin-wave spectrum with respect to a ferrom agnetic alignment.

III. GROUND STATES AND SPIN-WAVE SPECTRA IN TW O-D IM ENSIONAL LATTICES

In the follow ing we consider an orthorom bic lattice (see Fig. 3a) with primitive vectors

$$\mathfrak{a}_1 = \frac{1}{2} (a; b); \mathfrak{a}_2 = \frac{1}{2} (a; b)$$
 (5)

where $a = 2D_0 \sin(22)$, $b = 2D_0 \cos(22)$, and D_0 is the rhom bus side. For $= \frac{1}{3}$ and $= \frac{1}{2}$, the orthorom bic lattice reduces to a triangular and to a square lattice, respectively. The angle can be supposed sm aller than $\frac{1}{2}$, because if $> \frac{1}{2}$ there is just an interchange between a and b (see Fig. 3a).

It is know n^{8,10} that the ground state is ferrom agnetic for < $_{\rm c}$ 80 and antiferrom agnetic for larger values of the angle . It is noteworthy that we nd $_{\rm c}$ to be alm ost una ected when ${\rm E}_{\rm dip}^{(2)}$ is added to ${\rm E}_{\rm dip}^{(0)}$: as a rst approximation, the nite size of the particle has therefore negligible e ects on the ground state. We can say as well that the nite size of the particles (i.e. the term ${\rm E}_{\rm dip}^{(2)}$) reinforces the FM character of the ground state for a triangular lattice, $= \frac{1}{3}$, and the AFM one for a square lattice, $= \frac{1}{2}$. This statement will be substantiated by the analysis of the spin-wave spectra at the end of this Section.



FIG.3: (a) O rthorom bic lattice with coordinate axes directed along the rhom bus diagonals, a and b; is the rhom bic angle. (b) Reciprocal lattice of the orthorom bic lattice. The angle $_{k}$ denotes the orientation of the in-plane wavevector \tilde{k} with respect to the \hat{x} axis.

Let us now calculate the frequency of spin-wave excitations with respect to a ferrom agnetic con guration with magnetization directed in plane. We remind that, depending on the value of the rhom bic angle , the ferrom agnetic ground state is di erent⁸ for =3, the dipoles are oriented along the short diagonal of the rhom bus (i.e. along the x axis in Fig. 3a) while for =3 , along the long diagonal (\hat{y} axis).

The e ective dipolar interaction between particles of spins whose centers of mass are located on the sites D_i of an orthorom bic lattice is $H_{dip} = H_{dip}^{(0)} + H_{dip}^{(2)}$; it is obtained from Eqs. (3,4) sum ming over all sites

$$H_{dip}^{(0)} = \frac{1}{2} \begin{pmatrix} X & X & X & \frac{S_{i} & S_{j}}{D_{ij}^{3}} & 3\frac{(S_{i} & D_{ij})(S_{j} & D_{ij})}{D_{ij}^{5}} \\ H_{dip}^{(2)} = \frac{1}{2} \begin{pmatrix} X & X & X & \frac{S_{i} & S_{j}}{D_{ij}^{5}} \\ & & 3I_{ij} & \frac{S_{i}^{2} & S_{j}^{2}}{D_{ij}^{5}} \\ & & & +\frac{3I_{ij}}{2} & \frac{S_{i} & S_{j}}{D_{ij}^{5}} & 5\frac{(S_{i} & D_{ij})(S_{j} & D_{ij})}{D_{ij}^{7}} \end{pmatrix}$$
(6)

where $\tilde{D}_{ij} = \tilde{D}_j$ \tilde{D}_i and $I_{ij} = \frac{1}{2}(I_i + I_j)$ is the sem isum of the \m om ents of inertia" of two particles whose centers

of m ass are located in D_i and D_j , respectively. In the following we are assuming to have an array of identical particles, so that I_i I.

Taking the ightharpoindow direction as quantization axis, we perform the Holstein-P rim ako transform ation from spin to boson operators

$$S_{j}^{x} = i \frac{S}{2} (a_{j}^{y} a_{j}); S_{j}^{y} = S a_{j}^{y} a_{j}; S_{j}^{z} = \frac{r}{2} (a_{j} + a_{j}^{y})$$
(7)

Next, exploiting the translational invariance in the lm plane, we introduce the Fourier transform

$$a_{j} = \int_{K_{R}}^{S} \frac{1}{N_{k}} X_{k} a_{k} e^{i \kappa \mathcal{D}_{ij}}; a_{j}^{Y} = \int_{K_{R}}^{S} \frac{1}{N_{k}} X_{k} a_{k}^{Y} e^{i \kappa \mathcal{D}_{ij}};$$
(8)

where $\tilde{k} = (k_x; k_y)$ is the two-dimensional in-plane wavevector ranging over the rst Brilbuin zone, generated by the primitive vectors (see Fig. 3b)

$$\mathbf{v}_1 = 2 \ (\frac{1}{a}; \frac{1}{b}); \ \mathbf{v}_2 = 2 \ (\frac{1}{a}; \frac{1}{b})$$
(9)

and N $_{\rm k}\,$ is the total number of spins in the two-dimensional lattice. The spin-wave Hamiltonian takes the form

$$H_{dip} = \sum_{R}^{X} A_{R} a_{R}^{Y} a_{R} + \frac{1}{2} B_{R} (a_{R} a_{R} + a_{R}^{Y} a_{R}^{Y})$$
(10)

The coe cients $A_{k} = A_{k}^{(0)} + A_{k}^{(2)}$ and $B_{k} = B_{k}^{(0)} + B_{k}^{(2)}$ can be expressed (see Appendix C) through the dipolar sum s (; = x;y;z)

$$D^{(n)}(\vec{k}) = \frac{X}{D_{j}^{3+n}} \frac{1}{D_{j}^{3+n}} 1 \qquad (3+n) \frac{D_{ij}D_{ij}}{D_{ij}^{2}} e^{i\vec{k}\cdot\vec{D}_{ij}}$$
(11)

where for n = 0 and n = 2 one has respectively the zero and second order expressions in the ratio $L=D_0$ between the linear dimension of the particle and the interparticle distance. The spin-wave energy is

In the continuum lim if $\tilde{\kappa}$! 0, one $% \tilde{\kappa}$ nds the approximate analytic expression

ĩč

$$\int_{0}^{h} \int_{1}^{1} () \frac{4 k}{ab} + 0 (k^{2}) \int_{0}^{1} () + \frac{4 k}{ab} \cos^{2} k + 0 (k^{2}) \int_{1=2}^{1} (13)$$

where $_0$ and $_1$, de ned in Appendix C, depend on the angle . In particular, $_0$ vanishes for the highly symmetric cases = =3 (triangular lattice) and = =2 (square lattice). The angle $_k$ de nes the orientation of the in-plane wavevector \tilde{k} with respect to the \hat{x} axis. It is worth stressing that $_{\rm R}$ has the same structure both at zero and second order, because H $_{\rm dip}^{(2)}$ does not contribute to the linear term in k. In particular, we have that the linear term in the quantity (A_R + B_R) vanishes when K is oriented along the magnetization ($_{\rm R}$ = =2). Its sign is therefore decided by the quadratic term, which is di erent for di erent lattices. It is positive for the triangular lattice (see Fig. 4) and it may be either positive (Fig. 5b) or negative (Fig. 5a) for the square lattice, depending on the orientation of the magnetization.

In Figs. 4,5 we show the dispersion relation of the spin waves, as obtained from Eq. (12), in the case of a triangular lattice (= =3) and of a square one (= =2), for di erent orientations $_k$.

In the remaining part of this Section we are making general comments on these results.

D ipolar interaction, since it couples the spins to the underlying lattice, is not rotationally invariant, contrary to, e.g., the Heisenberg interaction (H = $Jq_2 g$). Therefore, the energy of a generic spin con guration depends on how the spins are oriented with respect to the lattice. However, lattices with four-fold (= =2) or six-fold (= =3) symmetries are special, in the sense that the energy of certain con gurations (the ferrom agnetic one, for example) is rotationally invariant. This means that the dipolar ferrom agnetic ground state of a triangular lattice has a continuous degeneracy.

The coupling between spins and crystal lattice manifests itself in two ways (we are considering the highly symmetric cases, $_0() = 0$). First, the spin-wave energy $_{k}$ depends on the orientation of the wavevector in the continuum limit k ! 0 as well. A coording to Eq. (13), $_{k}$ jcos $_{k}$ jc¹⁻², showing that the $_{k}$ -dependence of $_{k}$ is maintained in the limit k ! 0.

Second, even if the energy of the FM state is degenerate with respect to its orientation in the plane, the spin-wave energy is not (see Fig. 5). This is true for the triangular lattice as well (not shown), but it has most striking consequences for the square lattice. In this case, the FM con guration is known to have a higher energy than the structure where spins are ferrom agnetically coupled along lines and antiferrom agnetically coupled between neighbouring lines.8 The FM state, if oriented along an axis of the square lattice (the typical con guration considered in the literature) is not even locally stable. This is clearly shown in Fig. 5a where the square of the spin-wave energy is plotted, in the case of \tilde{k} and M parallel to the a side of the square lattice. The square of the energy is negative, signaling that the corresponding FM state is unstable. However, if the magnetization is oriented along the diagonal, the FM state is no more unstable, as shown in Fig. 5b (we show just the case of it parallel to M , but no instability appears for any value of $_k$).

Figures 4 and 5 display the e $\operatorname{ect} of E_{dip}^{(2)}$ on the spinwave spectrum : the energy increases for any value and orientation of \tilde{K} . This result corroborates our statem ent that the nite size of the particles reinforces ferrom ag-



FIG. 4: Spin-wave dispersion curves calculated for the triangular lattice (rhom bic angle = =3) both numerically (Eq. (12), symbols) and in the continuum limit (Eq. (13), lines). Solid circles and full lines refer to $H_{dip}^{(0)}$; open circles and dashed lines refer to $(H_{dip}^{(0)} + H_{dip}^{(2)})$, with I = 0.1 (units with D₀ = 1 are used). The magnetization is assumed to lie along the \hat{y} axis and three di erent propagation directions are reported: (a) $_{k}$ = 0; (b) $_{k}$ = =6; (c) $_{k}$ = =2. Note the di erent periodicities of the spin-wave energy.

netism in the triangular lattice (Fig. 4). For the square lattice we have showed that ferrom agnetism is locally stable if M is oriented along a diagonal of the square lattice (Fig. 5b) and locally unstable if M is parallel to a side of the square lattice (Fig. 5a): $E_{\rm dip}^{(2)}$ reinforces the stability in the form er case and the instability in the latter one.



FIG. 5: The same as in Fig. 4, but for the square lattice (rhom bic angle = = 2). (a) W hen magnetization and wavevector K are directed along a side of the square lattice, the square of the spin-wave energy is found to be negative, signaling the instability of the ferrom agnetic con guration. (b) W hen magnetization and wavevector K are directed along the diagonal of the square, the ferrom agnetic state is found to be m etastable.

IV. THE CUR IE TEM PERATURE

The Curie transition temperature of an orthorom bic lattice of particles with magnetization directed in plane along the \circ axis can be estimated in the framework of spin-wave theory. The relative deviation of the magnetization from the saturation value takes the form ⁷

$$\frac{S}{S} = \frac{1}{N_k S} \frac{X}{k} h_k^y a_k i = \frac{V_2}{(2)^2 S}$$

$$Z \frac{X}{d^2 \kappa} \frac{A_k}{\kappa} \frac{1}{e^{\kappa^{-T}}} \frac{A_k}{1} \frac{A_k}{2\kappa} \qquad (14)$$

where V_2 is the volume of the two-dimensional unit cell and the integration is over the st B rillouin zone. The

rst term on the rh.s. of Eq. (14) gives the tem perature dependence of the magnetization, while the second term represents the zero-point spin deviation, which can be safely neglected. A rough estimate of the Curie tem perature $T_{\rm C}$ is obtained by in posing that S ($T_{\rm C}$)=S 1.

Since the only energy scale in the problem is given by the dipolar interaction, T_c is expected to be of order

 $W_{eff} = S^2 = D_0^3$ (g B s)² (L=a_0)⁴ (t=c_0)² = D_0^3, the e ective dipolar interaction between di erent particles.

The convergence of the integral (14) in $\tilde{K} = 0$ is easily proved.⁹ For generic orthorom bic lattices, it is guaranteed by the gap in the dispersion curve, $_0 \notin 0$. For square and triangular lattices, the spin-wave energy vanishes for $k \mid 0$ and one can expand the exponential on the denom inator of Eq.(14), because the possible divergence is infrared-like. Thus, the integral giving the temperature dependent spin deviation is found to converge, provided that the positive¹¹ O (k^2) term s in the spin-w ave energy are taken into account. Eq. (14) can be rew ritten as follow s:

$$\frac{S}{S} = \frac{T}{W_{eff}} \begin{bmatrix} Z_2 & Z_{q_{M}} \\ 0 & 0 \end{bmatrix} \frac{qdq}{c_1 q \cos^2 + c_2 q^2}$$
(15)

where $q = kD_0$, = k, c_1 and c_2 are positive constants, and q_1 1. The double integral can be easily evaluated, giving

$$\Gamma_{\rm C} = W_{\rm eff} \frac{C_2}{2} \ln \frac{q_1 + p_1 \frac{p_1}{q_1^2 + (c_1 = c_2)^2}}{c_1 = c_2} ! \#_1$$
 : (16)

In the lim it $c_1 = 0$, $_{\rm K} = c_2 q^2$ reproduces the dispersion curve of the H eisenberg ferrom agnet and the Curie tem perature $T_{\rm C}$ vanishes, in agreem ent with the M erm in-W agner theorem $.^{12}$

Finally, it is interesting to discuss the case where a uniaxial single-ion anisotropy , favouring the in-plane \hat{y} axis, is present in the system. The e ect of the nite size of the particle is straightforward, in this case:

$$E_{ani} = N \frac{X}{(S_{i}^{Y})^{2}} = \sim (S_{i}^{Y})^{2}$$
(17)
$$D_{i} D_{i}$$

where $\sim = = N$ and, as usual, S = N s.

The e $\,$ ect of $E_{\rm ani}$ on the spin-wave energy is simply to add the quantity 2 to $A_{\rm g}$; for large particles, this constant factor dom inates the dipolar term s in Eq. (13). Because of that, spin-wave approximation is no more suitable and Eq. (14) can not be used to evaluate $T_{\rm C}$: in fact, it would give a Curie temperature $T_{\rm C}$ $\,$ 2N $\,$, which diverges when $\,$! 1 .

On physical grounds, we expect that $T_{\rm C}$ is an increasing function of , but in the lim it of strong an isotropy, $T_{\rm C}$ is always of order W $_{\rm eff}$. An analogy can be done with the three dimensional Heisenberg model in the presence of an easy-axis anisotropy : $T_{\rm C}$ increases with , but $T_{\rm C}$ (0) and $T_{\rm C}$ (1) are of the same order of magnitude and are both of order J, the exchange coupling constant. In our case, W $_{\rm eff}$ replaces J and the dimension of the system is two instead of three (the two-dimensional Heisenberg model is not ordered at nite temperature in the absence of an isotropy).

In order to corroborate our argument, T_c will be calculated in the mean eld approximation, starting from

the H am iltonian

$$H^{MF} = \begin{array}{c} X & h \\ S_{i}^{Y} & \sim S_{i}^{Y} \end{array}$$
(18)

where $=\frac{1}{2}$ hS^y iD_{yy}⁽⁰⁾ (0). The magnetization is given by

$$hS^{y}i = \frac{\frac{P_{S}}{M = S} M e^{(M - M^{2})=T}}{\frac{P_{S}}{M = S} e^{(M - M^{2})=T}}$$
(19)

where M , M ² denote the eigenstates of S^Y, $(S^{Y})^{2}$ respectively. As T ! T_C one has $hS^{Y}i$! 0 so that ! 0 and the exponential can be expanded. Thus $hS^{Y}i$ $\frac{1}{T_{C}}R$ where R is de ned as

$$R = \frac{P_{S}}{\frac{P_{S}}{M = S} M^{2} e^{\frac{\gamma_{M}^{2}}{T_{c}}}}{P_{S}} = h(S^{y})^{2} i_{T_{c}} :$$
(20)

For ~ = 0 one has R = $\frac{1}{3}$ S (S + 1), so that T_C (~ = 0) = $\frac{1}{6}$ [D_{yy}⁽⁰⁾ (0)]S (S + 1) W_{eff}.

For ~ 60 the mean eld critical tem perature is

$$\frac{T_{C}(\tilde{})}{T_{C}(\tilde{}=0)} = \frac{3}{S(S+1)}h(S^{Y})^{2}\dot{I}_{T_{C}}; \qquad (21)$$

where the mean on the rhs. must be callated numerically. Now we observe that in the lim \pm $^{\prime}$! 1, one has $h(S^{\,y}\,)^2\,i_{T_C}$! S^2 , so that the ratio T_C (1)= T_C (0) tends to the nite value 3S=(S + 1). We conclude that for any value of $^{\prime}$, the Curie transition temperature remains of the order of the elective dipolar interaction $W_{\rm eff},$ with a prefactor changing by a factor three as $^{\prime}$ increases from 0 to 1.

V. DISCUSSION

Let us get back to the three questions formulated at the end of the Introduction.

i) ${\tt W}$ hat is the e ective dipolar interaction between single dom ain particles?

In the hypothesis that spins are strongly coupled ferrom agnetically inside each particle, it is straightforward to de ne an e ective dipolar coupling between (m icroscopic) spins s of two particles at distance D: W _{eff} =

(sN)²=D³, where = (g _B)² and N is the number of spins in each particle. If L and t are respectively its linear size and thickness, W _{eff} (g _B s)² (L=a₀)⁴ (t=c₀)²=D³. If a single-ion anisotropy is present, its e ective value is just¹³ _{eff} = N (L=a₀)² (t=c₀).

The full dipolar interaction between particles can be expanded in (even) powers of $(L=D)^m$. The st correction term (m = 2) gives an interaction decaying as $1=D^5$ with the distance between particles. A couple of remarks are in order here. First, the 'purely' spin term in the

dipolar interaction (i.e., the term not coupled to the lattice) is no m ore rotationally invariant: the z-com ponents are m ore strongly coupled than in-plane components. Second, $E_{dip}^{(2)}$ preserves two in portant features: it is m inim ized when spins are aligned ferrom agnetically along the joining line, and the dipolar eld generated by a 'continuum' line of spins aligned along the line in a point outside the line, vanishes.

ii) W hat is the dipolar ground state of an ordered array of m agnetic particles?

We have considered the class of orthorom bic lattices, which comprises the triangular and the square lattices. It is known that in the case of a lattice of spins, the ground state for the six-fold symmetry is ferrom agnetic and for the four-fold symmetry has zero net magnetization. These results are not modiled when single-domain particles replace single spins and E $_{\rm dip}^{(2)}$ is considered in addition to E $_{\rm dip}^{(0)}$. The elect of $E_{\rm tip}^{(2)}$ is to reinforce, in some sense, the elect of $E_{\rm dip}^{(0)}$. In particular, therefore, a triangular lattice of two dimensional particles interacting through the dipolar interaction has a ferrom agnetic ground state.

iii) W hat is the nite tem perature behaviour of a inplane ferrom agnetically ordered array of particles?

In two dimensional systems, long range order at nite temperature is not certain: how ever, the long range dipolar forces are known to grant it. In this respect, $E_{\rm dip}^{(2)}$ is of m inor in portance, because it decays as 1=D⁵ and consequently the dipolar sums in the K-space do not contribute to the terms linear in K, but to the quadratic terms only.

In the absence of an isotropies, it is elementary that the Curie temperature $T_{\rm C}$ is of order of the elective dipolar coupling, $T_{\rm C}$ $W_{\rm eff}$, because it is the only energy scale in the problem. If in-plane easy-axis an isotropies are present, we have shown that $T_{\rm C}$ is expected to increase, but not to change in order of magnitude: according to mean eld theory, $T_{\rm C}$ increases by a factor three passing from the Weak' an isotropy regime into the 'strong' an isotropy regime.

Denoting by w = $(g_B s)^2 = a_0^3$ the dipolar coupling between microscopic spins on a two-dimensional lattice with atom ic distance a_0 , the elective dipolar interaction between particles of linear dimension L and thickness t at distance D₀ can be rewritten as W_{eff} = w $(L=a_0)^4 (t=c_0)^2 = (D_0=a_0)^3$. Thus, the Curie temperature T_C W_{eff} of an ensemble of magnetic particles may be signi cantly larger than the Curie temperature of a two-dimensional lattice of microscopic spins, which is of order w. However, L cannot be made larger than D₀, because D₀ scales with L: at the best, therefore, T_C w $(L=a_0)(t=c_0)^2$.

Even if we have no de nite evaluation of the num erical prefactor appearing in the previous estimate for T_c , we suggest that regular arrays of two-dimensional particles magnetized in plane might sustain long range order at experimentally relevant temperatures (see also Ref. 14). However, this collective phenomenon may be masked by

the superparam agnetic behaviour of the single particle, appearing below the blocking tem perature $T_B = (L=a_0)^2$ (t=c_0).

The condition $T_B \ > \ T_C$ is equivalent to =w > $L^2 t=D_0^3$, where ~ is an unknown numerical factor. If such a condition is satis ed, the C urie phase transition at T = T_C is not visible because them odinam ic equilibrium cannot be attained below T_B . So, if we decrease tem perature from the high-T region each particle becomes superparamagnetic when dipolar forces are still unable to induce a long range order in the system . When T = T_C dipolar interaction comes into play, but the magnetization of each particle is frozen and the system is unable to attain equilibrium . In the opposite case, $T_C \ T_B$, a phase transition at T_C should be visible.

Recently, the system Co/Cu (001) has drawn the attention because it has been suggested 15,16 that for t < 1.8M L (M L=monolayer) this system displays a dipolar induced ferrom agnetic order. $T_{\rm C}$ (t) is seen 15 to be nite and increase from $T_{\rm C}$ (1M L)=25K to $T_{\rm C}$ (1.8M L)=200K , where it has a sudden jump, attributed to the percolation in the second layer.

The growth morphology of the system Co/Cu (001) is complicated by the alloying^{16,17} between the two elements, which mainly takes place in the rst layer (75% in Co, 25% in Cu). However, with such a high percentage of Cobalt, it is hard to suppose that the rst layer is made up of an ensemble of disconnected Co-islands which interact only through long range forces (in Ref. 16 the percolation threshold is theoretically estimated to be of order 60%). More likely, an in nite cluster of Cobalt does exist in the rst layer and therefore the magnetic behaviour of the system (and the value of $T_{\rm C}$) follows from the combining e $~\rm ect^{16}$ of the direct exchange interaction between spins and long range forces.

Finally, we would like to mention an additional di culty in the interpretation of experimental data concerning an array of magnetic islands: the random character of deposition and di usion gives rise to a non-uniform distribution of sizes and positions.¹⁴ This fact, along with frustration due to dipolar interaction, makes di cult even the determ ination of the ground state, because the system has a glassy behaviourw ith a lot of metastable states.

APPENDIX A : MULTIPOLAR EXPANSION OF INTERPARTICLE INTERACTION

We start from Eq. (1), assuming single monolayers.¹⁸ Summations on $\Re_{1,2}$ are replaced by sums on $r_{1,2}$ (see Fig.1 for notations):

W e m ake the expansions:

$$\frac{1}{R_{12}^3} = \frac{1}{D^3} + \frac{3r}{D^2} + \frac{3}{2} \frac{r^2}{D^2} + \frac{15}{2} \frac{(r}{D^4} + \frac{15}{2})^2$$
(A2)

The following expressions are easily calculated:

In the previous expressions, N $_{1;2}$ are the number of spins in the particles $I_{1;2}$ and $\tilde{V}_{1;2}$ are generic vectors.

It is always possible to choose the origin of the reference system for a given particle in its center of mass, so that $hr_i i = 0$ and the \m om ent of inertia" I_i of a particle is $I_i = hr_i^2 i$. Consequently, we have the following results

$$h(\mathcal{D} \quad \mathbf{i})^{2}\mathbf{i} = \frac{1}{2}D^{2}I_{\mathbf{i}} \qquad (A4)$$

$$h(\nabla_1 \quad \underline{i}) (\nabla_2 \quad \underline{i}) = \frac{1}{2} I_{\underline{i}} \nabla_1^k \quad \nabla_2^k \qquad (A5)$$

where $\widetilde{V}^{\,\,k}\,$ is the in-plane component of the generic vector ∇ .

If we de ne $I_{12} = \frac{1}{2}(I_1 + I_2)$ and $S_i = N_i s_i$, we obtain the following expression for the electric dipolar interaction between two particles at distance $\ensuremath{\mathbb{D}}$:

$$E_{dip} = \frac{1}{2} \frac{S_1^2 S_2^2}{D^3} 1 + \frac{9}{2} \frac{I_{12}}{D^2}$$
 (A 6)

+
$$\frac{1}{2} \frac{S_1^k S_2^k}{D^3} 1 + \frac{3}{2} \frac{I_{12}}{D^2}$$
 (A 7)

$$\frac{3}{2} \quad \frac{(S_1^k \ \vec{D}) (S_2^k \ \vec{D})}{D^5} \quad 1 + \frac{5}{2} \frac{I_{12}}{D^2} \quad (A8)$$

APPENDIX B:M IN IM IZATION OF THE DIPOLAR COUPLING BETWEEN TWO SPINS

Let us consider two unitary spins $S_1;S_2$ located at a distance R_{12} along the in-plane \hat{x} axis, taken as the polar axis, while the \hat{z} axis is perpendicular to the plane. Their orientations are dened by the polar and azim uthal angles $_{i};'_{i}$.

The dipolar coupling can be generally written as

$$E_{12} \qquad E_{12}^{(0)} + E_{12}^{(2)} \sim_{0} (S_{1} S_{2} 3S_{1}^{x}S_{2}^{x}) + \sim_{2} (2S_{1}^{z}S_{2}^{z} + S_{1} S_{2} 5S_{1}^{x}S_{2}^{x})$$

where $\sim_0 = \frac{1}{2} S^2 = R_{12}^3$ and $\sim_2 = \frac{3}{4}I_{12} S^2 = R_{12}^5$ (see Eqs. 3,4).

Both term s $E_{12}^{(0)}$ and $E_{12}^{(2)}$ are m in in ized by the same conguration. First, let us treat the zero-order term . We have to m in in ize the function

$$E_{12}^{(0)} = c_0 = \sin_1 \sin_2 \cos(\prime_1 \prime_2) 2\cos_1 \cos_2 (B1)$$

By taking the derivatives with respect to $'_{1;2}$ we nd that $('_1 \quad '_2) = 0$; or that one $_i$ at least must vanish. If, e.g., $_1 = 0$, it is straightforward to derive that $_2 = 0$ as well. If both $_{1;2}$ are not vanishing, taking the derivatives with respect to them in plies $\cos_1 = \cos_2 = 0$, i.e. $_{1;2} = \frac{1}{2}$. In simple words, it is su cient to consider two kinds of con gurations: i) the con guration where both spins are perpendicular to the joining vector and they are parallelor antiparallel; ii) the con guration where both spins are aligned along the joining vector. The form er con guration, with antiparallel spins, corresponds to the minimization of $(S_1 \quad S_2)$ and its energy is

 $^{\circ}_{0}$. The latter conguration, with parallel spins, corresponds to the minimization of $(3S_{1}^{x}S_{2}^{x})$ and its energy is $^{\circ}_{0} = 2^{\circ}_{0}$. We conclude that $E_{12}^{(0)}$ is minimized by the ferrom agnetic conguration with spins aligned along their joining vector.

The minimization of $E_{12}^{(2)}$ proceeds along the same lines, with the minor di erence that con gurations with both spins perpendicular to the joining line are no more degenerate with respect to a global rotation around the \hat{x} axis: the lowest energy one corresponds to antiparallel spins along the \hat{z} direction and its energy is \mathcal{F}_2 . On the other hand, the ferrom agnetic con guration with

both spins parallel to the x axis has the energy 4^{2} , so the conclusion is unchanged.

APPENDIX C:DIPOLAR SUM S FOR THE ORTHOROM BIC LATTICE

For spins ferrom agnetically oriented along the y axis, the coe cients of the spin-wave H am iltonian in Eq. (10) take the form

$$\frac{A_{\tilde{\kappa}}^{(0)}}{S} = \frac{1}{2} D_{zz}^{(0)} (\tilde{\kappa}) + \frac{1}{2} D_{xx}^{(0)} (\tilde{\kappa}) \quad D_{yy}^{(0)} (0)$$

$$\frac{B_{\tilde{\kappa}}^{(0)}}{S} = \frac{1}{2} D_{zz}^{(0)} (\tilde{\kappa}) \quad \frac{1}{2} D_{xx}^{(0)} (\tilde{\kappa}) + i D_{zx}^{(0)} (\tilde{\kappa}) \quad (C1)$$

and

*(*0)

$$\frac{A_{\kappa}^{(2)}}{S_{\pi}^{2}I} = \frac{1}{2}D_{zz}^{(2)}(\kappa) + \frac{1}{2}D_{xx}^{(2)}(\kappa) \quad D_{yy}^{(2)}(0) + E^{(2)}(\kappa)$$

$$\frac{B_{\kappa}^{(2)}}{S_{\pi}^{2}I} = \frac{1}{2}D_{zz}^{(2)}(\kappa) \quad \frac{1}{2}D_{xx}^{(2)}(\kappa) + iD_{zx}^{(2)}(\kappa) + E^{(2)}(\kappa)$$
(C 2)

where N is the number of spins in each particle and the dipolar sum s are de ned as (; = x;y;z)

$$D^{(n)}(\vec{k}) = \frac{X}{D_{j}} \frac{1}{D_{ij}^{3+n}} 1 \qquad (3+n) \frac{D_{ij}D_{ij}}{D_{ij}^{2}} e^{i\vec{k} D_{ij}} e^{i\vec{k} D_{ij}}$$
$$E^{(n)}(\vec{k}) = \frac{X}{D_{ij}} \frac{e^{i\vec{k} D_{ij}}}{D_{ij}^{3+n}} \qquad (C3)$$

We observe that in the ultra at particle limit, one has $E^{(n)}(\tilde{K}) = D_{zz}^{(n)}(\tilde{K})$ and $D_{zx}^{(n)}(\tilde{K}) = 0$ and the D 's can be approximately expressed

in terms of the dipolar sum s

$$X^{(n)}(k) = \frac{X}{D_{ij}^{(n)}} \frac{(D_{ij}^{(n)})^2}{D_{ij}^{(n)}} e^{ik D_{ij}}$$

$$Y^{(n)}(k) = \frac{X}{D_{ij}^{(n)}} \frac{(D_{ij}^{(n)})^2}{D_{ij}^{(n)}} e^{ik D_{ij}^{(n)}} (C5)$$

The latter sum s can be numerically calculated in a very e cient way following a method, developed some years ago by Benson and M $ills_{,}^{19}$ sim ilar to Ewald's one for the evaluation of lattice sum s. For n = 0 one has

$$X^{(0)}(k_x;k_y;a;b) = U^{(0)}(k_x;k_y) + V^{(0)}(k_x;k_y)$$
 (C6)

where U is a sum m ation over the sites of the orthorom bic lattice which are located at integer multiples of a and b

$$U^{(0)}(k_{x};k_{y}) = \frac{16}{3} \frac{1}{b} \frac{1}{b} \cos(k_{x}al)$$

$$\frac{\chi^{1}}{(\frac{m}{b} + \frac{k_{y}}{2})^{2}} K_{2} 2alj\frac{m}{b} + \frac{k_{y}}{2}j$$

while V refers to sem i-integer multiples

$$V^{(0)}(k_{x};k_{y}) = \frac{16}{3} \frac{1}{b} \sum_{l=0}^{k^{1}} \cos k_{x} a(l+\frac{1}{2})$$

$$\overset{X^{1}}{\underset{m=1}{}} (1)^{m} (\frac{m}{b} + \frac{k_{y}}{2})^{2} K_{2} 2a(l+\frac{1}{2}) \frac{m}{b} + \frac{k_{y}}{2} j$$

For n = 2 one has

$$X^{(2)}(k_x;k_y;a;b) = U^{(2)}(k_x;k_y) + V^{(2)}(k_x;k_y)$$
 (C7)

where

$$U^{(2)}(k_{x};k_{y}) = \frac{32}{15} \frac{1}{ab} \sum_{l=1}^{k^{1}} \frac{\cos(k_{x}al)}{l}$$

$$\frac{k^{1}}{ab} (\frac{m}{b} + \frac{k_{y}}{2})^{3}K_{3} 2alj\frac{m}{b} + \frac{k_{y}}{2}j$$

and

$$V^{(2)}(k_{x};k_{y}) = \frac{32}{15} \frac{1}{ab} \frac{X^{1}}{1_{l=0}} \frac{\cos k_{x}a(l+\frac{1}{2})}{(l+\frac{1}{2})}$$

$$\overset{X^{1}}{\underset{m=-1}{}} (1)^{m} (\frac{m}{b} + \frac{k_{y}}{2})^{3}K_{3} 2a(l+\frac{1}{2})\frac{m}{b} + \frac{k_{y}}{2}j$$

Here above, K $_2$ (z) and K $_3$ (z) are the modi ed Bessel functions of second and third order, respectively. By symmetry reasons, one has

$$Y^{(n)}(k_x;k_y;a;b) = X^{(n)}(k_y;k_x;b;a)$$
 (C8)

Finally, in the continuum limit $\tilde{k} ! 0$, one can obtain analytical expressions for the dipolar sum s. D enoting by k the modulus of the two-dimensional wavevector $\tilde{k} = (k_x; k_y)$ and by k the angle that \tilde{k} form swith the \hat{x} axis, we obtain

$$X^{(0)}(k) \qquad X^{(0)}(0) \qquad \frac{2}{ab} k \qquad 1 + \frac{1}{3} \cos(2_k)$$
$$Y^{(0)}(k) \qquad Y^{(0)}(0) \qquad \frac{2}{ab} k \qquad 1 \qquad \frac{1}{3} \cos(2_k) \qquad (C9)$$

and

$$\begin{array}{ll} X^{(2)}(k) & X^{(2)}(0) + O(k^2) \\ Y^{(2)}(k) & Y^{(2)}(0) + O(k^2) \end{array} (C10) \end{array}$$

where for the triangular lattice one has $X^{(0)}(0) = 5.5170879=D_0^3$, $X^{(2)}(0) = 3.3809493=D_0^3$ and for the square lattice $X^{(0)}(0) = 4.5168109=D_0^3$, $X^{(2)}(0) = 2.5451291=D_0^3$. From the previous expressions one obtains approximate expansions for the quantities in Eqs. (12,14):

$$\frac{A_{\underline{k}} - B_{\underline{k}}}{S} = 0 + \frac{4 k}{ab} \cos^2 k + 0 (k^2)$$

$$\frac{A_{\underline{k}} + B_{\underline{k}}}{S} = 1 - \frac{4 k}{ab} + 0 (k^2)$$

$$\frac{A_{\underline{k}}}{S} = 2 - \frac{2 k}{ab} \sin^2 k + 0 (k^2) \quad (C 11)$$

where

$$\begin{array}{rcl} & & & & & & \\ _{0} & = & 3 & Y & ^{(0)} & (0) & & X & ^{(0)} & (0) & + & \frac{15}{2} I & Y & ^{(2)} & (0) & & X & ^{(2)} & (0) \\ \\ _{1} & = & 3Y & ^{(0)} & (0) & + & \frac{3}{2} I & ^{h} & ^{T} Y & ^{(2)} & (0) & + & 2X & ^{(2)} & (0) \\ \\ _{2} & = & & \frac{3}{2} & ^{h} & ^{2} Y & ^{(0)} & (0) & & X & ^{(0)} & (0) & + & \frac{9}{4} I & ^{H} & ^{(2)} & (0) & & X & ^{(2)} & (0) \\ \end{array}$$

$$(C 12)$$

Hence we observe that for a generic orthorom bic lattice one has X ⁽ⁿ⁾ (0) \notin Y ⁽ⁿ⁾ (0), so that the dispersion curve $_{\mathfrak{K}} = (A_{\mathfrak{K}} \quad B_{\mathfrak{K}})(A_{\mathfrak{K}} + B_{\mathfrak{K}})^{1=2}$ presents a gap for \mathfrak{K} ! 0. For the special cases of the triangular and the square lattice one has X ⁽ⁿ⁾ (0) = Y ⁽ⁿ⁾ (0) by symmetry reasons; this im plies that $_{0} = 0$, so that a G oldstone mode is present in the dispersion curve: $_{\mathfrak{K}}$! 0 for \mathfrak{K} ! 0.

ACKNOW LEDGMENTS

W e thank Angelo R ettori for his critical reading of the manuscript.

Corresponding author.

Electronic address: politi@ifac.cnr.it

^Y E lectronic address: m gpini@ ifac.cnr.it

- ¹ A.Pimpinelli, J.V illain, Physics of CrystalG rowth (Cambridge University Press, Cambridge, 1998).
- ² B.Voigtlander, G.Meyer, and NM.Amer, Phys.Rev.B 44, 10354 (1991); H.Takeshita et al, Appl.Phys.Lett. 68, 3040 (1996).
- ³ H.Brune, M.Giovannini, K.Brom ann, and K.Kem, Nature 394, 451 (1998).
- ⁴ R M H.New, R F W. Pease, and R L.W hite, J.Vac.Sci. Technol.12, 3196 (1994); S.Y.Chou, P R.K rauss, and L. Kong, J.Appl.Phys.79, 6101 (1996); J.I.Martin et al., J.Appl.Phys.84, 411 (1998).
- ⁵ P.Politi and M G.Pini, Eur. Phys. J.B 2, 475 (1998).
- ⁶ C. Stamm, F. Marty, A. Vaterlaus, V. Weich, S. Egger, U. Maier, U. Ram sperger, H. Fuhrmann, and D. Pescia, Science 282, 449 (1998).
- ⁷ S.V.Maleev, Sov.Phys.JETP 43, 1240 (1977).
- ⁸ V.M.Rozenbaum, V.M.Ogenko, and A.A.Chuiko, Sov. Phys.Usp. 34, 883 (1991).
- ⁹ Yu.M. Malozovsky and V.M. Rozenbaum, Physica A 175, 127 (1991).

- ¹⁰ A.A.Fraem an and M.V.Sapozhnikov, J.M agn.M agn. M ater. 192, 191 (1999).
- ¹¹ This condition rules out the square lattice magnetized along a square side.
- ¹² N.D.Merm in and H.W agner, Phys. Rev. Lett. 17, 1133 (1966); ibidem, 1307 (1966).
- 13 $_{\rm eff}$ should not be m is taken for $^{\sim}$. The form er is the elective an isotropy for a m icroscopic spin s, the latter for the giant spin S .
- ¹⁴ P.J.Jensen and G.M. Pastor, Phys. Stat. Sol. A 189, 527 (2002).
- ¹⁵ U.Bovensiepen, P.Poulopoulos, W.Platow, M.Farle, and K.Baberschke, J.Magn.Magn.Mater. 192, L386 (1999).
- ¹⁶ P.Poulopoulos, P.J.Jensen, A.Ney, J.Lindner, and K. Baberschke, Phys.Rev.B 65, 064431 (2002).
- ¹⁷ J.Fassbender, R.Allenspach, and U.Durig, Surf.Sci.383, L742 (1997).
- 18 Let us rem ind that E $_{\text{dip}}$ is just linear in $t_1{=}c_0$ and $t_2{=}c_0$.
- ¹⁹ H.Benson and D.L.M ills, Phys. Rev. 178, 839 (1969).