

¹¹⁵In-NQR evidence for unconventional superconductivity in CeIn₃ under pressureS. Kawasaki¹, T. Mito², Y. Kawasaki¹, G.-q. Zheng¹, Y. Kitaoka¹, H. Shishido³, S. Araki⁴, R. Settai³ and Y. Onuki^{3,4}¹*Department of Physical Science, Graduate School of Engineering Science, Osaka University, Osaka 560-8531, Japan*²*Faculty of Science, Kobe University, Kobe, Hyogo 657-8501, Japan*³*Department of Physics, Graduate School of Science, Osaka University, Toyonaka, Osaka 560-0043, Japan*⁴*Advanced Science Research Center, Japan Atomic Energy Research Institute, Tokai, Ibaraki 319-1195, Japan*

(March 22, 2022)

We report evidence for unconventional superconductivity in CeIn₃ at a pressure $P = 2.65$ GPa above critical pressure ($P_c \sim 2.5$ GPa) revealed by the measurements of nuclear-spin-lattice-relaxation time (T_1) and ac-susceptibility (ac- χ). Both the measurements of T_1 and ac- χ have pointed to a superconducting transition at $T_c = 95$ mK, which is much lower than an onset temperature $T_{onset} = 0.15$ K at zero resistance. The temperature dependence of $1/T_1$ shows no coherence peak just below T_c , indicative of an unconventional nature for the superconductivity induced in CeIn₃.

PACS: 74.25.Ha, 74.62.Fj, 74.70.Tx, 75.30.Kz, 76.60.Gv

I. INTRODUCTION

Since the discovery of cerium (Ce) based heavy-fermion (HF) superconductivity in CeCu₂Si₂¹, many experimental works on CeCu₂Ge₂,² CeIn₃^{3,4,5} and CePd₂Si₂⁶ have suggested that the antiferromagnetism and superconductivity are closely related each other. The discovery of pressure (P)-induced HF superconductivity in Ce-based HF antiferromagnetic (AF) compounds has stimulated further experimental works under P .^{7,8,9,10} Recently, a new HF material CeRhIn₅ consisting of alternating layers of CeIn₃ and RhIn₂ was found to reveal an AF to superconducting (SC) transition at a relatively lower critical pressure $P_c = 1.63$ GPa than in previous examples.^{2,3,6} The SC transition temperature $T_c = 2.2$ K is the highest one to date among P -induced superconductors.⁷ This finding has opened a way to investigate the P -induced evolution of both magnetic and SC properties over a wide P range. In the previous paper¹⁰, the ¹¹⁵In-NQR study of CeRhIn₅ has clarified the P -induced anomalous magnetism and unconventional superconductivity. At $P = 2.1$ GPa, the nuclear spin-lattice relaxation rate $1/T_1$ reveals a T^3 dependence below the SC transition temperature T_c , which shows the existence of line-node in the gap function.¹⁰ Note that the unconventional superconductivity in CeMIn₅ ($M = \text{Co, Rh, Ir}$) occurs at the border of the AF phase.^{7,10,12,13}

It is suggested that P -induced superconductivity in CeIn₃, which is the host crystal of CeMIn₅, is also mediated by AF magnetic fluctuations from resistivity measurements under P .³ However, evidence for a bulk superconductivity and whether it is mediated by AF magnetic fluctuations or not in CeIn₃ has not been established because its superconductivity under P is observed only in the resistivity measurements.^{3,4,5} It is still unclear whether any problem concerning a sample surface or its

quality that could prevent the onset of bulk P -induced superconductivity is ruled out or not. This is in contrast to the case of CeRhIn₅ where the bulk nature of the SC phase was fully established^{10,17} over a wide P range 2 – 5 GPa⁴. Note that the P -induced superconductivity in CeRhIn₅ occurs in the non-Fermi-liquid state in the whole P range.⁴

CeIn₃ crystallizes in the cubic AuCu₃ structure and orders antiferromagnetically ($T_N = 10$ K) at $P = 0$ with an ordering vector $\mathbf{Q} = (1/2, 1/2, 1/2)$.¹⁴ T_N monotonically decreases with P and superconductivity appears below $T_c \sim 0.2$ K at a critical pressure $P_c = 2.55$ GPa and the onset of superconductivity has been observed by the resistivity measurements and is limited in a narrow P range of about 0.5 GPa.^{3,6,15} Also it is reported that non-Fermi-liquid regime in CeIn₃ under P is limited in a quite narrow P range around the peak of resistive T_c in the SC phase.⁵ The previous ¹¹⁵In-NQR result on CeIn₃ revealed that the AF order disappears around $P^* = 2.44$ GPa close to P_c and the Fermi-liquid behavior was observed below 10 K at $P = 2.74$ GPa¹⁶. In the previous paper¹³, we reported that the localized magnetic character is robust against the application of P up to 1.9 GPa, beyond which T^* , which marks an evolution into an itinerant magnetic regime, increases rapidly. It is of great interest that the superconductivity in CeIn₃ emerges in such an itinerant regime. The window for the 3D AF fluctuation regime with respect to an external pressure is much narrower in CeIn₃ than in CeRhIn₅, which may also be partly responsible for the narrower SC region in CeIn₃.

In this paper, we report measurements of $1/T_1$ and ac-susceptibility at $P = 2.65$ GPa down to $T = 50$ mK which provide evidence for unconventional and bulk nature of superconductivity in CeIn₃. At $P = 2.65$ GPa, from the relation of $T_1 T = \text{const.}$ below $T_{FL} \sim 5$ K char-

acteristic for the Fermi-liquid state, we conclude that the P -induced superconductivity occurs well below T_{FL} without any signature for a non-Fermi-liquid behavior governed by AF spin-fluctuations. Our result is consistent with the recent resistivity measurements.⁵ This is in contrast to the case of CeRhIn₅ where superconductivity occurs *only* in the non-Fermi-liquid regime.⁴

II. EXPERIMENTAL

The single crystals of CeIn₃ were grown by Czochralski method as reported elsewhere¹⁸ and moderately crushed into grains in order to make rf pulses penetrate into samples easily. To avoid some crystal distortions, however, the size of the grains is kept with diameters larger than 100 μ m. In a small piece of CeIn₃ from the same batch used in this work, the zero resistance transition was confirmed in the P range of 2.2 – 2.8 GPa. The phase diagram inferred from the resistivity data is shown in the inset of Fig. 4b,⁴ which is in good agreement with the previous reports.^{3,5} At $P = 2.5$ GPa that is close to a critical pressure P_c , the T_c determined by the resistivity measurement reaches a maximum value of $T_c = 0.19$ K and its transition width becomes the sharpest. Measurement of $1/T_1$ was made by the conventional saturation-recovery method in the temperature (T) range of 0.05 – 100 K at $P = 2.65$ GPa. The ¹¹⁵In-NQR $1/T_1$ was measured at the transition of $3\nu_Q$ ($\pm 5/2 \leftrightarrow \pm 7/2$) above $T = 1.4$ K, but at $1\nu_Q$ ($\pm 1/2 \leftrightarrow \pm 3/2$) below $T = 1.4$ K. The ac-susceptibility ($ac-\chi$) was measured by using an *in-situ* NQR coil. Hydrostatic pressure was applied by utilizing a NiCrAl-BeCu piston-cylinder cell, filled with Si-based organic liquid as a pressure-transmitting medium. To calibrate the pressure at low temperatures, the shift in T_c of Sn metal under pressure was monitored by the resistivity measurement.¹⁹ To reach the lowest temperature of 50 mK, a ³He-⁴He dilution refrigerator is used.

III. EXPERIMENTAL RESULT

Figures 1 and 2 show the respective T dependencies of $1/T_1$ and $1/T_1T$ at $P = 0, 2.35$, and 2.65 GPa. At $P = 0$, the AF order occurs at $T_N = 10$ K without any clear signature for an itinerant HF regime. Rather, in the paramagnetic state, the $4f$ -electron derived moments behave as if localized, since $1/T_1$ stays a constant. It was reported that T_N monotonically decreases with pressure and eventually is reduced to $T_N = 5$ K at $P = 2.35$ GPa. At this pressure, it is noteworthy that $1/T_1$ starts to decrease below $T^* \sim 15$ K. This is defined as a characteristic temperature below which the system crosses over to the itinerant HF regime.¹³ At pressures exceeding $P = 2.35$ GPa, the internal field at the ¹¹⁵In site due to the AF ordering decreases, revealing a same P dependence as T_N .^{16,20} At $P = 2.65$ GPa, it is remarkable, as presented

in Figs. 1 and 2, that $1/T_1$ shows a significant decrease below $T^* \sim 30$ K, followed by a behavior of $T_1T = \text{const.}$ that is characteristic for the Fermi-liquid state to be realized below $T_{FL} = 5$ K. This result proves that the Fermi-liquid description is valid over a wide T range 0.1 – 5 K at $P = 2.65$ GPa. Any trace of AF spin-fluctuations at $P = 2.65$ GPa is not appreciable due to an increase of the hybridization of Ce- $4f$ electrons and conduction electrons as discussed in the previous paper.¹³ This is in good agreement with the recent resistivity measurement.⁵

Next, we discuss about the superconductivity in CeIn₃ at $P = 2.65$ GPa. The SC transition at $P = 2.65$ GPa is evidenced by the $1/T_1$ measurement. As seen in Figs. 1 and 2, below $T_c = 95$ mK, $1/T_1$ decreases suddenly, signaling the onset of bulk SC transition. In addition, the absence of the coherence peak in $1/T_1$ just below T_c is consistent with an anisotropic SC gap. The T_1 measurement below 50 mK was too hard to determine the nodal structure because of a heat-up problem arising from the exciting rf pulses.

The SC transition is also corroborated by the $ac-\chi$ measurement. The T dependence of the $ac-\chi$ at $P = 2.65$ GPa is shown in Fig. 3. The absolute value of susceptibility was determined by using a single crystals of CeIrIn₅ as a reference in which bulk superconductivity is fully established.²¹ The $ac-\chi$ decreases below $T_c \sim 95$ mK due to the SC diamagnetism, indicating a clear signature of a SC transition. The diamagnetic signal of CeIn₃ reaches 80% of the value of CeIrIn₅. It indicates the P -induced superconductivity in CeIn₃ is the bulk one. Note that the T_c probed by the T_1 and $ac-\chi$ measurements is lower than $T_c^p \sim 0.15$ K at zero resistance on the same sample.⁴ This suggests that the surface of the sample makes a short cut for the electrical current flow, exhibiting a rather higher T_c value than that for the bulk one. This phenomenon is similar to the SC characteristics in CeIrIn₅, in which the bulk $T_c \sim 0.4$ K confirmed by the measurements of the specific heat, the susceptibility¹¹, and the NQR measurements¹² is much lower than $T_c \sim 1$ K determined by the zero resistance. A reason why this inconsistency occurs is still unresolved.

Note that, at $P = 2.65$ GPa, the normal state is dominated by the Fermi-liquid excitations below $T_{FL} = 5$ K that is far above $T_c = 95$ mK, but not by AF spin-fluctuations. The superconductivity occurs thus in the Fermi-liquid regime, contrasting with the unconventional superconductivity in CeCu₂Si₂⁹ and CeMnIn₅^{10,12} both of which reveal a higher T_c near the border of AF and SC transitions in the non-Fermi-liquid state. Fig. 4a indicates the T dependence of $1/T_1T$ in CeRhIn₅ at $P = 2.1$ GPa where the superconductivity is fully established.¹⁰ This T dependence was consistent with the AF spin-fluctuation model²² near a magnetic criticality. Most remarkably, the P -induced superconductivity in CeRhIn₅ occurs under the dominance of strong AF spin-fluctuations near the border to the AF phase. As seen in Figs. 4a and 4b, the behavior of $1/T_1T = \text{const.}$ in CeIn₃ strongly contrasts with that in CeRhIn₅. This

difference in magnetic fluctuations is suggested to be intimately related to the fact that the maximum $T_c^{max} = 2.1$ K in CeRhIn₅ is an order magnitude larger than $T_c^{max} = 0.2$ K in CeIn₃. Note that T_c is much smaller for CeIn₃ because non-Fermi-liquid and AF spin-fluctuations regime is limited in quite narrow P range^{5,13} than that in CeCu₂Si₂ and CeRhIn₅. For the latter, the superconductivity occurs at the border of the AF phase where the non-Fermi liquid takes place and even coexists with it. This may be related to the robustness of SC region against increasing P for the latter.¹³ It is an issue to study in future whether or not the superconductivity and the antiferromagnetism in CeIn₃ coexist and whether or not the AF magnetic fluctuations in the non-Fermi-liquid state raise T_c near the border of AF and SC phases.

IV. CONCLUSION

In conclusion, we have provided evidences for the bulk and unconventional superconductivity in CeIn₃ below 95 mK at $P = 2.65$ GPa on the basis of the measurements of T_1 and ac-susceptibility. We have found that the system changes the magnetic character from the localized to itinerant regime below $T^* \sim 30$ K and the Fermi-liquid description becomes valid below $T_{FL} \sim 5$ K without any appreciable trace of AF spin-fluctuations developing. $1/T_1$ reveals no coherence peak just below $T_c = 95$ mK, indicative of unconventional superconductivity. We remark that the P -induced SC phase in CeIn₃ is characterized by a lower T_c and a narrower SC region than in CeRhIn₅ where SC phase coexists with the AF phase and $T_c = 2.1$ K is obtained in virtue of the non-Fermi-liquid state dominated by strong AF spin-fluctuations.

ACKNOWLEDGEMENTS

We thank K. Ishida and C. Thessieu for useful discussions. This work was supported by the COE Research (10CE2004) in Grant-in-Aid for Scientific Research from the Ministry of Education, Sport, Science and Culture of Japan. One of the author (Yu Kawasaki) has been supported by JSPS Research Fellowships for Young Scientists.

- ⁴ T. Muramatsu *et al.*, Ph. D. Thesis, Osaka University (2001), unpublished.
- ⁵ G. Knebel, D. Braithwaite, P. C. Canfield, G. Lapertot, and J. Flouquet, Phys. Rev. B. **65**, 024425 (2002).
- ⁶ F. M. Grosche *et al.*, Physica B **223-224**, 50 (1996); J. Phys. Condens. Matter **13**, 2845 (2001). J. Flouquet *et al.*, unpublished.
- ⁷ H. Hegger, C. Petrovic, E. G. Moshopoulou, M. F. Hundley, J. L. Sarrao, Z. Fisk, and J. D. Thompson, Phys. Rev. Lett. **84**, 4986 (2000).
- ⁸ P. Gegenwart, C. Langhammer, C. Geibel, R. Helfrich, M. Lang, G. Sparn, F. Steglich, R. Horn, L. Donnevert, A. Link and W. Assmus, Phys. Rev. Lett. **81**, 1501 (1998).
- ⁹ Y. Kawasaki, K. Ishida, T. Mito, C. Thessieu, G.-q. Zheng, Y. Kitaoka, C. Geibel and F. Steglich, Phys. Rev. B **63**, R140501 (2001).
- ¹⁰ T. Mito, S. Kawasaki, G.-q. Zheng, Y. Kawasaki, K. Ishida, Y. Kitaoka, D. Aoki, Y. Haga, and Y. Ōnuki, Phys. Rev. B **63**, 220507(R) (2001).
- ¹¹ C. Petrovic, R. Movshovich, M. Jaime, P.G. Pagliuso, M. F. Hundley, J. L. Sarrao, Z. Fisk, and J. D. Thompson, Europhys. Lett. **53**, 354 (2001).
- ¹² G.-q. Zheng, K. Tanabe, T. Mito, S. Kawasaki, Y. Kitaoka, D. Aoki, Y. Haga, and Y. Ōnuki, Phys. Rev. Lett. **86**, 4664 (2001).
- ¹³ S. Kawasaki, T. Mito, G.-q. Zheng, C. Thessieu, Y. Kawasaki, K. Ishida, Y. Kitaoka, T. Muramatsu, T. C. Kobayashi, D. Aoki, S. Araki, Y. Haga, R. Settai, and Y. Ōnuki, Phys. Rev. B. **65**, 020504(R) (2002).
- ¹⁴ P. Morin, C. Vettier, J. Flouquet, M. Konczykowski, Y. Lassailly, J. -M. Mignot, and U. Welp, J. Low Temp. Physics **70**, 377 (1988).
- ¹⁵ I. R. Walker, F. M. Grosche, D. M. Freye, G. G. Lonzarich, Physica C **282-287**, 303 (1997).
- ¹⁶ Y. Kohori, T. Kohara, Y. Yamato, G. Tomka, P. C. Riedi, Physica B **281 & 282**, 12 (2000).
- ¹⁷ R. A. Fisher, F. Bouquet, N. E. Phillips, M. F. Hundley, P. G. Pagliuso, J. L. Sarrao, Z. Fisk, and J. D. Thompson, cond-mat/0109221
- ¹⁸ Y. Ōnuki *et al.*, unpublished.
- ¹⁹ T. F. Smith, C. W. Chu, M. B. Maple, Cryogenics. **9**, 53 (1969).
- ²⁰ C. Thessieu, K. Ishida, S. Kawasaki, T. Mito, Y. Kawasaki, G.-q. Zheng, Y. Kitaoka and Y. Ōnuki, Physica B. **281-282**, 9-11 (2000).
- ²¹ A. Sumiyama, D. Katayama, Y. Oda, Y. Inada, D. Aoki, Y. Tokiwa, Y. Haga and Y. Ōnuki, J. Phys.: Condens. Matter **13**, L879-L884 (2001).
- ²² T. Moriya and T. Takimoto, J. Phys. Soc. Jpn. **64**, 960 (1995).

FIG. 1. T dependence of $^{115}(1/T_1)$ in CeIn₃ at $P = 0$, 2.35 and 2.65 GPa. The dotted line indicates a relation of $^{115}(1/T_1 T) = \text{const.}$

FIG. 2. T dependence of $^{115}(1/T_1 T)$ in CeIn₃ at $P = 0$, 2.35 and 2.65 GPa. The dotted line indicates a relation of $^{115}(1/T_1 T) = \text{const.}$

¹ F. Steglich, J. Aarts, C. D. Bredl, W. Lieke, D. Meshede, W. Franz and H. Schafer, Phys. Rev. Lett. **43**, (1979) 1892.
² D. Jaccard, K. Behnia, and J. Sierro, Phys. Lett. A **163**, 475 (1992).
³ N. D. Mathur, F. M. Grosche, S. R. Julian, I. R. Walker, D. M. Freye, R. K. W. Haselwimmer and G. G. Lonzarich, Nature **394**, 39 (1998).

FIG. 3. T dependence of ac-susceptibility in CeIn_3 at $P = 2.65$ GPa. The solid arrow indicates the onset temperature of superconductivity.

FIG. 4. (a) T dependence of $^{115}(1/T_1T)$ in CeRhIn_5 at $P = 2.1$ GPa.¹⁰ The solid arrow indicates T_c . The inset shows the P - T phase diagram of CeRhIn_5 .¹³ (b) T dependence of $^{115}(1/T_1T)$ in CeIn_3 at $P = 2.65$ GPa. The solid (dashed) arrow indicate $T_c(T_{FL})$. The dotted line indicates a relation of $^{115}(1/T_1T) = \text{const.}$. The inset shows the P - T phase diagram of CeIn_3 .¹³







