

December 27, 2021

Electronic structures of La_3S_4 and Ce_3S_4

J. H. Shim¹, Kyoo Kim¹, B. I. Min¹, and J.-S. Kang²

¹ *Department of Physics, Pohang University of Science and Technology, Pohang 790-784, Korea*

² *Department of Physics, The Catholic University of Korea, Puchon 420-743, Korea*

Abstract

We have investigated electronic structures of La_3S_4 and Ce_3S_4 using the LSDA and LSDA+ U methods. Calculated density of states (DOS) are compared with the experimental DOS obtained by the valence band photoemission spectroscopy. The DOS at E_F indicates the $5d$ character in La_3S_4 and $4f$ character in Ce_3S_4 . It is found to be nearly half metallic in the ferromagnetic ground state of Ce_3S_4 . We discuss the superconductivity and structural transition in La_3S_4 , and the absence of structural transition in Ce_3S_4 .

Keywords: La_3S_4 , Ce_3S_4 , electronic structure, band Jahn-Teller

Corresponding author:

Prof. B. I. Min,

Department of Physics,

Pohang University of Science and Technology,

Pohang, 790-784, KOREA

(e-mail) bimin@postech.ac.kr

(Fax) +82-54-279-3099

Typeset using REVTeX

The Th_3P_4 -type La_3S_4 undergoes cubic to tetragonal transition at ~ 103 K, and shows superconductivity at $T_c = 8.3$ K [1]. On the other hand, Ce_3S_4 with the same structure shows no tetragonal distortion and has ferromagnetic ground state with the transition temperature of ~ 7.2 K [2]. The structural transition in La_3S_4 has been explained by the band Jahn-Teller mechanism, in which the degenerate La e_g band induces the tetragonal phase transition [3,4]. It has been suggested that the existence of $4f$ band at Fermi level (E_F) in Ce_3S_4 prevents the band Jahn-Teller type structural transition [5]. However the electronic structures of La_3S_4 and Ce_3S_4 have not been confirmed yet.

In this study, we have investigated electronic structures of La_3S_4 and Ce_3S_4 using the local spin-density approximation (LSDA) and the LSDA+ U method on the basis of the linearized muffin-tin orbital (LMTO) band method. In the LSDA+ U method, the spin-orbit interaction is taken into account in the self-consistent variational loop, so that the orbital polarization is properly taken into account [6]. The angular momentum projected local density of states (PLDOS) is compared to the result of photoemission spectroscopy (PES). Samples were fractured and measured in vacuum with a base pressure better than 3×10^{-11} Torr and at $T \approx 15$ K. Experimental details will be reported elsewhere [7].

The LSDA DOSs of La_3S_4 in the paramagnetic ground state are shown in Fig. 1. La $5d$ and S $3p$ PLDOSs are very similar each other, reflecting the large hybridization between them. Small DOS peak appears near E_F corresponding to the tail of huge unoccupied DOS above E_F . The main contribution to $N(E_F)$ comes from La $5d$ states ($\sim 60\%$). The superconductivity of La_3S_4 is due to the high DOS of La $5d$ states at E_F . From the cubic to tetragonal structure, the bands at E_F are split and the DOS becomes a bit wider, as is consistent with the band Jahn-Teller model. But Fig. 1(b) shows that t_{2g} states are dominant at $N(E_F)$ rather than the e_g states. Hence, it is not compatible with the band Jahn-Teller model assuming the degenerate e_g bands near $N(E_F)$. The present study indicates that a modified band Jahn-Teller model considering realistic band structures is required.

Figure 2(a) provides the DOSs of ferromagnetic Ce_3S_4 obtained by using the LSDA+ U method. We use the parameters of the on-site Coulomb interaction $U = 7.0$ eV and the

exchange $J = 0.98$ eV for the Ce $4f$ electrons. The majority occupied spin $4f$ band is located near -2 eV, and the second majority spin $4f$ band is near E_F , whereas minority spin $4f$ bands are all above E_F . The minority spin states are negligible at E_F , suggesting that Ce_3S_4 is nearly half metallic in the ferromagnetic ground state. The large contribution to $N(E_F)$ comes from mainly Ce $4f$ states ($\sim 87\%$), which is compatible with the previous analysis that the existence of f electrons at E_F prevents the band Jahn-Teller type structural transition in Ce_3S_4 [5]. The calculated spin and orbital magnetic moments for Ce are $1.27 \mu_B$ and $-2.81 \mu_B$, respectively.

Figure 2(b)-(d) compare the PLDOSs to the measured partial spectral weight (PSW). Figure 2(b) presents the comparison of Ce $4f$ PLDOS with the extracted Ce $4f$ PSW obtained by the Ce $4d \rightarrow 4f$ on-resonance spectrum ($h\nu = 121$ eV). Ce $4f$ PSW exhibits the prominent features at -0.5 eV, -2.5 eV, and -5.5 eV. Although the main Ce $4f$ PLDOS states are ~ 0.5 eV off from the experimental result, the LSDA+ U calculation provides a reasonably good description of electronic structure of Ce_3S_4 . Likewise, there are good agreements between Ce $5d$ and S $3p$ PLDOSs and the Ce $5d$ ($h\nu = 26$ eV) and S $3p$ ($h\nu = 18$ eV) PSWs.

In conclusion, we have studied the electronic structures of La_3S_4 and Ce_3S_4 using the LSDA and LSDA+ U methods, and the PLDOSs are compared to the measured PSWs. The DOS of La_3S_4 shows the high contribution from the La $5d$ character at E_F . For the ferromagnetic Ce_3S_4 , the DOS at E_F shows mainly Ce $4f$ character. Nearly half metallic LSDA+ U band structure for Ce_3S_4 provides the good agreement with experimental results.

Acknowledgments— This work was supported by the KRF grant (KRF-2002-070-C00038). JSK acknowledges the support from the Catholic University of Korea (20020019).

REFERENCES

- [1] K. Westerholt *et al.*, Solid State Commun. 31 (1979) 961.
- [2] H. Fütterer, Ph. D. Thesis, Ruhr-Universität, Bochum (1988).
- [3] D. K. Ray *et al.*, Solid State Commun. 38 (1981) 783.
- [4] C. K. Kim *et al.*, J. Phys. F: Metal Phys. 18 (1988) L271.
- [5] T. H. Cho *et al.*, Appl. Phys. A 70 (2000) 595.
- [6] S. K. Kwon and B. I. Min, Phys. Rev. Lett. 84 (2000) 3970.
- [7] J. -S. Kang *et al.*, Phys. Rev. B 66 (2002) 075108.

FIGURES

FIG. 1. (a) Total DOS of La_3S_4 in the paramagnetic ground state. (b) La $5d$ (t_{2g} for dotted line) and (c) S $3p$ PLDOSs.

FIG. 2. (a) Spin polarized total DOS of Ce_3S_4 in the ferromagnetic ground state. (b)-(d) Ce $4f$, Ce $5d$, and S $3p$ PLDOSs are compared to the experimental Ce $4f$, the $h\nu = 26$ eV, and $h\nu = 18$ eV PSWs (dotted lines). The majority and minority spin DOSs are summed for comparison.

