Magnetically induced signatures in a thin Im superconductor

Lars Egil Helseth

Max Planck Institute of Colloids and Interfaces, D-14424 Potsdam, Germany

Abstract

We study the interaction between a one dimensional magnetic nanostructure and a thin lm superconductor. It is shown that di erent magnetic distributions produce characteristic magnetic eld signatures. Moreover, the magnetic structure can induce a weak link in the superconducting lm, or be positioned directly above a prede ned nonsuperconducting weak link. We estimate the magnetic ux associated with such a structure, and discuss a general expression for the energy calculated within the London model.

W eak links in superconductors have generated a lot of interest over the past decades, both in the study of conventional and high T_c superconductors. M ore recently, research has also been focused towards junctions in thin Im s, due to their potential in future technology (see e.g. Ref. [1] and references therein). For such junctions it has been found that the eld is a superposition of elds from Pearl vortices along the junction with a certain line density [1]. An interesting special case is the generation of weak links with spatially localized magnetic elds. Creation of a weak link in a bulk (or thick lm) superconductor using a magnetic domain wall was rst proposed by Sonin [2]. In that paper expressions for the m agnetice elds where found, and it was argued that dom ain walls can induce m ovable weak links. In the current paper we try to extend the idea of Ref. [2] to thin Im superconductors, and estimate the magnetic eld and ux distribution associated with an one dimensional magnetic nanostructure. The weak link could be a dom ain wall, generated and controlled by a stress pattern or external eld, or it could be a stationary prefabricated nanom agnetic stripe. A particular advantage of using m agnetic dom ain walls as weak links is that they can be m oved at high speeds, and m ay therefore have potential applications in future uxtronics devices. On the other hand, in a prefabricated magnetic stripe (e.g. perm alloy) the polarity of the magnetic vector could easily be switched by an external ed[3]. This could also be of interest for creation and annihilation of vortices. Since the vortex pinning energy offen can be regarded as proportional to the thickness of the superconductor, it is reasonable to assume that pinning by nonmagnetic sources are negligible in a thin lm. Therefore, it should in principle be possible to produce Im systems in which the magnetic texture determ ines the junction properties.

Consider a thin superconducting Im located at z = 0 with thickness much smaller than the penetration depth of the superconductor. The surface is covered by a one dimensional magnetic structure centered at x = 0, with thickness much smaller than that of the superconducting Im. It is assumed that them agnetic structure is su ciently long that end e ects are not a problem, and that it consists of surface charges separated from the superconductor by a very thin (negligible) oxide layer to avoid the exchange of electrons or spin (see e.g. Ref. [4]). We will here analyze the case where the magnetization is perpendicular to the plane of the superconductor. In order to gain some insight into the behavior of the weak link, let us rst compare the magnetic elds from the two following models for the magnetization

2

distribution:

$$M^{G} = M_{0} \exp(x^{2}) (z) e_{z};$$
 (1)

and

$$M^{S} = \begin{cases} 8 \\ < M_{0} (z) e_{z} \text{ if } W \times W \\ \vdots & 0 & \text{ if } y \text{ j } W \end{cases};$$

where M $_{z0}$ and are constants. Here we assume that = 2W 2 .

U sing the m ethod R ef. [5, 6], we nd that the gaussian m agnetization distribution results in the following eld components (per unit length):

$$H_{z}^{G}(\mathbf{x};\mathbf{z}) = \frac{\mathbf{p}^{e^{M_{0}}}}{\mathbf{p}^{2}} \int_{0}^{Z_{1}} k_{x}^{2} \frac{\exp(k_{x}^{2}=4)\cos(k_{x}\mathbf{x})}{1+2e^{k_{x}}} \exp(k_{x}\mathbf{j}\mathbf{z}) dk_{x}; \qquad (2)$$

$$H_{x}^{G}(\mathbf{x};\mathbf{z}) = \frac{e^{M_{0}}}{P_{x}} \int_{0}^{Z_{1}} k_{x}^{2} \frac{\exp(k_{x}^{2}=4) \sin(k_{x}\mathbf{x})}{1+2e^{k_{x}}} \exp(k_{x}\mathbf{j}\mathbf{z}) dk_{x} : \qquad (3)$$

On the other hand, the step m agnetization distribution gives

$$H_{z}^{S}(\mathbf{x};z) = \frac{2 e^{M_{0}}}{1 + 2 e^{k_{x}}} \exp(k_{x}j_{z})dk_{x}; \qquad (4)$$

$$H_{x}^{S}(x;z) = \frac{2 e^{M_{0}}}{1} k_{x} \frac{\sin(k_{x}W)\sin(k_{x}x)}{1+2 e^{k_{x}}} \exp((k_{x}jz))dk_{x} :$$
(5)

Figure 1 shows H $_z^S$ when $z = _e=200$ (solid line) and z = 0 (dash-dotted line). Note that when z = 0 the magnetic eld oscillates due to the steep magnetization gradient. This could therefore be interpreted as G ibbs oscillations, well known in Fourier analysis. At a certain height above the surface these oscillations are smoothed out due to the exponential decay factor. Figure 2 shows H $_z^G$ (solid line) and H $_x^G$ (dash-dotted line) when $W = _e=40$ and z = 0. Note that the peak of the z component is located at the origin. This is in contrast to Fig. 1, where the maximum eld is located near the edges. Moreover, the two negative peaks of the eld are much less pronounced for a gaussian distribution.

It is clear that if the magnetic eld exceed the critical eld of the superconductor, then a weak link is generated at which vortices may exists [2]. The current across the link is, in absence of any external currents, given by

$$J_x^s = dJ_c sin_2 + 2 - ;$$
 (6)

where $= 2_{1} + 2_{0}$ is the phase di erence across the junction, the magnetic ux through the junction and $_{0}$ the ux quantum. The magnetic ux for a gaussian magnetization distribution is estimated to be

$$\int_{y_{1}}^{Z} \sum_{y_{2}} Z_{W} + \int_{z} dy dz = \frac{0}{p} \frac{y_{e} M_{0}}{2} \int_{0}^{Z_{1}} k_{x} \frac{\exp(k_{x}^{2}=4)\sin(k_{x}W)}{1+2ek_{x}} dk_{x};$$
(7)

where $y = y_2$ y_1 is the length of the weak link. It is seen that the ux, and therefore also the phase, is dependent on the magnetization, the wall width and the penetration depth.

Let us now consider a norm al weak link (i.e. not m agnetic), in which the phase can be found by using the approach of Ref. [1]. If we position a very thin m agnetic structure (as discussed above) directly over the prede ned weak link, a ux will ow through this junction. Here we may set $_{\rm e}$! 1, since the junction is entirely nonsuperconducting, and this results in

$$\frac{{}_{0}}{2^{p}} \frac{yM_{0}}{2^{n}} \int_{0}^{Z_{1}} \exp(k_{x}^{2} = 4) \sin(k_{x}W) dk_{x} = C_{0}M_{0} y; \qquad (8)$$

where C is an unimportant constant (C = [exp(2)] $P_{2}^{p} = P_{2}^{p} = P_{$

$$E = \int_{V}^{Z} \left(\frac{1}{2} _{0}H^{2} + \frac{1}{2} _{0}^{2}J_{s}^{2} _{0}M H\right) dV :$$
(9)

Here $_0$ is the perm eability, and the current due to supercurrents and m agnetization gradients can be written as

$$J = J_s + J_m = J_s + r \qquad (10)$$

Note that the integration over the energy density is taken over the whole space, although the current can only ow in the volume of the thin lm superconductor. I.e., we do not adopt the usual approach of dividing the space into superconducting and nonsuperconducting regions. Thus, we believe that the approach shown below can be applied to a more general class of systems, as long as there is no exchange of electrons and spin between the magnetic and superconducting structures. In order to obtain a more useful expression for the energy, we

rst transform the part associated with kinetic energy of the superconducting electrons

$$E_{\text{kinetic}} = \frac{1}{2} \int_{V}^{2} J_{s}^{2} dV = \frac{1}{2} \int_{V}^{2} J_{s} \left[r \quad (H \quad M) \right] dV :$$
(11)

Here we have used that $J_s = r$ (H M). To further transform this integral, we note that a surface integral over the kernel J_s (H M) vanishes when the surface is located far from the system. This means that we can write

$$E_{kinetic} = \frac{1}{2} \int_{V}^{Z} J_{s}^{2} dV = \frac{1}{2} \int_{V}^{Z}$$

But now it should be rem em bered that the London equation gives

r
$$J_s = \frac{1}{2}H + \frac{1}{2}V$$
; (13)

where V is the vortex source function, which represents all the vortices in the system (In the case of Pearl vortices it is simply a sum of delta functions). We obtain

$$E_{kinetic} = \frac{1}{2} \int_{V}^{2} J_{s}^{2} dV = \frac{1}{2} \int_{V}^{2} H^{2} + M + (H - M) V dV : (14)$$

In total, the energy becom es

$$E = \frac{1}{2} \int_{V}^{Z} [M + (H M) V] dV :$$
(15)

Equation 15 can be applied to system s which are sulficiently local that the surface corrections can be neglected. The usefulness of Eq. 15 relies on the fact that for a thin \ln superconductor it reduces to a two dimensional integral, since the vortex source function and the magnetization distribution both are assumed to be located at z=0. Then the Fourier analysis of R efs. [4, 5] can be applied to obtain simple integrals for the energy. In their interesting paper E rdin and cow orkers demonstrated a dimensional for calculating the energy within the London approximation [4]. The technique presented here gives an alternative and perhaps more intuitive route to evaluate the energy. It is instructive to divide the

energy terms in three di erent parts. The self-energy of the magnetic structure is

$$E_{m} = \frac{1}{2} \int_{V}^{Z} M H_{m} dV ; \qquad (16)$$

the energy associated with the vortex is

$$E_{v} = \frac{1}{2} \int_{V}^{Z} H_{v} V dV ; \qquad (17)$$

and the interaction energy

$$E_{vm} = \frac{1}{2} \int_{V}^{U} M H_{v} H_{m} V + M V] dV :$$
(18)

It is seen that the E_{vm} consists of the interaction between the magnetization and the vortex

eld, the magnetically generated eld and the vortex source function and also the interaction between the magnetization and the vortex source function. Note that the two rst contributions have opposite sign, and their sum is equal to $_{0 v}^{R}M$ $H_{v}dV$ only in the case when they are equal. A lthough this is a reasonable approximation in some particular cases, the above analysis shows that it is not correct in general[5, 7, 8]. Moreover, one should take into account the nite distribution of the vortex source function.

In conclusion, we have discussed some properties of thin Im superconductors in the close vicinity of one dimensional magnetic structures. It was found that the magnetic eld depends strongly on the magnetic distribution function, and simple estimates for the ux through a weak link were derived. Finally, we derived an expression for the energy associated with a more general class of system s.

- [L] V.G. Kogan, V.V. Dobrovitsky, Y. Mawatari, R.G. Mints and J.R. Clem, Phys. Rev. B 63, 144501 (2001).
- [2] E B.Sonin, Pisma Zh.Tekh.Fiz.14, 1640 (1988) [Sov.Tech.Phys.Lett.14, 714 (1988)].
- [3] G.Yi, P.R.Aitchison, W. D.Doyle, JN.Chapman and C.D.W. Wilkinson, J.Appl.Phys. 92, 6087 (2002).
- [4] S.Erdin, A.F.Kayali, IF.Lyuksytov, and V.L.Pokrovsky, Phys. Rev. B 65, 014414 (2002).
- [5] LE.Helseth, Phys.Rev.B 66, 104508 (2002).
- [6] On p. 1, Eq. 1 in Ref. [5] the term containing the vortex source function should be multiplied with (z), and also on p. 4 (line 7) the magnetization distribution should be multiplied with (z). These errors did not in uence the nalresult.
- [7] Even though the expression for the interaction energy is not complete, it should be pointed out that Eqs. 30, 38 and 44 in Ref. [5] m ay serve as a reasonable starting point for computing the energy when the magnetization is directed perpendicular to the lm plane.
- [8] In Figs. 2 and 4 in Ref. [5] an attractive force is de ned to be pointing towards the magnetic bubble. Thus, an attractive force for negative is de ned to be positive and points to the right, whereas an repulsive force points to the left. In the case of > 0, an attractive force is negative and points to the left, whereas an repulsive force points to the right. In sum, the force is allways attractive or repulsive, depending on the polarities of the magnetic bubble as well as the vortex. A lthough this sign convention is not mathematically pleasing (because negative is allowed), it is nonetheless allowed physically as long as one clearly points out the de nition. Unfortunately, this was not done in Ref. [5]. The author thanks F M. Peeters for a discussion on this matter.

7




FIG.1: The z component of the magnetic eld generated by a step-like magnetization distribution when z = 0 (dash-dotted line) and $z = _e=200$ (solid line). Here W = =40, and the curves have been normalized with respect to the maximum peak of the dash-dotted line.




FIG. 2: The x (dash-dotted line) and z (solid line) component of the magnetic eld generated by a gaussian magnetization distribution. Here z=0, W = =40 and = 2W². The curves are normalized with respect to the maximum peak of the z component.