

The exchange coupling and spin waves in metallic magnets: removal of the long-wave approximation

V P Antropov

Ames Lab, Ames, IA, 50011

Abstract

A well-known connection between the magnetic susceptibility and the effective exchange parameter is analyzed. It is shown that all current computational schemes use a long-wave approximation which is suitable only for localized moments systems. A corresponding spin stiffness parameter is derived in real and reciprocal space. General 'inverse susceptibility' approach is combined with a multiple scattering theory and applied for the studies of elementary metals Fe, Ni and Gd. It is shown that the proposed approach significantly improves the description of the exchange coupling between nearest atoms, the spin wave spectrum at large wave vectors for the itinerant degrees of freedom in metallic magnets. A consistent usage of this method leads to the proper description of magnetic short-range order effects.

PACS numbers: 71.28.+d, 71.25.Pi, 75.30.Mb

The exchange coupling is one of the most important fundamental interactions in magnets. Knowledge of the parameters of this interaction facilitates the description of numerous properties of magnets and provides a critical test of the applicability of different models. In addition, the current applied research in the area of magnetorecording, spintronics and magnetotransport phenomena requires the knowledge of the effective exchange coupling between atoms or layers[1]. Therefore reliable calculations of the parameters of this coupling are especially important both from fundamental and applied points of view. Many computational expressions for magnets with different magnetic orderings were proposed [2, 3, 4, 5, 6, 7, 8]. However, most of them were derived only for localized spin systems at equilibrium. In this treatment the atomic magnetization is directly proportional to the effective 'exchange' field (localized approach). In real non-equilibrium state these directions are always different due to coexistence of localized and itinerant degrees of freedom. Any model assumption about this non-locality restricts certain degrees of freedom and affects the spin-spin correlation function and hence the dynamic and thermal properties. For instance, the local approach implemented in Ref.[4] directly leads to the concept of a strong short range magnetic order which by no means is a universal behavior of magnets. It is desirable that both short-range (large q) and long-range (small q) fluctuations be present in the general theory in a consistent fashion at any finite temperatures, whereas the perturbation theory [4, 5, 6, 7, 8] is used only at small temperatures (spin wave (SW) stiffness calculations). In addition, for weak magnets or magnets with some weakly magnetized regions the non-spherical parts of the effective magnetic field must be included.

In this paper starting from the general principles I provide a critical analysis of the approximations used in the theory of exchange coupling, and discuss an opportunity to calculate the parameters of such coupling rigorously without specific assumptions about the range of magnetic order or any approximations about the form of magnetization density.

In a nonuniformly magnetized medium, the total energy depends on the relative orientation of vectors $\mathbf{m}(\mathbf{r})$ at different points. The stability of the magnetic state with respect to the variation of magnetization density is determined by the tensor of the second derivatives

$$J(\mathbf{r}; \mathbf{r}^0) = \frac{\partial^2 E}{\partial \mathbf{m}(\mathbf{r}) \partial \mathbf{m}(\mathbf{r}^0)} \Big|_{\mathbf{h} = \mathbf{m}_0} \quad (1)$$

where $\mathbf{r} = x; y; z$ and \mathbf{m}_0 is the magnetization of any stationary state. In general, unlike the parameters of Heisenberg model, the parameters $J(\mathbf{r}; \mathbf{r}^0)$ depend on the magnetic configuration and are not necessarily related to the total energy differences between different magnetic phases. The quantity J is a model quantity and the definition (1) is not unique.

To calculate $J(\mathbf{r}; \mathbf{r}^0)$ one has to know the variation over the spin density. The real physical perturbation which can induce such a variation is the external magnetic field. Thus, we have to employ the ideas of linear response and calculate the dynamic magnetic susceptibility (DMS) [9]. In this case the variation of magnetization is written as

$$\mathbf{m} = b \mathbf{B}_{\text{ext}}; \quad (2)$$

where b is the (non-local) DMS which can be presented as

$$b = \frac{\mathbf{m}}{B_{\text{ext}}} = b \frac{\partial^2 E}{\partial \mathbf{m}(\mathbf{r}) \partial \mathbf{m}(\mathbf{r}^0)} b = b \mathcal{J}(\mathbf{r}; \mathbf{r}^0) b; \quad (3)$$

Therefore $\mathcal{J} = b^{-1}$: This definition of the effective exchange is nothing but the well-known connection between the inverse static susceptibility and the parameter χ_2 in the Landau theory of phase transitions (T.Moriya also uses the inverse susceptibility in the Heisenberg model; see Ref.[2]). The goal of this paper is to consider the relationship between this definition and those currently used in magnetism research. Also the corresponding modification of the adiabatic SW spectra will be analyzed.

Let us generalize this concept and introduce the frequency dependent exchange coupling $\mathcal{J}(\mathbf{r}; \mathbf{r}^0; !)$ as

$$\int d\mathbf{r}^0 \mathcal{J}(\mathbf{r}; \mathbf{r}^0; !) b(\mathbf{r}^0; \mathbf{r}^0; !) = (\mathbf{r} - \mathbf{r}^0); \quad (4)$$

The parameter $\mathcal{J}(\mathbf{r}; \mathbf{r}^0; !)$ (below we will omit matrix notations where it is not important) is the full exchange containing all enhancement effects. Some approximate expressions for $J(\mathbf{q}; !)$ in a long wave approximation have been obtained in Ref.[8]. Unfortunately, the exact calculation of DMS in the case of interacting particles is not possible at the moment and any practical evaluations of $J(\mathbf{r}; \mathbf{r}^0; !)$ require certain simplifying assumptions.

Using linear response for interacting electrons for the inverse DM S one can decompose the total exchange as follows:

$$J(\mathbf{r}; \mathbf{r}^0; !) = J^0(\mathbf{r}; \mathbf{r}^0; !) - I_{xc}(\mathbf{r}; \mathbf{r}^0; !) \quad (5)$$

Here $J^0(\mathbf{r}; \mathbf{r}^0; !)$ is the 'bare' exchange coupling (obtained, for instance, from the Kohn-Sham wave functions) whereas $I_{xc}(\mathbf{r}; \mathbf{r}^0; !)$ is the exchange and correlation tensor that connects B_{xc} to the induced magnetization $B_{xc}(\mathbf{r}; !) = \int d\mathbf{r}^0 I_{xc}(\mathbf{r}; \mathbf{r}^0; !) m(\mathbf{r}^0; !)$:

Eq.5 represents a very convenient way to add enhancement effects to the exchange coupling parameter. In the absence of an explicit form for I_{xc} from many-body theory, Eq.5 must be considered as a formal definition of the frequency dependent Stoner parameter $I_{xc}(\mathbf{r}; \mathbf{r}^0; !)$: It becomes practical only when the translational invariance of a perfect crystal $J(\mathbf{r}; \mathbf{r}^0; !) = J(\mathbf{r} - \mathbf{r}^0; !)$ and the condition $I_{xc}(\mathbf{r}; \mathbf{r}^0; !) = I_{xc}(\mathbf{r} - \mathbf{r}^0; 0) = I$ are assumed. Then the condition of the SW existence is written as

$$J^0(\mathbf{q}; !) = I_{xc} : \quad (6)$$

One has to emphasize that Eq.(5) is suitable for full-potential band structure treatment and requires a complete basis set for its computation for the real materials. Also, below we will consider only the ferromagnetic case and will limit our consideration to analyzing the effects related to $+$ component. For arbitrary magnetic ordering, the matrix $b(\mathbf{r}; \mathbf{r}^0; !)$ is a 4x4 matrix and its $+$ component can not be easily separated from zz and charge components[9].

To illustrate how the parameter J enters the spin dynamics (SD) equation of motion (EOM), let us consider the adiabatic limit of Eq.5. In this case a following density functional torque equation is valid

$$\frac{dm(\mathbf{r}; t)}{dt} = m(\mathbf{r}; t) \times B(\mathbf{r}) \quad (7)$$

where B the total field acting on the electronic spin at point \mathbf{r} and γ is gyromagnetic ratio. Not all components of m are independent in Eq.7 because of the relation $m \cdot dm/dt = 0$:

For the adiabatic SD Eq.(7) can be solved for several simplest magnetic orderings by linearizing this EOM analogously to the rigid spin approximation (RSA) case[10]. For instance, for ferromagnet (FM) we obtain

$$b_q = m_q^{-1} K_q - 0^{-1} : \quad (8)$$

where q is the Fourier transform of the 'bare' static susceptibility ($\mathbf{r} - \mathbf{r}^0; ! = 0$) in the case of a periodic system. K_q is a 'kinetic gradient' matrix which takes into account the difference in spatial gradients of wave functions for the different spin direction[11]. This result for the adiabatic SW spectra is obtained here in the non-local case without using RSA for the shape of magnetic perturbation. For more complicated magnetic structures (spirals, and etc) the corresponding dispersion law may be obtained using a rotating coordinate system. The above results were obtained assuming that the decay of SW is absent (adiabatic SD); otherwise these equations are exact (in linear regime) and treat both short and long wavelength scales on an equal footing. If a magnetic field of relativistic origin is included, then in Eq.(8) one can add the energy of the free precession (rotation of the magnetization of the whole crystal).

To analyze the relationship between the dispersion law (8) and that[4] commonly used in the DFT, $!_q^{-1} = m I - 0 - q I$, we assume that the ratio

$$= \text{Tr} b = \text{Tr} - q - 0 - 0^{-1} !_q^{-1} = m I \quad (9)$$

is small (long-wave approximation) and $K_q = 1$ (effective bandwidths for the different spin directions are equal). Then, by expanding Eq.8 over the parameter $;$ we obtain the desired result:

$$\begin{aligned} b_q &= m_q^{-1} - 0^{-1} = m_0^{-1} b_{-1} - b^{-1} \\ &= b_q^{-1} - 1 - b_q^{-1} b_m^{-1} - 1^{-1}, m_0^{-1} - 0 - q - 0^{-1} \\ &= m J_0^{-1} - J_q^{-1} \end{aligned} \quad (10)$$

or

$$J_q = J_0^{-1} + b_{-1} - b^{-1} = J_0^{-1} + b + b^2 + \dots; \quad (11)$$

where the susceptibility has a matrix structure and

$$J_q^{-1} = J_0^{-1} + b = \chi_0^{-1} - q \chi_0^{-1} = I - q I = I \frac{\partial^2 E}{\partial B_{\text{tot}} \partial B_{\text{tot}}} I \quad (12)$$

is the matrix of the exchange parameter in the local (long-wave) approximation. Eq.(12) is the widely accepted definition of the exchange coupling parameter which was introduced in Ref.[2, 3, 4] and used in different modifications in Ref.[5, 6, 7, 8]. Eq.8 and the relations (10,11) are the main results of this paper. Below we will apply this result to the calculations of the exchange parameters and adiabatic SW spectra in Fe, Ni, and Gd using the multiple scattering technique.

From the computational point of view two alternatives can be used. First one is a calculation of the total energy of the system with an external field included and the second one is to use of so-called 'local force' theorem which does not require self-consistency and the total energy calculations.

In Ref.[6] a general 'local force' theorem was formulated for magnetic perturbations and a convenient multiple scattering technique was suggested for calculations of $\chi_{xc} = \partial^2 E / \partial B_{xc} \partial B_{xc}$; where a role of B_{xc} belongs to one-site scattering matrix t^{-1} . We stress that this theorem can be used for the calculations of both the magnetic susceptibility χ and the effective exchange $J = \partial^2 E / \partial m \partial m$ without any modifications of the original theorem. This statement can be also seen as a trivial result of the well known linear response theory.

The usual assumption of weak enhancement (see Eq.5) has always been used previously. This is a reasonable approximation for the SW spectrum, because if we assume usual $I_{xc}(q) = I$; then the important equality $J(q) - J(0) = J^0(q) - J^0(0)$ is valid. As a consequence, the spectrum of elementary excitations is not affected by exchange-correlation enhancement effects. So, the definition (12) is directly related to several very strong approximations: RSA, smallness of SW dispersion compared to the effective exchange splitting (atomic limit), and small dispersion of $I_{xc}(q)$.

From the formal point of view, the RSA was directly contained in the way that the local force theorem was previously used. While the exact formulation of this theorem contains the first functional variation of the total energy, in RSA one has to use the corresponding first derivative

$$\frac{\partial E}{\partial m(R_i + r)} = \frac{\partial E}{\partial m_i} \quad (13)$$

with all gradient terms (large q vectors) omitted. Here i is index of the atomic site.

The second approximation $\chi_{q00}^{-1} \ll 1$ also removes certain degrees of freedom with large q which are present in the Brillouin zone. Analogous one site approximations have been employed in modern dynamic mean field techniques[12], self-consistent GW scheme[13] and the coherent potential approximation[5]. Such a restriction affects the spin-spin correlation function and in turn the dynamic and thermal properties of magnets. It is true that (as one can easily obtain from Eq.11), such a long wave approximation can safely be used for SW stiffness calculations.

The term $I_{xc}(q)$ is usually short-ranged, which coincides with the corresponding smallness criteria in real space $i_j = i_i \ll 1$ (where i_j is a Fourier transform of q and i_i is the on-site susceptibility), hence the local approximation $I_{xc}(q) = I$ may affect the exchange between the nearest atoms only.

Let us quantitatively discuss the range of applicability of the above formalism for real magnetic systems. To perform realistic calculations we use multiple scattering theory (see, for instance[8] and references therein) to obtain 'bare' J_q : In this theory a key equation is

$$(\mu) = [P(\mu) - S]^{-1} \quad (14)$$

where (μ) is scattering path operator, $P(\mu)$ is the inverse of the one-site scattering matrix and S is the matrix of structure constants. It is convenient to separate spin structure explicitly:

$$(\mu) = T_0(\mu) + T(\mu); \quad P(\mu) = p(\mu) + p(\mu); \quad (15)$$

Then the total energy variation with respect to the deviation of magnetic field at the site i can be presented in the static linear response scheme as[8]

$$E = - \frac{2}{\pi} \sum_{\mathbf{q}} \text{Im} \text{Tr} \int_0^{\beta} d\tau \mu_i T_{iL}(\tau) p_0 T_{00}(\tau); \quad (16)$$

lengths correctly, is vitally important for the reliable description of the itinerant magnetism at finite temperatures in 3d metals.

In summary, we presented a technique for the calculation of the effective exchange parameters without any assumptions about the form of magnetization density and the degree of magnetic order. Our results for elementary magnets (Fe, Ni and Gd) indicated that the most significant improvement is obtained for exchange coupling between nearest magnetic atoms and for SW spectrum at finite wave vectors. The large error of previous long-wave approximation is determined for fcc Ni. This result indicates also that some important effects (which are essential for the correct description of T_c in itinerant magnets) are still missing from the current magnetism theories when the nearest neighbors J_{ij} parameters determined at $T = 0$ K are being used at the finite temperatures. In Fe and especially in Gd the proposed technique gives the result similar to localized model result, as expected.

Overall, we expect that the emphasized above approach for the exchange coupling and SW spectra Eq.(8,11,17) will significantly improve the description of the nearest neighbors interaction or large q part of SW spectra in any magnet with not fully localized magnetism ($m < 2 \mu_B$ and metallic r_s). We expect an increasing importance of this formalism at the finite temperatures and in systems with strong magnetic short range order.

The author thank N. E. Zein and K. D. Belashchenko for many stimulating discussions and P. Bruno for the opportunity to present the results of this paper at the seminar in his group in Halle, in May 2002. This manuscript has been authored by Iowa State University of Science and Technology under Contract No. W-7405-ENG-82 with the U.S. Department of Energy.

-
- [1] Magnetism Beyond 2000. J. Magn. Magn. Mater. 200 (1999).
 - [2] T. Moriya. Spin Fluctuations in Itinerant Electron Magnetism, (Berlin, Heidelberg, Springer-Verlag, 1985).
 - [3] S. H. Liu, Phys. Rev. B 15, 4281 (1977).
 - [4] V. Korenman, J. L. Murray, and R. E. Prange, Phys. Rev. B 16, 4032 (1977); C. S. Wang, R. E. Prange, V. Korenman. Phys. Rev. B 25, 5766 (1982).
 - [5] T. Oguchi, K. Terakura and N. Hamada. J. Phys. F 13, 145 (1983); B. L. Gyorffy, A. J. Pindor and J. Staunton. J. Phys. F 15, 1337 (1985).
 - [6] A. I. Liechtenstein, M. I. Katsnelson and V. A. Gubanov. J. Phys. F 14, L125, (1984); E. Bruno, B. L. Gyorffy, J. B. Staunton. NATO ASI Series, Series E: Applied Sciences, 256, 321 (1994).
 - [7] A. I. Liechtenstein, M. I. Katsnelson, V. P. Antropov and V. A. Gubanov. J. Magn. Magn. Mater. 67, 65 (1987).
 - [8] V. P. Antropov, M. I. Katsnelson and A. I. Liechtenstein. Physica B. 237-238, 336 (1997); V. P. Antropov, B. N. Harmon and A. V. Smimov. J. Magn. Magn. Mater. 200, 148 (1999); V. P. Antropov. in Computer Simulation Studies in Condensed-Matter Physics X III. ed. by D. P. Landau. v.86. (Berlin, Heidelberg, Springer-Verlag, 2001) p.7.
 - [9] Magnetism of metals and alloys. Ed. by M. Cyrot. (Amsterdam, North Holland Publishing Company, 1982).
 - [10] V. P. Antropov, M. I. Katsnelson, M. van Schilfgaarde, B. N. Harmon and N. Kusnezov. Phys. Rev. B 54, 1019 (1996).
 - [11] V. P. Antropov. V. P. Antropov. in Computer Simulation Studies in Condensed-Matter Physics XV. ed. by D. P. Landau. v.88. (Berlin, Heidelberg, Springer-Verlag, 2003) (in press).
 - [12] A. Georges, G. Kotliar, W. Krauth and M. Rosenberg. Rev. Mod. Phys. 68, 13 (1996).
 - [13] N. E. Zein and V. P. Antropov. Phys. Rev. Lett. 89, 126402 (2002); N. E. Zein and V. P. Antropov. J. Appl. Phys. 89, 7314 (2001).
 - [14] M. van Schilfgaarde and V. P. Antropov. J. Appl. Phys. 85, 4827 (1999).