arXiv:cond-mat/0211320v1 [cond-mat.supr-con] 15 Nov 2002

Observation of Superconductivity in Heavy-Fermion Compounds of Ce_2CoIn_8

Genfu CHEN*, Shigeo OHARA, Masato HEDO[1], Yoshiya UWATOKO[1], Kazuya SAITO[2], Michio SORAI[2] and Isao SAKAMOTO

Department of Electrical and Computer Engineering, Nagoya Institute of Technology, Nagoya 466-8555
[1]*The Institute for Solid State Physics, The University of Tokyo, Kashiwa 277-8581*
[2]*Research Center for Molecular Thermodynamics, Graduate School of Science, Osaka University, Toyonaka, Osaka 560-0043*

(Received July 25, 2002; to be published December 2002)

We succeeded in growing a single crystal of Ce_2CoIn_8 by the flux method. The results of specific heat and electrical resistivity measurements indicate that Ce_2CoIn_8 is a heavy-fermion superconductor below 0.4 K with an electronic specific heat coefficient γ as large as 500 mJ/K^{2}mol-Ce.

KEYWORDS: superconductivity, heavy fermion, crystal growth, specific heat, electrical resistivity, Ce_2CoIn_8

Considerable research has recently been focused on a new family of Ce-based heavy-fermion compounds with the general formula Ce_nMIn_{3n+2} (M=Co, Rh, Ir; n=1, 2), which crystallize in tetragonal Ho_nCoGa_{3n+2}-type structures.[1–3] The crystal structure of Ce_nMIn_{3n+2} can be seen as the n layers of $CeIn_3$ stacked sequentially along the c-axis with intervening one layer of MIn_2. These compounds exhibit a variety of interesting phenomena, such as heavy-fermion superconductivity, antiferromagnetism and pressure-induced superconductivity.

For transition metals M=Rh and Ir, a series of compounds n=1 and 2 has been synthesized in single crystal form. For M=Rh, both n=1 and 2 compounds are antiferromagnets with Néel temperatures of T_N=3.8 and 2.8 K for $CeRhIn_5$ and Ce_2RhIn_8, respectively.[4,5] The electronic specific heat coefficient γ is estimated to be about 50 mJ/K^{2}mol-Ce for $CeRhIn_5$ and 370 mJ/K^{2}mol-Ce for Ce_2RhIn_8.[6,7] In both compounds, superconductivity was observed under high pressures. $CeRhIn_5$ transforms from antiferromagnetic state to superconducting state at 2 K under the pressure of 1.6 GPa.[4] For Ce_2RhIn_8, very recently, pressure-induced superconductivity was reported.[8]

For M=Ir, the n=1 member $CeIrIn_5$ is a heavy-fermion superconductor with a transition temperature of T_c=0.4 K at ambient pressure, while the n=2 member Ce_2IrIn_8 is a paramagnet down to 50 mK with no evidence of a phase transition.[5,9] The γ values are about 700 mJ/K^{2}mol-Ce for both compounds.[5,10]

For M=Co, the n=1 member $CeCoIn_5$ is a heavy-fermion superconductor with a transition temperature of T_c=2.3 K.[11] The γ value of $CeCoIn_5$ is about 300 mJ/K^{2}mol-Ce at T_c. When the superconductivity is suppressed by a magnetic field of 50 kOe, the γ value increases with decreasing temperature and reaches a very large value of about 1 J/K^{2}mol-Ce.[11,12] To our knowledge, however, there is no report on the n=2 member Ce_2CoIn_8, except for the structural study.[1,2]

The purpose of this paper is to clarify the thermal and electronic properties of Ce_2CoIn_8. We attempted to synthesize Ce_2CoIn_8 by the flux method and found the conditions for single crystal growth. Measurements of specific heat and electrical resistivity were carried out on single crystals of Ce_2CoIn_8. In this paper, we report the observed superconductivity at $T_c\sim$0.4 K for Ce_2CoIn_8 at ambient pressure.

Single crystals of Ce_2CoIn_8 were grown from an In flux. An arc-melted Ce_2Co button and excess In were sealed in a quartz ampoule under high vacuum. The ampoule was heated up to 750°C over 7 h and then raised quickly to 1000°C and held for 5 minutes, followed by rapid cooling to 750°C. The single crystals grew in the temperature region of 750-300°C. After spinning off the remaining In, many mm-sized, cube(or tetragon)-with-octahedron-like single crystals were obtained. The residual In on grown crystal surfaces was further removed by acid etching. The crystals were characterized by a powder X-ray diffraction method using Cu$K\alpha$ radiation at room temperature. The specific heat was measured by the relaxation method in the temperature range of 2-20 K. The resistivity measurement was performed by a standard four-probe ac bridge method down to 0.1 K.

Figure 1 shows the X-ray diffraction pattern obtained for crushed crystals. The X-ray pattern is well indexed on the base of the tetragonal Ho_2CoGa_8-type structure (the space group P4/mmm), as indicated by the indices in Fig. 1. There is no trace of $CeCoIn_5$. A weak peak, marked by an arrow, is the (011) reflection of the residual In-flux. The lattice parameters are determined as a = 4.643 Å and c = 12.25 Å, which agree with the reported values.[1]

Specific heat divided by temperature C_p/T *vs* T^2 for Ce_2CoIn_8 is illustrated in Fig. 2. With decreasing temperature, C_p/T decreases linearly for T^2 and shows a minimum around 7 K. At lower temperatures, C_p/T increases with decreasing temperature. At 2 K, C_p/T reaches 500 mJ/K^{2}mol-Ce. This indicates that the γ value of Ce_2CoIn_8 is more than 500 mJ/K^{2}mol-Ce, showing a heavy-fermion characteristic.

Figure 3 shows the temperature dependence of the

* Present address: Department of Electrical and Computer Engineering, Nagoya Institute of Technology, Nagoya 466-8555




Fig. 1. X-ray diffraction pattern of Ce_2CoIn_8 with Miller indices. The arrow denotes the (011) reflection of the residual In-flux.




Fig. 2. Specific heat divided by temperature C_p/T versus T^2 for Ce_2CoIn_8.




Fig. 3. Electrical resistivity plotted with $\log T$ in the temperature range from 0.1 to 300 K for Ce_2CoIn_8. The inset shows the resistivity in the lowest temperature region on a linear scale.

electrical resistivity ρ as a function of log T with the current along the a-axis. The inset shows the resistivity below 0.8 K on a linear scale. With decreasing temperature, the resistivity shows a -log T dependence below 80 K down to 30 K, reaches a maximum, and decreases at lower temperatures. A kink at 3.4 K is attributed to the superconducting transition of free In that might be included in the crystal. As the temperature decreases further, the ρ-T curve shows a few abrupt drops near 1.4 K, 1.0 K and 0.4 K, as shown in Fig. 3. Below 0.4 K, the resistivity becomes zero, as shown in the inset in Fig. 3. This suggests that Ce_2CoIn_8 is a heavy-fermion superconductor with a transition temperature of T_c∼0.4 K.

To determine the upper critical field H_{c2} for Ce_2CoIn_8, we measured the resistivity on a single crystal Ce_2CoIn_8 with a magnetic field applied along the a-axis. The zero resistivity state is broken with the field H=1 T at 0.1 K, which indicates that H_{c2}∼1 T for Ce_2CoIn_8. The values of T_c∼0.4 K and H_{c2}∼1 T for Ce_2CoIn_8 are much lower than those for $CeCoIn_5$, but are very similar to those for $CeIrIn_5$.[7,13,14] The complete H-T phase diagram will be reported in the near future.

The causes of the resistivity drops near T=1.4 and 1.0 K for Ce_2CoIn_8 are yet to be clarified. However, a similar resistivity anomaly is also observed in $CeIrIn_5$, where the anomaly is viewed as an appearance of superconductivity but is distinguished from bulk superconductivity.[7,9,15] To clarify the origin of these resistivity drops and the bulk properties of the superconducting state for Ce_2CoIn_8, more detailed studies of specific heat and magnetic susceptibility at lower temperatures are being carried out.

Here, we have presented the specific heat and the resistivity measurements performed on the single crystals of Ce_2CoIn_8. It is found that Ce_2CoIn_8 is a heavy-fermion superconductor with T_c∼0.4 K.

We thank S. Okada, Y. Shomi and Y. X. Jin for their experimental assistance. One of the authors (S. Ohara) was financially supported by the Nitto Foundation.

1) Ya. M. Kalychak, V. I. Zaremba, V. M. Baranyak, V. A. Bruskov and P. Yu. Zavalij: Izv. Acad. Nauk SSSR Metally **1** (1989) 209.
2) Ya. M. Kalychak: J. Alloys compd. **291** (1999) 80.
3) E. G. Moshopoulou, Z. Fisk, J. L. Sarrao and J. D. Thompson: J. Solid State Chem. **158** (2001) 25.
4) H. Hegger, C. Petrovic, E. G. Moshopoulou, M. F. Hundley, J. L. Sarrao, Z. Fisk and J. D. Thompson: Phys. Rev. Lett. **84** (2000) 4986.
5) J. D. Thompson, R. Movshovich, Z. Fisk, F. Bouquet, N. J. Curro, R. A. Fisher, P. C. Hammel, H. Hegger, M. F. Hundley, M. Jaime, P. G. Pagliuso, C. Petrovic, N. E. Phillips and J. L. Sarrao: J. Magn. & Magn. Mater. **226** (2001) 5.
6) P. G. Pagliuso, M. F. Hundley and J. L. Sarrao: Phys. Rev. B **64** (2001) 144411.
7) H. Shishido, R. Settai, D. Aoki, S. Ikeda, H. Nakazawa, N. Nakamura, T. Iizuka, Y. Inada, K. Sugiyama, T. Takeuchi, K. Kindo, T. C. Kobayashi, Y. Haga, H. Harima, Y. Aoki, T. Namiki, H. Sato and Y. Onuki: J. Phys. Soc. Jpn. **71** (2002) 162.
8) M. Nicklas, V. A. Sidorov, H. A. Borges, P. G. Pagliuso, Z. Fisk, J. L. Sarrao and J. D. Thompson: cond-mat/0204064.
9) C. Petrovic, R. Movshovich, M. Jaime, P. G. Pagliuso, M. F. Hundley, J. L. Sarrao, Z. Fisk and J. D. Thompson: Europhysics Lett. **53** (2001) 354.
10) J. S. Kim, J. Alwood, G. R. Stewart, J. L. Sarrao and J. D. Thompson: Phys. Rev. B **64** (2001) 134524.
11) C. Petrovic, P. G. Pagliuso, M. F. Hundley, R. Movshovich, J. L. Sarrao, J. D. Thompson, Z. Fisk and P. Monthoux: J. Phys. Condens. Matter **13** (2001) L337.
12) S. Ikeda, H. Shishido, M. Nakashima, R. Settai, D. Aoki, Y. Haga, H. Harima, Y. Aoki, T. Namiki, H. Sato and Y. Onuki: J. Phys. Soc. Jpn. **70** (2001) 2248.
13) R. Movshovich, A. Bianchi, M. Jaime, M. F. Hundley, J. D. Thompson, N. J. Curro, P. C. Hammel, Z. Fisk, P. G. Pagliuso and J. L. Sarrao: Physica B **312-313** (2002) 7.
14) G. Sparn, R. Borth, E. Lengyel, P. G. Pagliuso, J. L. Sarrao, F. Steglich, M. Jaime and J. D. Thompson: Physica B **319** (2002) 262.
15) A. Bianchi, R. Movshovich, M. Jaime, J. D. Thompson, P. G. Pagliuso and J. L. Sarrao: Phys. Rev. B **64** (2001) 220504(R).