Organization of atom ic bond tensions in model glasses

T.Kustanovich and Y.Rabin

Departm ent of Physics, Bar Ilan University, Ram at-Gan 52900

Z. Olami

Department of Chemical Physics, The Weizmann Institute of Science, Rehovot 76100, Israel

In order to understand whether internal stresses in glasses are correlated or random ly distributed, we study the organization of atom ic bond tensions (norm al forces between pairs of atom s). Measurements of the invariants of the atom ic bond tension tensor in simulated 2D and 3D binary Lennard (Jones glasses, revealnew and unexpected correlations and provide support for A lexander's conjecture about the non-random character of internal stresses in am orphous solids.

PACS num bers: 61.43.-j61.43Fs

I. IN TRODUCTION

A lthough the existence of internal stresses in glasses is well-established [1], little is known about their statistical properties and about their role in the physics of glasses and am orphous solids. Intuitively, one expects that since local stresses and strains in a glass are a by-product of the structural disorder produced by rapid freezing of a liquid (or of incompatible local packing and space-ling requirements [2] [3]), their distribution should be random. A di erent view is advocated in ref. [4], where it is argued that the local stresses are not random , and that their organization is closely related to the low temperature vibrational spectra of glasses. Even though the question whether internal stresses in glasses are random [5] or are subject to some complex ordering is of fundam ental in portance, to the best of our know ledge this issue was not directly addressed by experim ents to date. A possible reason is that the e ects of internal stresses are discernible only on atom ic length scales, whereas on larger, but still m icroscopic length scales, they average to zero and the usual description of a glass as an isotropic solid with zero average internal stress, applies.

Unlike the stress singularities produced by lattice defects (vacancies, dislocations) in crystalline solids, internal stresses in glasses cannot be attributed to strongly strained core regions em bedded in a weakly strained bulk. As a consequence, classical elastic theory m ethods for the calculation of strains and of the resultant stresses [6], are not applicable to glassy system s. The problem has been solved for periodic solids subjected to arbitrary hom ogeneous stress, for which one can extend the continuum approach down to atom ic scales and calculate the local stress acting on a prim it ive cell[7]. Lately, it was shown that if the internal stresses in an am orphous solid vary su ciently slow ly on m icroscopic length scales, one can obtain a similar (to the crystalline case) expression for the local internal stress, with the volume of the prim it ive cell replaced by the Voronoi volum e[4]. However, recent num erical studies of atom ic stresses in two and three dimensional glassy systems at mechanical equilibrium, have dem onstrated that the atom ic environm ents

vary rapidly even between neighboring atoms at zero temperature [8, 9, 10]. The breakdown of the continuum approach implies that the macroscopic concept of stress can not be extrapolated down to atom ic scales in glassy solids.

In order to bypass these di culties, in this paper we introduce the atom ic bond tension tensor that accounts for the magnitudes and the directions of the normal forces (bond tensions in the term inology of ref. [4]) acting between pairs of atom s with radial pair interaction. Since this tensor can not be identi ed with the stress tensor, the original question about the random vs. non-random character of the internal stresses, is replaced by that concerning the organization of atom ic bond tensions in glasses.

In section II we de ne the atom ic bond tension tensor and discuss its physical meaning. In section III we describe the measurement of this parameter in simulated two and three dimensional binary Lennard-Jones Inherent States of liquids (using the term inology of ref. [11]) and of glasses in mechanical equilibrium. In section IV we show that the local organization of bond tensions belonging to an atom is not random and that the observed correlations between the eigenvalues of the proposed tensor have a physicalm eaning. In section V, directional correlations and clustering are addressed, and som e parallels with granular matter are drawn. These results, which dem onstrate that the atom ic bond tension tensor probes simulated glasses in a new way, thus extracting inform ation unavailable by the existing methods, are discussed in section VI.

II. THE ATOM IC BOND TENSION TENSOR

Consider a classical system of atom s with coordinates fR ig; interacting through the pair potential U (fR ijg), where $R_{ij} = j\vec{R}_i \quad \vec{R}_j$ is the distance between atom s i and j. The tension in the \bond" [ij] between the i th

and the j th atom is de ned as

$$J_{ij} = \frac{dU (R_{ij})}{dR_{ij}}$$
(1)

Notice that in a perfect monatom ic crystal, all bond tensions vanish in mechanical equilibrium, whereas in a multi(component crystal there are $J_{ij} \in 0$. Non-vanishing J_{ij} are indications of \mismatches" in the bonds.

W hereas the de nition of bond tensions (or, equivalently, of the norm al forces) is strictly local, their distribution, P (J_{ij}) , depends on the spatial order. P (J_{ij}) is related to the radial distribution function g(r) by $P(J_{ij})dJ_{ij} = g(r)dr$, where $P(J_{ij})dJ_{ij}$ is the probability to nd bond tension with values between Jij and $J_{ij} + dJ_{ij}$, and g(r)dr is the probability of nding a particle between r and r + dr; given a particle at the origin. Therefore, the variation in nearest neighbor separations, manifested in the width of rst peak of g(r), leads to a broad distribution of bond tensions (the distribution of the norm al forces was calculated for granular materials subjected to external forces [12], [13], and for liquid and glassy system s[14]). The above connection between the distributions P (J_{ij}) and g(r) has several in portant in plications. If the separations R_{ij} between an atom and its neighbors are random ly chosen from the distribution q(r), one does not expect to nd correlations between the corresponding J_{ij}. If separations between nearestneighbors are nearly equal, the corresponding bond tensions must be nearly equal as well (the atom ic environments are either isotropically stretched or isotropically com pressed).

A lthough there are numerous possible realizations of the set of interatom ic distances $fR_{ij}g$, their number is limited by several constraints. In mechanical equilibrium, the atom ic positions are constrained by the requirement that the net force on every atom in the system vanishes, i.e.,

$$f_{i} = \int_{j}^{X} J_{ij} \hat{R}_{ij} = 0; \qquad (2)$$

where \hat{R}_{ij} is a unit vector in the direction of \vec{R}_{ij} . Moreover, mechanical stability requires that every atom in the system is located at its local energy minimum. That means that not only the Einstein frequencies of every atom in the system but also all the eigenvalues of the complete dynamic matrix are positive [4]. These requirements must be satis ed by Inherent States of a liquid (in the term inology of ref. [11]) as well as by glasses at zero temperature. In the case of granular matter thermal uctuations play no role and only the requirem ent of force balance applies at rest [15], [16]. This is an in portant di erence, especially in view of a suggestion due to A lexander [4], that the structural disorder in glasses at zero tem perature should be constrained by the stability requirem ents.

If the distribution of bond tensions belonging to an atom i is not isotropic, the directions associated with the di erent bonds should be taken into consideration. This is done by introducing the tensor $T_{\rm ij}$ (with i 6 j) with components

$$T_{ij} = J_{ij} \hat{R}_{ij} \hat{R}_{ij}$$
(3)

In order to describe the bond tensions acting on an atom ic environment, the site of atom i is taken as a reference point and summation over all T_{ij} (with $j \in i$) is performed. The resulting atom ic bond tension tensor T_i is given by

$$\mathbf{I}_{i} = \mathbf{I}_{ij} \mathbf{I$$

The physical meaning of \dot{T}_i become apparent when it is decomposed to its trace

$$J_{i} = \begin{array}{c} X \\ J_{ij} \\ j \end{array}$$
(5)

and to the traceless part $\dot{L_i}$, with components

$$L_{i} = \begin{array}{c} X \\ J_{ij} \quad \hat{R}_{ij} \quad \hat{R}_{ij} \quad \frac{1}{d} \end{array}$$
(6)

where d is the spatial dimensionality of the system and

is the K ronecker delta function. If the distribution of atom ic bond tensions (ABT) is isotropic, the bond tensions acting on an atom i are com pletely described by the trace J_i that can be interpreted as the e ective pressure acting on the atom ic environm ent [17], [10]. The traceless tensor \dot{L}_i , Eq. 6, describes the e ect of an isotropy on the ABT tensor. To illustrate this point, consider a monatom ic crystal. At mechanical equilibrium with no external stresses, all bond tensions vanish. If the system is under hydrostatic com pression, the atom ic environm ents vary isotropically so that $J_i \in 0$; while all the com ponents L_i vanish. Under pure shear, J_i vanishes whereas $L_i \in 0$ and we conclude that \dot{L}_i describes the locale ect of shear. Since $\dot{L_i}$ and J_i are related to bcal shear and local pressure, respectively, for m on atom ic crystals T_i can be identi ed (upon suitable norm alization by the surface area of the unit cell) with the local stress. For structurally disordered system s, the variation in system 's volum e would lead, in general, to variations in the local $\dot{\text{L}_{\text{i}}}$. If the system is not sheared as a whole, $\dot{\text{L}_{\text{i}}}$ m easures the weighted e ect of the intrinsic anisotropy, on the distribution of ABT.

A lthough the ABT tensor, Eq. 4, was constructed with the aim to characterize the bond tensions acting on an atom ic environment, its components are not rotationtranslation invariant and, unlike bond tensions, depend on the choice of the coordinate system. In order to obtain a basis{independent (scalar) characterization of bond tensions, one can consider the invariants of the ABT tensor (e.g., in 2 dimensions, the trace and the determ inant). A drawback of such an approach is that am ong the d invariants (d is the dimensionality of space), only the trace, eq. 5, has the units of bond tension. An alternative approach utilizes the fact that the eigenvalues of the real symm etricmatrix \dot{T}_{i} are invariant under arbitrary translation and rotation and, therefore, for every atom i in the system, there is a set of d eigenvalues $ft_i g = t_i^1$; and d eigenvectors $f\hat{e}_i g = \hat{e}_i^1$; ^d; po€the ABT tensor. W e stress that although ft_ig have the sam e units as the components of the force acting on the atom, there is a profound di erence between the two; the eigenvalues of ABT tensor are uniquely de ned scalars that can be com pared for di erent atom s at di erent tim es and external conditions (tem perature, pressure). They do not vanish when the force acting on the atom vanishes, and therefore are suitable parameters to characterize atom ic environments in amorphous systems and in Inherent States of liquids.

The object of the present study is to characterize the organization of atom ic bond tensions in glassy system s. To do so using the ABT tensor, the distribution of the sets ftig should be known for every atom in the system . Such a distribution is trivial in m onatom ic crystals under hydrostatic com pression, for which all the eigenvalues of ABT tensor are degenerate. W hile in multi(component crystalline solids the eigenvalues are, in general, nondegenerate, the fact that the atom s are arranged on a periodic lattice in plies the existence of correlations between the eigenvalues. W hether the eigenvalues of the ABT tensor in structurally disordered materials are degenerate, correlated or random ly distributed, is an open question. In the following we address this question for two and three dim ensional binary Lennard { Jones glasses in mechanical equilibrium.

III. THE SIM ULATED SYSTEM S

The simplest (and perhaps the only) way to calculate atom ic bond tensions is by num erical simulations. Since the ABT tensor is a hitherto unexplored quantity, there are m any factors to be considered when choosing the param eters of the simulated system . Local properties, such as the existence of short range structural order, or global factors, such as the dimensionality of the system [18], may a ect the generality of the results. In order to suppress short-range-order e ects, we use binary mixtures of two types of atom s interacting through Lennard-Jones potentials (results for m on atom ic system s with a pair potential that leads to local icosahedral ordering were reported elsewhere[10]). Since 2D models of glasses o er som e advantages (in terms of computational load and visualization options) over the more realistic 3D systems, we consider both two and three dimensional systems with sim ilar repulsive-attractive pair potentials.

For 3D glasses we use binary 6-12 Lennard-Jones 80 : 20 m ixtures of atom s of types A and B (denoted 3D bLJ) with interaction parameters[19]: $^{MAB} = 1:0; ^{MAB} = 1:5; ^{MBB} = 0:5; ^{AA} = 1:0; ^{AB} = 0:8; ^{BB} = 0:5;$ 0:88:Particles of type A arem a prity particles (i.e., 80%). The interaction vanishes for $r>2:5^{\rm AA}$.

For 2D glasses we use binary 6-12 Lennard-Jones 50 : 50 m ixtures (denoted 2D bLJ) where [14]

^{AB} = 0.5(^A + ^B) for A; B = 1;2 with r 4.5^{AB} . ;t Allm easurements are given in reduced LJ units (for Argon these units correspond to " = $120k_B$ and = 3:4 A). The bond tensions are given in units of "^{AA} = ^{AA} for the 3D bLJ system s, and "= ¹ for the 2D bLJ system s. All atom s are assumed to have unit m ass.

Liquids and glasses were prepared using standard m olecular dynam ics simulations preform ed at a constant volum e[20]. Periodic boundary conditions were assumed. For each system type we considered two densities: 12 and = 1.4 for the 3D bLJ system s, and = 0.596and = 0:735 for the 2D bLJ system s. Such di erence in densities corresponds to 5% (10%) di erence in the average nearest neighbor separation for the 3D bLJ (2D bLJ) system. The number of atoms N for each 3D bLJ system is 16384. For 3D bLJ system with = 1:2; sam ples with 4000 atom s were also considered. C om parison between ABT tensors calculated for the small and the large system s shows that sim ilar results are obtained in both cases. For 2D bLJ systems, we used samples with N = 4096 atom s.

Since the binary Lennard (Jones system s used in this study do not tend to crystallize [19],[14], sam ples at zero tem perature can be prepared either by steepest descent quench from the liquid state (Inherent States of the liquid), or by obtaining a well(equilibrated glass at a suf-

ciently low temperature (at which all atom s are e ectively trapped in their cages), and then using steepest descent quench to yield glassy system s in m echanical equilibrium . For dense 2D bLJ system s, an additional route of preparation was used: taking sam ples of low-density 2D bLJ glasses (at zero tem perature), we decreased the length of the simulation box and rescaled all the atom ic positions by 10%. Perform ing a steepest descent quench on the rescaled samples (in order to relax the interatom ic forces) yields dense 2D bLJ system s at m echanical equilibrium . A Ithough the above preparation routes are not equivalent, we did not nd statistical di erences (through com parison of means, ranges and variances) between samples prepared by di erent methods. A lso, directional correlations related to ABT tensor are sim ilar, regardless of the preparation m ethod. D etails about the preparation and the distribution functions $P(ft_ig)$ are sum m arized elsew here [10].

IV. LOCAL ORGAN IZATION OF EIGENVALUES OF ATOM IC BOND TENSION TENSOR

Since we are not aware of theoretical models that predict correlations between bond tensions in structurally disordered systems, we rst address the question: Is the organization of the d eigenvalues of the ABT tensor of an atom random? If the atom ic environment is such that it can be reproduced by a random choice of d numbers from the complete distribution function P (ft_ig), then the directional information contained in the ABT tensor is redundant. Observation of non-random organization, on the other hand, would con rm that the bond tensions acting on an atom ic environment are correlated.

First we show that eigenvalues belonging to the same atom are not degenerate at zero temperature. This is an interesting point because the non-degeneracy of the d eigenvalues of ABT tensor in plies that the corresponding d eigenvectors form an orthogonal basis, i.e. . Since in structurally disordered sysê, ;ê = tem s the atom ic bond tensions corresponding to any two (even nearby) atom siand j, m ay be very di erent, one does not know a priori how to relate between the corresponding local coordinate systems fêigand fêig. If, how ever, the eigenvalues of ABT tensor are not degenerate for every atom in the system, then the local coordinate system fêig for each atom, can be uniquely written in terms of the external global coordinate system fX₁; $X_{d}g$ that we choose to project J_{ij} on. Calculation of the fraction f (in %) of pairs of eigenvalues with where 6 (; = 1; :::; d), yields that ţj< Ĵ, for = 0:5, f1% ; 0:2% and 2 3% for 3D bLJ with $= 1.2, 3D bLJ w \pm h = 1.4 and 2D bLJ w \pm h = 0.596;$ respectively. For 2D bLJ with = 0.735, f < 0.1%. Taking = 0:1 yields f < 0:1% for all systems except 2D bLJ w ith = 0.596 for which f 0:1 0:15% . These calculations indicate that the degeneracy increases when the density decreases. Nevertheless, the actual values of f are very small for all the system s considered, proving that the probability of degenerate pairs of eigenvalues is negligible.

Next, we compare between the distribution of the N sets ftig (for each atom i out of the N atoms in the sample) and the distribution of the N sets ftrg, r and random ly chosen where the d numbers t_r^1 ; from the measured distribution P (ftig). For each set of d numbers, we choose two numbers according to ^d);;tt_{m ax} = $m ax(t^{\perp};$ $t_{min} = min(t^{\perp};$ d);;and $(t_r)_{m in} = m in (t_r^1;$ ${}^{d}_{r}$;;t(t_r)_{m ax} = m ax(t_r¹; ^d_r);;t respectively [21]. Contour plots of the non-norm alized distributions P (ft_{m in}; t_{m ax}g) and P (f(t_r)_{m in}; (t_r)_{m ax}g)) for the system s considered (all at zero tem perature) are shown in gures 1{4. The solid lines correspond to $t_{m in} = t_{m ax}$. For the 3D bLJ glasses, each contour plot was calculated using one sample with N = 16384 for every system. Similar contour plots were obtained for other sam ples of the system (at the sam e density). In order to improve the resolution, in the case of 2D bLJ glass we considered sets with N = 16384 and combined four samples for each system (we veri ed that P (ft; t₂q) are sim ilar in these sets). Comparing the contour plots of 3D bLJ = 1:2 and = 1:4; and 2D bLJ = 0:596 and = 0.735 systems (gures 1 a, 2 a, 3 a and 4 a, respectively), with the contour plots of the corresponding random sets (gures 1 b, 2 b, 3 b, 4 b, respectively), we

nd that the distribution of eigenvalues of the ABT tensor di ers from that of the random sets. In particular, the non-degeneracy of eigenvalues ft_m in; t_m axg is very pronounced in the simulated 3D bLJ and dense 2D bLJ glasses, but not in the corresponding random sets. We conclude that the observed non-degeneracy of eigenvalues belonging to the same atom is the consequence of a physical constraint, and not just a trivial consequence of the sm all probability to random ly choose d num bers with close values.

Exam ining the simulated and random histogram s, one observes that the peak of P ($ft_{m \text{ in}}; t_{m ax}g$) is considerably higher than the peak of P ($f(t_r)_{m \text{ in}}; (t_r)_{m ax}g$). The di erences between the most probable "simulated" and "random " combinations of $ft_{m \text{ in}}; t_{m ax}g$, can be estimated by comparing the position and the height of "random " and "simulated" peaks. Those values for the systems in gures 1-4 are sum marized in the table below. The fraction f of atom s with P ($t_{m \text{ in}}; t_{m ax}$) > 2=3h_s, where h_s is the height of the simulated peak, is also presented:

	peak coordinates		pæak height		$f(P > 2=3h_s)$	
	sim u lated	random	sim ulated	random	sim ulated	random
1	(- 9,5)	(-7,4)	100	80	0.27	0.06
2	(-50, -12)	(-44,-14)	75	50	0.24	0.003!
3	(1,3)	(1,1.5)	200	190	0.36	0.19
4	(-44, -32)	(-42,-40)	100	90	0.20	0.13

C om parison between the peak coordinates indicates that the most probable ft_m in; t_m ax g are sin ilar for the sim – ulated and the corresponding random distributions. For the 2D bLJ and 3D bLJ w ith the low erdensities, the corresponding t_m in $(t_m$ ax) have small negative (positive) values, indicating that the average atom ic bond tensions are small. For the dense system s, the corresponding values of t_m in and t_m ax are both negative, relating the compression of typical atom ic environments in these system s. On the other hand, com parison of the peak heights and of the fraction of atom s in the vicinity of peaks, demonstrates that the probability for the preferred com binations of ft_m in ; t_m ax g that was measured for simulated system s, can not be reconstructed by a random choice of eigenvalues.

There are also marked di erences in the shapes of the distributions: the contours of P (ft_m in; t_m ax g) resemble a cone that expands towards smaller values of t_m in, whereas those of P (f(t_r)_m in; (t_r)_m ax g) tend to have a more circular form. To quantify the di erence between the respective histogram s, we calculated the Pearson product moment correlations

$$X_{i} = \frac{P_{i}(X_{i} - \overline{X})(X_{i} - \overline{Y}) = n}{P_{i}(X_{i} - \overline{X})^{2} = n} \frac{P_{i}(X_{i} - \overline{X})(X_{i} - \overline{Y}) = n}{P_{i}(X_{i} - \overline{X})^{2} = n}$$

between $t_{m in}$ and $t_{m ax}$ and between $(t_r)_{m in}$ and $(t_r)_{m ax}$.

system	(t _{m in} ;t _{m ax})	$(t_{m in}^{r}; t_{m ax}^{r})$	
3D bLJ (= 12)	0 : 7	0:3	
3D bLJ (= 1:4)	0 : 75	0:3	
2D bLJ (= 0.596)	0 : 75	0:5	
2D bLJ (= 0.735)	0:7	0:5	

The obtained values are (with last signi cant digit 0:05):

A lthough the shapes of the distributions (com pare gures 1a and 2a for the 3d case, and gures 3a and 4a for the 2d case) and the correlations between $t_{m \ in}$ and $t_{m \ ax}$ are quite sim ilar for the densities studied, the dispersion in the values of $t_{m \ in}$ and $t_{m \ ax}$ is much larger for the denser system s (notice the di erent scaling of the axes in the above gures).

The observed high correlations show that if t_m in has a small (negative) value then it is highly probable that t_{max} is also small. Vice versa, if t_{min} is large we expect t_{m ax} to be large too. The absence of local environm ents with t_{min} 0 and t_{max} 0 in the simulated system s, suggests that the local organization of the eigenvalues of ABT tensor is more isotropic than if they were random ly distributed. On the other hand, the previously discussed observation that the eigenvalues belonging to the same atom are always non-degenerate, im plies that this tendency towards local isotropy of atom ic bond tension is frustrated, and that the local stresses in the glass state can not be completely characterized by isotropic pressure.

V. D IRECTIONAL CORRELATIONS AND CLUSTER ING

Having shown that the eigenvalues of ABT tensor belonging to the same atom are correlated on average, we address a related question of whether atom s with sim ilar eigenvalues t_i are clustered in space. Since for most of the atom s the tensions in their bonds are quite sm all, the issue of clustering is mostly relevant for atom s with extrem e (high and low) atom ic bond tensions, i.e. for the tails of the distribution of P (t_i). U sing di erent sam ples of 2D bLJ and 3D bLJ glasses at zero temperature, we looked (for each sam ple) for clusters of atom s with $t_{m \ in}$ ($t_{m \ ax}$) below (above) some given threshold. We did not observe clustering of atom s with high $t_{m \ ax}$ in any of the sam ples. For dense 2D bLJ glasses and for all 3D bLJ glasses studied, atom s with the lowest (negative) values of $t_{m \ in}$ were found to cluster together.

A simulated realization of a dense 2D bLJ glass in mechanical equilibrium is presented in gure 5 (both types of atoms are drawn with the same size). The 33% of atoms with the lowest (negative) values of t_m in are marked with yellow color and the remaining 67% are colored in blue, light blue, white, pink and red, corresponding to increasing values of t_m in . As can be seen from the

gure, the yellow atom s form nearly one dimensional percolating chains. Sim ilar pictures were obtained for other samples. The measured percolation threshold for atom s with lowest $t_{m \ in}$ is 30%. This value is lower than the theoretical percolation threshold for two dimensional lattices[22]. Indeed, for random ly chosen 30% of atom s, we found considerably sm aller clusters (with less atom s), that did not percolate.

Repeating the above measurements (with di erent thresholds) for snapshots of dense 2D bLJ glasses at higher temperatures, we did not observe such "force chains". On the other hand, running these systems at temperatures well within the vibrational regime (i.e. when no hopping occurred), and then performing a steepest descent quench to freeze the atom ic positions at local energy minima (see details in [10]), we observed similar patterns. This observation suggests that the mechanical equilibrium condition of zero force on each atom is a necessary condition for the form ation of percolating force chains.

To further investigate this point, a di erent preparation schem e was used to generate dense 2D bLJ system s. U sing sam ples of frozen 2D bLJ glass with = 0.596, all atom ic positions and the length of the simulation box were rescaled by 10%, then the system was frozen again to its new localm inim a. Com paring between the initial (with = 0.596) and nal (with = 0.735) sam ples, we observed that atom s with sm allest $t_{m \ in}$ are not the same e in the original and the nal states. We also observed that such com pression alone can not account for the form ation of force chains. Only after relaxation to a state of localm echanical equilibrium, the resultant sam ple form ed \force chains" sim ilar to those previously described.

A percolating cluster of atom s with lowest values of $t_{m \ in}$ in 3D bLJ glass at zero temperature is shown in gure 6 (to improve visualization, only a single cluster is plotted). If the threshold for $t_{m \ in}$ is chosen to include

5 6% of atom s (we found that with such a threshold the system is near to or slightly above percolation), the percolating clusters form nearly one dimensional chains and bops. A lthough the threshold values of $t_{m \ in}$ are di erent for the compressed and non-compressed 3D bLJ glasses ($t_{m \ in} < 77.5$ and $t_{m \ in} < 23$, respectively), we did not observe qualitative di erences in the force chains.

From the observations described in the previous paragraphs, we conclude that both the mechanical equilibrium condition of zero net force on every atom and small values of $t_{m \ in}$, are necessary for the form ation of force chains. To see why this is so, recall that mechanical equilibrium implies that the components of the force on an atom along mutually orthogonal directions have to vanish. In particular, for = 1; :::;d

$$f_{i} = \int_{j=1}^{X^{N}} J_{ij} f_{ij} \quad e = 0; \quad (7)$$

where f is the component of the force acting along the eigenvector \hat{e} . The environment of a typical atom i (corresponding to the vicinity of the peak of the distribution shown, e.g., in gure 1a) consists of mildly

com pressed and m ildly stretched bonds, and is therefore nearly isotropic. In this case, the mechanical equilibrium condition, equation 7, can be satis ed by balancing the negative and positive tensions in the bonds of the atom with all its neighbors. Now, consider an atom with

$$(t_{i})_{m in} = m in \int_{ij} J_{ij} (\hat{r}_{ij} \ _{i} \Theta)^{2} \qquad 0:$$

that belongs to the tail of the distribution. Inspection of

gure 1a reveals that for $t_{m,in}$ 0; the spread of values taken by $t_{m,ax}$ (and, in 3d, by the interm ediate eigenvalue) increases with decreasing $t_{m,in}$ resulting in increasingly anisotropic atom ic environment. In this case, the condition of zero force on atom i can only be satis ed by two sim ilarly compressed bonds with atom s j and k; oriented at nearly opposite directions. In order to balance the forces on atom j there should be another nearestneighbor with a highly compressed bond in a nearly opposite direction, and so on, leading to the form ation of force chains. Note that above arguments in ply that force chains would also be observed if one considers extrem al norm al forces J_{ij} instead of extrem al eigenvalues of the ABT tensor t_i . This result is in accord with that of ref. [9].

The above arguments can also explain, why for two and three dim ensional binary LJ glasses, sim ilar form ation of force chains of atom swith high values of t_{max} is not likely (although in ref. [9] weaker force chains were observed for pairs of highly stretched bonds). For these system s, the eigenvalues of ABT tensor corresponding to a highly stretched atom ic environm ent are of sim ilarm agnitude (see gures 1a, 2a, 3a and 4a) and force balance is achieved by nearly isotropic stretching of bonds between nearest neighbor atom s. Such a nearly isotropic organization implies that even if atom swith high t_{max} were to cluster, the clusters would not take the form of nearly one-dimensional chains, but rather that of isotropic localized inclusions. These results demonstrate that the directional organization of highly stretched atom ic environments is dierent from that of highly compressed ones. Since t are related to the internal stresses that are present in glassy system s even in m echanical equilibrium, our num erical results agree with A lexander's conjecture about the di erent organization of positive and negative internal stresses in glasses (the atom swith high values of t_{m ax} correspond to the "soft inclusions" discussed in ref. [4]).

VI. DISCUSSION AND CONCLUSIONS

In this paper we de ned a new parameter, the atom ic bond tension (ABT) tensor, and used it to study the directional organization of atom ic bond tensions. We found that in su ciently dense systems at very low tem – perature, the eigenvalues ft_1 ; dg ϕ fABT tensor are correlated i.e. are on the average, similar in sign and m agnitude. Thus, if one observes that the environm ent of an atom is stretched (com pressed) along some direction, one can predict with high probability that it would be com pressed (stretched) along other directions as well. Based on this correlation, one may conclude that atom ic environm ents in glasses in mechanical equilibrium are isotropic, at least in a statistical sense. However, since the eigenvalues of the ABT tensor of an atom are strictly non-degenerate, we conclude that the tendency towards perfect isotropy of atom ic environm ents is flustrated.

Since for systems with radial pair potential there is one-to-one correspondence between the separation R_{ij} and the tension J_{ij} in the bond [ij], the observed correlations between the bond tensions in ply also correlations between the corresponding R_{ij}. Thus, various combinations of inter-atom ic distances, and especially of nearest-neighbor separations in glassy systems, are constrained, and their localorganization is not random. The observed deviations from random ness are associated with directional correlations; if only isotropic m easures of disorder such as local volum e strain [5], deviation from local sphericity [23] or local pressure [17] are considered, such correlations are not taken into account and a m ore random description of dense liquids and glasses results.

The results of num erical simulations reported in this paper provide a direct con mation of A lexander's conjecture that \the reference state of the glass cannot be regarded as an arbitrary random state" (see chapter 16 in ref. [4]). Qualitatively, correlations among ABT are expected from the requirement that the forces on each atom of a structurally disordered system in mechanical equilibrium are balanced, and that each atom is caged in a potential well, i.e., that each atom is subject to a set of constraints that include zero net force and a stable atom ic environment. For systems with a radial pair potential, the one-to-one correspondence between the separation of two atoms and the tension on their \bond" means that achieving balance of forces and local stability simultaneously for every atom in the system, reduces the number of degrees of freedom and sets strong constraints on the observed ABT. The observed strong correlations between the eigenvalues of ABT, in two-and three-dim ensional binary LJ glasses, in ply that when the asymmetry between the bonds is strong (e.g., due to two types of atom s), the directional organization of bond tensions that would comply with force balance and local stability is subject to stronger constraints.

Since the Einstein frequencies of atom ic vibration around an equilibrium position are determined by the derivatives of the inter-particle pair potential, the observation of correlations between the corresponding R_{ij} im plies that the atom ic force constants are not random as well. Thus, further quanti cation of correlations in atom ic force constants is required before one can incorporate them into lattice-based models which aim to reproduce the inhom ogeneous network of force constants m easured for simulated glasses (see, e.g., [24]).

The self-organization of norm al forces under various

external stresses (com pression, shear) has been extensively studied for granularm aterials [25, 26, 27, 28], and recently also for liquids and glasses [14], and for model random packing [29]. We studied the self organization of bond tensions on an atom ic level, and showed that external com pression has strong qualitative e ect on the local organization of the atom ic bond tensions. In com pressed two and three dimensional binary LJ glasses, atom s with the sm allest eigenvalues of ABT tensor are organized in nearly one dimensional chains and loops. Since force chains were observed only for systems at zero tem perature, we concluded that balance of forces on each atom is a necessary requirement for such organization. Although this is a custom ary requirement in modeling of force chains in granular materials [12], to the best of our know ledge such a requirem ent, although obvious, was not previously suggested in the context of glasses. In glasses with repulsive {attractive pair interactions, force balance can be achieved both by directional organization of stretched and compressed bonds in a way that their total e ect is zero, or by strong, nearly collinear compression of pairs of bonds (sim ilar stretching of pairs of bonds is not possible, since it is not a stable con guration). For externally compressed glassy system s, there are not enough stretched bonds to

7

balance the compressed ones, and only self-organization into one-dimensional structures (force chains) of highly compressed bonds can balance the forces for every atom.

Finally we would like to comment on several open issues for future research. We do not yet understand the physical origin of the observed condict between the directional correlations and the strict non-degeneracy of the eigenvalues of ABT, and of the resulting frustrated tendency towards local isotropy of atom ic environments in glasses. While we demonstrated the existence of organization of the atom ic bond tensions in glasses and in Inherent States of liquids and quantiled the extent to which they deviate from a random distribution, a more intuitive understanding of the dilerence between such complex organized states and purely random ones, is clearly needed.

A cknow ledgm ents

 $Y\,R\,$ would like to acknow ledge the support by a grant from the Israel Science Foundation.

Zeev O lam i died before this manuscript was submitted. We miss him a lot.

- [L] T.Egam i, K.M adea and V.V itek, Philos. M ag. A 41, 883 (1980); S.-P.Chen, T.Egam i and V.V itek, Phys. Rev. B 37, 2440 (1988).
- [2] M.K lem an and J.F.Sadoc, J.Physique 40, L569 (1979).
- [3] D.K ivelson and G.Tarjıs, J.Non-Cryst. Solids 235, 86 (1998).
- [4] S.Alexander Phys. Rep. 296, 65 (1998).
- [5] T.Egam i, Mater. Sci. Eng. A 226, 261 (1997).
- [6] L.D. Landau and E.M. Lifshitz, Theory of Elasticity, third edition (Pergam on Press, Oxford, 1986).
- [7] M. Born and K. Huang, Dynamical Theory of Crystal Lattices (Oxford University Press, 1954).
- [8] T.Kustanovich, S.Alexander and Z.O lam i, Physica A 266, 434 (1999).
- [9] J. P. W ittm er, A. Tanguy, J. -L. Barrat and L. Lewis, Europhys. Lett. 57, 423 (2002).
- [10] T. Kustanovich Ph. D. Thesis, W eizm ann Institute of Science, Rehovot (2002).
- [11] F. H. Stillinger and T. A. W aber, Science 225, 983 (1984).
- [12] C. -h. Liu, S. R. Nagel, D. A. Schecter, S. N. Coppersm ith, S.M ajum dar, O. Narayan and T. A. W itten, Science 269, 513 (1995).
- [13] F.Radjai, M. Jean, J.J.M oreau and S.Roux, Phys. Rev. Lett. 77, 274 (1996).
- [14] C.S.O'Hem, S.A.Langer, A.J.Liu and S.R.Nagel, Phys. Rev. Lett. 86, 111 (2001).
- [15] S.F.Edwards and C.C.Moun eld, Physica A 226, 1 (1996).
- [16] S.N. Coppersm ith, C.-h.Liu, S.M a jum dar, O.N arayan and T.A.W itten, Phys. Rev. E 53, 4673 (1996).
- [17] T.Kustanovich and Z.Olami, Phys. Rev. B 61, 4813

(2000).

- [18] D. N. Perera and P. Harrowell Phys. Rev. E 59, 5721 (1999); J. Chem. Phys. 111, 5441 (1999).
- [19] W . Kob and H. C. Andersen Phys. Rev. E 51, 4626 (1995).
- [20] M. P. Allen and D. J. Tilesley Computer Simulation of Liquids (Clarendon Press, Oxford, 1987).
- [21] In nearly isotropic atom ic environment, the eigenvalues $ft^1;t^2;t^3g$ have close values and considering only the extrem e values t_m in and t_m ax captures this point. If the atom ic environment is highly compressed in one direction (corresponding to t_m in) and highly stretched in an orthogonal direction (corresponding to t_m ax), there is a considerable range of values that the third eigenvalue can take, and in portant information may be lost by considering only ft_m in; t_m ax g. For the 3D bLJ system s considered, both simulated and random distributions, the probability for having simultaneously t_m in 0 and t_m ax 0 was found to be vanishingly sm all, thus validating our approach.
- [22] D. Stau er, Introduction to percolation theory (Taylor and Francis, London, 1985).
- [23] F.W. Starr, S. Sastry, J.F. Douglas and S.C.G lotzer Phys. Rev. Lett. 89, 125501 (2002).
- [24] L. Angelani, M. Montagna, G. Ruocco and G. Viliani Phys. Rev. Lett. 84, 4874 (2000).
- [25] M. E. Cates, J. P. W ittmer, J. -P. Bouchaud and P. Claudin, Phys. Rev. Lett. 81, 1841 (1998).
- [26] A.V.Tkachenko and T.A.W itten, Phys. Rev. E 60, 687 (1999).
- [27] F. Radjai, S. Roux and J. J. Moreau, Chaos 9, 544 (1999).

- [28] J. -P. Bouchaud, P. C laudin, D. Levine and M. Otto, Eur. Phys. J. E 4, 451 (2001).
- [29] C.S.O 'Hem, S.A.Langer, A.J.Liu and S.R.Nagel, Phys. Rev. Lett. 88, 075507 (2002).

F igu res

- 1.a. Histogram of P ($t_{m \text{ in}}; t_{m \text{ ax}}$) for 3D bLJ system with = 12 at T = 0 (N = 16384).b. Histogram P ($t_{m \text{ in}}^{r}; t_{m \text{ ax}}^{r}$) for the sam e 3D bLJ system.
- 2.a. Histogram of P ($t_{m in}; t_{m ax}$) for dense 3D bLJ system with = 1:4 at T = 0 (N = 16384 particles). b. Histogram P ($t_{m in}^r; t_{m ax}^r$) for the same dense 3D bLJ system.
- 3.a. Histogram of P ($t_{m in}$; $t_{m ax}$) for 2D bLJ system s

with = 0:596 at T = 0. (Totalnum berof particles is 16384.) b. H istogram P (t_m^r in; t_m^r ax) for the same 2D bLJ system s.

- 4. a. H istogram of P ($t_{m in}; t_{m ax}$) for dense 2D bLJ system s with = 0:735 at T = 0. (Total number of particles is 16384.) b. H istogram P ($t_{m in}^{r}; t_{m ax}^{r}$) for the same dense 2D bLJ system.
- 6.3D bLJ systems with = 1:4 loop-like cluster of atom s with $t_{m in} < 77.5$.

This figure "fig1a.jpg" is available in "jpg" format from:

This figure "fig1b.jpg" is available in "jpg" format from:

This figure "fig2a.jpg" is available in "jpg" format from:

This figure "fig2b.jpg" is available in "jpg" format from:

This figure "fig3a.jpg" is available in "jpg" format from:

This figure "fig3b.jpg" is available in "jpg" format from:

This figure "fig4a.jpg" is available in "jpg" format from:

This figure "fig4b.jpg" is available in "jpg" format from:

This figure "fig5.jpg" is available in "jpg" format from:

This figure "fig6.jpg" is available in "jpg" format from: