

Nonlinear microscopic relaxation of uniform magnetization precession

Vladimir L. Safonov and H. Neal Bertram
 Center for Magnetic Recording Research,
 University of California – San Diego,
 9500 Gilman Drive, La Jolla, CA 92093-0401
 (March 22, 2024)

Dynamic relaxation for nonlinear magnetization excitation is analyzed. For direct processes, such as magnon-electron scattering and two-magnon scattering, the relaxation rate is determined from the linear case simply by utilizing the magnetization oscillation frequency for nonlinear excitation. For an indirect process, such as slow-relaxing impurities, the analysis gives an additional relaxation term proportional to the excitation level. In all cases the effective magnetization damping is increased compared to Landau-Lifshitz-Gilbert damping.

I. INTRODUCTION

The study of damped magnetization dynamics of ferromagnetic particles and thin films is important for the development of nanomagnetic devices and high-density magnetic recording. A conventional theoretical tool to study magnetization relaxation is based on the phenomenological Landau-Lifshitz equation [1] or its modification with Gilbert damping [2]. These equations conserve the absolute value of magnetization ($M_j = \text{const}$) in a single domain region due to a strong exchange interaction approximation. They are relatively simple and therefore have been utilized for various calculations and micromagnetic simulations. However both Landau-Lifshitz and Gilbert equations were introduced (a) for small magnetization motions and (b) for the case of high magnetic symmetry (axial symmetry) with an isotropic damping fitting parameter ("damping constant"). Nevertheless both "a" and "b" conditions are usually violated.

Recently a theoretical approach [3], [4], [5], [6], [7] has been developed to correct the limitations of the Landau-Lifshitz-Gilbert (LLG) theory. The main idea was to represent the magnetization dynamics as the motion of a damped nonlinear oscillator with the random force of thermal fluctuations. The oscillator model is a convenient tool to establish a "bridge" between themicroscopic physics, where the rotational oscillator variables a and b naturally describe spin excitations (as creation and annihilation operators) and the macroscopic magnetization dynamics. In particular, it has been rigorously shown by including specific coupling of a magnetic system to a variety of loss mechanisms, that for small oscillations near equilibrium the macroscopic damping term reflects

the anisotropy of the system [8], [9]. Only for complete uniaxial symmetry do the LLG results apply.

Nonlinearity in the relaxation process appears with the increase of magnetization deviation from equilibrium. Depending on the situation, the nonlinear magnetization damping either increases or decreases the total relaxation rate. For example, in our simulations of magnetization reversal (large magnetization motion) by spin-wave dynamics in a quasi-single-domain grain [10] we have demonstrated that an effective damping parameter can be about hundred times greater than that in the linear regime. For a single-domain grain a phenomenological extension of the oscillator approach to nonlinear excitations has been made [3]. In this case for large amplitudes the effective damping is much greater than that of LLG.

The aim of this paper is to give a microscopic analysis of nonlinear magnetization damping. We consider both direct and indirect loss mechanisms and show explicitly how nonlinearity is included in the relaxation rate. The approach is to first transform the magnetization dynamics without damping to rotational oscillator coordinates. This transformation yields equations where the oscillator frequency depends on the degree of nonlinearity. The analysis parallels the approach for low-level excitations.

II. THE NONLINEAR OSCILLATOR MODEL

Here we review the magnetization dynamics in terms of a nonlinear oscillator. For simplicity we shall consider a single-domain grain in the case when the external magnetic field H_0 is parallel to the uniaxial anisotropy axis (z). To describe the magnetization dynamics $M(t)$, we introduce the classical spin $S = MV/\hbar$, where V is the grain volume, \hbar is Planck's constant and γ is the gyromagnetic ratio. Using the Holstein-Primakoff transformation:

$$\begin{aligned} S^+ &= a \sqrt{\frac{2S}{N}}; \quad S^z = S - a^\dagger a; \\ S^- &= a^\dagger \sqrt{\frac{2S}{N}}; \quad S^x = \frac{S^+ + S^-}{2}; \quad S^y = \frac{S^+ - S^-}{2i}; \end{aligned} \quad (1)$$

where $N = a^\dagger a = \frac{1}{2}(S^+ S^- + S^- S^+)$, we can represent the magnetization dynamics in terms of the oscillator variables:

$$da/dt = -i\omega(N)a; \quad (2)$$

The oscillator (2) is characterized by the magnetization oscillation frequency for nonlinear excitation:

$$\dot{\epsilon}(N) = \omega_0 [1 - N/S(1 + H_0/H_K)]; \quad (3)$$

which reflects the change of effective magnetic field with increasing magnetization deviation from equilibrium. H_K is the anisotropy field, $\omega_0 = (H_0 + H_K)$ is the ferromagnetic resonance frequency.

Previously it was assumed that the corresponding stochastic differential equation is of the following form [3], [5]:

$$(d=dt + \dot{\epsilon}(N))a = i\dot{\epsilon}(N)a + f(t); \quad (4)$$

where $f(t)$ describes a random uncorrelated force and $\dot{\epsilon}(N)$ is the nonlinear damping. The formulas (1) and (3) are valid within one potential well up to the top of the energy barrier $0 < N < N_{top}$, where $\dot{\epsilon}(N) = 0$ ($N_{top} = S(1 + H_0/H_K)$). Utilizing the fluctuation-dissipation theorem for (4), the nonlinear damping is given by [3]:

$$\dot{\epsilon}(N) = -\frac{1}{2} \frac{d^2 \dot{\epsilon}(N)}{dN^2} \Big|_{N=0} = -\dot{\epsilon}'(0)N; \quad (5)$$

III. NONLINEAR RELAXATION MECHANISMS

In this section we show how nonlinear relaxation arises from microscopic mechanisms. The linear relaxation rate (0) is well understood and determined by solving the coupled magnetic-thermodynamic equations. The main mathematical idea is that the principal complex amplitude dynamics in the small damping approximation ($\dot{\epsilon}(N) = \dot{\epsilon}(N)$) is given (from either (2) and (4)) by

$$a(t) / \exp[i\dot{\epsilon}(N)t]; \quad (6)$$

For all cases where the relaxation is of a direct form of coupling (see, [9]), the microscopic analysis will yield the same relaxation expression for a given mechanism except that ω_0 is replaced by $\dot{\epsilon}(N)$.

A. Magnon-electron scattering

Let us consider the magnon-electron scattering process in a ferromagnetic metal [9], [11]. A magnon with wave vector $k = 0$ and energy $\hbar\omega_0$ and a conduction electron with wave vector $k \neq 0$ and energy $\hbar\omega_{ek}$ are transformed into a conduction electron with wave vector k^0 and energy $\hbar\omega_{ek^0} = \hbar\omega_{ek} + \hbar\omega_0$. This confluence process occurs in the presence of defects to violate momentum conservation. The linear relaxation rate for this process can be written as:

$$\gamma_{me} = c_{def} \sum_{k,k^0} \frac{f_{kk^0}^2}{N} (\bar{n}_k - \bar{n}_{k^0}) (\omega_{ek^0} - \omega_{ek} - \omega_0); \quad (7)$$

where c_{def} is the defect concentration, f_{kk^0} is the scattering amplitude and \bar{n}_k is the Fermi occupation number. Neglecting ω_0 dependence in the scattering amplitude and taking into account that $\omega_0 \ll \omega_{ek}$ and $\bar{n}_k \approx \bar{n}_{k^0}$, $\omega_0 \bar{n}_k \approx \omega_{ek}$, from (7) we obtain:

$$\gamma_{me} = c_{def} \omega_0 \sum_k \frac{(\partial \bar{n}_k / \partial \omega_{ek})^2}{N} (\omega_{ek^0} - \omega_{ek}) \quad (8)$$

with a linear dependence γ_{me} / ω_0 . Replacing $\omega_0 \bar{n}_k$ by $\dot{\epsilon}(N)$, we have:

$$\gamma_{me}(N) = \dot{\epsilon}(N) \gamma_{me} / \omega_0 = \gamma_{me} \quad (9)$$

in agreement with the phenomenological relation (5).

B. Two-magnon scattering

The linear regime of two-magnon scattering on defects has been considered by many authors (e.g., [12], [13], [14], [15]). The linear relaxation rate for this process is given by:

$$\gamma_{2m} = \sum_k G_k^2 (\omega_k - \omega_0); \quad (10)$$

where G_k describes the scattering amplitude and ω_k is the spin-wave frequency with $k \neq 0$. The above mentioned simplification gives:

$$\gamma_{2m}(N) = \sum_k G_k^2 [\omega_k(N) - \dot{\epsilon}(N)]; \quad (11)$$

Here $\omega_k(N)$ is the spin-wave frequency taking account of nonlinear excitation. This example does not give, in general, a linear relation between $\gamma_{2m}(N)$ and $\dot{\epsilon}(N)$.

C. Slow relaxation

The energy loss in this case occurs via an intermediate damped dynamic system, the 'slow relaxing' impurities (e.g., [9], [13], [16]). The magnetization motion modulates the impurity splittings and varies the thermalequilibrium populations of the energy levels. Let us consider two-level impurities with energy:

$$H_{imp;j} = \hbar \omega_{0;j} + \hbar \omega_j(t) n_j; \quad (12)$$

where $\omega_{0;j}$ is the splitting frequency, n_j is the upper level population and j is the impurity index. The impurity level modulation is defined as:

$$\omega_j(t) = \omega_{ja}(t) + \omega_{jb}(t); \quad (13)$$

The nonlinear dynamic equation for the complex amplitude is:

$$\begin{aligned} da/dt &= i\epsilon(N)a - i\epsilon(H_{imp;j}=h)/da \\ &= i\epsilon(N)a - i \sum_j n_j(t): \end{aligned} \quad (14)$$

The kinetics of the impurity population is defined by the following equation:

$$dn_j/dt = k_{ij}(j)[n_j - n_T(j)] \quad (15)$$

Here $k_{ij}(j)$ is the impurity relaxation rate and $n_T(j) = [\exp(h_j/k_B T) + 1]^{-1}$ is the equilibrium population at frequency $j(t) = \omega_{ij} + j(t)$. We can solve Eq.(15) and obtain:

$$\begin{aligned} n_j(t) &= \exp[k_{ij}(t_1) - k_{ij}(t)] k_{ij}[j(t_1)] \\ &\quad \int_{t_1}^t n_T(j(t_1)) - n_T(\omega_{ij}) g dt_1; \end{aligned} \quad (16)$$

where $n_j(t) = n_j(t) - n_T(\omega_{ij})$ and $k_{ij}(t) = \int_{t_1}^t k_{ij}[j(t_1)] dt_1$.

In the case of small modulation $h_j(t) \ll k_B T$ we can write the following expansion: $n_T[\omega_{ij} + j(t)] = n_T(\omega_{ij}) + [\partial n_T(\omega_{ij})/\partial \omega_{ij}] j(t) + \dots$ Neglecting for simplicity the $j(t)$ dependence of k_{ij} , we can rewrite Eq.(16) in terms of $a(t)$ and $a^*(t)$ and substitute these terms into (14). Thus, we can obtain the nonlinear relaxation rate in the form:

$$s_r(N)' = s_r + \frac{(1)}{s_r} N; \quad (17)$$

where

$$s_r' = \sum_j X_j j j^2 \frac{\partial n_T(\omega_{ij})}{\partial \omega_{ij}} \frac{\omega_{0k;j}}{2k_{ij}^2 + \omega_{0k;j}^2} \quad (18)$$

is a linear relaxation rate and

$$\frac{(1)}{s_r} = \sum_j X_j \frac{j j^4}{2} \frac{\partial^3 n_T(\omega_{ij})}{\partial \omega_{ij}^3} \frac{\omega_{0k;j}}{2k_{ij}^2 + \omega_{0k;j}^2} \quad (19)$$

is the coefficient of a nonlinear damping. We can see that, even though the relaxation rate depends on the level of excitation, in general, $s_r(N) = \epsilon(N) \neq s_r = 0$.

IV. DISCUSSION

We have considered nonlinear relaxation for both direct and indirect coupling to a thermal bath. For direct coupling it was shown that the linear relaxation rate can be simply converted to the nonlinear rate by replacing the linear frequency ω_0 by the nonlinear frequency $\epsilon(N)$. In one case of direct coupling, magnon-electron

scattering, the nonlinear relaxation rate was shown to be directly proportional to the nonlinear frequency, as in the initial phenomenological approach (5). For the case of two-magnon scattering the relaxation rate, in general, is not proportional to the nonlinear frequency. A specific case of indirect interaction, 'slow-relaxing' impurities, was analyzed in detail. The resulting relaxation rate was the sum of the linear term plus a nonlinear term proportional to the level of excitation. An absence of linear relation between the nonlinear damping $\epsilon(N)$ and magnetization oscillation frequency for nonlinear excitation $\epsilon(N)$ indicates a colored thermal noise in the system.

In Ref. [3] it was shown that the nonlinear oscillator damping is greater than the conventional damping in the Landau-Lifshitz equation. This result is a general conclusion for all the relaxation mechanisms considered here. Corresponding to (4) and (5) the magnetization dynamic equation can be written as

$$dM/dt = M H_e + (e - M_s)M \quad dM/dt; \quad (20)$$

where, in general,

$$e = \frac{\epsilon(N)}{\epsilon(N)(1 - N/2S)}; \quad \frac{N}{S} = \frac{M_s - M_z}{M_s} = 1 - \cos \theta; \quad (21)$$

Here θ is the deviation angle. In the vicinity of equilibrium ($N = 0, M_z = M_s, \theta = 0$) $e = e(0) = 1/\alpha$, where α is the LLG parameter. Away from equilibrium, the damping parameter increases with increasing nonlinearity, becoming infinite as $N \rightarrow 2S$ ($M_z \rightarrow -M_s$, or $\theta \rightarrow \pi$). An application of this approach to magnetization reversal is discussed in Ref. [17].

V. ACKNOWLEDGMENT

This work was partly supported by matching funds from the Center for Magnetic Recording Research at the University of California - San Diego and CMRR incorporated sponsor accounts.

-
- [1] L. Landau and E. Lifshitz, Phys. Z. Sowjet. 8, 153 (1935); in Landau L.D. Collected Papers, edited by D. ter Haar (Gordon and Breach, New York, 1967) p.101.
 - [2] T. L. Gilbert, Phys. Rev. 100, 1243 (1955).
 - [3] V. L. Safonov, J. Magn. Mater. 195, 526 (1999); J. Appl. Phys. 85, 4370 (1999).
 - [4] V. L. Safonov and H. N. Bertram, J. Appl. Phys. 87, 5681 (2000).
 - [5] V. L. Safonov and H. N. Bertram, in: The Physics of Ultra-High-Density Magnetic Recording, edited by M.

- Plumer, J. van Ek, and D. Weller (Springer, Berlin, 2001), p.81.
- [6] X. Wang, H. N. Bertram, and V. L. Safonov, J. Appl. Phys. 91, 6920 (2002).
 - [7] X. Wang, H. N. Bertram, and V. L. Safonov, J. Appl. Phys. 92, 2064 (2002).
 - [8] H. N. Bertram, V. L. Safonov, and Z. Jin, Trans. Magn. 38, 2514 (2002).
 - [9] V. L. Safonov and H. N. Bertram, arXiv: cond-mat/0207721, submitted to J. Appl. Phys.
 - [10] V. L. Safonov and H. N. Bertram, J. Appl. Phys. 87, 5508 (2000).
 - [11] V. Kambersky and C. E. Patton, Phys. Rev. B 11, 2668 (1975).
 - [12] M. Sparks, Ferromagnetic-Relaxation Theory (McGraw-Hill, New York, 1964).
 - [13] A. G. Gurevich and G. A. Melkov, Magnetization Oscillations and Waves (CRC Press, Boca Raton, Fla., 1996)
 - [14] M. J. Hurben and C. E. Patton, J. Appl. Phys. 83, 4344 (1998).
 - [15] R. Arias and D. L. Mills, Phys. Rev. B 60, 7395 (1999).
 - [16] A. S. Mikhailov and R. M. Farzetdinova, Sov. Phys. JETP 57, 109 (1983).
 - [17] X. Wang and H. N. Bertram, MMM '02, DH-04, to appear in J. Appl. Phys. (2003).