The 3d-electron states in FeB r_2

Z.Ropka

Center for Solid State Physics, S^{nt} Filip 5,31-150K rakow, Poland

R.J.Radwanski

Center for Solid State Physics, S^{nt} Filip 5,31–150K rakow, Poland Institute of Physics, Pedagogical University, 30–084 K rakow, Poland

em ail: sfradwan@ cyf-kr.edu.pl, http://www.css-physics.edu.pl

The fundamental controversy about the electronic structure for 3delectron states in FeB r_2 is discussed. We advocate for the localized electron atom ic-like many-electron crystal- eld approach that yields the discrete energy spectrum, in the scale of 1 m eV, associated with the atom ic-like states of the Fe²⁺ ions in contrary to the (sem i-)continuous energy spectrum yielded by band theories. In our approach the six d electrons of the Fe²⁺ ion form the highly-correlated atom ic-like electron system 3d⁶ described by two H und's rules quantum num bers S = 2 and L = 2 with taking into account the spin-orbit coupling. The superiority of our model relies in the fact that it explains consistently properties of FeB r_2 , the insulating and the magnetic ground state as well as therm odynam ics and R am an low-energy spectra, using wellestablished physical concepts.

PACS No: 75.50 Ee: 71.15 M b

Keywords: 3d m agnetism, Hund's rules, spin-orbit coupling, crystal eld,

FeBr₂

There is a fundam ental controversy in the description of 3d states in FeB r_2 : This controversy is related to origin of the magnetism and of the electronic structure of 3d-atom containing compounds. The understanding of the magnetism and of the electronic structure is very closely related to a general problem "how to treat d electrons in 3d-atom containing com pounds". The fundam ental controversy "how to treat d electrons" starts already at the beginning – should they be treated as localized or itinerant (in the scienting composition of the scienting com ie. the localized or the itinerant picture should be taken as the start). D irectly related to this problem is the structure of the available states: do they form the continuous energy spectrum like it is in the band picture or do they form the discrete energy spectrum typical for the localized states. Recently, at the beginning of 2002, Youn, Sahu and K im (YSK) have presented an all-electron fully relativistic density-functional calculations, an extension of the density-functional approximation (LDA), for the electronic structure and the resulting m agnetic m on ent, including the orbital m on ent [1]. This paper followed a paper of Ropka, M ichalski and Radwanski (RMR), from M ay 2001, who have presented, within the quasi-atom ic approach, the electronic structure and the resulting properties like spin and orbital contributions to the m agnetic m on ent of the iron atom and therm odynam ics [2]. Y SK claim, contradicting the earlier RMR result for the spin-orbit coupling origin of the orbitalm on ent, that the orbitalm on ent is rather due to the strong on-site correlations of the 3d orbitals.

The aim of this paper is to show up that both approaches largely concurs as far as the origin of the orbitalm on ent is concerned. However, there is a fundam ental di erence between these two approaches as far as the description of the electronic structure and the physical nature of the 3d states is discussed. A coording to us, this fundam ental di erence in the electronic structure can be experim entally revealed and can be used as the experim ental veri cation of di erent theoretical approaches.

The electronic structure for the 3d electrons in the YSK approach is related to the band description. Youn et al. have extended the standard local density approximation (LDA), in fact the LSDA, calculations by introducing a large intraorbital correlation energy U of the d electrons. Such the calculations are known as L(S)DA+U calculations [3{7]. Their L(S)DA+U results for the d-electron states are schematically shown in Fig. 1. The energy spectrum for the 3d states contains continuous, though quite narrow, bands centered at -9 eV, -6.5 eV (built up from 5 spin-up states) and at -0.2, +1.6 and +2.2 eV for the spin-down states. Thus, the occupied 3d states spread over 10 eV. A gap, needed for the insulating state, within this band picture is obtained by the correlation energy U [1].

The general shape of the bands presented in Fig. 1 can be som show understood knowing the localized states within the single-electron crystal eld. The continuous energy spectrum looks like the smooth convolution on the available, largely spread, localized 3d one-electron orbitals, t_{2g} and higher e_g orbital. A coording to this picture 6 electrons (spins) of the Fe²⁺ ion are put subsequently one by one on the one-electron states form ed for one d electron in the octahedral crystal eld (CEF): three spins are put to the spin-up $\frac{1}{2g}$ orbitals, other two occupies spin-up e_g orbitals, and the last electron has to occupy one spin-down t_{2g} orbital. A coording to Refs [1] such the electron/spin arrangement satis es the rst Hund's rule.

Ropka et al.'s description, Ref. [2], of the electronic structure, Fig. 2, is related to the localized picture, but with taking into account two H und's rules and the intra-atom ic spin-orbit coupling. In this atom ic-like m any-electron CEF approach the 6 d electrons in the open 3d shell form the highly-correlated intra-atom ic $3d^6$ electron system. The strong correlations am ong the 3d electrons are accounted for, in a zero-order approximation, by two H und's rules. The two H und's rules yield for the d^6 system the ground term 5D with S=2 and L=2. Its 25-fold degeneracy is removed by the crystal eld and spin-orbit interactions. In the octahedral brom ium -anion surrounding of the Fe²⁺ ion, realized in the hexagonal structure of FeB r_2 , the orbital triplet ${}^5T_{2g}$ is lower than the orbital doublet 5E_g , being separated by

of about 2 eV. The T_{2g} ground subtem is conmed by our ab initio calculations of the hexadecapolar potential (the A_4 CEF coemicant) at the Fe site in the bromium -anion octahedron. The A_4 CEF coemicant in the center of the anion octahedron is positive. The A_4 CEF coemicant together with the Stevens factor for the $3d^6$ system, of + 2/63 ([8], table 19 on page 873), yields the positive value of the octahedral CEF parameter B_4 and the ${}^5T_{2g}$ ground subtem. The positive sign for B_4 in the anion octahedron has been derived already a pretty long time ago by Abragam and B leaney ([8], see page 374). However, this result has been completely forgotten in the current theoretical solid-state physics.

In general, we take the VSK results as the con mation of our result about the substantial orbitalm om ent. We fully agree that the orbitalm om ent is mostly due to the correlations of the 3d orbitals, though the YSK paper tries to contradict both our results about the origin

3

of the large orbital magnetic moment pointing out that Ropka et al. have speculated (no, no, we have calculated it, and we can prove it!!!) that the orbital moment is due to the spin-orbit coupling. A coording to us, our statement about the spin-orbit coupling origin of the orbital moment does not exclude the correlation e ects. In contrast, our many-electron CEF approach considers d electrons in the very strong correlation limit. It was, somehow, correctly recognized by VSK that in the quasi-atom ic model the d-d on-site correlations are included inherently (by two H und's rules), despite of their lack in the explicit form.

The obtained value of the ordered magnetic moment at zero temperature amounts to 4.26_{B} . It is built up from the spin moment of $+3.48_{B}$ and from the orbital moment of $+0.78_{B}$ [2]. We point out that the same sign of the spin and orbital moments comes out directly from our calculations and is related to the negative sign of the intra-atom ic spin-orbit coupling. The elective moment calculated from the 1 vs T plot in the 300-400 K region amounts to 5.39_{B} . It is only slightly larger value than the spin-only value of 4.90_{B} what is a surprise owing to the fact that the full quantum orbital value L (= 2) is taken into calculations.

Our description of the electronic structure of FeBr₂ proceeds within the intermediate crystal- eld regim e in contrary to the current-literature view that prefers the strong crystal eld regim e in the description of 3d-atom compounds. A coording to our picture, the crystal eld is intermediate in the sense that it is stronger than the spin-orbit coupling but it is relatively weak because it does not break the intra-atom ic arrangement of electrons within the 3d shell, as is in the one-electron version of the crystal- eld theory. It means, that we think that the intra-atom ic structure of a param agnetic atom largely perseveres even when this atom becomes the full part of a solid - on this basis we have developed a Quantum A tom istic Solid-State Theory (QUASST) for compounds containing open 3d-/4f-/5f-shell atom s [9,10]. This weak crystal- eld approach, know n within the rare-earth CEF community as the CEF approach, has been offen successfully applied to 3d-ion doped system s, when 3d ions were introduced as in purities, in interpretation of, for instance, electron-param agnetic-resonance experiments [8,11,12]. In Refs [13(16] we have applied this approach to a 3d-ion

4

system where Co/Fe/Ni i ions are the full part of a solid form ing $LaCoO_3$, FeO or NiO. Of course, in our picture the crystal eld is much stronger than the spin-orbit coupling as is generally accepted in the 3d magnetism. It is worth noting that the CEF states in our approach are many-electron states of the whole highly-correlated electron system $3d^6$. M oreover, in QUASST the magnetic state, below T_N of 14 K, is clearly distinguished from the paramagnetic state, see Fig. 4 of Ref. [2]. It is not clear how will look like the band electronic structure of Ref. [1] in the paramagnetic state, i.e. above T_N of 14 K, because it was not presented and not discussed in Ref. [1].

We would like to point out that the QUASST approach should not be considered as the treatment of an isolated ion -we consider the cation in the octahedral crystal ekd. This octahedral crystal ekd is predom inantly associated with the anion octahedron FeB g. The FeB r_2 structure is built up from the face sharing octahedra FeB r_6 - thus such the atom ic structure occurs at each cation due to the translational symmetry. The strength of the crystal- ekd interactions is determined by the whole charge surroundings, not only by the nearest brom ium octahedron. It makes that the CEF approach, in the version applied in QUASST, boks like a single-ion approach but in fact it describes the coherent states of the whole crystal. The parameters used in the discussion of properties of FeB r_2 in Ref. [2], are fully physical: the octahedral CEF parameter $B_4 = +200$ K, the trigonal $B_2^0 = -30$ K and the spin-orbit coupling = -150 K. They yield the overall elect of 2.06, 0.06, and 0.13 eV, respectively.

The electronic structure can be experimentally veried. In QUASST the shown states manifest in many physical properties like tem perature dependence of the heat capacity, of the paramagnetic susceptibility , of the magnetic moment value. The energy separations should be detected by energy spectroscopy experiments like R am an spectroscopy, for instance. In fact, we take old, but rather unknown, results of the R am an spectroscopy [17,18] revealing a number of well-de ned energy excitations as a conmation of our atom istic model. The observed 8 excitations up to 637 cm⁻¹ can be fully reproduced by our calculations with the same crystal- eld parameters $B_4 = +200$ K and $B_2^0 = -30$ K and a spin-orbit coupling of -161

5

 $K:0 (\exp - 0); 22.8 \text{ cm}^{-1} (\exp : -23 \text{ cm}^{-1}); 181 (192); 209 (244); 281 (296); 516 (517); 517 (517); 608 (584); 630 (630); 636 (637 \text{ cm}^{-1}) [19]. The tted value for the spin-orbit coupling in FeB r₂ is only slightly larger than the assumed by us free-ion value of -150 K [20]. So good description of new type of experimental results with the parameters derived from analysis of the heat capacity and of the magnetic moment we take as a strong argument for the high physical adequacy of QUASST.$

In conclusion, we point out that the band L (S)DA description of FeB r_2 , completed by the U term, largely concurs to the localized many-electron CEF description in revealing the very strong electron correlations determ ining the orbital magnetic moment. These two approaches can, however, be easily distinguished, as the proposed electronic structures are completely di erent. Also the nature of the 3d states is completely di erent. We are in favour of the localized electron atom ic-like many-electron crystal- eld approach that yields the discrete energy spectrum associated with the atom ic-like states of the Fe^{2+} ions. The superiority of our model relies in the fact that it consistently describes both zero-tem perature properties of FeBr, and therm odynamics and it makes use of the well-de ned physical concepts. Our atom ic-like approach provides in the very natural way the insulating ground state for FeBr₂ independently on the lattice distortions. The success of the LDA+U calculations of Youn et al. is related to the orientation of LDA calculations to the strong intra-atom ic d-d correlation limit. A coording to us, the LDA+U calculations have to largely reproduce two Hund's rules. We welcome the paper of Ref. [1]-it bridges somehow LDA calculations and CEF calculations. However, we would like to put attention that our electronic structure is determined within the meV scale what is about 5000 times smaller than the band width of Ref. [1] of 0.5 eV.

[1] S.J.Youn, B.R.Sahu, and Kwang S.K im, Phys. Rev. B 65, 052415 (2002).

[2] Z. Ropka, R. Michalski, and R. J. Radwanski, Phys. Rev. B 63, 172404 (2001);

http://xxx.lanlgov/abs/cond-m at/0005502.

- [3] D.D.Sarma, N.Shanthi, S.R.Barman, N.Hamada, H.Sawada, and K.Terakura, Phys. Rev. Lett. 75, 1126 (1995).
- [4] S. Satpathy, Z. S. Popovic, and F. R. Vuka jovic, Phys. Rev. Lett. 76, 960 (1996); Z. Popovic and S. Satpathy, Phys. Rev. Lett. 84, 1603 (2000).
- [5] W.E.Pickett and D.J.Singh, Phys. Rev. 53, 1146 (1996).
- [6] I.V. Solovyev, N. Hamada, and K. Terakura, Phys. Rev. B 53, 7158 (1996); I. Solovyev, N.
 Hamada, and K. Terakura, Phys. Rev. Lett. 76, 4825 (1996); I.V. Solovyev, A. I. Liechtenstein, and K. Terakura, Phys. Rev. Lett. 80, 5758 (1998).
- [7] T. Saitoh, A.E. Boucquet, T.M izokawa, H.Nam atame, A.Fujimori, M.Abbate, Y.Takeda, and M. Takano, Phys. Rev. B 51, 13942 (1995); T. Saitoh, T.M izokawa, A.Fujimori, M. Abbate, Y.Takeda, and M.Takano, Phys. Rev. B 55, 4257 (1997).
- [8] A.Abragam and B.Bleaney, Electron Paramagnetic Resonance of Transition Ions (Clarendon, Oxford) 1970.
- [9] R. J. Radwanski and Z. Ropka, Quantum Atomistic Solid-State Theory; http://xxx.lanl.gov/abs/cond-mat/0010081.
- [10] R.J.Radwanski, R.M ichalski, and Z.Ropka, Acta Phys. Pol. B 31, 3079 (2000).
- [11] C.J.Ballhausen, Ligand Field Theory (M oG raw -H ill C om p.) 1962.
- [12] W . Low, Param agnetic resonance in solids (A cadem ic) 1960.
- [13] R. J. Radwanski and Z. Ropka, Solid State Commun. 112, 621 (1999); http://xxx.lanlgov/abs/cond-mat/9906437.
- [14] Z. Ropka and R. J. Radwanski, Physica B 312& 313, 777 (2002).
- [15] R.J.Radwanski and Z.Ropka, http://xxx.lanlgov/abs/cond-mat/0010032.

- [16] R. J. Radwanski and Z. Ropka, Acta Phys. Pol. A 97, 963 (2000); http://xxx.lanl.gov/abs/cond-m at/0005471.
- [17] W .Johnstone, D.J.Lockwood, and G.M ischler, J.Phys.C 11, 2147 (1978).
- [18] D.J.Lockwood, G.Mischler, and A.Zwick, J.Phys.: Condens. Matter 6, 6515 (1994).
- [19] Z.Ropka, Thesis 2001 (April), University of Mining and Metallurgy, Krakow; http://www.cssphysics.edu.pl.
- [20] The recently found atom ic data, in N IST Atom ic Spectra D atabase in http://physics.nist.gov, yields the average value for the spin-orbit coupling in FeIII (= Fe^{2+}) of -148 K.

Figure caption:

Fig. 1. Description of the d states in FeB r_2 within the band approach obtained within the L (S)DA + U approach of Youn et al. There is a sem i-continuous energy spectrum of the d states spread over 10 eV.

Fig. 2. The neelectronic structure of the highly-correlated 3d electronic system of the Fe^{2+} ion in FeB r_2 . a) the 25-fold degenerated ⁵D term given by H und's rules: S = 2 and L = 2. b) the e lect of the octahedral crystal- eld, c) the combined action of the spin-orbit coupling and the octahedral crystal eld: $B_4 = +200$ K, = -150 K; d) the electronic structure of the Fe^{2+} ion in FeB r_2 ; the trigonal-distortion parameter $B_2^0 = -30$ K produces a spin-like gap of 2.8 m eV; the double degeneracy of the ground state is removed in the magnetically-ordered state below T_N of 14 K.



