DETERMINATION AND CONTROL OF OXYGEN STOICHIOMETRY IN THE CUPRATE $Bi_2Sr_2CuO_{6+\Delta}.$

F. JEAN*^{,§}, D. COLSON[&], G. COLLIN*, N. BLANCHARD^{°,*} and A. FORGET[&]

*LLB, DSM / DRECAM, CEA-Saclay 91191 Gif-sur-Yvette Cedex, France [§]LEMHE, Université Paris-Sud, Bât.415, 91405 Orsay Cedex, France [&]SPEC, DSM / DRECAM, CEA-Saclay 91191 Gif-sur-Yvette Cedex, France °LPS, Université Paris-Sud, Bât.510, 91405 Orsay Cedex, France

The relatively low Tc of Bi₂Sr₂CuO_{6+ Δ} allows to study normal-state down to low temperatures and the non-substituted compound is intrinsically strongly overdoped. Hole concentration can be adjusted trough oxygen excess, but few data exist in the literature about the quantitative control of Δ . The synthesis, achieved in air by solid-state reaction, needs long-time annealing to obtain pure phase with stoichiometric cationic ratios. Thermogravimetric techniques were used to explore oxygen non-stoichiometry. Absolute oxygen content was determined by reduction with hydrogen, while the oxygen exchange was studied between 300°C and 670°C with $10^{-4} \leq Po_2 \leq 1$ atm. Oxygen excess varies between 0.14 and 0.18, with possibly two regimes of oxygen intercalation. These results are compared to Bi-2212.

1. INTRODUCTION

The high-Tc superconducting oxides present oxygen non-stoichiometry, which is closely related to electronic and magnetic properties. Whereas the underdoped region of the phase diagram has been extensively studied, the strongly overdoped regime, currently considered as a conventional Fermi liquid, has been less investigated. However, properties near the suppression of superconductivity are still poorly understood.

The cuprate $Bi_2Sr_2CuO_{6+\Delta}$ (Bi-2201) is an ideal candidate for studying the normal state in this regime. It is intrinsically overdoped, the hole concentration can be adjusted through oxygen excess, and its relatively low critical temperature (Tc_{max} ~20 K) allows studying the normal state properties over a large temperature range.

Recently, our group has reported anomalous spin susceptibility and thermopower in the strongly overdoped Bi-2201^{1,2}. In these experimental studies, relevant conclusions can be drawn if an adapted stoichiometry control is developed³.

In this work, oxygen non-stoichiometry and thermodynamic properties of $Bi_2Sr_2CuO_{6+\Delta}$ are investigated by thermogravimetric techniques on wide range of oxygen partial pressure (1-10⁻⁴ atm), in conditions of thermodynamic equilibrium. An attempt is made to clarify the conditions for excess oxygen uptake in a temperature range compatible with the system stability.

2. EXPERIMENTAL

Polycrystalline Bi₂Sr₂CuO_{6+A} was prepared by solid state reaction in air, starting from a stoichiometric mix of oxides (Bi₂O₃, CuO) and strontium carbonate. Powder diffraction method with CuK α radiation was used to follow the synthesis advancement. Thermogravimetric studies were achieved using three different balances by Setaram (Labsys, B60) and Netzsch (STA449C) with sensibilities from 1 to 1.5 µg, which represent, in composition, much less than 0.001 oxygen per formula unit as our samples were pellets of ~3 g. Reversible oxygen exchange was monitored through temperature between 300°C and 670°C, and atmosphere composition with $10^{-4} \le Po_2 \le 1$ atm. To determine absolute oxygen content, samples of ~0.5 g were reduced into Bi, Cu and SrO under H₂ / Ar flow (10% H₂) at 460°C. It should be noted that initial desorption of adsorbed species (~3 mg of H₂O and CO₂ per gram of Bi-2201) was observed at 700°C under Po₂ = 1 atm for several days at the beginning of every experiment.

3. RESULTS

According to powder x-ray diffraction patterns analysis, pure phase with no significant departure from ideal cationic ratios 2:2:1 was obtained after long-time annealing at $700-730^{\circ}C^{3}$.

Figure 1 shows typical thermogram when Bi-2201 is reduced by hydrogen, where the measured mass loss yields the oxygen excess in the initial state (300°C, Po₂ = 0.1 atm). The experiment was repeated several times and the uncertainty calculated from statistical dispersion, as the confidence interval with a confidence level at 80% : $\Delta = \overline{\Delta} \pm 1.44 \times \sigma / \sqrt{n}$, where $\sigma = [(n \times \Sigma \Delta^2 - (\Sigma \Delta)^2) / (n \times (n-1))]^{1/2}$ and n is the number of experiments. It was found that $\Delta = 0.18 \pm 0.04$ at 300°C in pure O₂, and this value, consistent with other determinations^{4,5}, was taken as a reference for the reversible

oxygen exchange measurements.



FIGURE 1 Reduction of Bi-2201 by H₂. The sample was previously treated at 700°C under $Po_2 = 0.1$ atm to allow H₂O / CO₂ desorption, then equilibrated at 300°C.

The variation of oxygen excess in Bi-2201 with temperature and Po_2 is presented in figure 2. Changes in composition were reproducible within 0.002 oxygen / formula unit.



Isothermal variation of oxygen excess in Bi-2201, plotted at various temperatures.

It appears that oxygen excess in $Bi_2Sr_2CuO_{6+\Delta}$ varies within a small range, between 0.14 and 0.18 extra-oxygen per formula unit. The use of higher temperatures and/or lowest

Po₂ must be considered carefully because of phase decomposition³. Like in Bi-2212⁶, the stoichiometric phase ($\Delta = 0$) is probably out of access, at least by the classical post-synthesis annealing method under atmospheric pressure. Another common feature with the two-layer analogue is the enhancement of oxygen excess dependence on Po₂ when temperature increases^{4,6-8}, associated with a modification of the isotherms shape. Inverted curvatures are observed whether T≤500°C or T>600°C, and a linear behaviour in the intermediate range (~580°C). This is likely to be related to different defect structures depending on the temperature used to adjust oxygen content, and is expected to affect significantly the oxide physical properties.

4. CONCLUSION

Controlling with accuracy the doping level of Bi-2201 through the oxygen excess implies the ability to prepare samples at regular intervals within the non-stoichiometric domain. In this view, systematic thermogravimetric measurements under well defined conditions of temperature and atmosphere composition were achieved. Oxygen excess in $Bi_2Sr_2CuO_{6+\Delta}$ can be adjusted in a reversible way between 0.14 and 0.18 by proper annealing. Our results also show that, as it was seen with Bi-2212, a specific regime of oxygen intercalation takes place in the high-temperature part of the diagram.

REFERENCES

- 1) G. Lebras et al., Anormal spin susceptibility of overdoped $Bi_2Sr_2CuO_{6+\Delta}$, this volume.
- 2) Z. Konstantinovic et al., Thermopower in the overdoped region of cuprates, this volume; Z. Konstantinovic et al., submitted to Phys. Rev. B, Cond-mat/0203515.
- 3) F. Jean et al., to be published.
- 4) Y. Idemoto et al., Physica C 190 (1992) 502.
- 5) D.C. Sinclair et al., Jpn. J. Appl. Phys. 29 (1990) L2002.
- 6) F. Jean et al., Physica C 339 (2000) 269.
- 7) M. Quilitz et al., J. Superconductivity 9 (1996) 121.
- 8) Y. Idemoto et al., Physica C 168 (1990) 167.