T. Im af and F.C. Choub

^aD epartm ent of Physics and A stronom y, M cM aster University, H am ilton, O ntario L8S 4M 1, CANADA

^bCenter for Materials Science and Engineering, M.I.T., Cambridge, MA 02139, U.S.A.

(April 14, 2024)

We have investigated the spin uctuations and their interplay with lattice instabilities in a layered $S = \frac{1}{2}$ quantum spin system TiOCl. Our 47,49 Ti and 35 ClNMR data demonstrate a pseudo spin-gap behavior below T = 135K, followed by successive phase transitions at $T_{c1} = 94K$ and $T_{c2} = 66K$ into the singlet ground state with an unusually large energy gap $E_g = 430K$. The broad distribution of the local electric eld gradient in the interm ediate phase between T_{c1} and T_{c2} suggests unconventional spin and lattice (probably orbital) states with an emerging spin-gap.

76.60.k, 75.10.Jm

The provocative proposal that the mechanism of high tem perature superconductivity in layered cuprates may be related to the exotic properties of low dimensional quantum spin systems, such as the RVB (Resonanting Valence Bond) state [1], has been a major driving force behind the rapid advance of quantum magnetism. Naturally, the initial emphasis was placed on understanding m aterials involving Cu^{2+} ions with the $3d^9$ conguration $(S = \frac{1}{2})$ [2,3]. More recently, $S = \frac{1}{2}$ quantum magnets involving V⁴⁺ [4{6] and T i^{3+} [7{12] ions with $3d^1$ con gurations have been attracting strong attention. Potential interests include the realization of doped m etallic states in 3d¹ M ott insulators, and ultim ately, superconductivity [6]. In addition, the near degeneracy of the t_{2a} -orbitals often gives rise to the orbital and/or charge ordering [13]. In the orbital ordered state, the con guration of the occupied $3d_{xy;yz;zx}$ -orbitals exhibits a long range order. On the other hand, the valence of ions differs site by site in charge ordered states. The additional orbital and charge degrees of freedom make the underlying physics of 3d¹ quantum spin system smore intriguing, yet more complicated. A fascinating example is a mixed valence system NaV205 [5,14] (the average valence of V-ions is +4.5). N aV $_2$ O $_5$ undergoes orbital and charge ordering at $T_c = 34K$, where a large energy gap $E_{\alpha} = 98K$ opens [14{17]. The ratio $2E_{\alpha} = k_B T_C = 6$ is much larger than the BCS value 3.5 expected for conventional spin-Peierls transitions with lattice-dimerization. Intensive theoretical and experimental e orts have been underway to understand the exotic phase transition.

An equally exciting new avenue to investigate $S = \frac{1}{2}$ quantum spin system swith $3d^1$ electrons is the titanates involving T i^{3+} ions. Starting from the metal-insulator transition in $Sr_1 \times La_x T$ io₃ [7], growing e orts are under way in search for a new form of quantum magnetism in titanates: strong orbital uctuations in LaT io₃ [8]; a quasi 1D S = $\frac{1}{2}$ chain system (Na,Li)T iSi₂O₆ [9]; 3D P yrochlore system M gT i₂O₄ [10]; and a quasi-2D layered system T iO C 1 [11,12].

Among these titanates, the TiOCl system has partic-

ularly unique characteristics. First, $Ti^{3+}O^2$ form bilayers separated by Cl bi-layers. The quasi-2D layered structure may be considered a close analogue to those realized in high $\mathrm{T_{c}}$ cuprates. In fact, Beynon and W ilson [11] reported the very little tem perature dependence in uniform susceptibility (T), and discussed the possible realization of a RVB ground state in the M ott-insulator. They also noted that (T) is very sensitive to impurities, and demonstrated that a Sc^{3+} ion (S = 0) substituted into a T i^{3+} site (S = $\frac{1}{2}$) gives rise to a localized spin $S = \frac{1}{2}$, in analogy with creation of a free spin by Zn^{2+} (S = 0) substituted into Cu^{2+} (S = $\frac{1}{2}$) sites in cuprates. Second, in a very recent report, Seidel et al. observed a sharp, nearly isotropic drop of (T) below 100K in defect-free sam ples, signaling the emergence of an energy gap [12]. The drop in (T) is even more pronounced in high quality single crystals. Since (T) above 200K can be tted with a $S = \frac{1}{2}$ Heisenberg chain model with the nearest neighbor exchange interaction J = 660K, Seidelet al. proposed, based on LDA+U calculations, that the e ective dimension of the TiD layers are reduced from 2D to 1D by an orbital order at T i^{3+} sites along the a-or b-axis. The gapped behavior of (T) was attributed to a spin-Peierls transition [12]. Third, but related to the second point, the near degeneracy of the energy levels of di erent 3 d'orbital con gurations without mixed-valence nature m ight m ake T iO C lan idealm odelsystem to investigate spin-Peierls-like transitions with additional orbital degrees of freedom but probably without charge order.

In this Letter, we report the $\,$ rst NMR investigation of T iO C l. W hile the spin-Peierls transition in CuGeO $_3$ (without orbital and charge degrees of freedom) and the exotic order in NaV $_2$ O $_5$ (with orbital and charge degrees of freedom) have seen m any detailed m icroscopic investigations, to the best of our know ledge this is the $\,$ rst successful m icroscopic experiments reported for T iO C l. W e demonstrate that T iO C l reveals a unique spin-gap behavior accompanied by lattice instabilities, and undergoes successive phase transitions at $T_{\rm c1}$ = 94 $\,$ 2K and $T_{\rm c2}$ = 66 $\,$ 2K \cdot Unlike CuGeO $_3$ and NaV $_2$ O $_5$,

the uctuation e ects in TiDCl are so strong above T_{c1} that a pseudo spin-gap manifests itself as high as $T = 135 \quad 10K$. Moreover, our observation of a broad continuum in the NMR lineshape data indicates that the interm ediate phase between T_{c1} and T_{c2} is not a simple, dimerized state in 1D.Below T_{c2} , TiDCl undergoes a

rst order phase transition to a fully gapped state (rather than to the gapless RVB state) with an extraordinarily large energy gap E $_{\rm g}$ = 430 $\,$ 60K . The unusually large energy gap (2E $_{\rm g}$ =k_B $_{\rm C1;c2}$ = 10 $\,$ 15) as well as the presence of the interm ediate state between $T_{\rm c1}$ and $T_{\rm c2}$ suggest that the observed phase transitions are not conventional spin-P eierls transitions, and point towards the signi cance of the roles played by the additional orbital degrees of freedom over the entire tem perature range.

Our TiOCl single crystals were synthesized by standard vapor-transport techniques from TiO_2 and TiC_3 [12]. A large number of very thin, aky single crystals with typical dimensions of 2mm 2mm were assembled on a Macor sample holder. NMR measurements were conducted by applying an external magnetic eld in parallel with the aligned crystal c-axis. Random alignment within the TiO-plane prevented us from conducting measurements along the a- and b-directions. We emphasize that, unlike $^{63;65}$ Cu and 51 V NMR, the sensitivity of 47;49 T i NMR is notoriously low [18]. Very short transverse relaxation times T2 at T isites and the sm all volume of the available crystals made the NMR measurements even more di cult. W e needed to average spin-echo sig-10⁶ scans to obtain a reasonable signal to nals up to noise ratio. In general, NMR signal intensities increase as 1=T in proportion to the Boltzm an factor. However, the exponentially growing spin-lattice relaxation time T1 below T_{c1} slows down the NMR pulse-sequence, hence the m easurem ents at low er tem peratures were equally di cult and time consuming. Despite our intensive e orts, we have been able to nd^{47;49}TiNMR signals only for the central transition from the $I_z = +\frac{1}{2}$ to $\frac{1}{2}$ state. The detection of ³⁵ClNMR signal was som ew hat easier, and we did manage to nd the $I_2 = \frac{3}{2}$ to $\frac{1}{2}$ transitions above T_{c1} [19]. All the nuclear spin-lattice relaxation data were deduced by tting the nuclear spin recovery after an inversion -pulse to the standard rate equations. We con $m = 4 \tan^{47} T i$ (nuclear spin I = 5=2) and 49 Ti (nuclear spin I = 7=2) NMR gives identical 1=T₁. G iven that the magnetic recovery process of nuclearm agnetization M (t) is dominated by di erent term s for 47 Ti (M (t) exp[$15t=T_1$]) and $49Ti(M (t) exp[<math>28t=T_1$]), we conclude that $1=T_1$ is dom instead entirely by magnetic uctuations at all tem peratures. The di erence in the re-

covery characteristic of M (t) also helped us identify the pairs of 47 T i and 49 T i lines below T_{c2}, where the NM R lines split into doublets.

The experimental information on the spin degrees of freedom is summarized in Fig. 1. Quite generally, the 47 ; 49 T inuclear spin-lattice relaxation rate, caused by low

frequency m agnetic uctuations m ay be expressed as [20],

$$\frac{1}{T_{1}} = T \frac{k_{B} \frac{2}{n} X}{\frac{2}{B} - q} f(q) f(q; !_{n}); \qquad (1)$$

where F (q) is the form factor of the electron-nucleus hyper ne couplings, and $^{(0)}(q; !_n)$ is the imaginary part of the dynam ical susceptibility at the observed NMR frequency $!_n$. $1=T_1$ appears to asymptote to a constant value near 300K, $1=T_1$ 1400 sec 1 . This implies that $^{(0)}(q; !_n)$ asymptotes to a Curie law at higher temperatures. This is consistent with the behavior expected for typical S = $\frac{1}{2}$ 1D H eisenberg chains such as Sr₂CuO₃ [21]. However, we caution that $1=T_1$ const: may also be expected for S = $\frac{1}{2}$ 2D H eisenberg model [22]. Certainly (T) of TiO C lalso tsnicely to the 1D H eisenberg chain m odel between 200K and 800K [12], but we recall that N aV₂O₅ turns out to be a 2D spin-charge-orbital hybrid system [23] despite the similarly nice t of (T) to the 1D m odel.

In general, the growth of short-range order enhances low frequency spin uctuations (hence 1=T_1T) with decreasing temperature in the absence of a gap in the spin excitation spectrum. The most striking feature in Fig.1 is that 1=T_1T begins to decrease below T 135K. This implies that low frequency spin uctuations are suppressed below T , by almost two orders of magnitude between 135K and 65K. Interestingly, the observed behavior of 1=T_1T is qualitatively sim ilar to the pseudo-gap phase in underdoped high T_c cuprates. N eedless to say, it does not necessarily in ply that the underlying mechanism is identical.

We can also probe the lattice degrees of freedom by observing the EFG (Electric Field Gradient) re ected on NMR lineshapes. In Fig2, we present the ^{47;49}Ti and ³⁵ClNMR lineshapes for the central transition. We observed a single NMR line for both Ti and Cl down to $T_{c1} = 94$ 2K. For ${}^{35}Cl$, we also managed to detect $\frac{3}{2}$ to $I_z = \frac{1}{2}$ satellite transitions, but again $I_z =$ there was only one kind of signal [19]. These results indicate that there is only one kind of Ti and Cl site in T iO C l w ithin our experim ental resolution, and rule out any potential orbital order con gurations above T_{c1} that would lead to more than one inequivalent sites. Below T_{c1} , both ${}^{47;49}$ Ti and 35 ClNMR central lines begin to broaden, signaling a second order phase transition. We con med that the magnitude of the³⁵C 1NMR line splitting is inversely proportional to the external magnetic

eld. Therefore the line splitting is caused by the secondorder nuclear quadrupole interaction with the EFG.W e also found that the drop of $1=T_1T$ is accelerated below $T_{\rm cl}$. In addition, close inspection of the (T) data reported in [12] reveals a kink at $T_{\rm cl}$, followed by a rapid decrease with tem perature with positive curvatures. These results suggest that a clear gap structure emerges in the spin excitation spectrum at $T_{\rm cl}$, accompanied by a static distortion of the lattice. The NMR lineshape exhibits a broad continuum below $T_{\rm c1}$ down to $T_{\rm c2}$ as summarized in Fig.3(b). The broad continuous distribution of the local EFG environment implies the presence of numerous inequivalent T i and C l sites in the T iO C l lattice. The most plausible scenario is that the emergence of the spin-gap at $T_{\rm c1}$ is accompanied by an orbital-order (possibly incommensurate). That is, the phase transition at $T_{\rm c1}$ is not a simple spin-Peierls transition due to lattice dimerization, even though the well-developed short-rage spin order below 400K and the gapped behavior of (T) below 100K [12] suggest the contrary.

W e found additional evidence for the involvement of the lattice in the phase transition at T_{c1} by $^{35}Clnu$ clear relaxation data $^{35}1=T_1$ as shown in Fig.3 (a). $^{35}1=T_1$ is two orders of magnitude slower than $1=T_1$ at 47;49 T isites. This implies that the magnetic hyper ne coupling of ³⁵Cl nuclear spins with Ti 3d¹ electron spins is at least by an order of magnitude smaller. The qualitatively di erent tem perature dependence between $^{35}1=T_1$ [see F ig 3 (a)] and $1=T_1$ [see F ig 1 (a)] suggests that slow ing of EFG uctuations below T toward the phase transition at T_{c1} causes the cusp of $^{35}1=T_1$ at T_{c1} [24]. Even m ore straightforward evidence is that the ³⁵Clspin-echo decay (transverse T2 relaxation) in Fig.3 (c) and (d) shows typicalm otional narrowing e ects below T tow ards T_{c1} due to lattice softening. The slow lattice dynamics at or below the ³⁵ClNMR frequency (37.6 MHz) transforms the spin echo-decay to Lorentzian-like as T_{c1} is approached. Taken together with the precursive suppression observed for $1=T_1T$ below T in Fig.1(a), we conclude that the drastic softening of the lattice below T drives the observed pseudo spin-gap behavior prior to the actual second-order phase transition at $T_{c1} = 94K$. The high onset tem perature 200K of the gradual decrease of 1=T1 suggests that phonon softening at higher frequency scales begins at much higher tem perature.

At $T_{\rm c2}$, the continuum of the $^{35}{\rm Cl}$ and $^{47;49}{\rm TiNM\,R}$ lineshape suddenly collapses into doublets, whose line positions correspond to the two extrem a observed above T_{c2} . This strongly suggests that the unit cell of Ti-OClhas two and only two inequivalent Ti and Cl sites below T_{c2} [25]. The low-frequency Ti 3d¹ spin uctuations exhibit an activation behavior below T_{c2} , as shown in Fig.1 (b). From the t to an exponential form, $1 = T_1 T$ exp($E_q = k_B T$), we deduce the energy gap $E_{a} = 430$ 60K . These results are consistent with the formation of a singlet ground state at T_{c2} by lattice dimerization. Our results are also consistent with the recent observation of doubling of the unit cell along the b-axis at 66 1K by Y.S. Lee et al. based on xray scattering measurements [26]. On the other hand, there are many experimental signatures which are at odds with conventional second order spin-Peierls transitions. $1=T_1$ [Fig.1], the NMR lineshapes [Fig.2], and 35 1=T₁ [Fig.3(a)] change discontinuously at T_{c2}. 35 Cl

spin-echo decay curve also changes suddenly to a slow Gaussian type at T_{c2} [Fig.3 (d)]. This indicates that the soft vibration of the lattice disappears suddenly below T_{c2}. All these NMR results as well as the discontinuous change in (T) [12] and the x-ray data [26] at T_{c2} indicate that the phase transition at T_{c2} is st order. Furtherm ore, the observed energy gap is unusually large, $2E_{q} = k_{B} T_{c1;c2} = 10$ 15. In the case of conventional, mean-eld spin-Peierls gap, one would expect the ratio to be close to the BCS value, $2E_q = k_B T_c = 3:5$, as observed for CuGeO₃ ($2E_{g}=k_{B}T_{c}=3:3$ [27,28]). The observed ratio in TiOCl is even larger than that for NaV $_2$ O $_5$, $2E_{a} = k_{B} T_{c}$ 6 [14,17]. It is in portant to realize that E_{a} is comparable to the apparent exchange energy J = 660Kestimated by the 1D tof (T) [12]. Such a large magnitude of the energy gap E_q strongly suggests that the spin excitations from the singlet ground state is dressed by other electronic degrees of freedom, most likely of the orbitalorigin.

To sum marize, T iO C l is a rather unique layered S = $\frac{1}{2}$ quantum - material with a pre-existing pseudo spin-gap above T_{c1}, the unconventional interm ediate spin and lattice (probably orbital) states between T_{c1} and T_{c2} , and rst order phase transition into a singlet ground state а with an unusually large energy gap. At rst sight, the strong uctuation e ects evidenced in the pseudo spingap behavior suggest a genuinely 1D nature of the T iOC1 along the a-or b-axis, achieved by an orbital order well. above T_{c1}. We recall that the pre-existing orbital order above T_{c1} m ay reduce the e ective dimensions of the T iO layer from 2D to 1D, as suggested by Seidelet al. based on LDA+U calculations [12]. On the other hand, the additional orbital degrees of freedom along the two orthogonal directions within the 2D T iO -layers m ay cause strong orbital uctuations, which could e ectively suppress the tendency towards a spin-Peierls transition at

nite tem perature. In such a scenario, the manifestation of the pseudo spin-gap above T_{c1} m ay be the consequence of the suppression of the spin-Peierls transition, and the successive phase transitions at T_{c1} and T_{c2} m ay arise from a competition between di erent orbital orders. In addition, if the second nearest-neighbor exchange interaction J_a^0 in the zig-zag chain structure along the a-axis (see Fig.1(c) in [12]) exceeds $0.241J_a$ (where J_a being the nearest-neighbor exchange interaction along the a-axis), a spontaneous spin dimerization along the a-axis m ay be favoured [29] over the unit-cell doubling along the b-axis observed below T_{c2} , introducing frustration. In any case, the unprecedented behavior of T iO C lpoints tow ards the crucial roles played by the orbital degrees of freedom and their uctuations below 200K . Recalling that T iO C l is not a mixed-valence system such as NaV₂O₅, TiOCl may be an ideal model spin-Peierls system with additional orbital degrees of freedom , and we call for futher m icroscopic studies.

We thank PA. Lee, Y.S. Lee, G. Sawatzky, V.

K iryukhin, and B D. G aulin for helpful discussions, and I.A eck for calling our attention to Ref. [29]. The work at M J.T. was supported by NSF DM R 98-08941. FIG.2. NMR lineshapes of the $I_z = +\frac{1}{2}$ to $\frac{1}{2}$ central transition for ${}^{35}Cl$ (left panels) and ${}^{47;49}Ti$ (right panels). The FFT envelope was obtained at 9 Tesla by repeating spin-echo m easurem ents at several frequencies.

- [1] P.W. Anderson, Science 253, 1196 (1987).
- [2] M.Hase et al, Phys.Rev.Lett.70, 3651 (1993).
- [3] M .Azum a et al, Phys. Rev. Lett. 73, 3463 (1994).
- [4] H. Iwase et al., J. Phys. Soc. Jpn. 65, 2397 (1996).
- [5] M . Isobe and Y . U eda, J. Phys. Soc. Jpn. 65,1178 (1996).
- [6] T.Yam auchiet al, Phys. Rev. Lett. 89, 057002 (2002).
- [7] Y. Tokura et al, Phys. Rev. Lett 70, 2126 (1993).
- [8] B.Keimeretal, Phys.Rev.Lett 85, 3946 (2000).
- [9] M. Isobe et al., J. Phys. Soc. Jpn. 71, 1423 (2002).
- [10] M . Loobe and Y . U eda, J. Phys. Soc. Jpn. 71, 1848 (2002).
- [11] R J. Beynon and J. A. W ilson, J. Phys. Cond. M att. 5, 1983 (1993).
- [12] A . Seidelet al, cond-m att/0206374 (To appear in Phys. Rev.B).
- [13] Y. Tokura and N. Nagaosa, Science 288, 462 (2000).
- [14] T.Oham a et al., J. Phys. Soc. Jpn. 66, 545 (1997).
- [15] Y.Fagot-Revurat et al., Phys. Rev. Lett 84, 4176 (2000).
- [16] T.Ohama et al, Phys. Rev. B 59, 3299 (1999).
- [17] T.Yoshiham a et al., J.Phys.Soc.Jpn. 67, 744 (1998).
- [18] The natural abundance of ${}^{47;49}$ Ti is low (7.3% and 5.5%, respectively). The nuclear gyrom agnetic ratio is also rather small (${}^{47;49}$ $_{n}$ =2 = 2:4000 and 2:4005 M H z/Tesla, respectively).
- [19] The 35 Cl quadrupole tensor along the c-axis was determined to be 35 ${}^{c}_{0}$ = 1:641 0:005M H z at 130K.
- [20] T.Moriya, J.Phys.Soc.Jpn.18, 516 (1963).
- [21] M. Takigawa et al, Phys. Rev. Lett 76, 4612 (1996).
- [22] T.Imaietal, Phys.Rev.Lett 70, 1002 (1993).
- [23] B D. Gaulin et al, Phys. Rev. Lett 84, 3446 (2000).
- [24] Strictly speaking, thing the ${}^{35}Cl$ nuclear spin recovery M (t) to a purely magnetic form may not be valid near T_{cl} . However, it is su cient for the present purpose.
- [25] O ur prelim inary attempts to deduce more detailed information on the lattice distortion at $T_{\rm c1}$ and $T_{\rm c2}$ have been unsuccessful, as NMR signals are too weak to detect satellite transitions below $T_{\rm c1}$. We defer further e orts until much larger single crystals become available.
- [26] Y S.Lee et al, private communications.
- [27] J.K kuchiet al, J.Phys.Soc.Jpn.63, 872 (1994).
- [28] L.P.Regnault et al, Phys.Rev.B 53, 5579 (1996).
- [29] F D M . Haldane, Phys. Rev. B 25, 4925 (1982). A lso see S.Eggert, Phys. Rev. B 54, R 9612 (1996).

FIG.1. (a) $1=T_1$ () and $1=T_1T$ () at ${}^{47;49}T$ isites. $1=T_1$ was measured at the center peak for T . T_{c1} . Solid and dashed curves are guides for eyes. (b) The sam e $1=T_1T$ data plotted in a sem i-log scale. Solid line is the best exponential t. $1=T_1T$ was identical for the doublets below T_{c2} .

FIG.3. (a) 35 1=T₁. (b) 35 ClNMR frequencies observed at 9 Tesla. Dashed lines represent continuum. Solid error bars represent the frequency range corresponding to the half-intensity. (c) 35 ClNMR spin-echo decay observed at the m ain peak, as a function of the pulse separation time 2 between 90-180 degree R F.pulses above T_{c1}, and (d) below T_{c1}. Solid curves are quides for eyes.





