On the Generalized Borel Transform and its Application to the Statistical Mechanics of Macromolecules.

Marcelo Marucho and Gustavo A. Carri^{yz}

The Maurice Morton Institute of Polymer Science, The University of Akron, Akron, OH 44325-3909, USA.

Abstract

We present a new integral transform called the Generalized Borel Transform (GBT) and show how to use it to compute some distribution functions used to describe the statistico-mechanical behavior of macromolecules. For this purpose, we choose the Random Flight Model (RFM) of macromolecules and show that the application of the GBT to this model leads to the exact expression of the polymer propagator (two-point correlation function) from which all the statistical properties of the model can be obtained. We also discuss the mathematical simplicity of the GBT and its applicability to polymers with other topologies.

^y To whom any correspondence should be addressed Electronic address: marucho@polymer.uakron.edu

^zElectronic address: carri@polymer.uakron.edu

I. INTRODUCTION

Consider a group of n small molecules connected in a sequential manner such that each small molecule has only two nearest neighbours with whom it forms a chemical bond except for the small molecules at the end of the chain that have only one connected nearest neighbour. This chain is called a polymer. In this particular case, the chain ends do not form a chemical bond thus, the polymer is said to have a linear topology (linear polymer). If the ends were to form a chemical bond, then the polymer is said to be a ring (cyclic) polymer. Another well known topology is the star topology where m linear polymers grow from the same point and they are connected at this point. This defines an m-arm star polymer. Combinations of these three topologies or new topologies define more complex macromolecules.

Another characteristic of polymers is that they can be made of two or more different kinds of small molecules.

We conclude this section by speculating about other possible models for which the GBT might provide some useful insight. But, before we proceed, we should note that extensions of the present calculation to other polymer topologies like rings and stars are straightforward. For example, in the case of rings the cyclic topology of the polymer generates an extra constraint in the polymer propagator of the form

$$\begin{array}{c} X^{n} \\ R_{j} \\ j=1 \end{array}$$
(1)

which can be easily handled by the GBT.

A generalization of Eq. (23) that takes into account more complex systems like copolymers and the effects of external fields has the mathematical expression given by

$$P R;n; p_{j} = dfR_{k}g \qquad p_{j j}(R_{j}) \qquad R_{j} R exp(!(fR_{j}g));$$

$$j=1 = 1 \qquad j=1 \qquad (2)$$

where s is the total number of chemical species forming the copolymer, p_j is the probability of finding the j-th segment in the -th chemical species and ! (fR jg) has the mathematical form

!
$$(fR_{j}g) = {X^n \atop j=1} (R_{j});$$
 (3)

(R) being any function. In particular, the effects of external vectorial ((R) = F R) and quadrupolar ((R) = $Q_{ij}R_iR_j$) fields can be studied exactly. In general, the statistical properties of the model defined by Eq. (2) can be computed exactly using GBT.

In recent years, new experimental tools have been developed to study the behavior of single macromolecules. These tools have given researchers the ability to manipulate polymers individually. Perhaps, the force-elongation measurements done in different biopolymers using Atomic Force Microscopes and Optical Tweezers are the best known examples[14]. This new experimental capability has proved that our most advanced models are still incomplete and cannot describe modern experimental data adequately. One example of this statement is the force-elongation curve of the polyprotein made of the I27 module of human cardiac titin[15]. This curve shows discontinuities that occur when one module of the polyprotein unravels. The data is generally fitted to the WCM. But, this model cannot describe structures like -helices or -sheets present in polyproteins.

The solution of the WCM is mathematically involved and the addition of secondary structure like -helices does not simplify the model. On the contrary, the mathematical complexity of this "extended" WCM is expected to be even more involved. As a consequence of this, we have started to explore new mathematical tools that might lead to alternative approaches to the models of polymers. One tool that has proved to be potentially useful is the Generalized Borel Transform (GBT) which we present in this paper. This technique was borrowed from Quantum Mechanics (QM) and Quantum Field Theories (QFT) where it has been successfully applied to solve different problems such as heavy quark-antiquark interaction in QFT [16] and singular scattering potentials in QM [17]. In addition, this mathematical tool allows one to obtain analytical solutions of parametric integrals like Laplace/Mellin transforms for all range of its parameters. Therefore, it is extremely useful to study nonperturbative regimes. In this paper, we show how to use this computational tool in the field of statistical mechanics of single polymers by computing exactly the polymer propagator of the RFM of linear macromolecules. In the companion paper, we generalize these ideas to the statistical mechanics of linear semiflexible polymer chains, as described by the WCM, and present new results for this model.

The RFM is the simplest attempt to describe the statistical properties of flexible polymer chains. Thus, it is the first model where the GBT should be applied. In this model, polymers are assumed to be made of n segments of length l (=Kuhn length) which are connected in a sequential manner. These segments are free to rotate around any axis as long as the move does not break the polymer chain. Figure 1 depicts the RFM.

This paper is organized as follows. In section II we show how is possible to calculate Fourier sin/cos transforms using the Generalized Borel Transform and we present a brief summary of the mathematical aspects of this technique. Then in section III we solve exactly a particular Fourier sin transform, namely the polymer propagator (normalized distribution function) of the RFM. Finally, in section IV we present the conclusions and discuss some other models in polymer physics where this new application of the GBT might lead to exact solutions.

II. THE GENERALIZED BOREL TRANSFORM

In the previous section we have shown that the Fourier Sine transform plays a very important role in the evaluation of the statistical properties of models for single macromolecules. Therefore, let us start the description of the GBT by writing the general expression of a Fourier Sine transform of a function H (k;a)

Q (R;a) =
$$\sum_{0}^{Z_{1}} \sin (Rk) H (k;a) dk$$
: (4)

Furthermore, consider the Laplace transform of the same function which is given by the definition

$$S(g;a) = \begin{bmatrix} Z_{1} \\ H(x;a) \exp((gx) dx \\ g > 0; \end{bmatrix}$$
 (5)

Then, we observe that we can obtain the Fourier Sine transform, Q (R;a), from the Laplace transform, S (g;a), as the analytic continuation of S (g;a) to the complex plane as follows

$$Q (R;a) = \text{Im fS} (g = iR;a)g:$$
(6)

Consequently, we will focus on the evaluation of Laplace transforms. For this purpose, we will employ the GBT technique described hereafter.

The main goal of the GBT is to obtain analytical solutions of parametric integrals of the Mellin/Laplace type[16, 17, 18] for all the range of values of the parameters. Therefore, this technique is very useful to study non-perturbative regimes. The basic idea of method consists of introducing two auxiliary functions, S (g;a;n) and B (s;a;n)(the Generalized Borel Transform). These functions depend on auxiliary parameters called n and . These parameters have no physical meaning and are introduced for the sole purpose of helping in the computation of an explicit mathematical expression for S (g;a) for all values of the true parameters g and a.

Let us start with the mathematical definition of S (g;a;n) which is the following

$$S (g;a;n) = \int_{0}^{Z_{1}} x^{n} H (x;a) \exp((gx) dx; g > 0$$
 (7)

We have explicitly extracted a factor \mathbf{x}^n from the function to be transformed. This integral is related to the Laplace transform, Eq. (5), by the following relationship

$$S(g;a;n) = ()^{n} \frac{Q^{n}}{Q^{n}} S(g;a);$$
 (8)

which can be inverted to give

$$S (g;a) = ()^{n} dg dg S (g;a;n) + \overset{X^{1}}{\underset{n}{}} c_{p} (a;n) g^{p}: \qquad (9)$$

The finite sum comes from the indefinite integrations. Note that all the coefficients vanish whenever the Laplace transform, Eq. (5), fulfills the following asymptotic condition

$$\lim_{g! \ 1} S (g;a) = 0:$$
(10)

In addition, the expression given by Eq. (9), is valid for any value of the parameter n; in particular for n 1 where the GBT provides an approximate analytical expression for S (g;a;n) as we describe below. Let us define the Generalized Borel Transform of S (g;a;n) as follows

B (s;a;n)
$$\sum_{0}^{Z_{1}} \exp[s=(g)] - \frac{1}{(g)} + 1 = \sum_{0}^{s} \frac{S(g;a;n)}{[(g)]^{2}} \frac{g}{(g)} dg; Re(s) < 0$$
 (11)

where is any real, positive and non-zero number, and is defined as follows 1=
 (exp (g=) 1). Then, B (s;a;n) is an analytic function for real values of s less than
zero. Moreover, the analytic continuation to the other half of the complex plane generates
an analytic function with a cut on the positive real axis.

In order to invert the transform defined by Eq.(11), we note that the change of variables u (g) = 1= $\ln [1 + 1 =]$ transforms the integral, Eq.(11), into a Laplace transform

$$\begin{array}{ccc} & & Z_{1} \\ B & (s;a;n) & & \exp \left[su\right]L & (S;a;n;u) du; & Re(s) < 0 \end{array}$$
(12)

where L (S;a;n;u) depends on S (g;a;n). Consequently, the inverse Laplace transform of Eq.(12) provides a procedure for the evaluation of S (g;a;n) by integrating B (s;a;n) on the imaginary axis or over the discontinuity of B (s;a;n) on the cut. After a change of variables we can write S (g;a;n) as follows

$$S (g;a;n) = 2^{2} (1 \exp(g=)) \exp[G (w;t;g;;a;n)]dwdt: (13)$$

G (w;t;g; ;a;n) is given by the following expression (for more details see Ref. [16])

$$G (w;t;g;;a;n) = s(t)u(g) + t \ln f [(s(t) + x(w))]g + f [s(t) + x(w)] lg \ln (s(t)) s(t) + w + \ln [x(w)^{n} H (x(w))];$$
(14)

where $s(t) = \exp(t)$ and $x(w) = \exp(w)$.

Note that the expression given by Eq. (13) is valid for any non-zero, real and positive value of the parameter :However, the resulting expression for S (g;a;n) does not depend on explicitly. Thus, each value of the parameter defines a particular Borel transform. Consequently, we can choose the value of this parameter in such a way that it allows us to solve Eq. (13).

The dominant contribution to the double integral is obtained using steepest descent[23, 24] in the variables t and w. For this purpose, we first compute the expressions of the saddle point t_o (g;a;n) and w_o (g;a;n) in the limit 1:The results are the following

$$t_{o} (g;a;n) = \ln \frac{x_{o}^{2} (g;a;n)}{f (x_{o} (g;a;n);a;n)} ; w_{o} (g;a;n) = \ln [x_{o} (g;a;n)];$$
(15)

where x_{o} (g;a;n) is the real and positive solution of the implicit equation coming from the extremes of the function G (w;t;g; ;a;n) in the asymptotic limit in . Explicitly, the equation is

$$x_{o}^{2}g^{2} = f(x_{o};a;n) [f(x_{o};a;n) + 1];$$
 (16)

where

$$f(\mathbf{x}_{o};\mathbf{a};\mathbf{n}) = 1 + \mathbf{n} + \mathbf{x}_{o} \frac{d \ln \left[\mathbf{H} \left(\mathbf{x}_{o};\mathbf{a} \right) \right]}{d \mathbf{x}_{o}}$$
(17)

Afterward, we check the positivity condition [25] (the Hessian of G (w;t;g;;a;n) at the saddle point must be positive). Let us call the Hessian D ($x_o;a;n$). Its mathematical expression is

$$D(\mathbf{x}_{o};\mathbf{a};\mathbf{n}) \qquad \mathbf{x} \frac{d\mathbf{f}(\mathbf{x}_{o};\mathbf{a};\mathbf{n})}{d\mathbf{x}_{o}} [\mathbf{I}=2 + \mathbf{f}(\mathbf{x}_{o};\mathbf{a};\mathbf{n})] + \mathbf{f}(\mathbf{x}_{o};\mathbf{a};\mathbf{n}) [\mathbf{I} + \mathbf{f}(\mathbf{x}_{o};\mathbf{a};\mathbf{n})]: \quad (18)$$

Observe that in the range of the parameters where $f(x_0;a;n) = 1$, which is fulfilled when n = 1, we can keep the second order term in the expansion of G (w;t;g; ;a;n) around the saddle point. Then, we can approximate the double integral in Eq. (13) as follows

In the limit ! 1 we obtain the following approximate expression for S (g;a;n)

$$S_{A prox} (g;a;n) = \frac{p}{2 e} \frac{p}{1 e^{1-2}} \frac{p}{p} \frac{f[k_{o};a;n]+1}{D[k_{o};a;n]} [k_{o}]^{n+1} H[k_{o};a] exp[f[k_{o};a;n]]: (20)$$

Note that the expression given by Eq. (20) is valid for functions H (x;a) that fulfill the following general conditions. Firstly, the relationship given by Eq. (16) must be biunivocal. Secondly, D $(x_o;a;n)$ must be positive at x_o . Thirdly, f $(x_o;a;n)$ must be larger than one. In particular, this condition is fulfilled when n 1: These conditions provide the range of values of the parameters where the approximate solution, Eq. (20), is valid.

Finally, we replace the expression given by Eq. (20) into Eq. (9) to obtain an approximate analytical expression for the Laplace transform S (g;a). In particular, in the limit n ! 1, we obtain the following analytical solution for S (g;a)

$$S (g;a) = \lim_{\substack{n \ ! \ 1}} \left(\int_{n}^{n} dg dg S_{A prox} (g;a;n) \right)$$
(21)

One particular case of this result is the one where H (x;a) does not contribute to the saddle point. This is the case when f $(x_o;a;n)$ can be approximated by 1+ n (the derivative of H $(x_o;a)$ is negligible). Then, the saddle point solution is x_o (g;a;n) ' (n + 3=2) = g and the expression of S_{Aprox} (g;a;n) is

$$S_{A prox}$$
 (g;a;n) ' $\frac{(n+1)}{q^{n+1}}H$ [x_o (g;a;n);a] n 1: (22)

Another important property of the expression given by Eq. (21) is that, in the limit n ! 1, the approximate solution, Eq. (20), becomes an exact solution for Eq. (7). Thus, as long as the n indefinite integrals are calculated without approximations, then Eq. (21) is an exact solution for Eq. (5).

In summary, the procedure to use the GBT to compute Fourier Sine transforms is the following. Firstly, one has to solve the implicit equation, Eq. (16), for n 1 to obtain the mathematical expression of \mathbf{x}_{o} (g;a;n). Replacing this expression into Eq. (20) and doing the n indefinite integrals in Eq. (21), we get the exact/approximate expression for S (g;a). Finally, one has to compute the analytic continuation of S (g;a), Eq. (6), to get the exact/approximate solution of the Fourier Sine transform, Eq. (4).

In the next section we apply this technique to solve exactly the statistical mechanics of flexible macromolecules.

III. APPLICATION

Let us start by analyzing the polymer propagator predicted by the Random-Flight Model which is given by

$$P (R;n) = \begin{array}{ccc} Z & Y^{n} & X^{n} & ! \\ d f R_{k} g & (R_{j}) & R_{j} & R_{j} \\ & & & \\ j=1 & & & \\ \end{array}$$
(23)

where R_j is the bond vector between the (j 1)-th and j-th beads, n is the total number of segments per polymer chain, R is the end-to-end vector and (R_j) is given by the formula

$$(R_{j}) = \frac{(R_{j}j \ l)}{4 \ l^{2}}$$
(24)

Using the Fourier representation of the delta function, we obtain

$$P(R;n) = \frac{Z}{(2)^{3}(4 \ 1^{2})^{n}} \frac{d^{3}k \exp(iR \ k)}{dR_{k}g} \frac{Y^{n}}{(R_{j}j)} \exp(iR_{j}k) \exp(iR_{j}k)$$

where the characteristic function, K (k;n;1), is

$$K (k;n;l) = \frac{\sin(k;l)}{k;l}^{n} :$$
(26)

The evaluation of the angular integrals in Eq. (25) is straightforward. After rescaling R and k with the Kuhn length, l, we obtain the final expression for the polymer propagator

$$P(R;n) = \frac{2}{(2)^{2}R} \int_{0}^{Z_{1}} dk \sin(kR) \frac{\sin(k)}{k} k; \qquad (27)$$

where $k = j_k j_{and} R = j_k j$

This integral representation of the polymer propagator is a Fourier Sine transform and can be solve exactly using GBT. Then, our first step consists of expressing the polymer propagator, Eq. (27), in terms of a Laplace Transform. For this purpose we define the function

$$\begin{array}{ccc} & Z_{1} \\ S (b;n) & dw exp (wb) \frac{\sin (w)}{w} & w \end{array}$$
(28)

from where we recover the expression of the polymer propagator, Eq. (27), as the analytic continuation of the function S (b;n) to the complex plane

P (R;n) =
$$\frac{2}{(2)^2 R}$$
 Im fS (b = iR;n)g: (29)

Let us now rewrite Eq. (28) as follows

$$S(b;n) = \frac{e^{n}}{e^{n}} \int_{0}^{Z_{1}} dw \quad w \exp(wb) \exp(c\frac{\sin(w)}{w} \int_{0}^{Z_{1}} dGA(b;c)g_{c=0}; \quad (30)$$

where

$$\begin{array}{ccc} & & Z_{1} \\ \text{GA (b;c)} & & \text{dwwexp (wb)} H (w;c); \\ & & 0 \end{array}$$
(31)

and

H (w;c)
$$\exp c \frac{\sin (w)}{w}$$
: (32)

Then, the integral expressed by Eq. (31) satisfies all the requirements of the GBT technique [17]. Consequently, we evaluate this integral in the following way

$$GA(b;c) = \frac{\lim_{N \to \infty} ()^{N} db dbGA_{N};}{N! 1}$$
(33)

where we have defined

$$GA_{N} (b;c) \qquad \overset{Z_{1}}{\operatorname{dw}} w^{N+1} \exp(wb) H (w;c): \qquad (34)$$

In the asymptotic limit of N $\,!\,$ 1 , the GBT provides an analytical solution for Eq. (34). Following the technique, we first solve the following implicit equation for w_{o} , Eq. (16),

$$N + 1 + w_{\circ} \frac{\theta}{\theta w_{\circ}} \ln \left[\mathbb{H} (w_{\circ}; c) \right] \qquad N + 2 + w_{\circ} \frac{\theta}{\theta w_{\circ}} \ln \left[\mathbb{H} (w_{\circ}; c) \right] = w_{\circ}^{2} b^{2}; \qquad (35)$$

whose asymptotic solution is

$$w_{\circ}' \frac{N+5=2}{b} N 1:$$
 (36)

Replacing this expression for w_{\circ} in the expression provided by the GBT, Eq. (20), we obtain

$$GA_{N}$$
 (b;c) $' \frac{(N+2)}{b^{N+2}}H \frac{N+5=2}{b}$;c N 1: (37)

Furthermore, we replace Eq. (37) into Eq. (33) and the resulting expression into Eq. (30), then we obtain

$$S(b;n) = \frac{\lim_{n \to \infty} \frac{e^n}{e^{C^n}}}{c! 0^{\frac{1}{2}C^n}} \frac{2}{N! 1} \qquad ()^{N} \frac{db}{db} \qquad ()^{N} \frac{db}{db} \frac{db \frac{(N+2)}{b^{N+2}}}{(2m-1)^{\frac{1}{2}}} \frac{N+5=2}{b}; c \stackrel{2}{\geq} (38)$$

We now proceed to exchange the order of the operators, first we evaluate the n-th derivative of the function H with respect to c and, afterward, we take the limit of c! 0. As a result, we obtain

$$S(b;n) = \lim_{N \neq 1} \left(\begin{array}{ccc} 2 & Z \\ 0 & db \\ N \neq 1 \end{array} \right)^{N} \left(\begin{array}{ccc} 0 & Z \\ db \\ b \\ 0 \end{array} \right)^{N+2} \left(\begin{array}{ccc} \frac{1}{2} & \frac{1}{2} \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \\ \frac{N}{2} \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2 \end{array} \right)^{N} \left(\begin{array}{ccc} 1 & 2$$

Next, we solve the N integrations. Using properties of the function sin(x) we can write S (b;n) for any odd number of segments as follows

$$S(b;n) = \frac{1}{2^{n-1}} \begin{pmatrix} 0 & 1 \\ X^2 \\ k = 0 \end{pmatrix} \begin{pmatrix} 0 & 1 \\ n \\ k = 0 \end{pmatrix} \begin{pmatrix} 0 & 1 \\ n \\ k \end{pmatrix} (N;n;k;b);$$
(40)

where

$$M (N;n;k;b) \qquad \lim_{N ! 1} ()^{N} Im \sum_{r=0}^{X^{1}} \frac{(i(n - 2k))^{r} N^{rn}}{r!} db \qquad Z db \sum_{b^{N+2} n+r}^{N+2} (41)$$

We note that the only powers of b in Eq. (41) that fulfill the asymptotic behavior of the function S (b;n), Eq. (10), are those that satisfy the condition r (n 1). Consequently, the N indefinite integrations are exactly doable, the result is

^Z db ^Z db
$$\frac{1}{b^{N+2}n+r} = \frac{(2+r-n)}{(N+2-n+r)b^{2+r-n}}$$
: (42)

Replacing Eq. (42) into Eq. (41) and introducing the dummy variable r = x + n - 1 we can write

$$M (N;n;k;b) Im \frac{1}{b} (i(n 2k))^{n-1} \frac{X^{4}}{x=0} \frac{i(n 2k)}{b} \frac{x}{(x+1)} (x+n)$$

$$\lim_{N \leq i \leq 1} \frac{N^{x-1}}{(N+x+1)} (N+2);$$
(43)

which, after using the asymptotic properties of the Gamma function [19]

$$\lim_{N ! 1} \frac{N^{\times 1} (N + 2)}{(N + x + 1)} = 1;$$
(44)

becomes

$$M (n;k;b) = \frac{1}{b} Im \sum_{x=0}^{X^{1}} (i(n-2k))^{n-1} - \frac{i(n-2k)}{b} - \frac{x+1}{(x+n)}; \quad (45)$$

The sum over x is doable, the result gives the following expression for M (n;k;b)

$$M (n;k;b) = \frac{1}{b} Im (i(n 2k))^{n-1} FD (n;k;b) ;$$
 (46)

where we have defined

FD (n;k;b)
$$\frac{\frac{1}{2} {}_{3}F_{2} {}_{1};1;\frac{1}{2};\frac{n+1}{2};\frac{n}{2};\frac{(n-2k)^{2}}{b^{2}}}{P-(n)} + \frac{i(n-2k)^{3}F_{2} {}_{3}F_{2} {}_{1};1;\frac{3}{2};\frac{n+1}{2};\frac{n+2}{2};\frac{(n-2k)^{2}}{b^{2}}}{(n+1)};$$
(47)

 $_{3}F_{2}$ ([;;];[;];x) is the Generalized Hypergeometric function [20]. From Eq. (46) we can see that the imaginary part affects only the function FD (n;k;b). Thus, we obtain the final expression for S (b;n)

$$S(p;n) = \begin{pmatrix} n & 1 \\ X^2 \\ k = 0 \end{pmatrix} \begin{pmatrix} 0 & 1 \\ n & A \\ k \end{pmatrix} \begin{pmatrix} (n & 2k)^n & 3F_2 \\ b^2 & 2^{n-1} \end{pmatrix} \begin{pmatrix} (n+1)^2 & (n+2k)^2 \\ b^2 & 2^{n-1} \end{pmatrix} (48)$$

The last step to obtain the analytical expression of the polymer propagator consists of inserting Eq. (48) into Eq. (29) and computing the analytic continuation of the resulting expression to the complex plane through the substitution b = iR. After doing these computations, we arrived at the following expression for the polymer propagator

$$P(R;n) = \frac{1}{2^{n-2}R^{3}} \begin{pmatrix} 0 & 1 \\ \frac{1}{X^{2}} & 0 & 1 \\ k^{k+1} & n & k & 2k^{n} & \frac{1}{(n+1)} \\ k & & 1 \end{pmatrix}$$

$$Im_{3}F_{2} = 1;1;\frac{3}{2}; \frac{n+1}{2}; \frac{n+2}{2}; \frac{(n-2k)^{2}}{R^{2}} :$$
(49)

This expression can be simplified even further if we use the well known analytical properties of the Hypergeometric function $_{3}F_{2}(z)[20]$ which is an analytic function for values of $\dot{z}_{j} < 1$ and its continuation to the rest of complex plane generates one cut on the positive real axis starting at Re(z) = 1. This implies that only values of $\frac{(n - 2k)^{2}}{R^{2}} = 1$ will contribute to the imaginary part of $_{3}F_{2}(z)$. Consequently, this condition reduces the number of terms in the k-sum such that the last term of Eq. (49) is $k = \frac{n - R}{2}$.

in the k-sum such that the last term of Eq. (49) is $k = \frac{n R}{2}$. The explicit evaluation of $\text{Im}_{3}F_{2}$ 1;1; $\frac{3}{2}$; $\frac{n+1}{2}$; $\frac{n+2}{2}$; $\frac{(n 2k)^{2}}{R^{2}}$ can be found in Appendix A. The final expression is

Finally, we replace Eq. (50) into Eq.(49) to obtain the exact expression for the polymer propagator

$$P(R;n) = \frac{1}{2^{n+1}R} \frac{\left[\frac{n}{X^{2}}\right]}{k=0} \left(\begin{array}{c} 0 & 1 \\ 0 & n \\ k \end{array} \right)^{k} \left(\begin{array}{c} n \\ n \end{array} \right)$$
 \right)^{k} \left(\begin{array}{c} n \\ n \end{array} \right)^{k} \left(

Equation (51) is valid for odd number of segments but, it is extended to polymers with any number of segments larger than two via analytic continuation.

Therefore, we have obtained the well-known [21, 22] exact analytical expression for the polymer propagator of flexible chains, Eq. (27), with any number of segments, n, and any end-to-end distance, R.

Observe that the result given by Eq. (51) can be used to describe the statistical properties of polymers with other topologies. For example, consider the case of a flexible m-arm star polymer as shown in Fig. . Since the polymer is flexible, then each arm behaves independently from the other ones except for the fact that all of them start at the origin. Thus, the probability of finding the end of the j-th arm in the shell of radius R_j with thickness dR_j centered at the origin is

$$4 \operatorname{R}_{j}^{2} \operatorname{P} (\operatorname{R}_{j}; n_{j}) \operatorname{dR}_{j};$$
(52)

where n_j is the number of segments in the j-th arm. If we consider all the arms, then the probability of finding the end of the first, second, etc. arms in the shells of radii R_1, R_2 , etc. with thicknesses dR_1 , dR_2 , etc. centered at the origin is

(4)^m
$$\sum_{j=1}^{Y^n} R_j^2 P(R_j;n_j) dR_j$$
: (53)

Other probability distributions for star polymers can also be computed easily.

Another example is the case of ring (cyclic) polymers. Figure shows this topology. From this figure and following the steps presented in this paper for linear polymers it can be proved that the probability of finding any pair of segments separated by a distance R should be proportional to the product of two propagators of the form given by Eq. (51)

$$P_{Ring}(R;s;L s) / P(R;s) P(R;n s);$$
 (54)

where n is the total number of segments in the ring and s is the number of segments (along the contour of the polymer chain) between the two chosen segments.

The aformentioned two examples clearly show that the results obtained for linear polymers using the GBT can be used for polymers with other topologies thus, increasing the range of models that are mathematically tractable with the GBT.

IV. CONCLUSIONS

In this paper we have described a new mathematical method called the Generalized Borel Transform and applied it to compute some statistical properties (polymer propagator) of models of flexible polymers. Specifically, we showed how the GBT is constructed and how to use it to compute Mellin/Laplace transforms. Moreover, some mathematical properties were presented. The application of this technique to the statistical mechanics of single flexible polymers led to the exact solution for the polymer propagator of linear polymers. The propagator obtained turned out to be a finite sum of polynomials valid for any end-toend distance, R, and number of segments, n. Furthermore, this result was used to construct distribution functions for two other topologies, rings and stars.

The exact computation of the polymer propagator of the RFM is a straightforward calculation that requires simple mathematics when the GBT is used. This mathematical simplicity of the GBT makes it a potentially very useful computational tool for more complex models of single polymer chains because it does not add any complexity to the physics of the starting model.

Equation (51) together with its extensions to stars and rings, Eqs. (53) and (54), and the discussion presented in the introduction show that the GBT can solve exactly a wide range of models for polymers. However, more advanced models of single polymer chains like the Wormlike Chain Model or helical polymers where the bond vectors are correlated with each other through potential interactions are not exactly soluble with the GBT at present. A generalization of the GBT to multidimensional integrals is required to address these models.

ACKNOWLEDGMENTS

We acknowledge the National Science Foundation, Grant # CHE-0132278 (CAREER), the Ohio Board of Regents Action Fund, Proposal # R566 and The University of Akron for financial support.

Appendix A: EVALUATION OF THE IMAGINARY PART OF THE HYPERGE-OMETRIC FUNCTION

In this appendix, we calculate the expression $\text{Im } f_3F_2$ (z)g. For this purpose, we use the following integral representation of the Hypergeometric function [26]

where B (;) is the Beta function [26].

We now assign the values = $1; = 2; = n \quad 1; q = n \quad 2k; w = b$ to the parameters in Eq. (A1) to obtain

$${}_{3}F_{2} = 1;1;\frac{3}{2}; \frac{n+1}{2};\frac{n+2}{2}; \frac{(n-2k)^{2}}{b^{2}} = \frac{1}{b^{2}(n-2k)^{n}B(2;n-1)}$$
(A2)
$$\times [n-2k-x^{n}]^{2} \times x^{2} + b^{2} + b^{2} dx:$$

This integral representation is valid only for n 2. Therefore, when we take the analytic continuation to the complex plane as before (b = iR), we can express the imaginary part of the Hypergeometric function as follows

$$Im {}_{3}F_{2} 1;1;\frac{3}{2};\frac{n+1}{2};\frac{n+2}{2};\frac{(n+2k)^{2}}{R^{2}} = \frac{R^{2}}{(n-2k)^{n}B(2;n-1)}$$

$$Im {}_{0} x [n-2k-x^{n}]^{2} x^{2} R^{2}^{-1} dx:$$
(A3)

Thus, we need to evaluate

$$L \quad \text{Im} \qquad \begin{array}{c} & X & [n & 2k & x^{n}]^{2} & [x & R]^{1} & [x + R]^{1} & dx \end{array}$$
(A4)

After analyzing the analytical behavior of the integrand, we concluded that we can exchange the operations of integration and imaginary part to obtain

$$L = \sum_{0}^{Z_{n 2k}} x [n 2k x^{n}]^{2} [x + R]^{1} Im [x R]^{1} dx:$$
(A5)

Thus, we have to compute

$$LS = Im \quad \frac{1}{(x R)} ; \qquad (A6)$$

first and, afterward, we have to solve the integral given by Eq. (A5).

The analytical behavior of the function $(\mathbf{x} - \mathbf{R})^1$ is well known. It is an analytic function for $\mathbf{j}\mathbf{x}\mathbf{j} > \mathbf{R}$ but, its analytic continuation to the complex plane generates a cut on the real axis in the range $\mathbf{R} < \mathbf{Re}(\mathbf{x}) < \mathbf{R}$. This cut generates its imaginary part which is

$$Im \quad \frac{1}{(x R)} = (x R): \quad (A7)$$

Thus, replacing the expression given by Eq. (A7) into Eq. (A5) and making the change of variables y = x R, we obtain

$$L = \sum_{R}^{Z_{n 2k R}} F_{k} (y;n;R) (y) dy;$$
(A8)

where

$$F_{k}(y;n;R) (y+R) [n 2k R y] [y+2R]^{1}$$
: (A9)

The result of the integration gives

$$L = \frac{1}{2} \left[n \quad 2k \quad R^{n} \right]^{2} :$$
 (A10)

Finally, we replace Eq. (A10) into Eq. (A3) to obtain the final expression

$$Im_{3}F_{2} = \frac{1}{2} \frac{1}{(n-2k)^{n}} \frac{1}{2} \frac{n+1}{2} \frac{n+2}{2} \frac{(n-2k)^{2}}{R^{2}} \frac{1}{R^{2}} \frac{1}{(n-2k)^{n}} \frac{1$$

- [1] W. Kuhn, Kolloid Z. 68, 2 (1934).
- [2] J. des Cloiseaux and G. Jannink, Polymers in Solution, Their Modeling and Structure (Clarendon Press, Oxford, 1990).
- [3] K. F. Freed, Renormalization Group Theory of Macromolecules (John Wiley & Sons, New York, 1987).
- [4] H. Yamakawa, Modern Theory of Polymer Solutions (Harper & Row, New York, 1971).
- [5] H. Yamakawa, Helical Worm-like Chains in Polymer Solutions (Springer, Berlin, 1997).
- [6] W. L. Mattice and U. W. Suter, Conformational Theory of Large Macromolecules: The Rotational Isomeric State Model in Macromolecular Systems (John Wiley & Sons, Ner York, 1994).
- [7] P. J. Flory, Statistical Mechanics of Chain Molecules (Oxford University Press, New York, 1988).
- [8] H. Fujita, Polymer Solutions (Elsevier, New York, 1990).
- [9] M. Muthukumar and S. F. Edwards, J. Chem. Phys. 76, 2720 (1982).
- [10] W. E. McMullen and K. F. Freed, *Macromolecules* 23, 255 (1990); W. E. McMullen and K. F. Freed, *J. Chem. Phys.* 92,1413 (1990); H. Tang and K. F. Freed, *J. Chem. Phys.* 94, 1572 (1991).
- [11] L. Leiber, Macromolecules 13, 1602 (1980); T. Otha and K. Kawasaki, Macromolecules 19, 2621 (1986); G. H. Fredrickson and E. Helfand, J. Chem. Phys. 87, 697 (1987); J. L. Barrat and G. H. Fredrickson, J. Chem. Phys. 95, 1281 (1991).
- [12] L. Kielhorn and M. Muthukumar, J. Chem. Phys. 107, 5588 (1997); D. Broseta and G. H. Fredrickson, J. Chem. Phys. 93, 2927 (1990).
- [13] S. F. Edwards, Proc. Phys. Soc. 85, 613 (1965), S. F. Edwards, *ibid.* 88, 265 (1966).

- [14] M. G. Poirier et al., Phys. Rev. Lett. 86, 360 (2001); J. F. Leger et at., Phys. Rev. Lett. 83, 1066 (1999); V. Parpura and J. M. Fernandez, Biophys. J. 71, 2356 (1996); M. D. Wang et al., Biophys. J. 72, 1335 (1997); A. D. Mehta, K. A. Pullen and A. Spudich, FEBS Lett. 430, 23 (1998); A. D. Mehta, M. Rief and J. A. Spudich, J. Biol. Chem. 274, 14517 (1999).
- [15] T. E. Fisher, P. E. Marszalek and J. M. Fernandez, Nat. Struct. Biol. 7, 719 (2000); T. E. Fisher et al., Trends Biochem. Sci. 24, 379 (1999); M. Carrion-Vazquez et al., Prog. Biophys. Mol. Biol. 74, 63 (2000).
- [16] L.N.Epele, H. Fanchiotti, C.A. Garcia Canal and M. Marucho, Phys. Lett. B523, 102 (2001).
- [17] L.N.Epele, H. Fanchiotti, C.A. Garcia Canal and M. Marucho, *Phys. Lett.* **B556**, 87 (2003).
- [18] L.N.Epele, H. Fanchiotti, C.A. Garcia Canal and M. Marucho, Nucl. Phys. B583, 454 (2000).
- [19] M. Abramowitz and I. Stegun, Handbook of Mathematical Functions (Dover, New York, 1970).
- [20] H. Bateman, Higher Transcendental Functions (Mc Graw Hill, New York, 1953).
- [21] M. C. Wang and E. Guth, J. Chem. Phys. 20, 1144 (1952).
- [22] C. Hsiung, H. Hsiung and A. Gordus, J. Chem. Phys. 34, 535 (1961).
- [23] Norman Bleistein and Richard Handelsman, Asymptotic expansion of integrals (Dover, New York, 1986).
- [24] E.T. Copson, Asymptotic Expansions (Cambridge University Press, 1965).
- [25] H. Jeffrey and B.S. Jeffrey, Methods of Mathematical Physics (Cambridge University Press, , 1966).
- [26] I.S. Gradshteyn and I.M. Ryzhik, Table of Integrals, Series, and Products (Academic Press, New York, 2000).

List of Figures

- FIG. 1: Linear, ring and 4-arm star topologies for flexible polymers. R indicates the end-toend vector for the linear topology and the relative position of two segments in the case of a ring polymer. R j indicates the position of the end of the j-th arm in the star topology.
- FIG. 2: The Random Flight Model of polymer chains. 1 is the Kuhn length and is the bond angle.



FIG. 1: Linear, ring and 4-arm star topologies for flexible polymers. R indicates the end-to-end vector for the linear topology and the relative position of two segments in the case of a ring polymer. R j indicates the position of the end of the j-th arm in the star topology.



FIG. 2: The Random Flight Model of polymer chains. 1is the Kuhn length and is the bond angle.