

Comment on "Proximity effect in ultra n Pb/Ag multilayers within the Cooper limit"

M.V. Feigel'man

L.D. Landau Institute for Theoretical Physics, Moscow, Russia

The paper [1] is concerned with experimental data on "proximity effect in ultra n Pb/Ag multilayers within the Cooper limit". While the authors do present some new experimental data, their presentation, to my point of view, is seriously deficient in i) adequate analysis of those data, and ii) in proper account of the results obtained previously within the same field of research.

Concerning item i), I have two different points to mention: a) While McMillan's formula for T_c of strong-coupled superconductor (Eq.(2) of [1]) is well-known, as well as the Cooper-limit formula for T_c of S-N bilayer (Eq.(3) of [1]), there is no any reason to believe that combination of both formulae makes any physical sense. Indeed, what are the reasons to use in the McMillan's formula some average electron-phonon coupling λ_{SN} while keeping the same constant Coulomb repulsion constant

known for Pb? The Eq.(3) was derived within the BCS weak-coupling model of superconductivity, and its extension to strong-coupling case needs some additional work at least. The authors argue that "electrons probe the entire sample" - why then the authors assume they can neglect Coulomb repulsion in the Ag layers? Without clear answers to these questions the "fit" used to describe the obtained experimental results will stay extremely speculative. b) The author's idea that bilayers studied can be described as being within "Cooper limit" is based implicitly upon the assumption that resistance of the S-N interface is sufficiently low (it's trivial to see that in the case of low-conductive interface the "Cooper limit" formula is not valid). Theory of $T_c(\lambda)$ dependence for thin S-N bilayer upon S-N interface resistance was presented in e.g. papers [2, 3, 4]. While it is possible that samples studied in [1] do indeed belong to the Cooper limit, this is to be checked carefully.

Now I proceed to the item ii). The authors claim they have shown in this paper and in their previous paper [5] that they called "inverse proximity effect" - i.e. increase of T_c of ultra n S-N bilayers with increase of normal metal thickness d_N . In fact, this effect was for the first time experimentally observed more than 10 years before, in paper [6], and then studied in more details in [7]. The authors of [5] exactly reproduce the idea and experimental approach of [6, 7] for the study of T_c of ultrathin bilayers (just with another choice for normal and superconductive metals), without any reference to those papers. Detailed studies of T_c behavior in multilayers and bilayers can be found, e.g. even in earlier papers [8, 9].

On theoretical side, the authors ignore the existence of

broadly accepted detailed microscopic theory of that the authors called "inverse proximity effect", cf. [10, 11, 12] - not to mention previous papers on the same issue [13, 14]. In particular, in the review paper [12] a detailed analysis of the experiments [6, 7] is presented. None of these papers is even mentioned in [1, 5].

There exists however some that new (at least, in comparison with [6, 7]) element in the experiments reported in [1, 5]: apart from determination of T_c via in-plane resistive measurements, the authors studied tunnelling conductance into the bilayer, thus determining energy gap dependence upon thicknesses of S and N layers. Theoretical results for the energy gap in S-N bilayers are published in e.g. [4] within BCS mean-field model; modification of tunnelling conductance in dirty S-N films due to enhanced Coulomb interaction was discussed in [15]. None of those papers is referred to in [1, 5].

-
- [1] "Proximity effect in ultra n Pb/Ag multilayers within the Cooper limit", O. Bourgeois, A. Frydman and R.C. Dynes, cond-mat/0302251.
 - [2] G. Bergmann, Solid State Comm. 76, 415 (1990).
 - [3] M.G. Khusainov, JETP Lett. 53, 554 (1991).
 - [4] Ya.V. Fominov and M.V. Feigel'man, "Superconductive properties of thin dirty S-N bilayers", Phys. Rev. B 63, 094518 (2001).
 - [5] O. Bourgeois, A. Frydman and R.C. Dynes, Phys. Rev. Lett. 88, 186403 (2002).
 - [6] I.L. Landau, D.L. Shapovalov and I.A. Parshin JETP Lett. 53, 642 (1991).
 - [7] D.L. Shapovalov, JETP Lett, 60, 193 (1994).
 - [8] N.M. Isseret and M.R. Beasley, Phys. Rev. Lett. 63, 672 (1989).
 - [9] E.Yap and G. Bergman, Solid State Comm. 78, 245 (1991).
 - [10] A.M. Finkelstein, JETP Letters 45, 46 (1987).
 - [11] A.M. Finkelstein, "Electron liquid in Disordered Conductors", v.14 of Soviet Sciences Reviews, ed. I.M. Khalatnikov, Harwood Academic Publishers, London (1990).
 - [12] A.M. Finkelstein, Physica B 197, 636 (1994).
 - [13] S. Maekawa and H. Fukuyama, J. Phys. Soc. Jpn. 51, 1380 (1982).
 - [14] H. Takagi and Y. Kuroda, Solid State Comm. 41, 643 (1982).
 - [15] Y. Oreg, P. Browner, B. Simons and A. A. Altland, Phys. Rev. Lett. 82, 1269 (1999).