

Lucarelli et al. reply to Tajima et al.

In their Comment on our paper, [1] Tajima et al. [2] argue that our infrared results on nine single crystals of $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ (LSCO) are not valid because:

i) Ref. [1] reports three peaks, at 30 (for $x = 0.12$), 250, and 500 cm^{-1} ; ii) the $x = 0.05$ sample shows a dip at 470 cm^{-1} due to a transverse optical phonon of the c -axis at 500 cm^{-1} ; therefore, the sample is not a single crystal or it is miscut; iii) the same dip is observed more or less in all samples, except for those with $x = 0.0$ and 0.26; therefore, all samples are bad crystals, are miscut, or the polarizer was not effective; iv) as most samples contain the c -axis, also the peak at 30 cm^{-1} is a spurious feature; v) the previous observations on the same system do not show the peaks we report in Ref. [1].

Details on the samples and experiments will be given in a forthcoming paper. [3] Here, we reply to each of the above points.

i) In all the superconducting crystals investigated in Ref. [1], strong peaks are observed below 150 cm^{-1} , which depend on temperature and doping consistently with a charge stripe scenario (Figs. 2 and 3 of Ref. [1]). The strong conductivity peak at 250 cm^{-1} and the weak peak at 500 cm^{-1} are discussed only for the semiconducting 0.05 sample, in connection with Thomas et al. who observed very similar features in a ux -grown $\text{La}_2\text{SrCuO}_{4+y}$ crystal where the surface is intrinsically antib. [4]

ii) The $x = 0.05$ sample arrived already cut. We verified that it is an excellent single crystal by X-ray measurements at the Walter-Meißner Institut of Garching (Germany). [3]

iii) This is a crucial point, as it questions the peaks below 150 cm^{-1} . We are surprised by this comment. Fig. 1 shows the reflectivity $R(\omega)$ for our $x = 0.12$ sample and for an $x = 0.13$ LSCO crystal from a paper co-authored by one (D. N. B.) of the authors of the Comment. [5] Both samples show a dip at 470 cm^{-1} for electric field orthogonal to the c axis. In Ref. 5, the 0.13 sample is described as follows: "The miscut angle between the polished surface and the c axis was checked by a high precision triple axis X-ray diffractometer and was determined to be less than 0.8° ". Therefore, in no way the presence of the dip at 470 cm^{-1} can be used as evidence for a miscut of the crystal. This feature has been observed, indeed, in ux -grown $\text{La}_2\text{CuO}_{4+y}$, [6] in well-cut (error less than 1°) LSCO [7] and, with minor changes, in many other cuprates where it has been explained in a non-trivial way. [8]

iv) In Fig. 1 one sees also that the low-frequency side of the ab plane $R(\omega)$, where the strong peaks appear, is not affected by the c -axis reflectivity. The same holds for the other samples. [3] Incidentally, in the $x = 0.15$

spectrum, [1] strong far-infrared peaks spring up at low T while the dip at 470 cm^{-1} is very weak at any T .

v) The authors of Ref. [2] support their argument by citing three papers. Two of them report data on thin films, known to be affected by the subtraction of the sub-




FIG. 1: Reflectivity for field orthogonal to the c axis for our sample with $x = 0.12$ at 30 K and for a sample with $x = 0.13$ at 10 K from Ref. [5]. In the latter crystal the miscut was less than 0.8° . A test of $R(\omega)$ along c at 295 K for the same $x = 0.12$ sample is also shown.

strate contribution, the third one reports measurements at grazing incidence. When measuring at quasi-normal incidence single LSCO crystals, anomalous peaks are observed instead, similar to those in Ref. [1]: see, therein, Refs. [16], [21], [22], and a recent preprint as well. [9] Concerning the paper of Dummet al., [10] the remark in Ref. [2] does not report faithfully the note we added to Ref. [1].

In conclusion, the high quality and good orientation of the crystals measured in Ref. [1] is not questioned by the presence of a dip in $R(\omega)$ at 470 cm^{-1} . The latter feature appears both in well-cut crystals grown by the coating-zone method and in ux -grown samples. Our case on a charge-stripe scenario for LSCO is supported by a sound trend of the optical conductivity throughout its phase diagram and fully agrees with the results of Ramann [11] and neutron [12] spectroscopy on samples from the same laboratories.

A. Lucarelli, S. Lupi, M. Ortolani, P. Calvani, P. Maselli, and M. Capizzi

"Coherencia"-INFN and Dipartimento di Fisica, Università di Roma La Sapienza, Roma, Italy.

[1] A. Lucarelli et al. Phys. Rev. Lett. 90, 037002 (2003).

[2] S. Tajima et al., cond-mat 0303493.

- [3] S. Lupi et al, submitted to Phys. Rev. B.
- [4] G. A. Thomas et al, Phys. Rev. B 47, 11369 (1993).
- [5] T. Startseva et al, Phys. Rev. B 59, 7184 (1999).
- [6] M. A. Quijada et al, Phys. Rev. B 52, 15485 (1995).
- [7] M. Shimada et al, Physica C 193, 277 (1992).
- [8] M. Reedyk and T. Timusk, Phys. Rev. Lett. 69, 2705 (1992).
- [9] Y. H. Kim et al, cond-mat 0303010.
- [10] M. Dumm et al, Phys. Rev. Lett. 88, 147003 (2002).
- [11] F. Venturini et al, Phys. Rev. B 66, 060502(R) (2002).
- [12] M. Fujita et al, Phys. Rev. B 65, 64505 (2002).