## Comment on "*c*-axis Josephson tunneling in $d_{x^2-y^2}$ -wave superconductors"

G. B. Arnold<sup>\*</sup>, R. A. Klemm<sup>†</sup>, W. Körner<sup>‡</sup>, K. Scharnberg<sup>‡</sup>

\* Physics Department, University of Notre Dame, Notre Dame, Indiana 46556

<sup>†</sup>Max-Planck-Institut für Physik komplexer Systeme, Nöthnitzer Str. 38, D-01187 Dresden, Germany

<sup>‡</sup>I. Institut für Theoretische Physik, Universität Hamburg, Jungiusstr. 9, D-05535 Hamburg, Germany

Recently, Maki and Haas (MH) presented an expression, Eq. (3), for the critical current  $I_c$  for coherent *c*-axis tunneling across the interface between identical  $d_{x^2-y^2}$ wave superconductors twisted a relative angle  $\alpha$  about the *c*-axis.<sup>1</sup> They implied that Eq. (3) was valid to all orders in the *c*-axis tunneling probability  $t_{\perp}$ , accounting for "the effects of Andreev reflections at the grain boundary".<sup>1</sup> However, they made many qualitative and quantitative errors, which invalidate their conclusions.

The errors are present in their Eq. (3). MH state that this result is obtained "by applying the Ambegaokar-Baratoff formalism", but a derivation is neither given nor cited. The result of Ambegaokar and Baratoff (AB) is based on the tunneling Hamiltonian approximation,<sup>2</sup> valid to lowest order in  $t_{\perp}$ , while the MH result clearly involves higher orders in  $t_{\perp}$ . Therefore, we first take this equation at face value and examine its consequences.

MH assumed a cylindrical, two-dimensional Fermi surface in each superconductor adjacent to the interface, in contrast to the experimental tight-binding Fermi surface of Bi<sub>2</sub>Sr<sub>2</sub>CaCu<sub>2</sub>O<sub>8+ $\delta$ </sub> (Bi2212). In the s-wave limit, the MH Eq. (3) for  $I_c$  is independent of  $t_{\perp}$ , which is clearly unphysical. Even if Eq. (3) were to apply for  $I_c R/e$ , it is wrong, because exact calculations for s-wave superconductors have shown that  $I_c R/e$  for an SIS junction depends upon  $t_{\perp}$ .<sup>3</sup> At low temperature T,  $I_c R/e$  increases from the AB value to twice that value as  $t_{\perp}$  increases from 0 to unity. Only as  $T \rightarrow T_c$  does  $I_c R/e$  become independent of  $t_{\perp}$ .

In addition, the MH result disagrees with an exact calculation of  $I_c$  for tunneling between SIS layered superconductors obtained by Arnold and Klemm (AK),<sup>4</sup> given in their Eq. (18). Comparing the MH Eq. (3) with the AK Eq. (18), we identify many significant differences. The exact AK Eq. (18) contains the phase difference  $\delta\phi$  across the tunnel barrier in the coefficient of each order in  $t_{\perp}$ , and  $I_c$  is optimized for each  $\alpha$  by setting  $\delta\phi = \delta\phi^* < \pi/2$ . Each Andreev reflection should also involve  $\delta\phi$ , but the MH Eq. (3) evidently set  $\delta\phi^* = \pi/2$ . The MH gap  $\Delta_0$  is evidently independent of T. This disagrees with the AB limit. In the d-wave case, as  $t_{\perp} \to 0$ , the MH result also disagrees with the d-wave AB limit.

And reev reflections at the interface could only arise if it were an SNS junction. It would then be much stronger than the intrinsic interplanar couplings in the single crystals, which are generally agreed to be of the SIS type. However, MH neglected altogether the intrinsic tunneling between the junctions in the layered superconducting half-spaces adjacent to the interface.<sup>4</sup> Furthermore, the  $t_{\perp}(\mathbf{k})$  employed by MH in their Eq. (6) is inappropriate for the cylindrical Fermi surface they employed.<sup>1</sup> As shown previously,<sup>4,5</sup> tight-binding Fermi surfaces of layered superconductors such as Bi2212 misoriented relative to each other also introduce a strong  $\alpha$  dependence of  $I_c$ for coherent tunneling, even in the s-wave case, especially with a  $t_{\perp}(\mathbf{k})$  analogous to that used in Eq. (6) of MH.<sup>4</sup>

The  $I_c$ s observed by Li *et al.* are equal to those observed in single crystals,<sup>6</sup> which are not "small", as claimed by MH. Li *et al.* fed the c-axis current into the top of the crystal. We have studied this case theoretically,<sup>8</sup> and find that within a few layers from the current leads, the current becomes uniform over the crystal surface on the scale of the c-axis penetration depth,  $\lambda_c > 100 \mu$ m. However, in the whisker experiment of Takano *et al.*,<sup>7</sup> the current was fed in from the edge, producing current inhomogeneities on the scale of the Josephson penetration depth,  $\approx 2 - 3\mu m.^8$ 

Finally, we note that the  $\alpha$  dependence of  $I_c$  observed in the experiments of Takano *et al.* may have an extrinsic origin, due to systematic variations with  $\alpha$  of the Bi2212-Bi<sub>2</sub>Sr<sub>2</sub>Ca<sub>2</sub>Cu<sub>3</sub>O<sub>10+ $\delta$ </sub> mixture and additional insulating barrier thicknesses near the cross-whisker interface.<sup>9,10</sup>

- <sup>1</sup> K. Maki and S. Haas, Phys. Rev. B **67**, 020510 (2003).
- <sup>2</sup> V. Ambegaokar and A. Baratoff, Phys. Rev. Lett. **10**, 456 (1963); **11**, 104 (1963).
- <sup>3</sup> Gerald B. Arnold, J. Low Temp. Phys. **59**, 143 (1985).
- <sup>4</sup> G. B. Arnold and R. A. Klemm, Phys. Rev. B 62, 661 (2000).
- <sup>5</sup> A. Bille, R. A. Klemm, K. Scharnberg, Phys. Rev. B 64, 174507 (2001).
- <sup>6</sup> Q. Li, Y. N. Tsay, M. Suenaga, R. A. Klemm, G. D. Gu, and N. Koshizuka, Phys. Rev. Lett. 83, 4160 (1999).
- <sup>7</sup> Y. Takano, T. Hatano, A. Fukuyo, A. Ishii, M. Ohmori, S. Arisawa, K. Togano, and M. Tachiki, Phys. Rev. B 65, 140513 (2002).
- <sup>8</sup> W. Körner, Diplomarbeit, Universität Hamburg, (2002).
- $^9$  R. A. Klemm, Phys. Rev. B 67, xxxx (2003), to be published.
- <sup>10</sup> Y. Takano, T. Hatano, A. Fukuyo, M. Ohmori, P. Ahmet, T. Naruke, K. Nakajima, T. Chikyow, K. Ishii, S. Arisawa, K. Togano, and M. Tachiki, Sing. J. Phys. **18**, 67 (2002).