R ung{singlet charge{ordering in 0 -N aV $_{2}$ O $_{5}$

R.T. $C lay^{1,2}$ and S. M azum dar³

¹D epartm ent of Physics and A stronom y, M ississippi State University, M ississippi State, M S 39762-5167 ²ERC Center for Computational Science, M ississippi State University, M ississippi State, M S 39762-9627

³Department of Physics, University of Arizona, Tucson, AZ 85721

(D ated: January 12, 2022)

We show that the proposed zig{zag charge{ordering m odel for 0 {N aV ${}_{2}$ O ${}_{5}$ is incom patible w ith a single transition that induces both charge{ordering and spin gap. We introduce a two{band m odel for 0 {N aV ${}_{2}$ O ${}_{5}$ within which the simultaneous charge{spin order transition is driven principally by electron-phonon interactions. The spin gap is due to the form ation of local dimers, thus explaining the weak m agnetic e ect on this transition.

PACS num bers: 71.30.+ h, 71.45.Lr, 75.10-b

⁰-NaV₂O₅ has attracted considerable attention because of a peculiar insulator{insulator transition at T_c = 34 K with the simultaneous appearance of charge{ ordering (CO) and spin gap (SG)¹. The material consists of V {0 ladders coupled through direct V {V bonds, with the V {O layers separated by layers of Na^+ ions. The average number of d-electrons per V -ion is 1/2. The insulating behavior above T_c is understood if each V {O { V rung containing one d{electron is considered a \site" within a Mott{Hubbard picture. The SG transition to a nonmagnetic insulator¹ was originally explained within a \chain m odel"², which assumes CO into alternate V⁴⁺ and V^{5+} chains at $T > T_c$, and spin {Peierls (SP) transition in the V $^{4+}$ chains at T < T $_{\rm c}$. NM R demonstrations of only one kind of V (ions³ at T > T_c precludes this model. Inequivalent V { ions are, however, found for T T_c.

Subsequently, there have been a num ber of theoretical discussions of the low T state of 0 -N aV $_{2}O_{5}^{4,5,6,7,8,9,10}$, also based on the one{band V {only picture. Several of these recent theories predict the so-called \zig-zag" CO (see Fig. 1)^{4,8}, which is driven by the C oulom b repulsion between electrons occupying neighboring V ions within an extended H ubbard m odel,

$$H = \begin{array}{c} X \\ t_{ij} (d_i^y d_j + d_j^y d_i) & (1) \\ & \begin{pmatrix} < ij > \\ X \\ + U_0 \\ i \end{pmatrix} \begin{pmatrix} n_{i^{\#}}^d n_{i^{\#}}^d + U_1 \\ i \end{pmatrix} \begin{pmatrix} x \\ n_{i^{\#}}^d n_{j^{\#}}^d \end{pmatrix}$$

In the above, d_i^y creates an electron with spin on a V d{orbital, $n_i^d = d_i^y d_i$, $n_i^d = n_{i''}^d + n_{i\#}^d$, and $\langle ij \rangle$ im plies nearest-neighbor V-ions. The hopping integrals t_{ij} will be denoted by t_2 , t_{jj} and t_{ab} for rung, leg and interladder V {V bonds, respectively. For $U_0; U_1 > > j_{ij}j$ the ground state is the zig-zag CO of Fig. 1. The origin of the SG is not clear, and di erent theories have proposed di erent bond distortions that generate the SG ^{4,8,9}.

Experimentally, X-ray di raction studies agree that below T_c there occurs a superlattice with 2a 2b 4c supercell. The period doublings along a and b directions and the quadruplings along the c direction must originate

from lattice displacements. A nom alous X { ray scattering experiments have con med CO, and have also claimed to have detected the $zig{zag CO^{11,12}}$, although other X – ray analysis have suggested that the ordering occurs only on alternate ladders¹³. In portantly, the relationship between the SG and the CO is not obvious from these studies, and there is no consensus on the pattern of bond distortions leading to the SG . M any experim ental investigations have focused on proving that the zig{zag CO is more appropriate than the chain model, an approach that m isses the possibility of a third di erent CO.Optical measurem ents indicate a strong role of phonons in the CO {SG transition¹⁴. M agnetic m easurem ents have shown that (a) the spin gap 2 $_{\rm s}$ is nearly twice that predicted from the BCS relation 2 $_{\rm s} = 3.5 T_{\rm c}^{15}$, and (b) the e ect of magnetic elds on T $_{\rm c}$ is much weaker than that expected for a simple SP transition¹⁶.

There are two objectives of the present Letter. First, combining recent theoretical results for 1/4{ lled band system s^{17,18} and exact diagonalization studies we have performed for nite two{dimensional (2D) clusters we show that Eq. (1) necessarily predicts distinct CO and SG transitions. Second, we present a two {band m odel for 0 { NaV₂O₅ within which a single co-operative CO {SG transition is explained naturally. Speci cally, we show that within the two{band model incorporating both electron{ electron (e(e) and electron (phonon (e(ph) interactions, V {O {V ladder rungs are alternately electron {rich and electron (poor (see Fig. 2). The SG is a direct consequence of the CO, and is due to the form ation of local singlets on the electron {rich rung V {0 {V bonds. We point out that there is no contradiction between this picture and the M ott{Hubbard description of the T > T_c state. Localdim ers, em phasized in several recent theories of correlated electrons^{17,19}, were also discussed in earlier bipolaron theories of Ti and V {oxides²⁰ and provide a new paradigm for SG in 2D systems.

The fundamental problem with Eq. (1) is that CO driven by the spin (independent interaction U_1 should have occurred at higher T where the free energy is dom – inated by high (spin excitations, and the SG transition should have occurred within the CO phase at lower T. This has also been recognized by other investigators^{9,10}.




FIG.1: Schem atics of the proposed zig-zag CO.B lack and white circles correspond to V⁴⁺ and V⁵⁺, respectively. (a) Two ladders, periodic boundary conditions along \hat{a} and \hat{b} . (b) Single ladder with two neighboring chains, open boundary conditions along \hat{a} .

Recent num erical work¹⁸ for the single ladder has show n that for the zig{zag CO to occur, U₁ m ust be greater than a critical value U_{1c} 2j_{ij}j as in one dimension (1D). The magnitude of U_{1c} increases as U₀ decreases from in nity¹⁸, exactly as in 1D¹⁷. This result, taken together with the known result that the ferror agnetic state with total spin S = S_{m ax} is described by the U₀ ! 1 lim it of Eq. (1), in plies that U_{1c} (S = S_{m ax}) < U_{1c} (S = 0). Hence if U₁ > U_{1c} in ⁰ NaV₂O₅, CO should occur at tem peratures com parable to the energy of the ferror magnetic state, while the SG would occur only at lower T where singlet form ation takes place.

An alternate scenario, not considered previously, is that $U_1 < U_{1c}$ in 0 {N aV $_2$ O $_5$ and the CO {SG transition is driven by a co-operative lattice distortion. The SP transition in 1D 1/4{ lled band system s with $U_1 < U_{1c}$, for example, is accompanied by a CO, and has been referred to as a bond { charge density wave¹⁷. There are two ways lattice{driven SG transition and zig{zag CO can occur in 0 {N aV $_{2}$ O $_{5}$: (i) SP transitions involving the zig{zag bonds of single ladders, or (ii) bond distortions that involve the entire multiple { ladder system . We postpone the discussion of (i) until after we have presented the two{bandmodel, when we discuss why this transition is not possible. The co-operative nature of the zig{zag CO and bond distortions in the multiple { ladder system s has been discussed before⁸, albeit from a di erent perspective. First, the di erence in the site occupancies can drive period 4 bond distortions among the interladder bonds4,9. Next, consider nearest neighbor electron hops along the legs of the ladders in Fig. 1. In addition to the direct hops, there occur \indirect hops" between them that involve a V { ion of the neighboring ladder. Since the indirect hops involve either a charge { rich ion or a charge { poor ion of the neighboring ladder, consecutive leg bonds become inequivalent upon CO formation. Similarly, inequivalent leg bonds can drive a dimerization of the intraladder zig{zag bonds in the lattice of Fig. 1 (b)⁸. Note

TABLE I: Exact bond orders for the 16-site lattices in Fig.1. A llentries are for lattice of Fig.1 (a) except the zig-zag bonds labeled with , which are for lattice of Fig.1 (b).

	$S_z = 0$		S _z =4	
Bond	$t_{ab} = :05eV$ n= 0.238	t _{ab} = :1eV n=0.191	t _{ab} = :05eV n= 0.391	t _{ab} = :1eV n=0.368
B _{1;2}	0.0280	0.1425	0.0169	0.0188
B _{2;3}	0.0275	0.1244	0.0472	0.0869
B 3;4	0.0261	0.1187	0.0168	0.0178
B 4;5	0.0275	0.1244	0.0471	0.0869
B _{2;4}	0.1795	0.1893	0.0807	0.1054
B _{4;6}	0.1800	0.1958	0.0780	0.0934
B _{2;12}	0.1731	0.1916	0.0917	0.0921
B 12;6	0.1546	0.0251	0.0849	0.0632

that the coupled CO (bond distortion necessarily implies that these arguments can be reversed, and bond distortions can be considered to drive the CO 17 .

The tendency to bond distortions is measured within electronic models from calculations of the bond $\operatorname{orders}^{17}$, de ned as,

$$B_{i;j} = M_{i}^{y} d_{j} + d_{j}^{y} d_{i} i:$$
 (2)

Di erences in the bond orders corresponding to equivalent bonds indicate spontaneous distortions that would occur for 0^+ e{ph coupling¹⁷. In Fig. 1 we show the nite lattices for which we have done exact diagonalization studies. CO is achieved in our nite cluster calculations by adding a site (energy term $\int_{i}^{d} n_{i}^{d}$ to Eq. (1), where ^d is negative (positive) for the charge { rich (charge { poor) V { ions of Fig. 1, and can originate from e{ph coupling⁹. Our calculations are for²¹ U₀ = 1 { 4 eV, $t_2 = 0.35$ eV, $t_{\rm ii}$ = 0.15 eV and $t_{\rm ab}$ = 0.05 { 0.2 eV , and 0 $~\rm U_1$ $~\rm 0.5$ eV. Since the CO and bond order di erences are driven by the site energies in our calculations, our results are qualitatively the same for both $U_1 = 0$ and $U_1 \in 0$, and we report the results for $U_1 = 0$ only. In Table I we present the results for $U_0 = 3 \text{ eV}$ and $j_i^d j = 0.1 \text{ eV}$ for two values of tab. For both values of tab there occur period 4 bond distortions along the interladder bonds and period 2 distortions of the ladder leg bonds in the S = 0state. In addition there occur period 2 bond distortions along the $zig{zag bonds for the lattice of Fig. 1(b). As$ mentioned above and discussed extensively in reference 17, it is not necessary that the CO drives the lattice distortion. Rather, the bond distortions of Table I can also drive a $zig\{zag CO$.

To investigate one versus two transitions, we have studied total spin $S = S_{m ax} = 4$ and these results are also reported in Table I. It is seen that the tendency to bond distortion is probably even stronger in $S = S_{m ax}$ than in S= 0. Note in particular that the di erence in the charge densities between the charge{rich and the charge{poor

FIG.2: Two-band models for (a) M X chains, (b) single ladder of $^0\{N \ aV \ _2 \ O \ _5$. In (b) the large (sm all) circles correspond to O (V)(ions. O ccupancy by electrons is larger (sm aller) in the black (gray) sm aller circles in both (a) and (b). Singlet form ation occurs on the electron (rich rungs in (b).

(b

sites, n, is larger in the S = S $_{m ax}$ state. We have performed similar calculations also for the case of CO on alternate ladders¹³. Once again, n and the bond distortions are larger in the ferrom agnetic state than in the singlet state. There is therefore no reason for the coupled CO (bond distortion to occur only in the S = 0 state. We therefore conclude that even with nonzero e{ph coupling the zig{zag CO does not explain the observed CO {SG transition in 0 {N aV $_{2}$ O $_{5}$. This is understandable: exactly as there are two chains per ladder, there are two possible zig{zag CO patterns, and there is no fundam ental di erence between the chain and zig{zag m odels, except that a short range U₁ instead of long range M adelung interaction has been invoked to stabilize one zig{zag CO over the other^{4,8}.

We now show that a di erent CO pattern emerges when we include the O² ions. The most natural two{ band model for 0 {N aV $_{2}$ O $_{5}$ is the 2D extension of the H am iltonian that has been successfully used to describe 1D transition m etal{halogen (M {X}) chains²²,

$$H = \begin{pmatrix} X \\ [t_{1,2} + j;i] (d_{1}^{y} p_{j} + h c;) \\ X \\ + \\ (ij); ; \\ X \\ (j_{1}j^{0}); ; \\ X \\ t_{ab} \\ (d_{1}^{y} d_{j} + h c;) + U_{0} \\ (d_{1}^{y} d_$$

In the above, i, j can be both V and O; d_i^y and p_i^y create electrons in V d{orbitals and O p{orbitals, respectively; is the ladder index; hjij⁰i im plies consecutive sites in any direction, and h ⁰i im plies neighboring ladders. The V {O hopping integrals t_1 and t_2 are along the ladder legs and rungs, respectively, and i are the site energies (v = +, o = -); u_i are the displacements of the V or O ions from their equilibrium positions and $j; i = u_i - u_j$, and are the intersite and on-site e{ph coupling constants, and K is the spring constant. For sim plicity we have chosen , and K to be same for leg and rung bonds. The number operator n_i corresponds to both V and O. We have included the on{




FIG. 3: The amplitude of the ladder-leg O (ion distortion versus the H ubbard repulsion for V (ions for electron (phonon coupling constants = 2 =K t₁ = 0:44, = 2 =K t₁ = 0:11 (solid curve) and = 0:28 = 0:07 (dashed curve). Inset shows the behavior for U₀ = 1 eV

site C oulom b interaction only for V.B ecause of the large negative site energy for O, the Hubbard interaction for O {ions makes little di erence in the nal results. We have not explicitly included intersite C oulom b interactions, the e ects of which we discuss later.

W e have calculated self{consistent solutions to the U₀ = 0 lim it of Eq. (2) for both single ladders and coupled multiple{ladder systems, with periodic boundary conditions along a and b directions for systems up to 320 atom s. Typical parameters were $t_1 = 0.9 \text{ eV}$, $t_2 =$ 1.3 eV, and $_{\rm V}$ ($_{\rm O}$) = 2.5 eV ({ 2.5 eV), which were derived from reference 21. Stable solutions for $= 0^+$ correspond to breathing mode distortions of the O { ions shown in Fig. 2(b) for the single ladder, leading to (i) inequivalent charges on the V { ions on consecutive ladder rungs, (ii) shorter V {0 {V bonds on the rungs containing nom inally V⁴⁺ ions, and (iii) period doubling along the b direction. As there are two possible phases between adjacent ladders, period doubling in the a direction is possible as $w \in \mathbb{R}^9$. As indicated in Fig. 2(a), there is a one{to{one correspondence between the distortions in the V {O ladders and the M {X chains²². Each ladder rung is analogous to a single M {site, with internal structure that leads to on {rung bond distortion. There also em erges a strong reason to ignore the SP transition involving the zig{zag bonds within the single ladder (see above). The distortion in Fig. 2(b) corresponds to alternating leg 0 {0 distances and inequivalent V charges; the SP distortion of the intraladder zig{zag V {bonds requires alternating leg V {V distances and nom inally 0¹ and 0^3 anions. The impossibility of obtaining 0^3 prevents this particular distortion. This result is identical to the observation that M {M distances are uniform within the two{band model for M {X $chains^{22}$.

The above two{band $U_0 = 0$ calculation is signicant, as the shorter bonds on the rungs containing the charge{rich V {ions suggest singlet formation. CO and SG therefore occur simultaneously within this model. The $U_0 = 0 \mod del$ is, however, unsuitable for the insulating state observed at $T > T_c$. A correct description of ${}^0{N \operatorname{aV}_2O_5}$ then requires nonzero but sm all U_0 within Eq. (3). Speci cally, U_0 should be large enough that the M ott{Hubbard picture for insulating behavior for $T > T_c$ is qualitatively valid, and sm all enough that the rung{based CO is not precluded. N ote that the repulsion between two electrons on the same rung bond is an e ective Hubbard interaction U_{eff} that is much sm aller than the bare U_0 , while for sm all t_{ab} , the electrony 1D $1/2\{$ led band ladder is insulating for all U_{eff} . For our m odel to be valid there must exist a range of U_0 over which the distortion of Fig. 2 is nonvanishing and its am plitude decreases slow by.

We have calculated the 0 {ion distortion j_{10} j for nonzero U_0 within Eq. (3) for the single ladder with 4 rungs, using the constrained path quantum M onte Carlo technique²³. We retain the leg O { ions, but consider only e ective V {V bonds on the rungs, as the rung oxygens play a weak role in the CO and in uence only the intrarung distortion. For dierent, and K, we calculate the distortion j_{u_0} jat which the energy minimum occurs for each U_0 (see insert, Fig. 3). The overall results for two di erent sets of e{ph coupling constants are shown in Fig. 3. As expected, j_{10} jdepends strongly on and , and also decreases with U0. Signi cantly though, while the decrease in ju_0 j is moderately rapid at sm all U $_0$, the decrease is rather slow for U₀ 2 eV. This behavior is a signature of the persistence of the rung { based CO for realistic U_0 ' 3 4 eV.

A strong test of the rung{based CO model involves dem onstrating the co-operative nature of the CO {SG transition. The calculated n and bond distortions in Table I for the zig{zag CO are larger for $S = S_{m ax}$ than for S = 0. W e have done the sam e one{band calculation also for the rung distortion, for the lattice of Fig. 1 (b), and for isolated 6 and 8 rung ladders. The m odel H am iltonian is again the Hubbard Ham iltonian (Eq. $1 \text{ with } U_1$ = 0) including the site {energy term $\int_{i}^{d} n_{i}^{d}$, but now the $\frac{d}{d}$ are equal for V (ions on the same rung, and alternate in sign for consecutive rungs. The results are identical in all cases, viz., (i) bond orders are larger on rungs with larger charge density in the S = 0 state, and (ii) the CO and bond distortion is absent in S = $S_m ax$. For the same U_0 and $\frac{d}{i}$ as in Table I, for example, n' 0.1 and B ii ' 0.05 in the S = 0 state of the single ladder with 8 rungs, while both n and B $_{\rm ij}$ are ' 0 in the ferrom agnetic state. In contrast to the zig{zag m odel therefore, there occurs a single insulator { insulator transition

4

involving both charge and spin within the rung distortion picture. W hile the zig-zag CO could be obtained in a two-band model with oxygen breathing distortions out ofphase on the ladder \log^8 , this would still give distinct CO and SG transitions.

We now discuss the role of intersite C oulomb interactions, which were ignored in Eq. 3. Intersite V {O C oulomb interactions have a weak e ect on the CO {SG transition, as m ight be expected. We have already argued that the V {V C oulomb interaction is smaller than the critical value necessary to promote the zig{zag CO. On the other hand, the second neighbor V {V interaction, ignored in Eq. 1, strongly destabilizes the zig{zag CO and promotes the rung CO. There exists therefore a wide range of parameters for which the rung{based CO dom inates over the zig{zag CO.

In summary, we have shown that the zig{zag CO is not compatible with a single CO {SG transition in ⁰{ $N aV_2O_5$, and have proposed a two{band model for this system within which a co-operative transition involving both charge and spin is driven by breathing mode vibrations. Strong d-p hybridization exceeding the energy scale of U₀ in V-oxides has been suggested by Z immerm ann et al., based on photoem ission studies²⁴. Interestingly, the bond-order structure proposed in ref. 6 (see Fig. 4) is consistent with rung ordering. Our theory is consistent with the observed strong phonon e ects¹⁴, while local tightly bound singlet dimers would be in agreem ent with the observed weak e ect of magnetic eld on the CO (SG transition¹⁶. Careful reexam inations of the X-ray data are called for. As mentioned already, many of these experiments were carried out to distinguish between the chain and zig{zagCO's, which are the only CO patterns possible within the one{band model. Our results dem onstrate that the tendency to form local dim ers is particularly strong at or near 1/4{ lling of the band^{17,20}. Local dim er form ation provides a new mechanism for SG transitions beyond the more common mechanisms involving SP dimerizations in 1D and spin frustrations, and it has even been suggested that local dim ers m ay be relevant in the context of superconductivity in correlated electron system s^{17,19}. It is highly interesting in this context that (a) in superconducting {N a_{0:33}V₂O₅ there occur crystallographically three dif-

ferent kinds of V (ions, with perhaps one class of V (band 1/4 (lled²⁵, and (b) the same band lling characterizes organic superconductors.

W e thank J.T.G am m el, M.V.M ostovoy, J.L.M usfeldt and A.Painelli for useful discussions. W ork at A rizona was partially supported by the NSF.

- ¹ M. Isobe and Y. Ueda, J. Phys. Soc. Jpn. 65, 1178 (1996).
- ² P.A. Carpy and J.Galy, Acta Cryst. Sect. B 31, 1481 (1975).
- ³ T.Oham a et al, Phys. Rev. B 59, 3299 (1999).
- ⁴ H. Seo and H. Fukuyama, J. Phys. Soc. Jpn. 67, 2602

(1998).

- ⁵ P.Horsch and F.M ack, Eur. Phys. J.B 5, 367 (1998).
- ⁶ T.Chatterjiet al, Solid St.Comm.108,23 (1998).
- 7 C.G ros and R.Valenti, Phys.Rev.Lett. 82, 976 (1999).
- ⁸ M.V.M ostovoy and D.I.K hom skii, Solid St.Comm.113,

159 (2000).

- ⁹ J.R iera and D.Poilblanc, Phys.Rev.B 59, 2667 (1999).
- ¹⁰ P.Thalm eier and P.Fulde, Europhys.Lett. 44, 242 (1998).
- ¹¹ H.Nakao et al, Phys. Rev. Lett. 85, 4349 (2000).
- ¹² S.G renier et al, Phys. Rev. B 65, 180101 (R) (2002).
- ¹³ J.Ludecke et al, Phys. Rev. Lett. 82, 3633 (1999).
- ¹⁴ M.N.Popova et al, Phys.Rev.B 65, 144303 (2002).
- ¹⁵ Y.Fu jiet al., J.Phys. Soc. Jpn. 66, 326 (1997).
- ¹⁶ P.Fertey et al, Phys. Rev. B 57, 13698 (1998).
- ¹⁷ R.T.Clay, S.M azum dar, and D.K.Cam pbell, Phys.Rev. B 67, 115121 (2003).
- ¹⁸ M.Vojta, A.Hubsch, and R.M.Noack, Phys.Rev.B 63, 045105 (2001).

- ¹⁹ S.Sachdev (2003), cond-m at/0211005.
- ²⁰ B.K.Chakraverty, M.J.Sienko, and J.Bonnerot, Phys. Rev.B 17, 3781 (1978).
- ²¹ H.Smolinskiet al, Phys. Rev. Lett. 80, 5164 (1998).
- ²² S.M.Weber-Milbrodtetal, Phys.Rev.B 45, 6435 (1992).
- ²³ S. Zhang, J. Carlson, and J. E. Gubernatis, Phys. Rev. Lett. 74, 3652 (1995).
- ²⁴ R.Zim m erm ann et al., J.Phys: Condens.M atter 10, 5697 (1998).
- ²⁵ T.Yam auchi, Y.Ueda, and N.Mori, Phys. Rev. Lett. 89, 057002 (2002).