Stabilized jellium model and structural relaxation e ects on the fragmentation energies of ionized silver clusters

M.Payami

M arch 22, 2024

Center for Theoretical Physics and M athem atics, A tom ic Energy O rganization of Iran, P.O.Box 11365-8486, Tehran, Iran

Abstract

Using the stabilized jellium model in two schemes of 'velaxed' and 'rigid', we have calculated the dissociation energies and the ssion barrier heights for the binary fragm entations of singly-ionized and doubly-ionized A g clusters. In the calculations, we have assumed spherical geometries for the clusters. C om parison of the fragm entation energies in the two schemes show di erences which are signi cant in some cases. This result reveals the advantages of the relaxed SJM over the rigid SJM in dynamical processes such as fragm entation. C om paring the relaxed SJM results and axperimental data on fragm entation energies, it is possible to predict the sizes of the clusters just before their fragm entations.

1 Introduction

M etalclusters are one of the building blocks of the nano-structured system s. The stability of these system s is of great in portance in nano-technology. One of the mechanism s which can destroy the stability of metalclusters is charging. These system shave been extensively studied [1] in the context of jellium model (JM). In the JM, the discrete ions are replaced by a uniform positive charge background of density $n^{B} = 3=4$ $(r_{s}^{B})^{3}$ in which r_{s}^{B} is the bulk value of the W igner-Seitz (W S) radius of the valence electrons in the metal. A more realistic version of the JM, the stabilized jellium model (SJM), which was introduced

[2] by Perdew et. al. in 1990, has improved some drawbacks of the JM. The SJM calculations for the fragmentation processes of metal clusters reported so far [3], were based on the assumption that the density parameter r_s takes its bulk value r_s^B , which we call 'rigid' SJM. However, since the surface e ects have large contributions in the energetics and sizes of sm all clusters, a more sophisticated use[4] of the SJM is needed to predict the correct energetics of the clusters in the study of the fragmentation processes. This method, 'relaxed' SJM, has already been used to predict the equilibrium sizes and energies of neutral as well as the charged [5] metal clusters (This method is also called self-compression method). In contrast to the JM and the rigid SJM in which the r_s value is borrowed from the bulk system, in the relaxed SJM, the density parameter of the jellium sphere assumes a value such that a cluster with a given number of electrons and speci c electronic con guration achieves its equilibrium state. C om paring the relaxed SJM results with the rigid SJM results on the one hand, and the experiment on the other hand, provide information on the possible structural relaxations of the clusters in the fragmentation processes.

In this work, we have studied the binary decay processes of positively charged silver clusters Ag_N^Z (Z = 1, 2) containing up to 100 atom s, in all possible channels, using the relaxed and the rigid SJM s. The possible decay channels for singly-ionized Ag clusters are

$$Ag_{N}^{1+} ! Ag_{Np}^{1+} + Ag_{p}^{0}; p = 1;2; ;N 2:$$
 (1)

For doubly charged clusters, the decays can proceed via two di erent processes. The rst one is the evaporation process

$$Ag_{N}^{2^{+}} ! Ag_{N p}^{2^{+}} + Ag_{p}^{0}; p = 1;2; ;N 3;$$
 (2)

in which one of the products is neutral; and the second one is ssion into two charged products

$$Ag_N^{2^+} ! Ag_N^{1^+} + Ag_p^{1^+}; p = 2;3; ; N = 2]:$$
 (3)

In the evaporation processes, the negativity of the di erence between total energies before and after fragm entation in a speci c channel,

$$D^{Z}(N;p) = E^{Z}(N p) + E^{0}(p) E^{Z}(N);$$
(4)

is su cient for the decay in that channel to take place. In the above equation, E^Z (N) and E⁰ (N) are the total energies of Z -ply ionized and neutral N -atom clusters, respectively. However, in ssion processes a negative value for the di erence energy is not a su cient

condition for the decay of the parent cluster. This is because the competition between the short-range surface tension and the long-range repulsive C oulom b force m ay give rise to a ssion barrier. The height of the ssion barriers are calculated using the two-spheres approximation [6]. The situation in a ssion process is shown in Fig. 1. In gure 1, the ssion of a Z -ply charged N -atom cluster into two clusters of respective sizes N₁, N₂ = N N₁ and respective charges Z₁, Z₂ = Z Z₁ is schematically shown. Q_f is the energy release, B_c is the fusion barrier which is the maximum energy of the C oulom b interaction of two positively-charged conducting spheres, taking their polarizabilities into account. B_f is the ssion barrier height which is de ned as

$$B_f = Q_f + B_c:$$
(5)

The coulomb interaction energy, E_c , as a function of their separations, d, for two charged m etal spheres can be num erically calculated using the classical m ethod of in age charges [6]. Our calculations show that the maximum of the interaction energy, B_c , is achieved for a separation $d_0 = R_1 + R_2$. The equality applies for equal cluster radii and charges. The electrostatic interaction energies of pairs of equally charged ($Z_1 = Z_2 = 1$) clusters as functions of the pair separation are shown in Fig. 2 for di erent pair sizes. The radii of the clusters in this gure are calculated from $R = N^{1=3}r_s^B$. In Fig. 3, the values of the C oulom b barrier, B_c are plotted for di erent pair sizes but equal charges $Z_1 = Z_2 = 1$ in the rigid SJM . As is seen, when both of the cluster sizes are small, the barrier is higher than the case when at least one of them is larger.

The most favored decay channel in evaporation processes is de ned as the channel for which the dissociation energy attains its minimum value

$$D^{Z}(N;p) = m \operatorname{in}^{n} D^{Z}(N;p)^{\circ}; \qquad (6)$$

and the most favored decay channel in ssion processes is de ned as the channel for which the ssion-barrier height attains its minimum value

$$B_{f}(N;p) = \min f B_{f}(N;p) g:$$
(7)

2 Total energies of clusters

The total energy of an N -electron Z -ply charged cluster is obtained by solution of the selfconsistent K ohn-Sham (K S) equations [7] in the density functional[8] theory (D F T) with local spin density approximation (LSD A) for the exchange-correlation energy functional. The SJM energy for a cluster in the LSD A is given by [5]

$$E_{SJM} [n_{*}; n_{*}; n_{+}] = E_{JM} [n_{*}; n_{*}; n_{+}] + "_{M} (r_{s}) + w_{R} (r_{s}; r_{c}^{B}) dr n_{+} (r)$$

$$+ h v_{W} (r_{s}; r_{c}^{B}) dr (r) [n (r) n_{+} (r)]; \qquad (8)$$

where

$$E_{JM} [n_{*}; n_{*}; n_{*}] = T_{s} [n_{*}; n_{*}] + E_{xc} [n_{*}; n_{*}] + \frac{1}{2}^{Z} dr ([n; n_{+}]; r) [n (r) n_{+} (r)]$$
(9)

and

$$([n;n_{+}];r) = \frac{Z}{dr^{0}} \frac{[n(r^{0}) - n_{+}(r^{0})]}{jr - r^{0}j};$$
(10)

Here, $n = n_{*} + n_{\#}$ which satis es R^{R} drn (r) = N Z, and n_{+} is the jellium density which satis es $drn_{+}(r) = N$. (r) takes the value of unity inside the jellium background and zero, outside. The rst and second terms in the right hand side of Eq. (9) are the non-interacting kinetic energy and the exchange-correlation energy, and the last term is the C oulom b interaction energy of the system . T_{M} is the average M adelung energy. All equations throughout this paper are expressed in atom ic units ($h = e^{2} = m = 1$, the units of length and energy are bohr and hartree, respectively). The quantity h $v_{M_{N}S}$ is the average of the di erence potential over the W igner-Seitz cell and the di erence potential, v, is de ned as the di erence between the pseudo-potential of a lattice of ions and the electrostatic potential of the jellium positive background [2].

The SJM ground-state energy [Eq. (8)] for a cluster with N electrons is a function of N, r_s , and r_c^B . In the rigid SJM, r_s takes the bulk value r_s^B , whereas in the relaxed SJM, it takes the equilibrium value, r_s (N), which for a cluster in the ground state electronic con guration, is obtained by the solution of the equation

$$\frac{\partial}{\partial r_{s}} E_{SJM} \left(N ; r_{s} ; r_{c}^{B} \right) ; \qquad (11)$$

where, the derivative is taken at xed values of N and r_c^B . The total energies of the cluster in the relaxed SJM and the rigid SJM are given by $E_{SJM} = E_{SJM} (N; r_s (N); r_c^B)$ and $E_{SJM} (N; r_s^B; r_c^B)$, respectively.

3 Results and discussion

To obtain the relaxed SJM properties, we have perform ed an extensive self-consistent solutions of the KS equations along with Eqs. (8)-(11), and have calculated the equilibrium r_s and the energy values of A q_N^Z clusters (Z = 0;1;2) for di erent cluster sizes (N 100). To show the main di erences in the equilibrium r_s values of these clusters, which are appreciable for small clusters, we have plotted in Fig. 4 the corresponding values only up to N = 34. As is obviously seen in the gure, the neutral and singly-ionized clusters are self-com pressed for all values of N . However, for doubly-ionized clusters, the values cross the bulk border (i.e., $r_s^B = 3.02$) at N = 7.

Figure 5 shows the relaxed SJM energies per atom in electron volts for neutral, singlyionized, and doubly-ionized silver clusters with N 34. For comparison, we have also plotted the bulk value (" = 7:89 eV) by a dashed line. U sing these values of equilibrium energies and sizes, the relaxed SJM fragmentation energies are calculated by the Eqs. (5)-(7).

In Fig. 6, we have plotted the dissociation energies of the most favored evaporation channels of the singly ionized clusters. We have shown the most favored value of p by p. The solid small square symbols show the most favored values p on the right vertical axis whereas, the corresponding dissociation energies, D¹⁺ (N; p), are shown on the left vertical axis by large open squares. As is seen in the gure, there exist some maxim a and minim a. The maxim a of the D^Z (N; p) correspond to the closed-shell A g_N^+ clusters with N = 3, 9, 19, 35, 59,:::. These clusters have high stabilities compared to their neighboring sizes. On the other hand, the minim a correspond to the sizes which decay into two closed-shell clusters (for example, A g_{11}^+ ! A g_9^+ + A g_2). A negative value for the dissociation energy in plies that the cluster is unstable against the spontaneous decay.

In Fig. 7(a), we have shown the most favored products Ag_p^0 and the dissociation energies D^{2+} (N;p) for the decay of Ag_N^{2+} via evaporation channel. It is seen that, here, the mean dissociation energy is higher than that in the evaporation of singly ionized clusters. That is, here, the number of clusters stable against the spontaneous evaporation is larger than that in the singly ionized case. However, evaporation is not the only decay mechanism for multiply charged clusters, and they can also decay via ssion processes in which both fragments are charged.

Figure 7 (b) shows the barrier heights $B_f(N;p)$ for the most favored ssion channels Ag_N^{2+} ! $Ag_N^+ _p + Ag_p^+$. Here, in the relaxed SJM, the Coulomb barriers are calculated using the equilibrium sizes of each Z-ply charged fragments i.e., $R^Z(N) = N^{1-3}r_s^Z(N)$. As is seen, for small clusters, the majority have negative barrier heights. That is, most of them are unstable against spontaneous ssion. However, as N increases, the number of clusters with negative barrier heights decreases and beyond a certain size range, all the

barrier heights become positive. As before, the fragment sizes p are shown in the left vertical axis.

As mentioned before, a doubly charged cluster can decay both via evaporation and ssion. To estimate at what sizes which decay mechanism is dominant, we have compared the dissociation energies and the ssion barrier heights in Fig. 7 (c). At small sizes (N < 21), the ssion process dominates because, the barrier heights for the ssion are lower than the dissociation energies for the evaporation. However, the competition between the evaporation and ssion starts at N = 21. This competition continues with some uctuations until the evaporation dominates completely. Ag clusters of sizes 1 nm and

2 nm contain 40 and 300 atom s, respectively. Knowing the fact that, in doubly ionized clusters, the induced evaporation is most favored for N > 21, we conclude that the ionized clusters of nano-meter size undergo the fragmentation mostly via the evaporation processes.

The rigid SJM fragmentation energies have been calculated by the self-consistent solutions of the KS equations for the system with the positive background density parameter of r_s^B . In Figs. 8(a)-(c), the corresponding fragmentation energies of the relaxed and the rigid SJM are compared. As is seen, in some cases the energy difference is as large as 0.5 eV, indicating the significant elect of relaxation.

In provem ents over our relaxed SJM results can be obtained by assuming that, at the instant the fragm entation takes place, the the parent and the products are not at their individual equilibrium state but that, the r_s values of the products are equal to that of the parent at that instant. Thus, in the equations used for the dissociation energies and the ssion barrier heights this fact must be taken into account. The r_s value of the parent cluster at the fragm entation instant (i.e., at the instant the two pieces are created) is something which is between that of the neutral cluster with the same N and that of the relaxed Z-ply charged of the same N. That is, $r_s^0(N) = r_s = r_s^{2+}(N)$ for the ssion of a doubly charged N-atom cluster. The reason for this fact lies in the probabilistic nature of the energy absorption in the ionization process of the neutral cluster as well as the energy absorption in the fragmentation process of the Z-ply charged parent cluster. If the fragmentation energy is absorbed as soon as the electrons are detached from the neutral cluster, then the parent charged cluster does not have enough time for structural relaxation due to its charging. Therefore, the appropriate r_s value would be that of the neutral cluster. On the other hand, if the absorption of the fragm entation energy takes place with enough delay relative to the ionization instant, then the parent charged cluster has a chance to arrive at its relaxed r_s value. These arguments lead us to conclude that the experim ental fragm entation energies are highly dependent on the details of the experimental setup. This freedom in taking the r_s values of the clusters in a dynamical process such as fragm entation shows the advantages of the relaxed SJM over the rigid

one. However, in cases where the relaxed and the rigid r_s values are more or less the same, one would expect that applying the time-saving rigid SJM would lead to the same estimates of the fragmentation energies.

4 Summary and conclusions

In this work, we have calculated the dissociation energies and the ssion barrier heights of the fragmentations of singly and doubly ionized silver clusters in the two schemes of relaxed and rigid SJM s for dierent cluster sizes, N 100. In our calculations, we have assumed spherical geometries for the clusters. In the rigid SJM, the density of the positive charge background is taken to be that of the bulk system, n^{B} . However, in the relaxed SJM, that density is obtained in a self-consistent way which corresponds to the equilibrium state of the cluster. The ssion barrier heights are calculated using the two-spheres approximation and for the Coulomb interaction of the two metallic spheres we have employed the method of im age charges numerically. The dierences in the results of the two schemes show the advantages of the relaxed SJM over the rigid one in that, one is able to take into account the structural relaxations in dynam ical processes such as fragmentations.

References

- [1] M. Brack, Rev. Mod. Phys. 65, 677 (1993), and references therein.
- [2] J.P.Perdew, H.Q.Tran, and E.D.Sm ith, Phys. Rev. B 42, 11627 (1990).
- [3] A.Vieira and C.Fiolhais, Phys. Rev. B 57, 7352 (1998).
- [4] J.P.Perdew, M.Brajczewska, and C.Fiolhais, Solid State Commun. 88, 795 (1993).
- [5] M. Payam i, J. Phys.: Condens. M atter 13, 4129 (2001).
- [6] U.Naher, S.Bjmholm, S.Frauendorf, F.Garcias, and C.Guet, Phys. Rep. 285, 245 (1997) and references therein.
- [7] W .Kohn and L.J.Sham, Phys. Rev. 140, A 1133 (1965).
- [8] P.Hohenberg and W.Kohn, Phys. Rev. B 136, 864 (1964).

Figure 1: Fission barrier in the two-spheres approximation. The parent N -atom Z -ply charged cluster decays into two clusters of sizes N_1 and N_1 , with charges Z_1 and Z_2 , respectively.

Figure 2: Coulomb energy in electron volts of two singly charged metallic spheres as a function of their separation distance.

Figure 3: Coulom b barrier heights in electron volts for two singly charged m etallic spheres with di erent sizes.

Figure 4: Equilibrium r_s values in atom ic units for neutral, singly ionized, and doubly ionized silver clusters. The horizontal dashed-line shows the bulk value for silver, 3.02.

Figure 5: Equilibrium energies in electron volts of neutral, singly ionized, and doubly ionized silver clusters. The horizontal dashed-line shows the bulk value for silver, -7.89 eV.

Figure 6: D issociation energies, in electron volts, of the most favored decay channels of singly ionized clusters, in relaxed SJM, are shown with respect to the left vertical axis. The right vertical axis shows the sizes of the fragments in the most favored channels.

Figure 7: Relaxed SJM results for doubly ionized silver clusters. a) - the same quantities as in Fig.6 for doubly ionized clusters; b) - the ssion barrier height in electron volts for the most favored ssion channel as a function of the cluster size. The right vertical axis shows the most favored product sizes of the neutral clusters; c) - com parison of the decay energies of via evaporation and ssion mechanism s. C om petition starts at N = 21

Figure 8: C om parison of the most favored channel fragmentation energies, in electron volts, for the two schemes of the relaxed and rigid SJM s. a)-dissociation energies of singly ionized clusters; b)-dissociation energies of doubly ionized clusters; c)- ssion barrier heights for the ssion of doubly ionized clusters into two singly ionized clusters.

This figure "fig1.jpg" is available in "jpg" format from:

This figure "fig2.jpg" is available in "jpg" format from:

This figure "fig3.jpg" is available in "jpg" format from:

This figure "fig4.jpg" is available in "jpg" format from:

This figure "fig5.jpg" is available in "jpg" format from:

This figure "fig6.jpg" is available in "jpg" format from:

This figure "fig7a.jpg" is available in "jpg" format from:

This figure "fig7b.jpg" is available in "jpg" format from:

This figure "fig7c.jpg" is available in "jpg" format from:

This figure "fig8a.jpg" is available in "jpg" format from:

This figure "fig8b.jpg" is available in "jpg" format from:

This figure "fig8c.jpg" is available in "jpg" format from: