

Estimation of vortex density after superconducting film quench

T.W.B. Kibble

*Blackett Laboratory, Imperial College London,
London SW7 2AZ, United Kingdom*

A. Rajantie

*DAMTP, CMS, University of Cambridge, Wilberforce Road,
Cambridge CB3 0WA, United Kingdom*

(Dated: 25 June, 2003)

This paper addresses the problem of vortex formation during a rapid quench in a superconducting film. It builds on previous work showing that in a local gauge theory there are two distinct mechanisms of defect formation, based on fluctuations of the scalar and gauge fields, respectively. We show how vortex formation in a thin film differs from the fully two-dimensional case, on which most theoretical studies have focused. We discuss ways of testing theoretical predictions in superconductor experiments and analyse the results of recent experiments in this light.

I. INTRODUCTION

There has been much recent interest in testing cosmological defect-formation scenarios [1, 2, 3] in the laboratory. In the Nineties, experiments in liquid crystals [4, 5, 6] and especially in liquid ^3He [7, 8] clearly showed the formation of defects in line with predictions. In ^4He , experiments have proved negative [9], but there is good reason to believe that this is due to the fact that vortices disappear too rapidly to be seen [10, 11].

More recently, the focus of the experimental activity has shifted towards superconductors [12, 13, 14, 15, 16, 17, 18]. In the pioneering experiment by Carmi and Polturak [12], no evidence of spontaneous vortex formation was seen, but later experiments with a multiple-Josephson-junction loop [13] and with an annular Josephson junction [14, 15, 16] have been positive. Earlier this year, successful experiments have also been carried out with an array of superconducting rings [17] and a thin superconducting film [18].

It is not possible to apply the original estimates of defect numbers directly to the case of the superconducting transition, because it involves a local gauge theory rather than a global symmetry breaking [3, 19, 20]. In ref. [12], a somewhat *ad hoc* modification of the standard prediction was proposed for comparison with experiment, but a more firmly based estimate is needed. The problem of defect formation in a gauge theory has been analyzed by Hindmarsh and Rajantie [3], who showed that in addition to the standard mechanism of defect formation, there is a second mechanism operating. This flux trapping mechanism stems from the fluctuations in the magnetic field, which get frozen out during the quench.

The two mechanisms produce defect distributions with characteristically very different correlation properties. In a gauge theory, one would expect positive vortex-vortex correlations at short distances. In other words, the vortices should be formed in clusters of equal sign. This is supported by numerical simulations carried out in the Abelian Higgs model [21, 22]. On the other hand, the

vortices should have negative correlations at all distances in global theories.

One of us [23] has studied an $\text{SO}(3)$ gauge theory, and shown that monopoles form, even when there is no true phase transition, only a smooth crossover. The monopole distribution again shows positive monopole-monopole correlation, in contrast to the situation in a global symmetry theory, where one would expect monopole-antimonopole correlations.

In this paper, we examine the spontaneous formation of vortices (or fluxons or fluxoids) in a thin film undergoing the normal-to-superconducting transition in the light of existing and future experiments. This setup differs significantly from the fully two-dimensional case studied in Ref. [22], because the magnetic field extends outside the film and leads to long-range $1/r$ interaction between vortices [24]. Therefore, there are actually many similarities with monopole formation in three dimensions. In both cases, the interaction is screened by thermal effects, although the screening is less effective here.

We also discuss the results of the experiments carried out so far, and conclude that whilst they are compatible with the two mechanisms, they do not currently constitute a positive confirmation of either.

Throughout this paper, we use the natural units $c = \hbar = k_B = 1$. We will write three-vectors with bold-faced symbols as \mathbf{k} , and two-vectors on the film with an arrow as \vec{k} .

II. TWO-DIMENSIONAL SUPERCONDUCTORS

Theoretical studies of defect formation in two dimensions have shown that there are essentially two different regimes. At a weak enough coupling or low enough critical temperature, the relevant degree of freedom is the order parameter field and the process is well described by the Kibble-Zurek mechanism [1, 2]. On the other hand, at strong coupling or high critical temperature, it is dominated by thermal fluctuations of the gauge field [3].

The simplest example of the Kibble-Zurek mechanism is the phase transition in a Ginzburg-Landau model with a global U(1) symmetry. Because the mechanism is very generic, we can consider a two-dimensional relativistic version of the model, with the Lagrangian density

$$\mathcal{L} = \dot{\phi}^* \dot{\phi} - \vec{\nabla} \phi^* \cdot \vec{\nabla} \phi - \beta(\phi^* \phi - v^2)^2. \quad (1)$$

The U(1) symmetry, which is spontaneously broken at zero temperature, is restored at temperatures above a critical value T_c . Above T_c , the field has a finite correlation length, which diverges at T_c . In the broken phase, the phase angle is a Goldstone mode and therefore it has an infinite correlation length.

Imagine now that the temperature is initially above T_c , and is gradually decreased so that the system undergoes a phase transition. When T_c is approached, the correlation length would have to grow faster and faster in order to stay in equilibrium. Sooner or later that becomes impossible. As a result, the phase angle can only be ordered over some finite distance $\hat{\xi}$ in the broken phase, and this leads to formation of vortices with number density $n \sim 1/\hat{\xi}^2$ [1]. The length scale $\hat{\xi}$ has a power-law dependence on the cooling rate, with an exponent that depends on the universality class of the transition [2].

The spatial vortex distribution can be characterized by how the typical net vortex number ΔN inside a circular curve depends on its radius R . As long as $R \gg \hat{\xi}$, the curve should pass through roughly $2\pi R/\hat{\xi}$ correlated domains, and each time it moves from one domain to another, the phase changes by a random amount. As a consequence, the net vortex number should behave like a random walk of $2\pi R/\hat{\xi}$ steps,

$$\Delta N(R) \approx \frac{1}{2\pi} \sqrt{\frac{2\pi R}{\hat{\xi}}} \propto R^{1/2}. \quad (2)$$

For comparison, if the signs of the vortices were randomly distributed, the net vortex number would grow like $\Delta N(R) \propto R$. This shows that the vortices formed by this mechanism have negative correlations.

Superconductors have a spontaneously broken local gauge symmetry, and therefore we modify the Lagrangian by adding a gauge field, i.e., the electromagnetic vector potential \vec{A} ,

$$\mathcal{L} = \frac{1}{2} (\vec{E}^2 - B^2) + \dot{\phi}^* \dot{\phi} - \vec{D} \phi^* \cdot \vec{D} \phi - \beta(\phi^* \phi - v^2)^2, \quad (3)$$

where we have introduced the covariant derivative $\vec{D} = \vec{\nabla} + ie\vec{A}$, and used the gauge invariance to set the electric scalar potential to zero. With this choice, the electric and magnetic fields are given by $\vec{E} = -\partial\vec{A}/\partial t$ and $B = \partial_1 A_2 - \partial_2 A_1$.

This describes a relativistic, fully two-dimensional superconductor, and is not a good approximation for a superconductor film, as we will see later. Nevertheless, we will use it to illustrate the flux trapping mechanism of defect formation [3].

Classically, the initial thermal state is given by the Boltzmann distribution $p[\phi, A_\mu] \propto \exp(-E[\phi, A_\mu]/T)$, where

$$E = \int d^2 \vec{x} \left[\frac{1}{2} (\vec{E}^2 + B^2) + \dot{\phi}^* \dot{\phi} + \vec{D} \phi^* \cdot \vec{D} \phi + \beta(\phi^* \phi - v^2)^2 \right]. \quad (4)$$

The most relevant terms for us are the one containing the magnetic field and the covariant derivative term.

If the magnetic field vanishes, the covariant derivative reduces to the ordinary gradient, and one expects that the above Kibble-Zurek picture is valid. However, at a non-zero temperature, there are always thermal fluctuations, which have to be taken into account. In the symmetric phase, the effect of the scalar ϕ on the magnetic field is insignificant, and to a good approximation we can say that B is a Gaussian random field with a two-point function

$$\langle B(\vec{x}) B(\vec{y}) \rangle \approx T \delta(\vec{x} - \vec{y}), \quad (5)$$

or

$$\langle B(\vec{k}) B(\vec{q}) \rangle \approx T (2\pi)^2 \delta(\vec{k} + \vec{q}). \quad (6)$$

This is simply the classical Rayleigh-Jeans spectrum of blackbody radiation, and therefore it is only valid when $|\vec{k}| \ll k_B T / c\hbar \approx 440(T/\text{K})\text{m}^{-1}$. This constraint may be important in the case of low-temperature superconductors, but we will not discuss it here any further.

In the broken phase, the Meissner effect suppresses the fluctuations, and the two-point function (for modes with $k \lesssim T$) becomes

$$\langle B(\vec{k}) B(\vec{q}) \rangle \approx T \frac{k^2}{k^2 + \lambda^{-2}} (2\pi)^2 \delta(\vec{k} + \vec{q}). \quad (7)$$

where λ is the penetration depth, which starts to decrease from infinity at T_c .

However, the magnetic field is conserved, because $\partial_0 B = \vec{\nabla} \cdot \vec{E}$, where $\vec{E} = (-E_2, E_1)$. Therefore, the long-wavelength modes can only decay very slowly. Because of causality, the decay rate must be lower than the wave number $\gamma(k) \lesssim k$, but there are also other, much stronger constraints arising from the detailed dynamics.

In any case, for any cooling rate, there are going to be some long-wavelength modes that are too slow to react. Their amplitudes are therefore frozen to the values they had before the transition. The corresponding magnetic flux gets trapped into vortices. We can define a critical wavenumber k_c , so that this happens to modes with $k < k_c$.

Now, consider the typical (root-mean-squared) magnetic flux through a circle of radius $R \approx 1/k_c$,

$$\Phi(R) = \left\langle \left(\int^R d^2 \vec{x} B(\vec{x}) \right)^2 \right\rangle^{1/2}. \quad (8)$$

The whole contribution to this quantity comes from modes with $k < k_c$, and therefore $\Phi(R)$ does not change during the transition. After the transition, it will have the same value as in the symmetric phase before the transition, and we can calculate that, using Eq. (7) (and neglecting factors of order 1),

$$\Phi(R) \approx \sqrt{T}/k_c. \quad (9)$$

However, because of Meissner effect, this magnetic flux must be confined into vortices. Each vortex carries one flux quantum $\Phi_0 = 2\pi/e$, and therefore we can say that the typical number of vortices in a region of radius $R = 1/k_c$ is

$$N(R) = e\Phi(R) \approx e\sqrt{T}/k_c. \quad (10)$$

Dividing this by the area of such a region gives an estimate for the number density [3]

$$n \approx ek_c\sqrt{T}. \quad (11)$$

Nevertheless, the most obvious difference with the Kibble mechanism is that all $N(R)$ vortices formed in any given region have the same sign, which leads to positive correlations between vortices and formation of clusters of $N(R)$ vortices. These clusters have been seen in numerical simulations in Ref. [22].

Note that our discussion was only based on the behaviour of the long-wavelength magnetic fields, namely the qualitative form of the two-point function in Eq. (7), causality and the conservation of magnetic field. It should therefore be independent of the microscopic details of the system and should apply to real superconductors as well as to the toy model in Eq. (3). However, as we shall see, one will have to consider a three-dimensional setup.

III. SUPERCONDUCTING FILMS

Superconductor experiments are typically carried out with a thin superconducting film, but the fully two-dimensional geometry discussed in Section II does not describe that situation correctly, because the magnetic field should extend outside the superconductor and induce long-range interactions between vortices [24].

In the symmetric phase, we can calculate the analogue of Eq. (7), i.e., the two-point function on the film from the three-dimensional correlation function in the Feynman gauge,

$$\langle A_i(\mathbf{k})A_j(\mathbf{q}) \rangle = \frac{T\delta_{ij}}{\mathbf{k}^2}(2\pi)^3\delta(\mathbf{k} + \mathbf{q}). \quad (12)$$

Again, this is equivalent to the classical Rayleigh-Jeans spectrum. For the magnetic field normal to the film, we find

$$\langle B_3(\vec{x}, 0)B_3(\vec{y}, 0) \rangle = T \int \frac{d^3\mathbf{k}}{(2\pi)^3} \frac{\vec{k}^2}{\mathbf{k}^2} e^{i\vec{k}\cdot(\vec{x}-\vec{y})}, \quad (13)$$

where we have set $\mathbf{k} = (\vec{k}, k_3)$. Equivalently, defining

$$B(\vec{k}) = \int d^2\vec{x} B_3(\vec{x}, 0)e^{-i\vec{k}\cdot\vec{x}}, \quad (14)$$

we have

$$\langle B(\vec{k})B(\vec{q}) \rangle = \frac{Tk}{2}(2\pi)^2\delta(\vec{k} + \vec{q}). \quad (15)$$

It is less straightforward to calculate the two-point function in the broken phase, because the gauge field is massive on the film but massless outside it. Therefore, we use a different approach. Deep in the broken phase, the vortices are well defined, localized objects, and we can approximate them by point particles on the film. Because the magnetic field cannot penetrate the film, we can flip the direction of the magnetic field on one side of the film, without changing the energy of the configuration. This changes a vortex into a magnetic monopole of charge $q_M = 2\Phi_0 = 4\pi/e$. Therefore, the vortices must behave as magnetic monopoles confined on the film. Correspondingly, their interaction potential falls off as $1/r$, as opposed to the $\log(r)$ of global vortices and $\exp(mr)$ of local vortices in a fully two-dimensional case. In fact, this result is only valid at distances longer than the Pearl length $\Lambda_P \approx \lambda^2/d$, where d is the thickness of the film [24]. In what follows, we assume that Λ_P is shorter than any of the length scales we discuss.

We now assume that the number density of thermal vortices is $n_f = n_+ + n_-$, where n_+ and n_- are the densities of positive and negative vortices, respectively, and calculate what kind of correlations the magnetic Coulomb interaction induces. This calculation is very similar to the calculation of Debye screening in three dimensions. In the absence of thermal fluctuations, the magnetic potential around a vortex would be simply $\phi_0(r) = q_M/4\pi r$. However, the presence of such a potential biases the thermal distribution of vortices and antivortices such that

$$n_{\pm}(r) = \frac{n_f}{2} \exp(\mp q_M\phi(r)/T) \approx \frac{n_f}{2} \left(1 \mp \frac{q_M\phi(r)}{T} \right). \quad (16)$$

The magnetic flux density is

$$B(r) = q_M(n_+(r) - n_-(r)) = -\frac{q_M^2 n_f \phi(r)}{T} = -\frac{\phi(r)}{\Lambda_{\text{scr}}}, \quad (17)$$

where we have defined

$$\Lambda_{\text{scr}} = \frac{T}{q_M^2 n_f}. \quad (18)$$

This flux density, in turn, modifies the potential, and we find the integral equation

$$\phi(\vec{r}) = \frac{q_M}{4\pi r} + \int \frac{d^2\vec{r}'}{4\pi|\vec{r}-\vec{r}'|} 2B(\vec{r}') = \frac{q_M}{4\pi r} - \frac{2}{\Lambda_{\text{scr}}} \int \frac{d^2\vec{r}'}{4\pi|\vec{r}-\vec{r}'|} \phi(\vec{r}'). \quad (19)$$

We can solve this equation in Fourier space, and find

$$\phi(\vec{k}) = \frac{1}{2} \frac{q_M}{k + \Lambda_{\text{scr}}^{-1}} \quad (20)$$

In coordinate space, ϕ behaves asymptotically as

$$\phi(r) \sim \frac{q_M}{4\pi r} \quad \text{at } r \ll \Lambda_{\text{scr}},$$

$$\phi(r) \sim \frac{q_M \Lambda_{\text{scr}}^2}{4\pi r^3} \quad \text{at } r \gg \Lambda_{\text{scr}},$$

which shows that the thermal fluctuations screen the interaction potential, but the potential still has a power-law form rather than an exponential. Including the contribution from the original vortex, the magnetic flux density around a vortex is

$$B(\vec{r}) = \frac{q_M}{2} \delta(\vec{r}) - \frac{\phi(\vec{r})}{\Lambda_{\text{scr}}}, \quad (21)$$

and since there is a density n_f of these vortices each with charge q_M , the two-point function of the flux density is

$$\langle B(\vec{x})B(\vec{y}) \rangle = q n_f B(|\vec{x} - \vec{y}|). \quad (22)$$

In Fourier space, this corresponds to

$$\begin{aligned} \langle B(\vec{k})B(\vec{q}) \rangle &= q n_f \left[\frac{q_M}{2} - \frac{\phi(k)}{\Lambda_{\text{scr}}} \right] (2\pi)^2 \delta(\vec{k} + \vec{q}) \\ &= \frac{q_M^2 n_f}{2} \frac{k}{k + \Lambda_{\text{scr}}^{-1}} (2\pi)^2 \delta(\vec{k} + \vec{q}). \end{aligned} \quad (23)$$

We can rewrite this as

$$\langle B(\vec{k})B(\vec{q}) \rangle = \frac{T}{2} \frac{k}{1 + k\Lambda_{\text{scr}}} (2\pi)^2 \delta(\vec{k} + \vec{q}), \quad (24)$$

where we have used Eq. (18). From this expression, it is easy to see that the long-distance (low k) behaviour agrees with the symmetric phase, where Λ_{scr} is small.

The crucial difference between Eqs. (7) and (24) is that in the case of a film, the important length scale is not the penetration depth λ (or the Pearl length Λ_P), but the screening length Λ_{scr} . Whilst λ starts from infinity and approaches the zero-temperature penetration depth, Λ_{scr} behaves in the opposite way: It is initially very short and approaches infinity at zero temperature.

As Λ_{scr} increases, each mode gets suppressed only when the wavelength becomes shorter than the screening length, $1/k \lesssim \Lambda_{\text{scr}}$. Therefore, the long-wavelength modes feel the effect of the phase transition later than short-wavelength modes. In fact, the present case is actually very similar to monopole formation in three-dimensional non-Abelian theories [23], since the magnetic charge-charge correlator in that case,

$$\langle \rho_M(\mathbf{k})\rho_M(\mathbf{q}) \rangle \approx T \frac{k^2}{1 + k^2/M^2} (2\pi)^3 \delta(\mathbf{k} + \mathbf{q}), \quad (25)$$

behaves in the same way.

In any case, Eq. (24) shows that if the system could stay in equilibrium, the fluctuations of all wavelengths would be suppressed in the zero-temperature limit, where

$\Lambda_{\text{scr}} \rightarrow \infty$. However, the slowness of the long-wavelength modes implies that the modes with wave numbers below a certain critical value k_c freeze out to the amplitudes they had in the symmetric phase, and we can approximate

$$\langle B(\vec{k})B(\vec{q}) \rangle = \frac{Tk}{2} \exp(-k/k_c) (2\pi)^2 \delta(\vec{k} + \vec{q}). \quad (26)$$

At this point, we do not specify the value of k_c , but only note that it must be finite and non-zero. The precise form of the cutoff at k_c is irrelevant, and this exponential form simplifies the calculations, because the coordinate space correlator has the simple form

$$\langle B(0)B(\vec{r}) \rangle = \frac{Tk_c^3}{4\pi} \frac{2 - r^2 k_c^2}{(1 + r^2 k_c^2)^{5/2}}. \quad (27)$$

This is constant at short distances, $r \ll k_c^{-1}$, and from that we can deduce the number density

$$n \approx q_M^{-1} \sqrt{\lim_{r \rightarrow 0} \langle B(0)B(\vec{r}) \rangle} = \frac{e}{2\pi} \sqrt{\frac{Tk_c^3}{2\pi}}. \quad (28)$$

This can also be seen by calculating the variance of the flux $\Phi(R)$ through a circle of radius R ,

$$\begin{aligned} \langle \Phi^2 \rangle &= \int^R d^2x \int^R d^2y \langle B(\vec{x})B(\vec{y}) \rangle \\ &\approx \begin{cases} (\pi/2) T k_c^3 R^4, & \text{for } R \ll k_c^{-1} \\ T R \ln k_c R, & \text{for } R \gg k_c^{-1}. \end{cases} \end{aligned} \quad (29)$$

At short distances, the typical (rms) flux through a small curve is proportional to its area and implies a uniform flux density $B \approx (T k_c^3)^{1/2}$, in agreement with Eq. (28). At long distances, the scaling is the same as in the Kibble-Zurek scenario, $\Delta N(R) \sim R^{1/2}$, apart of the logarithm.

By choosing $R = k_c^{-1}$ in Eq. (29) we can also see that the number of vortices in a cluster is

$$N_{\text{cl}} \approx \sqrt{\frac{\langle \Phi^2 \rangle}{q_M^2}} \approx \sqrt{\frac{e^2 T}{8\pi k_c}}. \quad (30)$$

These results agree with the estimates in Ref. [3].

So far, we have not discussed the value of k_c , and indeed, it is generally more sensitive to the detailed dynamics than the above considerations. On the other hand, one can carry out an k_c -independent test of the mechanism by measuring, for instance, the combination $N_{\text{cl}}^3 n$, which is predicted to be

$$N_{\text{cl}}^3 n \approx \frac{e^4 T^2}{(4\pi)^3}. \quad (31)$$

To get a crude estimate of k_c , let us assume that Ohm's law $\vec{j} = \sigma \vec{E}$ is valid, and that the dynamics of the magnetic field fluctuations is dominated by the conductivity σ . In that case, Maxwell's equations imply that the dynamics of the magnetic field normal to the film is given by the damped wave equation

$$\frac{d^2 B_z}{dt^2} = \partial_z^2 B_z + \vec{\nabla}^2 B_z - \sigma \frac{dB_z}{dt}. \quad (32)$$

Ignoring the z derivative, which would give rise to radiation, we find that the maximum decay rate of any long-wavelength mode with wavenumber $|\vec{k}| \ll \sigma$ is $\gamma(\vec{k}) = \vec{k}^2/\sigma$. According to Eq. (24), the amplitude of the mode must decrease as

$$B(\vec{k}) \sim \sqrt{T/\Lambda_{\text{scr}}} \quad (33)$$

for the system to stay in equilibrium once $\Lambda_{\text{scr}} \gtrsim 1/k$. The time scale for decrease of $B(\vec{k})$ is therefore the quench time τ_Q . The decay rate $1/\tau_Q$ exceeds the maximum decay rate $\gamma(\vec{k})$, if

$$k < k_c \approx \sqrt{\sigma/\tau_Q}. \quad (34)$$

IV. COMPARISON WITH EXPERIMENT

We now turn to the question of whether these results can throw any light on recent experimental results. Experiments that were very similar to the setup we have discussed have been carried out by Carmi and Polturak [12] and more recently by Maniv et al [18]. They involved a rapid quench of a thin film of the high-temperature superconductor $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$, using a SQUID to measure the net flux following the quench. This corresponds to the net number of vortices minus antivortices produced by the quench.

In the first set of experiments [12], no evidence for vortices were found. The standard causality argument used in cases of global symmetry breaking [1, 2] suggests that the expected scalar-field correlation length $\hat{\xi}$ at the relevant time after the transition should in this case be about $0.1 \mu\text{m}$. In the 1 cm^2 area of the sample, the number of vortices N should then be about 10^9 or 10^{10} . If one assumes, with Zurek [2], that the phase of the scalar field makes a random walk around the perimeter of the sample with a step length of $\hat{\xi}$, then one finds $\Delta N \sim N^{1/4}$, suggesting that ΔN should be at least of order 100. The experiment should have seen anything in excess of $\Delta N \sim 20$, so this was thought to be a contradiction.

In the revised experiment [18], faster cooling rates of around $dT/dt \approx -10^8 \text{ K/s}$ were used. This increases the predicted number of vortices, and indeed, net vortex numbers between 30 and 45 were measured. This number showed a weak dependence on the cooling rate, with faster quenches producing more vortices. This is compatible with theoretical predictions. The Kibble-Zurek scenario with overdamped dynamics would yield a domain size of $\hat{\xi} \propto |dT/dt|^{-1/4}$. The net flux would then be

$$\Phi = \Delta N \Phi_0 \approx (R/\hat{\xi})^{1/2} \Phi_0 \propto |dT/dt|^{1/8}, \quad (35)$$

where $R \approx 1 \text{ cm}$ is the linear size of the film. The experimental results are consistent with this scaling [18], although the error bars are so large that one cannot use

that data to determine the exponent. The prefactor in the theoretical prediction is rather uncertain, and to obtain a fit the authors reduced the prediction by a factor of four. Extrapolation to the cooling rate 20 K/s used in Ref. [12] then gives $\Delta N \approx 6$, which is below the noise level and explains why no vortices were seen in the original experiment.

However, Carmi and Polturak [12] rightly pointed out that these arguments are unreliable in the case of a gauge theory, and suggested an *ad hoc* modification leading to a prediction $\Delta N \sim 0.1N^{1/2} \sim 10^4$, which is in very severe disagreement with the experimental results.

We wish to argue, however, that this modification is not the appropriate way of treating a gauge field. It is important to note that the two mechanisms of defect formation, based on fluctuations of the scalar field and the gauge field, are characterized by different length scales. In the case of the scalar field, it is the correlation length $\hat{\xi}$; for the gauge field, it is $1/k_c$. So to estimate the contribution to be expected from magnetic-field fluctuations, we need to estimate k_c . This is hard to do, because it is not clear how fast gauge-field correlations can propagate. However, we can still put a limit on the expected number of defects formed. It seems probable that $1/k_c$ would be smaller than the size of the sample. In that case, the net flux through the sample should be essentially the same as that in the high-temperature phase due to thermal fluctuations. From Eq. (29), we find

$$\Delta N \approx \sqrt{e^2 T R}. \quad (36)$$

With a sample size $R \approx 1 \text{ cm}$, this gives $\Delta N \sim 10$. If in fact $1/k_c$ is larger than R , then the net flux would actually be less than this,

$$\Delta N \approx \sqrt{e^2 T k_c^3 R^4} \propto |dT/dt|^{3/4}, \quad (37)$$

where we have used Eq. (34).

The above estimate shows that the contribution from the gauge-field fluctuations to the net flux is so small that it would have been below the noise level in Ref. [12], just like the contribution from the Kibble-Zurek mechanism. However, in contrast to the Kibble-Zurek mechanism, the contribution is independent of the cooling rate, and the faster cooling used in Ref. [18] would not help detecting it. At most, it would shift the data points in Fig. 4 of Ref. [18] up by a small amount, but because the errors are relatively large and the overall scaling of the theoretical prediction the data points are compared with is undetermined, one cannot draw any conclusions about the gauge-field contribution based on these measurements.

We conclude therefore that it is unlikely that the magnetic-field fluctuations contribute a detectable amount to ΔN . This does not mean, however, that they can be ignored. The two mechanisms differ radically in the nature of the resulting defect distributions. If scalar-field fluctuations are dominant, one expects strong vortex-anti-vortex correlations — the two-dimensional analogue of a preponderance of small vortex loops —

whereas, as noted above, if magnetic-field fluctuations dominate, we expect clusters of similarly oriented defects.

Clearly, it would be very desirable to be able to get some information on the distribution of vortices, and in particular to measure N as well as ΔN . Only in that way could one separate the contributions of the two mechanisms. Achieving this in an experiment with a superconductor film is probably difficult, because the vortices produced during the quench may escape the sample in a short time. The flux distribution would therefore have to be measured very rapidly immediately after the quench.

However, a recent experiment by Kirtley et al [17] shows how this problem can be solved. Instead of a film, they used a square array of 12×12 thin (50 nm) superconducting rings with inner radius of 10 μm and outer radius of 15 μm , spaced by 60 μm . After the quench, the magnetic flux through any ring can only change if a vortex can cross the high energy barrier created by the superconducting ring, and therefore the original fluxes survive a long enough time to be measured with a scanning SQUID.

For this experiment, the Kibble-Zurek mechanism would predict that each ring behaves independently of the others. From Eq. (2), the typical number of fluxons trapped in a ring would be

$$N \propto |dT/dt|^{1/8}. \quad (38)$$

In fact, there was typically only one flux quantum or no flux at all through one ring in the experiment, and it is therefore not at all clear one can use Eq. (38) to predict the fluxes. Nevertheless, if one interprets it as the probability of having a fluxon, the result of the experiment was in a clear disagreement with it. Instead of a power-law, the measurements showed a very weak, perhaps logarithmic, dependence on the cooling rate.

Kirtley et al [17] were able to fit their data with a

simple model, which is similar in spirit to the flux trapping scenario. They argue that any vortices formed by the Kibble-Zurek mechanism would be ‘washed out’ by their thermally activated vortex mechanism. Because the rings are relatively far apart from each other, they can be assumed to be independent, and the problem simplifies considerably. For this reason, the results in Ref. [17] cannot be thought to have confirmed the flux trapping scenario.

On the other hand, it seems that the predictions for the spatial vortex distribution, which can best distinguish the two mechanisms, could be tested with a relatively simple experimental setup. Instead of a homogeneous film or an array of rings, one would use a film with small holes in a regular array. The vortices formed during a quench would simply move to the nearest hole and get trapped there. They could then be measured with a scanning SQUID device in the same way as in Ref. [17].

It should be noted, however, that there are many other complicating factors in the case of a superconducting film, notably the importance of impurities and pinning centres, which could drastically affect the vortex numbers. Moreover, high-temperature superconductors involve Cooper pairs with d-wave pairing, so a full description should involve a multi-component order parameter. As a result, the vortices can have more structure, for example antiferromagnetic cores. The effects of these complications on defect formation remain to be studied.

Acknowledgments

We would like to thank Manuel Donaire, Tom Girard and Ray Rivers for useful discussions. This work was partly funded by the ESF COSLAB programme. AR was supported by PPARC and Churchill College, Cambridge.

-
- [1] T. W. B. Kibble, *Phys. Rep.* **67C** (1980) 183–199.
 - [2] W. H. Zurek, *Phys. Rep.* **276** (1996) 177–221.
 - [3] M. B. Hindmarsh and A. Rajantie, *Phys. Rev. Lett.* **85** (2000) 4660–63.
 - [4] I. Chuang, R. Durrer, N. Turok and B. Yurke, *Science* **251** (1991) 1336–42.
 - [5] M. J. Bowick, L. Chandar, E. A. Schiff and A. M. Srivastava, *Science* **263** (1994) 943–5.
 - [6] S. Digal, R. Ray and A. M. Srivastava, *Phys. Rev. Lett.* **83** (1999) 5030–33.
 - [7] C. Bäuerle, Yu. M. Bunkov, S. N. Fisher, H. Godfrin and G. R. Pickett, *Nature* **382** (1996) 332–334.
 - [8] V. M. H. Ruutu, V. B. Eltsov, A. J. Gill, T. W. B. Kibble, M. Krusius, Yu. G. Makhlin, B. Plaçais, G. E. Volovik and W. Xu, *Nature* **382** (1996) 334–336.
 - [9] M. E. Dodd, P. C. Hendry, N. S. Lawson, P. V. E. McClintock and C. D. H. Williams, *Phys. Rev. Lett.* **81** (1998) 3703–3706.
 - [10] R. J. Rivers, *Phys. Rev. Lett.* **84** (2000) 1248–51.
 - [11] P. C. Hendry, N. S. Lawson and P. V. E. McClintock, *J. Low Temp. Phys.* **119** (2000) 249–256.
 - [12] R. Carmi and E. Polturak, *Phys. Rev. B* **60** (1999) 7595–7600.
 - [13] R. Carmi, E. Polturak and G. Koren, *Phys. Rev. Lett.* **84** (2000) 4966–69.
 - [14] E. Kavoussanaki, R. Monaco and R. J. Rivers, *Phys. Rev. Lett.* **85** (2000) 3452–5.
 - [15] R. Monaco, J. Mygind and R. J. Rivers, *Phys. Rev. Lett.* **89** (2002) 080603.
 - [16] R. Monaco, J. Mygind, R. J. Rivers arXiv:cond-mat/0207504.
 - [17] J. R. Kirtley, C. C. Tsuei and F. Tafuri, arXiv:cond-mat/0302384.
 - [18] A. Maniv, E. Polturak and G. Koren, arXiv:cond-mat/0304359.
 - [19] S. Rudaz and A. M. Srivastava, *Mod. Phys. Lett. A* **8** (1993) 1443–50.
 - [20] E. J. Copeland and P. Saffin, *Phys. Rev. D* **54** (1996)

- 6088–94.
- [21] M. B. Hindmarsh and A. Rajantie, *Phys. Rev. D* **64** (2001) 065016.
- [22] G. J. Stephens, L. M. Bettencourt and W. H. Zurek, *Phys. Rev. Lett.* **88** (2002) 137004.
- [23] A. Rajantie, arXiv:hep-ph/0212130.
- [24] J. Pearl, *App. Phys. Lett.* **5** (1964) 65.