

Orbital moment in CoO and in NiO

R. J. Radwanski

Institute of Physics, Pedagogical University, 30-084 Krakow, Poland

ℳ Center for Solid State Physics, S^{nt} Filip5,31-150Krakow,Poland.

Z. Ropka

Center for Solid State Physics, S^{nt} Filip5,31-150Krakow,Poland.

email: sfradwan@cyf-kr.edu.pl, http://css-physics.edu.pl

The total, orbital and spin moment of the Co^{2+} ion in CoO has been calculated within the quasi-atomic approach with taking into account strong correlations, crystal-field interactions and the intra-atomic spin-orbit coupling. The orbital moment of $1.39 \mu_B$ amounts at 0 K, in the magnetically-ordered state, to more than 34% of the total moment ($4.01 \mu_B$) and yields the L/S ratio of 1.05, close to the experimental value. The same calculations yield for NiO the orbital and total moment of $0.46 \mu_B$ and $2.45 \mu_B$, respectively.

PACS No: 71.70.E; 75.10.D

Keywords: 3d magnetism, crystal field, spin-orbit coupling, orbital moment, CoO, NiO

1. Introduction

CoO and NiO attract a large attention of the magnetic community by more than 50 years. Despite of its simplicity (two atoms, *NaCl* structure, well-defined antiferromagnetism (AF) with T_N of 290 K and 525 K, respectively) and enormous theoretical and experimental works the consistent description of its properties, reconciling its insulating state with the unfilled *3d* band is still not reached [1–5].

The aim of this paper is to report the calculations of the magnetic moment of CoO and NiO, its direction and the value as well as the spin and orbital parts. In our approach, called Quantum Atomistic Solid-State theory (QUASST), we attribute the moment of CoO/NiO to the $\text{Co}^{2+}/\text{Ni}^{2+}$ ions. We have calculated the moment of the $\text{Co}^{2+}/\text{Ni}^{2+}$ ion in the $\text{CoO}_6/\text{NiO}_6$ octahedral complex, its spin and orbital parts. The orbital moment at 0 K as large as 1.38

μ_B and $0.46 \mu_B$ has been found in CoO and NiO. The approach used can be called the quasi-atomic approach [6,7] as the starting point for the description of a solid is the consideration of the atomic-like low-energy electronic structure of the constituting atoms/ions, in the present case of the $\text{Co}^{2+}/\text{Ni}^{2+}$ ions.

2. Theoretical outline

We have treated the 7 outer electrons of the Co^{2+} ion in Mott insulator $\text{Co}^{2+}\text{O}^{2-}$ as forming the strongly-correlated electron system $3d^7$. The correlations among electrons in the unfilled $3d$ shell are taken by two Hund's rules, that yield the ground-term quantum numbers $S=3/2$ and $L=3$ related to the ground term 4F [8,9]. Such the localized highly-correlated electron system interacts in a solid with the charge and spin surroundings. The charge surroundings has predominantly the octahedral symmetry owing to the *NaCl*-type of structure of CoO and NiO [4]. Distortions are important for the detailed formation of the AF structure and influence the spin and orbital moments but the most essential physical interaction is the intra-atomic spin-orbit coupling. Our Hamiltonian for CoO consists of two terms: the single-ion-like term H_d of the $3d^7$ system and the d - d intersite spin-dependent term H_{d-d} , that is indispensable for the formation of the magnetic state. The calculations follow those, that we have performed for the description of FeBr_2 and NiO [6,7,10]. For the quasi-atomic single-ion-like Hamiltonian of the $3d^7$ system we take into account the crystal-field interactions of the octahedral symmetry (the octahedral CEF parameter $B_4=-30$ K), the spin-orbit interactions with the spin-orbit coupling $\lambda_{s-o}=-260$ K and the tetragonal distortion approximated by the term $B_2^0=-5$ K. The single-ion states under the octahedral crystal field and the spin-orbit coupling have been calculated by consideration of the Hamiltonian:

$$H_d = B_4(O_4^0 + 5O_4^4) + \lambda_{s-o}L \cdot S \quad (1)$$

The calculated single-ion states under the octahedral crystal field and the spin-orbit coupling (the CoO_6 complex) are presented in Fig. 1(c). The intersite spin-dependent interactions cause the (antiferro-)magnetic ordering. They have been considered in the mean-

field approximation with the molecular-field coefficient n acting between magnetic moments $m_d=(L+2S) \mu_B$. Having the CEF interactions quantified, here B_4 mostly from optical studies, the value of n in the Hamiltonian

$$H_{d-d} = n \left(-m_d \cdot m_d + \frac{1}{2} \langle m_d^2 \rangle \right) \quad (2)$$

has been adjusted in order to reproduce the experimentally-observed Neel temperature. The fitted value of n , for T_N of 290 K, has been found to be $-2.43 \text{ meV} / \mu_B^2$ ($=42 \text{ T} / \mu_B$). It means that the Co-ion moment in the magnetically-ordered state experiences the molecular field of 169 T (at 0 K).

As the result of calculations we get the low-energy electronic structure, i.e. the energy of $(2L+1) \cdot (2S+1)$ states and their eigenfunctions. Having the energy of states we can calculate the free energy. It enables calculations of thermodynamical properties. The ground-state eigenfunction enables calculations of the total, orbital and spin moments.

In NiO the 8 outer electrons of the Ni^{2+} ion, forming the strongly-correlated electron system $3d^8$, are described by $S=1$ and $L=3$ related to the ground term 3F [8]. For the calculations of the quasi-atomic single-ion-like Hamiltonian of the $3d^8$ system we take into account the crystal-field interactions of the octahedral symmetry and the spin-orbit coupling (the octahedral CEF parameter $B_4=+2 \text{ meV}$ and the spin-orbit coupling constant $\lambda_{s-o}=-41 \text{ meV}$ [8], p. 399). The preliminary results for NiO have been reported in [10].

3. Results and discussion

The calculated value of the total magnetic moment at 0 K in CoO and NiO in the magnetically-ordered state amounts to 4.01 and 2.45 μ_B , respectively. In CoO it is built up from the spin moment m_s of 2.62 μ_B ($S_z=1.31$) and the orbital moment m_o of 1.39 μ_B . In NiO it is built up from the spin moment m_s of 1.99 μ_B and the orbital moment m_o of 0.46 μ_B .

The formation of the magnetic state and of the magnetic moment is associated to the polarization of two conjugate states as is shown in Fig. 2. The spin-like gap at 0 K amounts to 40 meV.

The orbital moment in CoO is quite substantial being more than 34% of the total moment. Our theoretical outcome, revealing the substantial orbital moment is in nice agreement with the very recent experimental result of $3.98 \pm 0.06 \mu_B$ for the Co moment [3]. The magnetic x-ray experiment has revealed the L/S ratio of 0.95 [11]- the calculated by us values lead to L/S ratio, in fact their z components, of 1.05. Also our theoretical result about the substantial orbital moment in NiO, is in nice agreement with the very recent experimental result of $2.2 \pm 0.3 \mu_B$ for the Ni moment at 300 K [11,13].

The effect of the small tetragonal distortion one can note comparing values of the moment in the paramagnetic state shown in Fig. 2 and the moment of the ground state in Fig. 1.

The calculated temperature dependence of the total moment, together with the orbital and spin moments, is shown in Fig. 3. These moments disappear above T_N - in the paramagnetic region the derived moment is the effective moment, that bears the information about the operators J^2 or S^2 .

We would like to point out that the evaluation of the orbital moment is possible provided the spin-orbit coupling is taken into account. It confirms the importance of the spin-orbit coupling for the description of the $3d$ -ion compounds. The magnetically-ordered state of CoO has lower energy than the paramagnetic one by 380 J/mol (= 3.9 meV/ion) at 0 K. Of course, the energies of magnetic and paramagnetic states become equal at T_N .

Finally, we would like to point out that our approach should not be considered as the treatment of an isolated ion only - we consider the Co^{2+} ion in the oxygen octahedron. The physical relevance of our discussion to CoO is obvious - the *NaCl* structure is built up from the edge sharing Co^{2+} octahedra and the same electronic structure occurs at each Co site. The sign of the octupolar CEF parameter B_4 is directly related to the oxygen anion surroundings and can be calculated from the first principles. Its change of sign from the Co^{2+} ion to Ni^{2+} ion is related to the sign reversal of the octupolar moment of the charge cloud of the $3d^7$ and $3d^8$ configurations, seen in Stevens factor β . The value of B_4 of -30 K in CoO is fully consistent with a value of +260 K found in LaCoO_3 [14] taking into account the change of the valency and the average Co-O distance from 192 pm to 213 pm in CoO.

4. Conclusions

The orbital and spin moment of the Co^{2+} ion in CoO has been calculated within the quasi-atomic approach taking into account strong correlations, crystal-field interactions and the intra-atomic spin-orbit interactions by the same approach as we have earlier used for NiO [10], for FeBr_2 [7] and for LaCoO_3 [14]. The orbital moment of $1.39 \mu_B$ amounts at 0 K, in the magnetically-ordered state, to more than 34% of the total moment of $4.01 \mu_B$. This value is much larger than $3 \mu_B$ expected for 3 spin-holes in case of seven $3d$ electrons in the Co^{2+} ion. The presented approach explains in a very natural way the insulating state of NiO - in fact, CoO and NiO are the best insulators. Our atomic-like approach provides the discrete energy states for $3d$ electrons in CoO and calculates, apart of the spin moment, the orbital moment. Our studies indicate that it is the highest time in solid-state physics to "unquench" the orbital moment in the description of $3d$ -atom containing compounds, the more that it becomes visible in recent advanced experiments. The consistent description of the low-energy electronic structure and the ordered magnetic moment of four different compounds CoO, NiO, FeBr_2 and LaCoO_3 within the same atomistic approach we take as very strong argument for high physical adequacy of our approach pointing out the existence of discrete atomic-like states in $3d$ -atom containing compounds.

- [1] V. J. Anisimov, J. Zaanen and O. K. Anderson, Phys. Rev. B **44**, 943 (1991).
- [2] I. V Solovyev, A. I. Liechtenstein, and K. Terakura, Phys. Rev. Lett. **80**, 5758 (1998).
- [3] T. Bredow and A. R. Gerson, Phys. Rev. B **61**, 5194 (2000).
- [4] W. Jauch, M. Reehuis, H. -J. Bleif, F. Kubanek, P. Pattison, Phys. Rev. B **64**, 052102 (2001).
- [5] W. Jauch and M. Reehuis, Phys. Rev. B **65**, 125111 (2002).
- [6] R. J. Radwanski, R. Michalski, and Z. Ropka, Acta Phys. Pol. B **31**, 3079 (2000).

- [7] Z. Ropka, R. Michalski, and R. J. Radwanski, Phys. Rev. B **63**, 172404 (2001); <http://xxx.lanl.gov/abs/cond-mat/0005502>.
- [8] A. Abragam and B. Bleaney, in: *Electron Paramagnetic Resonance of Transition Ions* (Clarendon, Oxford) 1970, ch.7.
- [9] C. J. Ballhausen, in: *Ligand Field Theory* (Mc-Graw-Hill Comp.) 1962.
- [10] R. J. Radwanski and Z. Ropka, Acta Phys. Pol. A **97**, 963 (2000).
- [11] W. Neubeck, C. Vettier, F. de Bergevin, F. Yakhou, D. Mannix, L. Ranno, and T. Chatterji, J.Phys.Chem. Solids **62**, 2173 (2001).
- [12] V. Fernandez, C. Vettier, F. de Bergevin, C.Giles, W. Neubeck, Phys. Rev. B **57**, 7870 (1998).
- [13] W. Neubeck, C. Vettier, F. de Bergevin, F. Yakhou, D. Mannix, O. Bengone, M. Alouani, and A. Barbier, Phys. Rev. B **63**, 134430 (2001).
- [14] Z. Ropka and R. J. Radwanski, Phys. Rev. B **67**, 172401 (2003); <http://xxx.lanl.gov/abs/cond-mat/0301129>.

Figure captions. Fig. 1. The electronic structure of the Co^{2+} ion in CoO. a) the free-ion $4F$ term, b) the Co^{2+} ion in the purely octahedral crystal field, c) the electronic structure resulting from the octahedral crystal field and the intra-atomic spin-orbit interactions.

Fig. 2. The splitting of the ground-state Kramers doublet, shown as the lowest state in Fig. 1(c), in the magnetically-ordered state of CoO. Below T_N a spin gap opens.

Fig. 3. Temperature dependence of the Co^{2+} -ion moment in CoO. At 0 K the total moment of $4.01 \mu_B$ is built up from the orbital and spin moment of 1.39 and $2.62 \mu_B$, respectively. The calculations have been performed for the quasi-atomic parameters with the octahedral crystal-field parameter $B_4 = -30$ K, the spin-orbit coupling constant $\lambda_{s-o} = -260$ K, the intersite spin-dependent interactions given by the molecular-field coefficient $n = -42$ T/ μ_B and the tetragonal distortion parameter B_2^0 of -5 K.