

Quantum phase transition in easy-axis antiferromagnetic integer-spin chains.

Massimo Capone^{1,2}, Sergio Caprara², Luca Cataldi²¹ Enrico Fermi Center, Roma, Italy² Dipartimento di Fisica – Università di Roma "La Sapienza",
and Istituto Nazionale per la Fisica della Materia (INFM) – SMC and UdR Roma 1,
Piazzale Aldo Moro 2, I-00185 Roma, Italy

(Dated: April 14, 2024)

Antiferromagnetic Heisenberg integer-spin chains are characterized by a spin-liquid ground state with no long-range order, due to the relevance of quantum fluctuations. Spin anisotropy, however, freezes quantum fluctuations, and the system is magnetized in the presence of a sufficiently large easy-axis anisotropy. We numerically investigate the case $S = 1$, by means of the density-matrix renormalization group, and find that the freezing of the spin liquid into a Neel spin solid, with increasing easy-axis anisotropy, is a continuous quantum phase transition. Numerical evidence indicates that the transition is not in the two-dimensional Ising universality class.

PACS numbers: 75.10.Jm, 75.30.Cr, 75.40.Mg

Quantum fluctuations play a crucial role in antiferromagnetic (AFM) Heisenberg spin chains, as they are strong enough to suppress magnetic long-range order at zero temperature. Despite the common absence of a spontaneous staggered magnetization in the ground state, the physical properties are, however, different for integer and half-integer spin S [1]. Indeed, half-integer-spin chains are characterized by a gapless excitation spectrum, power-law spin-spin correlations, and a divergent linear response to a staggered magnetic field, and are therefore usually considered as nearly ordered. The spectrum of integer-spin chains is instead gapped in the thermodynamic limit, with a finite linear response to staggered magnetic fields. The ground state is a spin liquid with finite spin-spin correlation length, and the gap to the first excited state is usually called Haldane gap.

In this paper we present a numerical investigation of integer-spin (namely $S = 1$) chains, for which the presence of different energy scales makes a unified theoretical approach problematic [2]. This difficulty is mirrored by a richer variety of physical regimes with respect to half-integer-spin chains. Physical effects which freeze quantum fluctuations are expected to destroy the spin-liquid phase, possibly leading to a magnetization. In a previous paper [3] two of us focused on the freezing of the spin liquid induced by a staggered magnetic field, and found that the nature of the spin-liquid ground state entails a peculiar non-monotonic dependence of the staggered magnetization on the system size in the region of small fields (i.e., whose characteristic energy scale is smaller than the Haldane gap), and that the full freezing of quantum fluctuations into a polarized Neel "crystal" is only achieved at fields larger than the exchange coupling constant, with a large crossover region at intermediate fields.

Here, as another effect suppressing quantum fluctuations, we consider an anisotropy in the AFM coupling. Since the Haldane gap is small with respect to the exchange coupling, a small (but finite) anisotropy is ex-

pected to freeze the spin liquid. Thus a zero-temperature phase transition to an ordered phase should take place upon increasing the anisotropy. We will focus on easy-axis anisotropy: When the anisotropy is large, the system approaches the Ising limit, magnetized along the easy axis. Since the two limiting fixed points, which correspond to the disordered and fully ordered phases, are characterized by different dynamical exponents z , the issue arises of determining the evolution from the $z = 1$ (relativistically invariant) description of the spin liquid within the non-linear model in the isotropic case, toward the $z = 0$ Ising limit.

We base our analysis on the infinite-size density-matrix renormalization-group (DMRG) approach [4], which allows for a very accurate description of the ground-state properties of one-dimensional systems. We provide a complete description of the freezing of the spin-liquid with increasing anisotropy, measuring both non-universal features, such as the spontaneous staggered magnetization and the location of the transition point, and universal properties, such as the values of the critical exponents and hence the universality class of the transition. The analysis of an easy-plane anisotropy, which excludes the appearance of an order parameter, leaving the way open to a Kosterlitz-Thouless phase transition, is technically and numerically more involved, and is currently under investigation [5].

Our starting Hamiltonian is a simple modification of the Heisenberg (exchange) Hamiltonian to describe a system with easy-axis anisotropy,

$$H = J \sum_{r=1}^{X-1} S_r^z S_{r+1}^z + p \sum_{r=1}^{X-1} S_r^x S_{r+1}^x + S_r^y S_{r+1}^y + \sum_{r=1}^{X-1} (\Delta)^r S_r^z; \quad (1)$$

where $S_r = (S_r^x; S_r^y; S_r^z)$ is the spin operator on site r , S is integer, and L is the number of sites in the chain.

$J > 0$ is the AFM Heisenberg coupling, $0 \leq p \leq 1$ is the easy-axis anisotropy parameter [6], and H is the amplitude of the staggered magnetic field along the z (easy) axis, which is coupled with the staggered magnetization. As it is customary and convenient in DMRG calculations, we assume open boundary conditions. The two limiting cases $p = 1$ and $p = 0$ correspond to the Haldane spin liquid and Ising antiferromagnet respectively. It is worth noting that the model (1) is invariant for $p \rightarrow 1 - p$, so that our results equally apply to a system with a ferromagnetic coupling on the xy plane.

As discussed in [3], we find it more convenient to perform a transformation on the Hamiltonian (1) which allows us to make use of the standard implementation of DMRG [4]. After a local rotation of the reference frame, $S_r^z = (1)^x S_r^z, S_r^x = (1)^x S_r^x, S_r^y = S_r^y$, the Hamiltonian (1) is re-cast in the "ferromagnetic" form

$$\tilde{H} = \sum_{r=1}^{N-1} J \left(S_r^x S_{r+1}^x + S_r^y S_{r+1}^y \right) + \frac{p}{2} \sum_{r=1}^{N-1} S_r^z S_{r+1}^z + H \sum_{r=1}^N S_r^z; \quad (2)$$

where $S_r^x = S_r^x, S_r^y = S_r^y$ are the rising and lowering operators, and the external field H is now coupled to the uniform magnetization $S^z = \sum_r S_r^z$. The easy-axis anisotropy corresponds to $|p| < 1$, whereas the case $|p| > 1$ corresponds to an easy-plane anisotropy. In the following we refer to the properties of the transformed model described by the Hamiltonian (2), and in particular to the uniform magnetization along the easy axis, $\langle S^z \rangle$. The correspondence with the original AFM model (1) is straightforward.

Differently from the case discussed in Ref. [3], where the magnetization was forced by the external field, a spontaneous magnetization m_0 is expected to appear now, as quantum fluctuations are frozen with increasing easy-axis anisotropy. Indeed, the limiting results, $m_0 = 1$ for $p = 0$ (Ising limit), and $m_0 = 0$ for $p = 1$ (isotropic limit), suggest that m_0 should decrease with increasing p . However, contrary to the case of half-integer spin, where the system is critical at $p = 1$, and is therefore spontaneously magnetized for arbitrarily small anisotropy, here we expect that the system persists in the magnetized phase only up to a critical value $p = p_c < 1$, and the spin-liquid phase extends over a finite region $p_c \leq p \leq 1$. Since, as we discuss below, the transition is continuous (of the second order), the issue arises whether the proper dimension of the effective model at the phase transition equals or not the effective dimension of the relativistically invariant spin-liquid phase ($d_{\text{eff}} = d + z = 2$, where $d = 1$ is the spatial dimension and $z = 1$ is the dynamical exponent). It is worth noting that the two phases (magnetized and spin liquid) are both characterized by a gapped excitation spectrum, although of different origin.

The gap in the easy-axis phase is related to the discrete symmetry, whereas the Haldane gap in the spin-liquid phase is of a more subtle nature.

To characterize the ordered phase and the transition, we compute the magnetization $M(J; p; H; L; N_k) = \langle S^z \rangle$, where $\langle \cdot \rangle$ denotes the expectation value over the DMRG approximate ground-state wave function, for the system of linear size L , with N_k states retained in the density-matrix truncation procedure, and the superscript T indicates the truncated operators defined in the approximate basis. We consider the magnetization per site in units of S , $m = M/(SL)$ (we always take $S = 1$), such that $0 \leq m \leq 1$ for $H > 0$. m depends on J and H only through $h = H/J$. Starting from $m(p; h; L; N_k)$, we perform three subsequent extrapolations [7] to extract the spontaneous magnetization and the linear susceptibility:

(i) We extrapolate the finite-size results to the thermodynamic limit $L \rightarrow \infty$ for any given number of states N_k and field h by fitting the large- L behavior of the magnetization as $m(p; h; L; N_k) = m(p; h; N_k) + A/L$, where the long-living corrections are $O(1/L)$ due to the open boundary conditions. According to our previous results [3], the linear fit in $1/L$ at small field is accurate only if the size L of the chain is larger than roughly twice the characteristic length scale of the spin-liquid state ($\xi = 6.03$ in units of the lattice spacing, for $S = 1$ [8]).

(ii) Once $m(p; h; N_k)$ is obtained, we carefully check the convergence with respect to the Hilbert space, by taking the extrapolation to the limit $N_k \rightarrow \infty$ in the region where m displays a clear asymptotic dependence on $1/N_k$ [7], $m(p; h; N_k) = m(p; h) + B/N_k$. Up to $N_k = 100$ states were needed for the smallest field $h = 0.0001$, to obtain the asymptotic behavior. We emphasize that this procedure represents a direct measure of the convergence to the limit of infinite Hilbert space of the expectation values of the different observables, and is not equivalent to a small truncation error for the density matrix.

(iii) We finally obtain the spontaneous magnetization m_0 and the linear susceptibility $\chi(p)$ by means of the extrapolation for small magnetic fields $m(p; h) = m_0(p) + \chi(p)h$. All the above extrapolations are carefully checked for convergence, e.g., with respect to various extrapolation schemes, and the least-square linear fits used thereby are chi-square tested. The numerical values that we report below are affected by an error on the last digit. The error bars for the data points reported in the various figures are always smaller than the symbol size.

The change in the ground-state properties with decreasing p is already witnessed by the behavior of $m(p; h; L; N_k)$ at fixed N_k and h as a function of the system size L (not shown). Due to the presence of a finite characteristic length, a non-monotonic behavior characterizes the spin-liquid phase at $p = 1$, with a bump for $L \rightarrow \infty$ [3]. Reducing p gradually leads to a monotonic behavior as a function of L , with much larger bulk ($L \rightarrow \infty$) magnetization. The study of the spontaneous magneti-




FIG. 1: The spontaneous magnetization m as a function of the anisotropy p . The different data points refer to different values of the lowest magnetic field h_{min} used in the small-field extrapolation: $h_{min} = 0.001$ (black dots), 0.0005 (full triangles), 0.0001 (open circles), and 0.00005 (open triangles). The inset displays the same quantity in log-log plot to emphasize the power-law behavior. The dashed line is the fitting curve $m_0 = a(p_c - p)$ (see text).

ization, reported below, confirms that the change of behavior is associated with the change in the ground state from spin liquid to spontaneously magnetized.

The magnetization $m(p;h)$ increases with decreasing p at each fixed value of h , and naturally increases with the magnetic field h at each p . The dependence on h is weak at $p \neq 1$ and vanishes as $p \rightarrow 0$. The critical behavior is evident in Fig. 1, where we report $m_0(p)$ as a function of p , obtained through a zero-field extrapolation [9]. Except for a narrow region around the critical point [10], the data are well described by $m_0 = a(p_c - p)$, for $p < p_c$, and $m_0 = 0$ for $p > p_c$, with $a = 1.09$, $p_c = 0.845$, as obtained by numerically minimizing, with respect to p_c , the least-square fit of $\log m_0$, which yields an "optimum" value of a and p_c for any given p_c . The inset of Fig. 1 shows that all extrapolated points fall on the fitting curve.

We can also extrapolate the linear susceptibility $\chi(p)$ for $h \neq 0$ (see Fig. 2), finding the power-law behavior $\chi^{-1} = b(p_c - p)$ for $p < p_c$, and $\chi^{-1} = b^0(p - p_c)^0$ for $p > p_c$, once again except in a small region close to the critical point. Using for p_c the value obtained from the spontaneous magnetization, $p_c = 0.845$, and performing a least-square fit of $\log \chi^{-1}$, we find $b = 41.1$, $b^0 = 1.71$, $b^0 = 1.30$, and $\chi^0 = 1.70$. The numerical agreement of the two indices b and b^0 within numerical accuracy is a check of the reliability of our results. When studied over the entire parameter range, as a function of p , $\chi(p)$ obviously vanishes in the Ising limit ($p \rightarrow 0$), where the magnetization saturates ($m_0 \rightarrow 1$), and has a finite value in the Haldane spin-liquid phase at $p = 1$, which increases




FIG. 2: Inverse susceptibility χ^{-1} as a function of p in a log-log scale. Notations are the same as in Fig. 1. The dashed lines are the fitting curves $\chi^{-1} = b(p_c - p)$ for $p < p_c$, and $\chi^{-1} = b^0(p - p_c)^0$ for $p > p_c$ (see text).




FIG. 3: The magnetization at the critical point $p = p_c$ as a function of the magnetic field. The inset shows the same quantity in log-log scale to emphasize the critical behavior. The dashed line is the fitting curve $m(h; p = p_c) = ch^{1/c}$ (see text).

with increasing S ($\chi = 18.50$, for $S = 1$ [8]).

The exponent χ which characterizes the behavior of the magnetization as a function of the external field h at criticality, $m(h; p = p_c) = ch^{1/c}$, can be calculated by means of the scaling law $\chi = 1 + \beta/\nu$. Substituting the values of β and ν found above we obtain $\chi = 13.4$. We can compare this value with a direct measure of χ . Fig. 3 shows the data for $m(p = p_c; h)$, with $p_c = 0.845$, as a function of h . The log-log plot shows a linear behavior over three decades with a least-square exponent $\chi = 13.0$ in agreement with the one obtained from the scaling law within numerical accuracy, and $c = 0.938$.




FIG. 4: Correlation length ξ as a function of the anisotropy p . The dashed line is a guide to the eye.

Finally, by calculating the spin-spin correlation function along the easy axis $C_K(r) = \langle S_{K+3+r}^z S_{K+3+2r}^z \rangle$ ($r = 0; 1; 2; \dots$) [11], we determine the exponents ν and η which characterize the divergence of the correlation length, given by $\xi \sim (p_c - p)^{-\nu}$ for $p < p_c$, and $\xi \sim (p - p_c)^{-\eta}$ for $p > p_c$. The correlation length is obtained by fitting the long-distance behavior of the correlation function as $C_K(r) = A e^{-r/\xi} + B$, where $B = C_K(r \rightarrow \infty)$. (see Fig. 4). By fitting the data for $\log \xi$ as a function of $\log |p - p_c|$, assuming $p_c = 0.845$ as determined from the fit of the spontaneous magnetization, we find $\nu = 0.86$, $\eta = 0.45$ (fitted with 11 points) and $\nu = 0.87$, $\eta = 1.04$ (fitted with 12 points). It is worth noticing that the correlation length ξ as a function of the anisotropy parameter p is rapidly reduced to a quantity of the order of the lattice spacing as p is reduced on the Ising (ordered) side, and reaches the finite value $\xi \approx 6$ in the Haldane spin-liquid state, at $p = 1$.

Using the scaling laws, we can determine the effective dimension at the phase transition $d_{eff} = (2 + \nu)/\eta = 2.3$. We have therefore numerical evidence that the fixed-point effective model is not relativistically invariant. In the flow from the spin-liquid to the fixed point, along with the various critical exponents, also the dynamical exponent z is therefore corrected in a non-trivial way.

In summary, we have studied the role of easy-axis anisotropy in the $S = 1$ AFM spin chain by means of DMRG. Our calculations show that the freezing of the quantum fluctuations due to increasing easy-axis anisotropy at small magnetic field is much alike the one obtained with increasing field [3]. In particular the non-monotonic dependence of the magnetization m on the size of the system L observed for the isotropic chain is gradually transformed into a monotonic increase. The extrapolation to zero magnetic field reveals a quantum phase transition from a spin liquid to a spin solid at a finite value of the anisotropy parameter, $p_c = 0.845$. The values of the exponents indicate that the phase transition falls within a different universality class than the $d = 2$

Ising universality class (although quite close to it). Thus in the evolution from the spin liquid (where $d_{eff} = 2$) to the Ising antiferromagnet (where $d_{eff} = 1$), a fixed point is reached with a different effective dimensionality $d_{eff} = 2.3$ (i.e., a dynamical exponent $z = 1.3$). This result indicates that the lattice-renormalization effects and/or the less relevant coupling constants neglected in Ref. [12], play a role, even if quantitatively small, so that the critical exponents are close to, but different from, those of the two-dimensional Ising model.

We acknowledge a stimulating conversation with A. Parola, and many fruitful discussions with C. Castellani. We also acknowledge financial support of INFN /G through PA-G0-4 and of MIUR Con 2001, prot. 2001023848.

-
- [1] F. D. M. Haldane, Phys. Rev. Lett. 50, 1153 (1983).
 - [2] E. Ercolessi, G. Morandi, P. Pieri, and M. Roncaglia, Europhys. Lett. 49, 434 (2000); Phys. Rev. B 62, 14 860 (2000); A. S. G. Liebzi and A. Parola, Phys. Rev. B 64, 184439 (2001).
 - [3] M. Capone and S. Caprara, Phys. Rev. B. 64, 184418 (2001).
 - [4] S. R. White, Phys. Rev. Lett. 69, 2863 (1992); Phys. Rev. B 48, 10 345 (1993).
 - [5] L. Cataldi, S. Caprara, M. Capone, work in progress.
 - [6] p_m measures the ratio between the xy coupling ($J_{xy} = pJ$) and the coupling along the z (easy) axis ($J_z = J$), and decreases with increasing easy-axis anisotropy. A direct measure of the anisotropy is provided, e.g., by $(J_z = J_{xy})$ $1 = (1 - p)/p$, which vanishes in the isotropic limit ($p \rightarrow 1$), and diverges in the Ising limit ($p \rightarrow 0$).
 - [7] A. Juozapavicius, S. Caprara, and A. Rosengren, Phys. Rev. B 56, 11 097 (1997); A. Juozapavicius, L. Ueba, S. Caprara, and A. Rosengren, Phys. Rev. B 60, 14 771 (1999).
 - [8] J. Lou, X. Dai, S. Qin, Z. Su, and L. Yu, Phys. Rev. B 60, 52 (1999).
 - [9] We report data obtained by varying the minimum field h_{min} used in the extrapolation. The value of h_{min} is important only close to the critical point.
 - [10] The divergence of the response functions and of the correlation length at the critical point makes it impossible to numerically access a small region around it, where very long chains and small magnetic fields would be required for a good extrapolation, implying a loss of numerical accuracy and/or an increase of the computing time.
 - [11] The correlation function is calculated, as customary within DMRG [4], by first increasing the chain up to a length $2K + 2$, where K is taken reasonably large to reduce boundary effects, and then starting the calculation by fixing a spin on one of the two central sites of the chain, while the other goes further and further inside the block nearby, as DMRG iterations are continued. Convergence is checked by the overlap of the curves $C_K(r)$ at various K . We used $K = 50; 100; 150; 200$ and explored the range $0 \leq r \leq 100$ to extract the correlation length.
 - [12] H. J. Schulz, Phys. Rev. B 34, 6372 (1986).