

Nodal quasiparticles and classical phase fluctuations in d -wave superconductors

K. V. Samokhin and B. Mitrović

Department of Physics, Brock University, St. Catharines, Ontario, Canada L2S 3A1

(Dated: March 22, 2022)

We show that the nodal quasiparticles have significant effect on the classical phase fluctuations in a quasi-two-dimensional d -wave superconductor. They give rise to singularities in the temperature behavior of some of the coupling constants in the phase-only effective action. One of the consequences is that the classical XY -model is not adequate for the description of the superconducting fluctuations in d -wave superconductors at low temperatures.

PACS numbers: 74.40.+k, 74.72.-h, 74.20.Rp

In superconductors with low superfluid density ρ_s , the phase fluctuations of the order parameter can play a significant role. Emery and Kivelson [1] suggested that it is the classical phase fluctuations of the pre-formed Cooper pairs that are responsible for the pseudogap phenomenon in the underdoped high- T_c materials (HTSC's) [2]. This idea has been further elaborated by many authors, see, e.g., the review article [3]. On the other hand, it was argued in Refs. [4, 5] that the phase fluctuations in HTSC's are important down to $T \ll T_c$, which could explain a linear in T behavior of the magnetic penetration depth $\lambda(T)$ at low temperatures [6], even for a nodeless order parameter (in a superconductor with lines of nodes, a linear T -dependence of λ occurs already at the mean-field level due to the thermally excited nodal quasiparticles [7]).

The effects of the phase fluctuations in HTSC's are usually studied using either the classical or the quantum versions of the XY -model, which is believed to provide a correct description of any system with a one-component complex order parameter of fixed magnitude. The energy of the classical two-dimensional (2D) XY -model in the absence of external fields has the form

$$\mathcal{E}_{XY} = \sum_{\mathbf{r}\mathbf{r}'} J_{\mathbf{r}\mathbf{r}'} [1 - \cos(\theta_{\mathbf{r}} - \theta_{\mathbf{r}'})] \quad (1)$$

Here $J_{\mathbf{r}\mathbf{r}'}$ are the phase stiffness coefficients, and $\theta_{\mathbf{r}}$ is the phase of the order parameter at site \mathbf{r} of a coarse-grained square lattice. The lattice spacing d is of the order of the superconducting correlation length ξ , which is almost constant at low temperatures. The XY -model has also been applied to other systems, such as fabricated arrays of Josephson junctions, or granular superconductors (see, e.g., Ref. [8] and the references therein), where d is equal to the distance between grains.

Although the simplicity of the model (1) is physically appealing, it should be stressed that its rigorous microscopic derivation for homogeneous high- T_c superconductors does not exist. The usual way of justification (see, e.g., Ref. [9]) involves expanding the cosine in the continuous version of Eq. (1) and matching the coefficients with those in the Gaussian phase-only action obtained by integrating out the fermionic degrees of freedom. At low temperatures, θ varies slowly at the length scale of d and vortices can be neglected. Then, assuming the nearest-

neighbor interaction $J_{\mathbf{r}\mathbf{r}'} = J$ in Eq. (1), introducing the superfluid velocity $\mathbf{v}_s = \nabla\theta/2m$ (m is the electron mass, and we use such units that $\hbar = c = e = 1$) and expanding the cosine in powers of \mathbf{v}_s and its gradients, we obtain

$$\mathcal{E}_{XY} = \int d^2r \left\{ \frac{\rho_s}{2} \mathbf{v}_s^2 + \frac{K}{2} [(\nabla_x v_{s,x})^2 + (\nabla_y v_{s,y})^2] + \frac{B}{4} (v_{s,x}^4 + v_{s,y}^4) + \dots \right\}. \quad (2)$$

Here $\rho_s = 4m^2 J$ is the mass density of the superfluid electrons, $K = m^2 d^2 J$, and $B = -(8/3)m^4 d^2 J$. The ellipsis stands for the terms of higher order in \mathbf{v}_s or its gradients, such as $(\nabla \mathbf{v}_s)^2 \mathbf{v}_s^2$, etc. Given J and d in Eq. (1), one can easily work out the coefficients in all orders of the expansion. [If to take into account the next-nearest-neighbor interactions $J_{\mathbf{r}\mathbf{r}''}$ [10], then the tensor structure of the gradient and interaction terms in Eq. (2) will change, for example the terms proportional to $(\nabla_x v_{s,x})(\nabla_y v_{s,y})$, or $v_x^2 v_y^2$ will appear.] An important feature of the XY -model (1), (2) is that K , B and all the other expansion coefficients are *temperature-independent* at low T .

That the consistent microscopic theory fails to reproduce the quantum generalization of the XY -model has already been noticed in Ref. [11]. In this Letter, we show that the long-wavelength field theory even for the classical phase fluctuations in a d -wave superconductor at low temperatures does not have the form of Eq. (2). Briefly, the microscopic theory shows that the coefficient in front of the gradient term in the energy of fluctuations *diverges* at $T \rightarrow 0$, indicating a strongly non-local interaction of the phase fluctuations. In addition, the Taylor expansion of the energy of the phase fluctuations in powers of the uniform superfluid velocity breaks down at $T \rightarrow 0$, leading to a *non-analytical* dependence on \mathbf{v}_s . To the best of our knowledge, the non-local and non-linear effects on the phase fluctuations in high- T_c superconductors have not been emphasized before.

The starting point of our microscopic analysis is a tight-binding Hamiltonian on a 2D square crystal lattice with the “microscopic” lattice constant a :

$$H = \sum_{\mathbf{ij}} \xi_{\mathbf{ij}} c_{\mathbf{i}\sigma}^\dagger c_{\mathbf{j}\sigma} - g \sum_{\langle \mathbf{ij} \rangle} B_{\mathbf{ij}}^\dagger B_{\mathbf{ij}}. \quad (3)$$

Here $\xi_{\mathbf{ij}} = -t_{\mathbf{ij}} - \mu\delta_{\mathbf{ij}}$, $t_{\mathbf{ij}}$ is the hopping amplitude, μ

is the chemical potential, $g > 0$ is the superconducting coupling constant, and the operator $B_{\mathbf{ij}} = (c_{j\downarrow}c_{i\uparrow} - c_{j\uparrow}c_{i\downarrow})/\sqrt{2}$ creates a singlet pair of electrons at the nearest-neighbor sites $\langle \mathbf{ij} \rangle$. The sites of the crystal lattice are labelled by \mathbf{i} , in contrast to the sites of the coarse-grained lattice in Eq. (1). We assume zero external magnetic field and neglect disorder and the electron-electron interactions other than that responsible for the Cooper pairing (it can be shown that the results below for the classical phase fluctuations are not affected by the latter assumption).

Following the standard procedure, the partition function for the model (3) can be written as a Grassmann functional integral. The interaction term are then decoupled using the Hubbard-Stratonovich transformation, and the fermionic fields are integrated out. After these manipulations [12], we end up with a representation of the partition function as a functional integral over a complex bosonic field Δ which is non-zero only on the bonds between the nearest neighbors:

$$Z = \int \mathcal{D}\Delta_{\mathbf{ij}}(\tau) \mathcal{D}\Delta_{\mathbf{ij}}^*(\tau) e^{-S_{eff}[\Delta^*, \Delta]}. \quad (4)$$

Here $0 \leq \tau \leq \beta$ is the Matsubara time, $\beta = 1/T$, and the effective action is given by

$$S_{eff} = -\text{Tr} \ln \mathcal{G}^{-1} + \frac{2}{g} \int_0^\beta d\tau \sum_{\langle \mathbf{ij} \rangle} |\Delta_{\mathbf{ij}}|^2, \quad (5)$$

with

$$\mathcal{G}_{\mathbf{ij}}^{-1} = \begin{pmatrix} -\delta_{\mathbf{ij}}\partial_\tau - \xi_{\mathbf{ij}} & \Delta_{\mathbf{ij}} \\ \Delta_{\mathbf{ij}}^* & -\delta_{\mathbf{ij}}\partial_\tau + \xi_{\mathbf{ij}} \end{pmatrix}. \quad (6)$$

We use the notation Tr for the full operator trace with respect to the space-time coordinates and the Nambu indices, reserving the notation tr for the 2×2 matrix trace in the electron-hole space.

The mean-field BCS theory corresponds to a stationary and uniform saddle point of the functional integral (4). The d -wave saddle point in the momentum representation is given by $\Delta_{\mathbf{k}} = \Delta_0(T)\phi_{\mathbf{k}}$, where $\phi_{\mathbf{k}} = 2(\cos k_x a - \cos k_y a)$ is the symmetry factor. The temperature dependence of the order parameter is determined by the standard BCS self-consistency equation, generalized for the case of an anisotropic order parameter (see, e.g., Ref. [13]). Deviations from the mean-field solution can be represented in terms of the amplitude and phase fluctuations: $\Delta_{\mathbf{ij}}(\tau) = [\Delta_{\mathbf{ij}}^{(0)} + \delta\Delta_{\mathbf{ij}}(\tau)]e^{i\phi_{\mathbf{ij}}(\tau)}$, where $\Delta_{\mathbf{ij}}^{(0)}$ is the Fourier transform of $\Delta_{\mathbf{k}}$. We neglect the amplitude fluctuations because they are gapped and therefore make a negligible contribution at low temperatures. Since the number of bonds in a square lattice is twice the number of sites, one should introduce two phase fields on sites, $\theta_i(\tau)$ and $\tilde{\theta}_i(\tau)$, to describe the phase degrees of freedom. One possible parametrization is $\phi_{\mathbf{ij}} = \theta_i$ for $\mathbf{r}_j = \mathbf{r}_i + a\hat{x}$, and $\phi_{\mathbf{ij}} = \theta_i + \tilde{\theta}_i$ for $\mathbf{r}_j = \mathbf{r}_i + a\hat{y}$. As shown in Ref. [9], the fluctuations of $\tilde{\theta}$, which describe a change in the

symmetry of the order parameter from d -wave to $d + is$ -wave, can be neglected. Making a gauge transformation $\mathcal{G}_{\mathbf{ij}}^{-1} \rightarrow \tilde{\mathcal{G}}_{\mathbf{ij}}^{-1} = U_i^\dagger \mathcal{G}_{\mathbf{ij}}^{-1} U_j$, where $U = \exp[-(i/2)\theta\tau_3]$ (τ_3 is the Pauli matrix in the electron-hole space) [14], and expanding the $\text{Tr} \ln \mathcal{G}^{-1} = \text{Tr} \ln \tilde{\mathcal{G}}^{-1}$ in powers of the small temporal and spatial gradients of θ , we obtain a phase-only effective action.

Motivated by the arguments of Emery and Kivelson that the phase fluctuations in HTSC's are predominantly classical down to low temperatures, we consider in this Letter only the classical case, which corresponds to neglecting the τ -dependence of θ . The effective action then becomes $S_{eff} = \beta(\mathcal{E}_0 + \mathcal{E})$, where \mathcal{E}_0 is the mean-field energy, and \mathcal{E} is the energy of phase fluctuations. In the Gaussian approximation,

$$\mathcal{E} = \frac{1}{2} \int d^2r_1 d^2r_2 \mathcal{K}_{ij}(\mathbf{r}_1 - \mathbf{r}_2) v_{s,i}(\mathbf{r}_1) v_{s,j}(\mathbf{r}_2), \quad (7)$$

where $i, j = x, y$, and the Fourier transform of the kernel $\mathcal{K}(\mathbf{R})$ has the form

$$\mathcal{K}_{ij}(\mathbf{q}) = \rho_{s,0}\delta_{ij} - m^2\Pi_{ij}(\mathbf{q}). \quad (8)$$

To simplify the notations, from this point on we assume a quadratic band dispersion $\xi_{\mathbf{k}} = (k^2 - k_F^2)/2m^*$ with the effective mass m^* equal to the electron mass m . In Eq. (8), $\rho_{s,0} = n_0 m/a^2$ is the superfluid density at zero temperature, n_0 is the average number of electrons per site, and Π_{ij} is the current-current correlator:

$$\begin{aligned} \Pi_{ij}(\mathbf{q}) = & -2T \sum_n \int \frac{d^2k}{(2\pi)^2} v_i v_j \\ & \times \text{tr} [\mathcal{G}_0(\mathbf{k} + \mathbf{q}, \omega_n) \mathcal{G}_0(\mathbf{k}, \omega_n)]. \end{aligned} \quad (9)$$

Here $\mathcal{G}_0(\mathbf{k}, \omega_n) = (i\omega_n\tau_0 - \xi_{\mathbf{k}}\tau_3 - \Delta_{\mathbf{k}}\tau_1)^{-1}$ is the mean-field matrix Green's function, $\omega_n = (2n+1)\pi T$ is the fermionic Matsubara frequency, and $\mathbf{v} = \nabla_{\mathbf{k}}\xi_{\mathbf{k}}$ is the Fermi velocity. The energy of excitations, $E_{\mathbf{k}} = \sqrt{\xi_{\mathbf{k}}^2 + \Delta_{\mathbf{k}}^2}$, vanishes at the four gap nodes $\mathbf{k} = \mathbf{k}_n = k_F(\pm\hat{x} \pm \hat{y})/\sqrt{2}$, $n = 1 \div 4$.

At low temperatures, only the nodal excitations with $\mathbf{k} = \mathbf{k}_i + \delta\mathbf{k}$ are important, which allows one to linearize both the quasiparticle dispersion $\xi_{\mathbf{k}} = v_F\delta k_{\perp}$ and the order parameter $\Delta_{\mathbf{k}} = v_{\Delta}\delta k_{\parallel}$, where δk_{\perp} and δk_{\parallel} are the components of $\delta\mathbf{k}$ perpendicular and parallel to the Fermi surface. The anisotropy ratio v_F/v_{Δ} depends on the material and the doping level, e.g. $v_F/v_{\Delta} = 14$ and 19 in optimally doped YBCO and Bi-2212, respectively [15]. The fermionic excitations have a conical spectrum: $E_{\mathbf{k}} = \sqrt{v_F^2\delta k_{\perp}^2 + v_{\Delta}^2\delta k_{\parallel}^2}$ [16, 17]. Calculating the Matsubara sum in Eqs. (8), we find

$$\mathcal{K}_{xx}(\mathbf{q}) = \mathcal{K}_{yy}(\mathbf{q}) = \rho_{s,0} - \mathcal{K}_+(\mathbf{q}) \quad (10)$$

$$\mathcal{K}_{xy}(\mathbf{q}) = \mathcal{K}_{yx}(\mathbf{q}) = -\mathcal{K}_-(\mathbf{q}),$$

where

$$\mathcal{K}_{\pm}(\mathbf{q}) = \frac{m^2 v_F}{2\pi v_{\Delta}} T \left[s\left(\frac{\gamma_1}{T}\right) \pm s\left(\frac{\gamma_2}{T}\right) \right]. \quad (11)$$

Here

$$\gamma_{1,2}(\mathbf{q}) = \frac{1}{\sqrt{2}} \sqrt{v_F^2(q_x \pm q_y)^2 + v_\Delta^2(q_x \mp q_y)^2} \quad (12)$$

are the energies of the nodal quasiparticles with $\delta\mathbf{k} = \mathbf{q}$, and $s(x)$ is a dimensionless scaling function, which is defined by a rather cumbersome integral, whose asymptotic expansions at large and small x are

$$s(x) = \begin{cases} 2 \ln 2 + x^2/24 & , \text{ at } x \rightarrow 0 \\ \pi x/8 & , \text{ at } x \rightarrow \infty. \end{cases} \quad (13)$$

We would like to emphasize that the expressions (11) are exact in the nodal approximation, i.e. for the conical quasiparticle spectrum. In terms of \mathbf{q} , the applicability region of the nodal approximation is $\gamma_{1,2}(\mathbf{q}) \ll \Delta_0$.

At finite temperatures, the long-wavelength behavior of the kernel $\mathcal{K}(\mathbf{R})$ corresponds to the limit $\gamma_{1,2}(\mathbf{q}) \ll T$. In this case, according to Eqs. (10) and (13), the Fourier components $\mathcal{K}_{ij}(\mathbf{q})$ are analytical functions of momentum, which can be written in the following form:

$$\mathcal{K}_{xx}(\mathbf{q}) = \mathcal{K}_{yy}(\mathbf{q}) = \rho_s \left[1 - \tilde{\xi}^2(q_x^2 + q_y^2) \right] \quad (14)$$

$$\mathcal{K}_{xy}(\mathbf{q}) = \mathcal{K}_{yx}(\mathbf{q}) = -2\rho_s \tilde{\xi}^2 q_x q_y,$$

where $\rho_s(T) = \rho_{s,0} - (2 \ln 2/\pi)(m^2 v_F/v_\Delta)T$ is the mean-field superfluid mass density suppressed by the thermally excited nodal quasiparticles [17]. To leading order in $(v_\Delta/v_F)^2 \ll 1$, the characteristic length $\tilde{\xi}$ is given by

$$\tilde{\xi}(T) = \left(\frac{m^2 v_F^3}{48\pi v_\Delta \rho_s T} \right)^{1/2} = C \left(\frac{T_c}{T} \right)^{1/2} \xi_0, \quad (15)$$

where T_c is the critical temperature, $\xi_0 = v_F/2\pi T_c$ is the BCS coherence length, and $C = (\pi m^2 T_c v_F/12\rho_s v_\Delta)^{1/2}$ is almost constant at low T . For a circular Fermi surface and $T = 0$, $C = \sqrt{(\pi^2/12)(v_F/v_\Delta)(T_c/\omega_F)} \sim 1$.

The quadratic \mathbf{q} -dependence (14) implies that the kernel $\mathcal{K}(\mathbf{R})$ in real space is proportional to $\exp(-|\mathbf{R}|/\tilde{\xi})$. This behavior is similar to that of the electromagnetic response function in conventional s -wave superconductors, see e.g. Ref. [18]. An important difference however is that the characteristic length of fluctuations $\tilde{\xi}$ is now *temperature-dependent*: $\tilde{\xi}(T) \sim T^{-1/2}$ at $T \rightarrow 0$. Qualitatively, this can be attributed to the partial filling of the gap nodes by the thermally-excited quasiparticles, which creates an effective temperature-dependent s -wave gap. Note that the length $\tilde{\xi}$, defined by the gradient expansion of the current-current correlation function, Eq. (14), is different from other characteristic lengths discussed in the literature: the coherence length ξ_0 , which is the correlation length of the amplitude fluctuations, and the size of a Cooper pair ξ_{pair} , which is infinite in the d -wave case [19]. In a conventional s -wave superconductor, all three lengths are of the same order.

If the typical length scale of the phase fluctuations exceeds $\tilde{\xi}(T)$, then the energy of such fluctuations at finite temperatures in the Gaussian approximation can be written as $\mathcal{E} = (1/2)(\int d^2 R \mathcal{K}_{xx})(\int d^2 r \mathbf{v}_s^2) = (\rho_s/2) \int d^2 r \mathbf{v}_s^2$, which indeed reproduces the quadratic term in the continuum version of the XY -model (2). However, comparing the gradient terms in the XY -model (2) with the microscopic result (14), we see that they are clearly different. First, the coefficient K turns out to be *singular* at $T \rightarrow 0$. Second, the sign and the tensor structure of the gradient terms are different.

Because of the divergence of $\tilde{\xi}$, the gradient expansion of \mathcal{E} breaks down at $T \rightarrow 0$. As evident from Eqs. (10) and (13), at $T = 0$ the matrix elements $\mathcal{K}_{ij}(\mathbf{q})$ are non-analytical functions of momentum. One can therefore expect that the kernel $\mathcal{K}(\mathbf{R})$ decays algebraically at large \mathbf{R} . Indeed, calculating the Fourier integrals, we obtain

$$\mathcal{K}_\pm(\mathbf{R}) \simeq \frac{m^2}{16\pi v_\Delta^2} [f_+(\mathbf{R}) \pm f_-(\mathbf{R})], \quad (16)$$

where

$$f_\pm(\mathbf{R}) = \left[\left(\frac{R_x \pm R_y}{v_F} \right)^2 + \left(\frac{R_x \mp R_y}{v_\Delta} \right)^2 \right]^{-3/2}. \quad (17)$$

Thus, the functions $\mathcal{K}_{ij}(\mathbf{R})$ are strongly anisotropic and decay slowly, as $|\mathbf{R}|^{-3}$, along a given direction. These expressions also describe the behavior of $\mathcal{K}_{ij}(\mathbf{R})$ at finite T and at shorter distances, such that $T \ll \gamma_{1,2}(\mathbf{q}) \ll \Delta_0$. At larger distances there is a crossover to the exponential decay obtained above.

In order to go beyond the Gaussian approximation, one has to take into account the higher-order terms in the Taylor expansion of the effective action (5) in powers of $\nabla\theta$ or \mathbf{v}_s . Assuming a uniform superfluid velocity, one can derive from (5) the following *exact* expression for the energy density of fluctuations valid in all orders in \mathbf{v}_s [12]:

$$\frac{\mathcal{E}}{V} = -T \int \frac{d^2 k}{(2\pi)^2} \ln \frac{\cosh \frac{\tilde{E}_{\mathbf{k},+}}{2T} \cosh \frac{\tilde{E}_{\mathbf{k},-}}{2T}}{\cosh^2 \frac{\tilde{E}_{\mathbf{k}}}{2T}}, \quad (18)$$

where V is the system volume, $\tilde{E}_{\mathbf{k},\pm} = (\xi_{\mathbf{k},+} - \xi_{\mathbf{k},-})/2 \pm \sqrt{(\xi_{\mathbf{k},+} + \xi_{\mathbf{k},-})^2/4 + \Delta_{\mathbf{k}}^2}$ are the excitation energies affected by the superflow via the Doppler shift in the energy spectrum, $\xi_{\mathbf{k},\pm} = \xi_{\mathbf{k} \pm m\mathbf{v}_s}$. Keeping the first terms in the Taylor expansion of \mathcal{E} , we have

$$\frac{\mathcal{E}}{V} = \frac{\rho_s}{2} \mathbf{v}_s^2 + \frac{B}{4} (\mathbf{v}_s^4 + 4v_{s,x}^2 v_{s,y}^2), \quad (19)$$

where $\rho_s(T)$ is the mean-field superfluid density defined above, and $B(T) = \text{const} - 2m^2 \tilde{\xi}^2(T) \rho_s \propto T^{-1}$, to leading order in T^{-1} , with $\tilde{\xi}$ given by Eq. (15). We see that this expression does not have the form of the continuum XY -model (2), since the coupling constant B is *divergent* at $T \rightarrow 0$. The singularity of B in Eq. (19) indicates that

the Taylor expansion of the energy of fluctuations \mathcal{E} in powers of \mathbf{v}_s breaks down at low temperatures. Indeed, at $T = 0$ the \mathbf{k} -integral in Eq. (18) can be calculated, with the result

$$\frac{\mathcal{E}}{V} = \frac{\rho_{s,0}}{2} \mathbf{v}_s^2 - \frac{m^3 v_F^2}{12\sqrt{2}\pi v_\Delta} \left(|v_{s,x} + v_{s,y}|^3 + |v_{s,x} - v_{s,y}|^3 \right). \quad (20)$$

It is this non-analytical dependence that is responsible for the non-linear Meissner effect in HTSC's [20] [to see this, one should use the gauge-invariant superfluid velocity in the presence of a vector potential \mathbf{A} , $\mathbf{v}_s \rightarrow \mathbf{v}_s = (1/2m)\nabla\theta - \mathbf{A}$].

The non-linear terms in \mathcal{E} are responsible for the interaction of the thermally-excited classical phase fluctuations, which in turn will lead to a renormalization of the bare superfluid density $\rho_s(T)$. Despite the divergence of the uniform coupling constant B at $T \rightarrow 0$, it is possible to calculate the lowest-order correction to ρ_s , which turns out to be non-singular (and moreover it identically vanishes at $T = 0$ if the quantum effects are taken into account [11]). The formal reason is that the contribution of the uniform vertex vanishes because of the momentum structure of the corresponding diagrams.

In conclusion, we have shown that the effect of the d -wave nodal quasiparticles on classical phase fluctuations cannot be ignored. The microscopic derivation of a low-

temperature effective energy of the classical phase fluctuations gives a result that is very different from the XY -model. The nodal quasiparticles with conical dispersion lead to the appearance of a new, temperature-dependent, length scale ξ , whose divergence at $T \rightarrow 0$ causes both the gradient expansion and the Taylor expansion in powers of \mathbf{v}_s of the energy of fluctuations to break down. The physical origin of the first effect is the same as that of the non-local Meissner effect in d -wave superconductors [21]: since the superconducting order parameter $\Delta_{\mathbf{k}}$ has nodes on the Fermi surface, then close to the nodes anisotropic coherence length $v_F/|\Delta_{\mathbf{k}}|$ exceeds the London penetration depth λ_0 , and the local electrodynamics breaks down. The failure of the Taylor expansion is closely related to the non-linear Meissner effect [20]: the superfluid velocity acts as a pair-breaker in d -wave superconductors, creating a finite density of normal excitations even at $T = 0$. The backflow of these excitations leads to a non-analytical dependence of the electromagnetic response functions on \mathbf{v}_s . The divergence of ξ at $T \rightarrow 0$ might be cut off by the effects not included in our analysis, such as quantum fluctuations, inter-layer tunnelling, or disorder.

The authors are pleased to thank J. Carbotte for pointing out Ref. [10] and E. Sternin for useful discussions. This work was supported by the Natural Sciences and Engineering Research Council of Canada.

-
- [1] V. J. Emery and S. A. Kivelson, *Nature (London)* **374**, 434 (1995); V. J. Emery and S. A. Kivelson, *Phys. Rev. Lett.* **74**, 3253 (1995).
 - [2] T. Timusk and B. Statt, *Rep. Progr. Phys.* **62**, 61 (1999).
 - [3] V. M. Loktev, R. Quick, and S. G. Shaparov, *Phys. Rep.* **349**, 1 (2001).
 - [4] E. Roddick and D. Stroud, *Phys. Rev. Lett.* **74**, 1430 (1995).
 - [5] E. W. Carlson, S. A. Kivelson, V. J. Emery, and E. Manousakis, *Phys. Rev. Lett.* **83**, 612 (1999).
 - [6] W. N. Hardy, D. A. Bonn, D. C. Morgan, R. Liang, and K. Zhang, *Phys. Rev. Lett.* **70**, 3999 (1993).
 - [7] F. Gross *et al.*, *Z. Phys.* **64**, 175 (1986); J. Annett, N. Goldenfeld, and S. R. Renn, *Phys. Rev. B* **43**, 2778 (1991).
 - [8] C. Ebner and D. Stroud, *Phys. Rev. B* **28**, 5053 (1983).
 - [9] A. Paramekanti, M. Randeria, T. V. Ramakrishnan, and S. S. Mandal, *Phys. Rev. B* **62**, 6786 (2000).
 - [10] W. Kim and J. P. Carbotte, *Europhys. Lett.* **59**, 761 (2002).
 - [11] L. Benfatto, A. Toschi, and S. Caprara, preprint cond-mat/0302255 (unpublished).
 - [12] The details of calculations will be published separately.
 - [13] V. P. Mineev and K. V. Samokhin, *Introduction to Unconventional Superconductivity* (Gordon and Breach, London, 1999).
 - [14] Such choice of the transformation matrix U results in the invariance under $\theta_i \rightarrow \theta_i + 2\pi$ being lost. This does not lead to any consequences since we are working in the low-temperature limit and the contribution of vortices can be safely neglected.
 - [15] M. Chiao, R. W. Hill, C. Lupien, L. Taillefer, P. Lambert, R. Gagnon, and P. Fournier, *Phys. Rev.* **62**, 3554 (2000).
 - [16] P. A. Lee, *Phys. Rev. Lett.* **71**, 1887 (1993).
 - [17] P. A. Lee and X.-G. Wen, *Phys. Rev. Lett.* **78**, 4111 (1997).
 - [18] M. Tinkham, *Introduction to Superconductivity* (McGraw-Hill, New York, 1996).
 - [19] L. Benfatto, A. Toschi, S. Caprara, and C. Castellani, *Phys. Rev. B* **66**, 054515 (2002).
 - [20] S. K. Yip and J. A. Sauls, *Phys. Rev. Lett.* **69**, 2264 (1992); D. Xu, S. K. Yip, and J. A. Sauls, *Phys. Rev. B* **51**, 16233 (1995).
 - [21] I. Kosztin and A. J. Leggett, *Phys. Rev. Lett.* **79**, 135 (1997); M. Franz, I. Affleck, and M. H. S. Amin, *Phys. Rev. Lett.* **79**, 1555 (1997).