

Symmetry of Magnetically Ordered Three
Dimensional Octagonal Quasicrystals

Shahar Even-Dar Mandel and Ron Lifshitz *

School of Physics and Astronomy, Raymond and Beverly Sackler Faculty of Exact Sciences, Tel Aviv University, Tel Aviv 69978, Israel. Correspondence e-mail: ronlif@post.tau.ac.il

The theory of magnetic symmetry in quasicrystals, described in a companion paper [*Acta Crystallographica AXX* (2003) xxx-xxx], is used to enumerate all 3-dimensional octagonal spin point groups and spin space-group types, and calculate the resulting selection rules for neutron diffraction experiments.

1. Introduction

We enumerate here all three-dimensional octagonal spin groups and calculate their selection rules for neutron scattering, based on the theory developed in a companion paper (Lifshitz & Even-Dar Mandel, 2003) where we have provided the details for the extension to quasicrystals (Lifshitz, 1998) of Litvin and Opechowski's theory of spin groups (Litvin, 1973; Litvin & Opechowski, 1974; Litvin, 1977). We assume the reader is familiar with the companion paper, where we have also given experimental as well as theoretical motivation for carrying out a systematic enumeration of spin groups for quasicrystals. This is the first complete and rigorous enumeration of spin groups and calculation of selection rules for any 3-dimensional quasicrystal. Other than the pedagogical example of 2-dimensional octagonal spin groups given in the companion paper, past calculations are scarce. Decagonal spin point groups and spin space-group types in two dimensions have been listed by Lifshitz (1995) without providing much detail regarding the enumeration process. All possible lattice spin groups Γ_e for icosahedral quasicrystals have been tabulated by Lifshitz (1998) along with the selection rules that they impose, but a complete enumeration of icosahedral spin groups was not given. We intend to continue the systematic enumeration of spin groups in future publications by treating all the other common quasiperiodic crystal systems (pentagonal, decagonal, dodecagonal, and icosahedral), though we shall not provide complete details of the calculations as we do here.

Although the enumeration in three dimensions is more elaborate, it proceeds along the same lines as the two-dimensional example given in the companion paper (Lifshitz & Even-Dar Mandel, 2003). Familiarity with the calculation of ordinary (non-magnetic) octagonal space groups (Rabson *et al.*, 1991) may also assist the reader in following the calculations performed here, although knowledge of that calculation is not assumed. We begin in Sec. 2. with a description of the two rank-5 octagonal Bravais classes, a reminder of the octagonal point groups in three dimensions (summarized in Table 1), and a summary of the effect of the different point group operations on the generating vectors of the two lattice types (Table 2). In Sec. 3. we enumerate the octagonal spin point groups by noting the restrictions (summarized in Table 3), imposed on their generators due to the isomorphism between $G=G$ and $\Gamma=\Gamma_e$. We then proceed to calculate the phase functions associated with the generators

of the spin point groups by making use of the group compatibility condition

$$8(g; \cdot; \cdot; \cdot) 2 G : \Phi_{gh}(\mathbf{k}) = \Phi_g(h\mathbf{k}) + \Phi_h(\mathbf{k}) : \quad (1)$$

We begin this in Sec. 4. by calculating the gauge-invariant phase functions $\Phi_e(\mathbf{k})$ associated with the lattice spin group Γ_e . We then choose a gauge by a sequence of gauge-transformations which we describe in Sec. 5.. We complete the calculation of the remaining phase functions, separately for each octagonal point group, in Sec. 6.. The resulting spin space groups are listed, by point group and lattice type, in Tables 4–19, using a generalized format in which we do not explicitly identify the spin-space operations that are paired with the generators of the point group. In Sec. 7. we complete the enumeration, by making this explicit identification, and introduce the notation used for octagonal spin space groups. The actual identification of spin-space operations is given in Appendix B. which is not included in this publication but can be obtained via... [PRODUCTION EDITOR: please indicate how one can obtain this appendix.]. We conclude in Sec. 8. by calculating the selection rules for neutron diffraction experiments, imposed by the different octagonal spin space-groups, which are summarized in Tables 20–24.

2. Background for the enumeration

2.1. Three dimensional octagonal Bravais classes

Recall that all rank-5 octagonal lattices in three dimensions fall into two Bravais classes (Mermin *et al.*, 1990). Lattices of both types contain a two-dimensional rank-4 *horizontal* sublattice in the plane perpendicular to the unique *vertical* 8-fold axis. The horizontal sublattice can be generated by four wave vectors $\mathbf{b}^{(1)} :: \mathbf{b}^{(4)}$ of equal length, separated by angles of $\frac{\pi}{4}$ (as shown in Fig. 1). Throughout the paper we denote horizontal generating vectors and their negatives by $\mathbf{b}^{(i)}$, where the index i is taken modulo 8, and $\mathbf{b}^{(i)} = -\mathbf{b}^{(i-4)}$ if $i = 5; 6; 7$; or 8.

If the fifth generating vector $\mathbf{c}$ —which must be out of the horizontal plane—is parallel to the 8-fold axis, the lattice is called a *vertical lattice* or *V-lattice* (also called a primitive or *P-lattice*). In this case we write $\mathbf{c} = \mathbf{z}$, to emphasize that it is parallel to the 8-fold axis, and call $\mathbf{c}$ a *vertical stacking vector*, since the *V-lattice* can be viewed as a vertical stacking of horizontal planes containing 2-dimensional rank-4 octagonal lattices.

research papers

If the fifth generating vector $\mathbf{c}$ contains both a vertical component $\mathbf{z}$ and a non-zero horizontal component $\mathbf{h}$, then it is called a *staggered stacking vector*, and the lattice is called a *staggered lattice*, or *S-lattice*. One can show (Mermin *et al.*, 1990) that to within a rotation of the lattice, or the addition of a horizontal lattice vector, the horizontal shift can be taken to have the form

$$\mathbf{h} = \frac{1}{2} \mathbf{b}^{(1)} + \mathbf{b}^{(2)} + \mathbf{b}^{(3)} - \mathbf{b}^{(4)} : \quad (2)$$

As shown in Fig. 1, $\mathbf{h}$ lies halfway between the generating vectors $\mathbf{b}^{(1)}$ and $\mathbf{b}^{(2)}$. Both lattice types are periodic along the vertical axis with a period of one layer for *V*-lattices and two layers for *S*-lattices.

2.2. Three dimensional octagonal point groups and their generators

There are seven octagonal point groups (geometric crystal classes) in three dimensions, one of which ($8m2$) has two distinct orientations with respect to both types of octagonal lattices, giving rise to the eight octagonal arithmetic crystal classes, listed in the first column of Table 1. The point group generators, listed in the second column of the Table, are an 8-fold rotation r_8 , an 8-fold roto-inversion $\bar{r}_8 = ir_8$ (where i is the three-dimensional inversion), a horizontal mirror h whose invariant plane is perpendicular to the the 8-fold axis, a vertical mirror m whose invariant plane includes the 8-fold axis, and a 2-fold (dihedral) axis d perpendicular to the the 8-fold axis. The effect of these point group operations on the generating vectors of the two lattice types are summarized in Table 2.

As shown in Fig. 1, the invariant planes of the vertical mirrors and the axes of the 2-fold rotations can be oriented either along (labeled m and d) or between (labeled m^0 and d^0) the 8-fold star, formed by the generating vectors of the octagonal horizontal sublattice and their negatives. The point group $8m2$ has four mirrors and four 2-fold axes. If the mirrors are of type m (along the star vectors) and the dihedral axes are of type d^0 (between them) it is denoted by $8m2$. If the mirrors are of type m^0 (between the star vectors) and the dihedral axes are of type d (along the star vectors) the point group is denoted by $82m$.

3. Enumeration of spin point groups

As generators of the spin point group G_S we take the generators of the point group G , and combine each one with a representative spin-space operation from the coset of Γ_e with which it is paired, as listed in the second column of Table 1. The spin-space operation paired in the spin point group with the 8-fold generator r_8 or $\bar{r}_8$ is denoted by σ , the operation paired with the vertical mirror m by τ , the operation paired with the horizontal mirror h by ρ , and the spin-space operation paired with the dihedral rotation d is denoted by ϕ . To these generators we add as many generators of the form $(e; i)$ as required, where i are the generators of Γ_e (three at the most).

We begin by listing in Table 3 all the normal subgroups G of the seven octagonal point groups, along with the resulting quotient groups $G=G$. The constraints on the operations σ , τ , ρ , and ϕ due to the isomorphism between $G=G$ and $\Gamma=\Gamma_e$, are

summarized in the last column of Table 3. The actual identification of these spin-space operations is done at the last step of the enumeration process, as described in Sec. 7..

4. Enumeration of lattice spin groups Γ_e

We calculate the phase functions $\Phi_e(\mathbf{k})$, associated with elements in the lattice spin group Γ_e —keeping in mind that Γ_e is abelian, and that no two phase functions $\Phi_e(\mathbf{k})$ are identical—by finding the solutions to the constraints imposed on these phase functions by all the other elements $\in \Gamma$,

$$\sigma \in \Gamma_e; (g; \sigma) \in G_S: \Phi_e(\mathbf{k}) = \Phi_e^{-1}(g\mathbf{k}); \quad (3)$$

by applying the group compatibility condition (1) to the relation $geg^{-1} = e$, where g is one of the point group generators r_8 , $\bar{r}_8$, m , h , and d . The constraints imposed by the different operations are calculated in Appendix A. of this paper which can be obtained via.... [PRODUCTION EDITOR: please indicate how one can obtain this appendix.].

The results of these calculations are used below to enumerate the lattice spin groups and calculate their phase functions. We also introduce a notation—to be used in the final spin space-group symbol—that encodes the the values of these phase functions. In this notation the symbol of the lattice spin group Γ_e is added as a superscript over the lattice symbol (unless Γ_e is 1 or 1^0). In addition, for each spin-space operation σ in the symbol for Γ_e (with one exception when these operations are $2_{\bar{x}}$ and $2_{\bar{y}}$, as noted below) we add a subscript to the lattice symbol describing the sublattice of L , defined by all wave vectors $\mathbf{k}$ for which $\Phi_e(\mathbf{k}) = 0$, with an additional index whenever this sublattice does not uniquely describe the phase function. The results of this section are summarized in the left-hand sides of Tables 20–23 and in the headings of Table 24.

There are a few cases in which the zeros of the phase functions, associated with the operations $2_{\bar{x}}$ and $2_{\bar{y}}$, define a pair of rank-5 *tetragonal* sublattices related by an 8-fold rotation. Each wave vector in these tetragonal sublattices can be decomposed into the sum of two vectors, one belonging to a 3-dimensional rank-3 tetragonal lattice of type P or I , and the second belonging to a 2-dimensional rank-2 square lattice. If the squares of the rank-2 lattice are aligned along the same directions as the squares of the rank-3 lattice then we denote the combined rank-5 lattice by $P+p$ or $I+p$; if they are aligned along the diagonals of the rank-3 lattice we denote the combined rank-5 lattice by $P-p$ (a lattice that does not occur here) or $I-p$. This is somewhat of an *ad hoc* notation for rank-5 tetragonal lattices as compared, for example, with the notation used by Lifshitz & Mermin (1994) in their enumeration of the analogous hexagonal and trigonal lattices of arbitrary finite rank. Nevertheless, it is more compact and sufficient for our current purpose. Since the pair of sublattices, associated with the operations $2_{\bar{x}}$ and $2_{\bar{y}}$, are identical (to within an 8-fold rotation), and the different assignments of the two sublattices to the two operations are scale equivalent, we denote their symbol only once.

In all that follows we write $\Phi_g(\mathbf{h}^{(i)})$ $abcd$ instead of fully writing $\Phi_g(\mathbf{h}^{(1)})$ a , $\Phi_g(\mathbf{h}^{(2)})$ b , $\Phi_g(\mathbf{h}^{(3)})$ c , and $\Phi_g(\mathbf{h}^{(4)})$ d ; we write $\Phi_g(\mathbf{h}^{(i)}\mathbf{c})$ $abcde$ to indicate in addition

that $\Phi_g(\mathbf{c}) = e$; and occasionally, if the four phases on the horizontal generating vectors are equal to a we write $\Phi_g(\mathbf{b}^{(i)}) = a$ or $\Phi_g(\mathbf{b}^{(i)}|\mathbf{c}) = a$.

4.1. $\Gamma_e = 1$

The trivial lattice spin group is always possible. In this case every operation in G is paired with a single operation in Γ . The lattice symbol remains the same as for nonmagnetic space groups: P for vertical lattices, and S for staggered lattices.

4.2. $\Gamma_e = 2; 2^0; 1^0$

Let σ denote the single generator (2 , 2^0 , or 1^0) of Γ_e . Since σ commutes with all elements of Γ we can infer the possible values of the phase function Φ_e from results R2, M1, D1, and H1 of Appendix A.. We find that for all point groups G

$$\Phi_e(\mathbf{b}^{(i)}|\mathbf{c}) = \begin{cases} 0\frac{1}{2}; \frac{1}{2}0; \text{ or } \frac{1}{2}\frac{1}{2} & \text{V-lattice;} \\ 0\frac{1}{2} & \text{S-lattice;} \end{cases} \quad (4)$$

Because σ is an operation of order 2, the zeros of its phase function define a sublattice of index 2 in L . Let us express an arbitrary wave vector in L as $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$. The zeros of the first solution $\Phi_e(\mathbf{b}^{(i)}|\mathbf{c}) = 0\frac{1}{2}$ define a vertical octagonal sublattice, containing all wave vectors with even l , or simply all the even layers of L , whether L is a V-lattice or an S-lattice. This solution is denoted on the two lattice types by P_{2c} and S_P , respectively. The second solution $\Phi_e(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}0$ on the V-lattice defines a vertical octagonal sublattice, containing all vectors with even n_i , and is denoted by P_P . The third solution $\Phi_e(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}\frac{1}{2}$ on the V-lattice defines a staggered octagonal sublattice, containing all vectors with even $n_i + l$, and is denoted by P_S . If $\sigma = 1^0$ it is omitted from the symbols, yielding the same symbols used for the so-called magnetic (or black-and-white) space groups (Lifshitz, 1997). The possible phase functions for $\Gamma_e = 2; 2^0; 1^0$ are summarized in the left-hand side of Table 20.

4.3. $\Gamma_e = 21^0$

Here Γ_e contains three operations of order 2 that commute with all the elements of Γ . For V-lattices, there are $3! = 6$ distinct ways of assigning the three different solutions (4) to the three phase functions of these operations. These are denoted by $P_{2cP}^{21^0}$, $P_{PS}^{21^0}$, $P_{S2c}^{21^0}$, $P_{P2c}^{21^0}$, $P_{SP}^{21^0}$, and $P_{2cS}^{21^0}$, where the first subscript denotes the sublattice defined by the phase function Φ_e^2 , and the second subscript denotes that of Φ_e^1 . These solutions are summarized in the left-hand side of Table 21.

For S-lattices Γ_e cannot be 21^0 , because there is only one solution in (4), and therefore there can be only one operation in Γ_e that commutes with all elements of Γ .

4.4. $\Gamma_e = 222; 2^0 2^0 2^0$

We generate Γ_e by $2_{\bar{x}}$ ($2_{\bar{x}}$ or $2_{\bar{x}}^0$) and $2_{\bar{y}}$ ($2_{\bar{y}}$ or $2_{\bar{y}}^0$), noting that in the case of $\Gamma_e = 2^0 2^0 2^0$ the unprimed 2-fold rotation defines the direction of the $\bar{z}$ axis in spin space.

For vertical lattices we see from results M3, D3, and H3 of Appendix A. that the operations σ , τ , and ρ , paired with m ,

d , and h if they are in the point group, must all commute with $2_{\bar{x}}$ and $2_{\bar{y}}$. It only remains to check whether σ , paired with the 8-fold generator, commutes with the generators of Γ_e .

If σ commutes with $2_{\bar{x}}$ and $2_{\bar{y}}$ then again, as in the previous section, we have three operations in Γ_e that commute with all the elements of Γ , implying that Γ is orthorhombic and not tetragonal. The difference between this case and that of the previous section is that here different solutions can be related by scale transformations that reorient the directions of the spin-space axes. For $\Gamma_e = 222$, all three operations are equivalent so we can define the directions of the spin-space axes such that

$$\Phi_e^{2_{\bar{x}}}(\mathbf{b}^{(i)}|\mathbf{c}) = 0\frac{1}{2}; \Phi_e^{2_{\bar{y}}}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}0; \Phi_e^{2_{\bar{z}}}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}\frac{1}{2}; \quad (5)$$

and denote the lattice spin group and its associated phase functions by P_{2cP}^{222} . Any permutation of the three subscripts in the symbol yields an alternative setting for the same scale-equivalence class of solutions.

For $\Gamma_e = 2^0 2^0 2^0$, only the two primed rotations are equivalent, so we have three distinct solutions, where we choose the directions of the $\bar{x}$ and $\bar{y}$ axes in spin space such that the phase function associated with $2_{\bar{y}}^0$ is 1=2 on the horizontal generating vectors,

$$\begin{aligned} 1: & \Phi_e^{2_{\bar{x}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = 0\frac{1}{2}; \Phi_e^{2_{\bar{y}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}0; \Phi_e^{2_{\bar{z}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}\frac{1}{2}; \\ 2: & \Phi_e^{2_{\bar{x}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = 0\frac{1}{2}; \Phi_e^{2_{\bar{y}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}\frac{1}{2}; \Phi_e^{2_{\bar{z}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}0; \\ 3: & \Phi_e^{2_{\bar{x}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}0; \Phi_e^{2_{\bar{y}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}\frac{1}{2}; \Phi_e^{2_{\bar{z}}^0}(\mathbf{b}^{(i)}|\mathbf{c}) = 0\frac{1}{2}; \end{aligned} \quad (6)$$

These three solutions are denoted by $P_{2cP}^{2^0 2^0 2^0}$, P_{2cS}^{222} , and P_{PS}^{222} , respectively. Their scale-equivalent forms are obtained by exchanging the first two subscripts: $P_{P2c}^{2^0 2^0 2^0}$, P_{S2c}^{222} , and P_{SP}^{222} .

If σ is a 4-fold rotation or a 2-fold diagonal rotation (requiring Γ to be tetragonal) such that $2_{\bar{x}}^{-1} = 2_{\bar{y}}$ then according to result R4 there are two solutions for the phase functions

$$\Phi_e^{2_{\bar{x}}}(\mathbf{b}^{(i)}|\mathbf{c}) = 0\frac{1}{2}0\frac{1}{2}c; \Phi_e^{2_{\bar{y}}}(\mathbf{b}^{(i)}|\mathbf{c}) = \frac{1}{2}0\frac{1}{2}0c; \quad c = 0 \text{ or } \frac{1}{2}; \quad (7)$$

These are interesting solutions in which the horizontal planes of the sublattices, defined by the zeros of the phase functions associated with the operations $2_{\bar{x}}$ and $2_{\bar{y}}$, contain all vectors $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$ from L with even $n_2 + n_4$, and even $n_1 + n_3$, respectively. Consequently the two sublattices are not octagonal, but rather a pair of tetragonal lattices of rank 5, related to each other by an 8-fold rotation. As described in the introduction to this section, we denote the lattice spin groups in this case by $P_{PcP}^{2^2 2^2 2^2}$ ($c = 0$) and $P_{PcP}^{2^2 2^2 2^2}$ ($c = 1=2$). Note that in both cases the sublattice defined by the zeros of the phase function of $2_{\bar{z}}$ is an octagonal V-lattice with a thinned-out horizontal plane.

All these solutions on the V-lattice are valid for all octagonal point groups because other generators of Γ , if they exist, impose no further restrictions on the phase functions above.

On staggered lattices (from results R2, M1, and D1 of Appendix A.) only a single 2-fold operation can commute with

research papers

, , or that are paired with the 8-fold generator, the mirror m , and the dihedral rotation d , respectively. These operations therefore necessarily exchange the two generators of Γ_e , requiring Γ to be tetragonal. On the other hand, (from result H3 of Appendix A.) which is paired with h necessarily commutes with the two generators of Γ_e . If these conditions are satisfied then for all point groups the directions of the $\bar{x}$ and $\bar{y}$ axes in spin space can be chosen so that there is a single solution for the phase functions,

$$\Phi_e^{2\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}0; \Phi_e^{2\bar{y}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}\frac{1}{2}; \quad (8)$$

The sublattices defined by the zeros of these two phase functions are rank-5 tetragonal lattices of type $I-p$. One has the rank-3 I -lattice oriented in the directions of the x - and y -axes and the other has the rank-3 I lattice oriented along the diagonal directions. The sublattice defined by the zeros of the phase function of $2\bar{z}$ is an octagonal V -lattice. The lattice spin group is therefore denoted by $S_{I-p}^{2\bar{z}}$.

The possible phase functions for $\Gamma_e = 222;2^02^0$ are summarized in the left-hand side of Table 22.

4.5. $\Gamma_e = 2^02^02^0 = 2221^0$

We choose to generate Γ_e using the three primed rotations and note that since Γ_e has three 2-fold operations ($2\bar{z}$, $2\bar{y}$, and 0) that commute with all elements of Γ , the lattice must be vertical. Furthermore, since there can be no more than 3 operations that commute with , all other 2-fold operations in $\Gamma_e = 2^02^02^0$, including the two generators $2\bar{x}$ and $2\bar{y}$, cannot commute with (requiring Γ to be tetragonal). The operations , , and must commute with all operations in Γ_e .

If all these conditions are satisfied then the phase functions for $2\bar{x}$ and $2\bar{y}$ have the same two solutions given in Eq. (7) for $\Gamma_e = 2^02^02^0$. In both of these solutions $\Phi_e^{2\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}0$. This leaves two possibilities for the phase function of the third generator of Γ_e ,

$$\Phi_e^{2\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = 0\frac{1}{2} \text{ or } \frac{1}{2}\frac{1}{2}; \quad (9)$$

giving a total of four distinct solutions for the phase functions of $\Gamma_e = 2^02^02^0$ on the V -lattice, denoted by $P_{P+p,2c}^{2^02^02^0}$, $P_{P+p,S}^{2^02^02^0}$, $P_{P+p,2c}^{2^02^02^0}$, and $P_{P+p,S}^{2^02^02^0}$ (and none on the S -lattice). These solutions are summarized in the left-hand side of Table 23.

4.6. $\Gamma_e = n;n^0;n1^0$ ($n > 2$)

These lattice spin groups contain a single generator of order $N > 2$, where $N = n$ unless $\Gamma_e = n^0$ and n is odd, in which case $N = 2n$. Note that if n is odd then $n1^0$ need not be considered because it is the same as n^0 . For operations of order N it follows from the group compatibility condition (1) that

$$\Phi_e^N(\mathbf{k}) = N\Phi_e(\mathbf{k}) \pmod{0} \Rightarrow \Phi_e(\mathbf{k}) = \frac{j}{N}; \quad j = 0;1;\dots;N-1; \quad (10)$$

For vertical lattices we find from result R3 of Appendix A. that if the 8-fold generator is r_8 then , paired with it, must commute with , and if it is $\bar{r}_8$ then must be a perpendicular

2-fold rotation taking to 1 . Furthermore, we find from results M2, D2, and H2 of Appendix A. that (paired with m) must commute with , and and (paired with d and h) must both be perpendicular 2-fold rotations. If these conditions are satisfied whenever these operations are in the point group then

$$\Phi_e(\mathbf{b}^{(i)}\mathbf{c}) = \begin{cases} aaaa & N \text{ even;} \\ 0000 & N \text{ odd;} \end{cases} \quad (11)$$

where a is either 0 or 1=2. The only constraint on the phase $\Phi_e(\mathbf{z})$ comes from the requirement that is an operation of order N . If the in-plane phases are 0 then $\Phi_e(\mathbf{z}) = j/N$, where j and N must be co-prime, otherwise the true denominator is smaller than N , and consequently the order of is smaller than N . If the in-plane phase $a = 1=2$ and N is twice an even number, then j and N must still be co-prime, but if N is twice an odd number then j may be also even and would still be an operation of order N . This is so because even though the phase of $^{N=2}$ is zero on the stacking vector it is 1=2 on the horizontal generating vector, and therefore $^{N=2} \notin$.

To summarize, for $\Gamma_e = n$ (odd or even n) or $\Gamma_e = n^0;n1^0$ (even n) the possible solutions for the phase function $\Phi_e^{n\bar{z}}$ are

$$\Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) \geq \begin{cases} 0\frac{j}{n} & n \text{ odd;} \\ 0\frac{j}{n}; \frac{1}{2}\frac{j}{n} & n \text{ twice even;} \\ 0\frac{j}{n}; \frac{1}{2}\frac{j}{n}; \frac{1}{2}\frac{2j}{n} & n \text{ twice odd;} \end{cases} \quad (12)$$

where in all cases j and n are co-prime. The first subscript in the symbols for the three distinct solutions for $\Phi_e^{n\bar{z}}$ are n_jc for $\Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = 0\frac{j}{n}$, n_jS for $\Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}\frac{j}{n}$, and $(\frac{n}{2})_jP$ for $\Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}\frac{2j}{n}$. The index j is necessary here because the sublattices defined by the zeros of these phase functions do not depend on j , and therefore it must be specified in addition to specifying the sublattice symbol.

For $\Gamma_e = n^0$ with odd n the order of the generator is $2n$ and the possible solutions are

$$\Phi_e^{n^0}(\mathbf{b}^{(i)}\mathbf{c}) = 0\frac{j}{2n}; \frac{1}{2}\frac{j}{2n}; \frac{1}{2}\frac{j}{n} \quad n \text{ odd;} \quad (13)$$

where j and $2n$ are co-prime. The symbols for these three types of lattice spin groups are $P_{(2n)j,c}^{n^0}$, $P_{(2n)j,S}^{n^0}$, and $P_{n_j,P}^{n^0}$. Finally, for $\Gamma_e = n1^0$ (n necessarily even), we need to find the possible solutions for the phase function associated with the second generator 0 . Since the phase function $\Phi_e^{2\bar{z}}$ is determined by the phase function $\Phi_e^{n\bar{z}}$ we are left with only two possible solutions for the phase function Φ_e^0 . If n is twice even then we always have

$$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}0 \text{ or } \frac{1}{2}\frac{1}{2}; \quad (14)$$

thus obtaining a total of four solutions denoted $P_{n_jc,P}^{n1^0}$, $P_{n_jc,S}^{n1^0}$, $P_{n_jS,P}^{n1^0}$, and $P_{n_jS,S}^{n1^0}$. If n is twice odd then the possible solutions depend on $\Phi_e^{n\bar{z}}$ as follows:

$$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c}) \geq \begin{cases} \frac{1}{2}0 \text{ or } \frac{1}{2}\frac{1}{2} & \Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = 0\frac{j}{n}; \\ 0\frac{1}{2} \text{ or } \frac{1}{2}0 & \Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}\frac{j}{n}; \\ \frac{1}{2}\frac{1}{2} \text{ or } 0\frac{1}{2} & \Phi_e^{n\bar{z}}(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}\frac{2j}{n}; \end{cases} \quad (15)$$

giving a total of six solutions denoted by $P_{n_j c \mathcal{P}}^{n1^0}$, $P_{n_j c \mathcal{S}}^{n1^0}$, $P_{n_j S 2c}^{n1^0}$, $P_{n_j S \mathcal{P}}^{n1^0}$, $P_{(\frac{n}{2})_j \mathcal{P} \mathcal{S}}^{n1^0}$, and $P_{(\frac{n}{2})_j \mathcal{P} 2c}^{n1^0}$.

On staggered lattices we first note that Γ_e cannot be $n1^0$ which contains three operations of order 2 that commute with all the elements of Γ . Furthermore, we find from the results of the previous sections that (paired with h if it is in G) must be a 2-fold rotation perpendicular to the axis of and that two possibilities exist for the remaining generators of Γ :

(1) If the 8-fold generator is r_8 then , paired with it, must commute with , and if it is $\bar{r}_8$ then must be a perpendicular 2-fold rotation taking to 1 . The operation (paired with m) must commute with , and (paired with d) must be a perpendicular 2-fold rotation. If these conditions are satisfied whenever these operations are in G then the in-plane phases are all 0. For $\Gamma_e = n$ (either parity) and $\Gamma_e = n^0$ (even n) the possible solutions for the phase function $\Phi_e^{n^0}$ are therefore

$$\Phi_e^{n^0}(\mathbf{b}^{(i)} \mathbf{c}) = 0 \frac{j}{n}; \quad (16)$$

where j and n are co-prime. These are denoted by $S_{n_j c}^n$. For $\Gamma_e = n^0$ with odd n the order of the generator is $2n$ and the possible solutions are

$$\Phi_e^{n^0}(\mathbf{b}^{(i)} \mathbf{c}) = 0 \frac{j}{2n}; \quad (17)$$

where j and $2n$ are co-prime. These are denoted by $S_{2n_j c}^{n^0}$.

(2) If the 8-fold generator is $\bar{r}_8$ then , paired with it, must commute with , and if it is r_8 then must be a perpendicular 2-fold rotation taking to 1 . The operation (paired with d) must commute with , and (paired with m) must be a perpendicular 2-fold rotation. If these conditions are satisfied whenever these operations are in G then $n = 4$ and the possible solutions for the phase function $\Phi_e^{4^0}$ are

$$\Phi_e^{4^0}(\mathbf{b}^{(i)} \mathbf{c}) = \frac{1}{2} \frac{1}{4} \text{ or } \frac{1}{2} \frac{3}{4}; \quad (18)$$

denoted by $S_{4_1 S}^4$ and $S_{4_3 S}^4$.

The possible phase functions for $\Gamma_e = n; n^0; n1^0$ ($n > 2$) are summarized in the headings of Table 24.

5. Initial choice of gauge

Before starting the actual calculation of phase functions for the generators of the different octagonal point groups, we make an initial choice of gauge that (i) sets the phases $\Phi_{g_8}(\mathbf{b}^{(i)})$ to zero, where g_8 is the 8-fold generator— r_8 for point groups 8, $8mm$, 822 , $8=m$, and $8=mmm$, or $\bar{r}_8$ for 8, $8m2$, and $82m$; and (ii) sets the phase $\Phi_g(\mathbf{c})$ to zero for one generator satisfying $g\mathbf{z} = \mathbf{z}$.

5.1. Setting $\Phi_{g_8}(\mathbf{b}^{(i)})$ to zero

We can make $\Phi_{g_8}(\mathbf{b}^{(i)}) = 0$ with a gauge transformation given by

$$_1(\mathbf{b}^{(i)}) = \frac{1}{2} \Phi_{g_8}(\mathbf{b}^{(i)}) - \mathbf{b}^{(i+1)} + \mathbf{b}^{(i+2)} - \mathbf{b}^{(i+3)}; \quad (19)$$

where the upper signs are for $g_8 = r_8$ and the lower signs for $g_8 = \bar{r}_8$, and the value of $_1(\mathbf{c})$ is unimportant. Using this gauge function we obtain

$$\Delta \Phi_{g_8}(\mathbf{b}^{(i)}) = _1(g_8 \mathbf{b}^{(i)} - \mathbf{b}^{(i)}) - _1(\mathbf{b}^{(i+1)} - \mathbf{b}^{(i)}) = \frac{1}{2} \Phi_{g_8}(\mathbf{b}^{(i+4)} - \mathbf{b}^{(i)}) - \Phi_{g_8}(\mathbf{b}^{(i)}) \quad (20)$$

thereby setting $\Phi_{g_8}(\mathbf{b}^{(i)})$ to zero.

5.2. Setting $\Phi_g(\mathbf{c})$ to zero when $g\mathbf{z} = \mathbf{z}$

We apply a second gauge transformation to set $\Phi_g(\mathbf{c})$ to zero for a single $g \in G$ for which $g\mathbf{z} = \mathbf{z}$. We use this transformation for the operation $\bar{r}_8$ when G is 8, $82m$, or $8m2$, and for the operations d when G is 822 , and h when G is $8=m$ or $8=mmm$. For both lattice types we take

$$_2(\mathbf{b}^{(i)}) = 0; \quad _2(\mathbf{c}) = \frac{1}{2} \Phi_g(\mathbf{c}); \quad (21)$$

from which we get, for vertical lattices

$$\Delta \Phi_g(\mathbf{z}) = _2(g\mathbf{z} - \mathbf{z}) - _2(\mathbf{z} - 2\mathbf{z}) = \Phi_g(\mathbf{z}) \quad (22)$$

and for staggered lattices

$$\Delta \Phi_g(\mathbf{z} + \mathbf{h}) = _2(g(\mathbf{z} + \mathbf{h}) - (\mathbf{z} + \mathbf{h})) - _2((\mathbf{z} + \mathbf{h}) - (g\mathbf{h} + \mathbf{h})) = \Phi_g(\mathbf{z} + \mathbf{h}); \quad (23)$$

where the last equality is due to the fact that the vector $g\mathbf{h} + \mathbf{h}$ is in the horizontal plane where $_2$ is zero. Also note that since $_2$ is zero on the horizontal sublattice it does not affect the phases that were set to zero in the previous section.

5.3. Remaining gauge freedom

We still remain with some freedom to perform a third gauge transformation without undermining the effect of the previous two gauge transformations. Such a transformation can be performed with a gauge function $_3$ satisfying

$$\Delta \Phi_{g_8}(\mathbf{b}^{(i)}) = _3(g_8 \mathbf{b}^{(i)} - \mathbf{b}^{(i)}) = 0; \quad (24)$$

and

$$\Delta \Phi_g(\mathbf{c}) = _3(g\mathbf{c} - \mathbf{c}) = 0; \quad (25)$$

where g is the operation chosen in the previous section. The first condition, for all point groups and both lattice types, requires $_3$ to have the same value of 0 or 1=2 on all the horizontal generating vectors. For point groups 8 and $8mm$, where the second gauge transformation $_2$ is not used, there is no constraint on the value of $_3(\mathbf{c})$. For the remaining point groups we must consider the two lattice types separately. For V -lattices $g\mathbf{c}$ in Eq. (25) is $\mathbf{c}$ and therefore $_3(\mathbf{c}) = 0$ or 1=2 independently of its value on the horizontal generating vectors. Thus, on V -lattices one must check for gauge equivalence of solutions to the group compatibility conditions using the three non-trivial gauge functions

$$_3(\mathbf{b}^{(i)} \mathbf{c}) = 0 \frac{1}{2}; \frac{1}{2} 0; \text{ or } \frac{1}{2} \frac{1}{2}; \quad (26)$$

research papers

For S -lattices, using Table 2, and the fact that $\mathbf{z} \cdot 2\mathbf{h} = 0$, we find that we may still perform gauge-transformations using the gauge functions

$$\mathbf{z} \cdot \mathbf{h}^{(i)} \mathbf{c} = \begin{cases} 0\frac{1}{2}; \frac{1}{2}0; \text{ or } \frac{1}{2}\frac{1}{2}; & G = \bar{8}m; \bar{8}mmm; \\ 0\frac{1}{2}; \frac{1}{2}\frac{1}{4}; \text{ or } \frac{1}{2}\frac{3}{4}; & G = \bar{8}; \bar{8}m2; \bar{8}2m; 822; \end{cases} \quad (27)$$

6. Determination of phase functions for the different octagonal point groups

Further calculations of phase functions are carried out for each point group G separately, based on its specific generating relations. Two typical relations appear in most of the point groups. All 2-fold generators ($g; \cdot$) $\in G_S$ satisfy a generating relation of the form $g^2 = e$, and therefore impose, through the group compatibility condition (1), equations of the form

$$\Phi_e^2(\mathbf{k}) = \Phi_g(g\mathbf{k} + \mathbf{k}): \quad (28)$$

In general $\mathbf{z}^2$ may be different from $\mathbf{z}$ and therefore the phase $\Phi_e^2(\mathbf{k})$ is not necessarily zero. But note that for any $\mathbf{z} \in \Gamma$ the operation $\mathbf{z}^2$ is either $\mathbf{z}$, or a pure rotation about the $\bar{z}$ -axis in spin space, and therefore $\Phi_e^2(\mathbf{h}^{(i)}) = 0000$ or $\frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}$.

Generating relations involving pairs of generators are of the form $ghg = h$, where ($g; \cdot$) and ($h; \cdot$) are in G_S . Application of the group compatibility condition (1) to these generating relations yields

$$\Phi_h(\mathbf{k}) = \Phi_{ghg}(\mathbf{k}) = \Phi_g(\mathbf{k} + hg\mathbf{k}) + \Phi_h(g\mathbf{k}): \quad (29)$$

We expand the left hand side by

$$\Phi_h(\mathbf{k}) = \Phi_h^{-1}(\mathbf{k}) = \Phi_h(\mathbf{k}) + \Phi_e^{-1}(\mathbf{k}) \quad (30)$$

to obtain

$$\Phi_e^{-1}(\mathbf{k}) = \Phi_g(\mathbf{k} + hg\mathbf{k}) + \Phi_h(g\mathbf{k} - \mathbf{k}): \quad (31)$$

This last form, as well as Eq. (28) for the 2-fold generators, emphasizes the fact that the new phase functions that are yet to be determined may depend on the phase functions $\Phi_e(\mathbf{k})$ that were calculated in section 4.. Note that $\mathbf{z}^{-1}$ is the product of two conjugate operations in Γ and is therefore either the identity or a pure rotation about the $\bar{z}$ -axis in spin space, and therefore $\Phi_e^{-1}(\mathbf{h}^{(i)}) = 0000$ or $\frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}$.

6.1. Point group $G = \bar{8}$ (generator r_8)

The only phase to be determined is $\Phi_{r_8}(\mathbf{c})$ because the in-plane phases of Φ_{r_8} where set to zero by the gauge transformation of section 5.1.. Successive applications of the group compatibility condition to the generating relation $r_8^8 = e$ yield

$$\Phi_e^8(\mathbf{c}) = \Phi_{r_8}(\mathbf{c} + r_8\mathbf{c} + \dots + r_8^7\mathbf{c}); \quad (32)$$

where in general, $\mathbf{z}^8$ may be different from $\mathbf{z}$ and therefore the phase $\Phi_e^8(\mathbf{c})$ is not necessarily zero. For vertical lattices $\mathbf{c} = \mathbf{z}$ and Eq. (32) becomes

$$\Phi_e^8(\mathbf{z}) = 8\Phi_{r_8}(\mathbf{z}); \quad (33)$$

with gauge-invariant solutions of the form

$$\Phi_{r_8}(\mathbf{z}) = \frac{1}{8}\Phi_e^8(\mathbf{z}) + \frac{c}{8}; \quad c = 0 :: 7: \quad (34)$$

For staggered lattices $\mathbf{c} = \mathbf{z} + \mathbf{h}$ and Eq. (32) becomes

$$\Phi_e^8(\mathbf{z} + \mathbf{h}) = \Phi_{r_8}(\mathbf{z}) + 8\Phi_{r_8}(\mathbf{z} + \mathbf{h}); \quad (35)$$

where the second equality follows from the fact that $8\mathbf{h}$ is a lattice vector in the horizontal plane for which $\Phi_{r_8}(8\mathbf{h}) = 0$. The solutions of Eq. (35) are

$$\Phi_{r_8}(\mathbf{z} + \mathbf{h}) = \frac{1}{8}\Phi_e^8(\mathbf{z} + \mathbf{h}) + \frac{c}{8}; \quad c = 0 :: 7; \quad (36)$$

just as for the vertical stacking vector, but unlike the vertical stacking vector, the phase $\Phi_{r_8}(\mathbf{z} + \mathbf{h})$ is not gauge invariant because $r_8(\mathbf{z} + \mathbf{h}) \notin (\mathbf{z} + \mathbf{h})$. We need to check whether any of the solutions are gauge-equivalent through the remaining gauge freedom given by one of the gauge functions (27). Taking $\mathbf{z} \cdot \mathbf{h}^{(i)} = 1=2$ changes the phase $\Phi_{r_8}(\mathbf{z} + \mathbf{h})$ by

$$\Delta\Phi_{r_8}(\mathbf{z} + \mathbf{h}) = \mathbf{z} \cdot (r_8(\mathbf{z} + \mathbf{h}) - (\mathbf{z} + \mathbf{h})) = \mathbf{z} \cdot \mathbf{h}^{(4)} = \frac{1}{2}: \quad (37)$$

Therefore, on the S -lattice two solutions differing by $1=2$ are gauge-equivalent, so the distinct solutions are

$$\Phi_{r_8}(\mathbf{z} + \mathbf{h}) = \frac{1}{8}\Phi_e^8(\mathbf{z} + \mathbf{h}) + \frac{c^0}{8} \quad c^0 = 0 :: 3: \quad (38)$$

The phase functions for point group $G = \bar{8}$ are summarized in Table 4 for V -lattices, and Table 5 for S -lattices.

6.2. Point group $G = \bar{8}$ (generator r_8)

The only phase function to be determined, Φ_{r_8} , is zero everywhere on both lattice types due to the choice of gauge in sections 5.1. and 5.2.. Note that in this case

$$\Phi_e^8(\mathbf{k}) = \Phi_{r_8^8}(\mathbf{k}) = \Phi_{r_8}(\mathbf{k} + \bar{r}_8\mathbf{k} + \dots + \bar{r}_8^7\mathbf{k}) = 0; \quad (39)$$

and therefore $\mathbf{z}^8 = \mathbf{z}$ whenever $\bar{r}_8$ is a generator of G .

The phase functions for point group $G = \bar{8}$ are summarized in Table 6 for V -lattices, and Table 7 for S -lattices.

6.3. Point group $G = 8mm$ (generators r_8 and m)

We need to determine the phase $\Phi_{r_8}(\mathbf{c})$ and the phase function $\Phi_m(\mathbf{k})$. We use the generating relations $r_8^8 = m^2 = e$ and $r_8mr_8 = m$, which impose Eq. (32) for the 8-fold generator, Eq. (28) for the 2-fold generator, and Eq. (31) for the additional generating relation $r_8mr_8 = m$. We begin by noting that if m is the mirror that leaves $\mathbf{b}^{(1)}$ invariant, then application of Eq. (28) to $\mathbf{b}^{(3)}$ which is perpendicular to m ($m\mathbf{b}^{(3)} = -\mathbf{b}^{(3)}$) yields

$$\Phi_e^2(\mathbf{b}^{(3)}) = \Phi_m(m\mathbf{b}^{(3)} + \mathbf{b}^{(3)}) = 0; \quad (40)$$

implying that $\Phi_e^2(\mathbf{b}^{(i)}) = 0000$. Application of Eq. (28) to $\mathbf{b}^{(1)}$ then yields

$$0 = 2\Phi_m(\mathbf{b}^{(1)}) = \Phi_m(\mathbf{b}^{(1)}) = 0 \text{ or } \frac{1}{2}; \quad (41)$$

and application of Eq. (28) to $\mathbf{b}^{(2)}$ and $\mathbf{b}^{(4)}$ shows that $\Phi_m(\mathbf{b}^{(2)}) = \Phi_m(\mathbf{b}^{(4)})$, but provides no further information regarding the actual values of these phases. Next, we apply Eq. (31) to the horizontal generating vectors to obtain

$$\Phi_m(\mathbf{b}^{(i+1)}) = \Phi_m(\mathbf{b}^{(i)}) + \Phi_e^{-1}(\mathbf{b}^{(i)}); \quad (42)$$

Thus, the value of Φ_m on $\mathbf{b}^{(1)}$ determines the values of Φ_m on the remaining horizontal generating vectors through the phase function Φ_e^{-1} :

$$\Phi_m(\mathbf{b}^{(i)}) = \begin{cases} 0000 \text{ or } \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2} & \text{if } \Phi_e^{-1}(\mathbf{b}^{(i)}) = 0000; \\ 0\frac{1}{2}0\frac{1}{2} \text{ or } \frac{1}{2}0\frac{1}{2}0 & \text{if } \Phi_e^{-1}(\mathbf{b}^{(i)}) = \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}; \end{cases} \quad (43)$$

For the vertical stacking vector in V -lattices, for which $m\mathbf{z} = r_8\mathbf{z} = \mathbf{z}$, Eq. (33) remains unchanged, and Eqs. (31) and (28) become

$$\Phi_e^{-1}(\mathbf{z}) = 2\Phi_m(\mathbf{z}) \quad (44a)$$

$$\Phi_e^2(\mathbf{z}) = 2\Phi_m(\mathbf{z}) \quad (44b)$$

The solutions to these equations are

$$\Phi_{r_8}(\mathbf{z}) = \frac{1}{2}\Phi_e^{-1}(\mathbf{z}) + a; \quad (45a)$$

$$\Phi_m(\mathbf{z}) = \frac{1}{2}\Phi_e^2(\mathbf{z}) + b; \quad (45b)$$

where a and b are independently 0 or 1=2.

For the staggered stacking vector in S -lattices, for which $r_8(\mathbf{z} + \mathbf{h}) = \mathbf{z} + \mathbf{h} + \mathbf{b}^{(4)}$ and $m(\mathbf{z} + \mathbf{h}) = \mathbf{z} + \mathbf{h} - \mathbf{b}^{(3)}$ we obtain Eq. (35) together with

$$\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) = 2\Phi_{r_8}(\mathbf{z} + \mathbf{h}) + \Phi_m(\mathbf{b}^{(4)}) \quad (46a)$$

$$\Phi_e^2(\mathbf{z} + \mathbf{h}) = 2\Phi_m(\mathbf{z} + \mathbf{h}) - \Phi_m(\mathbf{b}^{(3)}) \quad (46b)$$

Noting that the signs of the phases $\Phi_m(\mathbf{b}^{(i)})$ are unimportant, the solutions to these equations are

$$\Phi_{r_8}(\mathbf{z} + \mathbf{h}) = \frac{1}{2}\Phi_m(\mathbf{b}^{(4)}) + \frac{1}{2}\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) + a; \quad (47a)$$

$$\Phi_m(\mathbf{z} + \mathbf{h}) = \frac{1}{2}\Phi_m(\mathbf{b}^{(3)}) + \frac{1}{2}\Phi_e^2(\mathbf{z} + \mathbf{h}) + b; \quad (47b)$$

where a and b are independently 0 or 1=2, but we still need to check for gauge-equivalence using the remaining gauge freedom given by the gauge functions (27). A gauge transformation with $\gamma_3(\mathbf{b}^{(i)}) = 1=2$ changes both of the phases in Eqs. (47) by 1=2, implying that the two solutions with $ab = 00$ and $\frac{1}{2}\frac{1}{2}$ are gauge-equivalent and the two solutions $ab = 0\frac{1}{2}$ and $\frac{1}{2}0$ are also gauge-equivalent. As representatives of the gauge-equivalence classes we take the solutions with $a = 0$.

We finally note that Eqs. (33) and (35) further imply that for both lattice types

$$\Phi_e^8(\mathbf{c}) = 4\Phi_e^{-1}(\mathbf{c}); \quad (48)$$

which is true for the horizontal generating vectors as well and therefore $8 = \begin{pmatrix} 1 & 4 \end{pmatrix}$.

The phase functions for point group $G = 8mm$ are summarized in Table 8 for V -lattices, and Table 9 for S -lattices.

6.4. Point group $G = \bar{8}m2$ (generators $\bar{r}_8$ and m)

Here we only need to determine the phase function $\Phi_m(\mathbf{k})$ because by the initial choice of gauge $\Phi_{\bar{r}_8}(\mathbf{k}) = 0$. We use the generating relations $m^2 = e$ and $\bar{r}_8 m \bar{r}_8 = m$, which through group compatibility conditions of the form (28) and (31) yield equations that resemble those for $G = 8mm$ with $\bar{r}_8$ replacing r_8 .

For the horizontal generating vectors we again find that Φ_m has two possible solutions given by Eq. (43). For the vertical stacking vector, for which $\bar{r}_8\mathbf{z} = \mathbf{z}$ and $m\mathbf{z} = \mathbf{z}$, Eqs. (28) and (31) become

$$\Phi_e^{-1}(\mathbf{z}) = 2\Phi_m(\mathbf{z}); \quad (49a)$$

$$\Phi_e^2(\mathbf{z}) = 2\Phi_m(\mathbf{z}); \quad (49b)$$

The solutions to these equations are

$$\Phi_m(\mathbf{z}) = \frac{1}{2}\Phi_e^2(\mathbf{z}) + a; \quad a = 0 \text{ or } \frac{1}{2}; \quad (50a)$$

with the additional condition that

$$\Phi_e^2(\mathbf{z}) + \Phi_e^{-1}(\mathbf{z}) = 0; \quad (50b)$$

For the staggered stacking vector, for which $\bar{r}_8(\mathbf{z} + \mathbf{h}) = \mathbf{z} + \mathbf{h} - \mathbf{b}^{(4)}$ and $m(\mathbf{z} + \mathbf{h}) = \mathbf{z} + \mathbf{h} + \mathbf{b}^{(3)}$, Eqs. (28) and (31) become

$$\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) = 2\Phi_m(\mathbf{z} + \mathbf{h}) - \Phi_m(\mathbf{b}^{(4)}) \quad (51a)$$

$$\Phi_e^2(\mathbf{z} + \mathbf{h}) = 2\Phi_m(\mathbf{z} + \mathbf{h}) + \Phi_m(\mathbf{b}^{(3)}) \quad (51b)$$

The solutions to these equations are

$$\Phi_m(\mathbf{z} + \mathbf{h}) = \frac{1}{2}\Phi_m(\mathbf{b}^{(3)}) + \frac{1}{2}\Phi_e^2(\mathbf{z} + \mathbf{h}) + a; \quad a = 0 \text{ or } \frac{1}{2}; \quad (52a)$$

with the additional condition that

$$\Phi_e^2(\mathbf{z} + \mathbf{h}) + \Phi_e^{-1}(\mathbf{z} + \mathbf{h}) - \Phi_m(\mathbf{b}^{(3)}) + \Phi_m(\mathbf{b}^{(4)}) = 0; \quad (52b)$$

A gauge transformation (27) with $\gamma_3(\mathbf{b}^{(i)}) = 1=2$ changes the phase $\Phi_m(\mathbf{z} + \mathbf{h})$ by 1=2 and therefore the two solutions in Eq. (52a) are gauge-equivalent. We take the one with $a = 0$.

The phase functions for point group $G = \bar{8}m2$ are summarized in Table 10 for V -lattices, and Table 11 for S -lattices.

research papers

6.5. Point group $G = 822$ (generators r_8 and d)

We need to determine the phase $\Phi_{r_8}(\mathbf{c})$ and the phases $\Phi_d(\mathbf{b}^{(i)})$ —since $\Phi_{r_8}(\mathbf{b}^{(i)}) = \Phi_d(\mathbf{c}) = 0$ by our choice of gauge—using the generating relations $r_8^8 = d^2 = e$ and $r_8 d r_8 = d$. The relation $r_8^8 = e$ yields the same equation for $\Phi_{r_8}(\mathbf{c})$ as in the case of point group $G = 8$, giving rise to the same solutions as those given by Eqs. (34) and (38).

The determination of $\Phi_d(\mathbf{b}^{(i)})$ is similar to that of $\Phi_m(\mathbf{b}^{(i)})$ in the case of point group $G = 8mm$. If d is the dihedral rotation that leaves $\mathbf{b}^{(1)}$ invariant, then application of Eq. (28) to $\mathbf{b}^{(3)}$ which is perpendicular to $\mathbf{b}^{(1)}$ yields

$$\Phi_e^2(\mathbf{b}^{(3)}) = \Phi_d(d\mathbf{b}^{(3)} + \mathbf{b}^{(3)}) = 0; \quad (53)$$

implying that $\Phi_e^2(\mathbf{b}^{(3)}) = 0000$. Application of Eq. (28) to $\mathbf{b}^{(1)}$ then yields

$$0 = 2\Phi_d(\mathbf{b}^{(1)}) = \Phi_d(\mathbf{b}^{(1)}) = 0 \text{ or } \frac{1}{2}; \quad (54)$$

and application of Eq. (28) to $\mathbf{b}^{(2)}$ and $\mathbf{b}^{(4)}$ shows that $\Phi_d(\mathbf{b}^{(2)}) = \Phi_d(\mathbf{b}^{(4)})$, but provides no further information regarding the actual values of these phases. Next, we apply Eq. (31) to the horizontal generating vectors to obtain

$$\Phi_d(\mathbf{b}^{(i+1)}) = \Phi_d(\mathbf{b}^{(i)}) + \Phi_e^{-1}(\mathbf{b}^{(i)}); \quad (55)$$

Thus, $\Phi_d(\mathbf{b}^{(1)})$ determines the values of Φ_d on the remaining horizontal generating vectors through the phase function Φ_e^{-1} :

$$\Phi_d(\mathbf{b}^{(i)}) = \begin{cases} 0000 \text{ or } \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2} & \text{if } \Phi_e^{-1}(\mathbf{b}^{(i)}) = 0000; \\ 0\frac{1}{2}0\frac{1}{2} \text{ or } \frac{1}{2}0\frac{1}{2}0 & \text{if } \Phi_e^{-1}(\mathbf{b}^{(i)}) = \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}; \end{cases} \quad (56)$$

For the vertical stacking vector, for which $d\mathbf{z} = \mathbf{z}$, we obtain

$$\Phi_e^{-1}(\mathbf{z}) = 0; \quad (57a)$$

$$\Phi_e^2(\mathbf{z}) = 0; \quad (57b)$$

The latter of the two, together with Eq. (53), implies that on V -lattices $^2 = \frac{1}{2}$.

For the staggered stacking vector, for which $d(\mathbf{z} + \mathbf{h}) = (\mathbf{z} + \mathbf{h}) + 2\mathbf{h} = \mathbf{b}^{(3)}$, we obtain the additional constraints

$$\Phi_d(\mathbf{b}^{(4)}) = \Phi_e^{-1}(\mathbf{z} + \mathbf{h}); \quad (58a)$$

$$\Phi_d(\mathbf{b}^{(3)}) = \Phi_e^2(\mathbf{z} + \mathbf{h}); \quad (58b)$$

From Eq. (58a) we find that $\Phi_e^{-1}(\mathbf{z} + \mathbf{h})$ must be either 0 or $\frac{1}{2}$ and therefore that Φ_e^{-1} is either 0 or $\frac{1}{2}$. In either case $\Phi_e^{-1}(\mathbf{b}^{(i)}) = 0$ so only the first of the two cases given in Eq. (56) is possible. This then implies that the left-hand sides of Eqs. (58) are equal and therefore that $\Phi_e^{-1} = \Phi_e^2$. The values of Φ_d on the horizontal generating vectors for S -lattices are thus given by

$$\Phi_d(\mathbf{b}^{(i)}) = \begin{cases} 0000 & \text{if } \Phi_e^{-1} = \Phi_e^2 = \frac{1}{2}; \\ \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2} & \text{if } \Phi_e^{-1} = \Phi_e^2 = 2\frac{1}{2}; \end{cases} \quad (59)$$

The phase functions for point group $G = 822$ are summarized in Table 12 for V -lattices, and Table 13 for S -lattices.

6.6. Point group $G = \bar{8}2m$ (generators $\bar{r}_8$ and d)

We need to determine the phase function $\Phi_d(\mathbf{k})$ because we have chosen a gauge in which $\Phi_{\bar{r}_8}(\mathbf{k}) = 0$. We use the generating relations $d^2 = e$ and $\bar{r}_8 d \bar{r}_8 = d$, which through group compatibility conditions of the form (28) and (31) yield equations that resemble those for $G = 822$ with $\bar{r}_8$ replacing r_8 .

For the horizontal generating vectors we again find that Φ_d has two possible solutions given by Eq. (56), and that $\Phi_e^2(\mathbf{b}^{(i)}) = 0000$. For the vertical stacking vector, for which $\bar{r}_8 \mathbf{z} = d\mathbf{z} = \mathbf{z}$, Eqs. (28) and (31) become

$$\Phi_e^{-1}(\mathbf{z}) = 2\Phi_d(\mathbf{z}); \quad (60a)$$

$$\Phi_e^2(\mathbf{z}) = 0; \quad (60b)$$

The solutions to Eq. (60a) are

$$\Phi_d(\mathbf{z}) = \frac{1}{2}\Phi_e^{-1}(\mathbf{z}) + a; \quad a = 0 \text{ or } \frac{1}{2}; \quad (61)$$

and Eq. (60b) implies that on V -lattices $^2 = \frac{1}{2}$.

For the staggered stacking vector, for which $\bar{r}_8(\mathbf{z} + \mathbf{h}) = (\mathbf{z} + \mathbf{h}) = \mathbf{b}^{(4)}$ and $d(\mathbf{z} + \mathbf{h}) = (\mathbf{z} + \mathbf{h}) + 2\mathbf{h} = \mathbf{b}^{(3)}$, Eqs. (28) and (31) become

$$\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) = 2\Phi_d(\mathbf{z} + \mathbf{h}) = \Phi_d(\mathbf{b}^{(4)}); \quad (62a)$$

$$\Phi_e^2(\mathbf{z} + \mathbf{h}) = \Phi_d(\mathbf{b}^{(3)}); \quad (62b)$$

The solutions to Eq. (62a) are

$$\Phi_d(\mathbf{z} + \mathbf{h}) = \frac{1}{2}\Phi_d(\mathbf{b}^{(4)}) = \frac{1}{2}\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) + a; \quad a = 0 \text{ or } \frac{1}{2}; \quad (63)$$

with the additional condition, given by Eq. (62b), that $\Phi_d(\mathbf{b}^{(3)})$ is determined by 2 , reducing the possible solutions in (56) to one. Note that none of the gauge transformations Φ_3 in Eq. (27) can change the phase $\Phi_d(\mathbf{z} + \mathbf{h})$.

The phase functions for point group $G = \bar{8}2m$ are summarized in Table 14 for V -lattices, and Table 15 for S -lattices.

6.7. Point group $G = 8\bar{m}$ (generators r_8 and h)

We are using a gauge in which $\Phi_{r_8}(\mathbf{b}^{(i)}) = \Phi_h(\mathbf{c}) = 0$, and therefore need to determine the phases $\Phi_h(\mathbf{b}^{(i)})$ and $\Phi_{r_8}(\mathbf{c})$ using the generating relations $r_8^8 = h^2 = e$ and $h r_8 h = r_8$. Equations (31) and (28) for the horizontal generating vectors are

$$\Phi_h(\mathbf{b}^{(i)} + \mathbf{b}^{(i+1)}) = \Phi_e^{-1}(\mathbf{b}^{(i)}); \quad (64a)$$

$$2\Phi_h(\mathbf{b}^{(i)}) = \Phi_e^2(\mathbf{b}^{(i)}); \quad (64b)$$

Due to the fact that $\Phi_e^{-1}(\mathbf{b}^{(i)}) = 0000$ or $\frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}$, application of Eq. (64a) to successive horizontal generating vectors establishes that $\Phi_h(\mathbf{b}^{(i)}) = \Phi_h(\mathbf{b}^{(i)})$, and therefore that the in-plane phases are given by

$$\Phi_h(\mathbf{b}^{(i)}) = \begin{cases} 0000 \text{ or } \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2} & \text{if } \Phi_e^{-1}(\mathbf{b}^{(i)}) = 0000; \\ 0\frac{1}{2}0\frac{1}{2} \text{ or } \frac{1}{2}0\frac{1}{2}0 & \text{if } \Phi_e^{-1}(\mathbf{b}^{(i)}) = \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}; \end{cases} \quad (65)$$

Eq. (64b) then implies that $\Phi_e^2(\mathbf{b}^{(j)}) = 0000$. For the vertical stacking vector, for which $h\mathbf{z} = \mathbf{z}$, the equations are

$$2\Phi_{r_8}(\mathbf{z}) - \Phi_e^{-1}(\mathbf{z}) = 0 \quad (66a)$$

$$\Phi_e^2(\mathbf{z}) = 0 \quad (66b)$$

The solutions to Eq. (66a) are

$$\Phi_{r_8}(\mathbf{z}) = \frac{1}{2}\Phi_e^{-1}(\mathbf{z}) + c; \quad c = 0 \text{ or } \frac{1}{2}; \quad (67)$$

and Eq. (66b) implies that on V -lattices $\Phi_e^2 = 0$.

For the staggered stacking vector, for which $h(\mathbf{z} + \mathbf{h}) = (\mathbf{z} + \mathbf{h}) + 2\mathbf{h}$, and using the fact that $\Phi_{r_8}(2\mathbf{h}) = \Phi_h(2r_8\mathbf{h}) = 0$, the equations are

$$\Phi_h(\mathbf{b}^{(4)}) = 2\Phi_{r_8}(\mathbf{z} + \mathbf{h}) - \Phi_e^{-1}(\mathbf{z} + \mathbf{h}) \quad (68a)$$

$$\Phi_e^2(\mathbf{z} + \mathbf{h}) = 0; \quad (68b)$$

The solutions to Eq. (68a) are

$$\Phi_{r_8}(\mathbf{z} + \mathbf{h}) = \frac{1}{2}\Phi_h(\mathbf{b}^{(4)}) - \frac{1}{2}\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) + c; \quad c = 0 \text{ or } \frac{1}{2}; \quad (69)$$

but a gauge transformation (27) with $\Phi_3(\mathbf{b}^{(j)}) = 1=2$ shows that the two solutions are gauge-equivalent, allowing us to take $c = 0$. Eq. (68b) implies that $\Phi_e^2 = 0$ on S -lattices, as well. Finally, the generating relation $r_8^8 = e$ imposes Eq. (32) as in the case of point group $G = 8$, for both lattice types. Together with Eqs. (66a) and (68a) this implies that

$$\Phi_e^8(\mathbf{c}) = 4\Phi_e^{-1}(\mathbf{c}); \quad (70)$$

which is true for the horizontal generating vectors as well, and therefore $\Phi_e^8 = (\Phi_e^{-1})^4$.

The phase functions for point group $G = 8=m$ are summarized in Table 16 for V -lattices, and Table 17 for S -lattices.

6.8. Point group $G = 8=mmm$ (generators r_8 , m , and h)

We need to determine the phase $\Phi_{r_8}(\mathbf{c})$, the phases $\Phi_h(\mathbf{b}^{(j)})$, and the complete phase function $\Phi_m(\mathbf{k})$. The generating relations and the equations they impose are the same as those for $G = 8mm$ and those for $G = 8=m$, with the additional condition imposed by the generating relation $mh = h$ which yields

$$\Phi_e^{-1}(\mathbf{b}^{(j)}) - 2\Phi_m(\mathbf{b}^{(j)}) = 0; \quad (71a)$$

$$\Phi_e^{-1}(\mathbf{z}) = 0; \quad (71b)$$

$$\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) = \Phi_m(\mathbf{b}^{(1)}) - \Phi_h(\mathbf{b}^{(3)}); \quad (71c)$$

for the horizontal generating vectors, vertical stacking vector, and staggered stacking vector, respectively.

For V -lattices Eqs. (71a) and (71b) imply that $\Phi_e^{-1} = 0$ but do not impose any additional constraints on the phase functions already determined for point groups $G = 8mm$ and $G = 8=m$. Thus the solutions for point group $G = 8=mmm$ are simply the combination of the two, so $\Phi_h(\mathbf{b}^{(j)})$ is given by Eq. (65),

$\Phi_m(\mathbf{b}^{(j)})$ by Eq. (43), and $\Phi_{r_8}(\mathbf{z})$ and $\Phi_m(\mathbf{z})$ by Eqs. (45), with the additional conditions that

$$\Phi_e^{-1}(\mathbf{z}) + \Phi_e^{-1}(\mathbf{z}) = 0; \quad (72)$$

$$\Phi_e^2(\mathbf{b}^{(j)}) = 0000, \quad \Phi_e^2 = \Phi_e^{-1} = \Phi_e^{-1}, \text{ and } \Phi_e^8 = (\Phi_e^{-1})^4 = (\Phi_e^{-1})^4.$$

For S -lattices Eq. (71c) implies that $\Phi_e^{-1}(\mathbf{z} + \mathbf{h})$ can be either 0 or 1=2 and therefore that Φ_e^{-1} is either 0 or 2. It also imposes a constraint between the two phase functions Φ_m and Φ_h . Therefore, on S -lattices $\Phi_h(\mathbf{b}^{(j)})$ is again given by Eq. (65), but

$$\Phi_m(\mathbf{b}^{(j)}) = \Phi_h(\mathbf{b}^{(j)}) + \Phi_e^{-1}(\mathbf{z} + \mathbf{h}); \quad (73)$$

and $\Phi_{r_8}(\mathbf{z} + \mathbf{h})$ and $\Phi_m(\mathbf{z} + \mathbf{h})$ are given by Eqs. (47), with the additional conditions that

$$\Phi_e^{-1}(\mathbf{b}^{(j)}) = \Phi_e^{-1}(\mathbf{b}^{(j)}); \quad (74a)$$

$$\Phi_e^{-1}(\mathbf{z} + \mathbf{h}) + \Phi_e^{-1}(\mathbf{z} + \mathbf{h}) = \Phi_e^{-1}(\mathbf{z} + \mathbf{h}); \quad (74b)$$

$$\Phi_e^2(\mathbf{b}^{(j)}) = \Phi_e^{-1}(\mathbf{b}^{(j)}) = 0000, \quad \Phi_e^{-1}(\mathbf{z} + \mathbf{h}) = 0 \text{ or } 1=2 \text{ depending on whether } \Phi_e^{-1} \text{ is } 0 \text{ or } 2, \quad \Phi_e^2 = \Phi_e^{-1}, \text{ and } \Phi_e^8 = (\Phi_e^{-1})^4 = (\Phi_e^{-1})^4.$$

The phase functions for point group $G = 8=mmm$ are summarized in Table 18 for V -lattices, and Table 19 for S -lattices.

7. Spin group tables

Tables 4-19 contain in compact form all the information needed to generate the complete list of octagonal spin space-group types. All that is still required is to explicitly identify the spin-space operations, and whenever necessary, and, recalling that these operations must also satisfy the constraints, summarized in Table 3, that are due to the isomorphism between $G=G$ and $\Gamma=\Gamma_e$. Once these operations are identified their different combinations that determine the phase functions— Φ_e^8 , Φ_e^{-1} , Φ_e^{-1} , etc.—can be calculated to give the different spin space-group types. The explicit identification of spin-space operations is listed in Appendix B. which can be obtained via... [PRODUCTION EDITOR: please indicate how one can obtain this appendix.]. For each spin space-group Table (Tables 4-19) there is a corresponding Table in Appendix B. which lists all the possible identifications of spin-space operations, and for each one, indicates the line in the spin space-group Table to which it corresponds.

To each spin space-group type we give a unique symbol based on the familiar International (Hermann-Mauguin) symbols for the regular (nonmagnetic) space groups. To incorporate all the spin space-group information we augment the regular symbol, which for the case of octagonal quasicrystals is explained in detail by Rabson *et al.* (1991), in the following ways: (1) The symbol for the lattice spin group Γ_e is added as a superscript over the lattice symbol, unless $\Gamma_e = 1$ or 1^0 . (2) The values of the phase functions, associated with the elements of Γ_e , are encoded by subscripts under the lattice symbol, describing the sublattices defined by the zeros of the phase functions for the operations in the symbol for Γ_e (as explained in Sec. 4.). (3) To

research papers

each generator of the point group G we add a superscript listing an operation from the coset of Γ_e with which it is paired (if that operation can be we omit it, if it can be 0 we simply add a prime, and we omit the axis about which rotations are performed if it is the $\bar{z}$ -axis). (4) The values of phase functions for the spin point group generators Φ_{r_g} , $\Phi_{r_g'}$, Φ_m , Φ_d , and Φ_h are encoded by making changes and adding subscripts to the point group symbol (similar to the way it is done for the regular space groups), as described in the captions of Tables 4-19, where we use the same notation, simply without explicitly listing Γ_e and its associated phase functions, and without explicitly identifying the spin-space operations paired with the point group generators. Specific examples of spin space-group symbols can be found in the captions of Tables 4, 5, 8 and 19.

8. Magnetic selection rules

We calculate the symmetry-imposed constraints on $\mathbf{S}(\mathbf{k})$, for any wave vector $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$ in the magnetic lattice L , as described in the companion paper (Lifshitz & Even-Dar Mandel, 2003), by considering all spin point group operations ($g; \gamma$) for which $g\mathbf{k} = \mathbf{k}$. The point group condition for each of these operations provides an eigenvalue equation

$$\mathbf{S}(\mathbf{k}) = e^{-2i\Phi_g(\mathbf{k})} \mathbf{S}(\mathbf{k}) \quad (75)$$

from which we obtain the constraints on $\mathbf{S}$. These constraints may require $\mathbf{S}(\mathbf{k})$ to vanish or to take a particular form which transforms under the operations in (75) according to the 1-dimensional representation dictated by the phases $\Phi_g(\mathbf{k})$. When there are no constraints then $\mathbf{S} = (S_{\bar{x}}; S_{\bar{y}}; S_{\bar{z}})$ is an arbitrary 3-component axial vector. When there are constraints, $\mathbf{S}(\mathbf{k})$ takes one of the following forms:

$$\begin{aligned} \mathbf{S}_x &= (S_{\bar{x}}; 0; 0); & \mathbf{S}_y &= (0; S_{\bar{y}}; 0); & \mathbf{S}_z &= (0; 0; S_{\bar{z}}); \\ \mathbf{S}_{yz} &= (0; S_{\bar{y}}; S_{\bar{z}}); & \mathbf{S}_{zx} &= (S_{\bar{x}}; 0; S_{\bar{z}}); & \mathbf{S}_{xy} &= (S_{\bar{x}}; S_{\bar{y}}; 0); \\ \mathbf{S}_+ &= (S_{\bar{x}}; iS_{\bar{y}}; 0); & \mathbf{S}_- &= (S_{\bar{x}}; -iS_{\bar{y}}; 0); \end{aligned} \quad (76)$$

as explained below.

In section 8.1. we determine the selection rules due elements in Γ_e . These affect all wave vectors $\mathbf{k} \in L$, and are summarized in Tables 20–24. In section 8.2. we determine the remaining selection rules for wave vectors that lie in the invariant subspaces of the different point group elements. These selection rules are expressed in a general manner in terms of the spin-space operations paired with these point group elements, without identifying them explicitly.

8.1. Calculation of selection rules due to Γ_e

If γ is an operation of order 2 then its phases $\Phi_e(\mathbf{k})$ are either 0 or π . In this case Eq. (75) reduces to

$$\mathbf{S}(\mathbf{k}) = \begin{cases} \mathbf{S}(\mathbf{k}) & \text{if } \Phi_e(\mathbf{k}) = 0; \\ -\mathbf{S}(\mathbf{k}) & \text{if } \Phi_e(\mathbf{k}) = \pi; \end{cases} \quad (77)$$

so if $\Phi_e(\mathbf{k}) = 0$, $\mathbf{S}(\mathbf{k})$ must be invariant under γ , and if $\Phi_e(\mathbf{k}) = \pi$ it must change its sign under γ . This implies different constraints on the form of $\mathbf{S}(\mathbf{k})$ depending on the particular type of operation of order 2:

1. If γ is the time inversion 0 , then $\mathbf{S}(\mathbf{k}) = 0$ if $\Phi_e(\mathbf{k}) = 0$ and there are no constraints on $\mathbf{S}(\mathbf{k})$ if $\Phi_e(\mathbf{k}) = \pi$.
2. If γ is a 2-fold rotation 2_z , then $\mathbf{S}(\mathbf{k}) = S_z$ if $\Phi_e(\mathbf{k}) = 0$ and $\mathbf{S}(\mathbf{k}) = S_{xy}$ if $\Phi_e(\mathbf{k}) = \pi$. Similar constraints are obtained for rotations about the other two axes.
3. If γ is a 2-fold rotation followed by time inversion 2_z^0 , then $\mathbf{S}(\mathbf{k}) = S_{xy}$ if $\Phi_e(\mathbf{k}) = 0$ and $\mathbf{S}(\mathbf{k}) = S_z$ if $\Phi_e(\mathbf{k}) = \pi$. Similar constraints are obtained for primed rotations about the other two axes.

Thus, for lattice spin groups Γ_e containing only operations of order 2 the form of $\mathbf{S}(\mathbf{k})$ depends on whether the phases at $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$, associated with all the operations, are 0 or π . This can easily be calculated for each Γ_e from the values of its phase functions on the lattice generating vectors. The outcome depends, at most, on the parities of $n_1 + n_3$, $n_2 + n_4$, and l . Tables 20 - 23 summarize the results for all such Γ_e .

For operations of order greater than 2 we find that

4. If γ is an n -fold rotation n_z ($n > 2$) then Eq. (75) requires $\mathbf{S}(\mathbf{k})$ to acquire the phase $2\Phi_e^{n_z}(\mathbf{k})$ upon application of the n -fold rotation. One can directly verify that the only possible forms that $\mathbf{S}$ can have that satisfy this requirement are

$$\mathbf{S}(\mathbf{k}) = \begin{cases} S_z & \text{if } \Phi_e^{n_z}(\mathbf{k}) = 0; \\ S & \text{if } \Phi_e^{n_z}(\mathbf{k}) = \frac{1}{n}\pi; \\ 0 & \text{otherwise;} \end{cases} \quad (78)$$

5. If γ is an n -fold rotation followed by time inversion n_z^0 then one can obtain the constraints on the form of $\mathbf{S}$ from the constraints (78) by adding π to the phases, thus

$$\mathbf{S}(\mathbf{k}) = \begin{cases} S_z & \text{if } \Phi_e^{n_z^0}(\mathbf{k}) = \frac{1}{2}\pi; \\ S & \text{if } \Phi_e^{n_z^0}(\mathbf{k}) = \frac{1}{n}\pi; \\ 0 & \text{otherwise;} \end{cases} \quad (79)$$

Table 24 summarizes the results for lattice spin groups $\Gamma_e = n; n^0$ and $n1^0$, containing operations of order greater than 2.

8.2. Additional selection rules on invariant subspaces of nontrivial point group operations

In addition to the selection rules arising from Γ_e there are also selection rules that occur when $\mathbf{k}$ lies along one of the rotation axes or within one of the mirror planes and is therefore invariant under additional operations ($g; \gamma$) with non-trivial g . In this case the eigenvalue equation (75) imposes further restrictions on the Fourier coefficients of the spin density field.

8.2.1. Selection rules along the z -axis: When the eightfold rotation r_8 is in the point group G it leaves all the wave vectors along the z -axis invariant. These wave vectors are given by $\mathbf{k} = l\mathbf{z}$, where l is any integer if the lattice is vertical, and l is even if the lattice is staggered. For both lattice types Eq. (75), determining the selection rules for these wave vectors, becomes

$$\mathbf{S}(\mathbf{z}) = e^{-2i\Phi_{r_8}(\mathbf{c})} \mathbf{S}(\mathbf{z}); \quad (80)$$

where $\mathbf{c}$ is the appropriate stacking vector. When G is generated by $\bar{r}_8$, and does not contain r_8 , the wave vectors along the z -axis are left invariant by $\bar{r}_8^2$ and its powers. The phase $\Phi_{\bar{r}_8^2}(\mathbf{z}) = \Phi_{\bar{r}_8}(\bar{r}_8\mathbf{z}) + \Phi_{\bar{r}_8}(\mathbf{z})$ is necessarily zero because $\bar{r}_8\mathbf{z} = l\mathbf{z}$. Eq. (75) can therefore be written as

$$\bar{r}_8^2 \mathbf{S}(\mathbf{z}) = \mathbf{S}(\mathbf{z}); \quad (81)$$

requiring $\mathbf{S}(\mathbf{z})$ to be invariant under $\bar{r}_8^2$, where $\bar{r}_8^2$ is the spin-space operation paired with $\bar{r}_8$.

8.2.2. Selection rules within the horizontal mirror h : If the horizontal mirror h is present in the point group then all the Fourier coefficients of the spin density field associated with wave vectors $\mathbf{k}_h = \sum_i n_i \mathbf{b}^{(i)}$ in the horizontal sublattice are subject to selection rules, dictated by the values of the phase function Φ_h . Eq. (75), for both lattice types, is simply

$$\mathbf{S}(\mathbf{k}_h) = e^{-2i \sum_{i=1}^4 n_i \Phi_h(\mathbf{b}^{(i)})} \mathbf{S}(\mathbf{k}_h); \quad (82)$$

Thus, if a horizontal mirror is present in the point group then $\mathbf{S}(\mathbf{k}_h)$, for $\mathbf{k}_h = \sum_i n_i \mathbf{b}^{(i)}$ in the horizontal sublattice, must remain invariant under σ_h , unless (a) $\Phi_h(\mathbf{b}^{(i)}) = \frac{1}{2}0\frac{1}{2}0$ and $n_1 + n_3$ is odd; or (b) $\Phi_h(\mathbf{b}^{(i)}) = 0\frac{1}{2}0\frac{1}{2}$ and $n_2 + n_4$ is odd; or (c) $\Phi_h(\mathbf{b}^{(i)}) = \frac{1}{2}\frac{1}{2}\frac{1}{2}\frac{1}{2}$ and $\sum_i n_i$ is odd; in which case $\mathbf{S}(\mathbf{k}_h)$ must change its sign under σ_h .

8.2.3. Selection rules within vertical mirrors and along dihedral axes: There are two sets of conjugate vertical mirrors which we have labeled m and m^0 and two sets of conjugate dihedral axes d and d^0 . It is sufficient to determine the selection rules for a single member of each of these four sets because the selection rules for the remaining conjugate operations can be inferred from the 8-fold rotational symmetry of the spin density field. To see this, take for example the operation $(\eta n;)$ and examine all the wave vectors $\mathbf{k}$, satisfying $m\mathbf{k} = \mathbf{k}$, to obtain the general selection rules for the invariant subspace of m ,

$$\mathbf{S}(\mathbf{k}) = e^{-2i\Phi_m(\mathbf{k})} \mathbf{S}(\mathbf{k}); \quad (83)$$

If g is the 8-fold generator of the point group (r_8 or $\bar{r}_8$), paired with the spin space operation σ_g , then the selection rules on the invariant subspaces of the remaining three conjugate operations are simply given by

$$\sigma_g^n \mathbf{S}(g^n \mathbf{k}) = e^{-2i\Phi_m(g^n \mathbf{k})} \mathbf{S}(g^n \mathbf{k}); \quad n = 1; 2; 3; \quad (84)$$

where we have used that fact that, since $m\mathbf{k} = \mathbf{k}$, it follows from successive applications of the group compatibility condition (1) that

$$\Phi_{gm^{n-1}}(\mathbf{g}\mathbf{k}) = \Phi_m(\mathbf{k}); \quad (85)$$

Similar expressions can be derived for the other operations and so we proceed below to obtain the general selection rules only for the vertical mirrors and dihedral axes that are oriented either along the generating vector $\mathbf{b}^{(1)}$ or between the two generating vectors $\mathbf{b}^{(1)}$ and $\mathbf{b}^{(2)}$ (as depicted in Fig. 1).

Wave vectors along the dihedral axis d , containing the generating vector $\mathbf{b}^{(1)}$, on either lattice type, can be expressed as $\mathbf{k}_d = n_1 \mathbf{b}^{(1)} + n_2 (\mathbf{b}^{(2)} - \mathbf{b}^{(4)})$ for any two integers n_1 and n_2 . Since it is always the case that $\Phi_d(\mathbf{b}^{(2)} - \mathbf{b}^{(4)}) = 0$, the selection rules for such wave vectors are determined by

$$\mathbf{S}(\mathbf{k}_d) = e^{-2in_1\Phi_d(\mathbf{b}^{(1)})} \mathbf{S}(\mathbf{k}_d); \quad (86)$$

Thus, if a dihedral operation $(d;)$ is present in the spin point group then $\mathbf{S}(\mathbf{k}_d)$, for $\mathbf{k}_d$ along the axis of d , must remain invariant under σ_d , unless $\Phi_d(\mathbf{b}^{(1)}) = \frac{1}{2}$ and n_1 is odd, in which case $\mathbf{S}(\mathbf{k}_d)$ must change its sign under σ_d .

Wave vectors along the dihedral axis d^0 , between the generating vectors $\mathbf{b}^{(1)}$ and $\mathbf{b}^{(2)}$, on either lattice type, can be expressed as $\mathbf{k}_{d^0} = n_1 (\mathbf{b}^{(1)} + \mathbf{b}^{(2)}) + n_3 (\mathbf{b}^{(3)} - \mathbf{b}^{(4)})$ for any two integers n_1 and n_3 . Since it is always the case that $\Phi_{d^0}(\mathbf{b}^{(1)} + \mathbf{b}^{(2)}) = \Phi_{d^0}(\mathbf{b}^{(3)} - \mathbf{b}^{(4)}) = 0$, the selection rules are determined by

$$\sigma_{d^0} \mathbf{S}(\mathbf{k}_{d^0}) = e^{-2i(n_1+n_3)\Phi_{d^0}(\mathbf{b}^{(1)}+\mathbf{b}^{(2)})} \mathbf{S}(\mathbf{k}_{d^0}); \quad (87)$$

Thus, if a dihedral operation $(d^0;)$ is present in the spin point group then $\mathbf{S}(\mathbf{k}_{d^0})$, for $\mathbf{k}_{d^0}$ along the axis of d^0 , must remain invariant under σ_{d^0} , unless $\Phi_{d^0}(\mathbf{b}^{(i)}) = 0\frac{1}{2}0\frac{1}{2}$ or $\frac{1}{2}0\frac{1}{2}0$, and $n_1 + n_3$ is odd, in which case $\mathbf{S}(\mathbf{k}_{d^0})$ must change its sign under σ_{d^0} . The operation σ_{d^0} , as well as the values of the phase function Φ_{d^0} , are determined for each separate spin point group according to the generating relations for that group, namely, $(d^0;) = (\bar{r}_8;)(\eta n;)$ for point group 822, $(d^0;) = (\bar{r}_8;)(\eta n;)$ for point group 8m2, and $(d^0;) = (\bar{r}_8;)(\eta n;)(\eta l;)$ for point group 8mmm.

Wave vectors within the vertical mirror m , containing the generating vector $\mathbf{b}^{(1)}$, can be expressed as $\mathbf{k}_m = n_1 \mathbf{b}^{(1)} + n_2 (\mathbf{b}^{(2)} - \mathbf{b}^{(4)}) + l\mathbf{z}$, where l is any integer if the lattice is vertical and l is even if the lattice is staggered. This is due to the fact that there are no wave vectors in odd layers of S -lattices that are invariant under mirrors of type m (Rabson *et al.*, 1991, footnote 46). Since it is always the case that $\Phi_m(\mathbf{b}^{(2)} - \mathbf{b}^{(4)}) = 0$, the selection rules for such wave vectors are determined by

$$\mathbf{S}(\mathbf{k}_m) = e^{-2i[l\Phi_m(\mathbf{b}^{(1)}) + l\Phi_m(\mathbf{c})]} \mathbf{S}(\mathbf{k}_m); \quad (88)$$

Finally, wave vectors within the vertical mirror m^0 , between the generating vectors $\mathbf{b}^{(1)}$ and $\mathbf{b}^{(2)}$, on both lattice types, can be expressed as $\mathbf{k}_{m^0} = n_1 (\mathbf{b}^{(1)} + \mathbf{b}^{(2)}) + n_3 (\mathbf{b}^{(3)} - \mathbf{b}^{(4)}) + l\mathbf{c}$ for any three integers n_1 , n_3 , and l , where $\mathbf{c}$ is the appropriate stacking vector. Since it is always the case that $\Phi_{m^0}(\mathbf{b}^{(1)} + \mathbf{b}^{(2)}) = \Phi_{m^0}(\mathbf{b}^{(3)} - \mathbf{b}^{(4)}) = 0$, the selection rules are determined by

$$\sigma_{m^0} \mathbf{S}(\mathbf{k}_{m^0}) = e^{-2i[n_1+n_3]\Phi_{m^0}(\mathbf{b}^{(1)}+\mathbf{b}^{(2)}) + l\Phi_{m^0}(\mathbf{c})} \mathbf{S}(\mathbf{k}_{m^0}); \quad (89)$$

research papers

This completes the general calculation of selection rules on invariant subspaces of point group operations. One can apply these rules in a straightforward manner to each spin space group once the spin space operations σ , τ , ρ , and γ are explicitly identified.

This research was funded by the Israel Science Foundation through Grant No. 278/00.

References

Lifshitz, R. (1995). In *Proceedings of the 5th International Conference on Quasicrystals*, edited by C. Janot & R. Mosseri, pp. 43–46. Singapore: World Scientific.

Lifshitz, R. (1997). *Rev. Mod. Phys.* **69**, 1181–1218.

Lifshitz, R. (1998). *Phys. Rev. Lett.* **80**, 2717–2720.

Lifshitz, R. & Even-Dar Mandel, S. (2003). *Acta Cryst.* **AXX**, XXX–XXX. Companion paper.

Lifshitz, R. & Mermin, N. D. (1994). *Acta Cryst.* **A50**, 85–97.

Litvin, D. B. (1973). *Acta Cryst.* **A29**, 651–660.

Litvin, D. B. (1977). *Acta Cryst.* **A33**, 279–287.

Litvin, D. B. & Opechowski, W. (1974). *Physica*, **76**, 538–554.

Mermin, N. D., Rabson, D. A., Rokhsar, D. S. & Wright, D. C. (1990). *Phys. Rev. B*, **41**(15), 10498–10502.

Rabson, D. A., Mermin, N. D., Rokhsar, D. S. & Wright, D. C. (1991). *Rev. Mod. Phys.* **63**, 699–734.

Table 1

Three-dimensional octagonal point groups. There are seven octagonal point groups (geometric crystal classes) in three dimensions, one of which ($\overline{8}m2$) has two distinct orientations with respect to both types of octagonal lattices, giving the eight octagonal arithmetic crystal classes, listed in the first column. The set of generators for each point group, used throughout the paper, are listed in the second column along with the symbols, used to denote the spin-space operations with which they are paired in the spin point groups.

Point group	Generators
$\overline{8}$	$(r_8; \sigma)$
$\overline{8}$	$(\overline{r}_8; \sigma)$
$8mm$	$(r_8; \sigma); (\eta m; \sigma)$
$8m2$	$(\overline{r}_8; \sigma); (\eta m; \sigma)$
822	$(r_8; \sigma); (\eta d; \sigma)$
$82m$	$(\overline{r}_8; \sigma); (\eta d; \sigma)$
$8\overline{3}m$	$(r_8; \sigma); (\eta i; \sigma)$
$8\overline{3}mmm$	$(r_8; \sigma); (\eta m; \sigma); (\eta i; \sigma)$

Table 2

Effect of the point group generators on the lattice generating vectors. The horizontal shift $\mathbf{h}$ associated with the staggered stacking vector is defined in Eq. (2).

	$\mathbf{b}^{(1)}$	$\mathbf{b}^{(2)}$	$\mathbf{b}^{(3)}$	$\mathbf{b}^{(4)}$	$\mathbf{z}$	$\mathbf{z} + \mathbf{h}$
r_8	$\mathbf{b}^{(2)}$	$\mathbf{b}^{(3)}$	$\mathbf{b}^{(4)}$	$\mathbf{b}^{(1)}$	$\mathbf{z}$	$(\mathbf{z} + \mathbf{h}) + \mathbf{b}^{(4)}$
$\overline{r}_8$	$\mathbf{b}^{(2)}$	$\mathbf{b}^{(3)}$	$\mathbf{b}^{(4)}$	$\mathbf{b}^{(1)}$	$\mathbf{z}$	$(\mathbf{z} + \mathbf{h}) - \mathbf{b}^{(4)}$
m	$\mathbf{b}^{(1)}$	$\mathbf{b}^{(4)}$	$\mathbf{b}^{(3)}$	$\mathbf{b}^{(2)}$	$\mathbf{z}$	$(\mathbf{z} + \mathbf{h}) - \mathbf{b}^{(3)}$
d	$\mathbf{b}^{(1)}$	$\mathbf{b}^{(4)}$	$\mathbf{b}^{(3)}$	$\mathbf{b}^{(2)}$	$\mathbf{z}$	$(\mathbf{z} + \mathbf{h}) + 2\mathbf{h} - \mathbf{b}^{(3)}$
h	$\mathbf{b}^{(1)}$	$\mathbf{b}^{(2)}$	$\mathbf{b}^{(3)}$	$\mathbf{b}^{(4)}$	$\mathbf{z}$	$(\mathbf{z} + \mathbf{h}) + 2\mathbf{h}$

Table 3

Normal subgroups G of the seven octagonal point groups. The resulting quotient group $G=G$ is represented in the seventh column by a point group, isomorphic to it. Isomorphic groups G are listed in the same section of the Table. Constraints on the spin-space operations σ , τ , and ρ , paired with the generators g , m , d , and h of G are listed in the last column. In each line the first power of σ that is in Γ_e is given. σ^2 , τ^2 , and ρ^2 are always in Γ_e , therefore we only note whether σ , τ , and ρ are themselves in Γ_e . If a spin space operation is in Γ_e it is taken to be σ .

G	G	G	G	G	G	$G=G$	Constraints
		8	8	$\bar{8}$	$\bar{8}$	1	$\sigma =$
			4		4	2	$\sigma^2 \in \Gamma_e$
			2		2	4	$\sigma^4 \in \Gamma_e$
			1		1	8	$\sigma^8 \in \Gamma_e$
$8mm$	$8mm$	822	822	$\bar{8}m2$	$\bar{8}m2$	1	$\sigma =$; $\tau =$
	8		8		8	2	$\sigma =$; $\tau \notin \Gamma_e$
	$4mm$		422		$4mm$	2	$\sigma^2 \in \Gamma_e$; $\tau =$
	$4m^0m^0$		42^02^0		42^02^0	2	$\sigma =$; $\tau \notin \Gamma_e$
	4		4		4	222	$\sigma^2 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$
	2		2		2	422	$\sigma^4 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho^2 \notin \Gamma_e$
	1		1		1	822	$\sigma^8 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho^4 \notin \Gamma_e$
				$8=m$	$8=m$	1	$\sigma =$; $\tau =$
				8	8	2	$\sigma =$; $\tau \notin \Gamma_e$
				$\bar{8}$	$\bar{8}$	2	$\sigma =$; $\tau \notin \Gamma_e$
				$4=m$	$4=m$	2	$\sigma^2 \in \Gamma_e$; $\tau =$
				4	4	$2=m$	$\sigma^2 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$
				$\bar{4}$	$\bar{4}$	4	$\sigma^4 \in \Gamma_e$; $\tau^2 \in \Gamma_e$
				$2=m$	$2=m$	4	$\sigma^4 \in \Gamma_e$; $\tau =$
				2	2	$4=m$	$\sigma^4 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				m	m	8	$\sigma^8 \in \Gamma_e$; $\tau =$
				$\bar{1}$	$\bar{1}$	8	$\sigma^8 \in \Gamma_e$; $\tau^2 \in \Gamma_e$
				1	1	$8=m$	$\sigma^8 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho^4 \in \Gamma_e$
				$8=mmm$	$8=mmm$	1	$\sigma =$; $\tau =$; $\rho =$
				$8mm$	$8mm$	2	$\sigma =$; $\tau =$; $\rho \notin \Gamma_e$
				822	822	2	$\sigma =$; $\tau =$; $\rho \notin \Gamma_e$
				$8=m$	$8=m$	2	$\sigma =$; $\tau =$; $\rho \notin \Gamma_e$
				$\bar{8}m2$	$\bar{8}m2$	2	$\sigma =$; $\tau \notin \Gamma_e$; $\rho =$
				$\bar{8}2m$	$\bar{8}2m$	2	$\sigma =$; $\tau =$; $\rho \notin \Gamma_e$
				$4=mmm$	$4=mmm$	2	$\sigma^2 \in \Gamma_e$; $\tau =$; $\rho =$
				$4=mm^0m^0$	$4=mm^0m^0$	2	$\sigma =$; $\tau \notin \Gamma_e$; $\rho =$
				8	8	222	$\sigma =$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				$\bar{8}$	$\bar{8}$	222	$\sigma =$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				$4mm$	$4mm$	222	$\sigma^2 \in \Gamma_e$; $\tau =$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				$4m^0m^0$	$4m^0m^0$	222	$\sigma =$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				422	422	222	$\sigma^2 \in \Gamma_e$; $\tau =$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				42^02^0	42^02^0	222	$\sigma^2 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				$4=m$	$4=m$	222	$\sigma^2 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				4	4	mmm	$\sigma^2 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$; $\rho^4 \in \Gamma_e$; $\rho^6 \in \Gamma_e$
				$\bar{4}$	$\bar{4}$	422	$\sigma^4 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				$2=m$	$2=m$	422	$\sigma^4 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$
				2	2	$4=mmm$	$\sigma^4 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^2 \in \Gamma_e$; $\rho^4 \in \Gamma_e$; $\rho^6 \in \Gamma_e$
				m	m	822	$\sigma^8 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^4 \in \Gamma_e$
				$\bar{1}$	$\bar{1}$	822	$\sigma^8 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^4 \in \Gamma_e$
				1	1	$8=mmm$	$\sigma^8 \in \Gamma_e$; $\tau \notin \Gamma_e$; $\rho \notin \Gamma_e$; $\rho^4 \in \Gamma_e$; $\rho^6 \in \Gamma_e$

Table 4

Spin space-group types on V -lattices with $G = 8$. In this, and in the following tables a, b, a^0 , and b^0 are independently 0 or $\frac{1}{2}$, as long as there are no two operations in Γ_e with identical phase functions, and c is any integer between 0 and 7. For $\Gamma_e = n, n^0$, or $n1^0$ the integer j is co-prime with N , where $N = n$ unless $\Gamma_e = n^0$ and n is odd, in which case $N = 2n$. If N is odd a is necessarily 0. The integer $d = 1$ unless N is twice an odd number and $\Phi_e^{n_z^-}(\mathbf{h}^{(j)}\mathbf{c}) = \frac{1}{2}$, in which case $d = 1$ or 2. A_0 denotes the values $0\frac{1}{2}0\frac{1}{2}$ of a phase function on the horizontal generating vectors, and A_1 denotes the values $\frac{1}{2}0\frac{1}{2}0$ on the same generators. Lines $3a$ and $3b$ refer to distinct spin space-group types if $\Gamma_e = 2^02^02$, but give scale-equivalent solutions if $\Gamma_e = 222$, or $2^02^02^0$, where $3a$ is taken as the representative solution. The spin space group symbols for all groups in this table are of the form $P^{\Gamma_e}8_c$. For example, if $\Gamma_e = 222, G = 4$ and $\Gamma = 2^02^02^0$, then $\Phi_e^{n_z^-}(\mathbf{h}^{(j)}\mathbf{c}) = \frac{c}{8}$ can be chosen to be 0, the corresponding line in the Table is $3a$ or $3b$, but since for $\Gamma_e = 222$ they are scale-equivalent only $3a$ is taken. If, in addition, $\Phi_{r_8}(\mathbf{z}) = \frac{5}{8}$ the spin space group symbol is $P_{2c,4p,8}^{222}8_5^0$.

$\Gamma_e = 1;1^0;2;2^0;21^0$					
	8	$\Phi_e^{2_{\bar{z}}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_{r_8}(\mathbf{z})$	
1		ab	d^0b^0	$\frac{c}{8}$	
2	$2_{\bar{z}}$	$0\frac{1}{2}$		$\frac{c}{8} + \frac{1}{16}$	
$\Gamma_e = 222;2^02^02;2^02^02^0 \quad (\quad 2 \quad 4221^0) \quad 8 = \quad)$					
	$2_{\bar{x}}^{-1}$	$\Phi_e^{2_{\bar{x}}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_e^{2_{\bar{y}}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_e^{2_z^0}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_{r_8}(\mathbf{z})$
3a	$2_{\bar{x}}$	$0\frac{1}{2}$	$\frac{1}{2}0$		$\frac{c}{8}$
3b		ab	$\frac{1}{2}\frac{1}{2}$		$\frac{c}{8}$
4	$2_{\bar{y}}$	A_0b	A_1b	$a\frac{1}{2}$	$\frac{c}{8}$
$\Gamma_e = n;n^0;n1^0 \quad (\quad n \notin \quad ^{-1} = n_{\bar{z}})$					
	8	$\Phi_e^{n_{\bar{z}}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_{r_8}(\mathbf{z})$	
5		$a\frac{dj}{N}$	a^0b^0	$\frac{c}{8}$	
6	$n_{\bar{z}}$	$a\frac{dj}{n}$	a^0b^0	$\frac{c}{8} + \frac{dj}{8n}$	
7	$n_{\bar{z}}^2$	$a\frac{dj}{N}$	a^0b^0	$\frac{c}{8} + \frac{dj}{4N}$	
8	$n_{\bar{z}}^3$	$a\frac{dj}{n}$	a^0b^0	$\frac{c}{8} + \frac{3dj}{8n}$	
9	$n_{\bar{z}}^4$	$a\frac{dj}{N}$	a^0b^0	$\frac{c}{8} + \frac{dj}{2N}$	

Table 5

Spin space-group types on S -lattices with $G = 8$. In this and in the following tables c^0 is any integer between 0 and 3. For $\Gamma_e = n$, or n^0 , the integer j is co-prime with N , where $N = n$ unless $\Gamma_e = n^0$ and n is odd, in which case $N = 2n$. The spin space-group symbols for all groups in this table are of the form $S^{\Gamma_e}8_{c^0}$. For example, if $\Gamma_e = n, G = 4$ and $\Gamma = n22$ then $\Phi_e^{n_z^-}(\mathbf{h}^{(j)}\mathbf{c}) = \frac{c^0}{8}$ can be chosen to be $2_{\bar{x}}^-$ and the corresponding line in the Table is 9 (and n is necessarily 4). If, in addition, $j = 3$ and $\Phi_{r_8}(\mathbf{z} + \mathbf{h}) = \frac{1}{4}$ the spin space-group symbol is $S_{4,3,8}^48_2^{2_{\bar{x}}^-}$.

$\Gamma_e = 1;1^0;2;2^0$				
	8	$\Phi_e(\mathbf{k})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$	
1		$0\frac{1}{2}$	$\frac{c^0}{8}$	
2	$2\bar{z}$	$0\frac{1}{2}$	$\frac{c^0}{8} + \frac{1}{16}$	
$\Gamma_e = 222;2^02^02 \quad (\quad 2 \quad 4221^0) \quad 8 = \quad ; \quad 2^{-1} = 2\bar{y})$				
	$\Phi_e^{2\bar{z}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_e^{2\bar{y}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$	
3	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\frac{c^0}{8}$	
$\Gamma_e = n;n^0;n1^0$				
	$n\bar{\epsilon}^{-1}$	8	$\Phi_e^{n\bar{z}}(\mathbf{h}^{(j)}\mathbf{c})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$
4	$n\bar{z}$		$0\frac{j}{N}$	$\frac{c^0}{8}$
5	$n\bar{z}$	$n\bar{z}$	$0\frac{j}{n}$	$\frac{c^0}{8} + \frac{j}{8n}$
6	$n\bar{z}$	$n\bar{z}^2$	$0\frac{j}{N}$	$\frac{c^0}{8} + \frac{j}{4N}$
7	$n\bar{z}$	$n\bar{z}^3$	$0\frac{j}{n}$	$\frac{c^0}{8} + \frac{3j}{8n}$
8	$n\bar{z}$	$n\bar{z}^4$	$0\frac{j}{N}$	$\frac{c^0}{8} + \frac{j}{2N}$
9	$n\bar{z}^{-1}$		$\frac{1}{2}\frac{j}{n} \ (n = 4)$	$\frac{c^0}{8}$

Table 6

Spin space-group types on V -lattices with $G = \bar{8}$. The possible values of a, b, a^0, b^0, N, j , and d , as well as the notations A_0 and A_1 are as explained in the caption of Table 4. Recall that since $\bar{r}_8$ is a generator of G , $\bar{8}$ is necessarily . Lines $2a$ and $2b$ refer to distinct spin space-group types if $\Gamma_e = 2^0 2^0 2$ but are scale-equivalent if $\Gamma_e = 222$, or $2^0 2^0 2^0$, for which line $2a$ suffices. Spin space-group symbols for all groups in this table are of the form $P^{\Gamma_e} \bar{8}$.

$\Gamma_e = 1;1^0;2;2^0;21^0$				
	$\Phi_e^{2\bar{z}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(\theta)}\mathbf{c})$		
1	ab	a^0b^0		
$\Gamma_e = 222;2^02^0_2;2^02^0_2$				
	$2\bar{x}^{-1}$	$\Phi_e^{2\bar{x}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^{2\bar{y}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^{2\bar{z}}(\mathbf{b}^{(\theta)}\mathbf{c})$
2a	$2\bar{x}^{-}$	$0\frac{1}{2}$	$\frac{1}{2}0$	
2b	$2\bar{x}^{-}$	ab	$\frac{1}{2}\frac{1}{2}$	
3	$2\bar{y}^{-}$	A_0b	A_1b	$a\frac{1}{2}$
$\Gamma_e = n;n^0;n1^0$ ($n\bar{x}^{-1} = n\bar{z}^{-1}$)				
	8	$\Phi_e^{n\bar{z}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(\theta)}\mathbf{c})$	
4		$a\frac{d^j}{N}$	a^0b^0	

Table 7

Spin space group-types on S -lattices with $G = \bar{8}$. The possible values of N and j are as explained in the caption of Table 5. Recall that since $\bar{r}_8$ is a generator of G , $\bar{8}$ is necessarily . Spin space-group symbols for all groups in this table are of the form $S^{\Gamma_e} \bar{8}$.

$\Gamma_e = 1;1^0;2;2^0;21^0$			
	$\Phi_e(\mathfrak{h}^{(j)}\mathfrak{c})$		
1	$0\frac{1}{2}$		
$\Gamma_e = 222;2^{02}02$			
	$2\bar{x}^{-1}$	$\Phi_e^{2\bar{x}}(\mathfrak{h}^{(j)}\mathfrak{c})$	$\Phi_e^{2\bar{y}}(\mathfrak{h}^{(j)}\mathfrak{c})$
2	$2\bar{y}^{-}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$
$\Gamma_e = n;n^0$			
	$n\bar{x}^{-1}$	$\Phi_e^{n\bar{z}}(\mathfrak{h}^{(j)}\mathfrak{c})$	
3	$n\bar{z}^{-1}$	$0\frac{j}{N}$	
4	$n\bar{z}^{-}$	$\frac{1}{2}\frac{j}{n} \ (n=4)$	

research papers

Table 8
Spin space-group types on V -lattices with $G = 8mm$. The possible values of a, b, a^0, b^0, N, j , and d , as well as the notations A_0 and A_1 are as explained in the caption of Table 4. Lines 5a and 5b refer to distinct spin space-group types if $\Gamma_e = 2^02^02$ but are scale-equivalent if $\Gamma_e = 222$, or $2^02^02^0$, for which line 3a suffices. $\hat{a}; \hat{b}$ and $\tilde{a}$ denote either 0 or $\frac{1}{2}$. Spin space-group symbols are of the form $P^{\Gamma_e}8\ m\ m$ where the primary 8 is replaced by 8_4 if $\tilde{a} = \frac{1}{2}$ and the secondary m is replaced according to the values of $\hat{a}$ and $\hat{b}$: $\hat{a} = \hat{b} = 0 \rightarrow m \rightarrow m, \hat{a} = 0; \hat{b} = \frac{1}{2} \rightarrow m \rightarrow c, \hat{a} = \frac{1}{2}; \hat{b} = 0 \rightarrow m \rightarrow b, \hat{a} = \hat{b} = \frac{1}{2} \rightarrow m \rightarrow n$. The tertiary m is replaced by c if either $\hat{b}$ or $\tilde{a}$ (but not both) is $\frac{1}{2}$. Furthermore, a subscript a is added to the secondary m when $\Phi_m(\mathbf{b}^{\theta}) = A_0 + \hat{a}$. For example, if $\Gamma_e = 2^02^02, G = 4mm, \Gamma = 2^02^02^0$, then can be chosen to be 0 and the spin space group is described by line 5a or 5b, if $ab = \frac{1}{2}0, \hat{a} = \frac{1}{2}, \hat{b} = 0$ and $\tilde{a} = 0$ the spin space group symbol will be $P_{PS2c}^{2^02^02}8^0nc^0$.

$\Gamma_e = 1;1^0;2;2^0;21^0$							(⁸ =)	
	1	2	$\Phi_e^{2\bar{z}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(\theta)})$	$\Phi_m(\mathbf{z})$	$\Phi_{r_8}(\mathbf{z})$	
1			ab	$\hat{a}b^0$	$\hat{a}$	$\hat{b}$	$\tilde{a}$	
2		$2\bar{z}$	$0\frac{1}{2}$	$\frac{1}{2}a$	$\hat{a}$	$\hat{b}$	$\tilde{a}$	
3	$2\bar{z}$		$0\frac{1}{2}$	$\frac{1}{2}a$	$\hat{a}$	$\hat{b}$	$\tilde{a}$	
			$\frac{1}{2}a$	a^0b^0	$\hat{a} + A_0$	$\hat{b}$	$\tilde{a} + \frac{a}{2}$	
4	$2\bar{z}$	$2\bar{z}$	$0\frac{1}{2}$	$\frac{1}{2}b$	$\hat{a}$	$\hat{b} + \frac{1}{4}$	$\tilde{a} + \frac{1}{4}$	
$\Gamma_e = 222;2^02^02;2^02^02^0$							($2\bar{x}^{-1} = 2\bar{x}$) ² =)	
	$2\bar{x}^{-1}$	1	$\Phi_e^{2\bar{x}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^{2\bar{y}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^{2\bar{z}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(\theta)})$	$\Phi_m(\mathbf{z})$	$\Phi_{r_8}(\mathbf{z})$
5a	$2\bar{x}$		$0\frac{1}{2}$	$\frac{1}{2}0$		$\hat{a}$	$\hat{b}$	$\tilde{a}$
5b	$2\bar{x}$		ab	$\frac{1}{2}\frac{1}{2}$		$\hat{a}$	$\hat{b}$	$\tilde{a}$
6	$2\bar{y}$	$2\bar{z}$	A_0b	A_1b	$a\frac{1}{2}$	$A_0 + \hat{a}$	$\hat{b}$	$\tilde{a}$
$\Gamma_e = n;n^0;n1^0$							($n\bar{\epsilon}^{-1} = n\bar{z}^{-1} = n\bar{z}$) ⁸ = (¹ ⁴)	
	1	2	$\Phi_e^{n\bar{z}}(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(\theta)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(\theta)})$	$\Phi_m(\mathbf{z})$	$\Phi_{r_8}(\mathbf{z})$	
7			$\frac{dj}{N}$	a^0b^0	$\hat{a}$	$\hat{b}$	$\tilde{a}$	
8		$n\bar{\epsilon}$	$0\frac{j}{n}$	ab	$\hat{a}$	$\hat{b} + \frac{j}{2n}$	$\tilde{a}$	
9	$n\bar{z}$		$0\frac{j}{n}$	ab	$\hat{a}$	$\hat{b}$	$\tilde{a} + \frac{j}{2n}$	
			$\frac{1}{2}\frac{dj}{n}$	ab	$\hat{a} + A_0$	$\hat{b}$	$\tilde{a} + \frac{dj}{2n}$	
10	$n\bar{z}$	$n\bar{z}$	$0\frac{j}{n}$	ab	$\hat{a}$	$\hat{b} + \frac{j}{2n}$	$\tilde{a} + \frac{j}{2n}$	

Table 9

Spin space-group types on S -lattices with $G = 8mm$. The possible values of N and j are as explained in the caption of Table 5, and the notation A_0 is explained in the caption of Table 4. $\hat{a}$ and $\tilde{a}$ denote either 0 or $\frac{1}{2}$. For any choice of spin-space operations ($\bar{1} \quad \bar{4} = \bar{8}$). Spin space-group symbols are of the form $S^{\Gamma_e} 8 \quad m \quad m$ where the primary 8 is replaced by 8_2 if $\hat{a} = \frac{1}{2}$ and the secondary m is replaced by d if $\hat{a} = \frac{1}{2}$. The tertiary m is replaced by c if $\tilde{a} = \frac{1}{2}$. A subscript a is added to the secondary m if $\Phi_m(\mathbf{h}^{(i)}) = \hat{a} + A_0$.

$\Gamma_e = 1;1^0;2;2^0$							($\bar{8} = \bar{1}$)	
	1	2	$\Phi_e(\mathbf{k})$	$\Phi_m(\mathbf{h}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$		
1			$\frac{1}{2}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a}$	$\frac{1}{2}\hat{a}$		
2		$2\bar{z}$	$0\frac{1}{2}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a} + \frac{1}{4}$	$\frac{1}{2}\hat{a}$		
3	$2\bar{z}$		$0\frac{1}{2}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a}$	$\frac{1}{2}\hat{a} + \frac{1}{4}$		
4	$2\bar{z}$	$2\bar{z}$	$0\frac{1}{2}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a} + \frac{1}{4}$	$\frac{1}{2}\hat{a} + \frac{1}{4}$		
$\Gamma_e = 222;2^{02}2^0$							($2\bar{x} \quad \bar{1} = 2\bar{y} \quad \bar{2} = 2\bar{z}$)	
	$2\bar{x} \quad \bar{1}$	1	$\Phi_e^{2\bar{x}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2\bar{y}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{h}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$	
5	$2\bar{y}$	$2\bar{z}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a} + \frac{1}{4}$	$\frac{1}{2}\hat{a} + \frac{1}{4}$	
$\Gamma_e = n;n^0$							($n\bar{x} \quad \bar{1} = n\bar{z} \quad \bar{1}$)	
	$n\bar{x} \quad \bar{1}$	1	2	8	$\Phi_e^{n\bar{z}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{h}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$
6	$n\bar{z}$				$0\frac{j}{N}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a}$	$\frac{1}{2}\hat{a}$
7	$n\bar{z}$		$n\bar{x}$		$0\frac{j}{n}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a} + \frac{j}{2n}$	$\frac{1}{2}\hat{a}$
8	$n\bar{z}$	$n\bar{z}$		$n\bar{x}$	$0\frac{j}{n}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a}$	$\frac{1}{2}\hat{a} + \frac{j}{2n}$
9	$n\bar{z}$	$n\bar{z}$	$n\bar{z}$	$n\bar{x}$	$0\frac{j}{n}$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a} + \frac{j}{2n}$	$\frac{1}{2}\hat{a} + \frac{j}{2n}$
10	$n\bar{z}^{-1}$				$\frac{1}{2}\frac{j}{n} (n = 4)$	$\hat{a}$	$\tilde{a} + \frac{1}{2}\hat{a}$	$\frac{1}{2}\hat{a}$
11	$n\bar{z}^{-1}$	$n\bar{z}^{-1}$			$\frac{1}{2}\frac{j}{n} (n = 4)$	$\hat{a} + A_0$	$\tilde{a} + \frac{1}{2}\hat{a}$	$\frac{1}{2}(\frac{1}{2} \hat{a}) \frac{j}{8}$

Table 10

Spin space-group types on V -lattices with $G = \bar{8}m2$. The possible values of a, b, a^0, b^0, N, j , and d , as well as the notations A_0 and A_1 are as explained in the caption of Table 4. Lines 4a and 4b refer to distinct spin space-group types if $\Gamma_e = 2^{02}2^0$ but are scale-equivalent if $\Gamma_e = 222$, or $2^{02}2^0$, for which line 4a suffices. $\hat{a}$ and $\hat{b}$ denote either 0 or $\frac{1}{2}$. Note that since $\bar{8}$ is a generator of $G \quad \bar{8} = \bar{1}$. Spin space-group symbols are of the form $P^{\Gamma_e} \bar{8} \quad m \quad 2$ where the secondary m is replaced as in Table 8 above.

$\Gamma_e = 1;1^0;2;2^0;21^0$							
	1	2	$\Phi_e^{2\bar{z}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{h}^{(i)})$	$\Phi_m(\mathbf{z})$	
1			ab	$\hat{a}b^0$	$\hat{a}$	$\hat{b}$	
2	$2\bar{z}$		$\frac{1}{2}0$	$a\frac{1}{2}$	$\hat{a} + A_0$	$\hat{b}$	
3	$2\bar{z}$	$2\bar{z}$	$0\frac{1}{2}$	$\frac{1}{2}b$	$\hat{a}$	$\hat{b} + \frac{1}{4}$	
$\Gamma_e = 222;2^{02}2^0;2^{02}2^0$ ($\bar{2} = \bar{1}; 2\bar{x} \quad \bar{1} = 2\bar{y}$)							
	$2\bar{x} \quad \bar{1}$	1	$\Phi_e^{2\bar{x}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2\bar{y}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2\bar{z}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{h}^{(i)})$	$\Phi_m(\mathbf{z})$
4a	$2\bar{x}$		$0\frac{1}{2}$	$\frac{1}{2}0$		$\hat{a}$	$\hat{b}$
4b	$2\bar{x}$		ab	$\frac{1}{2}\frac{1}{2}$		$\hat{a}$	$\hat{b}$
5	$2\bar{y}$	$2\bar{z}$	A_0b	A_1b	$a\frac{1}{2}$	$\hat{a} + A_0$	$\hat{b}$
$\Gamma_e = n;n^0;n1^0$ ($n\bar{x} \quad \bar{1} = n\bar{z}^{-1}; n\bar{z} \quad \bar{1} = n\bar{z}; \bar{2} = (\bar{1} \quad \bar{1})^1$)							
	1		$\Phi_e^{n\bar{z}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{h}^{(i)})$	$\Phi_m(\mathbf{z})$	
6			$a\frac{d j}{N}$	a^0b^0	$\hat{a}$	$\hat{b}$	
7			$0\frac{j}{n}$	ab	$\hat{a}$	$\hat{b} + \frac{j}{n}$	

research papers

Table 11

Spin space-group types on S -lattices with $G = \overline{8}m2$. The possible values of N and j are as explained in the caption of Table 5. $\hat{a}$ denotes either 0 or $\frac{1}{2}$. Note that since $\overline{8}$ is a generator of $G \cong \overline{8} = \langle \overline{2} \rangle^4$. In addition $\overline{2} = \langle \overline{4} \rangle^2$. Spin space-group symbols are of the form $S^{\Gamma_e} \overline{8} \cdot m \cdot 2$ where the secondary m is replaced as in Table 9 above.

$\Gamma_e = 1;1^0;2;2^0$					
	$\overline{1}$	$\Phi_e(\mathbf{k})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	
1		$0\frac{1}{2}$	$\hat{a}$	$\frac{1}{2}\hat{a}$	
2	$2\overline{z}$	$0\frac{1}{2}$	$\hat{a}$	$\frac{1}{2}\hat{a} + \frac{1}{4}$	
$\Gamma_e = 222;2^02^02$ ($2\overline{x}^{-1} = 2\overline{y}^{-1} = 2\overline{z}$)					
	$\overline{1}$	$\Phi_e^{2\overline{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2\overline{y}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$
3	$2\overline{z}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\hat{a}$	$\frac{1}{2}\hat{a} + \frac{1}{4}$
$\Gamma_e = n;n^0$ ($n\overline{x}d^{-1} = n\overline{z}^{-1}d^{-1}$)					
	$n\overline{x}^{-1}$	$\overline{1}$	$\Phi_e^{n\overline{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$
4	$n\overline{z}^{-1}$		$0\frac{j}{N}$	$\hat{a}$	$\frac{1}{2}\hat{a}$
5	$n\overline{z}^{-1}$	$n\overline{z}^{-1}$	$0\frac{j}{n}$	$\hat{a}$	$\frac{1}{2}\hat{a} + \frac{j}{2n}$
6	$n\overline{z}$		$\frac{1}{2}\frac{j}{n}$ ($n = 4$)	$\hat{a}$	$\frac{1}{2}\hat{a}$

Table 12

Spin space-group types for V -lattices with $G = 822$. The possible values of a, b, a^0, b^0, c, N, j , and d , as well as the notations A_0 and A_1 are as explained in the caption of Table 4. Lines $4a$ and $4b$ refer to distinct spin space-group types if $\Gamma_e = 2^02^02$ but are scale-equivalent if $\Gamma_e = 222$, or $2^02^02^0$, for which line $4a$ suffices. $\hat{a}$ denotes either 0 or $\frac{1}{2}$. Note that $\overline{2} = \langle \overline{4} \rangle^2$. Spin space-group symbols are of the form $P^{\Gamma_e} 8_c \cdot 2 \cdot 2$, where the secondary 2 is replaced by 2_1 if $\hat{a} = \frac{1}{2}$. An additional subscript a is added to the secondary 2 if $\Phi_d(\mathbf{b}^{(i)}) = \hat{a} + A_0$.

$\Gamma_e = 1;1^0;2;2^0;21^0$							
	1	8	$\Phi_e^{2\overline{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{b}^{(i)})$	$\Phi_{r_8}(\mathbf{z})$	
1			ab	$\hat{a}b^0$	$\hat{a}$	$\frac{c}{8}$	
2		$2\overline{z}$	$0\frac{1}{2}$	$\frac{1}{2}a$	$\hat{a}$	$\frac{c}{8} + \frac{1}{16}$	
3	$2\overline{z}$		$\frac{1}{2}0$	$a\frac{1}{2}$	$\hat{a} + A_0$	$\frac{c}{8}$	
$\Gamma_e = 222;2^02^02;2^02^02^0$ ($2\overline{x}^{-1} = 2\overline{y}^{-1} = 2\overline{z}$)							
	$2\overline{x}^{-1}$	1	$\Phi_e^{2\overline{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2\overline{y}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2\overline{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{b}^{(i)})$	$\Phi_{r_8}(\mathbf{z})$
4a	$2\overline{x}$		$0\frac{1}{2}$	$\frac{1}{2}0$		$\hat{a}$	$\frac{c}{8}$
4b			ab	$\frac{1}{2}\frac{1}{2}$		$\hat{a}$	$\frac{c}{8}$
5	$2\overline{y}$	$2\overline{z}$	A_0b	A_1b	$a\frac{1}{2}$	$\hat{a} + A_0$	$\frac{c}{8}$
$\Gamma_e = n;n^0;n1^0$ ($n\overline{x}^{-1} = n\overline{z}; n\overline{z}^{-1} = n\overline{x}^{-1}; \overline{1} = \overline{z}$)							
	8	$\Phi_e^{n\overline{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{b}^{(i)})$	$\Phi_{r_8}(\mathbf{z})$		
6		$a\frac{dj}{N}$	a^0b^0	$\hat{a}$	$\frac{c}{8}$		
7	$n\overline{z}$	$0\frac{j}{n}$	ab	$\hat{a}$	$\frac{c}{8} + \frac{j}{8n}$		
8	$n\overline{z}^3$	$0\frac{j}{n}$	ab	$\hat{a}$	$\frac{c}{8} + \frac{3j}{8n}$		
9	$n\overline{z}^2$	$a\frac{dj}{N}$	a^0b^0	$\hat{a}$	$\frac{c}{8} + \frac{dj}{4N}$		
10	$n\frac{A}{z}$	$a\frac{dj}{N}$	a^0b^0	$\hat{a}$	$\frac{c}{8} + \frac{dj}{2N}$		

Table 13

Spin space-group types for S -lattices with $G = 822$. The possible values of c^0 , N and j are explained in the caption Table 5. Note that $\bar{1} = \bar{2}$. Spin space-group symbols are of the form $S^{\Gamma_e} 8_{c^0} 2_{\bar{2}}$, where the secondary $\bar{2}$ is replaced by 2_1 if $\Phi_d(\mathbf{h}^{\theta}) = \frac{1}{2}$.

$\Gamma_e = 1;1^0;2;2^0$					
	$\bar{1}$	$\bar{8}$	$\Phi_e(\mathbf{h}^{\theta})\mathbf{c}$	$\Phi_d(\mathbf{h}^{\theta})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$
1			$\frac{1}{2}$	0	$\frac{c^0}{8}$
2		$2_{\bar{c}}$	$0\frac{1}{2}$	0	$\frac{c^0}{8} + \frac{1}{16}$
3	$2_{\bar{c}}$		$0\frac{1}{2}$	$\frac{1}{2}$	$\frac{c^0}{8}$
$\Gamma_e = 222;2^0 2^0 2^0$ ($\bar{2} \ 4221^0$) $\bar{8} = \bar{2}$; $\bar{2}^1 = 2_{\bar{c}}^1 = 2_{\bar{y}}^1$)					
	$\bar{1}$	$\Phi_e^{2_{\bar{c}}}(\mathbf{h}^{\theta})\mathbf{c}$	$\Phi_e^{2_{\bar{y}}}(\mathbf{h}^{\theta})\mathbf{c}$	$\Phi_d(\mathbf{h}^{\theta})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$
4	$2_{\bar{c}}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\frac{1}{2}$	$\frac{c^0}{8}$
$\Gamma_e = n;n^0$ ($n\bar{c}^1 = n_{\bar{c}}^1$; $\bar{1} = \bar{2} = \bar{3}$)					
	$n\bar{c}^1$	$\bar{8}$	$\Phi_e^{n_{\bar{c}}}(\mathbf{h}^{\theta})\mathbf{c}$	$\Phi_d(\mathbf{h}^{\theta})$	$\Phi_{r_8}(\mathbf{z} + \mathbf{h})$
5	$n_{\bar{c}}$		$0\frac{j}{N}$	0	$\frac{c^0}{8}$
6	$n_{\bar{c}}$	$n_{\bar{c}}$	$0\frac{j}{n}$	0	$\frac{c^0}{8} + \frac{j}{8n}$
7	$n_{\bar{c}}$	$n_{\bar{c}}^2$	$0\frac{j}{N}$	0	$\frac{c^0}{8} + \frac{j}{4N}$
8	$n_{\bar{c}}$	$n_{\bar{c}}^3$	$0\frac{j}{n}$	0	$\frac{c^0}{8} + \frac{3j}{8n}$
9	$n_{\bar{c}}$	$n_{\bar{c}}^4$	$0\frac{j}{N}$	0	$\frac{c^0}{8} + \frac{j}{2N}$
10	$n_{\bar{c}}^1$		$\frac{1}{2}\frac{j}{n}$ ($n = 4$)	0	$\frac{c^0}{8}$

Table 14

Spin space-group types on V -lattices with $G = \bar{8}2m$. The possible values of a , b , a^0 , b^0 , N , j , and d , as well as the notations A_0 and A_1 are as explained in the caption of Table 4. Lines $3a$ and $3b$ refer to distinct spin space-group types if $\Gamma_e = 2^0 2^0 2^0$ but are scale-equivalent if $\Gamma_e = 222$, or $2^0 2^0 2^0$, for which line $3a$ suffices. $\hat{a}$ and $\hat{b}$ denote either 0 or $\frac{1}{2}$. Note that for all choices of spin-space operations $\bar{8} = \bar{2}$ and $\bar{2} = \bar{3}$. Spin space-group symbols are of the form $P^{\Gamma_e} \bar{8} 2_{\bar{m}}$ where $\bar{2}$ is replaced by 2_1 if $\hat{a} = \frac{1}{2}$, and $\bar{m}$ is replaced by c if $\hat{b} = \frac{1}{2}$. A subscript a is added to the secondary $\bar{2}$ if $\Phi_d(\mathbf{h}^{\theta}) = \hat{a} + A_0$.

$\Gamma_e = 1;1^0;2;2^0;21^0$							
	1	$\Phi_e^{2_{\bar{c}}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{h}^{(i)})$	$\Phi_d(\mathbf{z})$		
1		ab	a^0b^0	$\dot{a}$	$\dot{b}$		
2	$2_{\bar{c}}$	$0\frac{1}{2}$	a^0b^0	$\dot{a}$	$\dot{b} + \frac{1}{4}$		
		$\frac{1}{2}b$	a^0b^0	$\dot{a} + A_0$	$\dot{b} + \frac{1}{2}a$		
$\Gamma_e = 222;2^02^02;2^02^02^0$ ($2_{\bar{x}}^{-1} = 2_{\bar{y}}^{-1}$)							
	$2_{\bar{x}}^{-1}$	1	$\Phi_e^{2_{\bar{c}}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2_{\bar{y}}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2_{\bar{z}}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{h}^{(i)})$	$\Phi_d(\mathbf{z})$
3a	$2_{\bar{x}}$		$0\frac{1}{2}$	$\frac{1}{2}0$		$\dot{a}$	$\dot{b}$
3b			ab	$\frac{1}{2}\frac{1}{2}$		$\dot{a}$	$\dot{b}$
4	$2_{\bar{y}}$	$2_{\bar{z}}$	A_0b	A_1b	$a\frac{1}{2}$	$\dot{a} + A_0$	$\dot{b}$
$\Gamma_e = n;n^0;n1^0$ ($n_{\bar{x}}^{-1} = n_{\bar{y}}^{-1} = n_{\bar{z}}^{-1}$)							
	1	$\Phi_e^{n_{\bar{c}}}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{h}^{(i)})$	$\Phi_d(\mathbf{z})$		
5		$a\frac{d j}{N}$	a^0b^0	$\dot{a}$	$\dot{b}$		
6	$n_{\bar{c}}$	$0\frac{j}{n}$	a^0b^0	$\dot{a}$	$\dot{b} - \frac{j}{2n}$		
		$\frac{1}{2}\frac{d j}{n}$	a^0b^0	$\dot{a} + A_0$	$\dot{b} - \frac{d j}{2n}$		

research papers

Table 15

Spin space-group types for S -lattices with $G = \overline{8}2m$. The possible values of N and j are explained in the caption of Table 5, and the notation A_0 is as explained in the caption of Table 4. $\dot{b}$ denotes either 0 or $\frac{1}{2}$. Note that since $\overline{8}$ is a generator of $G^{\overline{8}} = \overline{8}$. Spin space-group symbols are $S^{\Gamma_e \overline{8} 2 m}$ if $\dot{b} = 0$ and $S^{\Gamma_e \overline{8} 2 c}$ if $\dot{b} = \frac{1}{2}$. The secondary 2 is replaced by 2₁ if $\Phi_d(\mathbf{h}^{(i)}) = \frac{1}{2}$ and by 2_a if $\Phi_d(\mathbf{h}^{(i)}) = 0\frac{1}{2}0\frac{1}{2}$.

$\Gamma_e = 1;1^0;2;2^0$					
	1	2	$\Phi_e(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{h}^{(i)})$	$\Phi_d(\mathbf{z} + \mathbf{h})$
1			$\frac{1}{2}$	0	$\dot{b}$
2		2^-	$0\frac{1}{2}$	$\frac{1}{2}$	$\dot{b} + \frac{1}{4}$
3	2^-		$0\frac{1}{2}$	0	$\dot{b} - \frac{1}{4}$
4	2^-	2^-	$0\frac{1}{2}$	$\frac{1}{2}$	$\dot{b}$
$\Gamma_e = 222;2^02^02^0 \quad (\quad 2^- \quad ^1 = \quad 2^- \quad ^1 = \quad 2^- \quad ^1 \quad) \quad ^1 \quad = \quad ^2 = \quad)$					
	$\Phi_e^{2^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{h}^{(i)})$	$\Phi_d(\mathbf{z} + \mathbf{h})$	
5	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\frac{1}{2}$	$\dot{b}$	
$\Gamma_e = n;n^0 \quad (\quad n^- \quad ^1 = \quad n^- \quad ^1 ; \quad ^2 = \quad)$					
	$n^- \quad ^1$	1	$\Phi_e^{n^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_d(\mathbf{h}^{(i)})$	$\Phi_d(\mathbf{z} + \mathbf{h})$
6	$n^- \quad ^1$		$0\frac{j}{N}$	0	$\dot{b} - \frac{j}{2N}$
7	$n^- \quad ^1$	n^-	$0\frac{j}{n}$	0	$\dot{b} - \frac{j}{2n}$
8	n^-		$\frac{1}{2}\frac{j}{n} \ (n = 4)$	A_0	$\dot{b}$
9	n^-	n^-	$\frac{1}{2}\frac{j}{n} \ (n = 4)$	A_0	$\dot{b} - \frac{j}{8}$

Table 16

Spin space-group types on V -lattices with $G = 8\overline{3}m$. The possible values of a, b, a^0, b^0, N, j , and d , as well as the notations A_0 and A_1 are as explained in the caption of Table 4. Lines 3a and 3b refer to distinct spin space-group types if $\Gamma_e = 2^02^02^0$ but are scale-equivalent if $\Gamma_e = 222$, or $2^02^02^0$, for which line 3a suffices. $\check{a}$ and $\tilde{a}$ denote either 0 or $\frac{1}{2}$. Note that $2^-1 = 2^-1$. Spin space-group symbols are of the form $P^{\Gamma_e \overline{8} \overline{3} m}$ where $\overline{8}$ is replaced by 8_4 if $\check{a} = \frac{1}{2}$ and m is replaced by n if $\check{a} = \frac{1}{2}$, a subscript a is added if $\Phi_h(\mathbf{h}^{(i)}) = \check{a} + A_0$.

$\Gamma_e = 1;1^0;2;2^0;21^0$ ($\overline{8} = \overline{8}$)						
	1	$\Phi_e^{2^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_h(\mathbf{h}^{(i)})$	$\Phi_{r_8}(\mathbf{z})$	
1		ab	a^0b^0	$\check{a}$	$\tilde{a}$	
2	2^-	$0\frac{1}{2}$	$\frac{1}{2}b$	$\check{a}$	$\tilde{a} + \frac{1}{4}$	
		$\frac{1}{2}b$	a^0b^0	$\check{a} + A_0$	$\tilde{a} + \frac{b}{2}$	
$\Gamma_e = 222;2^02^02^0;2^02^02^0$ ($2^-1 = 2^-; \overline{1} = \overline{8} = \overline{8}$)						
	2^-1	$\Phi_e^{2^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^{2^0}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_h(\mathbf{h}^{(i)})$	$\Phi_{r_8}(\mathbf{z})$
3a	2^-	$0\frac{1}{2}$	$\frac{1}{2}0$		$\check{a}$	$\tilde{a}$
3b		ab	$\frac{1}{2}\frac{1}{2}$		$\check{a}$	$\tilde{a}$
4	2^-	A_0b	A_1b	$a\frac{1}{2}$	$\check{a}$	$\tilde{a}$
$\Gamma_e = n;n^0$ ($n^-1 = n^-; n^-1 = n^-1; \overline{8} = (\overline{1})^4$)						
	1	$\Phi_e^{n^-}(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{h}^{(i)}\mathbf{c})$	$\Phi_h(\mathbf{h}^{(i)})$	$\Phi_{r_8}(\mathbf{z})$	
5		$a\frac{dj}{N}$	a^0b^0	$\check{a}$	$\tilde{a}$	
6	n^-1	$0\frac{j}{n}$	ab	$\check{a}$	$\tilde{a}$	
		$\frac{1}{2}\frac{dj}{n}$	ab	$\check{a} + A_0$	$\tilde{a} + \frac{dj}{2n}$	

Table 17

Spin space-group types on S -lattices with $G = 8m$. The possible values of N and j are explained in the caption of Table 5, and the notation A_0 is explained in the caption of Table 4. Note that $2 = \frac{1}{2}$. $\check{a}$ denotes either 0 or $\frac{1}{2}$. Spin space-group symbols are $S^{\Gamma_e} 8 = m$ if $\check{a} = 0$ and $S^{\Gamma_e} 8_2 = a$ if $\check{a} = \frac{1}{2}$.

$\Gamma_e = 1; 1^0; 2; 2^0$					$(\begin{smallmatrix} 8 \\ = \end{smallmatrix})$
	1	$\Phi(\mathfrak{h}^{(i)}\mathfrak{c})$	$\Phi_h(\mathfrak{h}^{(i)})$	$\Phi_{r_h}(\mathfrak{z} + \mathfrak{h})$	
1		$0\frac{1}{2}$	$\check{a}$	$\frac{1}{2}\check{a}$	
2	$2_{\bar{z}}$	$0\frac{1}{2}$	$\check{a}$	$\frac{1}{2}\check{a} + \frac{1}{4}$	
$\Gamma_e = 222; 2^0 2^0 2$					$(\begin{smallmatrix} 2_{\bar{x}}^{-1} = 2_{\bar{x}}; 1 \\ = 8 = \end{smallmatrix})$
	$2_{\bar{x}}^{-1}$	$\Phi_e^{2_{\bar{x}}}(\mathfrak{h}^{(i)}\mathfrak{c})$	$\Phi_e^{2_{\bar{y}}}(\mathfrak{h}^{(i)}\mathfrak{c})$	$\Phi_h(\mathfrak{h}^{(i)})$	$\Phi_{r_h}(\mathfrak{z} + \mathfrak{h})$
3	$2_{\bar{y}}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\check{a}$	$\frac{1}{2}\check{a}$
$\Gamma_e = n; n^0$					$(\begin{smallmatrix} n_{\bar{z}}^{-1} = n_{\bar{z}}^{-1}; 8 \\ = (\begin{smallmatrix} 1 \\ 2 \end{smallmatrix})^4 \end{smallmatrix})$
	$n_{\bar{z}}^{-1}$	1	$\Phi_{\bar{z}}^{n_{\bar{z}}}(\mathfrak{h}^{(i)}\mathfrak{c})$	$\Phi_h(\mathfrak{h}^{(i)})$	$\Phi_{r_h}(\mathfrak{z} + \mathfrak{h})$
4	$n_{\bar{z}}$		$0\frac{j}{N}$	$\check{a}$	$\frac{1}{2}\check{a}$
5	$n_{\bar{z}}$	$n_{\bar{z}}^{-1}$	$0\frac{j}{n}$	$\check{a}$	$\frac{1}{2}\check{a} + \frac{j}{2n}$
6	$n_{\bar{z}}^{-1}$		$\frac{1}{2}\frac{j}{n} (n = 4)$	$\check{a}$	$\frac{1}{2}\check{a}$
7	$n_{\bar{z}}^{-1}$	$n_{\bar{z}}^{-1}$	$\frac{1}{2}\frac{j}{n} (n = 4)$	$\check{a} + A_0$	$\frac{1}{2}\check{a} - \frac{1}{2}\frac{j}{n} (n = 4)$

Spin space-group types on V -lattices with $G = 8mmm$. The possible values of a, b, a^0, b^0, N, j , and d , as well as the notations A_0 and A_1 are explained in the caption of Table 4. Lines 7a and 7b refer to distinct spin space-group types if $\Gamma_e = 2^02^02$ but are scale-equivalent if $\Gamma_e = 222$, or $2^02^02^0$, for which line 7a suffices. Note that $\begin{smallmatrix} 2 \\ 1 \end{smallmatrix} = \begin{smallmatrix} 1 \\ 2 \end{smallmatrix} = \hat{a}, \hat{b}, \hat{a}, \hat{b}$ and $\tilde{a}$ and $\tilde{b}$ denote either 0 or $\frac{1}{2}$. Spin space-group symbols are of the form $P^{\Gamma_e}c \Rightarrow m \ m \ m$, where 8 and m are replaced as in Table 16 above, and m and m are replaced as in Table 8 above.

$\Gamma_e = 1; 1^0; 2; 2^0; 21^0$ ($1 = 2 = 8 =$)										
	1	1	2	$\Phi_e^{2^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z})$	$\Phi_h(\mathbf{b}^{(i)})$	$\Phi_{r8}(\mathbf{z})$	
1				ab	$0b^0$	$\hat{a}$	$\hat{b}$	$\check{a}$	$\tilde{a}$	
2			2^-	$0\frac{1}{2}$	$\frac{1}{2}b^0$	$\hat{a}$	$\hat{b} + \frac{1}{4}$	$\check{a}$	$\tilde{a}$	
3		2^-		$\frac{1}{2}0$	$a^0\frac{1}{2}$	$\hat{a}$	$\hat{b}$	$\check{a} + A_0$	$\tilde{a}$	
4	2^-			$\frac{1}{2}0$	$a^0\frac{1}{2}$	$\hat{a} + A_0$	$\hat{b}$	$\check{a}$	$\tilde{a}$	
5	2^-	2^-		$0\frac{1}{2}$	$\frac{1}{2}b^0$	$\hat{a}$	$\hat{b}$	$\check{a}$	$\tilde{a} + \frac{1}{4}$	
				$\frac{1}{2}b$	a^0b^0	$\hat{a} + A_0$	$\hat{b}$	$\check{a} + A_0$	$\tilde{a} + \frac{b}{2}$	
6	2^-	2^-	2^-	$0\frac{1}{2}$	$\frac{1}{2}b^0$	$\hat{a}$	$\hat{b} + \frac{1}{4}$	$\check{a}$	$\tilde{a} + \frac{1}{4}$	
$\Gamma_e = 222; 2^0 2^0 2; 2^0 2^0$ ($2^- 1 = 2^- 1 = 2^-) 2 =$)										
	$2^- 1$	1	1	$\Phi_e^{2^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2^0}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z})$	$\Phi_h(\mathbf{b}^{(i)})$	$\Phi_{r8}(\mathbf{z})$
7a	2^-			$0\frac{1}{2}$	$\frac{1}{2}0$		$\hat{a}$	$\hat{b}$	$\check{a}$	$\tilde{b}$
7b				ab	$\frac{1}{2}\frac{1}{2}$		$\hat{a}$	$\hat{b}$	$\check{a}$	$\tilde{b}$
8	2^-	2^-		A_0b	A_1b	$a\frac{1}{2}$	$\hat{a} + A_0$	$\hat{b}$	$\check{a}$	$\tilde{b}$
$\Gamma_e = n; n^0; n1^0$ ($n^- 1 = n^- 1 = n^-; n^- 1 = n^- 1; 8 = (1 \uparrow; (1)^1 = 1)$)										
	1	2		$\Phi_e^{n^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z})$	$\Phi_h(\mathbf{b}^{(i)})$	$\Phi_{r8}(\mathbf{z})$	
9				$\frac{dj}{dN}$	a^0b^0	$\hat{a}$	$\hat{b}$	$\check{a}$	$\tilde{b}$	
10		n^-		$0\frac{j}{n}$	a^0b^0	$\hat{a}$	$\hat{b} + \frac{j}{2n}$	$\check{a}$	$\tilde{b}$	
11	n^-			$0\frac{j}{n}$	a^0b^0	$\hat{a}$	$\hat{b}$	$\check{a}$	$\tilde{b} + \frac{j}{2n}$	
				$\frac{1}{2}\frac{dj}{n}$	a^0b^0	$\hat{a} + A_0$	$\hat{b}$	$\check{a} + A_0$	$\tilde{b} + \frac{dj}{2n}$	
12	n^-	n^-		$0\frac{j}{n}$	a^0b^0	$\hat{a}$	$\hat{b} + \frac{j}{2n}$	$\check{a}$	$\tilde{b} + \frac{j}{2n}$	

Table 19

Spin space-group types on S -lattices with $G = 8mmm$. The possible values of N and j are explained in the caption of Table 5, and the notation A_0 is explained in the caption of Table 4. Note that $2 = 2^0$, $\tilde{a}$ and $\tilde{b}$ denote either 0 or $\frac{1}{2}$. Spin space-group symbols are $S^{\Gamma_e}8 = m\bar{m}m$ if $\tilde{a} = \tilde{b} = 0$, $S^{\Gamma_e}8 = m\bar{m}c$ if $\tilde{a} = 0$ and $\tilde{b} = \frac{1}{2}$, $S^{\Gamma_e}8 = n\bar{d}m$ if $\tilde{a} = \frac{1}{2}$ and $\tilde{b} = 0$ and $S^{\Gamma_e}8 = n\bar{d}c$ if $\tilde{a} = \tilde{b} = \frac{1}{2}$. For example, if $\Gamma_e = 7$, $G = 4mm$ and $\Gamma = (14)2^02^0$ the spin-space operations can be chosen to be $= (14)\bar{c}$ and $= 2^0_x$, is necessarily $= m\bar{2}G$. The corresponding line in the Table is 12, if $\tilde{a} = 0$, $\tilde{b} = \frac{1}{2}$ and $\Phi_e^{7z}(\mathbf{z} + \mathbf{h}) = \frac{2}{7}$, the spin space-group symbol is $S_{72c}^7 8^{14} m^{2z} mc^{14}$.

$\Gamma_e = 1; 1^0; 2; 2^0$										$(\begin{smallmatrix} 2 & 8 \\ & \end{smallmatrix} = \begin{smallmatrix} & \end{smallmatrix})$	
	1	1	1	2	$\Phi_e(\mathbf{k})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	$\Phi_h(\mathbf{b}^{(i)})$	$\Phi_{r_B}(\mathbf{z} + \mathbf{h})$		
1					$\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2}$		
2				$\bar{2}$	$0\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b} + \frac{1}{4}$	$\tilde{a}$	$\frac{\tilde{a}}{2}$		
3		2^-	2^-		$0\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a} + \frac{1}{2}$	$\frac{ia}{2}$		
4	2^-		2^-		$0\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a} + \frac{1}{2}$	$\frac{\tilde{a}}{2} + \frac{1}{4}$		
5	2^-		2^-	2^-	$0\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b} + \frac{1}{4}$	$\tilde{a} + \frac{1}{2}$	$\frac{\tilde{a}}{2} + \frac{1}{4}$		
6	2^-	2^-			$\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \frac{1}{4}$		
7	2^-	2^-		2^-	$0\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b} + \frac{1}{4}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \frac{1}{4}$		
$\Gamma_e = 222; 2^02$										$(\begin{smallmatrix} 2^- & 1 \\ & \end{smallmatrix} = \begin{smallmatrix} 2^- & 1 \\ & \end{smallmatrix} = 2^-; \begin{smallmatrix} 2^- & 1 \\ & \end{smallmatrix} = 2^-)$	
	1	1	1	2	$\Phi_e^{2^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	$\Phi_h(\mathbf{b}^{(i)})$	$\Phi_{r_B}(\mathbf{z} + \mathbf{h})$	
8	2^-		2^-	2^-	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b} + \frac{1}{4}$	$\tilde{a} + \frac{1}{2}$	$\frac{\tilde{a}}{2} + \frac{1}{4}$	
$\Gamma_e = n; n^0$										$(\begin{smallmatrix} n^- & 1 \\ & \end{smallmatrix} = n^-^1; \begin{smallmatrix} n^- & 1 \\ & \end{smallmatrix} = n^-^1; \begin{smallmatrix} 1 \\ & \end{smallmatrix} = (\begin{smallmatrix} 1 \\ & \end{smallmatrix})^1; \begin{smallmatrix} 1 \\ & \end{smallmatrix} = ;^8 = (\begin{smallmatrix} 1 \\ & \end{smallmatrix})^4)$	
	n^-^1	1	2		$\Phi_e^{n^-}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_m(\mathbf{b}^{(i)})$	$\Phi_m(\mathbf{z} + \mathbf{h})$	$\Phi_h(\mathbf{b}^{(i)})$	$\Phi_{r_B}(\mathbf{z} + \mathbf{h})$		
9	n^-				$0\frac{j}{N}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2}$		
10	n^-		n^-		$0\frac{j}{n}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \frac{j}{2n} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2}$		
11	n^-	n^-			$0\frac{j}{n}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \frac{j}{2n}$		
12	n^-	n^-	n^-		$0\frac{j}{n}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \frac{j}{2n} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \frac{j}{2n}$		
13	n^-^1				$\frac{1}{2}\frac{j}{n} (n = 4)$	$\tilde{a}$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a}$	$\frac{\tilde{a}}{2}$		
14	n^-^1	n^-^1			$\frac{1}{2}\frac{j}{n} (n = 4)$	$\tilde{a} + A_0$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a} + A_0$	$\frac{\tilde{a}}{2} + \frac{1}{4}$		
15	n^-^1	n^-			$\frac{1}{2}\frac{j}{n} (n = 4)$	$\tilde{a} + A_0$	$\frac{\tilde{a}}{2} + \tilde{b}$	$\tilde{a} + A_0$	$\frac{\tilde{a}}{2} + \frac{1}{4}$		

Table 20

Restrictions on the form of $\mathbf{S}(\mathbf{k})$ for any wave vector $\mathbf{k}$ in the magnetic lattice L when $\Gamma_e = 2, 2^0$, or 1^0 . In each case the form of $\mathbf{S}(\mathbf{k})$ depends on the particular values of the phases $\Phi_e(\mathbf{b}^{(j)}\mathbf{c})$, where $\mathbf{b}$ is the generator of Γ_e , and on the parities of n_i and l , where $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$. Each entry in the Table contains three values for the form of $\mathbf{S}(\mathbf{k})$: the one on the left is for $\Gamma_e = 2$; the one in the center is for $\Gamma_e = 2^0$, and the one on the right is for $\Gamma_e = 1^0$.

Lattice spin group		$\Gamma_e = 2$		$\Gamma_e = 2^0$		$\Gamma_e = 1^0$	
Symbols	$\Phi_e(\mathbf{b}^{(j)}\mathbf{c})$	l even	l odd	l even	l odd	l even	l odd
$P_{2c}; S_P$	$0\frac{1}{2}$	$S_z = S_{xy} = 0$	$S_{xy} = S_z = S$	$S_z = S_{xy} = 0$	$S_{xy} = S_z = S$	$S_z = S_{xy} = 0$	$S_{xy} = S_z = S$
P_P	$\frac{1}{2}0$	$S_z = S_{xy} = 0$	$S_z = S_{xy} = 0$	$S_{xy} = S_z = S$	$S_{xy} = S_z = S$	$S_{xy} = S_z = S$	$S_{xy} = S_z = S$
P_S	$\frac{1}{2}\frac{1}{2}$	$S_z = S_{xy} = 0$	$S_{xy} = S_z = S$	$S_{xy} = S_z = S$	$S_{xy} = S_z = S$	$S_z = S_{xy} = 0$	$S_{xy} = S_z = 0$

research papers

Table 21

Restrictions on the form of $\mathbf{S}(\mathbf{k})$ for any wave vector $\mathbf{k} \in L$ when $\Gamma_e = 21^0$. In each case the form of $\mathbf{S}(\mathbf{k})$ depends on the particular values of the phase functions for the generators of Γ_e , and on the parities of $\sum_{i=1}^4 n_i$ and l , where $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$.

Lattice spin group			$\sum_{i=1}^4 n_i$ even		$\sum_{i=1}^4 n_i$ odd	
Symbols	$\Phi_e^{2\bar{z}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c})$	l even	l odd	l even	l odd
$P_{2c\mu}^{21^0}$	$0\frac{1}{2}$	$\frac{1}{2}0$	0	0	$\mathbf{S}_z$	$\mathbf{S}_{xy}$
$P_{2c\delta}^{21^0}$	$0\frac{1}{2}$	$\frac{1}{2}\frac{1}{2}$	0	$\mathbf{S}_{xy}$	$\mathbf{S}_z$	0
$P_{p2c}^{21^0}$	$\frac{1}{2}0$	$0\frac{1}{2}$	0	$\mathbf{S}_z$	0	$\mathbf{S}_{xy}$
$P_{p\delta}^{21^0}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	0	$\mathbf{S}_z$	$\mathbf{S}_{xy}$	0
$P_{s2c}^{21^0}$	$\frac{1}{2}\frac{1}{2}$	$0\frac{1}{2}$	0	$\mathbf{S}_{xy}$	0	$\mathbf{S}_z$
$P_{s\mu}^{21^0}$	$\frac{1}{2}\frac{1}{2}$	$\frac{1}{2}0$	0	0	$\mathbf{S}_{xy}$	$\mathbf{S}_z$

Table 22

Restrictions on the form of $\mathbf{S}(\mathbf{k})$ for any wave vector $\mathbf{k}$ in the magnetic lattice L when $\Gamma_e = 222$ and 2^02^0 . In each case the form of $\mathbf{S}(\mathbf{k})$ depends on the particular values of the phase functions for the generators 2_x^* and 2_y^* of Γ_e , where the asterisk denotes an optional prime, and on the parities of $n_1 + n_3$, $n_2 + n_4$, and l , where $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$. Each entry in the Table contains two values for the form of $\mathbf{S}(\mathbf{k})$: the one on the left is for $\Gamma_e = 222$; and the one on the right is for $\Gamma_e = 2^02^0$.

Lattice spin group			$n_1 + n_3$ even				$n_1 + n_3$ odd			
Symbols	$\Phi_e^{2\bar{x}}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2\bar{y}}(\mathbf{b}^{(i)}\mathbf{c})$	$n_2 + n_4$ even		$n_2 + n_4$ odd		$n_2 + n_4$ even		$n_2 + n_4$ odd	
			l even	l odd	l even	l odd	l even	l odd	l even	l odd
$P_{2c\mu}^{222}; P_{2c\mu}^{2^02^0}$	$0\frac{1}{2}$	$\frac{1}{2}0$	$0=\mathbf{S}_z$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_z=0$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_z=0$	$0=\mathbf{S}_z$	$\mathbf{S}_y=\mathbf{S}_x$
$P_{2c\delta}^{2^02^0}$	$0\frac{1}{2}$	$\frac{1}{2}\frac{1}{2}$	$0=\mathbf{S}_z$	$\mathbf{S}_z=0$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_y=\mathbf{S}_x$	$0=\mathbf{S}_z$	$\mathbf{S}_z=0$
$P_{p\delta}^{2^02^0}; P_{p\delta}^{222}; P_{l p \mu}^{2^02^0}; P_{l p \mu}^{222}$	$\frac{1}{2}0$	$\frac{1}{2}\frac{1}{2}$	$0=\mathbf{S}_z$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_z=0$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_z=0$	$\mathbf{S}_y=\mathbf{S}_x$	$0=\mathbf{S}_z$	$\mathbf{S}_x=\mathbf{S}_y$
$P_{p p \mu}^{222}; P_{p p \mu}^{2^02^0}$	A_00	A_10	$0=\mathbf{S}_z$	$0=\mathbf{S}_z$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_z=0$	$\mathbf{S}_z=0$
$P_{p p \mu}^{222}; P_{p p \mu}^{2^02^0}$	$A_0\frac{1}{2}$	$A_1\frac{1}{2}$	$0=\mathbf{S}_z$	$\mathbf{S}_z=0$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_x=\mathbf{S}_y$	$\mathbf{S}_y=\mathbf{S}_x$	$\mathbf{S}_z=0$	$0=\mathbf{S}_z$

Table 23

Restrictions on the form of $\mathbf{S}(\mathbf{k})$ for any wave vector $\mathbf{k} \in L$ when $\Gamma_e = 2^02^02^0$. In each case the form of $\mathbf{S}(\mathbf{k})$ depends on the particular values of the phase functions for the generators 2_x^0 , 2_y^0 , and 2_z^0 of Γ_e , and on the parities of $n_1 + n_3$, $n_2 + n_4$, and l , where $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$.

Lattice spin group				$n_1 + n_3$ even				$n_1 + n_3$ odd			
Symbols	$\Phi_e^{2_x^0}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2_y^0}(\mathbf{b}^{(i)}\mathbf{c})$	$\Phi_e^{2_z^0}(\mathbf{b}^{(i)}\mathbf{c})$	$n_2 + n_4$ even		$n_2 + n_4$ odd		$n_2 + n_4$ even		$n_2 + n_4$ odd	
				l even	l odd	l even	l odd	l even	l odd	l even	l odd
$P_{p p 2c}^{2^02^02^0}$	A_00	A_10	$0\frac{1}{2}$	0	$\mathbf{S}_z$	$\mathbf{S}_x$	0	$\mathbf{S}_y$	0	0	0
$P_{p p \delta}^{2^02^02^0}$	A_00	A_10	$\frac{1}{2}\frac{1}{2}$	0	$\mathbf{S}_z$	0	$\mathbf{S}_x$	0	$\mathbf{S}_y$	0	0
$P_{p p 2c}^{2^02^02^0}$	$A_0\frac{1}{2}$	$A_1\frac{1}{2}$	$0\frac{1}{2}$	0	0	$\mathbf{S}_x$	0	$\mathbf{S}_y$	0	0	$\mathbf{S}_z$
$P_{p p \delta}^{2^02^02^0}$	$A_0\frac{1}{2}$	$A_1\frac{1}{2}$	$\frac{1}{2}\frac{1}{2}$	0	0	0	$\mathbf{S}_y$	0	$\mathbf{S}_x$	0	$\mathbf{S}_z$

Table 24

Restrictions on the form of $\mathbf{S}(\mathbf{k})$ for any wave vector $\mathbf{k} \in L$ when $\Gamma_e = n, n^0$ and $n1^0$. In each case the form of $\mathbf{S}(\mathbf{k})$ depends on the particular value of the phase functions for the generators of Γ_e , on the parity of n_i , and on the value of l , where $\mathbf{k} = \sum_{i=1}^4 n_i \mathbf{b}^{(i)} + l\mathbf{c}$. The conditions for obtaining non-extinct $\mathbf{S}(\mathbf{k})$ are listed separately for $\Gamma_e = n$, $\Gamma_e = n^0$ (even n), and $\Gamma_e = n^0$ (odd n). The restrictions on the form of $\mathbf{S}(\mathbf{k})$ for $\Gamma_e = n1^0$ are obtained from those of $\Gamma_e = n$ with the additional requirement that $\mathbf{S}(\mathbf{k}) = 0$ if: (1) $\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c}) = 0$ and l is even; (2) $\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}$ and n_i is even; or (3) $\Phi_e^0(\mathbf{b}^{(i)}\mathbf{c}) = \frac{1}{2}$ and $n_i + l$ is even.

$\Gamma_e = n$		$\Gamma_e = n^0$ (even n)		$\Gamma_e = n^0$ (odd n)			
$P_{njc}^n; S_{njc}^n$		$P_{njc}^{n^0}; S_{njc}^{n^0}$		$P_{(2n)jc}^{n^0}; S_{(2n)jc}^{n^0}$			
$\Phi_e^{n^0}(\mathbf{b}^{(i)}\mathbf{c})$	$lj \pmod n$	$\Phi_e^{n^0}(\mathbf{b}^{(i)}\mathbf{c})$	$lj \pmod n$	$\Phi_e^{n^0}(\mathbf{b}^{(i)}\mathbf{c})$	$lj \pmod{2n}$	n_i even	n_i odd
0	0	0	$\frac{n}{2}$	0	n	$\mathbf{S}_z$	$\mathbf{S}_z$
	$+1$		$\frac{n}{2} + 1$		$n + 2$	$\mathbf{S}_+$	$\mathbf{S}_+$
	1		$\frac{n}{2} - 1$		$n - 2$	$\mathbf{S}$	$\mathbf{S}$
	otherwise		otherwise		otherwise	0	0
$P_{n_jS}^n; S_{4_jS}^4$		$P_{n_jS}^{n^0}; S_{4_jS}^{4^0}$		$P_{(2n)_jS}^{n^0}$			
$\frac{1}{2}$	0	$\frac{1}{2}$	$\frac{n}{2}$	$\frac{1}{2}$	n	$\mathbf{S}_z$	0
	$+1$		$\frac{n}{2} + 1$		$n + 2$	$\mathbf{S}_+$	0
	1		$\frac{n}{2} - 1$		$n - 2$	$\mathbf{S}$	0
	$\frac{n}{2}$		0		0	0	$\mathbf{S}_z$
	$\frac{n}{2} + 1$		$+1$		$+1$	0	$\mathbf{S}_+$
	$\frac{n}{2} - 1$		1		1	0	$\mathbf{S}$
	otherwise		otherwise		otherwise	0	0
$P_{(\frac{n}{2})_jP}^n$		$P_{(\frac{n}{2})_jP}^{n^0}$		$P_{n_jP}^{n^0}$			
$\frac{1}{2}$	0 or $\frac{n}{2}$	$\frac{1}{2}$	0 or $\frac{n}{2}$	$\frac{1}{2}$	0 or n	$\mathbf{S}_z$	0
	$\frac{n}{4} + \frac{1}{2}$ or $\frac{3n}{4} + \frac{1}{2}$		$\frac{n}{4} + \frac{1}{2}$ or $\frac{3n}{4} + \frac{1}{2}$		$\frac{n}{2} + 1$ or $\frac{3n}{2} + 1$	0	$\mathbf{S}_+$
	$\frac{n}{4} - \frac{1}{2}$ or $\frac{3n}{4} - \frac{1}{2}$		$\frac{n}{4} - \frac{1}{2}$ or $\frac{3n}{4} - \frac{1}{2}$		$\frac{n}{2} - 1$ or $\frac{3n}{2} - 1$	0	$\mathbf{S}$
	otherwise		otherwise		otherwise	0	0




Figure 1

The 8-fold star containing the horizontal generating vectors and their negatives $\mathbf{b}^{(1)} \dots \mathbf{b}^{(4)}$ is given by solid arrows. The horizontal shift $\mathbf{h}$ [Eq. (2)] of the staggered stacking vector is denoted by a dashed arrow. The dotted lines indicate the orientations of the two types of vertical mirrors and dihedral axes, as described in the text.

Appendix A.

Claculation of the phase functions associated with Γ_e

[Not to be included in the printed version of the paper]

Before starting we note from inspection of Table 3 that no quotient group $G=\Gamma_e$ contains an operation of order 3. This implies, among other things, that $\Gamma=\Gamma_e$ cannot contain such an operation and therefore that Γ cannot be cubic. This then implies that for any possible combination of Γ and Γ_e ,

$$8 \in \Gamma_e; \quad 2 \in \Gamma: \quad 2^2 = 1: \quad (90)$$

Relation (90) implies that one of three conditions must be satisfied:

1. $1 = 1$, or simply 1 and 1 commute.
2. $1 = 1$, where $1 \notin 1$. This may happen if 1 is an n -fold rotation ($n > 2$), possibly followed by time-inversion, and 1 is a perpendicular 2-fold rotation.
3. 1 is one of a pair of operations in Γ_e staisfying $1 = 0$ and $0 = 1 = 1$. This may happen if the two operations are $2_{\bar{x}}$ and $2_{\bar{y}}$, or $2_{\bar{x}}$ and $2_{\bar{y}}$, and 1 is either a 4-fold rotation about the $\bar{z}$ axis or a 2-fold rotation about the diagonal.

We shall use relation (90), and the three possibilities for satisfying it, in order to calculate the constraints imposed on $\Phi_e(\mathbf{k})$ by the spin-space operations, paired with the generators of the different octagonal point groups. Recall that we write $\Phi_g(\mathbf{b}^{(i)}) = abcd$ instead of fully writing $\Phi_g(\mathbf{b}^{(1)}) = a$, $\Phi_g(\mathbf{b}^{(2)}) = b$, $\Phi_g(\mathbf{b}^{(3)}) = c$, and $\Phi_g(\mathbf{b}^{(4)}) = d$; we write $\Phi_g(\mathbf{b}^{(i)}\mathbf{c}) = abcde$ to indicate in addition that $\Phi_g(\mathbf{c}) = e$; and occasionally, if the four phases on the horizontal generating vectors are equal to a we write $\Phi_g(\mathbf{b}^{(i)}) = a$ or $\Phi_g(\mathbf{b}^{(i)}\mathbf{c}) = a$.

A.1. Constraints imposed by Γ_e (all point groups)

Let g_8 denote the 8-fold generator (r_8 or $\bar{r}_8$), and recall that $2 \in \Gamma$ denotes the the operation paired with it in the spin point group. The constraints imposed by the operation 2 , which must be satisfied by all the octagonal spin groups, yield the following results:

R1. For any $2 \in \Gamma_e$, the in-plane phases of Φ_e are

$$\Phi_e(\mathbf{b}^{(i)}) = \begin{cases} abab & V\text{-lattice;} \\ aaaa & S\text{-lattice;} \end{cases} \quad (91)$$

where a and b are independently either 0 or 1=2.

Proof: Relation (90) together with Eq. (3) yields

$$\Phi_e(\mathbf{b}^{(i)}) = \Phi_e^{-2}(\mathbf{g}_8^2 \mathbf{b}^{(i)}) = \Phi_e(\mathbf{g}_8^2 \mathbf{b}^{(i)}): \quad (92)$$

Thus, for any $2 \in \Gamma_e$

$$\Phi_e(\mathbf{b}^{(1)}) = \Phi_e(\mathbf{b}^{(3)}) = a; \quad \Phi_e(\mathbf{b}^{(2)}) = \Phi_e(\mathbf{b}^{(4)}) = b; \quad (93)$$

and

$$\Phi_e(\mathbf{b}^{(i)}) = \Phi_e(\mathbf{b}^{(i)}) = 0 \text{ or } \frac{1}{2}: \quad (94)$$

The last result (due to the linearity of the phase function) implies that each of the phases a and b in (93) can be either 0 or 1=2. No further constraints arise from application of (3) to the vertical stacking vector, on the other hand, for the staggered stacking vector, using the fact [Table 2] that $\mathbf{g}_8^2(\mathbf{z} + \mathbf{h}) = (\mathbf{z} + \mathbf{h}) + \mathbf{b}^{(4)} - \mathbf{b}^{(1)}$, we obtain

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \Phi_e(\mathbf{z} + \mathbf{h}) + b - a; \quad (95)$$

implying that $a = b$.

Note that as a consequence of R1—along with the fact that for 2-fold operations all phases are either 0 or 1=2, and the fact that no two phase functions Φ_e can be the same—on S -lattices there can be no more than three operations of order 2 in Γ_e .

research papers

R2. For any Γ_e , if σ commutes with $\sigma^2 = 1$ and the 8-fold generator is r_8 , then the in-plane phases of Φ_e are

$$\Phi_e(\mathbf{b}^{(i)}) = \begin{cases} aaaa & \text{V-lattice;} \\ 0000 & \text{S-lattice;} \end{cases} \quad (96)$$

where a is either 0 or 1=2.

If the 8-fold generator is $\bar{r}_8$ the in-plane phases of Φ_e are

$$\Phi_e(\mathbf{b}^{(i)}) = aaaa \quad (97a)$$

regardless of the lattice type, and the phase on the stacking vector is

$$\Phi_e(\mathbf{c}) = \begin{cases} c & \text{V-lattice;} \\ \frac{a}{2} + c & \text{S-lattice;} \end{cases} \quad (97b)$$

where a and c are either 0 or 1=2 but they cannot both be 0. As a consequence, on vertical lattices σ is an operation of order 2, and on staggered lattices σ is of order 2 or 4 depending on whether $a = 0$ or 1=2.

Proof: From application of relation (3) to the horizontal generating vectors we obtain

$$\Phi_e(\mathbf{b}^{(i)}) = \Phi_e^{-1}(g_8 \mathbf{b}^{(i)}) = \Phi_e(\mathbf{b}^{(i+1)}); \quad (98)$$

where the upper (positive) sign is for $g_8 = r_8$ and the lower (negative) sign (due to the linearity of the phase function) is for $g_8 = \bar{r}_8$. This implies that on V-lattices the two phases a and b in (91) are equal. Application of (3) to the vertical stacking vector yields (with the same sign convention)

$$\Phi_e(\mathbf{z}) = \Phi_e(\mathbf{z}); \quad (99)$$

This implies for V-lattices that if $g_8 = \bar{r}_8$ the phase $\Phi_e(\mathbf{z}) = 0$ or 1=2 and therefore that σ is an operation of order 2. For the staggered stacking vector, with the aid of Table 2, we obtain

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \Phi_e(\mathbf{z} + \mathbf{h}) - a; \quad (100)$$

implying for S-lattices that if $g_8 = r_8$ the phase a in (91) is 0, and if $g_8 = \bar{r}_8$ then $2\Phi_e(\mathbf{z} + \mathbf{h}) = a$, whose solutions are given by Eq. (97b), and σ is an operation of order 2 or 4 depending on whether $a = 0$ or 1=2.

R3. If Γ_e is an operation of order $n > 2$, $\sigma^2 = 1$, and the 8-fold generator is r_8 , then the lattice must be staggered, n must be 4, and the phases of Φ_e are

$$\Phi_e(\mathbf{b}^{(i)}) = \frac{1}{2} \frac{1}{2} \frac{1}{2} \frac{1}{2}; \quad \Phi_e(\mathbf{z} + \mathbf{h}) = \frac{1}{4} \text{ or } \frac{3}{4}; \quad (101)$$

If the 8-fold generator is $\bar{r}_8$ the in-plane phases of Φ_e are

$$\Phi_e(\mathbf{b}^{(i)}) = \begin{cases} aaaa & \text{V-lattice;} \\ 0000 & \text{S-lattice;} \end{cases} \quad (102)$$

where a is either 0 or 1=2.

Proof: Application of (3) to the horizontal generating vectors shows again that on V-lattices the two phases a and b in (91) are equal. Application of (3) to the vertical stacking vector yields

$$\Phi_e(\mathbf{z}) = \Phi_e^{-1}(g_8 \mathbf{z}) = \Phi_e(\mathbf{z}); \quad (103)$$

where the upper (negative) sign is for $g_8 = r_8$ and the lower (positive) sign is for $g_8 = \bar{r}_8$. This implies that on V-lattices if $g_8 = r_8$ the phase $\Phi_e(\mathbf{z})$ is 0 or 1=2. If this is the case, then because we know that the in-plane phases of Φ_e are also either 0 or 1=2, $\sigma^2 = 1$ in contradiction to the statement that the order of σ is greater than 2, and therefore the lattice cannot be vertical.

For the staggered stacking vector we obtain (with the same sign convention)

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \Phi_e(\mathbf{z} + \mathbf{h}) - a; \quad (104)$$

implying for S-lattices that if $g_8 = \bar{r}_8$ the phase a in (91) is 0, and if $g_8 = r_8$ then $2\Phi_e(\mathbf{z} + \mathbf{h}) = a$. If $a = 0$ then all the phases of Φ_e are either 0 or 1=2 implying that σ is of order 2, and therefore we must take $a = 1=2$, in which case σ is of order 4, and $\Phi_e(\mathbf{z} + \mathbf{h}) = 1=4$ or $3=4$.

R4. If $2_{\bar{x}}; 2_{\bar{y}} \in \Gamma_e$, where the asterisk denotes an optional prime, and $2_{\bar{x}}^{-1} = 2_{\bar{y}}$, the directions of the $\bar{x}$ and $\bar{y}$ axes in spin-space can be chosen so that the in-plane phases of $\Phi_e^{2_{\bar{x}}}$ and $\Phi_e^{2_{\bar{y}}}$ are

$$\begin{aligned} & \left(\begin{array}{l} \Phi_e^{2_{\bar{x}}}(\mathbf{h}^{(i)}) = 0 \frac{1}{2} 0 \frac{1}{2}; \Phi_e^{2_{\bar{y}}}(\mathbf{h}^{(i)}) = \frac{1}{2} 0 \frac{1}{2} 0 \quad V\text{-lattice;} \\ \Phi_e^{2_{\bar{x}}}(\mathbf{h}^{(i)}) = \Phi_e^{2_{\bar{y}}}(\mathbf{h}^{(i)}) = \frac{1}{2} \frac{1}{2} \frac{1}{2} \frac{1}{2} \quad S\text{-lattice;} \end{array} \right. \end{aligned} \quad (105a)$$

and the phases on the stacking vector are

$$\begin{aligned} & \left(\begin{array}{l} \Phi_e^{2_{\bar{x}}}(\mathbf{z}) = \Phi_e^{2_{\bar{y}}}(\mathbf{z}) = 0 \text{ or } \frac{1}{2} \quad V\text{-lattice;} \\ \Phi_e^{2_{\bar{x}}}(\mathbf{z} + \mathbf{h}) = 0; \Phi_e^{2_{\bar{y}}}(\mathbf{z} + \mathbf{h}) = \frac{1}{2} \quad S\text{-lattice;} \end{array} \right. \end{aligned} \quad (105b)$$

Proof: Let σ_1 and σ_2 denote the two 2-fold operations, and note that since the phases $\Phi_e^{\sigma_1}(\mathbf{k})$ and $\Phi_e^{\sigma_2}(\mathbf{k})$ are always either 0 or $\frac{1}{2}$ the signs of these phases can be ignored. Application of Eq. (3) to the horizontal generating vectors yields

$$\Phi_e^{\sigma_1}(\mathbf{h}^{(i)}) = \Phi_e^{\sigma_1^{-1}}(g_8 \mathbf{h}^{(i)}) = \Phi_e^{\sigma_2}(\mathbf{h}^{(i+1)}); \quad (106)$$

This implies through result R1 that on V -lattices if $\Phi_e^{\sigma_1}(\mathbf{h}^{(i)}) = abab$ then $\Phi_e^{\sigma_2}(\mathbf{h}^{(i)}) = baba$, and that on S -lattices $\Phi_e^{\sigma_1}(\mathbf{h}^{(i)}) = \Phi_e^{\sigma_2}(\mathbf{h}^{(i)}) = aaaa$, where a and b are either 0 or $\frac{1}{2}$.

Application of Eq. (3) to the vertical stacking vector yields

$$\Phi_e^{\sigma_1}(\mathbf{z}) = \Phi_e^{\sigma_1^{-1}}(g_8 \mathbf{z}) = \Phi_e^{\sigma_2}(\mathbf{z}); \quad (107)$$

where we have ignored the sign difference between $r_8 \mathbf{z}$ and $\bar{r}_8 \mathbf{z}$. This equality of phases implies that a and b cannot be equal otherwise $\sigma_1 = \sigma_2$. We can always choose the orientation of the $\bar{x}$ and $\bar{y}$ axes in spin space such that the phase function associated with $2_{\bar{x}}$ is the one whose values on the horizontal generating vectors are $0 \frac{1}{2} 0 \frac{1}{2}$.

Finally, application of Eq. (3) to the staggered stacking vector, ignoring again the sign difference between $r_8(\mathbf{z} + \mathbf{h})$ and $\bar{r}_8(\mathbf{z} + \mathbf{h})$, yields

$$\Phi_e^{\sigma_1}(\mathbf{z} + \mathbf{h}) = \Phi_e^{\sigma_2}(\mathbf{z} + \mathbf{h}) + a; \quad (108)$$

Since the two phase functions have identical values on the horizontal sublattice they must differ on the stacking vector. This requires that a be $\frac{1}{2}$. Here we can always choose the orientation of the $\bar{x}$ and $\bar{y}$ axes in spin space such that the phase function associated with $2_{\bar{x}}$ is the one whose value on the staggered stacking vector is 0.

A.2. Constraints imposed by (point groups $8mm$, $\bar{8}m2$, and $8=mmm$)

Using the third line of Table 2, summarizing the effect of the mirror m on the lattice generating vectors, we obtain the following results:

M1. For any $\sigma \in \Gamma_e$, if σ commutes with m , the in-plane phases of Φ_e are

$$\Phi_e(\mathbf{h}^{(i)}) = \begin{cases} abab & V\text{-lattice;} \\ 0000 & S\text{-lattice;} \end{cases} \quad (109)$$

where a and b are independently either 0 or $\frac{1}{2}$.

Proof: Starting from the general result R1, we see that no further constraints arise from application of (3) to the horizontal generating vectors and to the vertical stacking vector, and so there is no change from the general case for V -lattices. For the staggered stacking vector we obtain

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \Phi_e(\mathbf{z} + \mathbf{h}) + a; \quad (110)$$

implying that on S -lattices the phase a in (91) is 0.

M2. If $\sigma \in \Gamma_e$, is an operation of order $n > 2$, and $\sigma^n = 1$, then the lattice must be staggered, n must be 4, and the phases of Φ_e are

$$\Phi_e(\mathbf{h}^{(i)}) = \frac{1}{2} \frac{1}{2} \frac{1}{2} \frac{1}{2}; \quad \Phi_e(\mathbf{z} + \mathbf{h}) = \frac{1}{4} \text{ or } \frac{3}{4}; \quad (111)$$

research papers

Proof: From result R1 we know that the in-plane phases of Φ_e are either 0 or 1=2. Application of (3) to the vertical stacking vector yields an expression similar to Eq. (103) for r_8 , implying that the phase of $\Phi_e(\mathbf{z})$ is also 0 or 1=2. If this is the case then $\bar{2} = \bar{2}$ in contradiction to the statement that the order of $\bar{2}$ is greater than 2. The only possibility that is left is for an S -lattice, in which case application of (3) to the staggered stacking vector yields an expression similar to Eq. (104) for r_8 and therefore to the same phases obtained in result R3 [Eq. (101)].

M3. If $2_{\bar{x}}; 2_{\bar{y}} \in \Gamma_e$, where the asterisk denotes an optional prime, $2_{\bar{x}}^{-1} = 2_{\bar{y}}$, and the mirror is of type m , then the lattice must be staggered, the in-plane phases of $\Phi_e^{2_{\bar{x}}}$ and $\Phi_e^{2_{\bar{y}}}$ are

$$\Phi_e^{2_{\bar{x}}}(\mathbf{b}^{(i)}) = \Phi_e^{2_{\bar{y}}}(\mathbf{b}^{(i)}) = \frac{1}{2} \frac{1}{2} \frac{1}{2} \frac{1}{2}; \quad (112a)$$

and the directions of the $\bar{x}$ and $\bar{y}$ axes in spin-space can be chosen so that the phases on the staggered stacking vector are

$$\Phi_e^{2_{\bar{x}}}(\mathbf{z} + \mathbf{h}) = 0; \Phi_e^{2_{\bar{y}}}(\mathbf{z} + \mathbf{h}) = \frac{1}{2}; \quad (112b)$$

Proof: Let $\bar{1}$ and $\bar{2}$ denote the two 2-fold operations, and note that since the phases $\Phi_e^{\bar{1}}(\mathbf{k})$ and $\Phi_e^{\bar{2}}(\mathbf{k})$ are always either 0 or 1=2 the signs of these phases can be ignored. Application of Eq. (3) to the horizontal generating vectors yields

$$\Phi_e^{\bar{1}}(\mathbf{b}^{(i)}) = \Phi_e^{\bar{2}}(\mathbf{b}^{(i+2k)}); \quad (113)$$

for some integer k that depends on i . Together with result R1, Eq. (113) implies that the two phase functions are identical on the horizontal sublattice. Application of Eq. (3) to the vertical stacking vector establishes that the two phase functions are identical everywhere in contradiction with the fact that $\bar{1} \notin \bar{2}$, and therefore that the lattice cannot be vertical. Application of Eq. (3) to the staggered stacking vector yields

$$\Phi_e^{\bar{1}}(\mathbf{z} + \mathbf{h}) = \Phi_e^{\bar{2}}(\mathbf{z} + \mathbf{h}) + a; \quad (114)$$

Since the two phase functions have identical values on the horizontal sublattice they must differ on the stacking vector, requiring that a be 1=2. We then choose the orientation of the $\bar{x}$ and $\bar{y}$ axes in spin space such that the phase function associated with $2_{\bar{x}}$ is the one whose value on the staggered stacking vector is 0.

A.3. Constraints imposed by $\bar{2}$ (point groups 822 and $\bar{8}2m$)

Using the fourth line of Table 2, summarizing the effect of the dihedral rotation d on the lattice generating vectors, we obtain the following results:

D1. For any $\bar{2} \in \Gamma_e$, if $\bar{2}$ commutes with $\bar{1}$ the in-plane phases are the general ones given in result R1 [Eq. (91)]. If the lattice is vertical, the phase of $\Phi_e(\mathbf{z})$ is independently 0 or 1=2, implying that $\bar{2}$ is an operation of order 2. If the lattice is staggered the phase on the stacking vector is

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \frac{a}{2} + c; \quad (115)$$

where a is the in-plane phase in (91), and $c = 0$ or 1=2 but a and c cannot both be 0. Consequently, $\bar{2}$ is an operation of order 2 or 4, depending on whether $a = 0$ or 1=2.

Proof: Application of Eq. (3) to the horizontal generating vectors yields no further constraints beyond the general result R1. Application of Eq. (3) to the vertical stacking vector yields

$$\Phi_e(\mathbf{z}) = \Phi_e(\mathbf{z}); \quad (116)$$

implying that the phase of $\Phi_e(\mathbf{z})$ is 0 or 1=2. If this is the case then $\bar{2}$ is necessarily an operation of order 2. Application of Eq. (3) to the vertical stacking vector yields

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \Phi_e(\mathbf{z} + \mathbf{h}) + \Phi_e(2\mathbf{h}) = a; \quad (117)$$

It follows from the general result R1 that $\Phi_e(2\mathbf{h}) = \Phi_e(\mathbf{b}^{(1)} + \mathbf{b}^{(2)} + \mathbf{b}^{(3)} - \mathbf{b}^{(4)}) = 0$, and therefore that $2\Phi_e(\mathbf{z} + \mathbf{h}) = a$, whose solutions are given by Eq. (115). If $a = 0$ then $\bar{2}$ is again of order 2; If $a = 1=2$ then $\bar{2}$ is of order 4.

D2. If $\bar{2} \in \Gamma_e$, is an operation of order $n > 2$, $\bar{2}^{-1} = \bar{2}^{n-1}$, and the lattice is vertical there are no additional constraints on the phase function Φ_e . If the lattice is staggered then the in-plane phases of Φ_e are all 0.

Proof: This can easily be seen by applying Eq. (3) to the generating vectors while noting that $\Phi_e(2\mathbf{h}) = 0$.

D3. If $2_{\bar{x}}; 2_{\bar{y}} \in \Gamma_e$, where the asterisk denotes an optional prime, and $2_{\bar{x}}^{-1} = 2_{\bar{y}}$, then the lattice must be staggered, the in-plane phases of $\Phi_e^{2_{\bar{x}}}$ and $\Phi_e^{2_{\bar{y}}}$ are

$$\Phi_e^{2_{\bar{x}}}(\mathbf{b}^{(i)}) = \Phi_e^{2_{\bar{y}}}(\mathbf{b}^{(i)}) = \frac{1}{2} \frac{1}{2} \frac{1}{2} \frac{1}{2}; \quad (118)$$

and the directions of the $\bar{x}$ and $\bar{y}$ axes in spin-space can be chosen so that the phases on the staggered stacking vector are

$$\Phi_e^{2_{\bar{x}}}(\mathbf{c}) = 0; \Phi_e^{2_{\bar{y}}}(\mathbf{c}) = \frac{1}{2}; \quad (119)$$

Proof: This result is established in the same way as result M3 for the mirror m due to the fact that the sign of the phases can be ignored and the fact that $\Phi_e(2\mathbf{h}) = 0$.

A.4. Constraints imposed by (point groups 8_m and 8_{mmm})

Finally, using the fifth line of Table 2, summarizing the effect of the horizontal mirror h on the lattice generating vectors, we obtain the following results:

H1. For any $2 \in \Gamma_e$, if 2 commutes with h , then the phase of Φ_e on the stacking vector is

$$\Phi_e(\mathbf{c}) = 0 \text{ or } \frac{1}{2}; \quad (120)$$

which implies that 2 is an operation of order 2.

Proof: Application of Eq. (3) to the horizontal generating vectors yields no further constraints beyond the general result R1. Application of Eq. (3) to the vertical stacking vector yields Eq. (116), and application of Eq. (3) to the staggered stacking vector yields

$$\Phi_e(\mathbf{z} + \mathbf{h}) = \Phi_e(\mathbf{z} + \mathbf{h}) + \Phi_e(2\mathbf{h}); \quad (121)$$

Because $\Phi_e(2\mathbf{h}) = 0$, Eqs. (116) and (121) imply that for both lattice types the phase on the stacking vector is either 0 or $\frac{1}{2}$.

H2. If $2 \in \Gamma_e$, is an operation of order $n > 2$, and $2^{-1} = 2$ there are no additional constraints on the phase function Φ_e .

Proof: This can easily be seen by applying Eq. (3) to the generating vectors while noting that $\Phi_e(2\mathbf{h}) = 0$.

H3. If $2_{\bar{x}}; 2_{\bar{y}} \in \Gamma_e$, where the asterisk denotes an optional prime, then they must both commute with h and their phase functions are only constrained by results R1 and H1.

Proof: Let us denote the two operations by 2_1 and 2_2 and assume that rather than commuting with h they satisfy $2_1^{-1} = 2_2$, then application of Eq. (3) to the generating vectors of both lattice types, while noting that $\Phi_e(2\mathbf{h}) = 0$, establishes that both phase functions are identical everywhere in contradiction with the fact that $2_1 \notin 2_2$.

Appendix B.
Octagonal spin space-group types
[Not to be included in the printed version of the paper]

The following Tables list all the 3-dimensional octagonal spin space-group types, explicitly identifying the spin-space operations σ , τ , ρ , and ϕ appearing in the spin point-group generators. There are a total of 16 tables, one for each combination of point group G and lattice type. The first few columns of each table give the structure of the spin point group G_S by listing Γ_e , G , Γ , and the quotient group $G=G$. Following these is a column that explicitly lists the generators $(r_8; \sigma)$, $(\bar{r}_8; \tau)$, $(\rho; \rho)$, $(\phi; \phi)$, and $(\phi; \phi)$. The last column in each table refers to a line in the corresponding spin space-group table in the main part of the paper (Tables 4–19), which gives the possible values of all the phase functions for the generators of the spin point group, as well as a rule for generating the spin space-group symbol.

Table 25: Explicit list of octagonal spin space-group types with $G = 8$ on V -lattices. The last column refers to line numbers in Table 4, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

Γ_e	G	$G=G$	Γ	generator	line
1	8	1	1	$(r_8; \sigma)$	1
	4	2	2	$(r_8; 2\bar{\sigma})$	1
			1^0	$(r_8; \bar{\sigma})$	1
	2	4	4	$(r_8; 4\bar{\sigma})$	1
	1	8	8	$(r_8; 8\bar{\sigma})$	1
2	8	1	2	$(r_8; \sigma)$	1
	4	2	4	$(r_8; 4\bar{\sigma})$	1
			$2 \ 2 \ 2$	$(r_8; 2\bar{\sigma})$	1
			21^0	$(r_8; \bar{\sigma})$	1
	2	4	8	$(r_8; 8\bar{\sigma})$	1
	1	8	16	$(r_8; 16\bar{\sigma})$	2
1^0	8	1	1^0	$(r_8; \sigma)$	1
	4	2	21^0	$(r_8; 2\bar{\sigma})$	1
	2	4	41^0	$(r_8; 4\bar{\sigma})$	1
	1	8	81^0	$(r_8; 8\bar{\sigma})$	1
2^0	8	1	2^0	$(r_8; \sigma)$	1
	4	2	$2^0 2^0$	$(r_8; 2\bar{\sigma})$	1
			21^0	$(r_8; \bar{\sigma})$	1
	2	4	41^0	$(r_8; 4\bar{\sigma})$	1
	1	8	81^0	$(r_8; 8\bar{\sigma})$	1
21^0	8	1	21^0	$(r_8; \sigma)$	1
	4	2	$2^0 2^0$	$(r_8; 2\bar{\sigma})$	1
			41^0	$(r_8; 4\bar{\sigma})$	1
	2	4	81^0	$(r_8; 8\bar{\sigma})$	1
	1	8	161^0	$(r_8; 16\bar{\sigma})$	2
n	8	1	n	$(r_8; \sigma)$	5
	4	2	$(2n)$	$(r_8; 2n\bar{\sigma})$	9
			$n1^0$	$(r_8; \bar{\sigma})$	5
	2	4	$(4n)$	$(r_8; 4n\bar{\sigma})$	7
	1	8	$(8n)$	$(r_8; 8n\bar{\sigma})$	6
n^0	8	1	n^0	$(r_8; \sigma)$	5
	4	2	$n1^0$	$(r_8; \bar{\sigma})$	5
	2	4	$(2n)1^0$	$(r_8; (2n)\bar{\sigma})$	9
	1	8	$(4n)1^0$	$(r_8; (4n)\bar{\sigma})$	7
$n1^0$	8	1	$n1^0$	$(r_8; \sigma)$	5
	4	2	$(2n)1^0$	$(r_8; 2n\bar{\sigma})$	9

continued on next page

Table 25: continued

Γ_e	G	$G=G$	Γ	generator	line
	2	4	$(4n)1^0$	$(v_8; 4n_{\bar{z}})$	7
	1	8	$(8n)1^0$	$(v_8; 8n_{\bar{z}})$	6
222	8	1	222	$(v_8;)$	3a
	4	2	$2^0 2^0 2^0$	$(v_8; {}^0)$	3a
			$4 \ 2^0 2^0 \ ^y$	$(v_8; 4_{\bar{z}})$	4
$2^0 2^0 2^0$	8	1	$2^0 2^0 2^0$	$(v_8;)$	3
	4	2	$2^0 2^0 2^0$	$(v_8; {}^0)$	3
			$4 \ 2^0 2^0 \ ^y$	$(v_8; 4_{\bar{z}})$	4
$2^0 2^0 2^0$	8	1	$2^0 2^0 2^0$	$(v_8;)$	3a
	4	2	4221^0	$(v_8; 4_{\bar{z}})$	4

Table 26: Explicit list of octagonal spin space-group types with $G = 8$ on S -lattices. The last column refers to line numbers in Table 5, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

Γ_e	G	$G=G$	Γ	generator	line
1	8	1	1	$(v_8;)$	1
	4	2	2	$(v_8; 2_{\bar{z}})$	1
			1^0	$(v_8; {}^0)$	1
	2	4	4	$(v_8; 4_{\bar{z}})$	1
	1	8	8	$(v_8; 8_{\bar{z}})$	1
2	8	1	2	$(v_8;)$	1
	4	2	4	$(v_8; 4_{\bar{z}})$	1
			$2 \ 2 \ 2$	$(v_8; 2_{\bar{x}})$	1
			21^0	$(v_8; {}^0)$	1
	2	4	8	$(v_8; 8_{\bar{z}})$	1
1^0	1	8	16	$(v_8; 16_{\bar{z}})$	2
	8	1	1^0	$(v_8;)$	1
	4	2	21^0	$(v_8; 2_{\bar{z}})$	1
	2	4	41^0	$(v_8; 4_{\bar{z}})$	1
	1	8	81^0	$(v_8; 8_{\bar{z}})$	1
2^0	8	1	2^0	$(v_8;)$	1
	4	2	$2^0 2^0 2^0$	$(v_8; 2_{\bar{x}})$	1
			21^0	$(v_8; {}^0)$	1
n	8	1	n	$(v_8;)$	4
	4	2	$(2n)$	$(v_8; 2n_{\bar{z}})$	8
			$n1^0$	$(v_8; {}^0)$	4
			$n2 \ 2$	$(v_8; 2_{\bar{x}})$	4
	2	4	$(4n)$	$(v_8; 4n_{\bar{z}})$	6
	1	8	$(8n)$	$(v_8; 8n_{\bar{z}})$	5
n^0	8	1	n^0	$(v_8;)$	4
	4	2	$n1^0$	$(v_8; {}^0)$	4
n^0	8	1	$n1^0$	$(v_8;)$	4
	4	2	$(2n)1^0$	$(v_8; n_{\bar{z}})$	8
	2	4	$(4n)1^0$	$(v_8; 4n_{\bar{z}})$	6
	1	8	$(8n)1^0$	$(v_8; 8n_{\bar{z}})$	5
$2 \ 2 \ 2$	4	2	$4 \ 2^0 2^0 \ ^y$	$(v_8; 4_{\bar{z}})$	3

Table 27: Explicit list of octagonal spin space-group types with $G = \bar{8}$ on V -lattices. The last column refers to line numbers in Table 6, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

Γ_e	G	$G=G$	Γ	generator	line
1	8	1	1	$(\bar{v}_8;)$	1
	4	2	2	$(\bar{v}_8; 2_{\bar{z}})$	1
			1^0	$(\bar{v}_8; {}^0)$	1
	2	4	4	$(\bar{v}_8; 4_{\bar{z}})$	1
2	1	8	8	$(\bar{v}_8; 8_{\bar{z}})$	1
	8	1	2	$(\bar{v}_8;)$	1
	4	2	4	$(\bar{v}_8; 4_{\bar{z}})$	1
			$2 \ 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}})$	1
			21^0	$(\bar{v}_8; {}^0)$	1
2^0	2	4	8	$(\bar{v}_8; 8_{\bar{z}})$	1
	8	1	2^0	$(\bar{v}_8;)$	1
	4	2	$2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}})$	1
			21^0	$(\bar{v}_8; {}^0)$	1
1^0	2	4	41^0	$(\bar{v}_8; 4_{\bar{z}})$	1
	1	8	81^0	$(\bar{v}_8; 8_{\bar{z}})$	1
	8	1	1^0	$(\bar{v}_8;)$	1
	4	2	21^0	$(\bar{v}_8; 2_{\bar{z}})$	1
21^0	2	4	41^0	$(\bar{v}_8; 4_{\bar{z}})$	1
	1	8	81^0	$(\bar{v}_8; 8_{\bar{z}})$	1
	8	1	21^0	$(\bar{v}_8;)$	1
	4	2	41^0	$(\bar{v}_8; 4_{\bar{z}})$	1
n	4	2	$2^0 2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}})$	1
			81^0	$(\bar{v}_8; 8_{\bar{z}})$	1
	2	4	81^0	$(\bar{v}_8; 8_{\bar{z}})$	1
	4	2	$n 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}})$	4
n^0	4	2	$n^0 2 \ n^0$	$(\bar{v}_8; 2_{\bar{x}})$	4
$n1^0$	4	2	$n 2 2 1^0$	$(\bar{v}_8; 2_{\bar{x}})$	4
222	8	1	222	$(\bar{v}_8;)$	2a
	4	2	$2^0 2^0 2^0$	$(\bar{v}_8; {}^0)$	2a
			$4 \ 2^y 2 \ {}^y$	$(\bar{v}_8; 4_{\bar{z}})$	3
$2^0 2^0 2$	8	1	$2^0 2^0 2$	$(\bar{v}_8;)$	2
	4	2	$2^0 2^0 2^0$	$(\bar{v}_8; {}^0)$	2
			$4 \ 2^y 2 \ {}^y$	$(\bar{v}_8; 4_{\bar{z}})$	3
$2^0 2^0 2^0$	4	2	$4 2 2 1^0$	$(\bar{v}_8; 4_{\bar{z}})$	3

Table 28: Explicit list of octagonal spin space-group types with $G = \bar{8}$ on S -lattices. The last column refers to line numbers in Table 7, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

Γ_e	G	$G=G$	Γ	generator	line
1	8	1	1	$(\bar{v}_8;)$	1
	4	2	2	$(\bar{v}_8; 2_{\bar{z}})$	1
			1^0	$(\bar{v}_8; {}^0)$	1
	2	4	4	$(\bar{v}_8; 4_{\bar{z}})$	1
2	1	8	8	$(\bar{v}_8; 8_{\bar{z}})$	1
	8	1	2	$(\bar{v}_8;)$	1
	4	2	4	$(\bar{v}_8; 4_{\bar{z}})$	1
			$2 \ 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}})$	1
			21^0	$(\bar{v}_8; {}^0)$	1

continued on next page

Table 28: continued

Γ_e	G	$G=G$	Γ	generator	line
	2	4	8	$(r_8; 8_{\bar{z}})$	1
2^0	8	1	2^0	$(r_8;)$	1
	4	2	$2^0 2^0$	$(r_8; 2_{\bar{x}})$	1
			21^0	$(r_8; \bar{0})$	1
	2	4	41^0	$(r_8; 4_{\bar{z}})$	1
	2	4	41^0	$(r_8; 8_{\bar{z}})$	1
1^0	8	1	1^0	$(r_8;)$	1
	4	2	21^0	$(r_8; 2_{\bar{z}})$	1
	2	4	41^0	$(r_8; 4_{\bar{z}})$	1
	1	8	81^0	$(r_8; 8_{\bar{z}})$	1
n	8	1	n	$(r_8;)$	4
	4	2	$(2n)$	$(r_8; 2n_{\bar{z}})$	4
			$n 2^0$	$(r_8; 2_{\bar{x}})$	3
			$n 1^0$	$(r_8; \bar{0})$	4
n^0	8	1	n^0	$(r_8;)$	4
	4	2	$n^0 2^0$	$(r_8; 2_{\bar{x}})$	3
$2^0 2^0 2^0$	4	2	$2^0 2^0 2^0$	$(r_8; \bar{0})$	2

Table 29: Explicit list of octagonal spin space-group types with $G = 8mm$ on V-lattices. The last column refers to line numbers in Table 8, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line	
$\Gamma_e = 1$					
$8mm$	1	1	$(r_8; \) \ (m; \)$	1	
8	m	2	$(r_8; \) \ (m; 2_{\bar{z}})$	1	
		2^0	$(r_8; \) \ (m; 2_{\bar{x}}^0)$	1	
		1^0	$(r_8; \) \ (m; \bar{0})$	1	
$4mm$	2	2	$(r_8; 2_{\bar{z}}) \ (m; \)$	1	
		1^0	$(r_8; \bar{0}) \ (m; \)$	1	
$4m^0m^0$	2	2	$(r_8; 2_{\bar{z}}) \ (m; 2_{\bar{z}})$	1	
		1^0	$(r_8; \bar{0}) \ (m; \bar{0})$	1	
4	$2mm$	$2 \ 2^y 2^y \ ^y$	$(r_8; 2_{\bar{z}}) \ (m; 2_{\bar{x}}^y)$	1	
			21^0	$(r_8; 2_{\bar{z}}) \ (m; \bar{0})$	1
				$(r_8; \bar{0}) \ (m; 2_{\bar{z}})$	1
				$(r_8; 2_{\bar{z}}) \ (m; 2_{\bar{x}}^0)$	1
2	$4mm$	$4 \ 2^y 2^y$	$(r_8; 4_{\bar{z}}) \ (m; 2_{\bar{x}}^y)$	1	
1	$8mm$	$8 \ 2^y 2^y \ ^y$	$(r_8; 8_{\bar{z}}) \ (m; 2_{\bar{x}}^y)$	1	
				$(r_8; 8_{\bar{z}}^3) \ (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2$					
$8mm$	1	2	$(r_8; \) \ (m; \)$	1	
8	m	$2 \ 2 \ 2$	$(r_8; \) \ (m; 2_{\bar{x}})$	1	
		21^0	$(r_8; \) \ (m; \bar{0})$	1	
		4	$(r_8; \) \ (m; 4_{\bar{x}})$	2	
$4mm$	2	$2 \ 2 \ 2$	$(r_8; 2_{\bar{x}}) \ (m; \)$	1	
		21^0	$(r_8; \bar{0}) \ (m; \)$	1	
		4	$(r_8; 4_{\bar{z}}) \ (m; \)$	3	
$4m^0m^0$	2	$2 \ 2 \ 2$	$(r_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}})$	1	
		21^0	$(r_8; \bar{0}) \ (m; \bar{0})$	1	

continued on next page

Table 29: continued

G	$G=G$	Γ	generators	line
		4	$(\varphi_8; 4_{\bar{x}}) (m; 4_{\bar{x}})$	4
4	2mm	$4 \ 2^y 2^y$	$(\varphi_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y)$	1
			$(\varphi_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}})$	4
			$(\varphi_8; 2_{\bar{x}}^y) (m; 2_{xy}^y)$	3
		41^0	$(\varphi_8; 4_{\bar{x}}) (m; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix})$	3
			$(\varphi_8; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix}) (m; 4_{\bar{x}})$	2
			$(\varphi_8; 4_{\bar{x}}) (m; 4_{\bar{x}}^0)$	4
		$2^0 2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix})$	1
			$(\varphi_8; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix}) (m; 2_{\bar{x}})$	1
			$(\varphi_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0)$	1
2	4mm	$8 \ 2^y 2^y$	$(\varphi_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2^0$				
8mm	1	2^0	$(\varphi_8; \) (m; \)$	1
8	m	$2^0 2^0$	$(\varphi_8; \) (m; 2_{\bar{x}})$	1
		21^0	$(\varphi_8; \) (m; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix})$	1
4mm	2	$2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; \)$	1
		21^0	$(\varphi_8; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix}) (m; \)$	1
$4m^0 m^0$	2	$2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; 2_{\bar{x}})$	1
		21^0	$(\varphi_8; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix}) (m; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix})$	1
4	2mm	$2^0 2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix})$	1
			$(\varphi_8; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix}) (m; 2_{\bar{x}})$	1
			$(\varphi_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0)$	1
2	4mm	4221^0	$(\varphi_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y)$	1
1	8mm	8221^0	$(\varphi_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 1^0$				
8mm	1	1^0	$(\varphi_8; \) (m; \)$	1
8	m	21^0	$(\varphi_8; \) (m; 2_{\bar{x}})$	1
4mm	2	21^0	$(\varphi_8; 2_{\bar{x}}) (m; \)$	1
$4m^0 m^0$	2	21^0	$(\varphi_8; 2_{\bar{x}}) (m; 2_{\bar{x}})$	1
4	2mm	$2^0 2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; 2_{\bar{x}})$	1
2	4mm	4221^0	$(\varphi_8; 4_{\bar{x}}) (m; 2_{\bar{x}})$	1
1	8mm	8221^0	$(\varphi_8; 8_{\bar{x}}) (m; 2_{\bar{x}})$	1
			$(\varphi_8; 8_{\bar{x}}^3) (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 21^0$				
8mm	1	21^0	$(\varphi_8; \) (m; \)$	1
8	m	41^0	$(\varphi_8; \) (m; 4_{\bar{x}})$	2
		$2^0 2^0 2^0$	$(\varphi_8; \) (m; 2_{\bar{x}})$	1
4mm	2	41^0	$(\varphi_8; 4_{\bar{x}}) (m; \)$	3
		$2^0 2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; \)$	1
$4m^0 m^0$	2	41^0	$(\varphi_8; 4_{\bar{x}}) (m; 4_{\bar{x}})$	4
		$2^0 2^0 2^0$	$(\varphi_8; 2_{\bar{x}}) (m; 2_{\bar{x}})$	1
4	2mm	4221^0	$(\varphi_8; 4_{\bar{x}}) (m; 2_{\bar{x}})$	1
			$(\varphi_8; 2_{\bar{x}}) (m; 4_{\bar{x}})$	4
			$(\varphi_8; 2_{\bar{x}}) (m; 2_{xy})$	3
2	4mm	8221^0	$(\varphi_8; 8_{\bar{x}}) (m; 2_{\bar{x}})$	1
$\Gamma_e = n$				
8mm	1	n	$(\varphi_8; \) (m; \)$	7
8	2	$(2n)$	$(\varphi_8; \) (m; (2n)_{\bar{x}})$	8
		$n1^0$	$(\varphi_8; \) (m; \begin{smallmatrix} 0 \\ \bar{x} \end{smallmatrix})$	7
4mm	2	$(2n)$	$(\varphi_8; (2n)_{\bar{x}}) (m; \)$	9

continued on next page

Table 29: continued

G	$G=G$	Γ	generators	line
		$n1^0$	$(\varphi_8; {}^0) (m; {}^0)$	7
$4m^0m^0$	2	$(2n)$	$(\varphi_8; (2n)_{\bar{z}}) (m; (2n)_{\bar{z}})$	10
		$n1^0$	$(\varphi_8; {}^0) (m; {}^0)$	7
4	$2mm$	$(2n)1^0$	$(\varphi_8; (2n)_{\bar{z}}) (m; {}^0)$	9
			$(\varphi_8; {}^0) (m; (2n)_{\bar{z}})$	8
			$(\varphi_8; (2n)_{\bar{z}}) (m; (2n)_{\bar{z}}^0)$	10
$\Gamma_e = n^0$				
$8mm$	1	n^0	$(\varphi_8; {}^0) (m; {}^0)$	7
8	m	$n1^0$	$(\varphi_8; {}^0) (m; {}^0)$	7
$4mm$	2	$n1^0$	$(\varphi_8; {}^0) (m; {}^0)$	7
$4m^0m^0$	2	$n1^0$	$(\varphi_8; {}^0) (m; {}^0)$	7
$\Gamma_e = n1^0$ or n^0				
$8mm$	1	$n1^0$	$(\varphi_8; {}^0) (m; {}^0)$	7
8	m	$(2n)1^0$	$(\varphi_8; {}^0) (m; (2n)_{\bar{z}})$	8
$4mm$	2	$(2n)1^0$	$(\varphi_8; (2n)_{\bar{z}}) (m; {}^0)$	9
$4m^0m^0$	2	$(2n)1^0$	$(\varphi_8; (2n)_{\bar{z}}) (m; (2n)_{\bar{z}})$	10
$\Gamma_e = 222$				
$8mm$	1	222	$(\varphi_8; {}^0) (m; {}^0)$	5a
8	m	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5a
$4mm$	2	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5a
		4 22	$(\varphi_8; 4_{\bar{z}}) (m; {}^0)$	6
$4m^0m^0$	2	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5a
4	$2mm$	4221^0	$(\varphi_8; 4_{\bar{z}}) (m; {}^0)$	6
$\Gamma_e = 2^0 2^0 2^0$				
$8mm$	1	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5
8	m	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5
$4mm$	2	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5
		4 22	$(\varphi_8; 4_{\bar{z}}) (m; {}^0)$	6
$4m^0m^0$	2	$2^0 2^0 2^0$	$(\varphi_8; {}^0) (m; {}^0)$	5
4	$2mm$	4221^0	$(\varphi_8; 4_{\bar{z}}) (m; {}^0)$	6
$\Gamma_e = 2^0 2^0 2^0$				
$4mm$	2	4221^0	$(\varphi_8; 4_{\bar{z}}) (m; {}^0)$	6

Table 30: Explicit list of octagonal spin space-group types with $G = 8mm$ on S -lattices. The last column refers to line numbers in Table 9, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
$8mm$	1	1	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
8	m	2	$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$	1
		2^0	$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$	1
		1^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
$4mm$	2	2	$(\varphi_8; \frac{2}{x}) (\eta m; \text{ })$	1
		1^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
$4m^0m^0$	2	2	$(\varphi_8; \frac{2}{x}) (\eta m; \frac{2}{x})$	1
		1^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
4	$2mm$	$2 \ 2^y 2^y$	$(\varphi_8; \frac{2}{x}) (\eta m; \frac{y}{x})$	1
		21^0	$(\varphi_8; \frac{2}{x}) (\eta m; \text{ })$	1
			$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$	1
			$(\varphi_8; \frac{2}{x}) (\eta m; \frac{0}{x})$	1
2	$4mm$	$4 \ 2^y 2^y$	$(\varphi_8; \frac{4}{x}) (\eta m; \frac{y}{x})$	1
1	$8mm$	$8 \ 2^y 2^y$	$(\varphi_8; \frac{8}{x}) (\eta m; \frac{y}{x})$	1
			$(\varphi_8; 8^3) (\eta m; \frac{y}{x})$	1
$\Gamma_e = 2$				
$8mm$	1	2	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
8	m	$2 \ 2 \ 2$	$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$	1
		21^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
		4	$(\varphi_8; \text{ }) (\eta m; \frac{4}{x})$	2
$4mm$	2	$2 \ 2 \ 2$	$(\varphi_8; \frac{2}{x}) (\eta m; \text{ })$	1
		21^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
		4	$(\varphi_8; \frac{4}{x}) (\eta m; \text{ })$	3
$4m^0m^0$	2	$2 \ 2 \ 2$	$(\varphi_8; \frac{2}{x}) (\eta m; \frac{2}{x})$	1
		21^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
		4	$(\varphi_8; \frac{4}{x}) (\eta m; \frac{4}{x})$	4
4	$2mm$	$4 \ 2^y 2^y$	$(\varphi_8; \frac{4}{x}) (\eta m; \frac{y}{x})$	1
			$(\varphi_8; \frac{y}{x}) (\eta m; \frac{4}{x})$	2
			$(\varphi_8; \frac{y}{x}) (\eta m; \frac{y}{xy})$	3
		41^0	$(\varphi_8; \frac{4}{x}) (\eta m; \text{ })$	3
			$(\varphi_8; \text{ }) (\eta m; \frac{4}{x})$	2
			$(\varphi_8; \frac{4}{x}) (\eta m; \frac{0}{x})$	4
			$2^0 2^0 2^0$	$(\varphi_8; \frac{2}{x}) (\eta m; \text{ })$
		$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$		1
		$(\varphi_8; \frac{2}{x}) (\eta m; \frac{0}{x})$		1
		2	$4mm$	$8 \ 2^y 2^y$
$\Gamma_e = 2^0$				
$8mm$	1	2^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
8	m	$2^0 2^0$	$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$	1
		21^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
$4mm$	2	$2^0 2^0$	$(\varphi_8; \frac{2}{x}) (\eta m; \text{ })$	1
		21^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
$4m^0m^0$	2	$2^0 2^0$	$(\varphi_8; \frac{2}{x}) (\eta m; \frac{2}{x})$	1
		21^0	$(\varphi_8; \text{ }) (\eta m; \text{ })$	1
4	$2mm$	$2^0 2^0 2^0$	$(\varphi_8; \frac{2}{x}) (\eta m; \text{ })$	1
			$(\varphi_8; \text{ }) (\eta m; \frac{2}{x})$	1
			$(\varphi_8; \frac{2}{x}) (\eta m; \frac{0}{x})$	1

continued on next page

Table 30: continued

G	$G=G$	Γ	generators	line
2	4mm	4221 ⁰	$(\varphi_8; 4_{\overline{x}}) (\eta; 2_{\overline{x}}^{\vee})$	1
1	8mm	8221 ⁰	$(\varphi_8; 8_{\overline{x}}) (\eta; 2_{\overline{x}}^{\vee})$	1
$\Gamma_e = 1^0$				
8mm	1	1 ⁰	$(\varphi_8;) (\eta;)$	1
8	m	21 ⁰	$(\varphi_8;) (\eta; 2_{\overline{x}})$	1
4mm	2	21 ⁰	$(\varphi_8; 2_{\overline{x}}) (\eta;)$	1
4m ⁰ m ⁰	2	21 ⁰	$(\varphi_8; 2_{\overline{x}}) (\eta; 2_{\overline{x}})$	1
4	2mm	2 ⁰ 2 ⁰ 2 ⁰	$(\varphi_8; 2_{\overline{x}}) (\eta; 2_{\overline{x}})$	1
2	4mm	4221 ⁰	$(\varphi_8; 4_{\overline{x}}) (\eta; 2_{\overline{x}})$	1
1	8mm	8221 ⁰	$(\varphi_8; 8_{\overline{x}}) (\eta; 2_{\overline{x}})$	1
			$(\varphi_8; 8_{\overline{x}}^3) (\eta; 2_{\overline{x}}^{\vee})$	1
$\Gamma_e = n$				
8mm	1	n	$(\varphi_8;) (\eta;)$	6
8	2	$2n$	$(\varphi_8;) (\eta; 2n_{\overline{x}})$	7
		$n1^0$	$(\varphi_8;) (\eta; {}^0)$	6
4mm	2	$2n$	$(\varphi_8; 2n_{\overline{x}}) (\eta;)$	8
		$n1^0$	$(\varphi_8; {}^0) (\eta;)$	6
4m ⁰ m ⁰	2	$2n$	$(\varphi_8; 2n_{\overline{x}}) (\eta; 2n_{\overline{x}})$	9
		$n2\ 2$	$(\varphi_8; 2_{\overline{x}}) (\eta 2_{\overline{x}})$	10
		$n1^0$	$(\varphi_8; {}^0) (\eta; {}^0)$	6
4	222	$2n\ 2^{\vee} 2\ ^{\vee}$	$(\varphi_8; 2n_{\overline{x}} 2_{\overline{x}}^{\vee}) (\eta; 2_{\overline{x}}^{\vee})$	11
		$n221^0$	$(\varphi_8; 2_{\overline{x}}) (\eta; 2_{\overline{x}}^0)$	10
		$2n)1^0$	$(\varphi_8; 2n_{\overline{x}}) (\eta; {}^0)$	8
			$(\varphi_8; {}^0) (\eta; 2n_{\overline{x}})$	7
			$(\varphi_8; 2n_{\overline{x}}) (\eta; 2n_{\overline{x}}^0)$	9
$\Gamma_e = n^0$				
8mm	1	n^0	$(\varphi_8;) (\eta;)$	6
8	m	$n1^0$	$(\varphi_8;) (\eta; {}^0)$	6
4mm	2	$n1^0$	$(\varphi_8; {}^0) (\eta;)$	6
4m ⁰ m ⁰	2	$n^0 2\ 2^0$	$(\varphi_8; 2_{\overline{x}}) (\eta; 2_{\overline{x}})$	10
		$n1^0$	$(\varphi_8; {}^0) (\eta; {}^0)$	6
4	222	$n221^0$	$(\varphi_8; 2_{\overline{x}}) (\eta; 2_{\overline{x}}^0)$	10
$\Gamma_e = 2\ 2\ 2$				
4m ⁰ m ⁰	2	$4^{\vee} 2\ 2\ ^{\vee}$	$(\varphi_8; 4_{\overline{x}}^{\vee}) (\eta; 4_{\overline{x}}^{\vee})$	5
4	2mm	4221 ⁰	$(\varphi_8; 4_{\overline{x}}^{\vee}) (\eta; 4_{\overline{x}}^{\vee})$	5

Table 31: Explicit list of octagonal spin space-group types with $G = \bar{8}m2$ on V -lattices. The last column refers to line numbers in Table 10, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
$8m2$	1	1	$(\bar{v}_8; \) \ (m; \)$	1
8	2	2	$(\bar{v}_8; \) \ (m; 2_{\bar{x}})$	1
		1^0	$(\bar{v}_8; \) \ (m; \overset{0}{\bar{x}})$	1
$4mm$	2	2	$(\bar{v}_8; 2_{\bar{x}}) \ (m; \)$	1
		1^0	$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; \)$	1
$42^0 2^0$	2	2	$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}})$	1
		1^0	$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; \overset{0}{\bar{x}})$	1
4	222	$2 \ 2^y 2^y$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
		21^0	$(\bar{v}_8; 2_{\bar{x}}) \ (m; \overset{0}{\bar{x}})$	1
			$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; 2_{\bar{x}})$	1
			$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}}^0)$	1
2	422	$4 \ 2^y 2^y$	$(\bar{v}_8; 4_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
1	$8m2$	$8 \ 2^y 2^y$	$(\bar{v}_8; 8_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
			$(\bar{v}_8; 8_{\bar{x}}^3) \ (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2$				
$8m2$	1	2	$(\bar{v}_8; \) \ (m; \)$	1
8	2	$2 \ 2 \ 2$	$(\bar{v}_8; \) \ (m; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8; \) \ (m; \overset{0}{\bar{x}})$	1
$4mm$	2	$2 \ 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; \)$	1
		21^0	$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; \)$	1
		4	$(\bar{v}_8; 4_{\bar{x}}) \ (m; \)$	2
$42^0 2^0$	2	$2 \ 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; \overset{0}{\bar{x}})$	1
		4	$(\bar{v}_8; 4_{\bar{x}}) \ (m; 4_{\bar{x}})$	3
4	222	$4 \ 2^y 2^y$	$(\bar{v}_8; 4_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
			$(\bar{v}_8; 2_{\bar{x}}^y) \ (m; 4_{\bar{x}})$	3
			$(\bar{v}_8; 2_{\bar{x}}^y) \ (m; 2_{\bar{x}}^y)$	2
		41^0	$(\bar{v}_8; 4_{\bar{x}}) \ (m; \overset{0}{\bar{x}})$	2
			$(\bar{v}_8; 4_{\bar{x}}) \ (m; 4_{\bar{x}}^0)$	3
			$2^0 2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; \overset{0}{\bar{x}})$
		$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; 2_{\bar{x}})$		1
		$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}}^0)$	1	
2	422	$8 \ 2^y 2^y$	$(\bar{v}_8; 8_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2^0$				
$8m2$	1	2^0	$(\bar{v}_8; \) \ (m; \)$	1
8	2	$2^0 2^0$	$(\bar{v}_8; \) \ (m; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8; \) \ (m; \overset{0}{\bar{x}})$	1
$4mm$	2	$2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; \)$	1
		21^0	$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; \)$	1
$42^0 2^0$	2	$2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; \overset{0}{\bar{x}})$	1
4	222	$2^0 2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) \ (m; \overset{0}{\bar{x}})$	1
			$(\bar{v}_8; \overset{0}{\bar{x}}) \ (m; 2_{\bar{x}})$	1
			$(\bar{v}_8; 2_{\bar{x}}) \ (m; 2_{\bar{x}}^0)$	1
2	422	4221^0	$(\bar{v}_8; 4_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
1	$8m2$	8221^0	$(\bar{v}_8; 8_{\bar{x}}) \ (m; 2_{\bar{x}}^y)$	1
$\Gamma_e = 1^0$				

continued on next page

Table 31: continued

G	$G=G$	Γ	generators	line
$8m2$	1	1^0	$(\bar{\nu}_8;) (m;)$	1
8	2	21^0	$(\bar{\nu}_8;) (m; 2_{\bar{z}})$	1
$4mm$	2	21^0	$(\bar{\nu}_8; 2_{\bar{z}}) (m;)$	1
$42^0 2^0$	2	21^0	$(\bar{\nu}_8; 2_{\bar{z}}) (m; 2_{\bar{z}})$	1
4	222	$2^0 2^0 2^0$	$(\bar{\nu}_8; 2_{\bar{z}}) (m; 2_{\bar{x}})$	1
2	422	4221^0	$(\bar{\nu}_8; 4_{\bar{z}}) (m; 2_{\bar{x}})$	1
1	$8m2$	8221^0	$(\bar{\nu}_8; 8_{\bar{z}}) (m; 2_{\bar{x}})$	1
			$(\bar{\nu}_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}})$	1
$\Gamma_e = 21^0$				
$8m2$	1	21^0	$(\bar{\nu}_8;) (m;)$	1
8	2	$2^0 2^0 2^0$	$(\bar{\nu}_8;) (m; 2_{\bar{x}})$	1
$4mm$	2	41^0	$(\bar{\nu}_8; 4_{\bar{z}}) (m;)$	1
		$2^0 2^0 2^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m;)$	1
$42^0 2^0$	2	41^0	$(\bar{\nu}_8; 4_{\bar{z}}) (m; 4_{\bar{z}})$	3
		$2^0 2^0 2^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m; 2_{\bar{x}})$	1
4	222	4221^0	$(\bar{\nu}_8; 4_{\bar{z}}) (m; 2_{\bar{x}})$	1
			$(\bar{\nu}_8; 2_{\bar{x}}) (m; 4_{\bar{z}})$	3
			$(\bar{\nu}_8; 2_{\bar{x}}) (m; 2_{\bar{x}\bar{y}})$	2
2	422	8221^0	$(\bar{\nu}_8; 8_{\bar{z}}) (m; 2_{\bar{x}})$	1
$\Gamma_e = n$				
$4mm$	2	$n2 \ 2$	$(\bar{\nu}_8; 2_{\bar{x}}) (m;)$	6
4	222	$(2n) \ 2^y 2 \ ^y$	$(\bar{\nu}_8; 2_{\bar{x}}^y) (m; (2n)_{\bar{z}})$	7
		$n221^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m; ^0)$	6
$\Gamma_e = n^0$				
$4mm$	2	$n^0 2 \ 2^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m;)$	6
4	222	$n221^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m; ^0)$	6
$\Gamma_e = n1^0$				
$4mm$	2	$n221^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m;)$	6
4	222	$(2n)221^0$	$(\bar{\nu}_8; 2_{\bar{x}}) (m; (2n)_{\bar{z}})$	7
$\Gamma_e = 222$				
$8m2$	1	222	$(\bar{\nu}_8;) (m;)$	4a
8	2	$2^0 2^0 2^0$	$(\bar{\nu}_8;) (m; ^0)$	4a
$4mm$	2	$2^0 2^0 2^0$	$(\bar{\nu}_8; ^0) (m;)$	4a
		$4^y 2 \ 2 \ ^y$	$(\bar{\nu}_8; 4_{\bar{z}}^y) (m;)$	5
$42^0 2^0$	2	$2^0 2^0 2^0$	$(\bar{\nu}_8; ^0) (m; ^0)$	4a
4	222	4221^0	$(\bar{\nu}_8; 4_{\bar{z}}^y) (m; ^0)$	5
$\Gamma_e = 2^0 2^0 2^0$				
$8m2$	1	$2 \ 2 \ 2$	$(\bar{\nu}_8;) (m;)$	4
8	2	$2^0 2^0 2^0$	$(\bar{\nu}_8;) (m; ^0)$	4
$4mm$	2	$2^0 2^0 2^0$	$(\bar{\nu}_8; ^0) (m;)$	4
		$4^y 2 \ 2 \ ^y$	$(\bar{\nu}_8; 4_{\bar{z}}^y) (m;)$	5
$42^0 2^0$	2	$2^0 2^0 2^0$	$(\bar{\nu}_8; ^0) (m; ^0)$	4
4	222	4221^0	$(\bar{\nu}_8; 4_{\bar{z}}^y) (m; ^0)$	5
$\Gamma_e = 2^0 2^0 2^0$				
$4mm$	2	4221^0	$(\bar{\nu}_8; 4_{\bar{z}}) (m;)$	5

Table 32: Explicit list of octagonal spin space-group types with $G = \bar{8}m2$ on S -lattices. The last column refers to line numbers in Table 11, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
$8m2$	1	1	$(\bar{r}_8; \) (m; \)$	1
$\bar{8}$	2	2	$(\bar{r}_8; \) (m; 2_-)$	1
		1^0	$(\bar{r}_8; \) (m; \ ^0)$	1
$4mm$	2	2	$(\bar{r}_8; 2_-) (m; \)$	1
		1^0	$(\bar{r}_8; \ ^0) (m; \)$	1
42^{02^0}	2	2	$(\bar{r}_8; 2_-) (m; 2_-)$	1
		1^0	$(\bar{r}_8; \ ^0) (m; \ ^0)$	1
4	222	$2 \ 2^y 2^y$	$(\bar{r}_8; 2_-) (m; 2^y_x)$	1
		21^0	$(\bar{r}_8; 2_-) (m; \ ^0)$	1
			$(\bar{r}_8; \ ^0) (m; 2_-)$	1
			$(\bar{r}_8; 2_-) (m; 2^0_x)$	1
2	422	$4 \ 2^y 2^y$	$(\bar{r}_8; 4_-) (m; 2^y_x)$	1
1	$8m2$	$8 \ 2^y 2^y$	$(\bar{r}_8; 8_-) (m; 2^y_x)$	1
			$(\bar{r}_8; 8^3_x) (m; 2^y_x)$	1
$\Gamma_e = 2$				
$8m2$	1	2	$(\bar{r}_8; \) (m; \)$	1
$\bar{8}$	2	$2 \ 2 \ 2$	$(\bar{r}_8; \) (m; 2_-)$	1
		21^0	$(\bar{r}_8; \) (m; \ ^0)$	1
$4mm$	2	$2 \ 2 \ 2$	$(\bar{r}_8; 2_-) (m; \)$	1
		21^0	$(\bar{r}_8; \ ^0) (m; \)$	1
42^{02^0}	2	$2 \ 2 \ 2$	$(\bar{r}_8; 2_-) (m; 2_-)$	1
		21^0	$(\bar{r}_8; \ ^0) (m; \ ^0)$	1
		4	$(\bar{r}_8; 4_-) (m; 4_-)$	2
4	222	$4 \ 2^y 2^y$	$(\bar{r}_8; 4_-) (m; 2^y_x)$	1
			$(\bar{r}_8; 2^y_x) (m; 4_-)$	2
		41^0	$(\bar{r}_8; 4_-) (m; 4^0_x)$	2
			$(\bar{r}_8; 2_-) (m; \ ^0)$	1
			$(\bar{r}_8; \ ^0) (m; 2_-)$	1
			$(\bar{r}_8; 2_-) (m; 2^0_x)$	1
2	422	$8 \ 2^y 2^y$	$(\bar{r}_8; 8_-) (m; 2^y_x)$	1
$\Gamma_e = 2^0$				
$8m2$	1	2^0	$(\bar{r}_8; \) (m; \)$	1
$\bar{8}$	2	$2^0 \ 2^0$	$(\bar{r}_8; \) (m; 2_-)$	1
		21^0	$(\bar{r}_8; \) (m; \ ^0)$	1
$4mm$	2	$2^0 \ 2^0$	$(\bar{r}_8; 2_-) (m; \)$	1
		21^0	$(\bar{r}_8; \ ^0) (m; \)$	1
42^{02^0}	2	$2^0 \ 2^0$	$(\bar{r}_8; 2_-) (m; 2_-)$	1
		21^0	$(\bar{r}_8; \ ^0) (m; \ ^0)$	1
4	222	$2^0 2^0 2^0$	$(\bar{r}_8; 2_-) (m; \ ^0)$	1
			$(\bar{r}_8; \ ^0) (m; 2_-)$	1
			$(\bar{r}_8; 2_-) (m; 2^0_x)$	1
2	422	4221^0	$(\bar{r}_8; 4_-) (m; 2^y_x)$	1
1	$8m2$	8221^0	$(\bar{r}_8; 8_-) (m; 2^y_x)$	1
$\Gamma_e = 1^0$				
$8m2$	1	1^0	$(\bar{r}_8; \) (m; \)$	1
$\bar{8}$	2	21^0	$(\bar{r}_8; \) (m; 2_-)$	1
$4mm$	2	21^0	$(\bar{r}_8; 2_-) (m; \)$	1

continued on next page

Table 32: continued

G	$G=G$	Γ	generators	line
42^{02}_0	2	21^0	$(\bar{r}_8; 2_{\bar{z}}) (m; 2_{\bar{z}})$	1
4	222	$2^{02}2^0$	$(\bar{r}_8; 2_{\bar{z}}) (m; 2_{\bar{x}})$	1
2	422	4221^0	$(\bar{r}_8; 4_{\bar{z}}) (m; 2_{\bar{x}})$	1
1	$8m2$	8221^0	$(\bar{r}_8; 8_{\bar{z}}) (m; 2_{\bar{x}})$	1
			$(\bar{r}_8; 8^3_{\bar{z}}) (m; 2_{\bar{x}})$	1
$\Gamma_e = n$				
$\bar{8}$	2	$n2 \ 2$	$(\bar{r}_8; \) (m; 2_{\bar{z}})$	6
$4mm$	2	$(2n) \ n2 \ 2$	$(\bar{r}_8; 2_{\bar{z}}) (m; \)$	4
4	222	$(2n) \ 2^y2 \ ^y$	$(\bar{r}_8; (2n)_{\bar{z}}) (m; 2^y_{\bar{x}})$	6
			$(\bar{r}_8; 2^y_{\bar{x}}) (m; (2n)_{\bar{z}})$	5
		$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (m; \ ^0)$	4
			$(\bar{r}_8; \ ^0) (m; 2_{\bar{x}})$	6
$\Gamma_e = n^0$				
$\bar{8}$	2	$n^{02} \ 2^0$	$(\bar{r}_8; \) (m; 2_{\bar{x}})$	6
$4mm$	2	$n^{02} \ 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (m; \)$	4
4	222	$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (m; \ ^0)$	4
			$(\bar{r}_8; \ ^0) (m; 2_{\bar{x}})$	6
2	422	$(2n)221^0$	$(\bar{r}_8; (2n)_{\bar{x}}) (m; 2^y_{\bar{x}})$	6
$\Gamma_e = 2 \ 2 \ 2$				
42^{02}_0	2	$4^y2 \ 2^y$	$(\bar{r}_8; 4^y_{\bar{z}}) (m; 4^y_{\bar{z}})$	3
4	222	4221^0	$(\bar{r}_8; 4^y_{\bar{z}}) (m; 4^y_{\bar{z}})$	3

Table 33: Explicit list of octagonal spin space-group types with $G = 822$ on V -lattices. The last column refers to line numbers in Table 12, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
822	1	1	$(r_8; \) (d; \)$	1
8	m	2	$(r_8; \) (d; 2_{\bar{z}})$	1
		1^0	$(r_8; \) (d; \overset{0}{\bar{z}})$	1
422	2	2	$(r_8; 2_{\bar{z}}) (d; \)$	1
		1^0	$(r_8; \overset{0}{\bar{z}}) (d; \)$	1
$42^0 2^0$	2	2	$(r_8; 2_{\bar{z}}) (d; 2_{\bar{z}})$	1
		1^0	$(r_8; \overset{0}{\bar{z}}) (d; \overset{0}{\bar{z}})$	1
4	222	$2 \ 2^y 2^y \ ^y$	$(r_8; 2_{\bar{z}}) (d; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{z}}) (d; \overset{0}{\bar{z}})$	1
		21^0	$(r_8; \overset{0}{\bar{z}}) (d; 2_{\bar{z}})$	1
			$(r_8; 2_{\bar{z}}) (d; 2_{\bar{z}}^0)$	1
2	422	$4 \ 2^y 2^y$	$(r_8; 4_{\bar{z}}) (d; 2_{\bar{x}}^y)$	1
1	822	$8 \ 2^y 2^y \ ^y$	$(r_8; 8_{\bar{z}}) (d; 2_{\bar{x}}^y)$	1
			$(r_8; 8_{\bar{z}}^3) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2$				
822	1	2	$(r_8; \) (d; \)$	1
8	m	$2 \ 2 \ 2$	$(r_8; \) (d; 2_{\bar{x}})$	1
		21^0	$(r_8; \) (d; \overset{0}{\bar{x}})$	1
422	2	$2 \ 2 \ 2$	$(r_8; 2_{\bar{x}}) (d; \)$	1
		21^0	$(r_8; \overset{0}{\bar{x}}) (d; \)$	1
		4	$(r_8; 4_{\bar{z}}) (d; \)$	3

continued on next page

Table 33: continued

G	$G=G$	Γ	generators	line
$42^0 2^0$	2	$2 \ 2 \ 2$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; {}^0) (d; {}^0)$	1
4	222	$4 \ 2^y 2 \ {}^y$	$(\nu_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
			$(\nu_8; 2_{\bar{x}}^y) (d; 2_{\bar{x}}^y)$	3
		41^0	$(\nu_8; 4_{\bar{x}}) (d; {}^0)$	3
		$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; {}^0)$	1
			$(\nu_8; {}^0) (d; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
2	422	$8 \ 2^y 2 \ {}^y$	$(\nu_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
1	822	$(16) \ 2^y 2 \ {}^y$	$(\nu_8; 16_{\bar{x}}) (d; 2_{\bar{x}}^y)$	2
			$(\nu_8; 16_{\bar{x}}^3) (d; 2_{\bar{x}}^y)$	2
$\Gamma_e = 2^0$				
822	1	2^0	$(\nu_8; \) (d; \)$	1
8	m	$2^0 2^0$	$(\nu_8; \) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; \) (d; {}^0)$	1
422	2	$2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
		21^0	$(\nu_8; {}^0) (d; \)$	1
$42^0 2^0$	2	$2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; {}^0) (d; {}^0)$	1
4	222	$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; {}^0)$	1
			$(\nu_8; {}^0) (d; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
2	422	4221^0	$(\nu_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
1	822	8221^0	$(\nu_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 1^0$				
822	1	1^0	$(\nu_8; \) (d; \)$	1
8	m	21^0	$(\nu_8; \) (d; 2_{\bar{x}})$	1
422	2	21^0	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
$42^0 2^0$	2	21^0	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
4	222	$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
2	422	4221^0	$(\nu_8; 4_{\bar{x}}) (d; 2_{\bar{x}})$	1
1	822	8221^0	$(\nu_8; 8_{\bar{x}}) (d; 2_{\bar{x}})$	1
			$(\nu_8; 8_{\bar{x}}^3) (d; 2_{\bar{x}})$	1
$\Gamma_e = 21^0$				
822	1	21^0	$(\nu_8; \) (d; \)$	1
8	m	$2^0 2^0 2^0$	$(\nu_8; \) (d; 2_{\bar{x}})$	1
422	2	41^0	$(\nu_8; 4_{\bar{x}}) (d; \)$	3
		$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
$42^0 2^0$	2	$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
4	222	4221^0	$(\nu_8; 4_{\bar{x}}) (d; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^y)$	3
2	422	8221^0	$(\nu_8; 8_{\bar{x}}) (d; 2_{\bar{x}})$	1
1	822	$(16) 221^0$	$(\nu_8; 16_{\bar{x}}) (d; 2_{\bar{x}})$	2
			$(\nu_8; 16_{\bar{x}}^3) (d; 2_{\bar{x}})$	2
$\Gamma_e = n$				
8	2	$n 2 \ 2$	$(\nu_8; \) (d; 2_{\bar{x}})$	6
4	222	$(2n) \ 2^y 2 \ {}^y$	$(\nu_8; (2n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	10
		$n 221^0$	$(\nu_8; {}^0) (d; 2_{\bar{x}})$	6
2	422	$(4n) \ 2^y 2 \ {}^y$	$(\nu_8; (4n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	9
1	822	$(8n) \ 2^y 2 \ {}^y$	$(\nu_8; (8n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	7

continued on next page

Table 33: continued

G	$G=G$	Γ	generators	line
			$(\nu_8; (8n)_{\bar{z}}^{\frac{3}{2}}) (d; 2_{\bar{x}}^{\frac{y}{2}})$	8
$\Gamma_e = n^0$				
8	m	$n^0 2^0$	$(\nu_8;) (d; 2_{\bar{x}})$	6
4	222	$n221^0$	$(\nu_8; {}^0) (d; 2_{\bar{x}})$	6
2	422	$(2n)221^0$	$(\nu_8; (2n)_{\bar{z}}) (d; 2_{\bar{x}}^{\frac{y}{2}})$	10
1	822	$(4n)221^0$	$(\nu_8; (4n)_{\bar{z}}) (d; 2_{\bar{x}}^{\frac{y}{2}})$	9
$\Gamma_e = n1^0$				
8	2	$n221^0$	$(\nu_8;) (d; 2_{\bar{x}})$	6
4	222	$(2n)221^0$	$(\nu_8; (2n)_{\bar{z}}) (d; 2_{\bar{x}})$	10
2	422	$(4n)221^0$	$(\nu_8; (4n)_{\bar{z}}) (d; 2_{\bar{x}})$	9
1	822	$(8n)221^0$	$(\nu_8; (8n)_{\bar{z}}) (d; 2_{\bar{x}})$	7
			$(\nu_8; (8n)_{\bar{z}}^{\frac{3}{2}}) (d; 2_{\bar{x}})$	8
$\Gamma_e = 222$				
822	1	222	$(\nu_8;) (d;)$	4a
8	m	$2^0 2^0 2^0$	$(\nu_8;) (d; {}^0)$	4a
422	2	$2^0 2^0 2^0$	$(\nu_8; {}^0) (d;)$	4a
		$4^y 2^0 2^0$	$(\nu_8; 4_{\bar{z}}^{\frac{y}{2}}) (d;)$	5
$42^0 2^0$	2	$2^0 2^0 2^0$	$(\nu_8; {}^0) (d; {}^0)$	4a
4	222	4221^0	$(\nu_8; 4_{\bar{z}}^{\frac{y}{2}}) (d; {}^0)$	5
$\Gamma_e = 2^0 2^0$				
822	1	$2^0 2^0$	$(\nu_8;) (d;)$	4
8	m	$2^0 2^0 2^0$	$(\nu_8;) (d; {}^0)$	4
422	2	$2^0 2^0 2^0$	$(\nu_8; {}^0) (d;)$	4
		$4^y 2^0 2^0$	$(\nu_8; 4_{\bar{z}}^{\frac{y}{2}}) (d;)$	5
$42^0 2^0$	2	$2^0 2^0 2^0$	$(\nu_8; {}^0) (d; {}^0)$	4
4	222	4221^0	$(\nu_8; 4_{\bar{z}}^{\frac{y}{2}}) (d; {}^0)$	5
$\Gamma_e = 2^0 2^0 2^0$				
822	1	$2^0 2^0 2^0$	$(\nu_8;) (d;)$	4a
422	2	4221^0	$(\nu_8; 4_{\bar{z}}) (d;)$	5

Table 34: Explicit list of octagonal spin space-group types with $G = 822$ on S -lattices. The last column refers to line numbers in Table 13, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
822	1	1	$(\nu_8; \) (d; \)$	1
8	2	2	$(\nu_8; \) (d; 2_{\bar{x}})$	1
		1^0	$(\nu_8; \) (d; \overset{0}{})$	1
422	2	2	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
		1^0	$(\nu_8; \overset{0}{}) (d; \)$	1
$42^0 2^0$	2	2	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		1^0	$(\nu_8; \overset{0}{}) (d; \overset{0}{})$	1
4	222	$2 \ 2^y 2^y$	$(\nu_8; 2_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
		21^0	$(\nu_8; 2_{\bar{x}}) (d; \overset{0}{})$	1
			$(\nu_8; \overset{0}{}) (d; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (d; 2^0_{\bar{x}})$	1
2	422	$4 \ 2^y 2^y$	$(\nu_8; 4_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
1	822	$8 \ 2^y 2^y$	$(\nu_8; 8_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
			$(\nu_8; 8^3_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
$\Gamma_e = 2$				
822	1	2	$(\nu_8; \) (d; \)$	1
8	2	$2 \ 2 \ 2$	$(\nu_8; \) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; \) (d; \overset{0}{})$	1
422	2	$2 \ 2 \ 2$	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
		21^0	$(\nu_8; \overset{0}{}) (d; \)$	1
$42^0 2^0$	2	$2 \ 2 \ 2$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; \overset{0}{}) (d; \overset{0}{})$	1
		4	$(\nu_8; 4_{\bar{x}}) (d; 4_{\bar{x}})$	3
4	222	$4 \ 2^y 2^y$	$(\nu_8; 4_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
			$(\nu_8; 2^y_{\bar{x}}) (d; 4_{\bar{x}})$	1
			$(\nu_8; 4_{\bar{x}}) (d; 4^0_{\bar{x}})$	1
		$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; \overset{0}{})$	1
			$(\nu_8; \overset{0}{}) (d; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (d; 2^0_{\bar{x}})$	1
2	422	$8 \ 2^y 2^y$	$(\nu_8; 8_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
1	822	$(16) \ 2^y 2^y$	$(\nu_8; 16_{\bar{x}}) (d; 2^y_{\bar{x}})$	2
			$(\nu_8; 16^3_{\bar{x}}) (d; 2^y_{\bar{x}})$	2
$\Gamma_e = 2^0$				
822	1	2^0	$(\nu_8; \) (d; \)$	1
8	2	$2^0 \ 2^0$	$(\nu_8; \) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; \) (d; \overset{0}{})$	1
422	2	$2^0 \ 2^0$	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
		21^0	$(\nu_8; \overset{0}{}) (d; \)$	1
$42^0 2^0$	2	$2^0 \ 2^0$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\nu_8; \overset{0}{}) (d; \overset{0}{})$	1
4	222	$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (d; \overset{0}{})$	1
			$(\nu_8; \overset{0}{}) (d; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (d; 2^0_{\bar{x}})$	1
2	422	4221^0	$(\nu_8; 4_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
1	822	8221^0	$(\nu_8; 8_{\bar{x}}) (d; 2^y_{\bar{x}})$	1
$\Gamma_e = 1^0$				
822	1	1^0	$(\nu_8; \) (d; \)$	1

continued on next page

Table 34: continued

G	$G=G$	Γ	generators	line
8	2	21^0	$(\nu_8; \) (d; 2_{\bar{x}})$	1
422	2	21^0	$(\nu_8; 2_{\bar{x}}) (d; \)$	1
42^{02^0}	2	21^0	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
4	222	$2^{02^0} 2^0$	$(\nu_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
2	422	4221^0	$(\nu_8; 4_{\bar{x}}) (d; 2_{\bar{x}})$	1
1	822	8221^0	$(\nu_8; 8_{\bar{x}}) (d; 2_{\bar{x}})$	1
			$(\nu_8; 8_{\bar{x}}^3) (d; 2_{\bar{x}})$	1
$\Gamma_e = n$				
8	2	$n2 \ 2$	$(\nu_8; \) (d; 2_{\bar{x}})$	5
422	2	$n2 \ 2$	$(\nu_8; 2_{\bar{x}}) (d; \)$	10
4	222	$(2n) \ 2^y 2 \ ^y$	$(\nu_8; (2n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	9
		$n221^0$	$(\nu_8; 2_{\bar{x}}) (d; \ ^0)$	10
			$(\nu_8; \ ^0) (d; 2_{\bar{x}})$	5
2	422	$(4n) \ 2^y 2 \ ^y$	$(\nu_8; (4n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	7
1	822	$(8n) \ 2^y 2 \ ^y$	$(\nu_8; (8n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	6
			$(\nu_8; (8n)_{\bar{x}}^3) (d; 2_{\bar{x}}^y)$	8
$\Gamma_e = n^0$				
8	2	$n^0 2 \ 2^0$	$(\nu_8; \) (d; 2_{\bar{x}})$	5
422	2	$n^0 2 \ 2^0$	$(\nu_8; 2_{\bar{x}}) (d; \)$	10
4	222	$n221^0$	$(\nu_8; 2_{\bar{x}}) (d; \ ^0)$	10
			$(\nu_8; \ ^0) (d; 2_{\bar{x}})$	5
2	422	$(2n)221^0$	$(\nu_8; (2n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	5
1	822	$(4n)221^0$	$(\nu_8; (4n)_{\bar{x}}) (d; 2_{\bar{x}}^y)$	5
$\Gamma_e = 2 \ 2 \ 2$				
42^{02^0}	2	$4^y 2 \ 2^y$	$(\nu_8; 4_{\bar{x}}^y) (d; 4_{\bar{x}}^y)$	4
4	222	4221^0	$(\nu_8; 4_{\bar{x}}^y) (d; 4_{\bar{x}}^{0y})$	4

Table 35: Explicit list of octagonal spin space-group types with $G = \bar{8}2m$ on V -lattices. The last column refers to line numbers in Table 14, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
$\bar{8}m2$	1	1	$(\bar{v}_8;) (d;)$	1
8	2	2	$(\bar{v}_8;) (d; 2_-)$	1
		1^0	$(\bar{v}_8;) (d; {}^0)$	1
$4mm$	2	2	$(\bar{v}_8; 2_{\bar{x}}) (d;)$	1
		1^0	$(\bar{v}_8; {}^0) (d;)$	1
$42^0 2^0$	2	2	$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		1^0	$(\bar{v}_8; {}^0) (d; {}^0)$	1
	222	$2 \ 2^y 2^y$	$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
		21^0	$(\bar{v}_8; 2_{\bar{x}}) (d; {}^0)$	1
			$(\bar{v}_8; {}^0) (d; 2_{\bar{x}})$	1
			$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
2	422	$4 \ 2^y 2^y$	$(\bar{v}_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
1	$\bar{8}m2$	$8 \ 2^y 2^y$	$(\bar{v}_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
			$(\bar{v}_8; 8_{\bar{x}}^3) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2$				
$\bar{8}2m$	1	2	$(\bar{v}_8;) (d;)$	1
8	2	$2 \ 2 \ 2$	$(\bar{v}_8;) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8;) (d; {}^0)$	1
422	2	$2 \ 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}}) (d;)$	1
		21^0	$(\bar{v}_8; {}^0) (d;)$	1
$4m^0 m^0$	2	$2 \ 2 \ 2$	$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8; {}^0) (d; {}^0)$	1
4	222	$4 \ 2^y 2^y$	$(\bar{v}_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
			$(\bar{v}_8; 2_{\bar{x}}^y) (d; 2_{\bar{x}}^y)$	2
		$2^0 2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) (d; {}^0)$	1
			$(\bar{v}_8; {}^0) (d; 2_{\bar{x}})$	1
			$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
		41^0	$(\bar{v}_8; 4_{\bar{x}}) (d; {}^0)$	2
2	422	$8 \ 2^y 2^y$	$(\bar{v}_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2^0$				
$\bar{8}m2$	1	2^0	$(\bar{v}_8;) (d;)$	1
8	2	$2^0 2^0$	$(\bar{v}_8;) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8;) (d; {}^0)$	1
$4mm$	2	$2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) (d;)$	1
		21^0	$(\bar{v}_8; {}^0) (d;)$	1
$42^0 2^0$	2	$2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{v}_8; {}^0) (d; {}^0)$	1
4	222	$2^0 2^0 2^0$	$(\bar{v}_8; 2_{\bar{x}}) (d; {}^0)$	1
			$(\bar{v}_8; {}^0) (d; 2_{\bar{x}})$	1
			$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
2	422	4221^0	$(\bar{v}_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
1	$\bar{8}m2$	8221^0	$(\bar{v}_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 1^0$				
$\bar{8}m2$	1	1^0	$(\bar{v}_8;) (d;)$	1
8	2	21^0	$(\bar{v}_8;) (d; 2_{\bar{x}})$	1
$4mm$	2	21^0	$(\bar{v}_8; 2_{\bar{x}}) (d;)$	1
$42^0 2^0$	2	21^0	$(\bar{v}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1

continued on next page

Table 35: continued

G	$G=G$	Γ	generators	line
4	222	$2^0 2^0 2^0$	$(\bar{r}_8; 2_{\bar{z}}) (d; 2_{\bar{x}})$	1
2	422	4221^0	$(\bar{r}_8; 4_{\bar{z}}) (d; 2_{\bar{x}})$	1
1	8m2	8221^0	$(\bar{r}_8; 8_{\bar{z}}) (d; 2_{\bar{x}})$	1
			$(\bar{r}_8; 8_{\bar{z}}^3) (d; 2_{\bar{x}})$	1
$\Gamma_e = 21^0$				
82m	1	21^0	$(\bar{r}_8;) (d;)$	1
8	2	$2^0 2^0 2^0$	$(\bar{r}_8;) (d; 2_{\bar{z}})$	1
422	2	41^0	$(\bar{r}_8; 4_{\bar{z}}) (d;)$	2
		$2^0 2^0 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d;)$	1
$4m^0 m^0$	2	$2^0 2^0 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
4	222	4221^0	$(\bar{r}_8; 4_{\bar{z}}) (d; 2_{\bar{x}})$	1
			$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	2
2	422	8221^0	$(\bar{r}_8; 8_{\bar{z}}) (d; 2_{\bar{x}})$	1
$\Gamma_e = n$				
$4m^0 m^0$	2	$n2 \ 2$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	5
4	222	$(2n) \ 2^y 2^y$	$(\bar{r}_8; 2_{\bar{x}}^y (2n)_{\bar{z}}) (d; 2_{\bar{x}}^y)$	6
		$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	5
$\Gamma_e = n^0$				
$4m^0 m^0$	2	$n^0 2 \ 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	5
4	222	$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	5
$\Gamma_e = n1^0$				
$4m^0 m^0$	2	$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	5
4	222	$(2n)221^0$	$(\bar{r}_8; 2_{\bar{x}} (2n)_{\bar{z}}) (d; 2_{\bar{x}})$	6
$\Gamma_e = 222$				
82m	1	222	$(\bar{r}_8; eps) (d;)$	3a
8	2	$2^0 2^0 2^0$	$(\bar{r}_8;) (d; ^0)$	3a
422	2	$2^0 2^0 2^0$	$(\bar{r}_8; ^0) (d;)$	3a
		4 22	$(\bar{r}_8; 4_{\bar{z}}) (d;)$	4
$4m^0 m^0$	2	$2^0 2^0 2^0$	$(\bar{r}_8; ^0) (d; ^0)$	3a
4	222	$42^0 2^0 2^0$	$(\bar{r}_8; 4_{\bar{z}}) (d; ^0)$	4
$\Gamma_e = 2^0 2^0 2^0$				
82m	1	$2^0 2^0 2^0$	$(\bar{r}_8; eps) (d;)$	3
8	2	$2^0 2^0 2^0$	$(\bar{r}_8;) (d; ^0)$	3
422	2	$2^0 2^0 2^0$	$(\bar{r}_8; ^0) (d;)$	3
		4 22	$(\bar{r}_8; 4_{\bar{z}}) (d;)$	4
$4m^0 m^0$	2	$2^0 2^0 2^0$	$(\bar{r}_8; ^0) (d; ^0)$	3
4	222	$42^0 2^0 2^0$	$(\bar{r}_8; 4_{\bar{z}}) (d; ^0)$	4
$\Gamma_e = 2^0 2^0 2^0$				
82m	1	$2^0 2^0 2^0$	$(\bar{r}_8;) (d;)$	3a
422	2	4221^0	$(\bar{r}_8; 4_{\bar{z}}) (d;)$	4

Table 36: Explicit list of octagonal spin space-group types with $G = \bar{8}2m$ on S -lattices. The last column refers to line numbers in Table 15, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
82m	1	1	$(\bar{r}_8;) (d;)$	1
8	2	2	$(\bar{r}_8;) (d; 2_{\bar{z}})$	1

continued on next page

Table 36: continued

G	$G=G$	Γ	generators	line
		1^0	$(\bar{r}_8; \) (d; \ ^0)$	1
422	2	2	$(\bar{r}_8; 2_{\bar{x}}) (d; \)$	1
		1^0	$(\bar{r}_8; \ ^0) (d; \)$	1
$4m^0m^0$	2	2	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		1^0	$(\bar{r}_8; \ ^0) (d; \ ^0)$	1
4	222	$2 \ 2^y 2 \ ^y$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
		21^0	$(\bar{r}_8; 2_{\bar{x}}) (d; \ ^0)$	1
			$(\bar{r}_8; \ ^0) (d; 2_{\bar{x}})$	1
			$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
2	422	$4 \ 2^y 2^y$	$(\bar{r}_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
1	$8m2$	$8 \ 2^y 2 \ ^y$	$(\bar{r}_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
			$(\bar{r}_8; 8_{\bar{x}}^3) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2$				
$82m$	1	2	$(\bar{r}_8; \) (m; \)$	1
8	2	4	$(\bar{r}_8; \) (d; 4_{\bar{x}})$	2
		$2 \ 2 \ 2$	$(\bar{r}_8; \) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{r}_8; \) (d; \ ^0)$	1
422	2	4	$(\bar{r}_8; 4_{\bar{x}}) (d; \)$	2
		$2 \ 2 \ 2$	$(\bar{r}_8; 2_{\bar{x}}) (d; \)$	1
		21^0	$(\bar{r}_8; \ ^0) (d; \)$	1
$4m^0m^0$	2	4	$(\bar{r}_8; 4_{\bar{x}}) (d; 4_{\bar{x}})$	2
		$2 \ 2 \ 2$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{r}_8; \ ^0) (d; \ ^0)$	1
4	222	$4 \ 2^y 2 \ ^y$	$(\bar{r}_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
			$(\bar{r}_8; 2_{\bar{x}}) (d; 4_{\bar{x}})$	4
			$(\bar{r}_8; 2_{\bar{x}}^y) (d; 2_{\bar{x}}^y)$	3
		$2^0 2^0 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; \ ^0)$	1
			$(\bar{r}_8; \ ^0) (d; 2_{\bar{x}})$	1
			$(\bar{r}_8; 2_{\bar{x}}) (s; 2_{\bar{x}}^0)$	1
		41^0	$(\bar{r}_8; 4_{\bar{x}}) (d; \ ^0)$	3
			$(\bar{r}_8; \ ^0) (d; \)$	2
			$(\bar{r}_8; 4_{\bar{x}}) (d; 4_{\bar{x}}^0)$	4
2	422	$8 \ 2^y 2 \ ^y$	$(\bar{r}_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 2^0$				
$82m$	1	2^0	$(\bar{r}_8; \) (d; \)$	1
8	2	$2^0 2^0$	$(\bar{r}_8; \) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{r}_8; \) (d; \ ^0)$	1
422	2	$2^0 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; \)$	1
		21^0	$(\bar{r}_8; \ ^0) (d; \)$	1
$4m^0m^0$	2	$2^0 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	1
		21^0	$(\bar{r}_8; \ ^0) (d; \ ^0)$	1
4	222	$2^0 2^0 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; \ ^0)$	1
			$(\bar{r}_8; \ ^0) (d; 2_{\bar{x}})$	1
			$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	1
2	422	4221^0	$(\bar{r}_8; 4_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
1	$8m2$	8221^0	$(\bar{r}_8; 8_{\bar{x}}) (d; 2_{\bar{x}}^y)$	1
$\Gamma_e = 1^0$				
$82m$	1	1^0	$(\bar{r}_8; \) (d; \)$	1
8	2	21^0	$(\bar{r}_8; \) (d; 2_{\bar{x}})$	1
422	2	21^0	$(\bar{r}_8; 2_{\bar{x}}) (d; \)$	1

continued on next page

Table 36: continued

G	$G=G$	Γ	generators	line
$4m^0m^0$	2	21^0	$(\bar{r}_8; 2_{\bar{z}}) (d; 2_{\bar{z}})$	1
4	222	$2^0 2^0 2^0$	$(\bar{r}_8; 2_{\bar{z}}) (d; 2_{\bar{x}})$	1
2	422	4221^0	$(\bar{r}_8; 4_{\bar{z}}) (d; 2_{\bar{x}})$	1
1	$8m2$	8221^0	$(\bar{r}_8; 8_{\bar{z}}) (d; 2_{\bar{x}})$	1
			$(\bar{r}_8; 8_{\bar{z}}^3) (d; 2_{\bar{x}})$	1
$\Gamma_e = n$				
$82m$	1	n	$(\bar{r}_8;) (d;)$	8
8	2	$n1^0$	$(\bar{r}_8;) (d; ^0)$	8
422	2	$n1^0$	$(\bar{r}_8; ^0) (d;)$	8
$4m^0m^0$	2	$n2 \ 2$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}})$	6
		$n1^0$	$(\bar{r}_8; ^0) (d; ^0)$	8
4	222	$(2n) \ 2^y 2^y$	$(\bar{r}_8; 2_{\bar{x}}^y (2n)_{\bar{z}}) (d; 2_{\bar{x}}^y)$	7
		$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	6
		$(2n)1^0$	$(\bar{r}_8; (2n)_{\bar{z}}) (d; ^0)$	9
$\Gamma_e = n^0$				
$82m$	1	n^0	$(\bar{r}_8; ^0) (d; ^0)$	8
8	2	$n1^0$	$(\bar{r}_8;) (d; ^0)$	8
422	2	$n1^0$	$(\bar{r}_8; ^0) (d;)$	8
$4m^0m^0$	2	$n1^0$	$(\bar{r}_8; ^0) (d; ^0)$	8
		$n^0 2 \ 2^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	6
4	222	$n221^0$	$(\bar{r}_8; 2_{\bar{x}}) (d; 2_{\bar{x}}^0)$	6
$\Gamma_e = 2 \ 2 \ 2$				
$4m^0m^0$	2	$4 \ 22$	$(\bar{r}_8; 4_{\bar{z}}) (d; 4_{\bar{z}}^0)$	5
4	222	4221^0	$(\bar{r}_8; 4_{\bar{z}}) (s; 4_{\bar{z}}^0)$	5

Table 37: Explicit list of octagonal spin space-group types with $G = 8 \Rightarrow m$ on V -lattices. The last column refers to line numbers in Table 16, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
$8 \Rightarrow m$	1	1	$(r_8;) (\hbar;)$	1
8	2	2	$(r_8;) (\hbar; 2_{\bar{z}})$	1
		1^0	$(r_8;) (\hbar; ^0)$	1
8	2	2	$(r_8; 2_{\bar{z}}) (\hbar; 2_{\bar{z}})$	1
		1^0	$(r_8; ^0) (\hbar; ^0)$	1
$4 \Rightarrow m$	2	2	$(r_8; 2_{\bar{z}}) (\hbar;)$	1
		1^0	$(r_8; ^0) (\hbar;)$	1
4	222	$2 \ 2^y 2^y$	$(r_8; 2_{\bar{z}}) (\hbar; 2_{\bar{x}}^y)$	1
		21^0	$(r_8; 2_{\bar{z}}) (\hbar; ^0)$	1
			$(r_8; ^0) (\hbar; 2_{\bar{z}})$	1
			$(r_8; 2_{\bar{z}}) (\hbar; 2_{\bar{z}}^0)$	1
4	4	4	$(r_8; 4_{\bar{z}}) (\hbar; 2_{\bar{z}})$	1
$2 \Rightarrow m$	4	4	$(r_8; 4_{\bar{z}}) (\hbar;)$	1
2	$4 \Rightarrow m$	41^0	$(r_8; 4_{\bar{z}}) (\hbar; ^0)$	1
			$(r_8; 4_{\bar{z}}) (\hbar; 2_{\bar{z}}^0)$	1
2	8	8	$(r_8; 8_{\bar{z}}) (\hbar;)$	1
			$(r_8; 8_{\bar{z}}^3) (\hbar;)$	1
1	8	8	$(r_8; 8_{\bar{z}}) (\hbar; 2_{\bar{z}})$	1

continued on next page

Table 37: continued

G	$G=G$	Γ	generators	line
			$(r_8; 8_{\bar{x}}^{-3}) (\eta; 2_{\bar{x}}^-)$	1
1	$8=m$	81^0	$(r_8; 8_{\bar{x}}^-) (\eta; {}^0)$	1
			$(r_8; 8_{\bar{x}}^{-3}) (\eta; {}^0)$	1
			$(r_8; 8_{\bar{x}}^-) (\eta; 2_{\bar{x}}^0)$	1
			$(r_8; 8_{\bar{x}}^{-3}) (\eta; 2_{\bar{x}}^0)$	1
$\Gamma_e = 2$				
$8=m$	1	2	$(r_8; \quad) (\eta; \quad)$	1
8	2	$2\ 2\ 2$	$(r_8; \quad) (\eta; 2_{\bar{x}}^-)$	1
		21^0	$(r_8; \quad) (\eta; {}^0)$	1
8	2	$2\ 2\ 2$	$(r_8; 2_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
		21^0	$(r_8; {}^0) (\eta; {}^0)$	1
$4=m$	2	4	$(r_8; 4_{\bar{x}}^-) (\eta; \quad)$	1
		$2\ 2\ 2$	$(r_8; 2_{\bar{x}}^-) (\eta; \quad)$	1
		21^0	$(r_8; {}^0) (\eta; \quad)$	1
4	$2=m$	$4\ 2^y 2^{-y}$	$(r_8; 4_{\bar{x}}^-) (\eta; 2_{\bar{x}}^y)$	2
			$(r_8; 2_{\bar{x}}^y) (\eta; 2_{\bar{x}}^{-y})$	2
		41^0	$(r_8; 4_{\bar{x}}^-) (\eta; {}^0)$	1
		$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}^-) (\eta; {}^0)$	1
			$(r_8; {}^0) (\eta; 2_{\bar{x}}^-)$	1
			$(r_8; 2_{\bar{x}}^-) (\eta; 2_{\bar{x}}^0)$	1
$2=m$	4	8	$(r_8; 8_{\bar{x}}^-) (\eta; \quad)$	1
$\Gamma_e = 2^0$				
$8=m$	1	2^0	$(r_8; \quad) (\eta; \quad)$	1
8	2	21^0	$(r_8; \quad) (\eta; {}^0)$	1
		$2^0 2^0$	$(r_8; \quad) (\eta; 2_{\bar{x}}^-)$	1
8	2	21^0	$(r_8; {}^0) (\eta; {}^0)$	1
		$2^0 2^0$	$(r_8; 2_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
$4=m$	2	21^0	$(r_8; {}^0) (\eta; \quad)$	1
		$2^0 2^0$	$(r_8; 2_{\bar{x}}^-) (\eta; \quad)$	1
4	$2=m$	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}^-) (\eta; {}^0)$	1
			$(r_8; {}^0) (\eta; 2_{\bar{x}}^-)$	1
			$(r_8; 2_{\bar{x}}^-) (\eta; 2_{\bar{x}}^0)$	1
4	4	41^0	$(r_8; 4_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
$2=m$	4	41^0	$(r_8; 4_{\bar{x}}^-) (\eta; \quad)$	1
2	8	81^0	$(r_8; 8_{\bar{x}}^-) (\eta; \quad)$	1
1	8	81^0	$(r_8; 8_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
$\Gamma_e = 1^0$				
$8=m$	1	1^0	$(r_8; \quad) (\eta; \quad)$	1
8	2	21^0	$(r_8; \quad) (\eta; 2_{\bar{x}}^-)$	1
8	2	21^0	$(r_8; 2_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
$4=m$	2	21^0	$(r_8; 2_{\bar{x}}^-) (\eta; \quad)$	1
4	$2=m$	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
4	4	41^0	$(r_8; 4_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
$2=m$	4	41^0	$(r_8; 4_{\bar{x}}^-) (\eta; \quad)$	1
2	8	81^0	$(r_8; 8_{\bar{x}}^-) (\eta; \quad)$	1
			$(r_8; 3_{\bar{x}}^3) (\eta; \quad)$	1
1	8	81^0	$(r_8; 8_{\bar{x}}^-) (\eta; 2_{\bar{x}}^-)$	1
			$(r_8; 8_{\bar{x}}^3) (\eta; 2_{\bar{x}}^-)$	1
$\Gamma_e = 21^0$				
$8=m$	1	21^0	$(r_8; \quad) (\eta; \quad)$	1

continued on next page

Table 37: continued

G	$G=G$	Γ	generators	line
8	2	$2^0 2^0 2^0$	$(r_8; \) (\bar{h}; 2_{\bar{x}})$	1
8	2	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (\bar{h}; 2_{\bar{x}})$	1
$4=m$	2	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (\bar{h}; h; \)$	1
		41^0	$(r_8; 4_{\bar{x}}) (\bar{h}; \)$	1
4	222	4221^0	$(r_8; 4_{\bar{x}}) (\bar{h}; 2_{\bar{x}})$	2
			$(r_8; 2_{\bar{x}}) (\bar{h}; 2_{\bar{xy}})$	2
$2=m$	4	81^0	$(r_8; 8_{\bar{x}}) (\bar{h}; \)$	1
$\Gamma_e = n$				
8	2	$n2 \ 2$	$(r_8; 2_{\bar{x}}) (\bar{h}; 2_{\bar{x}})$	5
4	$2=m$	$n221^0$	$(r_8; \ ^0) (\bar{h}; 2_{\bar{x}})$	5
		$(2n) \ 2^y 2 \ ^y$	$(r_8; 2n_{\bar{x}}) (\bar{h}; 2_{\bar{x}}^y)$	6
$\Gamma_e = n^0$				
8	2	$n^0 2 \ 2^0$	$(r_8; \) (\bar{h}; 2_{\bar{x}})$	5
4	$2=m$	$n221^0$	$(r_8; \ ^0) (\bar{h}; 2_{\bar{x}})$	5
$\Gamma_e = n1^0$				
8	2	$n221^0$	$(r_8; \) (\bar{h}; 2_{\bar{x}})$	5
4	$2=m$	$(2n)221^0$	$(r_8; 2n_{\bar{x}}) (\bar{h}; 2_{\bar{x}})$	6
$\Gamma_e = 222$				
$8=m$	1	222	$(r_8; \) (\bar{h}; \)$	3a
8	2	$2^0 2^0 2^0$	$(r_8; \) (\bar{h}; \ ^0)$	3a
8	2	$2^0 2^0 2^0$	$(r_8; \ ^0) (\bar{h}; \ ^0)$	3a
$4=m$	2	$2^0 2^0 2^0$	$(r_8; \ ^0) (\bar{h}; \)$	3a
		$4^y 2 \ 2 \ ^y$	$(r_8; 4_{\bar{x}}^y) (\bar{h}; \)$	4
4	$2=m$	4221^0	$(r_8; 4_{\bar{x}}^y) (\bar{h}; \ ^0)$	4
$\Gamma_e = 2^0 2^0 2^0$				
$8=m$	1	$2^0 2^0 2^0$	$(r_8; \) (\bar{h}; \)$	3
8	2	$2^0 2^0 2^0$	$(r_8; \) (\bar{h}; \ ^0)$	3
8	2	$2^0 2^0 2^0$	$(r_8; \ ^0) (\bar{h}; \ ^0)$	3
$4=m$	2	$2^0 2^0 2^0$	$(r_8; \ ^0) (\bar{h}; \)$	3
		$4^y 2 \ 2 \ ^y$	$(r_8; 4_{\bar{x}}^y) (\bar{h}; \)$	4
4	$2=m$	4221^0	$(r_8; 4_{\bar{x}}^y) (\bar{h}; \ ^0)$	4
$\Gamma_e = 2^0 2^0 2^0$				
$4=m$	2	4221^0	$(r_8; 4_{\bar{x}}) (\bar{h}; \)$	4

Table 38: Explicit list of octagonal spin space-group types with $G = 8=m$ on S -lattices. The last column refers to line numbers in Table 17, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
8=m	1	1	$(r_8; \) (h; \)$	1
8	2	2	$(r_8; \) (h; 2_{\bar{x}})$	1
		1^0	$(r_8; \) (h; \ ^0)$	1
8	2	2	$(r_8; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
		1^0	$(r_8; \ ^0) (h; \ ^0)$	1
4=m	2	2	$(r_8; 2_{\bar{x}}) (h; \)$	1
		1^0	$(r_8; \ ^0) (h; \)$	1
4	222	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{x}}) (h; 2_{\bar{x}}^y)$	1
		21^0	$(r_8; 2_{\bar{x}}) (h; \ ^0)$	1

continued on next page

Table 38: continued

G	$G=G$	Γ	generators	line
			$(\nu_8; {}^0) (\eta; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
4	4	4	$(\nu_8; 4_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$2=m$	4	4	$(\nu_8; 4_{\bar{x}}) (\eta;)$	1
2	$4=m$	41^0	$(\nu_8; 4_{\bar{x}}) (\eta; {}^0)$	1
			$(\nu_8; 4_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
2	8	8	$(\nu_8; 8_{\bar{x}}) (\eta;)$	1
			$(\nu_8; 8_{\bar{x}}^3) (\eta;)$	1
1	8	8	$(\nu_8; 8_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
			$(\nu_8; 8_{\bar{x}}^3) (\eta; 2_{\bar{x}})$	1
1	$8=m$	81^0	$(\nu_8; 8_{\bar{x}}) (\eta; {}^0)$	1
			$(\nu_8; 8_{\bar{x}}^3) (\eta; {}^0)$	1
			$(\nu_8; 8_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
			$(\nu_8; 8_{\bar{x}}^3) (\eta; 2_{\bar{x}}^0)$	1
$\Gamma_e = 2$				
$8=m$	1	2	$(\nu_8;) (\eta;)$	1
8	2	$2\ 2\ 2$	$(\nu_8;) (\eta; 2_{\bar{x}})$	1
		21^0	$(\nu_8;) (\eta; {}^0)$	1
8	2	$2\ 2\ 2$	$(\nu_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
		21^0	$(\nu_8; {}^0) (\eta; {}^0)$	1
$4=m$	2	4	$(\nu_8; 4_{\bar{x}}) (\eta;)$	1
		$2\ 2\ 2$	$(\nu_8; 2_{\bar{x}}) (\eta;)$	1
		21^0	$(\nu_8; {}^0) (\eta;)$	1
4	$2=m$	$4\ 2^y 2^y$	$(\nu_8; 4_{\bar{x}}) (\eta; 2_{\bar{x}}^y)$	2
			$(\nu_8; 2_{\bar{x}}^y) (\eta; 2_{\bar{x}}^y)$	2
		41^0	$(\nu_8; 4_{\bar{x}}) (\eta; {}^0)$	1
		$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (\eta; {}^0)$	1
			$(\nu_8; {}^0) (\eta; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
$2=m$	4	8	$(\nu_8; 8_{\bar{x}}) (\eta;)$	1
$\Gamma_e = 2^0$				
$8=m$	1	2^0	$(\nu_8;) (\eta;)$	1
8	2	21^0	$(\nu_8;) (\eta; {}^0)$	1
		$2^0 2^0$	$(\nu_8;) (\eta; 2_{\bar{x}})$	1
8	2	21^0	$(\nu_8; {}^0) (\eta; {}^0)$	1
		$2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$4=m$	2	21^0	$(\nu_8; {}^0) (\eta;)$	1
		$2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (\eta;)$	1
4	$2=m$	$2^0 2^0 2^0$	$(\nu_8; 2_{\bar{x}}) (\eta; {}^0)$	1
			$(\nu_8; {}^0) (\eta; 2_{\bar{x}})$	1
			$(\nu_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
4	4	41^0	$(\nu_8; 4_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$2=m$	4	41^0	$(\nu_8; 4_{\bar{x}}) (\eta;)$	1
2	8	81^0	$(\nu_8; 8_{\bar{x}}) (\eta;)$	1
1	8	81^0	$(\nu_8; 8_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$\Gamma_e = 1^0$				
$8=m$	1	1^0	$(\nu_8;) (\eta;)$	1
8	2	21^0	$(\nu_8;) (\eta; 2_{\bar{x}})$	1
8	2	21^0	$(\nu_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$4=m$	2	21^0	$(\nu_8; 2_{\bar{x}}) (\eta;)$	1

continued on next page

Table 38: continued

G	$G=G$	Γ	generators	line
4	$2=m$	$2^0 2^0 2^0$	$(\varphi_8; 2_{\bar{z}}) (\psi; 2_{\bar{x}})$	1
4	4	41^0	$(\varphi_8; 4_{\bar{z}}) (\psi; 2_{\bar{z}})$	1
$2=m$	4	41^0	$(\varphi_8; 4_{\bar{z}}) (\psi;)$	1
2	8	81^0	$(\varphi_8; 8_{\bar{z}}) (\psi;)$	1
			$(\varphi_8; 3_{\bar{z}}^3) (\psi;)$	1
1	8	81^0	$(\varphi_8; 8_{\bar{z}}) (\psi; 2_{\bar{z}})$	1
			$(\varphi_8; 8_{\bar{z}}^3) (\psi; 2_{\bar{z}})$	1
$\Gamma_e = n$				
8	2	$n2\ 2$	$(\varphi_8; 2_{\bar{x}}) (\psi; 2_{\bar{x}})$	4
8	2	$n2\ 2$	$(\varphi_8; 2_{\bar{x}}) (\psi; 2_{\bar{x}})$	6
4	$2=m$	$n221^0$	$(\varphi_8;)^0 (\psi; 2_{\bar{x}})$	4
			$(\varphi_8; 2_{\bar{x}}) (\psi; 2_{\bar{x}}^0)$	6
		$(Qn)\ 2^y 2^y$	$(\varphi_8; 2n_{\bar{z}}) (\psi; 2_{\bar{x}}^y)$	5
			$(\varphi_8; 2_{\bar{x}}^y) (\psi; (Qn)_{\bar{z}} 2_{\bar{x}}^y)$	7
$\Gamma_e = n^0$				
8	2	$n^0 2\ 2^0$	$(\varphi_8;) (\psi; 2_{\bar{x}})$	4
8	2	$n^0 2\ 2^0$	$(\varphi_8; 2_{\bar{x}}) (\psi; 2_{\bar{x}})$	6
4	$2=m$	$n221^0$	$(\varphi_8;)^0 (\psi; 2_{\bar{x}})$	4
			$(\varphi_8; 2_{\bar{x}}) (Q_{\bar{x}}^0)$	6
$\Gamma_e = 2\ 2\ 2$				
$4=m$	2	$4^y 2\ 2^y$	$(\varphi_8; 4_{\bar{z}}^y) (\psi;)$	3
4	$2=m$	4221^0	$(\varphi_8; 4_{\bar{z}}^y) (\psi;)^0$	3

Table 39: Explicit list of octagonal spin space-group types with $G = 8=mmm$ on V -lattices. The last column refers to line numbers in Table 18, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	$G=G$	Γ	generators	line
$\Gamma_e = 1$				
$8=mmm$	1	1	$(\varphi_8;) (\psi;) (\psi;)$	1
$8mm$	2	2	$(\varphi_8;) (\psi;) (\psi; 2_{\bar{z}})$	1
		1^0	$(\varphi_8;) (\psi;) (\psi;)^0$	1
822	2	2	$(\varphi_8;) (\psi; 2_{\bar{z}}) (\psi; 2_{\bar{z}})$	1
		1^0	$(\varphi_8;) (\psi;)^0 (\psi;)^0$	1
$8=8$	2	2	$(\varphi_8;) (\psi; 2_{\bar{z}}) (\psi;)$	1
		1^0	$(\varphi_8;) (\psi;)^0 (\psi;)$	1
$8m2$	2	2	$(\varphi_8; 2_{\bar{z}}) (\psi;) (\psi; 2_{\bar{x}})$	1
		1^0	$(\varphi_8;)^0 (\psi;) (\psi;)^0$	1
$82m$	2	2	$(\varphi_8; 2_{\bar{z}}) (\psi; 2_{\bar{z}}) (\psi; 2_{\bar{x}})$	1
		1^0	$(\varphi_8;)^0 (\psi;)^0 (\psi;)^0$	1
$4=mmm$	2	2	$(\varphi_8; 2_{\bar{z}}) (\psi;) (\psi;)$	1
		1^0	$(\varphi_8;)^0 (\psi;) (\psi;)$	1
$4=mm^0 m^0$	2	2	$(\varphi_8; 2_{\bar{z}}) (\psi; 2_{\bar{z}}) (\psi;)$	1
		1^0	$(\varphi_8;)^0 (\psi;)^0 (\psi;)$	1
8	222	$2\ 2^y 2^y$	$(\varphi_8;) (\psi; 2_{\bar{z}}) (\psi; 2_{\bar{x}}^y)$	1
		21^0	$(\varphi_8;) (\psi; 2_{\bar{z}}) (\psi;)^0$	1
			$(\varphi_8;) (\psi;)^0 (\psi; 2_{\bar{z}})$	1
			$(\varphi_8;) (\psi; 2_{\bar{z}}) (\psi; 2_{\bar{x}}^0)$	1
8	222	$2\ 2^y 2^y$	$(\varphi_8; 2_{\bar{z}}) (\psi; 2_{\bar{x}}^y) (\psi; 2_{\bar{z}})$	1

continued on next page

Table 39: continued

G	$G=G$	Γ	generators	line
		21^0	$(r_8; 2_{\bar{z}}) (m; {}^0) (h; 2_{\bar{z}})$	1
			$(r_8; {}^0) (m; 2_{\bar{z}}) (h; {}^0)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{z}})$	1
$4mm$	222	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{z}}) (m; \) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{z}}) (m; \) (h; {}^0)$	1
		21^0	$(r_8; {}^0) (m; \) (h; 2_{\bar{z}})$	1
			$(r_8; 2_{\bar{z}}) (m; \) (h; 2_{\bar{z}}^0)$	1
$4m^0m^0$	2	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}) (h; {}^0)$	1
		21^0	$(r_8; {}^0) (m; {}^0) (h; 2_{\bar{z}})$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}) (h; 2_{\bar{z}}^0)$	1
422	222	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{z}}) (m; {}^0) (h; {}^0)$	1
		21^0	$(r_8; {}^0) (m; 2_{\bar{z}}) (h; 2_{\bar{z}})$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{z}}^0)$	1
$42^0 2^0$	222	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{xy}}^y)$	1
			$(r_8; 2_{\bar{z}}) (m; {}^0) (h; 2_{\bar{z}}^0)$	1
		21^0	$(r_8; {}^0) (m; 2_{\bar{z}}) (h; 2_{\bar{z}}^0)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; {}^0)$	1
$4=m$	222	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
			$(r_8; 2_{\bar{z}}) (m; {}^0) (h; \)$	1
		21^0	$(r_8; {}^0) (m; 2_{\bar{z}}) (h; \)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; \)$	1
4	$2^0 2^0 2^0$	$2^0 2^0 2^0$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
			$(r_8; 2_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; {}^0) (m; 2_{\bar{z}}) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}) (h; 2_{\bar{y}})$	1
			$(r_8; 2_{\bar{x}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{y}})$	1
			$(r_8; 2_{\bar{y}}) (m; 2_{\bar{x}}) (h; 2_{\bar{z}}^0)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^0) (h; 2_{\bar{y}}^0)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}}^0)$	1
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{z}}) (h; 2_{\bar{z}}^0)$	1
4	422	$4 \ 2^y 2 \ ^y$	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}})$	1
$2=m$	422	$4 \ 2^y 2 \ ^y$	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
2	4221^0	4221^0	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
			$(r_8; 4_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{xy}}^0)$	1
			$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 4_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 4_{\bar{z}}) (m; 2_{\bar{z}}^y) (h; 2_{\bar{x}}^0)$	1
2	822	$8 \ 2^y 2 \ ^y$	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
			$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
1	922	$8 \ 2^y 2 \ ^y$	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}})$	1
			$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}})$	1
1	$8=mmm$	8221^0	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
			$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
			$(r_8; 8_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 8_{\bar{z}}^3) (m; {}^0) (h; 2_{\bar{x}}^y)$	1

continued on next page

Table 39: continued

G	$G=G$	Γ	generators	line
			$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{y}}^0)$	1
			$(r_8; 8_{\bar{x}}^3) (m; 2_{\bar{x}}^y) (h; 2_{\bar{y}}^0)$	1
			$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 8_{\bar{x}}^3) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 8_{\bar{x}}^3) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
$\Gamma_e = 2$				
$8=mmm$	1	2	$(r_8;) (m;) (h;)$	1
$8mm$	2	2 2 2	$(r_8;) (m;) (h; 2_{\bar{x}}^y)$	1
		21^0	$(r_8;) (m;) (h; 2_{\bar{x}}^0)$	1
822	2	2 2 2	$(r_8;) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	1
		21^0	$(r_8;) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
$8=m$	2	2 2 2	$(r_8;) (m; 2_{\bar{x}}^y) (h;)$	1
		21^0	$(r_8;) (m; 2_{\bar{x}}^0) (h;)$	1
$8m2$	2	2 2 2	$(r_8; 2_{\bar{x}}^y) (m;) (h; 2_{\bar{x}}^y)$	1
		21^0	$(r_8; 2_{\bar{x}}^0) (m;) (h; 2_{\bar{x}}^0)$	1
$82m$	2	2 2 2	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	1
		21^0	$(r_8; 2_{\bar{x}}^0) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
$4=mmm$	2	4	$(r_8; 4_{\bar{x}}) (m;) (h;)$	4
		2 2 2	$(r_8; 2_{\bar{x}}^y) (m;) (h;)$	1
		21^0	$(r_8; 2_{\bar{x}}^0) (m;) (h;)$	1
$4=mm^0m^0$	2	2 2 2	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (h;)$	1
8	222	4 2^y2^y	$(r_8;) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	2
		$2^02^02^0$	$(r_8;) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8;) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8;) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
8	222	$2^02^02^0$	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{x}}^0) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
$4mm$	222	4 2^y2^y	$(r_8; 4_{\bar{x}}) (m;) (h; 2_{\bar{x}}^y)$	5
			$(r_8; 2_{\bar{x}}^y) (m;) (h; 2_{\bar{x}}^y)$	3
		$2^02^02^0$	$(r_8; 2_{\bar{x}}^y) (m;) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 2_{\bar{x}}^0) (m;) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{x}}^y) (m;) (h; 2_{\bar{x}}^0)$	1
		41^0	$(r_8; 4_{\bar{x}}) (m;) (h; 2_{\bar{x}}^0)$	4
$4m^0m^0$	222	4 2^y2^y	$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	6
		$2^02^02^0$	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 2_{\bar{x}}^0) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
422	222	4 2^y2^y	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	3
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	5
		$2^02^02^0$	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 2_{\bar{x}}^0) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	1
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
		41^0	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	4
42^02^0	222	4 2^y2^y	$(r_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	6
		$2^02^02^0$	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 2_{\bar{x}}^0) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^0)$	1

continued on next page

Table 39: continued

G	$G=G$	Γ	generators	line
$4=m$	222	$4 \ 2^y 2^y$	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; \)$	1
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}y}^y)$	4
		$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; \ ^0) (h; \)$	1
			$(r_8; \ ^0) (m; 2_{\bar{x}}) (h; \)$	1
			$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; \)$	1
		41^0	$(r_8; 4_{\bar{x}}) (m; \ ^0) (h; \)$	4
4	$2=mmm$	4221^0	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; \ ^0)$	1
			$(r_8; 4_{\bar{x}}) (m; \ ^0) (h; 2_{\bar{x}}^y)$	5
			$(r_8; \ ^0) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	2
			$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	6
			$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^{0y})$	3
			$(r_8; 2_{\bar{x}y}^y) (m; 2_{\bar{x}}^y) (2_{\bar{x}}^{0y})$	5
			$(r_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}}^0) (h; 2_{\bar{x}y}^y)$	6
			$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}y}^y) (h; \ ^0)$	4
			$(r_8; 2_{\bar{x}}^y) (m; \ ^0) (h; 2_{\bar{x}y}^y)$	3
$2=m$	422	$8 \ 2^y 2^y$	$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; \)$	1
2	$4=mmm$	8221^0	$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; \ ^0)$	1
2	822	$(16) \ 2^y 2^y$	$(r_8; 16_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; \)$	1
			$(r_8; 16_{\bar{x}}^{-3}) (m; 2_{\bar{x}}^y) (h; \)$	1
1	$8=mmm$	$(16)221^0$	$(r_8; 16_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; \ ^0)$	1
			$(r_8; 16_{\bar{x}}^{-3}) (m; 2_{\bar{x}}^y) (h; \ ^0)$	1
$\Gamma_e = 2^0$				
$8=mmm$	1	2^0	$(r_8; \) (m; \) (h; \)$	1
$8mm$	2	$2^0 2^0$	$(r_8; \) (m; \) (h; 2_{\bar{x}})$	1
		21^0	$(r_8; \) (m; \) (h; \ ^0)$	1
822	2	$2^0 2^0$	$(r_8; \) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
		21^0	$(r_8; \) (m; \ ^0) (h; \ ^0)$	1
$8=m$	2	$2^0 2^0$	$(r_8; \) (m; 2_{\bar{x}}) (h; \)$	1
		21^0	$(r_8; \) (m; \ ^0) (h; \)$	1
$8m2$	2	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; \) (h; 2_{\bar{x}})$	1
		21^0	$(r_8; \ ^0) (m; \) (h; \ ^0)$	1
$82m$	2	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
		21^0	$(r_8; \ ^0) (m; \ ^0) (h; \ ^0)$	1
$4=mmm$	2	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; \) (h; \)$	1
		21^0	$(r_8; \ ^0) (m; \) (h; \)$	1
$4=mm^0 m^0$	2	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; \)$	1
		21^0	$(r_8; \ ^0) (m; \ ^0) (h; \)$	1
8	222	$2^0 2^0 2^0$	$(r_8; \) (m; 2_{\bar{x}}) (h; \ ^0)$	1
			$(r_8; \) (m; \ ^0) (h; 2_{\bar{x}})$	1
			$(r_8; \) (m; 2_{\bar{x}}) (h; 2_{\bar{x}}^0)$	1
$\bar{8}$	222	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; \ ^0) (h; 2_{\bar{x}})$	1
			$(r_8; \ ^0) (m; 2_{\bar{x}}) (h; \ ^0)$	1
			$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}})$	1
$4mm$	222	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; \) (h; \ ^0)$	1
			$(r_8; \ ^0) (m; \) (h; 2_{\bar{x}})$	1
			$(r_8; 2_{\bar{x}}) (m; \) (h; 2_{\bar{x}}^0)$	1
$4m^0 m^0$	222	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; \ ^0)$	1
			$(r_8; \ ^0) (m; \ ^0) (h; 2_{\bar{x}})$	1
			$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}}^0)$	1

continued on next page

Table 39: continued

G	$G=G$	Γ	generators	line
422	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; {}^0) (\eta; {}^0)$	1
			$(\varphi_8; {}^0) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
			$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}^0) (\eta; 2_{\bar{x}}^0)$	1
$42^0 2^0$	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; {}^0) (\eta; 2_{\bar{x}}^0)$	1
			$(\varphi_8; {}^0) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
			$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}^0) (\eta; {}^0)$	1
$4=m$	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; {}^0) (\eta;)$	1
			$(\varphi_8; {}^0) (\eta m; 2_{\bar{x}}) (\eta;)$	1
			$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}^0) (\eta;)$	1
4	422	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m; 2_{\bar{x}}^y) (\eta; 2_{\bar{x}})$	1
$2=m$	422	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m; 2_{\bar{x}}^y) (\eta;)$	1
$\bar{2}$	822	8221^0	$(\varphi_8; 8_{\bar{x}}) (\eta m; 2_{\bar{x}}^y) (\eta;)$	1
1	822	8221^0	$(\varphi_8; 8_{\bar{x}}) (\eta m; 2_{\bar{x}}^y) (\eta; 2_{\bar{x}})$	1
$\Gamma_e = 1^0$				
$8=mmm$	1	1^0	$(\varphi_8;) (\eta m;) (\eta;)$	1
$8mm$	2	21^0	$(\varphi_8;) (\eta m;) (\eta; \bar{2})$	1
822	2	21^0	$(\varphi_8;) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$8=m$	2	21^0	$(\varphi_8;) (\eta m; 2_{\bar{x}}) (\eta;)$	1
$8m2$	2	21^0	$(\varphi_8; 2_{\bar{x}}) (\eta m;) (\eta; 2_{\bar{x}})$	1
$82m$	2	21^0	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$4=mmm$	2	21^0	$(\varphi_8; 2_{\bar{x}}) (\eta m;) (\eta;)$	1
$4=mm^0 m^0$	2	21^0	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta;)$	1
8	222	$2^0 2^0 0$	$(\varphi_8;) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
8	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$4mm$	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m;) (\eta; 2_{\bar{x}})$	1
$4m^0 m^0$	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
422	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$42^0 2^0$	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{y}})$	1
$4=m$	222	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta;)$	1
4	422	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$2=m$	422	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta;)$	1
$\bar{2}$	822	8221^0	$(\varphi_8; 8_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta;)$	1
			$(\varphi_8; 8_{\bar{x}}^3) (\eta m; 2_{\bar{x}}) (\eta;)$	1
1	822	8221^0	$(\varphi_8; 8_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
			$(\varphi_8; 8_{\bar{x}}^3) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$\Gamma_e = 21^0$				
$8=mmm$	1	21^0	$(\varphi_8;) (\eta m;) (\eta;)$	1
$8mm$	2	$2^0 2^0 0$	$(\varphi_8;) (\eta m;) (\eta; \bar{2})$	1
822	2	$2^0 2^0 0$	$(\varphi_8;) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$8=m$	2	$2^0 2^0 0$	$(\varphi_8;) (\eta m;) (\eta; \bar{2})$	1
$8m2$	2	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m;) (\eta; 2_{\bar{x}})$	1
$82m$	2	$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
$4=mmm$	2	41^0	$(\varphi_8; 4_{\bar{x}}) (\eta m;) (\eta;)$	4
		$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m;) (\eta;)$	1
		$2^0 2^0 0$	$(\varphi_8; 2_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta;)$	1
8	222	4221^0	$(\varphi_8;) (\eta m; 4_{\bar{x}}) (\eta; 2_{\bar{x}})$	2
$4mm$	222	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m;) (\eta; 2_{\bar{x}})$	5
			$(\varphi_8; 2_{\bar{x}}) (\eta m;) (\eta; 2_{\bar{xy}})$	3
$4m^0 m^0$	222	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m; 4_{\bar{x}}) (\eta; 2_{\bar{x}})$	6
422	222	4221^0	$(\varphi_8; 4_{\bar{x}}) (\eta m; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	3

continued on next page

Table 39: continued

G	$G=G$	Γ	generators	line
			$(r_8; 2_{\bar{x}}) (m; 2_{\bar{xy}}) (h; 2_{\bar{xy}})$	5
$42^0 2^0$	222	4221^0	$(r_8; 2_{\bar{x}}) (m; 4_{\bar{z}}) (h; 2_{\bar{xy}})$	6
$4=m$	222	4221^0	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}) (h;)$	1
			$(r_8; 2_{\bar{x}}) (m; 2_{\bar{xy}}) (h;)$	4
$2=m$	422	8221^0	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}) h;)$	1
2	822	$(16)221^0$	$(r_8; 16_{\bar{z}}) (m; 2_{\bar{x}}) (h;)$	1
			$(r_8; 16_{\bar{z}}^3) (m; 2_{\bar{x}}) (h;)$	1
$\Gamma_e = n$				
$8mm$	2	$n2\ 2$	$(r_8;) (m;) (h; 2_{\bar{x}})$	9
8	222	$n221^0$	$(r_8;) (m; {}^0) (h; 2_{\bar{x}})$	9
		$(2n)\ 2^y 2\ ^y$	$(r_8;) (m; 2n_{\bar{z}}) (h; 2_{\bar{x}}^y)$	10
$4mm$	222	$n221^0$	$(r_8; {}^0) (m;) (h; 2_{\bar{x}})$	9
		$(2n)\ 2^y 2\ ^y$	$(r_8; 2n_{\bar{z}}) (m;) (h; 2_{\bar{x}}^y)$	11
$4m^0 m^0$	222	$n221^0$	$(r_8; {}^0) (m; {}^0) (h; 2_{\bar{x}})$	9
		$(2n)\ 2^y 2\ ^y$	$(r_8; 2n_{\bar{z}}) (m; 2n_{\bar{z}}) (h; 2_{\bar{x}}^y)$	12
4	$2^0 2^0 2^0$	$(2n)221^0$	$(r_8; 2n_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	11
			$(r_8; {}^0) (m; 2n_{\bar{z}}) (h; 2_{\bar{x}}^y)$	10
			$(r_8; 2n_{\bar{z}}) (m; 2n_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	12
$\Gamma_e = n^0$				
$8mm$	2	$n^0 2\ 2^0$	$(r_8;) (m;) (h; 2_{\bar{x}})$	9
8	222	$n221^0$	$(r_8;) (m; {}^0) (h; 2_{\bar{x}})$	9
$4mm$	222	$n221^0$	$(r_8; {}^0) (m;) (h; 2_{\bar{x}})$	9
$4m^0 m^0$	222	$n221^0$	$(r_8; {}^0) (m; {}^0) (h; 2_{\bar{x}})$	9
$\Gamma_e = n1^0$				
8	222	$(2n)221^0$	$(r_8;) (h; (2n)_{\bar{z}}) (h; 2_{\bar{x}})$	10
$4mm$	222	$(2n)221^0$	$(r_8; (2n)_{\bar{z}}) (m;) (h; 2_{\bar{x}})$	11
$4m^0 m^0$	222	$(2n)221^0$	$(r_8; (2n)_{\bar{z}}) (m; (2n)_{\bar{z}}) (h; 2_{\bar{x}})$	12
$\Gamma_e = 222$				
$8=mmm$	1	222	$(r_8;) (m;) (h;)$	7a
$8mm$	2	$2^0 2^0 2^0$	$(r_8;) (m;) (h; {}^0)$	7a
822	2	$2^0 2^0 2^0$	$(r_8;) (m; {}^0) (h; {}^0)$	7a
$8=m$	2	$2^0 2^0 2^0$	$(r_8;) (m; {}^0) (h;)$	7a
$8m2$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m;) (h; {}^0)$	7a
$82m$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	7a
$4=mmm$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m;) (h;)$	7a
		$4^y 2\ 2\ ^y$	$(r_8; 4_{\bar{z}}^y) (m;) (h;)$	8
$4=mm^0 m^0$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m; {}^0) (h;)$	7a
$4mm$	222	4221^0	$(r_8; 4_{\bar{z}}^y) (m;) (h; {}^0)$	8
422	222	4221^0	$(r_8; 4_{\bar{z}}^y) (m; {}^0) (h; {}^0)$	8
$4=m$	222	4221^0	$(r_8; 4_{\bar{z}}^y) (m; {}^0) (h;)$	8
$\Gamma_e = 2^0 2^0 2$				
$8=mmm$	1	$2^0 2^0 2$	$(r_8;) (m;) (h;)$	7
$8mm$	2	$2^0 2^0 2^0$	$(r_8;) (m;) (h; {}^0)$	7
822	2	$2^0 2^0 2^0$	$(r_8;) (m; {}^0) (h; {}^0)$	7
$8=m$	2	$2^0 2^0 2^0$	$(r_8;) (m; {}^0) (h;)$	7
$8m2$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m;) (h; {}^0)$	7
$82m$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	7
$4=mmm$	2	$2^0 2^0 2^0$	$(r_8; {}^0) (m;) (h;)$	7
		$4^y 2\ 2\ ^y$	$(r_8; 4_{\bar{z}}^y) (m;) (h;)$	8

continued on next page

Table 39: continued

G	$G=G$	Γ	generators	line
$4=mm^0m^0$	2	$2^02^02^0$	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	7
$4mm$	222	4221^0	$(r_8; 4_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	8
422	222	4221^0	$(r_8; 4_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	8
$4=m$	222	4221^0	$(r_8; 4_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	8
$\Gamma_e = 2^02^02^0$				
$4=mmm$	2	4221^0	$(r_8; 4_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	8

Table 40: Explicit list of octagonal spin space-group types with $G = 8=mmm$ on S -lattices. The last column refers to line numbers in Table 19, where the possible phase functions are listed, and rules are given to generate the spin space-group symbol.

G	Γ	generators	line
$\Gamma_e = 1$			
$8=mmm$	1	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$8mm$	2	$(r_8; {}^0) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
822	2	$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$8=m$	2	$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; {}^0)$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$8m2$	2	$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$82m$	2	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$4=mmm$	2	$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$4=mm^0m^0$	2	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; {}^0)$	1
	1^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
8	$2 \ 2^y 2 \ ^y$	$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
	21^0	$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; {}^0)$	1
		$(r_8; {}^0) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
		$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
8	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
	21^0	$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
		$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; {}^0)$	1
		$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
$4mm$	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
	21^0	$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	1
		$(r_8; {}^0) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
		$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
$4m^0m^0$	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
	21^0	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; {}^0)$	1
		$(r_8; {}^0) (m; {}^0) (h; 2_{\frac{y}{x}})$	1
		$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
422	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
	21^0	$(r_8; 2_{\frac{y}{x}}) (m; {}^0) (h; {}^0)$	1
		$(r_8; {}^0) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
		$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1
42^02^0	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\frac{y}{x}}) (m; 2_{\frac{y}{x}}) (h; 2_{\frac{y}{x}})$	1

continued on next page

Table 40: continued

G	Γ	generators	line
	21^0	$(r_8; 2_{\bar{z}}) (m; {}^0) (h; 2_{\bar{z}}^0)$	1
		$(r_8; {}^0) (m; 2_{\bar{z}}) (h; 2_{\bar{z}}^0)$	1
		$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; {}^0)$	1
$4=m$	$2 \ 2^y 2 \ ^y$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
	21^0	$(r_8; 2_{\bar{z}}) (m; {}^0) (h; \)$	1
		$(r_8; {}^0) (m; 2_{\bar{z}}) (h; \)$	1
		$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; \)$	1
4	$2^0 2^0 2^0$	$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
		$(r_8; 2_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; {}^0) (m; 2_{\bar{z}}) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 2_{\bar{z}}^0) (m; 2_{\bar{x}}) (h; 2_{\bar{y}})$	1
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{y}})$	1
		$(r_8; 2_{\bar{y}}) (m; 2_{\bar{x}}) (h; 2_{\bar{z}}^0)$	1
		$(r_8; 2_{\bar{z}}^0) (m; 2_{\bar{x}}^0) (h; 2_{\bar{y}}^0)$	1
		$(r_8; 2_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 2_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}}^0)$	1
		$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{z}}) (h; 2_{\bar{z}}^0)$	1
4	$4 \ 2^y 2 \ ^y$	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}})$	1
$2=m$	$4 \ 2^y 2 \ ^y$	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
2	4221^0	$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
		$(r_8; 4_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{y}}^0)$	1
		$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
		$(r_8; 4_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 4_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}}^0)$	1
2	$8 \ 2^y 2 \ ^y$	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
		$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; \)$	1
1	$8 \ 2^y 2 \ ^y$	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}})$	1
		$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}})$	1
1	8221^0	$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
		$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
		$(r_8; 8_{\bar{z}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 8_{\bar{z}}^3) (m; {}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{y}}^0)$	1
		$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}}^y) (h; 2_{\bar{y}}^0)$	1
		$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
		$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^0)$	1
		$(r_8; 8_{\bar{z}}) (m; 2_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 8_{\bar{z}}^3) (m; 2_{\bar{z}}^0) (h; 2_{\bar{x}}^y)$	1
		$(r_8; 8_{\bar{z}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{z}}^0)$	1
$\Gamma_e = 2$			
$8=mmm$	2	$(r_8; \) (m; \) (h; \)$	1
$8mm$	$2 \ 2 \ 2$	$(r_8; \) (m; \) (h; 2_{\bar{x}})$	1
	21^0	$(r_8; \) (m; \) (h; {}^0)$	1
822	$2 \ 2 \ 2$	$(r_8; \) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
	21^0	$(r_8; \) (m; {}^0) (h; {}^0)$	1
$8=m$	$2 \ 2 \ 2$	$(r_8; \) (m; 2_{\bar{x}}) (h; \)$	1
	21^0	$(r_8; \) (m; {}^0) (h; \)$	1

continued on next page

Table 40: continued

G	Γ	generators	line
$8m2$	$2\ 2\ 2$	$(r_8; 2_{\bar{x}}) (m;) (h; 2_{\bar{x}})$	1
	21^0	$(r_8; {}^0) (m;) (h; {}^0)$	1
$82m$	$2\ 2\ 2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
	21^0	$(r_8; {}^0) (m; {}^0) (h; {}^0)$	1
$4=mmm$	$2\ 2\ 2$	$(r_8; 2_{\bar{x}}) (m;) (h;)$	1
	21^0	$(r_8; {}^0) (m;) (h;)$	1
$4=mm^0m^0$	4	$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}) (h;)$	5
	$2\ 2\ 2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h;)$	1
8	$4\ 2^y 2\ ^y$	$(r_8;) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	2
	$2^0 2^0 2^0$	$(r_8;) (m; 2_{\bar{x}}) (h; {}^0)$	1
		$(r_8;) (m; {}^0) (h; 2_{\bar{x}})$	1
		$(r_8;) (m; 2_{\bar{x}}) (h; 2_{\bar{x}}^0)$	1
8	$4\ 2^y 2\ ^y$	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	4
	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; {}^0) (h; 2_{\bar{x}})$	1
		$(r_8; {}^0) (m; 2_{\bar{x}}) (h; {}^0)$	1
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}})$	1
$4mm$	$4\ 2^y 2\ ^y$	$(r_8; 4_{\bar{x}}) (m;) (h; 2_{\bar{x}}^y)$	6
	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m;) (h; {}^0)$	1
		$(r_8; {}^0) (m;) (h; 2_{\bar{x}})$	1
		$(r_8; 2_{\bar{x}}) (m;) (h; 2_{\bar{x}}^0)$	1
$4m^0m^0$	$4\ 2^y 2\ ^y$	$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	7
	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; {}^0)$	1
		$(r_8; {}^0) (m; {}^0) (h; 2_{\bar{x}})$	1
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}}^0)$	1
	41^0	$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}) (h; {}^0)$	5
422	$4\ 2^y 2\ ^y$	$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	4
	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; {}^0) (h; {}^0)$	1
		$(r_8; {}^0) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}})$	1
$42^0 2^0$	$4\ 2^y 2\ ^y$	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; 2_{\bar{x}}^y)$	3
		$(r_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	7
	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; {}^0) (h; 2_{\bar{x}}^0)$	1
		$(r_8; {}^0) (m; 2_{\bar{x}}) (h; 2_{\bar{x}}^0)$	1
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0) (h; {}^0)$	1
	41^0	$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}^0) (h; {}^0)$	5
$4=m$	$4\ 2^y 2\ ^y$	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h;)$	1
		$(r_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}}) (h;)$	5
	$2^0 2^0 2^0$	$(r_8; 2_{\bar{x}}) (m; {}^0) (h;)$	1
		$(r_8; {}^0) (m; 2_{\bar{x}}) (h;)$	1
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}^0) (h;)$	1
	41^0	$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}^0) (h;)$	5
4	4221^0	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}^y) (h; {}^0)$	1
		$(r_8; 4_{\bar{x}}) (m; {}^0) (h; 2_{\bar{x}}^y)$	6
		$(r_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}}) (h; {}^0)$	5
		$(r_8; {}^0) (m; 4_{\bar{x}}) (h; 2_{\bar{x}}^y)$	2
		$(r_8; 4_{\bar{x}}) (m; 4_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	7
		$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	3
		$(r_8; 2_{\bar{x}}^y) (m; 2_{\bar{x}}^y) (2_{\bar{x}}^0)$	6
		$(r_8; 2_{\bar{x}}^y) (m; 4_{\bar{x}}^0) (h; 2_{\bar{x}}^y)$	7

continued on next page

Table 40: continued

G	Γ	generators	line
		$(r_8; 4_{\bar{z}}^0) (\eta; 2_{\bar{x}}^y) (\eta; 2_{\bar{xy}}^y)$	3
$2=m$	$8 \ 2^y 2^y$	$(r_8; 8_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; \)$	1
2	8221^0	$(r_8; 8_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; \ ^0)$	1
2	$(16) \ 2^y 2^y$	$(r_8; 16_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; \)$	1
		$(r_8; 16_{\bar{z}}^3) (\eta; 2_{\bar{x}}^y) (\eta; \)$	1
1	$(16) 221^0$	$(r_8; 16_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; \ ^0)$	1
		$(r_8; 16_{\bar{z}}^3) (\eta; 2_{\bar{x}}^y) (\eta; \ ^0)$	1
$\Gamma_e = 2^0$			
$8=mmm$	2^0	$(r_8; \) (\eta; \) (\eta; \)$	1
$8mm$	$2^0 2^0$	$(r_8; \) (\eta; \) (\eta; 2_{\bar{x}})$	1
	21^0	$(r_8; \) (\eta; \) (\eta; \ ^0)$	1
822	$2^0 2^0$	$(r_8; \) (\eta; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
	21^0	$(r_8; \) (\eta; \ ^0) (\eta; \ ^0)$	1
$8=m$	$2^0 2^0$	$(r_8; \) (\eta; 2_{\bar{x}}) (\eta; \)$	1
	21^0	$(r_8; \) (\eta; \ ^0) (\eta; \)$	1
$8m2$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \) (\eta; 2_{\bar{x}})$	1
	21^0	$(r_8; \ ^0) (\eta; \) (\eta; \ ^0)$	1
$82m$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
	21^0	$(r_8; \ ^0) (\eta; \ ^0) (\eta; \ ^0)$	1
$4=mmm$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \) (\eta; \)$	1
	21^0	$(r_8; \ ^0) (\eta; \) (\eta; \)$	1
$4=mm^0 m^0$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}) (\eta; \)$	1
	21^0	$(r_8; \ ^0) (\eta; \ ^0) (\eta; \)$	1
8	$2222^0 2^0$	$(r_8; \) (\eta; 2_{\bar{x}}) (\eta; \ ^0)$	1
		$(r_8; \) (\eta; \ ^0) (\eta; 2_{\bar{x}})$	1
		$(r_8; \) (\eta; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
8	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \ ^0) (\eta; 2_{\bar{x}})$	1
		$(r_8; \ ^0) (\eta; 2_{\bar{x}}) (\eta; \ ^0)$	1
		$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0) (\eta; 2_{\bar{x}})$	1
$4mm$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \) (\eta; \ ^0)$	1
		$(r_8; \ ^0) (\eta; \) (\eta; 2_{\bar{x}})$	1
		$(r_8; 2_{\bar{x}}) (\eta; \) (\eta; 2_{\bar{x}}^0)$	1
$4m^0 m^0$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}) (\eta; \ ^0)$	1
		$(r_8; \ ^0) (\eta; \ ^0) (\eta; 2_{\bar{x}})$	1
		$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
422	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \ ^0) (\eta; \ ^0)$	1
		$(r_8; \ ^0) (\eta; 2_{\bar{x}}) (\eta; 2_{\bar{x}})$	1
		$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0) (\eta; 2_{\bar{x}}^0)$	1
$42^0 2^0$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \ ^0) (\eta; 2_{\bar{x}}^0)$	1
		$(r_8; \ ^0) (\eta; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0)$	1
		$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0) (\eta; \ ^0)$	1
$4=m$	$2^0 2^0$	$(r_8; 2_{\bar{x}}) (\eta; \ ^0) (\eta; \)$	1
		$(r_8; \ ^0) (\eta; 2_{\bar{x}}) (\eta; \)$	1
		$(r_8; 2_{\bar{x}}) (\eta; 2_{\bar{x}}^0) (\eta; \)$	1
4	4221^0	$(r_8; 4_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; 2_{\bar{z}})$	1
$2=m$	4221^0	$(r_8; 4_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; \)$	1
2	8221^0	$(r_8; 8_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; \)$	1
1	8221^0	$(r_8; 8_{\bar{z}}) (\eta; 2_{\bar{x}}^y) (\eta; 2_{\bar{z}})$	1
$\Gamma_e = 1^0$			
$8=mmm$	1^0	$(r_8; \) (\eta; \) (\eta; \)$	1

continued on next page

Table 40: continued

G	Γ	generators	line
$8mm$	21^0	$(r_8;) (m;) (h; \frac{2}{x})$	1
822	21^0	$(r_8;) (m; \frac{2}{x}) (h; 2_{\bar{x}})$	1
$8=m$	21^0	$(r_8;) (m; \frac{2}{x}) (h;)$	1
$8m2$	21^0	$(r_8; 2_{\bar{x}}) (m;) (h; \frac{2}{x})$	1
$82m$	21^0	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
$4=mmm$	21^0	$(r_8; 2_{\bar{x}}) (m;) (h;)$	1
$4=mm^0m^0$	21^0	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h;)$	1
8	$2^0_2 2^0_2$	$(r_8;) (m; \frac{2}{x}) (h; 2_{\bar{x}})$	1
8	$2^0_2 2^0_2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
$4mm$	$2^0_2 2^0_2$	$(r_8; 2_{\bar{x}}) (m;) (h; \frac{2}{x})$	1
$4m^0m^0$	$2^0_2 2^0_2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
422	$2^0_2 2^0_2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
$42^0_2 2^0_2$	$2^0_2 2^0_2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
$4=m$	$2^0_2 2^0_2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h;)$	1
4	4221^0	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
$2=m$	4221^0	$(r_8; 4_{\bar{x}}) (m; 2_{\bar{x}}) (h;)$	1
2	8221^0	$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}) (h;)$	1
		$(r_8; 8_{\bar{x}}^{\frac{2}{x}}) (m; 2_{\bar{x}}) (h;)$	1
1	8221^0	$(r_8; 8_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
		$(r_8; 8_{\bar{x}}^{\frac{2}{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	1
$\Gamma_e = n$			
$8mm$	$n2\ 2$	$(r_8;) (m;) (h; \frac{2}{x})$	9
$82m$	$n2\ 2$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	13
8	$n221^0$	$(r_8;) (m; ^0) (h; 2_{\bar{x}})$	9
	$(Qn)\ 2^y_2\ 2^y$	$(r_8;) (m; 2n_{\bar{x}}) (h; 2^y_{\bar{x}})$	10
8	$n221^0$	$(r_8; 2_{\bar{x}}) (m; 2^0_{\bar{x}}) (h; 2_{\bar{x}})$	13
$4mm$	$n221^0$	$(r_8; ^0) (m;) (h; \frac{2}{x})$	9
	$(Qn)\ 2^y_2\ 2^y$	$(r_8; 2n_{\bar{x}}) (m;) (h; \frac{2^y}{x})$	11
$4m^0m^0$	$n221^0$	$(r_8; ^0) (m; ^0) (h; 2_{\bar{x}})$	9
		$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2^0_{\bar{x}})$	13
	$(Qn)\ 2^y_2\ 2^y$	$(r_8; 2n_{\bar{x}}) (m; 2n_{\bar{x}}) (h; 2^y_{\bar{x}})$	12
422	$n221^0$	$(r_8; 2_{\bar{x}}) (m; 2^0_{\bar{x}}) (h; 2^0_{\bar{x}})$	13
	$(Qn)\ 2^y_2\ 2^y$	$(r_8; 2^y_{\bar{x}}) (m; (Qn_{\bar{x}}) 2_{\bar{x}}^y) (h; (Qn_{\bar{x}}) 2_{\bar{x}}^y)$	15
4	$(Qn) 221^0$	$(r_8; 2n_{\bar{x}}) (m; ^0) (h; 2^y_{\bar{x}})$	11
		$(r_8; ^0) (m; 2n_{\bar{x}}) (h; 2^y_{\bar{x}})$	10
		$(r_8; 2n_{\bar{x}}) (m; 2n^0_{\bar{x}}) (h; 2^y_{\bar{x}})$	12
		$(r_8; (Qn_{\bar{x}}) 2^y_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2^0_{\bar{x}})$	14
$\Gamma_e = n^0$			
$8mm$	$n^0_2\ 2^0$	$(r_8;) (m;) (h; \frac{2}{x})$	9
$82m$	$n^0_2\ 2^0$	$(r_8; 2_{\bar{x}}) (m; 2_{\bar{x}}) (h; 2_{\bar{x}})$	13
8	$n221^0$	$(r_8;) (m; ^0) (h; 2_{\bar{x}})$	9
8	$n221^0$	$(r_8; 2_{\bar{x}}) (m; 2^0_{\bar{x}}) (h; 2_{\bar{x}})$	13
$4mm$	$n221^0$	$(r_8; ^0) (m;) (h; \frac{2}{x})$	9
$4m^0m^0$	$n221^0$	$(r_8; ^0) (m; ^0) (h; 2_{\bar{x}})$	9
422	$n221^0$	$(r_8; 2_{\bar{x}}) (m; 2^0_{\bar{x}}) (h; 2^0_{\bar{x}})$	13
$\Gamma_e = 2\ 2\ 2$			
	$4^y_2\ 2\ 2^y$	$(r_8; 4^y_{\bar{x}}) (m; 4^y_{\bar{x}}) (h;)$	8
$4m^0m^0$	4221^0	$(r_8; 4^y_{\bar{x}}) (m; 4^y_{\bar{x}}) (h; ^0)$	8
$42^0_2 2^0$	4221^0	$(r_8; 4^y_{\bar{x}}) (m; 4^0_{\bar{x}}) (h; ^0)$	8

continued on next page

|

Table 40: continued

G	Γ	generators	$line$
$4\Rightarrow m$	4221^0	$(r_8; 4_{\frac{y}{z}}^y) (n; 4_{\frac{y}{z}}^{0y}) (h; \quad)$	8