arXiv:cond-mat/0310350v1 [cond-mat.str-el] 15 Oct 2003

Orbital ordering in undoped manganites using Jahn-Teller interaction

Sudhakar Yarlagadda and Manidipa Mitra[1]

Saha Institute of Nuclear Physics, Salt Lake City, Kolkata, India

[1]S. N. Bose National Centre for Basic Sciences, Salt Lake City, Kolkata, India

Email : sudhakar@cmp.saha.ernet.in

Abstract : To understand the orbital ordering of $LaMnO_3$ in the ground state, we study it in the A-type spin antiferromagnetic state. We calculate the two-dimensional response functions associated with the Jahn-Teller Q_2 and Q_3 distortions and find that they diverge at the wavevector (π,π). Furthermore, the Q_2 response function diverges faster which indicates that perhaps the ordering of the orbitals at low temperatures is dominated by the Q_2 distortion. We calculate the ground state energy for the cases when only one of the Q_2 and Q_3 modes is excited cooperatively and find that the Q_2 excited state yields lower energy.

Keywords : Orbital density wave, Jahn-Teller interaction.

PACS No. : 71.45.Lr, 71.38.-k, 75.10.-b

1. Introduction

Undoped manganites like $LaMnO_3$ are the parent systems for the colossal magnetoresistive materials. It is well known that orbital ordering occurs around 780 K resulting in a C-type orbital structure with two kinds of orbitals alternating on adjacent sites in the xy plane while like orbitals are stacked in the z direction [1]. As the temperature is further lowered to 140 K an A-type spin antiferromagnetic order sets in wherein the spins are ferromagnetically aligned in the xy plane with the spin coupling in the z direction being antiferromagnetic [2]. To explain the observed order several studies have been reported. These studies fall into two classes, with one class based on Jahn-Teller (JT) interaction [3–6] being the main cause while the other class corresponds to Coulombic interaction [7–10] being the dominant cause for the observed order. However, it must be pointed out that the electron-phonon based studies do not point to a transparent mechanism.

The purpose of the present paper is to use the framework developed earlier by one of us (Ref. [11]) and analyze the orbital ordering by using a generalized Peierls instability approach. However, as compared to the one-dimensional Peierls charge density wave (CDW) approach, our higher dimensional orbital density wave (ODW) analysis is more complicated on account of there being two e_g orbitals (with inter-orbital hopping) and two response functions corresponding to the JT Q_2 and Q_3 distortions. We begin by assuming that the A-type antiferromagnetic ordering has already set in. Thus, on account of strong Hund's coupling, the transport is restricted to spin polarized electrons in two dimensions only. We assume that the Mn sites are fixed and that only the oxygen atoms between the Mn sites can move along the axis joining the neighboring Mn sites. We find that the non-interacting response functions $\chi_{2,3}$ corresponding to the $Q_{2,3}$ modes diverge at wavevector $\vec{Q} = (\pi, \pi)$. Thus one can expect local minima in energy for states corresponding to ODW being excited at wavevector $\vec{Q}$ by the cooperative Q_2 and Q_3 modes. We find that $\chi_2(\pi, \pi)$ diverges faster than $\chi_3(\pi, \pi)$ and as expected the energy for the Q_2 related ODW state has lower energy than the Q_3 related ODW state.

2. Mean-field approach to ODW

We will now consider manganite systems with two e_g orbitals per site and ignore spin. The Hamiltonian consists of the kinetic term, the ionic term, and the electron-ion interaction term. The kinetic term in momentum space is given by

$$H_1 = \sum_{\vec{p}} \mathbf{B}^\dagger_{\vec{p}} \cdot \mathbf{T} \cdot \mathbf{B}_{\vec{p}}, \tag{1}$$

where $\mathbf{B}^\dagger_{\vec{p}} \equiv (b^\dagger_{1\vec{p}}, b^\dagger_{2\vec{p}})$ with b_1 and b_2 corresponding to the destruction operators for electrons with the orthonormal wavefunctions $\psi_{x^2-y^2}$ and $\psi_{3z^2-r^2}$ respectively. Furthermore, $\mathbf{T}$ is a hermitian matrix with $\mathbf{T}_{1,1} = -1.5t[\cos p_x + \cos p_y]$, $\mathbf{T}_{2,2} = -0.5t[\cos p_x + \cos p_y]$, and $\mathbf{T}_{1,2} = 0.5\sqrt{3}t[\cos p_x - \cos p_y]$. The eigen values of the

kinetic energy are given by $\lambda_n^{\vec{p}} = -\cos p_x - \cos p_y - (-1)^n\sqrt{\cos^2 p_x + \cos^2 p_y - \cos p_x \cos p_y}$ with $n = 1, 2$. The Fermi sea corresponding to the lower eigen energy value $\lambda_2^{\vec{p}}$ is given by the union of the region $-\pi/2 \leq k_x \leq \pi/2$ (with all values of k_y allowed) and the region $-\pi/2 \leq k_y \leq \pi/2$ (with all values of k_x allowed). Whereas the Fermi sea corresponding to the higher eigen energy value $\lambda_1^{\vec{p}}$ is given by the intersection of the region $-\pi/2 \leq k_x \leq \pi/2$ and the region $-\pi/2 \leq k_y \leq \pi/2$. Since the number of electrons is equal to the number of sites, the total area occupied by both Fermi seas is equal to the area of the Brillouin zone ($4\pi^2$). Furthermore, the Fermi surface corresponds to $\lambda_n^{\vec{p}} = 0$.

Using mean-field approximation we get, after averaging the Hamiltonian over phonon coordinates, the following effective Hamiltonian (see Ref. [11] for details):

$$\bar{H} = H_1 - 2\frac{A^2}{\omega_0}\sum_j \Big[(b_{1j}^\dagger b_{2j} + b_{2j}^\dagger b_{1j})\langle b_{1j}^\dagger b_{2j} + b_{2j}^\dagger b_{1j}\rangle + (b_{1j}^\dagger b_{1j} - b_{2j}^\dagger b_{2j})\langle b_{1j}^\dagger b_{1j} - b_{2j}^\dagger b_{2j}\rangle\Big] + \frac{A^2}{\omega_0}\sum_j \Big[\langle b_{1j}^\dagger b_{2j} + b_{2j}^\dagger b_{1j}\rangle^2 + \langle b_{1j}^\dagger b_{1j} - b_{2j}^\dagger b_{2j}\rangle^2\Big], \quad (2)$$

where $< .. >$ implies averaging over the phonon coordinates, $A\sqrt{2M\omega_0}$ is the electron-JT coupling constant, $2A\langle b_{1j}^\dagger b_{2j} + b_{2j}^\dagger b_{1j}\rangle = -\omega_0\sqrt{2M\omega_0}\langle Q_{2j}\rangle$, and $2A\langle b_{1j}^\dagger b_{1j} - b_{2j}^\dagger b_{2j}\rangle = -\omega_0\sqrt{2M\omega_0}\langle Q_{3j}\rangle$.

We will now determine the wavevector for long range cooperative ordering of the $Q_{2,3}$ modes. For this we must figure out the values of q that make the susceptibilities $\chi_{2,3}(q,q)$ diverge. The expressions for $\chi_{2,3}(\vec{q})$ are given as

$$\chi_l(\vec{q}) = -2\sum_{\vec{k},n}\frac{\langle c_{\vec{k}}^{n\dagger} c_{\vec{k}}^n\rangle}{\lambda_n^{\vec{k}+\vec{q}} - \lambda_n^{\vec{k}}}\sin^2\left[\frac{\theta_{\vec{k}+\vec{q}} + \theta_{\vec{k}} + l\pi}{2}\right] + 2\sum_{\vec{k}}\frac{\langle c_{\vec{k}+\vec{q}}^{1\dagger} c_{\vec{k}+\vec{q}}^1\rangle - \langle c_{\vec{k}}^{2\dagger} c_{\vec{k}}^2\rangle}{\lambda_1^{\vec{k}+\vec{q}} - \lambda_2^{\vec{k}}}\cos^2\left[\frac{\theta_{\vec{k}+\vec{q}} + \theta_{\vec{k}} + l\pi}{2}\right], \quad (3)$$

where $(c_{\vec{k}}^{1\dagger}, c_{\vec{k}}^{2\dagger}) = (b_{1\vec{k}}^\dagger, b_{2\vec{k}}^\dagger)\cdot\mathbf{M}$, $\mathbf{M}$ is the diagonalizing matrix for the kinetic matrix $\mathbf{T}$ with $\mathbf{M}_{1,1} = \sin(\theta_{\vec{k}}/2)$, $\mathbf{M}_{2,2} = -\sin(\theta_{\vec{k}}/2)$, and $\mathbf{M}_{1,2} = \cos(\theta_{\vec{k}}/2)$. At 0 K the second term on the right hand side of both χ_2 and χ_3 produces a divergence at $\vec{Q}$ because of the fact that $\lambda_1^{\vec{k}+\vec{Q}} = -\lambda_2^{\vec{k}}$ and that the Fermi energy is zero. Furthermore the ratio of χ_2/χ_3 at 0 K and wavevector $\vec{Q}$ is expected to be 3.

3. Results and discussion

In Fig. 1 we plot $\chi_{2,3}(\vec{Q})$ as a function of temperature (with hopping term t set equal to 0.1 eV) and notice that they diverge as $T \to 0$ with χ_2 diverging faster than χ_3. In Fig. 2 we plot $\chi_{2,3}(q,q)$ as a function of q (with $0 \leq q \leq \pi$) at fixed temperature T = 0.01 K and hopping term t = 0.1 eV and find that they both peak sharply close to $\vec{Q}$ with χ_2 peaking faster. Then based on the fact that the phonon mode goes soft at wavevector $\vec{Q}$ we compute the ground state energy when only either Q_2 mode or Q_3 mode gets excited cooperatively in the system. The order parameters are given by $\langle b_{1j}^\dagger b_{2j} + b_{2j}^\dagger b_{1j}\rangle = c_2\cos(\vec{Q}\cdot\vec{R}_j)$ and $\langle b_{1j}^\dagger b_{1j} - b_{2j}^\dagger b_{2j}\rangle = c_3\cos(\vec{Q}\cdot\vec{R}_j)$ with $-1 \leq c_{2,3} \leq 1$




Figure 1. Plot of $\chi_{2,3}(\pi,\pi)$ as a function of temperature at $t = 0.1\ eV$.




Figure 2. Plot of $\chi_{2,3}(q,q)$ for different values of $(0 \leq q \leq \pi)$ at T = 0.01 K and $t = 0.1\ eV$.

and $\vec{R}_j$ being the position vector. Here it should be pointed out that the order parameter $\langle b_{1j}^\dagger b_{2j} + b_{2j}^\dagger b_{1j}\rangle$ corresponds to the density difference of electrons in the two orbitals $\psi_X \equiv (\psi_{x^2-y^2} - \psi_{3z^2-r^2})/\sqrt{2}$ and $\psi_Y \equiv$

$-(\psi_{x^2-y^2} + \psi_{3z^2-r^2})/\sqrt{2}$ (see Ref. [5]). From the symmetry of the ψ_X and ψ_Y orbitals it follows that at each site the total charge is unity. The unit cell needed to compute the ground state energy consists of two adjacent sites with the Brillouin zone being given by $-\pi \leq (k_x + k_y) \leq \pi$ and $-\pi \leq (k_x - k_y) \leq \pi$. We diagonalize a 4×4 matrix at each momentum and integrate the lowest two eigen energies over the Brillouin zone to obtain the ground state energy. The results of




Figure 3. Dependence on dimensionless polaronic energy $(A^2/\omega_0 t)$ of dimensionless ground state energy per site (E/t) for cooperative Q_2 and Q_3 modes.




Figure 4. Variation of coefficients $c_{2,3}$ of ODW order parameters for Q_2 and Q_3 distortions as a function of the dimensionless polaronic energy $(A^2/\omega_0 t)$.

our calculations are shown in Figs. 3 and 4. From Fig. 3 we see that the ground state energy corresponds to the Q_2 mode with the difference in energy between the Q_2 only state and the Q_3 only state peaking at intermediate values of the dimensionless polaronic energy $(A^2/\omega_0 t)$. For zero values and infinite values of the polaronic energy both modes yield the same energy because zero value implies no phononic coupling effect while infinite value corresponds to localized polarons. Thus for large values of the polaronic energy, the ground state energy is only slightly smaller than the polaronic energy. Furthermore, from Fig. 4 we also see that as the polaronic energy increases the values of $c_{2,3}$ increase and become unity around $A^2/(\omega_0 t) \sim 2$ implying that for the Q_3 (Q_2) mode $\psi_{x^2-y^2}$ (ψ_X) orbital is occupied fully at one site with the $\psi_{3z^2-r^2}$ (ψ_Y) orbital being fully occupied at the adjacent sites.

In conclusion, we have studied orbital ordering for the ground state of the undoped manganite systems. We find that the two-dimensional orbital ordering, in the ferromagnetic planes of the observed A-type antiferromagnetic state, is governed by the wavevector $\vec{Q}$ with Q_2 JT mode being cooperatively excited in the system.

References

[1] Y. Murakami, J. P. Hill, D. Gibbs, M. Blume, I. Koyama, M. Tanaka, H. Kawata, T. Arima, Y. Tokura, K. Hirota, and Y. Endoh, Phys. Rev. Lett. **81**, 582 (1998).

[2] E. O. Wollan and W. C. Koehler, Phys. Rev. **100**, 545 (1955).

[3] A. J. Millis, Phys. Rev. B **53**, 8434 (1996).

[4] T. Hotta, S. Yunoki, M. Mayr, and E. Dagotto, Phys. Rev. B **60**, R15009 (1999).

[5] P. B. Allen and V. Perebeinos, Phys. Rev. B **60**, 10747 (1999).

[6] Z. Popovic and S. Satpathy, Phys. Rev. Lett. **84**, 1603 (2000).

[7] K. I. Kugel and D. I. Khomskii, Sov. Phys. JETP **37**, 725 (1973).

[8] S. Ishihara, J. Inoue, and S. Maekawa, Phys. Rev. B **55**, 8280 (1997).

[9] L. Sheng and D. N. Sheng, Int. J. Mod. Phys. **B 13**, 1397 (1999).

[10] S. Okamoto, S. Ishihara, and S. Maekawa, Phys. Rev. B **65**, 144403 (2002).

[11] S. Yarlagadda, Int. J. Mod. Phys. B **15**, 3529 (2001).