

Comment on "Memory Effects in an Interacting Magnetic Nanoparticle System"

In a recent Letter, Sun et al. [1] study and discuss memory effects in an interacting nanoparticle system with specific temperature and field protocols. The authors claim that the observed memory effects originate from spin-glass dynamics and that the results are consistent with the hierarchical picture of the spin-glass phase. In this comment, we argue their claims premature by demonstrating that all their experimental curves can be reproduced qualitatively using only a simplified model of isolated nanoparticles [2] with a temperature dependent distribution of relaxation times.




FIG. 1: FC susceptibility vs temperature using the same protocols as in Fig. 2 of Sun et al. [1]. The field is cut during the temporary stops of the cooling at  $T = 0.088$  and at  $T = 0.042$  for  $10^{14}$  s. The cooling (and reheating) rate is  $2.4 \times 10^{13}$  s per temperature unit. The inset shows ZFC and FC susceptibility vs temperature.

The  $i$ -th magnetic moment in our model occupies one of two states with energies  $K V_i - H M_s V_i$ , where  $K$  is the anisotropy constant,  $M_s$  the saturation magnetization,  $H$  the applied field and  $V_i$  the volume of the  $i$ -th nanoparticle. The superparamagnetic relaxation time is  $\tau_i = \tau_0 \exp(K V_i / T)$ . The occupation probability of one of the states is  $p_i(t)$ , which is solved by the master equation approach for any temperature and field protocol from a given initial condition [2]. The magnetization of the particle system is evaluated by averaging over the volume distribution  $P(V) = \exp[-\ln(V)^2 / (2\sigma^2)] / (\sqrt{2\sigma^2})$  with  $\sigma = 0.6$ .

Figure 1 shows field-cooled (FC) magnetization vs temperature measured on cooling with temporary stops under zero field and the subsequent reheating. Since the field is cut at  $T_s$  for  $t_s$ ,  $f_{p_i}(t)$  of moments which are active on the present time scale relax to  $1/2$ . Among them, moments of particles fulfilling  $t_s \gg \tau_0 \exp(K V_i / T_s)$  are frozen in certain values when the cooling is restarted. Those frozen states are reactivated when the system is reheated to  $T_s$ , causing a dip in  $\chi$ . The time evolutions of the thermoremanent magnetization (TRM) shown in Fig. 2 can similarly be understood; an energy barrier specifies quite sharply a temperature, below (above) which the moment is blocked (superparamagnetic).

An appropriate protocol to confirm memory effects due to spin-glass dynamics is a zero-field-cooled (ZFC) process with a stop during cooling under zero field [3]. In a spin glass the correlation length of spin-glass order grows during the stop and a memory dip shows up upon reheating, but not in a noninteracting nanoparticle system. This protocol, however, has not been examined in [1].

We have argued that a distribution of (free-)energy barriers is a sufficient origin of the memory effects discussed in [1]. In noninteracting nanoparticle systems the distribution of relaxation times originates only from that of the particle volumes, and is thus extrinsic and static. In spin glasses, on the other hand, it is the consequence of the cooperative nature of spins with randomly frustrated interaction, and is intrinsic and dependent on the age of the system. To conclude, only through the memory effects studied by Sun et al. [1] we cannot draw any conclusion whether a nanoparticle system is a non-interacting superparamagnet or an interacting spin glass.




FIG. 2: TRM vs time using the same protocols as in Figs. 3,4,5 of Sun et al. [1]. The system is cooled to  $T = 0.029$  at the same rate as in Fig. 1 under a field which is cut just before recording TRM. After a time of  $t_1 = 3 \times 10^{12}$  s the temperature is changed. The relaxation at the new temperature is recorded either in  $H = 0$  or  $H = h$  in period of  $t_2 = 3 \times 10^{12}$  s. Then the temperature is shifted back to  $T = 0.029$  and the field is set to zero.

M. S. and P. E. J. acknowledge financial support from the Japan Society for the Promotion of Science.

M. Sasaki,<sup>1</sup> P. E. Jonsson,<sup>1</sup> H. Takayama,<sup>1</sup> and P. Nordblad<sup>2</sup>

<sup>1</sup>ISSP, Univ. of Tokyo, Kashiwa, Chiba 277-8581, Japan

<sup>2</sup>A-lab, Uppsala Univ., Box 534, SE-751 21 Uppsala, Sweden

[1] Y. Sun, M. B. Salamon, K. Gamier, and R. S. Averbach, Phys. Rev. Lett. 91, 167206 (2003).

[2] I. Klik, C.-R. Chang, and J. Lee, J. Appl. Phys. 75, 5487 (1994).

[3] R. Mathieu, P. Jonsson, D. N. H. Nam, and P. Nordblad Phys. Rev. B 63, 092401 (2001).