Light de ection by photonic crystals

Chao-H sien Kuo and Zhen Ye

W ave Phenom ena Laboratory, Departm ent of Physics, National Central University, Chungli, Taiwan 320, Republic of China.

W hen propagating through periodically structured media, i.e. photonic crystals, optical waves will be modulated with the periodicity. As a result, the dispersion of waves will no longer behave as in a free space, and so called frequency band structures appear. Under certain conditions, waves may be prohibited from propagation in certain or all directions, corresponding to partial and com plete bandgaps respectively. Here we report a new fascinating phenom enon associated with the partial gaps, that is, de ection of optical waves. This phenom enon will render novel applications in manipulating light ows.

The band phenom enon was rst investigated for electrons in solids. The well-known Bloch theorem has been proposed and led to successful explanation of som e in portant properties of solids such as conducting, sem i-conducting, and insulating states. Applying these concepts to electrom agnetic waves started and ourished with the sem inalpapers published in 1987¹. Not only all the phenom ena previously observed or discussed for electronic systems are successfully transplanted to classical system s, but m any m ore signic cant and novel ideas, and applications have well gone beyond expectation, and are so far reaching that a fruitful new eld called photonic crystals has come into existence, signiced by the establishment of a comprehensive webpage².

Photonic crystals (PCs) provide a new possibility in designing optoelectronic devices. Up to date, most applications have mainly relied on the existence of complete bandgaps. This includes, for example, cavity laser, optical bers, and optical waveguides³. Here we demonstrate a new property of PCs, which is associated with partial bandgaps, referring to the situation in which waves are prohibited from propagation along certain directions.

We show that partial bandgaps can give rise to a fascinating phenomenon: de ection of optical waves. This phenomenon would allow for better optical steering, bending and beam collimating. It may also help explain some recent mysteries about the negative refraction or left-handed-material (LHM) behavior and the amphoteric refraction revealed by $PC s^{47}$.

The system s considered here are two dimensional photonic crystals made of arrays of parallel dielectric cylinders placed in a uniform medium, which we assume to be air. Such systems are common in both theoretical simulations or experimental measurements of two dimensional PC s^{4,8}. For brevity, we only consider the E-polarized waves, that is, the electric eld is kept parallel to the cylinders. The following parameters are used in the simulation. (1) The dielectric constant of the cylinders is 14, and the cylinders are arranged to form a square lattice. (2) The lattice constant is a and the radius of the cylinders is 0.3a; in the computation, all lengths are scaled by the lattice constant. (3) The unit for frequency is 2 c=a.

The band structure is plotted in Fig. 1, and the qualitative features are similar to that obtained for a square array of alum ina rods in air. A complete band gap is shown between frequencies of 0.22 and 0.28. Just below the complete gap, there is a regime, sandwiched by two horizontal lines, of partial band gap in which waves are not allowed to travel along the X or [10] direction.

We wish to exam ine the properties of the energy ow of the eigenm odes which correspond to the frequency bands shown in Fig.1. Difference is a periodic frequency bands of PC s can be expressed as $E_{\kappa}(x) = e^{i\kappa \cdot x} u_{\kappa}(x)$, where κ is the B bch vector, as the wave vector, and $u_{\kappa}(x)$ is a periodic function with the periodicity of the lattice. When expressing $E_{\kappa}(x)$ as $f_{\kappa}(x) g^{i_{\kappa}(x)}$, the corresponding energy ow is derived as $J_{\kappa}(x) / f_{\kappa}(x) f_{\kappa}(x)$; clearly κ combines the phase from the term $e^{i\kappa \cdot x}$ and the phase from the function $u_{\kappa}(x)$, making the determination of the phase and group velocities in PC s less obvious, or even perhaps not so useful. To explore the characteristics of the partial bandgap, we have computed the eigen- eld $E_{\kappa}(x)$ and also the energy ow of the eigenmodes. The results are shown in Fig.2.

A signi cant discovery from Fig. 2 is that the energy ow of eigenm odes does not always follow the direction of the Bloch vectors. As evidenced by Fig. 2 (b2), the energy tends to ow into the direction of M, i.e the [11] direction, while the Bloch vector points to an angle of 22.5° that lies exactly between X and M. This feature, how ever, cannot be inferred from the eld pattern in (b1), i.e. the main wave front is more or less perpendicular to the direction of the Bloch vector rather than that of the energy ow, im plying that it is not appropriate to determ ine the energy ow purely from the eld pattern. For the other two Bloch vectors along X and M respectively, the net energy ow s and the norm als of the wave fronts follow the directions of the Bloch vectors, as shown by Figs. 2 (a)

and (c). From (a1), (b1) and (c1), we see that the eigenmodes have also periodic structures perpendicular to the direction of the propagation. The feature in (b2) can be explained in the context of partial bandgaps. In Fig. 2 (b), the frequency 0.185 lies within the partial bandgap in the X direction. Since waves are not allowed to propagate along X and the directions perpendicular to X, we may expect from the symmetry consideration that the energy

ow will be tilted towards M for waves whose B loch vectors make an angle to X. Note here that in Fig. 2, the frequency corresponding to the B loch vector along X is outside the partial gap.

The deviation of the energy ow from the direction of the Bloch vector, serving as the wave vector, suggests an intriguing phenomenon, that is, the light de ection. Consider a plane wave propagation in a uniform medium. When it encounters an perpendicular interface of PCs with the normal of the interface being along the direction exactly between X and M, what can be expected to happen? In the conventional thought, the wave would keep going straight, and the wave vectors on both sides of the interface will point to the same direction, as there are no components in the tangent direction. However, according to Fig. 2, the ow of the energy will be de ected into the direction of M. This is a surprising nding. To con m this, we have carried out further simulations. For exam ple, rst, when we chose frequencies that lie outside the partial gap region, the de ection phenom enon disappears.

We have also studied the transm ission properties. In Fig. 3, we plot the transm ission of EM waves across two slabs of photonic crystals with two dimental lattice orientations: one is along the diagonal direction M, and the other is along the direction making an equal angle to the X and M directions. The incidence is normal to the slab interface. In the simulation, we have employed the standard multiple scattering method⁹ to compute the transm itted intensity, which is usually the quantity to be measured in experiments. The frequencies chosen correspond to those in Fig. 2. We have used three types of sources in the simulations: (1) plane waves; (2) collimated waves by guiding the wave propagation through a window before incidence on the slabs; (3) a line source. The results from these three scenarios are similar. Here, we see that when the incidence is along the M direction, the transm ission follows a straight path inside the slab. For the second case in Fig. 3, the transm ission directions for waves to travel, fully in agreem ent with the above light de ection picture and in consistency with the results in Fig. 2. We also note that there is relatively small transm ission along the [1-1] direction; by symmetry, this direction is also a probable passing path for the waves.

The light de ection in the presence of partial bandgaps can be in portant in a number of occasions. First, it may help designing novel optoelectronic devices in controlling optical ows. C om pared to applications based on complete bandgaps, there is no rection loss because the light de ection occurs in the passing bands, allowing for e cient wave transmission. Second, the mechanism of the light de ection discussed here may help understand the recent puzzles about the negative refraction⁴ or LHM behavior⁶ and the amphotenic refraction revealed by PCs⁷. To elaborate, we consider the slab shown in Fig. 3 (b). A ssume that a plane wave is incident on the slab with a tilt angle. We can expect from the above results that as long as the tilt angle is not too large, the energy ow will be de ected tow ards the direction of M, no m atter the incidence is positive or negative. Consequently, an amphotenic refraction may prevail and is conceptually illustrated by Fig. 4.

- 1. Yablonovitch, E. Phys. Rev. Lett. 58, 2059 (1987); John, S. Phys. Rev. Lett. 58, 2486 (1987).
- 2. http://www.pbglink.com.
- 3. Joannopoulos, J., Meade, R., and Winn, J. Photonic Crystals (Princeton University Press, Princeton, NJ, 1995).
- 4. Luo, C., Johnson, S.G., Joannopoulos, J.D., and Pendry, J.B. Phys. Rev. B 65, 201104 (R) (2002).
- 5. Shelby, R.A., Smith, D.R., and Schultz, S. Science 292, 77 (2001).
- 6. Houck, A.A., Brock, J.B., and Chuang, I.L. Phys. Rev. Lett. 90, 137401 (2003).
- 7. Zhang, Y., Fluegel, B., and Mascarenhas, A. Phys. Rev. Lett. 91, 157404 (2003).
- 8. M of all, S.L., Platzm an, P.M., Dalichaouch, R., Sm ith, D.R., and Schultz, S.Phys. Rev. Lett. 67, 2017 (1991).
- 9. Chen, Y.-Y. and Ye, Z. Phys. Rev. Lett. 87, 184301 (2001).
- Correspondence and requests for materials should be addressed to Z.Y. (e-mail: zhen@ shaw.ca).

- Figure 1 The band structure of a square lattice of dielectric cylinders. The lattice constant is a and the radius of the cylinders is 0.3a. M and X denote the [11] and [10] directions respectively. A partial gap is between the two horizontal lines.
- Figure 2 Left panel: the eld pattern of eigenmodes. Right panel: the energy ow of the eigenmodes. The eigenmodes along three directions are considered: (a) K = (0.9 = a; 0), i.e. along X; the corresponding frequency is 0.175; (b) K = (0.9 = a; 0.37 = a), i.e. along an angle of 22.5° exactly between X and M directions; the corresponding frequency is 0.185; (c) K = (0.7 = a; 0.7 = a), i.e. along M; the corresponding frequency is 0.192. The direction of the B bch vectors are denoted by the blue arrows, while the red arrows denote the bcalenergy ow including the direction and the magnitude. The circles refer to the cylinders. Both frequencies in (b) and (c) lie within the partial gap. D ue to the periodicity, we only plot the energy ow within one unit cell. Note that although the features shown by (b) also hold for other B bch vectors for which the corresponding frequencies lie within the partial gap regine, we only plot here for the case of 22.5°
- Figure 3 The in aging elds for slabs of photonic crystal structure. Two lattice orientations are considered: (a) The slab m easures as about 56 10 and the incidence is along the [11] direction; (2) the slab m easures as 50 13 and the incidence is along the direction that m akes an equal angle to the [11] and [10] directions. The m ain lobes in the transm itted intensities are shown. There is a gap along the [10] direction.
- F igu re4 Conceptual illustration of am photeric refraction due to partial bandgaps, or perhaps better term ed as am photeric de ection. D epending on the incident angle, the de ection m ay not exactly follow the direction of [11].

This figure "fig1.jpg" is available in "jpg" format from:

This figure "fig2.jpg" is available in "jpg" format from:

This figure "fig3.jpg" is available in "jpg" format from:

This figure "fig4.jpg" is available in "jpg" format from: