arXiv:cond-mat/0402074v1 [cond-mat.str-el] 3 Feb 2004

^{23}Na NMR evidence for charge order and anomalous magnetism in Na_xCoO_2

I.R. Mukhamedshin,[1,*] H. Alloul,[1,†] G. Collin,[2] and N. Blanchard[1]

[1] *Laboratoire de Physique des Solides, UMR 8502, Université Paris-Sud, 91405 Orsay, France*
[2] *Laboratoire Léon Brillouin, CE Saclay, CEA-CNRS, 91191 Gif-sur-Yvette, France*

We have compared by ^{23}Na NMR and magnetic susceptibility the magnetic properties of oriented powder samples of Na_xCoO_2 compounds. The NMR spectra are found identical for various samples with nominal $0.50 \leq x \leq 0.70$, which establishes that the dominant phase has a single composition $x \approx 0.70$. Three Na sites are identified from their single valued quadrupole effects and magnetic shifts which implies a very definite order of the Na^+ ions and of the Co charges in the CoO_2 planes. The local susceptibility of the magnetic cobalt sites displays a large enhancement below 100 K with respect to the usually found high T Curie-Weiss law. A very distinct much weaker Pauli like magnetism is detected for $x \approx 0.35$, the parent of the superconducting hydrated compound.

PACS numbers: 76.60.-k, 71.27.+a, 75.20.Hr

The discovery of a new family of layered transition metal oxydes, the cobaltites, which display strong electric thermopower [1], metallicity and superconductivity [2] has triggered a large interest. In Na_xCoO_2, the CoO_2 layers have an hexagonal 2D crystal structure with a tetragonal distortion yielding a large crystal field and a low spin configuration for the Co ions. Those can be stabilized in 3^+ or 4^+ charged states which correspond to spin $S = 0$ and $S = \frac{1}{2}$ respectively. The cobalt-oxygen subsystem can be either considered as a Mott-Hubbard CoO_2 insulator doped with x electrons, or as a band insulator $NaCoO_2$ doped with $1 - x$ holes. One expects then more magnetism for low x in contradiction with the data, which exhibit magnetic phases [3, 4] for $x \geq 0.75$. Important questions are therefore raised concerning the interplay of transport properties [5, 6] with the magnetic properties. Whether electrons hop uniformly on all Co sites or local Co^{3+}-Co^{4+} charge segregation [7, 8] occurs for some values of x is a question which requires further investigations [9]. The variety of physical effects which are envisioned [10], depend critically on the actual details of the electronic structure. Although macroscopic magnetic data reveal a diversity of magnetic behaviours, the results might be governed at low T by traces of impurity phases, so that the ground states are still poorly characterized. Although ESR and NMR seem to indicate intrinsic inhomogeneous behaviour in the cobaltites [11], more detailed local hyperfine studies which would allow to isolate the properties of single phases are still lacking.

A significant effort in materials synthesis and characterization allowed us to provide aligned powder samples, as has been often done in cuprates. In this work we use ^{23}Na NMR to study for the first time the local magnetic properties of the CoO_2 planes in pure phases down to 1.3 K. This is permitted by the sizable hyperfine coupling of the ^{23}Na nuclear spin with the magnetic Co sites, yet small enough to ensure that all ^{23}Na spins are detected. The qualitative difference between the parent $x \sim 0.35$ of the superconducting compound and the $x \sim 0.70$ composition will be emphasized. The data will allow us to demonstrate that the charge segregation suggested in Ref. 7 does correspond to a perfectly charge ordered state of the Co ions accompanied by an ordering of the Na ions. The large T variation of the susceptibility of the magnetic cobalt site evidenced here points out that a Fermi liquid is only eventually reached below 1.5 K.

Samples have been synthesized by mixing powders of $NaCO_3$ and Co_3O_4 with nominal Na content $0.5 < x \leq 0.7$. After rapid heating and solid state reaction at 860-900° C, X-ray powder diffraction allowed to measure the lattice constants of the synthesized cobaltite phase. Both X-ray and initial ^{23}Na NMR data on various samples indicated that the dominant synthesized phase does not markedly differ and corresponds to a single composition x_0 plus an excess of cobalt oxides. SQUID magnetometry confirmed that Co_3O_4 was not completely reacted from the occurrence of an anomaly at its Néel temperature of 30 K. The ^{59}Co NMR signal of Co_3O_4 could be detected, as well as the characteristic diffraction peaks ($\theta = 31.28°, 36.86°, 59.34°, 65.22°$) in the X-ray spectra. Systematic X-ray studies versus x evidenced that traces of unreacted Co_3O_4 become undetectable for $x = 0.7$. This indicates that the major phase in all samples synthesized corresponds to $x_0 \approx 0.7$. For all nominal x, the common value of the c axis parameter of the gamma phase unit cell, lies between 10.91 and 10.93 Å, in good agreement with recent data [12]. Rietveld refinement on one $x \approx 0.7$ sample used for the NMR experiment leads to occupancies of 0.24(1) and 0.58(1) respectively for the $(0, 0, \frac{1}{4})$ and $(\frac{2}{3}, \frac{1}{3}, \frac{1}{4})$ Na sites at room T. Reduction of Na content in such a sample has been achieved by a reaction with Bromine and acetonitrile (40N) at room T during four days. The sample appears from X-rays rather free of impurity phases and can be indexed in the usual $P6_3/mmc$ group with cell parameters $a = 2.8076(2)$ Å and $c = 11.2086(4)$ Å corresponding to $x \simeq 0.35$ [12]. After water insertion such a sample displays superconductivity with $T_c = 3.1$ K.

As the room T susceptibility is known to be anisotropic [5], we have aligned the powders mixed with Stycast 1266




FIG. 1: ^{23}Na NMR spectra taken in two field directions in $Na_{0.66}CoO_2$. The fully resolved quadrupole structure for the three Na sites is discussed in the text. The weak extra line ($*$) with small Knight shift represents at most 5-10% of all Na nuclei and might be assigned to defect sites in the ordered Na structure. The inset displays an enlarged view of a slow scan through the central lines for $Na_{0.66}CoO_2$ and $Na_{0.35}CoO_2$ (the intensities are not in scale).

epoxy in a 7 T field, and epoxy was allowed to polymerize in the field. NMR spectra were obtained by pulse NMR spectroscopy: at fixed frequency, we measured the spin echo intensity after two 2 μS radio frequency pulses separated by 100 μS, while the field was increased by steps. A typical ^{23}Na NMR spectrum obtained below 150 K, when Na atomic motion is totally frozen [8], is displayed in Fig.1. Here, the crystal field lifts the degeneracy of the Zeeman level of the ^{23}Na nuclear spin ($I = \frac{3}{2}$). The $-\frac{3}{2} \leftrightarrow -\frac{1}{2}$ and $\frac{1}{2} \leftrightarrow \frac{3}{2}$ transitions split symmetrically of $\Delta\nu$ with respect to the $-\frac{1}{2} \leftrightarrow \frac{1}{2}$ transition, with

$$\Delta\nu = \nu_Q(3\cos^2\theta - 1 + \eta\sin^2\theta\cos 2\varphi)/2 \ ,$$

where θ and φ are the polar coordinates with respect to the external field $H_0 \| z$ of the principal axes X, Y, Z of the electric field gradient (EFG) tensor V_{ij} associated with the local structure. Here $\nu_Q = 3eQV_{ZZ}/(h2I(2I-1))$ is defined by the nuclear quadrupole moment Q and the largest principal axis component of the EFG tensor V_{ZZ}, and $\eta = |(V_{YY} - V_{XX})/V_{ZZ}|$ is the asymmetry parameter. In the typical spectra of Fig.1, for $H_0 \| c$, one can clearly distinguish three pairs of quadrupole transitions which correspond to three Na sites with distinct local environments. In our samples only the c axes of the crystallites are aligned and the a or b axes and therefore φ are at random. The narrow width of the transitions indicate from the above equation that $\theta \approx 0$ and that the largest principal axis of the EFG tensor for the three resolved sites is parallel to the c axis. For $H_0 \perp c$ only one pair of transitions remains narrow which shows that $\eta = 0$ for this site which will be labelled Na1 hereafter. The width of this quadrupole transition allows to estimate the mean deviation $\Delta\theta \approx 5°$ with respect to $\theta = 0$, which demonstrates the high degree of alignment of the sample. The broad quadrupole transitions for $H_0 \perp c$ correspond to two Na sites labelled Na2a and Na2b with slightly distinct EFG tensors and large η values. The full simulation of the spectra allows to deduce $\nu_Q \simeq 1.645(5)$ MHz and $\eta \simeq 0.00(1)$ for Na1, $\nu_Q \simeq 1.72(1)$ MHz and $\nu_Q \simeq 1.86(1)$ MHz, $\eta \simeq 0.82(2)$ and $\eta \simeq 0.87(2)$ respectively for Na2a and Na2b. These quadrupole frequencies were found to decrease at most of 5% from 5 K to 100 K. The intensity ratio between the lines allows us to assign the Na1 NMR to Na at $(0, 0, \frac{1}{4})$ which is vertically aligned with two Co, and Na2a and Na2b to Na at $(\frac{2}{3}, \frac{1}{3}, \frac{1}{4})$ aligned with the center of Co triangles in the neighboring CoO_2 planes.

In the $Na_{0.35}CoO_2$ sample, while ^{59}Co NMR spectra indicated that the sample is as well aligned, the ^{23}Na quadrupolar spectrum could not be resolved in either direction which indicates the occurrence of a large distribution of EFG values. The intensity of the ^{23}Na NMR signal has been also found about 2.0(2) larger than that expected from that of the central transition of $Na_{0.66}CoO_2$, which shows that for some sites the quadrupole effect is so small that satellites merge in the central line.

Simple calculations of the EFG in a point charge model indicate that the local configuration of the neighbouring Na^+ charges gives a large contribution to the EFG at the Na sites for both $x \approx 0.35$ and $x \approx 0.7$. So the distribution of EFG seen for $x \approx 0.35$ proves that the ordering of Na is not perfect, which might be expected, as the low T deintercalation process of Na does not lead to a thermodynamically stable phase. The well defined values of the EFG for $x \approx 0.7$ *a contrario* evidence that the Na atoms are well ordered. Both Na1 and Na2 sites have a threefold c axis symmetry with respect to the CoO_2 plane, which correspond to EFG tensors with axial symmetry around the c axis for the Co and O charges. So the fact that $\eta = 0$ for Na1 proves that the Na ordering keeps a high symmetry as well. On the contrary, the resolution of two slightly different sites with large η for Na2 indicates a lower symmetry for these sites. They could correspond to displaced positions of Na with respect to the center of the Co triangles, as suggested by X-ray refinements [13]. More refined information on the charge order of the Co will be obtained hereafter from the local magnetic data.

In the $x \approx 0.7$ samples the central transitions associated with the three Na sites are not well resolved above 100 K. As the magnetic shift increases drastically at low T they are progressively fully resolved, as seen in the inset of Fig. 1. The reproducibility of these spectra was found excellent even for samples with nominal x as low as 0.5. In Fig. 2 we report the large T variation of the shift of these lines, refereed to the ^{23}Na NMR of NaCl in solution. Before discussing in detail this important information, let us compare first the properties sampled by




FIG. 2: Variation with T of the shifts of the three Na sites. In the inset these shifts are shown to scale perfectly. The shift of ^{23}Na (x4) in $Na_{0.35}CoO_2$ is found practically T independent.

the different sites. The shift of a Na nuclear site β is determined by the magnetic properties of the neighbouring Co atoms through transferred hyperfine constants $A^{\alpha}_{\beta,i}$

$$K^{\alpha}_{\beta} = K^{\alpha}_{\beta,orb} + \sum_i A^{\alpha}_{\beta,i}\,\chi^{\alpha}_{s,i}(T)\ .$$

Here α corresponds to the field orientation with respect to the crystal axes, and $K^{\alpha}_{\beta,orb}$ a usually T independent orbital contribution which will be shown to be small hereafter. The spin contribution to the shift is single valued in a uniform system, but here we label $\chi^{\alpha}_{s,i}(T)$ of the Co sites with their index i, as ^{59}Co NMR [7, 14] indicates the occurence of charge segregation. In the inset of Fig. 2 the shifts of the Na lines are shown to scale linearly with each other. This does not mean that all Co sites have the same $\chi^{\alpha}_{s,i}(T)$, as some might display a T independent χ, e.g. for a Co^{3+} state. As the linear fits extrapolate to zero within experimental accuracy, the T independent contributions either from Co^{3+} sites or from $K^{\alpha}_{\beta,orb}$ are small and do not differ markedly for the three Na sites. The linear fits give $K^c_2 = 0.80(2)K^c_1$, $K^{ab}_1 = 1.10(2)K^c_1$, $K^{ab}_{2a} = 1.03(2)K^c_2$, and $K^{ab}_{2b} = 0.97(2)K^c_2$. While Na1 has a slightly anisotropic shift, the Na2a and Na2b shifts are more isotropic, but overall the local fields detected by the three sites are quite similar, which appears at first sight surprising as they couple to a different number of Co sites, with different $A^{\alpha}_{\beta,i}$.

An examination of the local structure done in Fig. 3 indicates that $A^{\alpha}_{\beta,i}$ occur through a sequence of Na-O-Co orbitals, e.g. Na1 couples to its first n.n. Co through 3O and to its second n.n. through one O. One could assume that these paths are independent of the Na-O-Co angle, so that $A^{\alpha}_{\beta,i}$ would be multiples of A^{α}_{O}, the hyperfine coupling through a single O. In absence of charge segregation on the Co orbitals one would obtain $K^{\alpha}_1 = K^{\alpha}_2 = 18A^{\alpha}_O\chi^{\alpha}_s(T)$. This simplistic count would explain then the fact that the K^{α}_{β} do not differ markedly and the ^{23}Na data are compatible with a homogeneous charged state. However, we have detected the ^{59}Co NMR signal of Co^{3+} in our own samples [14], as done in Ref. 7. In the presence of a distribution of Co^{3+} and Co^{4+}, only the latter would have a sizable $\chi^{\alpha}_{s,i}$, so that for each Na nuclear spin the numerical coefficient 18 should be reduced to a smaller integer n which depends on the number of Co^{4+} in its local environment. For $x \approx 0.7$, a random distribution of $\approx 0.3Co^{4+}$ would result in a splitting of each Na site NMR in a series of lines with shifts proportional to the local n value. So, the absence of magnetic splitting of the ^{23} Na central lines at low T for both sites indicates *that the environment of the Na sites is perfectly ordered* and corresponds then to a single value of n for each site. For example the natural ordering expected for $x = 2/3$ shown in Fig. 3, in which Co on the honeycomb lattice are Co^{3+} and those on the $\sqrt{3}*\sqrt{3}$ triangular lattice are Co^{4+} yields $n = 6$ for both Na1 and Na2 site, which would not be differentiated magnetically.

Although the above analysis is oversimplified, the conclusions drawn are even stronger when we take into account the angular dependence of the hyperfine couplings. Four values $A_1 \approx 3A_O, A_2 \approx A_3 \approx A_O, A_4 \approx 2A_O$ have to be considered (Fig. 3). From the angles in the structure we anticipate $A_1 \neq 3A_2$, so that the shift of Na1 would depend of the charge of the n.n. Co ions at the vertical of the Na. The occurence of a single Na1 line would then imply that a single configuration of Fig. 3 occurs, in which the n.n. is either Co^{3+} or Co^{4+}. This would even imply that the charge configurations in the two neighboring CoO_2 layers are correlated as Na1 couples to two layers. The small extra Na line which is nearly unshifted could be due to defect Na sites which essentially would




FIG. 3: Model representing a Co plane with the usually assumed Co^{3+}-Co^{4+} charge segregation [9] for x=0.66. This model of ordered state is used here to illustrate that the unicity of the NMR shift of the Na1 and Na2 sites imply a perfect order of the different cobalts in plane. The oxygens represented here are those in the layer between the Co and Na planes. Three representative Na sites are shown together with hyperfine coupling paths to their neighbouring Co.




FIG. 4: The inverse of the mean shift of the three Na lines is plotted versus T for two samples with different nominal concentrations of Na. The large low T enhancement of the susceptibility is evidenced by the θ values obtained for Curie-Weiss fits taken on either side of 100K. The inset shows that a saturation of susceptibility occurs below 3K, while the linewidth displays no low T anomaly.

have Co^{3+} neighbours. Let us recall that the occurence of a single EFG for Na1 was an independent proof that the ionic configuration including that of Na^+ itself is well defined around this site. On the contrary with the ordering suggested in Fig.3 the Na2 site is unique and assuming $A_4 \neq 2A_3$ would only change the effective hyperfine field for this site. The occurence of two slightly different Na2 signals could correspond to a an increase of unit cell with a perfectly commensurate CDW order.

As the shifts for all sites display the same T variation, the first moment (center of gravity) of the NMR spectrum $K = A\chi_s(T)$ allows to follow $\chi_s(T)$ beyond $T \approx 100$ K, where the lines merge together (Fig. 4). Both our SQUID data for $\chi_s(T)$ and ^{23}Na NMR confirm the variation usually found for $T > 100K$, that is $\chi_s = C/(T-\theta)$, with $\theta \approx -90$ K, and $K^{\alpha}_{orb} \simeq 0$. This allows us to deduce an effective hyperfine field of $H_{hf} = Ag\mu_B N_a = 14.9\ kG/\mu_B$. For $T < 100$ K the data for K^{-1} in fig. 4 lie below the high T Curie-Weiss law, which corresponds to an increase of χ_s. This upturn of χ_s at low T apparently tends to saturate below 3K, as can be seen in the inset of Fig. 4. Such a behaviour detected by an NMR local probe is intrinsic to the physics of the cobaltite planes. Let us point out that at the same time no anomaly is found in the linewidth nor in the signal intensity, which indicates that *no magnetic transition occurs down to 1.5 K.*

In the superconducting compound the intercalated water should reduce Na-Co coupling. However in our dry sample with $x \approx 0.35$ the small change of c axis withr espect to $x \approx 0.7$ should not change markedly the hyperfine couplings. The small T independent ^{23}Na shift measured reveals then a weak Pauli like magnetism (Fig. 2). As this doping corresponds to the overdoped case of cuprates it is not so surprising to find a situation in which the correlations are not prominent.

On the contrary, the metallic state for $x \approx 0.7$ displays a magnetism which resembles at high T that of local moments with large AF interactions, and at low T that of Heavy Fermions with a Kondo temperature $\lesssim$10 K. The data leads us to anticipate that a Fermi liquid behaviour would only be reached below 1.5 K. Comparison of χ_s at the lowest T with the specific heat C/T measured in comparable samples [6] gives a large value for the Wilson ratio $R = (T\chi_s/C)(\pi^2 k_B^2/3\mu_B^2) = 7.8$, which reveals that a simple effective mass enhancement as obtained in Heavy Fermion compounds does not describe the anomalous magnetic properties of this correlated electron system. We anticipate that they result from the quasi perfect charge order which we have evidenced here for these single phase $x \approx 0.7$ samples, both from magnetic and EFG measurements. The ordering of Co^{3+} charges should remove electrons from the conduction channels, and yield a system which is nearer from a Mott transition than the $x \approx 0.35$ sample. In the simple usually proposed model in Fig. 3, if conductivity is driven by the motion of holes on the triangular lattice of Co^{4+}, it would correspond indeed to a half filled state, and frustration would play a role in the magnetic properties. Our results demonstrate that the interplay of charge ordering, magnetism and metallicity is extremely rich and is certainly at the origin of the diverse magnetic properties found for $x \geq 0.7$. The present work recalls the power of NMR techniques to address problems of local order and initiates an approach in which both EFG's and hyperfine couplings can be combined to disentangle a complicated situation. Although we have illustrated this approach with the classical model for Co^{3+}-Co^{4+} charge order, the interplay of Co and Na ordering prevents us to ensure its validity solely from the ^{23}Na NMR data. We anticipate that ^{59}Co NMR data and numerical calculations of the EFG and hyperfine couplings will allow us in a near future to determine the exact type of local order occuring around the various sites. We should like to acknowledge stimulating discussions and help in experiments from J. Bobroff, D. Bono and P. Mendels.

* Permanent address: Physics Department, Kazan State University, 420008 Kazan, Russia
† Electronic address: alloul@lps.u-psud.fr

[1] I. Terasaki, Y. Sasago, and K. Uchinokura, Phys. Rev. B **56**, R12685 (1997).
[2] K. Takada *et al.*, Nature **422**, 53 (2003).
[3] T. Motohashi *et al.*, Phys. Rev. B **67**, 64406 (2003).
[4] J. Sugiyama *et al.*, cond-mat/0310516.
[5] Y. Wang, N. S. Rogado, R. J. Cava, and N. P. Ong, Nature **423**, 425 (2003).

[6] M. Brühwiller, B. Batlogg, S. M. Kazakov, and J. Karpinski, cond-mat/0309311.
[7] R. Ray, A. Ghoshray, K. Ghoshray, and S. Nakamura, Phys. Rev. B **59**, 9454 (1999).
[8] J.L. Gavilano *et al.*, cond-mat/0308383.
[9] O.I. Motrunich and P.A. Lee, cond-mat/0310387.
[10] G. Baskaran, cond-mat/0303649; 0310241.
[11] P. Caretta *et al.*, cond-mat/0312284.
[12] M.L. Foo *et al*, cond-mat / 0312174.
[13] J.D. Jorgensen *et al.*, Phys. Rev. B **68**, 214517 (2003).
[14] I.R. Mukhamedshin, H. Alloul *et al.* in preparation.